CNBM 中复神鹰

TECHNICAL DATA SHEET

ZHONGFU SHENYING CARBON FIBER

SYT65 12K

TECHNICAL DATA SHEET

SYT65-12K	Metric		English		Test Method	Note
Tensile Strength	6370	MPa	923	Ksi	GB/T 3362	Inspection standards can be implemented according to customer requirements
Elastic Modulus	294	GPa	42.6	Msi	GB/T 3362	
Elongation at Break	2.1	%	2.1	%	GB/T 3362	
Density	1.79	g/cm³	0.064	lbs/in³	GB/T 30019	
Linear Density	450	g/km	1047	ft/lbs	GB/T 3362	
Sizing Type	Epoxy					
Twist	Never twisted					


APPLICATION FIELD

The SYT65-12K carbon fibers applications involve aerospace, leisure sports, pressure vessels and other fields.

PACKAGING

The table below summarizes the standard packaging;
other bobbin sizes can be supplied to satisfy special needs.

Filament Count	Bobbin (Net weight kg)	Bobbin Size(mm)					Spools Per case	Case (Net weight kg)
		a	b	c	d	e		
12K	2	76	82	280	120	250	12	24
Box size： 565×420×305mm								



STORAGE

The product should be stored in a dry, cool and ventilated warehouse, away from fire and heat sources, moisture-proof, and the stacking layer should not exceed the stacking layer limit indicated on the packaging. Under the correct storage conditions, the shelf life of the product is 2 years. After the expiration date, it can continue to be used after passing the inspection.

Notice: The values in the table are for reference only, not guaranteed ones, technical parameters and packaging specifications are subject to change without prior notice, please consult our company for details.

TDS Rev.2025-3: Updated February 7, 2025