Brand name		**Tenax®**	**Tenax®**
Production site		**J**	**J/E**
Product designation		**UTS50 F13**	**UTS50 F24**
		12K 800tex	**24K 1600tex DCP**
Sizing properties		F13	F24
Number of filaments		12,000	24,000
Nominal linear density [1]	[tex]	800	1,630
Twist	[t/m]	0	0
Running length per kg	[m/kg]	1,250	613
Package weight, net	[kg]	2 / 4 / 6	6 / 8

1) without sizing

Characteristics (typical values)

Filament diameter	[µm]	7.0	7.0
Density	[g/cm^3]	1.78	1.78
Tensile strength	[MPa]	5,100	5,100
Tensile modulus	[GPa]	245	245
Elongation at break	[%]	2.1	2.1

Fiber family UTS

UTS is an “Ultra High Tenacity” (UT) fiber for specific requirements on high tensile strength and increased elongation at break.

F13: Type with ca. 1.0 % sizing based on polyurethane
F24: Type with ca. 2.0 % sizing based on polyurethane

D: Fixed Wide Band
CP: Center Pull (tube removable)

Please contact our sales team any time for choosing the right type. The stated numbers are typical values. For design purposes please request fiber specification.

Please note the application (aerospace or industry & sports) on your order.

The export or transfer of carbon fibers can be subject to authorization, depending on end-use and final destination.