Brand name		**Tenax®**	**Tenax®**	**Tenax®**	**Tenax®**
Production site		**J**	**J**	**E**	**E**
Product designation		**HTS40 E13 3K 200tex**	**HTS40 E13 6K 400tex**	**HTS40 F13 12K 800tex**	**HTS40 F13 24K 1600tex**
Fiber family & tensile properties		HTS40	HTS40	HTS40	HTS40
Sizing properties		E13	E13	F13	F13
Number of filaments		3K	6K	12K	24K
Nominal linear density*	[tex]	200	400	800	1600
Twist	[t/m]	0	0	0/10Z	0/5Z
Running length per kg	[m/kg]	5,000	2,500	1,250	625
Package weight, net	[kg]	1 / 2	1 / 2	2 / 4 / 6 / 8	4 / 6 / 8

*without sizing

Characteristics (typical values)

Filament diameter	[µm]	7.0	7.0	7.0	7.0
Density	[g/cm³]	1.77	1.77	1.77	1.77
Tensile strength	[MPa]	4,400	4,400	4,400	4,400
Tensile modulus	[GPa]	240	240	240	240
Elongation at break	[%]	1.8	1.8	1.8	1.8

Sizing properties for fiber family HTS

HTS is a classic Tenax® high performance carbon fiber. The high tenacity (HT) fibers provide excellent and well-balanced mechanical laminate properties.

E13: Type with ca. 1.3 % sizing based on epoxy resin

F13: Type with ca. 1.0% sizing based on polyurethane

- Please contact our sales team any time for choosing the right type. The stated numbers are typical values. For design purposes please request fiber specification.
- Please note the application (aerospace or industry & sports) on your order.
- The export or transfer of carbon fibers can be subject to authorization, depending on end-use and final destination