Computational Materials Science 136 (2017) S1–S828

Contents lists available at ScienceDirect

Computational Materials Science

www.elsevier.com/locate/commatsci

The AFLOW Library of Crystallographic Prototypes: Part 1

Michael J. Mehl[a], David Hicks[b,c], Cormac Toher[b,c], Ohad Levy[b,c,d], Robert M. Hanson[e], Gus Hart[f], Stefano Curtarolo[b,g]

[a] Center for Materials Physics and Technology, Code 6390, U.S. Naval Research Laboratory, Washington DC 20375
[b] Center for Materials Genomics, Duke University, Durham, NC 27708, USA
[c] Department of Mechanical Engineering and Materials Science, Duke University, Durham NC 27708
[d] Department of Physics, NRCN, P.O. Box 9001, Beer-Sheva 84190, Israel
[e] Department of Chemistry, St. Olaf College, Northfield, Minnesota 55057
[f] Department of Physics and Astronomy, Brigham Young University, Provo UT 84602
[g] Materials Science, Electrical Engineering, Physics and Chemistry, Duke University, Durham, North Carolina 27708

Available online 22 May 2017

Abstract

An easily available resource of common crystal structures is essential for researchers, teachers, and students. For many years this was provided by the U.S. Naval Research Laboratory's *Crystal Lattice Structures* web page, which contained nearly 300 crystal structures, including a majority of those which were given *Strukturbericht* designations. This article presents the updated version of the database, now including 288 standardized structures in 92 space groups. Similar to what was available on the web page before, we present a complete description of each structure, including the formulas for the primitive vectors, all of the basis vectors, and the AFLOW commands to generate the standardized cells. We also present a brief discussion of crystal systems, space groups, primitive and conventional lattices, Wyckoff positions, Pearson symbols and *Strukturbericht* designations. The web version of this database is located at http://aflow.org/CrystalDatabase.

Keywords: Crystal Structure, Space Groups, Wyckoff Positions, Lattice Vectors, Basis Vectors, Database

Table of Contents

1. Introduction S6
2. Periodic Three-Dimensional Systems S7
3. Crystal Systems, Lattices, Space Groups and Standard Lattice Vectors S9
4. The Triclinic Crystal System S10
   4.1. Lattice 1: Triclinic S10
5. The Monoclinic Crystal System S11
   5.1. Lattice 2: Simple Monoclinic S11
   5.2. Lattice 3: Base-Centered Monoclinic S11
6. The Orthorhombic Crystal System S12
   6.1. Lattice 4: Simple Orthorhombic S12
   6.2. Lattice 5: Base-Centered Orthorhombic S12
   6.3. Lattice 6: Body-Centered Orthorhombic S13
   6.4. Lattice 7: Face-Centered Orthorhombic S13
7. The Tetragonal Crystal System S13
   7.1. Lattice 8: Simple Tetragonal S13
   7.2. Lattice 9: Body-Centered Tetragonal S14
8. The Trigonal Crystal System S14
   8.1. Lattice 10: Hexagonal S15
   8.2. Lattice 11: Rhombohedral S15

Email addresses: mmehl@usna.edu (Michael J. Mehl), stefano@duke.edu (Stefano Curtarolo)

http://dx.doi.org/10.1016/j.commatsci.2017.01.017
0927-0256/© 2017 Elsevier B.V. All rights reserved.

9. The Hexagonal Crystal System S16
10. The Cubic Crystal System S16
10.1. Lattice 12: Simple Cubic S16
10.2. Lattice 13: Face-Centered Cubic S17
10.3. Lattice 14: Body-Centered Cubic S17
11. Locating the atoms in the unit cell S17
12. Description of a Database Entry S18
12.1. The Database S19
12.2. Visualization S20
12.3. The Crystallographic Information File S20
12.4. The POSCAR File S21
12.5. QUANTUM ESPRESSO, ABINIT, and FHI-AIMS Formats S22
13. Conclusion S22
14. Acknowledgments S22
15. References S22

Prototypes

P1 (1) .....
1. FeS_2: AB2_aP12_1_4a_8a S25
2. $AsKSe_2$: ABC2_aP16_1_4a_4a_8a S27
P$\bar{1}$ (2) .....
1. P_2I_4: A2B_aP6_2_2i_i S29
2. Cf: A_aP4_2_aci S31
P2 (3) .....
1. SiO_2: A2B_mP12_3_bc3e_2e S33
P2_1 (4) .....
1. High-Pressure Te: A_mP4_4_2a S35
C2 (5) .....
1. Po: A_mC12_5_3c S37
Cm (8) .....
1. Monoclinic PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_mC10_8_ab_a_a S39
Cc (9) .....
1. Monoclinic Low Tridymite: A2B_mC144_9_24a_12a S41
P2_1/m (11) .....
1. NiTi: AB_mP4_11_e_e S46
2. $KClO_3$: ABC3_mP10_11_e_e_ef S48
3. α-Pu: A_mP16_11_8e S50
C2/m (12) .....
1. Calaverite: AB2_mC6_12_a_i S52
2. β-Pu: A_mC34_12_ah3i2j S54
3. $AlCl_3$: AB3_mC16_12_g_ij S56
4. Au_5Mn_2: A5B2_mC14_12_a2i_i S58
5. α-O: A_mC4_12_i S60
P2/c (13) .....
1. Sylvanite: ABC4_mP12_13_e_a_2g S61
2. Monoclinic Phosphorus: A_mP84_13_21g S63
P2_1/c (14) .....
1. Baddeleyite: A2B_mP12_14_2e_e S68
2. β-Se: A_mP32_14_8e S70
3. Se: A_mP64_14_16e S73
C2/c (15) .....
1. B_2Pd_5: A2B5_mC28_15_f_e2f S78
2. Tenorite: AB_mC8_15_c_e S80
3. Coesite: A2B_mC48_15_ae3f_2f S82
4. Esseneite: ABC6D2_mC40_15_e_e_3f_f S84
P222 (16) .....
1. $AlPS_4$: ABC4_oP12_16_ag_cd_2u S86
P2_12_12 (18) .....
1. BaS_3: AB3_oP16_18_ab_3c S88
P$2_12_12_1$ (19) .....
1. Naumannite: A2B_oP12_19_2a_a S90
C222$_1$ (20) .....
1. Orthorhombic Tridymite: A2B_oC24_20_abc_c S92
Pmm2 (25) .....
1. High-Pressure CdTe: AB_oP2_25_b_a S94
Pma2 (28) .....
1. Krennerite: AB2_oP24_28_acd_2c3d S96
Pmn2$_1$ (31) .....
1. Enargite: AB3C4_oP16_31_a_ab_2ab S98
Pna2$_1$ (33) .....
1. Modderite: AB_oP8_33_a_a S100
2. AsK_3S_4: AB3C4_oP32_33_a_3a_4a S102
Cmc2$_1$ (36) .....
1. $HgBr_2$: A2B_oC12_36_2a_a S105
Amm2 (38) .....
1. C_2CeNi: A2BC_oC8_38_e_a_b S107
2. Au_2V: A2B_oC12_38_de_ab S109
Aba2 (41) .....
1. $PtSn_4$: AB4_oC20_41_a_2b S111
2. $PdSn_2$: AB2_oC24_41_2a_2b S113
Fdd2 (43) .....
1. GeS_2: AB2_oF72_43_ab_3b S115
Imm2 (44) .....
1. High-pressure GaAs: AB_oI4_44_a_b S118
Pmmm (47) .....
1. 1212C [$YBa_2Cu_3O_{7-x}$]: A2B3C7D_oP13_47_t_aq_eqrs_h S120
Pmma (51) .....
1. β'-AuCd: AB_oP4_51_e_f S122
Pccn (56) .....
1. Sb_2O_3: A3B2_oP20_56_ce_e S124
Pbcm (57) .....
1. KCNS: ABCD_oP16_57_d_c_d_d S126
2. TlF-II: AB_oP8_57_d_d S128
Pnnm (58) .....
1. Hydrophilite*: AB2_oP6_58_a_g S130
2. η-Fe_2C*: AB2_oP6_58_a_g S132
3. Marcasite*: AB2_oP6_58_a_g S134
Pmmn (59) .....
1. Vulcanite: AB_oP4_59_a_b S136

*Hydrophilite, η-Fe_2C, and marcasite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

2. CNCl: ABC_oP6_59_a_a_a S138
3. β-$TiCu_3$: A3B_oP8_59_bf_a S140

Pbca (61) .....
1. CdSb: AB_oP16_61_c_c S142
2. Brookite: A2B_oP24_61_2c_c S144

Pnma (62) .....
1. Stibnite: A3B2_oP20_62_3c_2c S146
2. $CaTiO_3$ Pnma Perovskite: AB3C_oP20_62_c_cd_a S148
3. MgB_4: A4B_oP20_62_2cd_c S150
4. Chalcostibite: AB2C_oP16_62_c_2c_c S152
5. Co_2Si[†]: A2B_oP12_62_2c_c S154
6. $HgCl_2$[†]: A2B_oP12_62_2c_c S156
7. Cotunnite[†]: A2B_oP12_62_2c_c S158
8. GeS[‡]: AB_oP8_62_c_c S160
9. MnP[‡]: AB_oP8_62_c_c S162
10. Cementite: AB3_oP16_62_c_cd S164
11. C_3Cr_7: A3B7_oP40_62_cd_3c2d S166
12. α-Np: A_oP8_62_2c S169
13. FeB[‡]: AB_oP8_62_c_c S171
14. SnS[‡]: AB_oP8_62_c_c S173

Cmcm (63) .....
1. $SrCuO_2$: AB2C_oC16_63_c_2c_c S175
2. $ZrSi_2$: A2B_oC12_63_2c_c S177
3. CrB: AB_oC8_63_c_c S179
4. α-U: A_oC4_63_c S181

Cmca (64) .....
1. α-Ga[§]: A_oC8_64_f S183
2. MgB_2C_2: A2B2C_oC80_64_efg_efg_df S185
3. Black Phosphorus[§]: A_oC8_64_f S188
4. Molecular Iodine[§]: A_oC8_64_f S190

Cmmm (65) .....
1. α-IrV: AB_oC8_65_j_g S192
2. Ga_3Pt_5: A3B5_oC16_65_ah_bej S194
3. Predicted $CdPt_3$: AB3_oC8_65_a_bf S196

Fmmm (69) .....
1. TlF: AB_oF8_69_a_b S198

Fddd (70) .....
1. γ-Pu: A_oF8_70_a S200
2. $TiSi_2$: A2B_oF24_70_e_a S202
3. α-S: A_oF128_70_4h S204

Immm (71) .....
1. $ReSi_2$: AB2_oI6_71_a_i S207
2. $MoPt_2$: AB2_oI6_71_a_g S208

Ibam (72) .....
1. SiS_2: A2B_oI12_72_j_a S210

I$\bar{4}$ (82) .....
1. BPO_4: AB4C_tI12_82_c_g_a S212
2. $CdAl_2S_4$: A2BC4_tI14_82_bc_a_g S214

$P4_2/m$ (84) .....
1. PdS: AB_tP16_84_cej_k S216

I4/m (87) .....
1. Ti_5Te_4: A4B5_tI18_87_h_ah S218
2. Ni_4Mo: AB4_tI10_87_a_h S220

$P4_12_12$ (92) .....
1. α-Cristobalite: A2B_tP12_92_b_a S222

$P4_32_12$ (96) .....
1. Keatite: A2B_tP36_96_3b_ab S224
2. "ST12" of Si: A_tP12_96_ab S227

P4mm (99) .....
1. Tetragonal PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_tP5_99_bc_a_b S229

P$\bar{4}2_1$m (113) .....
1. BaS_3: AB3_tP8_113_a_ce S231

I$\bar{4}$2m (121) .....
1. Stannite: A2BC4D_tI16_121_d_a_i_b S233

I$\bar{4}$2d (122) .....
1. Chalcopyrite: ABC2_tI16_122_a_b_d S235

P4/mmm (123) .....
1. $HoCoGa_5$: AB5C_tP7_123_b_ci_a S237
2. $CuTi_3$: AB3_tP4_123_a_ce S239
3. CuAu: AB_tP2_123_a_d S241
4. $CaCuO_2$: ABC2_tP4_123_d_a_f S243

P4/mbm (127) .....
1. Si_2U_3: A2B3_tP10_127_g_ah S245

P4/nmm (129) .....
1. AsCuSiZr: ABCD_tP8_129_c_b_a_c S247
2. β-Np: A_tP4_129_ac S249
3. Matlockite: ABC_tP6_129_c_a_c S251
4. Cu_2Sb: A2B_tP6_129_ac_c S253
5. PbO: AB_tP4_129_a_c S255
6. γ-CuTi: AB_tP4_129_c_c S257

$P4_2/mmc$ (131) .....
1. PtS: AB_tP4_131_c_e S259

$P4_2/nnm$ (134) .....
1. T-50 B: A_tP50_134_b2m2n S261

$P4_2/mnm$ (136) .....
1. β-U: A_tP30_136_bf2ij S264
2. β-BeO: AB_tP8_136_g_f S267
3. Rutile: A2B_tP6_136_f_a S269
4. σ-CrFe: sigma_tP30_136_bf2ij S271
5. γ-N: A_tP4_136_f S274

$P4_2/ncm$ (138) .....
1. Cl: A_tP16_138_j S276

I4/mmm (139) .....
1. Al_3Zr: A3B_tI16_139_cde_e S278
2. Hypothetical BCT5 Si: A_tI4_139_e S280
3. 0201 [$(La,Ba)_2CuO_4$]: AB2C4_tI14_139_a_e_ce . S282

[†] Co_2Si, $HgCl_2$, and cotunnite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡] GeS, MnP, FeB, and SnS have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[§] α-Ga, black phosphorus, and molecular iodine have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

4. $Mn_{12}Th$: A12B_tI26_139_fij_a S284
5. In[¶]: A_tI2_139_a S286
6. Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h S288
7. Al_3Ti: A3B_tI8_139_bd_a S290
8. $MoSi_2$: AB2_tI6_139_a_e S292
9. V_4Zn_5: A4B5_tI18_139_i_ah S294
10. Al_4Ba: A4B_tI10_139_de_a S296
11. Pt_8Ti: A8B_tI18_139_hi_a S298
12. ThH_2: A2B_tI6_139_d_a S300
13. α-Pa[¶]: A_tI2_139_a S302

I4/mcm (140) .....
1. Khatyrkite: A2B_tI12_140_h_a S304
2. SiU_3: AB3_tI16_140_b_ah S306
3. SeTl: AB_tI16_140_ab_h S308

$I4_1$/amd (141) .....
1. Zircon: A4BC_tI24_141_h_b_a S310
2. β-Sn: A_tI4_141_a S312
3. Hausmannite: A3B4_tI28_141_ad_h S314
4. Anatase: A2B_tI12_141_e_a S316
5. MoB: AB_tI16_141_e_e S318
6. Ga_2Hf: A2B_tI24_141_2e_e S320
7. NbP: AB_tI8_141_a_b S322
8. β-In_2S_3: A2B3_tI80_141_ceh_3h S324

$I4_1$/acd (142) .....
1. $PPrS_4$: ABC4_tI96_142_e_ab_2g S326

$P\bar{3}$ (147) .....
1. ζ-AgZn: A2B_hP9_147_g_ad S329

$R\bar{3}$ (148) .....
1. Solid Cubane: AB_hR16_148_cf_cf S331
2. BiI_3: AB3_hR8_148_c_f S333
3. PdAl: AB_hR26_148_b2f_a2f S335
4. Ilmenite: AB3C_hR10_148_c_f_c S338

P321 (150) .....
1. Original Fe_2P: A2B_hP9_150_ef_bd S340

$P3_112$ (151) .....
1. $CrCl_3$: A3B_hP24_151_3c_2a S342

$P3_121$ (152) .....
1. α-Quartz: A2B_hP9_152_c_a S345
2. γ-Se: A_hP3_152_a S347

$P3_221$ (154) .....
1. Cinnabar: AB_hP6_154_a_b S349

R32 (155) .....
1. AlF_3 : AB3_hR8_155_c_de S351
2. Hazelwoodite : A3B2_hR5_155_e_c S353

R3m (160) .....
1. Millerite: AB_hR6_160_b_b S355
2. Moissanite 9R: AB_hR6_160_3a_3a S357

R3c (161) .....
1. Ferroelectric $LiNbO_3$: ABC3_hR10_161_a_a_b S359

$P\bar{3}1m$ (162) .....
1. β-V_2N: AB2_hP9_162_ad_k S361

$P\bar{3}1c$ (163) .....
1. $KAg(CN)_2$: AB2CD2_hP36_163_h_i_bf_i S363

$P\bar{3}m1$ (164) .....
1. Al_3Ni_2: A3B2_hP5_164_ad_d S366
2. ω Phase: AB2_hP3_164_a_d S368

$P\bar{3}c1$ (165) .....
1. H_3Ho: A3B_hP24_165_adg_f S370

$R\bar{3}m$ (166) .....
1. CuPt: AB_hR2_166_a_b S373
2. α-As[‖]: A_hR2_166_c S375
3. β-Po[**]: A_hR1_166_a S377
4. Fe_7W_6 μ-phase: A7B6_hR13_166_ah_3c S379
5. α-Sm: A_hR3_166_ac S381
6. Bi_2Te_3: A2B3_hR5_166_c_ac S383
7. α-Hg[**]: A_hR1_166_a S385
8. Mo_2B_5: A5B2_hR7_166_a2c_c S387
9. Rhombohedral Graphite[‖]: A_hR2_166_c S389
10. α-B: A_hR12_166_2h S391
11. Caswellsilverite: ABC2_hR4_166_a_b_c S393
12. β-O[‖]: A_hR2_166_c S395
13. β-B: A_hR105_166_bc9h4i S397
14. CaC_6: A6B_hR7_166_g_a S404

$R\bar{3}c$ (167) .....
1. Paraelectric $LiNbO_3$[††]: ABC3_hR10_167_a_b_e S406
2. Calcite[††]: ABC3_hR10_167_a_b_e S408
3. Corundum: A2B3_hR10_167_c_e S410

$P6_222$ (180) .....
1. Mg_2Ni: A2B_hP18_180_fi_bd S412
2. $CrSi_2$: AB2_hP9_180_d_j S414
3. β-Quartz: A2B_hP9_180_j_c S416

$P6_322$ (182) .....
1. Bainite: AB3_hP8_182_c_g S418

$P6_3mc$ (186) .....
1. Buckled Graphite: A_hP4_186_ab S420
2. Moissanite-4H SiC: AB_hP8_186_ab_ab S422
3. Wurtzite: AB_hP4_186_b_b S424
4. Moissanite-6H SiC: AB_hP12_186_a2b_a2b S426
5. Al_5C_3N: A5B3C_hP18_186_2a3b_2ab_b S428
6. Original BN: AB_hP4_186_b_a S430

$P\bar{6}m2$ (187) .....
1. BaPtSb: ABC_hP3_187_a_d_f S432

[¶] In and α-Pa have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‖] α-As, rhombohedral graphite, and β-O have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[**] β-Po and α-Hg have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[††] Paraelectric $LiNbO_3$ and calcite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

2. Tungsten Carbide: AB_hP2_187_d_a S434

P$\bar{6}$2m (189) .....

1. Revised Fe_2P: A2B_hP9_189_fg_bc S436

P6/mmm (191) .....

1. AlB_4Mg: AB4C_hP6_191_a_h_b S438
2. $CaCu_5$: AB5_hP6_191_a_cg S440
3. Simple Hexagonal Lattice: A_hP1_191_a S442
4. Li_3N: A3B_hP4_191_bc_a S444
5. Hexagonal ω: AB2_hP3_191_a_d S446
6. Cu_2Te: A2B_hP6_191_h_e S448
7. CoSn: AB_hP6_191_f_ad S450

P6$_3$/mmc (194) .....

1. AsTi: AB_hP8_194_ad_f S452
2. Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h S454
3. CMo: AB_hP12_194_af_bf S456
4. α-La: A_hP4_194_ac S458
5. Na_3As: AB3_hP8_194_c_bf S460
6. $CaIn_2$: AB2_hP6_194_b_f S462
7. BN: AB_hP4_194_c_d S464
8. $AlCCr_2$: ABC2_hP8_194_d_a_f S466
9. Ni_3Sn: A3B_hP8_194_h_c S468
10. Hexagonal Graphite: A_hP4_194_bc S470
11. Molybdenite: AB2_hP6_194_c_f S472
12. W_2B_5: A5B2_hP14_194_abdf_f S474
13. $MgZn_2$ Hexagonal Laves: AB2_hP12_194_f_ah . S476
14. LiBC: ABC_hP6_194_c_d_a S478
15. Lonsdaleite: A_hP4_194_f S480
16. Ni_2In: AB2_hP6_194_c_ad S482
17. AlN_3Ti_4: AB3C4_hP16_194_c_af_ef S484
18. Hexagonal Close Packed: A_hP2_194_c S486
19. $MgNi_2$ Hexagonal Laves: AB2_hP24_194_ef_fgh S488
20. Covellite: AB_hP12_194_df_ce S490
21. NiAs: AB_hP4_194_c_a S492
22. β-Tridymite: A2B_hP12_194_cg_f S494

I23 (197) .....

1. Ga_4Ni: A4B_cI40_197_cde_c S496

P2$_1$3 (198) .....

1. Ullmanite: ABC_cP12_198_a_a_a S498
2. Ammonia: A3B_cP16_198_b_a S500
3. α-N: A_cP8_198_2a S502
4. α-CO[‡‡]: AB_cP8_198_a_a S504
5. FeSi[‡‡]: AB_cP8_198_a_a S506

I2$_1$3 (199) .....

1. CoU: AB_cI16_199_a_a S508

Im$\bar{3}$ (204) .....

1. Bergman [$Mg_{32}(Al,Zn)_{49}$]: AB32C48_cI162_204_a_2efg_2gh S510
2. Skutterudite: A3B_cI32_204_g_c S514
3. $Al_{12}W$: A12B_cI26_204_g_a S516

Pa$\bar{3}$ (205) .....

1. α-N: A_cP8_205_c S518
2. SC16: AB_cP16_205_c_c S520
3. Pyrite: AB2_cP12_205_a_c S522

Ia$\bar{3}$ (206) .....

1. Bixbyite: AB3C6_cI80_206_a_d_e S524
2. BC8: A_cI16_206_c S528

P4$_1$32 (213) .....

1. β-Mn: A_cP20_213_cd S530

P$\bar{4}$3m (215) .....

1. Sulvanite: A3B4C_cP8_215_d_e_a S532
2. Fe_4C: AB4_cP5_215_a_e S534
3. Cubic Lazarevićite: AB3C4_cP8_215_a_c_e S536

F$\bar{4}$3m (216) .....

1. $AuBe_5$: AB5_cF24_216_a_ce S538
2. Half-Heusler: ABC_cF12_216_b_c_a S540
3. Zincblende: AB_cF8_216_c_a S542

I$\bar{4}$3m (217) .....

1. SiF_4: A4B_cI10_217_c_a S544
2. α-Mn: A_cI58_217_ac2g S546
3. γ-Brass: A5B8_cI52_217_ce_cg S548

I$\bar{4}$3d (220) .....

1. High-Pressure cI16 Li: A_cI16_220_c S550
2. Pu_2C_3: A3B2_cI40_220_d_c S552

Pm$\bar{3}$m (221) .....

1. CsCl: AB_cP2_221_b_a S554
2. NbO: AB_cP6_221_c_d S556
3. Cubic Perovskite: AB3C_cP5_221_a_c_b S558
4. Model of Austenite: AB27CD3_cP32_221_a_dij_b_c S560
5. Cu_3Au: AB3_cP4_221_a_c S562
6. α-Po: A_cP1_221_a S564
7. $BaHg_{11}$: AB11_cP36_221_c_agij S566
8. Model of Ferrite: AB11CD3_cP16_221_a_dg_b_c S569
9. α-ReO_3: A3B_cP4_221_d_a S571
10. CaB_6: A6B_cP7_221_f_a S573

Pm$\bar{3}$n (223) .....

1. Cr_3Si: A3B_cP8_223_c_a S575
2. Si_{46} Clathrate: A_cP46_223_dik S577

Pn$\bar{3}$m (224) .....

1. Cuprite: A2B_cP6_224_b_a S580

Fm$\bar{3}$m (225) .....

1. Ca_7Ge: A7B_cF32_225_bd_a S582
2. BiF_3: AB3_cF16_225_a_bc S584
3. Model of Ferrite: A9B16C7_cF128_225_acd_2f_be S586
4. UB_{12}: A12B_cF52_225_i_a S589
5. Fluorite: AB2_cF12_225_a_c S591
6. $Cr_{23}C_6$: A6B23_cF116_225_e_acfh S593
7. Heusler: AB2C_cF16_225_a_c_b S595

[‡‡] α-CO and FeSi have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

8. Face-Centered Cubic: A_cF4_225_a S597
9. Model of Austenite: AB18C8_cF108_225_a_eh_f S599
10. Rock Salt: AB_cF8_225_a_b S601
Fd$\bar{3}$m (227) .....
1. Ideal β-Cristobalite: A2B_cF24_227_c_a S603
2. $NiTi_2$: AB2_cF96_227_e_cf S605
3. NaTl: AB_cF16_227_a_b S607
4. Si_{34} Clathrate: A_cF136_227_aeg S609
5. Cu_2Mg Cubic Laves: A2B_cF24_227_d_a S612
6. Diamond: A_cF8_227_a S614
7. Spinel: A2BC4_cF56_227_d_a_e S616
8. CTi_2: AB2_cF48_227_c_e S618
9. Fe_3W_3C: AB3C3_cF112_227_c_de_f S620
Im$\bar{3}$m (229) .....
1. Body-Centered Cubic: A_cI2_229_a S622
2. High-Pressure H_3S: A3B_cI8_229_b_a S624
3. Pt_3O_4: A4B3_cI14_229_c_b S626
4. Sb_2Tl_7: A2B7_cI54_229_e_afh S628
5. Model of Austenite: AB12C3_cI32_229_a_h_b .. S630
6. Model of Ferrite: AB4C3_cI16_229_a_c_b S632
Ia$\bar{3}$d (230) .....
1. Ga_4Ni_3: A4B3_cI112_230_af_g S634

Index
1. Prototype Index S809
2. Pearson Symbol Index S812
3. Strukturbericht Designation Index S816
4. Duplicate AFLOW Label S821
5. CIF Index S821
6. POSCAR Index S825

1. Introduction

In 1913, W. H. and W. L. Bragg [1] determined the crystal structure of diamond by X-ray diffraction. This was followed by many other structural determinations, some using rather unique techniques [2]. Soon large amounts of structural data were being generated, beyond the ability of the average scientist to collect, much less critically evaluate and organize.

The first systematic attempt to organize this data was the *Strukturbericht* series [3], first edited by P. P. Ewald and continued by others into the middle of the Second World War. The *Strukturbericht* volumes gave each crystal structure a letter designation followed by a number. *A* designated single element structures (A1 ≡ Cu, A2 ≡ W, A3 ≡ Mg, *etc.*), *B* binary compounds AB (B1 ≡ NaCl, B2 ≡ CsCl, ...), *C* for binary AB_2 compounds (C1 ≡ CaF_2 fluorite, C2 ≡ FeS_2 pyrite, ...), *L* for alloy related structures, and so on. The *Strukturbericht* designation did not apply to a single compound, *e.g.* all single element face-centered crystals were designated A1, all salts similar to sodium chloride were listed as B1, and so on. Although these designations are still in use today, they quickly became unwieldy, requiring both numerical ($L1_2 \equiv Cu_3Au$) [4] and alphabetic ($D5_a \equiv Si_2U_3$) [512] subscripts. Following the war, *Strukturbericht's* designations were dropped by its successor, the International Union of Crystallography's *Structure Reports* [6].

Strukturbericht was not the only compilation of crystal structures. In 1924, R. W. G. Wyckoff published the first edition of *The Structure of Crystals*, which eventually became a six volume set [7] describing hundreds of different crystals, organizing structures by prototype, *e.g.* ZnS for compounds with the zincblende/sphalerite structure [8].

Post-war, in 1958 W. B. Pearson published the first edition [9] of what is now known as *Pearson's Handbook*, a collection of crystallographic data for metals and intermetallic alloys. This classified the structures by prototype compound, space group, Pearson symbol, and, when available, *Strukturbericht* designation. This monumental work was updated by Villars and Calvert, whose second edition [10] contains more than 50,000 entries. In the intervening years, Pearson published *The Crystal Chemistry and Physics of Metals and Alloys* [11], which described a variety of crystal structures, categorizing them by physical and geometrical considerations.

After the turn of the century, the wide availability of computer storage and high speed internet connections made large electronic databases possible. The Inorganic Crystal Structure Database (ICSD), while not strictly organized by prototypes, is a useful and well-known online materials database that contains structural data for over 185,000 materials [12]. 2003 saw the first publication of *The American Mineralogist Crystal Structure Database* (AMCD) [13], which lists crystallographic data for well over two thousand minerals, often with multiple entries, drawn from *The American Mineralogist*, *Acta Crystallographica*, and other sources, including the compilations listed above. At the beginning of this decade, Pierre Villars and others made an enormous collection of data known as the Pauling File [14] available through the Springer Materials website. The crystallographic part of this database is essentially an extension of *Pearson's Handbook*, going well beyond metals and intermetallic alloys. More recently in 2007, a website *The Structure of Materials* [15] provided data for approximately 100 different structure types.

On a much more modest level, in 1995 one of us, with help from summer student R. Benjamin Young, first made a web page called *Crystal Lattice Structures* available on the World Wide Web. While it contained information that could also be found in the above sources, it provided information that was useful to researchers unfamiliar with crystallographic conventions. For example, the AMCD lists the structure of fluorite (CaF_2) as

```
5.4631 5.4631 5.4631 90 90 90 Fm-3m
atom x y z
```

```
Ca 0 0 0
F .25 .25 .25
```

Those familiar with crystallographic conventions would immediately recognize that the primitive unit cell of this system was face-centered cubic (from the space group label, $Fm\overline{3}m$), with cubic lattice constant 5.4631Å. A calcium atom is at the origin, and a fluorine atom is at the position $(1/4a, 1/4a, 1/4a)$. The researcher would then go to the *International Tables for Crystallography* [16] or the online Bilbao Crystallographic Server [17, 18, 19] to determine the complete set of atomic positions.

On the other hand, the *Crystal Lattice Structures* page included all of the above information, but also explicitly showed the primitive vectors of the face-centered cubic unit cell,

$$\begin{aligned}\mathbf{a}_1 &= \frac{a}{2}\,\hat{\mathbf{y}} + \frac{a}{2}\,\hat{\mathbf{z}}\\ \mathbf{a}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{a}{2}\,\hat{\mathbf{z}}\\ \mathbf{a}_3 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{a}{2}\,\hat{\mathbf{y}},\end{aligned}$$

(where $\hat{\mathbf{x}}, \hat{\mathbf{y}}$ and $\hat{\mathbf{z}}$ are the Cartesian unit vectors), as well as the atomic positions of all of the atoms, in terms of both the primitive lattice and Cartesian vectors:

$$\begin{aligned}\mathbf{B}_1 &= 0\,\mathbf{a}_1 + 0\,\mathbf{a}_2 + 0\,\mathbf{a}_3\\ &= 0\,\hat{\mathbf{x}} + 0\,\hat{\mathbf{y}} + 0\,\hat{\mathbf{z}} \qquad (4a) \qquad \text{Ca}\\ \mathbf{B}_2 &= \frac{1}{4}\,\mathbf{a}_1 + \frac{1}{4}\,\mathbf{a}_2 + \frac{1}{4}\,\mathbf{a}_3\\ &= \frac{a}{4}\,\hat{\mathbf{x}} + \frac{a}{4}\,\hat{\mathbf{y}} + \frac{a}{4}\,\hat{\mathbf{z}} \qquad (8c) \qquad \text{F}\\ \mathbf{B}_3 &= \frac{3}{4}\,\mathbf{a}_1 + \frac{3}{4}\,\mathbf{a}_2 + \frac{3}{4}\,\mathbf{a}_3\\ &= \frac{3a}{4}\,\hat{\mathbf{x}} + \frac{3a}{4}\,\hat{\mathbf{y}} + \frac{3a}{4}\,\hat{\mathbf{z}}. \qquad (8c) \qquad \text{F}\end{aligned}$$

This shows all of the atoms in the primitive unit cell of the system. The web page also offered views of the system from several angles, and in later iterations allowed the user to rotate the unit cell to see the crystal from any angle. Finally, all of the structures in the database were classified by type (face- or body-centered cubic, hexagonal close-packed, sp^3 bonding, *etc.*), Pearson Symbol, and space group. These features made the *Crystal Lattice Structures* page very popular with students and researchers.

While popular, the web site was never properly supported. It grew in a haphazard and piecemeal fashion, so that the format of one page might be different from another page. While many pages listed the original reference for a structure, many others did not. For these and other reasons the web site was removed for redesign in 2010.

Recent advances in computational materials science present novel opportunities for structure discovery and optimization, including uncovering of unsuspected compounds and metastable structures, electronic structure, surface, and nano-particle properties. These opportunities largely depend on the ability to apply modern high-throughput computational methods to analyze the properties of large data sets of structures and requires systematic generation and classification of the relevant computational data by high-throughput methods [20] and data repositories, such as AFLOW [21, 22, 23, 24], Materials Project [25], OQMD [26], NoMaD [27], and AiiDA [28]. It has become imperative to make the data from these structure databases more accessible to the growing community of computational materials scientists. Such exposure should provide an easy route to use the crystallographic data included in these compilations in advanced software frameworks, such as AFLOW [21, 22, 23, 24], for high-throughput calculation of crystal structure properties of alloys, intermetallics and inorganic compounds. These frameworks decorate structural prototypes, often sourced from databases such as those described in this work, with different species to perform automated high-throughput materials discovery and characterization. This synergy would provide materials scientists with a powerful tool for efficient quantum computational materials discovery and characterization [29, 30].

This article, then, describes a new version of the database, designed with this synergy in mind, and renamed as *The AFLOW Library of Crystallographic Prototypes*. The web version of this database is located at http://aflow.org/CrystalDatabase.

The format of this article is as follows: Section 2 discusses the basics of three dimensional periodic systems. Section 3 discusses the seven crystal systems and fourteen Bravais lattices that can exist in three dimensions as well as the definition of space groups, and gives our standard representation of the primitive vectors of each lattice. Section 11 shows how to take Wyckoff positions from the International Space Group tables and transform them into lattice coordinates for a given crystal system. Section 12 explains the format of the pages of the database, the online Crystallographic Information File (CIF) [31] for the structure, and the online POSCAR[1] file that summarizes the structural information.

2. Periodic Three-Dimensional Systems

In this section we give a brief review of the mathematics of three-dimensional periodic systems, describing the notation used in the database. Expanded descriptions of this topic, with an emphasis on condensed matter physics, can be found in Lax [33], Ashcroft and Mermin [34], Barrett and Massalski [35], and the various editions of Kittel [36].

In condensed matter physics, a crystal structure is a periodic system characterized by three primitive lattice vectors, $(\mathbf{a}_1, \mathbf{a}_2, \mathbf{a}_3)$. These vectors must not be co-planar, so that

[1] A POSCAR file is used to describe the primitive vectors and atomic positions in the *Vienna Ab-Initio Simulation Package* (VASP) [32].

$\mathbf{a}_1 \cdot (\mathbf{a}_2 \times \mathbf{a}_3) \neq 0$. If the atomic nuclei are located at basis vectors $\mathbf{B}_i$, then their periodic replicas are located at

$$\mathbf{B}_i + N_1\,\mathbf{a}_1 + N_2\,\mathbf{a}_2 + N_3\,\mathbf{a}_3 \tag{1}$$

for all positive and negative integers (N_1, N_2, N_3). Furthermore, everything in the crystal is periodic, including continuous functions such as the electronic density $\rho(\mathbf{r})$:

$$\rho\,(\mathbf{r}) = \rho\,(\mathbf{r} + N_1\,\mathbf{a}_1 + N_2\,\mathbf{a}_2 + N_3\,\mathbf{a}_3)\,. \tag{2}$$

A unit cell is a volume which, when translated through by all vectors of the form $N_1\,\mathbf{a}_1 + N_2\,\mathbf{a}_2 + N_3\mathbf{a}_3$ (the set points known as the Bravais lattice), fills all space. One possible unit cell is the set of all points [34]

$$\mathbf{r} = u_1\,\mathbf{a}_1 + u_2\,\mathbf{a}_2 + u_3\,\mathbf{a}_3 \tag{3}$$

such that $0 \leq u_i < 1$. This is obviously not unique, *e.g.* we could pick the interval $-1/2 < u_i \leq 1/2$. Indeed, the choice of primitive vectors is not unique. For any choice of $\mathbf{a}_I$, we can find alternative vectors $\mathbf{a}'_i$ which are related to the original primitive vectors by

$$\begin{pmatrix} \mathbf{a}'_1 \\ \mathbf{a}'_2 \\ \mathbf{a}'_3 \end{pmatrix} = \begin{pmatrix} n_{11} & n_{12} & n_{13} \\ n_{21} & n_{22} & n_{23} \\ n_{31} & n_{32} & n_{33} \end{pmatrix} \cdot \begin{pmatrix} \mathbf{a}_1 \\ \mathbf{a}_2 \\ \mathbf{a}_3 \end{pmatrix}, \tag{4}$$

where the n_{ij} are integers. This will produce an identical Bravais lattice provided the determinant of the n matrix is plus or minus unity:

$$\begin{vmatrix} n_{11} & n_{12} & n_{13} \\ n_{21} & n_{22} & n_{23} \\ n_{31} & n_{32} & n_{33} \end{vmatrix} = \pm 1. \tag{5}$$

No matter what choice we make, the volume of the unit cell is given by

$$V = \mathbf{a}_1 \cdot (\mathbf{a}_2 \times \mathbf{a}_3)\,. \tag{6}$$

We will always assume what is known as a right-handed coordinate system, so that $V > 0$.

Since the periodic replicas of a unit cell fill all space, any point $\mathbf{r}$ in space may be defined by its Cartesian coordinates

$$\mathbf{r} = x_1\,\hat{\mathbf{x}} + x_2\,\hat{\mathbf{y}} + x_3\,\hat{\mathbf{z}}, \tag{7}$$

where $(\hat{\mathbf{x}}, \hat{\mathbf{y}}, \hat{\mathbf{z}})$ are orthogonal vectors with unit length, or by its lattice coordinates,

$$\mathbf{r} = u_1\,\mathbf{a}_1 + u_2\,\mathbf{a}_2 + u_3\,\mathbf{a}_3. \tag{8}$$

Lattice coordinates are often called fractional coordinates. The transformation between the Cartesian coordinates (x_1, y_1, z_1) and lattice coordinates (u_1, u_2, u_3) is most easily accomplished by defining a periodic reciprocal lattice, defined by vectors ($\mathbf{b}_1$, $\mathbf{b}_2$, $\mathbf{b}_3$), which are chosen so that

$$\mathbf{a}_i \cdot \mathbf{b}_j = 2\pi\,\delta_{ij}, \tag{9}$$

where δ_{ij} is the Kronecker[2] δ. The reciprocal lattice vectors can be determined from the primitive lattice vectors via the formula

$$\mathbf{b}_i = \left(\frac{2\pi}{V}\right) \mathbf{a}_j \times \mathbf{a}_k, \tag{10}$$

where $(ijk) = (123), (231)$, or (312). Given this definition, we see that we can obtain the lattice coordinates for any vector $\mathbf{r}$ via

$$u_i = \frac{\mathbf{b}_i \cdot \mathbf{r}}{2\pi}. \tag{11}$$

This gives us a general procedure for translating between Cartesian and lattice coordinates: given the lattice coordinates of a point, we can find the Cartesian coordinates via (7). Given the Cartesian coordinates, we can find the lattice coordinates via (11).

It should also be noted that any function exhibiting the symmetry of the crystal can be written as a periodic function of the lattice coordinates with a period of 1 in each direction. In other words, in lattice coordinates equation (2) becomes

$$\rho\,(u_1, u_2, u_3) = \rho\,(u_1 + N_1, u_2 + N_2, u_3 + N_3)\,, \tag{12}$$

where (u_1, u_2, u_3) are given by (11). This means that we know everything about the crystal if we can describe it for values of u_i in the range $[\alpha_i, \alpha_i + 1]$, where α_i can be chosen arbitrarily. Usual values are 0 or 1/2, so that the range is $[0, 1]$ or $[-1/2, 1/2]$.

Lastly, a rotation of a crystal about any point does not change its physical properties, only its orientation in space. We could, for example replace the unit vectors $(\hat{\mathbf{x}}, \hat{\mathbf{y}}, \hat{\mathbf{z}})$ in (7) by any other three orthogonal unit vectors and still describe the same crystal. For that reason it is useful to define the lattice by the lengths of its primitive vectors and the angles between them. This requires six values conventionally chosen as (a, b, c) to describe the lengths and (α, β, γ) to describe the angles, where

$$\begin{aligned} a &= |\mathbf{a}_1| \\ b &= |\mathbf{a}_2| \\ c &= |\mathbf{a}_3|, \end{aligned} \tag{13}$$

and the cosines of the angles are given by

$$\begin{aligned} \cos\alpha &= \frac{\mathbf{a}_2 \cdot \mathbf{a}_3}{b\,c} \\ \cos\beta &= \frac{\mathbf{a}_3 \cdot \mathbf{a}_1}{c\,a} \\ \cos\gamma &= \frac{\mathbf{a}_1 \cdot \mathbf{a}_2}{a\,b}. \end{aligned} \tag{14}$$

[2]The physical and mathematical motivation for the definition of the reciprocal lattice, including the 2π factor, is beyond the scope of this article. More information can be found in any of the texts given at the beginning of this section. Here we simply use the reciprocal lattice to translate between Cartesian and lattice coordinates.

The primitive cell of a crystal is uniquely specified by these values (up to an arbitrary rotation), and crystallographic articles report the structures in this form.

3. Crystal Systems, Lattices, Space Groups and Standard Lattice Vectors

Having defined what we mean by a lattice, we now discuss the possible lattices that can exist in a three dimensional space, and some of their properties. Here we define our terms following Lax [37], paraphrasing his discussion.

1. A *Crystal* is a periodic array of physical objects. In this article we discuss crystals made of periodic arrays of atoms and their associated electrons.
2. A *Crystal Structure* is the complete description of the crystal including its periodic structure and the contents of the unit cell. In our case, we obtain a complete description of the crystal by specifying the primitive vectors of the periodic lattice $\mathbf{a}_i, (i = 1, 2, 3)$ and the positions $\mathbf{B}_j, (j = 1, 2, 3, \ldots, N)$ of the N atoms in a unit cell. The ground state electronic charge density, if desired, can then be computed from these atomic positions.
3. A *Space Group* is the set of all operations (translations, rotations, and reflections) that restore a crystal to itself. In three dimensional space there are 230 space groups.
4. A *Crystal Class* is the point group of the crystal. This includes all possible rotations and reflections (but not translations) that leave the shape of the crystal unchanged. This does not mean that the crystal is transformed into itself, only the point group. In three dimensions there are 32 crystal classes.
5. A *Bravais Lattice* is a collection of points
$$\{t_1\,\mathbf{a}_1 + t_2\,\mathbf{a}_2 + t_3\,\mathbf{a}_3\}\,, \tag{15}$$
where the t_i are integers and the $\mathbf{a}_i$ are not co-planar, *i.e.* the volume (6) is non-zero. Equation (4) allows some freedom in the choice of $\mathbf{a}_i$, but all choices lead to the same points for a given Bravais lattice. In three dimensions a given crystal class has at least one and a maximum of four Bravais lattices.
6. The *holohedry* of a Bravais lattice is the point group that describes its rotational symmetry.
7. A *Crystal System* is the set of all Bravais lattices that have the same holohedry. In three dimensions there are seven crystal systems, many of which contain multiple Bravais lattices.

In 1891 E. S. Federov [38] and A. Schönflies [39] determined the 230 space groups allowed in three dimensions. Wyckoff [40] tabulated all of these groups, and determined the special atomic coordinates (the Wyckoff positions) allowed for each space group. Here we briefly describe the properties of each crystal system and its associated Bravais lattices, and list the space groups associated with each lattice. In general we will start with the lowest symmetry and go to increasingly higher symmetries. Each space group will be labeled by the International symbol associated with its standard orientation as defined in the International Tables [16]. Alternative orientations of the space groups will lead to different labels. Cockcroft [41] has a complete list of these online.

In the following, we will frequently refer to conventional lattices and primitive, or Bravais, lattices. The basic definition of a Bravais lattice is that it describes the periodicity of a particular system. A conventional lattice, on the other hand, describes the holohedry of all of the Bravais lattices in a given crystal system. Each crystal system has a Bravais lattice that is identical with the conventional lattice.

Figure 1: A two-dimensional rectangular system, with primitive vectors $\mathbf{A}_1$ and $\mathbf{A}_2$ given by (16). The solid lines denote the edges of the unit cell.

This is most easily seen in two dimensions. Figure 1 shows a rectangular periodic structure. The periodicity can be described by the primitive vectors

$$\begin{aligned} \mathbf{A}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{A}_2 &= b\,\hat{\mathbf{y}}. \end{aligned} \tag{16}$$

The solid lines mark the edges of the unit cell for this system.

Next consider the structure shown in Figure 2. It can obviously be described as a periodic structure with primitive vectors (16) and a unit cell bounded by the solid lines. However, it can also be described by the primitive vectors

$$\begin{aligned} \mathbf{a}_1 &= \frac{a}{2}\,\hat{\mathbf{x}} - \frac{b}{2}\,\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{b}{2}\,\hat{\mathbf{y}}. \end{aligned} \tag{17}$$

These primitive vectors are shown in Figure 2, and the unit cells associated with these vectors are bounded by the dashed lines.

Both of these structures have the same holohedry, belonging to the two-dimensional rectangular crystal system. They have different Bravais lattices. We can call these lattices *simple* rectangular, shown in Figure 1, and *centered* rectangular, shown in Figure 2.[3]

Figure 2: A two-dimensional centered rectangular system, with primitive vectors $\mathbf{a}_1$ and $\mathbf{a}_2$ given by 17. The dashed lines denote the edges of the primitive unit cell, while the solid lines denote the edges of the conventional unit cell.

Both the holohedry and translational symmetry of these structures can be described by the vectors (16), although the centered cell has another translation. Equations (16) then define the *conventional* unit cell for the two-dimensional rectangular crystal system.

The area of the conventional Bravais lattice, ab, is twice that of the centered Bravais lattice, as can be seen from Figure 2, which also shows that the conventional lattice has twice as many triangles (atoms) per unit cell as the Bravais lattice. In three dimensions, as we will see, the conventional lattice can hold one, two, three or four times as many atoms as the underlying Bravais lattice.

Going back to three dimensions, standard crystallographic practice is to report the lattice parameters (a, b, c, α, β, γ) of (13-14) using the conventional lattice, rather than the Bravais lattice. While this may seem arbitrary, the primitive vectors

$$\begin{aligned} \mathbf{a}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{a}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{b}{2}\,\hat{\mathbf{y}} \end{aligned}$$

describe Figure 2 just as well as (17), but have different lengths and angles, and there are a multitude of other possible sets. There is, however, only one logical way to describe the conventional cell, (16). This happens in three dimensions as well. As a general rule,[4] (a, b, c, α, β, γ), and even the number of atoms in a unit cell, are given for the conventional lattice. The size of the primitive cell has to be inferred from knowledge of the space group.

We now consider the seven crystal systems, including the Bravais lattice, and the space groups associated with each Bravais lattice.

As noted above, there are an infinite number of choices for a set of primitive vectors describing a unit cell. In general we follow the choices made by Setyawan and Curtarolo [42]. Differences occur in the monoclinic, base-centered orthorhombic, and rhombohedral lattices, and are discussed in the footnotes.

4. The Triclinic Crystal System

The triclinic is the most general crystal system. All of the other crystal systems can be considered special cases of the triclinic. The primitive vectors are also completely general: their lengths (a, b, c) and angles (α, β, γ) may have arbitrary values. The triclinic system has one Bravais lattice, which is also the conventional lattice for this system.

Figure 3: The conventional and simple unit cells for the triclinic crystal system.

4.1. Lattice 1: Triclinic

There are many choices for the primitive vectors in the triclinic system. We make the choice

$$\begin{aligned} \mathbf{a}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{a}_2 &= b\,\cos\gamma\,\hat{\mathbf{x}} + b\,\sin\gamma\,\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c_x\,\hat{\mathbf{x}} + c_y\,\hat{\mathbf{y}} + c_z\,\hat{\mathbf{z}}, \end{aligned} \tag{18}$$

where

$$\begin{aligned} c_x &= c\,\cos\beta \\ c_y &= \frac{c\,(\cos\alpha - \cos\beta\,\cos\gamma)}{\sin\gamma} \end{aligned}$$

[3]This is called a centered lattice because the primitive vectors (17) point to the center of the rectangular unit cell.

[4]The one exception to this rule is the rhombohedral lattice, which we shall discuss below.

and

$$c_z = \sqrt{c^2 - c_x^2 - c_y^2}.$$

The volume of the triclinic unit cell is

$$V = a\,b\,c_z\,\sin\gamma. \tag{19}$$

The space groups associated with the triclinic lattice are given in Table 1.

Table 1: The space groups associated with the triclinic Bravais lattice (18) are

1. $P1$	2. $P\bar{1}$

5. The Monoclinic Crystal System

In the monoclinic crystal system, the conventional unit cell is defined by primitive vectors of arbitrary length, where one of the vectors is perpendicular to the other two. Modern convention chooses this vector to be the one with length b (or "unique axis b" in the literature), so that $\alpha = \gamma = \pi/2$ and $\beta \neq \pi/2$.[5]

Figure 4: The conventional, simple, and base-centered unit cells for the monoclinic crystal system.

The conventional unit cell can be described by the vectors

$$\begin{aligned} \mathbf{A}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{A}_2 &= b\,\hat{\mathbf{y}} \\ \mathbf{A}_3 &= c\,\cos\beta\,\hat{\mathbf{x}} + c\,\sin\beta\,\hat{\mathbf{z}}, \end{aligned} \tag{20}$$

and the volume of a conventional unit cell is

$$V = a\,b\,c\,\sin\beta. \tag{21}$$

[5]Note that this orientation differs from that of Setyawan and Curtarolo [42], who used an unique axis "a" setting. Their angle α would be γ in our notation.

5.1. Lattice 2: Simple Monoclinic

The simple monoclinic cell is identical to the conventional cell. Its primitive vectors are identical to (20)

$$\begin{aligned} \mathbf{a}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{a}_2 &= b\,\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\,\cos\beta\,\hat{\mathbf{x}} + c\,\sin\beta\,\hat{\mathbf{z}}, \end{aligned} \tag{22}$$

and the cell volume is just

$$V = a\,b\,c\,\sin\beta. \tag{23}$$

The space groups associated with the simple monoclinic lattice are given in Table 2.

Table 2: The space groups associated with the simple monoclinic Bravais lattice (22) are

3. $P2$	4. $P2_1$	6. Pm
7. Pc	10. $P2/m$	11. $P2_1/m$
13. $P2/c$	14. $P2_1/c$	

5.2. Lattice 3: Base-Centered Monoclinic

The base-centered monoclinic lattice is in the same crystal system as the monoclinic lattice, but its periodicity allows an additional translation in the plane defined by $\mathbf{a}_1$ and $\mathbf{a}_2$, much as in (17). The primitive vectors for the base-centered monoclinic lattice can be written

$$\begin{aligned} \mathbf{a}_1 &= \frac{a}{2}\,\hat{\mathbf{x}} - \frac{b}{2}\,\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{b}{2}\,\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\,\cos\beta\,\hat{\mathbf{x}} + c\,\sin\beta\,\hat{\mathbf{z}}. \end{aligned} \tag{24}$$

The volume of the base-centered monoclinic unit cell is

$$V = \left(\frac{1}{2}\right) a\,b\,c\,\sin\beta, \tag{25}$$

half that of the conventional unit cell.

The space groups associated with the base-centered monoclinic lattice are given in Table 3. The labels for these space groups all begin with C, indicating the base-centered translation associated with these groups. This differs from the labels for space groups in Table 1 and Table 2, which begin with P, indicating that the primitive lattice is the conventional lattice.

The *International Tables* offer two representations of the base-centered monoclinic space groups, one for "unique axis b" and one for "unique axis c," where $\alpha \neq \pi/2$ and $\beta = \pi/2$. Space group 5 is then listed as "B2" or "C2" depending on this choice. Most authors ignore this distinction, as will we.

Table 3: The space groups associated with the base-centered monoclinic Bravais lattice (24) are

5. $C2$	8. Cm	9. Cc
12. $C2/m$	15. $C2/c$	

6. The Orthorhombic Crystal System

In the orthorhombic system, the conventional unit cell is a parallelepiped, defined by three mutually orthogonal vectors of unequal length:

$$\begin{aligned} \mathbf{A}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{A}_2 &= b\,\hat{\mathbf{y}} \\ \mathbf{A}_3 &= c\,\hat{\mathbf{z}}, \end{aligned} \tag{26}$$

so that $a \neq b \neq c$, but $\alpha = \beta = \gamma = \pi/2$. It is a limiting case of the conventional monoclinic crystal with $\beta \to \pi/2$. The volume of the conventional unit cell is

$$V = a\,b\,c. \tag{27}$$

There are four Bravais lattices in the orthorhombic system.

Figure 5: The conventional, simple, face-centered, base-centered, and body-centered unit cells for the orthorhombic crystal system.

6.1. Lattice 4: Simple Orthorhombic

The simple orthorhombic Bravais lattice is identical to the conventional cell

$$\begin{aligned} \mathbf{a}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{a}_2 &= b\,\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\,\hat{\mathbf{z}}, \end{aligned} \tag{28}$$

with volume

$$V = a\,b\,c\,. \tag{29}$$

The space groups associated with the simple orthorhombic lattice are given in Table 4.

Table 4: The space groups associated with the simple orthorhombic lattice (28) are

16. $P222$	17. $P222_1$	18. $P2_12_12$
19. $P2_12_12_1$	25. $Pmm2$	26. $Pmc2_1$
27. $Pcc2$	28. $Pma2$	29. $Pca2_1$
30. $Pnc2$	31. $Pmn2_1$	32. $Pba2$
33. $Pna2_1$	34. $Pnn2$	47. $Pmmm$
48. $Pnnn$	49. $Pccm$	50. $Pban$
51. $Pmma$	52. $Pnna$	53. $Pmna$
54. $Pcca$	55. $Pbam$	56. $Pccn$
57. $Pbcm$	58. $Pnnm$	59. $Pmmn$
60. $Pbcn$	61. $Pbca$	62. $Pnma$

6.2. Lattice 5: Base-Centered Orthorhombic

Like the base-centered monoclinic lattice, the base-centered orthorhombic system allows a translation in one of the base planes. Unfortunately, the standard plane chosen depends on the space group, as shown in Table 5. Space groups beginning with C put the translation in the $a - b$ plane, that is, the plane defined by $\mathbf{A}_1$ and $\mathbf{A}_2$ (26). In this case the primitive vectors can be taken to be

$$\begin{aligned} \mathbf{a}_1 &= \frac{a}{2}\,\hat{\mathbf{x}} - \frac{b}{2}\,\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{b}{2}\,\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\,\hat{\mathbf{z}}\,. \end{aligned} \tag{30}$$

Space groups beginning with A put the translation in the $b - c$ plane, defined by $\mathbf{A}_2$ and $\mathbf{A}_3$. We use the primitive vectors[6]

$$\begin{aligned} \mathbf{a}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{a}_2 &= \frac{b}{2}\,\hat{\mathbf{y}} - \frac{c}{2}\,\hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{b}{2}\,\hat{\mathbf{y}} + \frac{c}{2}\,\hat{\mathbf{z}}. \end{aligned} \tag{31}$$

In both cases the volume of the primitive unit cell is

$$V = \frac{a\,b\,c}{2}. \tag{32}$$

There are two primitive base-centered orthorhombic unit cells in the conventional orthorhombic unit cell.

[6]Orientation (31) is not used by Setyawan and Curtarolo [42], who only considered centering in the "C" plane defined by $\mathbf{a}_2$ and $\mathbf{a}_3$. A simple rotation brings the vectors into agreement.

Table 5: The space groups associated with the base-centered orthorhombic lattice. Space groups beginning with C place the base-translation in the $a-b$ plane and use primitive vectors (30), while space groups beginning with A put the translation in the $b-c$ plane and use the primitive vectors (31).

20. $C222_1$	21. $C222$	35. $Cmm2$
36. $Cmc2_1$	37. $Ccc2$	38. $Amm2$
39. $Abm2$	40. $Ama2$	41. $Aba2$
63. $Cmcm$	64. $Cmca$	65. $Cmmm$
66. $Cccm$	67. $Cmma$	68. $Ccca$

6.3. Lattice 6: Body-Centered Orthorhombic

The body-centered orthorhombic lattice has the same point group and translational symmetry as the simple orthorhombic system, with the addition of a translation to the center of the parallelepiped defined by the vectors (26). Our standard form of the primitive vectors is

$$\begin{aligned} \mathbf{a}_1 &= -\frac{a}{2}\,\hat{\mathbf{x}} + \frac{b}{2}\,\hat{\mathbf{y}} + \frac{c}{2}\,\hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} - \frac{b}{2}\,\hat{\mathbf{y}} + \frac{c}{2}\,\hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{b}{2}\,\hat{\mathbf{y}} - \frac{c}{2}\,\hat{\mathbf{z}}. \end{aligned} \tag{33}$$

The volume of the primitive body-centered orthorhombic unit cell is

$$V = \frac{a\,b\,c}{2}. \tag{34}$$

There are two primitive body-centered orthorhombic unit cells in the conventional orthorhombic unit cell. The space groups associated with this lattice, all of which begin with I in standard notation, are given in Table 6.

Table 6: The space groups associated with the body-centered orthorhombic lattice (33).

23. $I222$	24. $I2_12_12_1$	44. $Imm2$
45. $Iba2$	46. $Ima2$	71. $Immm$
72. $Ibam$	73. $Ibca$	74. $Imma$

6.4. Lattice 7: Face-Centered Orthorhombic

While the base-centered monoclinic lattice allows translations to one base plane, the face-centered orthorhombic lattice allows translations to any of the base planes. Our standard choice for the primitive vectors of this system are given by

$$\mathbf{a}_1 = \frac{b}{2}\,\hat{\mathbf{y}} + \frac{c}{2}\,\hat{\mathbf{z}} \tag{35}$$

$$\mathbf{a}_2 = \frac{a}{2}\,\hat{\mathbf{x}} + \frac{c}{2}\,\hat{\mathbf{z}} \tag{36}$$

$$\mathbf{a}_3 = \frac{a}{2}\,\hat{\mathbf{x}} + \frac{b}{2}\,\hat{\mathbf{y}}. \tag{37}$$

The volume of the primitive face-centered orthorhombic unit cell is

$$V = \frac{a\,b\,c}{4}\,, \tag{38}$$

so that there are four primitive body-centered orthorhombic unit cells in the conventional orthorhombic unit cell. The space groups associated with this lattice, all of which begin with F in standard notation, are given in Table 7.

Table 7: The space groups associated with the face-centered orthorhombic lattice (37).

22. $F222$	42. $Fmm2$	43. $Fdd2$
69. $Fmmm$	70. $Fddd$	

7. The Tetragonal Crystal System

In the tetragonal system, like the orthorhombic, the conventional unit cell is a parallelepiped, but two sides are equal, so that $a = b$ and $c \neq a$, while $\alpha = \beta = \gamma = \pi/2$, and this is a special case of the orthorhombic system. The primitive vectors of the conventional unit cell are

$$\begin{aligned} \mathbf{A}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{A}_2 &= a\,\hat{\mathbf{y}} \\ \mathbf{A}_3 &= c\,\hat{\mathbf{z}}. \end{aligned} \tag{39}$$

The volume of the conventional unit cell is

$$V = a^2\,c. \tag{40}$$

Given the similarity between the tetragonal and orthorhombic crystal system, we might expect that the tetragonal system would have four Bravais lattices as well, but the additional symmetry generated because $b = a$ reduces this to two. When $b \to a$, the base-centered orthorhombic Bravais lattice (30) becomes a simple tetragonal lattice, while the face-centered orthorhombic lattice (37) can be shown to be identical to a body-centered tetragonal cell [43].

7.1. Lattice 8: Simple Tetragonal

The simple tetragonal Bravais lattice is identical to the conventional cell

$$\begin{aligned} \mathbf{a}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{a}_2 &= a\,\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\,\hat{\mathbf{z}}, \end{aligned} \tag{41}$$

with volume

$$V = a^2\,c. \tag{42}$$

The space groups associated with the simple tetragonal lattice are given in Table 8.

Table 8: The space groups associated with the simple tetragonal lattice (41).

75. $P4$	76. $P4_1$	77. $P4_2$
78. $P4_3$	81. $P\bar{4}$	83. $P4/m$
84. $P4_2/m$	85. $P4/n$	86. $P4_2/n$
89. $P422$	90. $P42_12$	91. $P4_122$
92. $P4_12_12$	93. $P4_222$	94. $P4_22_12$
95. $P4_322$	96. $P4_32_12$	99. $P4mm$
100. $P4bm$	101. $P4_2cm$	102. $P4_2nm$
103. $P4cc$	104. $P4nc$	105. $P4_2mc$
106. $P4_2bc$	111. $P\bar{4}2m$	112. $P\bar{4}2c$
113. $P\bar{4}2_1m$	114. $P\bar{4}2_1c$	115. $P\bar{4}m2$
116. $P\bar{4}c2$	117. $P\bar{4}b2$	118. $P\bar{4}n2$
123. $P4/mmm$	124. $P4/mcc$	125. $P4/nbm$
126. $P4/nnc$	127. $P4/mbm$	128. $P4/mnc$
129. $P4/nmm$	130. $P4/ncc$	131. $P4_2/mmc$
132. $P4_2/mcm$	133. $P4_2/nbc$	134. $P4_2/nnm$
135. $P4_2/mbc$	136. $P4_2/mnm$	137. $P4_2/nmc$
138. $P4_2/ncm$		

Figure 6: The conventional, simple, and body-centered unit cells for the tetragonal crystal system.

7.2. Lattice 9: Body-Centered Tetragonal

The body-centered tetragonal system has the same point group and translational symmetry as the simple tetragonal system, with the addition of a translation to the center of the parallelepiped defined by the vectors (39). Our standard form of the primitive vectors is

$$\begin{aligned} \mathbf{a}_1 &= -\frac{a}{2}\,\hat{\mathbf{x}} + \frac{a}{2}\,\hat{\mathbf{y}} + \frac{c}{2}\,\hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} - \frac{a}{2}\,\hat{\mathbf{y}} + \frac{c}{2}\,\hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{a}{2}\,\hat{\mathbf{y}} - \frac{c}{2}\,\hat{\mathbf{z}}. \end{aligned} \tag{43}$$

The volume of the primitive body-centered tetragonal unit cell is

$$V = \frac{a^2\,c}{2}. \tag{44}$$

There are two primitive body-centered tetragonal unit cells in the conventional tetragonal unit cell. The space groups associated with this lattice, all of which begin with I in standard notation, are given in Table 9.

Table 9: The space groups associated with the body-centered tetragonal lattice (43).

79. $I4$	80. $I4_1$	82. $I\bar{4}$
87. $I4/m$	88. $I4_1/a$	97. $I422$
98. $I4_122$	107. $I4mm$	108. $I4cm$
109. $I4_1md$	110. $I4_1cd$	119. $I\bar{4}m2$
120. $I\bar{4}c2$	121. $I\bar{4}2m$	122. $I\bar{4}2d$
139. $I4/mmm$	140. $I4/mcm$	141. $I4_1/amd$
142. $I4_1/acd$		

8. The Trigonal Crystal System

The trigonal crystal system is defined by a three-fold rotation axis, and can be generated from the cubic crystal system (Section 10) by stretching the cube along its diagonal. The symmetry requires the primitive vectors to have the form $a = b$, $\alpha = \beta = \pi/2$, $\gamma = 120°$.[7] The trigonal system is a limiting case of the simple monoclinic Bravais lattice (22), with $\beta = 120°$. It can also be obtained from the base-centered orthorhombic Bravais lattice (30) with $b = \sqrt{3}a$. The conventional unit cell is described by the vectors

$$\begin{aligned} \mathbf{A}_1 &= \frac{a}{2}\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}} \\ \mathbf{A}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}} \\ \mathbf{A}_3 &= c\,\hat{\mathbf{z}}. \end{aligned} \tag{45}$$

There are two Bravais lattices in the trigonal system.

[7] We could take $\gamma = 60°$, but in that case the three-fold rotation axis is not obvious from the primitive vectors.

Figure 7: The conventional, simple (hexagonal), and rhombohedral unit cells for the trigonal crystal system.

8.1. Lattice 10: Hexagonal

Somewhat confusingly, what might be called the simple trigonal Bravais lattice is known as the hexagonal lattice. It shares the same primitive vectors, but not point operations, as the hexagonal crystal system (9). The primitive vectors are identical to those of the conventional cell,

$$\begin{aligned} \mathbf{a}_1 &= \frac{a}{2}\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{a}{2}\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\,\hat{\mathbf{z}}. \end{aligned} \tag{46}$$

The volume of the primitive cell is

$$V = \left(\frac{\sqrt{3}}{2}\right) a^2\,c. \tag{47}$$

The space groups associated with the (trigonal) hexagonal lattice are given in Table 10.

Table 10: The space groups associated with the (trigonal) hexagonal lattice (46).

143. $P3$	144. $P3_1$	145. $P3_2$
147. $P\bar{3}$	149. $P312$	150. $P321$
151. $P3_112$	152. $P3_121$	153. $P3_212$
154. $P3_221$	156. $P3m1$	157. $P31m$
158. $P3c1$	159. $P31c$	162. $P\bar{3}1m$
163. $P\bar{3}1c$	164. $P\bar{3}m1$	165. $P\bar{3}c1$

8.2. Lattice 11: Rhombohedral

The rhombohedral Bravais lattice has the periodicity of the conventional trigonal cell (45), with the addition of two translation vectors, $2/3\mathbf{A}_1 + 1/3\mathbf{A}_2 + 1/3\mathbf{A}_3$ and $1/3\mathbf{A}_1 + 2/3\mathbf{A}_2 + 2/3\mathbf{A}_3$.

The primitive vectors can be taken in the form

$$\begin{aligned} \mathbf{a}_1 &= \frac{a}{2}\,\hat{\mathbf{x}} - \frac{a}{\left(2\sqrt{3}\right)}\,\hat{\mathbf{y}} + \frac{c}{3}\,\hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{a}{\sqrt{3}}\,\hat{\mathbf{y}} + \frac{c}{3}\,\hat{\mathbf{z}} \\ \mathbf{a}_3 &= -\frac{a}{2}\,\hat{\mathbf{x}} - \frac{a}{\left(2\sqrt{3}\right)}\,\hat{\mathbf{y}} + \frac{c}{3}\,\hat{\mathbf{z}}, \end{aligned} \tag{48}$$

and the volume of the primitive cell is one-third that of the conventional cell,

$$V = \left(\frac{2}{\sqrt{3}}\right) a^2\,c. \tag{49}$$

The vectors (48) are all of identical length,

$$|\mathbf{a}_1| = |\mathbf{a}_2| = |\mathbf{a}_3| = \sqrt{\frac{a^2}{3} + \frac{c^2}{9}} \equiv a', \tag{50}$$

or, equivalently, $a = b = c \equiv a'$, where we designate the common length as a' to distinguish it from the length of the first two vectors in the conventional lattice. The vectors also make equal angles with each other

$$\alpha = \beta = \gamma = \cos^{-1}\left(\frac{2c^2 - 3a^2}{2\left(c^2 + 3a^2\right)}\right). \tag{51}$$

Equations (50) and (51) provide another definition of the rhombohedral lattice. We can show this by writing the primitive vectors in a form that depends only on the common length and separation angle,[8]

$$\begin{aligned} \mathbf{a}_1 &= a'\begin{pmatrix} \sin\frac{\alpha}{2}\,\hat{\mathbf{x}} \\ -\left(\frac{1}{\sqrt{3}}\right)\sin\frac{\alpha}{2}\,\hat{\mathbf{y}} \\ +\sqrt{\frac{1}{3}\left(4\cos^2\frac{\alpha}{2} - 1\right)}\,\hat{\mathbf{z}} \end{pmatrix} \\ \mathbf{a}_2 &= a'\begin{pmatrix} \left(2/\sqrt{3}\right)\sin\frac{\alpha}{2}\,\hat{\mathbf{y}} \\ +\sqrt{\frac{1}{3}\left(4\cos^2\frac{\alpha}{2} - 1\right)}\,\hat{\mathbf{z}} \end{pmatrix} \\ \mathbf{a}_3 &= a'\begin{pmatrix} -\sin\frac{\alpha}{2}\,\hat{\mathbf{x}} \\ -\left(\frac{1}{\sqrt{3}}\right)\sin\frac{\alpha}{2}\,\hat{\mathbf{y}} \\ +\sqrt{\frac{1}{3}\left(4\cos^2\frac{\alpha}{2} - 1\right)}\,\hat{\mathbf{z}} \end{pmatrix}. \end{aligned} \tag{52}$$

We can define the rhombohedral lattice in two ways: as a trigonal lattice with additional translational vectors, or as a

[8] An alternative orientation is given by Setyawan and Curtarolo [42], who only give the primitive vectors in this (a', α) setting. The primitive vectors used for their rhombohedral cell (section A.11) differ from (52) only by the orientation of the vectors relative to the Cartesian axes. Their choice is simpler for computational purposes, but does not show the relationship between (48) and (52).

"simple" lattice with equal primitive vectors making equal angles with one another. The *International Tables* addresses this ambiguity by listing atomic positions for the rhombohedral lattice in a "hexagonal setting," where all coordinates are referenced to the conventional cell (45), and in a "rhombohedral setting," where the coordinates are referenced to (52). To further confuse matters, the unit cell's dimensions might be reported in terms of (a, c) from (45), or in terms of (a', α) from (52). An article might say that there were N atoms in the rhombohedral cell, or 3N atoms in the conventional cell. One has to pay attention to the context.

In the database, we will report the lattice parameters of the system by giving a and c, since that is the usual crystallographic practice. However, we will record atomic positions using the primitive vectors (48), since computer calculations work best with the smallest number of atoms needed to describe the system.

The space groups associated with the rhombohedral lattice are given in Table 11.

Table 11: The space groups associated with the rhombohedral lattice (48).

146. $R3$	148. $R\bar{3}$	155. $R32$
160. $R3m$	161. $R3c$	166. $R\bar{3}m$
167. $R\bar{3}c$		

9. The Hexagonal Crystal System

The hexagonal crystal system has a six-fold rotation axis. There is only one Bravais lattice in this system, the hexagonal Bravais lattice given by (45) and (46), so the conventional and primitive lattices are equivalent.

The space groups associated with the hexagonal crystal system and lattice are given in Table 12.

Table 12: The space groups associated with the hexagonal crystal system and lattice.

168. $P6$	169. $P6_1$	170. $P6_5$
171. $P6_2$	172. $P6_4$	173. $P6_3$
174. $P\bar{6}$	175. $P6/m$	176. $P6_3/m$
177. $P622$	178. $P6_122$	179. $P6_522$
180. $P6_222$	181. $P6_422$	182. $P6_322$
183. $P6mm$	184. $P6cc$	185. $P6_3cm$
186. $P6_3mc$	187. $P\bar{6}m2$	188. $P\bar{6}c2$
189. $P\bar{6}2m$	190. $P\bar{6}2c$	191. $P6/mmm$
192. $P6/mcc$	193. $P6_3/mcm$	194. $P6_3/mmc$

10. The Cubic Crystal System

The cubic crystal system is defined as having the symmetry of a cube: the conventional unit cell can be rotated by 90° about any axis, or by 180° around an axis running through the center of two opposing cube edges, or by 120° around a body diagonal, and retain the same shape. The conventional cell then takes the form

$$\begin{aligned} \mathbf{A}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{A}_2 &= a\,\hat{\mathbf{y}} \\ \mathbf{A}_3 &= a\,\hat{\mathbf{z}}, \end{aligned} \tag{53}$$

with unit cell volume

$$V = a^3. \tag{54}$$

This is the limiting case of both the orthorhombic (26) and tetragonal (39) systems when all primitive vectors are equal in length. There are three Bravais lattices in the cubic system.

Figure 8: The conventional, simple, face-centered, and and body-centered unit cells for the cubic crystal system.

10.1. Lattice 12: Simple Cubic

The simple cubic system is identical to the conventional cubic unit cell

$$\begin{aligned} \mathbf{a}_1 &= a\,\hat{\mathbf{x}} \\ \mathbf{a}_2 &= a\,\hat{\mathbf{y}} \\ \mathbf{a}_3 &= a\,\hat{\mathbf{z}}, \end{aligned} \tag{55}$$

with volume

$$V = a^3. \tag{56}$$

This can also be considered as a rhombohedral lattice (48) with $\alpha = \pi/2$. The space groups associated with this lattice are given in Table 13.

Table 13: The space groups associated with the simple cubic lattice (55).

195. $P23$	198. $P2_13$	200. $Pm\bar{3}$
201. $Pn\bar{3}$	205. $Pa\bar{3}$	207. $P432$
208. $P4_232$	212. $P4_332$	213. $P4_132$
215. $P\bar{4}3m$	218. $P\bar{4}3n$	221. $Pm\bar{3}m$
222. $Pn\bar{3}n$	223. $Pm\bar{3}n$	224. $Pn\bar{3}m$

10.2. Lattice 13: Face-Centered Cubic

The face-centered cubic lattice can be derived from its predecessors in the orthorhombic and tetragonal systems, having the same periodicity as its simple cubic parent with the addition of a translation from one corner of the cube to the center of any face. Our standard face-centered cubic primitive vectors have the form

$$\mathbf{a}_1 = \frac{a}{2}\hat{\mathbf{y}} + \frac{a}{2}\hat{\mathbf{z}} \tag{57}$$

$$\mathbf{a}_2 = \frac{a}{2}\hat{\mathbf{x}} + \frac{a}{2}\hat{\mathbf{z}} \tag{58}$$

$$\mathbf{a}_3 = \frac{a}{2}\hat{\mathbf{x}} + \frac{a}{2}\hat{\mathbf{y}}, \tag{59}$$

and the primitive cell volume is

$$V = \frac{a^3}{4}. \tag{60}$$

There are four face-centered cubic primitive cells in the conventional cubic cell. The face-centered cubic lattice can be considered as a rhombohedral lattice where $\alpha = 60°$. The space groups associated with this lattice are given in Table 14.

Table 14: The space groups associated with the face-centered cubic lattice (57).

196. $F23$	202. $Fm\bar{3}$	203. $Fd\bar{3}$
209. $F432$	210. $F4_132$	216. $F\bar{4}3m$
219. $F4\bar{3}c$	225. $Fm\bar{3}m$	226. $Fm\bar{3}c$
227. $Fd\bar{3}m$	228. $Fd\bar{3}c$	

10.3. Lattice 14: Body-Centered Cubic

Like its predecessors in the orthorhombic and tetragonal systems, the body-centered cubic crystal has the same periodicity as its parent with the addition of a translation from one corner of the cube to its center. Our standard body-centered cubic primitive vectors have the form

$$\mathbf{a}_1 = -\frac{a}{2}\hat{\mathbf{x}} + \frac{a}{2}\hat{\mathbf{y}} + \frac{a}{2}\hat{\mathbf{z}} \tag{61}$$

$$\mathbf{a}_2 = \frac{a}{2}\hat{\mathbf{x}} - \frac{a}{2}\hat{\mathbf{y}} + \frac{a}{2}\hat{\mathbf{z}} \tag{62}$$

$$\mathbf{a}_3 = \frac{a}{2}\hat{\mathbf{x}} + \frac{a}{2}\hat{\mathbf{y}} - \frac{a}{2}\hat{\mathbf{z}}, \tag{63}$$

and the primitive cell volume is

$$V = \frac{a^3}{2}. \tag{64}$$

There are two body-centered cubic primitive cells in the conventional cubic cell. The body-centered cubic lattice can be considered as a rhombohedral lattice where $\alpha = \cos^{-1}(-1/3) \approx 109.47°$. The space groups associated with this lattice are given in Table 15.

Table 15: The space groups associated with the body-centered cubic lattice (61).

197. $I23$	199. $I2_13$	204. $Im\bar{3}$
206. $Ia\bar{3}$	211. $I432$	214. $I4_132$
217. $I\bar{4}3m$	220. $I\bar{4}3d$	229. $Im\bar{3}m$
230. $Ia\bar{3}d$		

11. Locating the atoms in the unit cell

Section 3 describes the Bravais lattices that occur in three dimensional space. Just describing the lattice, however, does not describe the complete crystal system. We must also find the positions of the atoms in the primitive (or conventional) unit cell. These positions are restricted by the crystal system, Bravais lattice, and space group that the system is in.

We will illustrate this using our two-dimensional centered rectangular lattice (17). There are seventeen plane groups in two dimensions [44]. Two are centered rectangular plane groups, $c1m1$ (#5) and $c2mm$ (#9). If we look at the International Tables [16] or Bilbao server [17], we will find a table that looks much like Table 16.

Table 16: The Wyckoff positions for the plane group $c1m1$ (#5). This is a somewhat simplified version of the table, as we neglect the site symmetries of each point. See Refs. [16] and [17] for complete information.

Wyckoff Position	Coordinates +(1/2, 1/2)
(4b)	(x,y) (-x, y)
(2a)	(0,y)

This table gives a set of Wyckoff positions, so called because Wyckoff denoted all possible positions for the 230

three dimensional space groups [40]. The first set of points (4b) refer to the general points for the $c1m1$ system, and refer to atomic positions based on the conventional rectangular unit cell (16).[9] This says that there are atoms located at two basis vectors

$$\begin{aligned} \mathbf{B}_1 &= \quad x\,\mathbf{A}_1 + y\,\mathbf{A}_2 \quad = x\,a\,\hat{\mathbf{x}} + y\,b\,\hat{\mathbf{y}} \\ \mathbf{B}_2 &= -x\,\mathbf{A}_1 + y\,\mathbf{A}_2 \quad = -x\,a\,\hat{\mathbf{x}} + y\,b\,\hat{\mathbf{y}}. \end{aligned} \tag{65}$$

Note, however, the "Coordinates +(1/2, 1/2)" entry in Table 16. This means that each position (x, y) has a duplicate position at $(1/2+x, 1/2+y)$, giving rise to two more atomic positions

$$\begin{aligned} \mathbf{B}_1' &= \left(\frac{1}{2}+x\right)\mathbf{A}_1 + \left(\frac{1}{2}+y\right)\mathbf{A}_2 \\ &= \left(\frac{1}{2}+x\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}+y\right)b\,\hat{\mathbf{y}} \\ \mathbf{B}_2' &= \left(\frac{1}{2}-x\right)\mathbf{A}_1 + \left(\frac{1}{2}+y\right)\mathbf{A}_2 \\ &= \left(\frac{1}{2}-x\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}+y\right)b\,\hat{\mathbf{y}}. \end{aligned} \tag{66}$$

This extra shift of $(1/2, 1/2)$ occurs because plane group $c1m1$ is defined on a centered rectangular lattice, and this shift gives the extra atomic positions in the conventional unit cell. We can see this by setting $x = y = 0$ in (66), as then both vectors correspond to primitive vector $\mathbf{a}_2$ in the Bravais lattice (17). Indeed, we can express the atomic positions in terms of $\mathbf{a}_1$ and $\mathbf{a}_2$:

$$\begin{aligned} \mathbf{B}_1 &= (x_1 - y_1)\,\mathbf{a}_1 + (x_1 + y_1)\,\mathbf{a}_2 \\ &= x_1\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} \\ \mathbf{B}_2 &= -(x_1 + y_1)\,\mathbf{a}_1 + (y_1 - x_1)\,\mathbf{a}_2 \\ &= \left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}+y_1\right)b\,\hat{\mathbf{y}}. \end{aligned} \tag{67}$$

What about the other line in Table 16? If we set $x = 0$, the (4b) Wyckoff positions both become $(0, y)$, which means that instead of two atoms in the primitive cell, only one is allowed. In the conventional cell there are two such atoms, so this is known as the (2a) Wyckoff position. In terms of the primitive Bravais lattice this atom is located at

$$\mathbf{B}_3 = \quad -y_2\,\mathbf{a}_1 + y_2\,\mathbf{a}_2 \quad = y_2\,b\,\hat{\mathbf{y}}. \tag{68}$$

One possible arrangement of this crystal system is shown in Figure 9. The squares represent (4b) atoms, while the diamonds are (2a) atoms. There are two (2a) atoms and four (4b) atoms in each conventional unit cell, bounded by the solid lines, and one (2a) atom and two (4b) atoms in each primitive cell, bounded by the dashed lines.

Figure 9: A two-dimensional centered rectangular crystal system in plane group $c1m1$.

Table 16 could easily have been written with (4b) positions (x, y) $(x, -y)$ and (4a) positions $(x, 0)$, *i.e.* we could have rotated the lattice by 90°. The choice made here is a matter of convention. This convention persists in the three dimensional case, and explains why some base-centered orthorhombic space groups (Table 5) use the "A" orientation rather than the "C" orientation. For example, space group Amm2 (#38) has the (2a) Wyckoff position $(00z)$. If we used the equivalent space group C2mm, the resulting Wyckoff position would be $(x00)$. Keeping with convention demands that we rotate the system.

In the listings below, we will follow convention by giving the lattice coordinates $(a, b, c, \alpha, \beta, \gamma)$ in terms of the conventional lattice for the crystal system, and the atomic positions in terms of the coordinates of the corresponding Wyckoff position. However, we will describe the unit cell using the Bravais vectors of the primitive lattices in Section 3, and describe the lattice coordinates of an atom relative to the these vectors. The lattice coordinates of atom $\mathbf{B}_1$, above, will be given as $(x - y), (x + y)$. Finally, we will only list atomic positions in the primitive cell, not the conventional unit cell. This means, *e.g.*, that we will only give the positions of four atoms for a Wyckoff position of (8c) for a body-centered orthorhombic cell.

12. Description of a Database Entry

The current database consists of 288 entries. This section describes the format of a database entry, as well as an outline of the CIF and POSCAR files.

[9] Wyckoff positions are labeled by letter in descending order, from the most general symmetry to the most restrictive. Space group $Pm\bar{3}n$ (#223), for example, has twelve Wyckoff positions. The most general, which has forty-eight operations, is labeled (48l). Space group *Pmmm* (#47) has twenty seven Wyckoff positions, so its most general one is denoted (8A).

12.1. The Database

For each structure in the database, we have

Title: The title gives a brief description of the entry. If available this will include the mineral name, chemical formula, and the *Strukturbericht* Designation. In the case where an element or compound exists in multiple phases, the title may also list the space group, if that is necessary to distinguish one phase from another.

Diagrams: Four different views are shown for the structure: along each axis, and a tilted view. The boundaries of the conventional unit cell are also shown. For cells with trigonal (including rhombohedral) and hexagonal symmetry we also show two views of the structure containing three conventional cells. This allows us to see the full trigonal/hexagonal symmetry of the system.

Prototype: Each structure has a prototype compound which represents all compounds with that structure. For example, the prototype of the rock salt structure is NaCl.

AFLOW prototype label: The standardized name of a prototype, including stoichiometry, Pearson symbol, space group, and Wyckoff positions of the atoms.

***Strukturbericht* designation:** This gives the *Strukturbericht* symbol for the structure, if one is defined.

Pearson symbol: These were defined by W. B. Pearson [9] to give a shorthand description of a crystal structure. A Pearson symbol has three parts

1. *The crystal system* designates each crystal system by a letter:
   - 1.1. *a*: The triclinic system
   - 1.2. *m*: The monoclinic system
   - 1.3. *o*: The orthorhombic system
   - 1.4. *t*: The tetragonal system
   - 1.5. *h*: The trigonal and hexagonal system, combined
   - 1.6. *c*: The cubic system
2. *The lattice type* designates the type of lattice in the crystal system:
   - 2.1. *P*: A primitive (simple) lattice. Used when the primitive and conventional lattices are identical
   - 2.2. *C*: A base-centered lattice. The label could be A, B, or C, depending upon the base chosen, but C is usually chosen for all orientations. To avoid confusion, the symbol "S" is often used in place of C.
   - 2.3. *I*: A body-centered lattice
   - 2.4. *F*: A face-centered lattice
   - 2.5. *R*: A rhombohedral lattice
3. *The number of atoms* in the cell is given in the final field. For most systems this is *in the conventional cell*. As an example, consider copper, which is the prototype for the face-centered cubic (*Strukturbericht* A1) system. It has a face-centered cubic lattice, with one atom in the primitive cell. This means that there are four atoms in the conventional cubic cell, so the Pearson symbol of copper is $cF4$.

   An exception arises for the rhombohedral structure. If a rhombohedral system has five atoms in the primitive cell, then the Pearson Symbol might be hR5 or hR15, the number of atoms in the conventional hexagonal unit cell. This depends upon the author. We will use the number of atoms in the primitive cell. The AFLOW framework does the same [21, 22, 23, 24].

   A further complication arises because the number of atoms in the Pearson symbol might be replaced by the number of formula units. Wurtzite (*Strukturbericht* B4) is a hexagonal crystal, with two atoms of sulfur and two atoms of zinc. Its Pearson symbol is hR4. However, there are two Zn-S units in the cell, so it is often referred to as 2H. While this is not strictly a Pearson symbol, it is Pearson-like, and one must be aware of the difference.

Space group number: The crystal's space group in the International Tables.

Space group symbol: We use the International Tables' space group symbol, in the standard orientation.

AFLOW prototype command: The command used to generate this structure in the AFLOW [21, 22, 23, 24] software system. The choice of the prototype is performed with the keyword `--proto=label` where the label is the standardized name. The prototype's degrees of freedom, internal and external, are specified with the keyword `--params=parameter_1,parameter_2,...` with the parameters separated by commas. Note that while most prototype labels are unique, there are a few cases where the same geometrical structure could be generated through more than one prototype by modifying the parameters. By default, the `--proto` keyword generates structures where the species are fictitiously taken as *A*, *B*, *C*, etc. The user can override their order using the following syntax: `--proto=label:A:B:C...` (after the colon ":" any permutation of *A*, *B*, *C*... separated by colons ":"). The user can also associate the same

species with two or more different types using the following syntax: `--proto=label:A:A:B...` or use real element names using the following syntax: `--proto=label:Ag:Cd:Zr...`. After the generation of the prototype, the software will alphabetically reorder the atoms. Note that the total number of specified species (if provided) and parameters need to correspond to the exact requirements of the prototype otherwise AFLOW will prematurely terminate with an error message.[10]

Rhombohedral systems : All crystal structures are generated in AFLOW using the specifications of this document. Rhombohedral systems can be represented in either the rhombohedral or hexagonal settings. While the default is rhombohedral, a user can obtain the hexagonal setting by using the optional keyword `--hex`.

Reference: The journal article for the structure. If the structure was found in one of the standard locations (Pearson's Handbook, Pauling File, AMCD, *etc.*) then the reference to that entry is also given, under the label **Found in**.

Other compounds (elements) with this structure: One prototype phase may be observed with many different chemical compositions. This item provides a partial list for some compounds. *Pearson's Handbook* [10] provides a detailed list for intermetallic compounds.

Primitive vectors: Primitive vectors are given in the standard orientations listed in Section 2. A small figure next to the listing of the vectors shows the primitive vectors as well as outlining the primitive and conventional cells of the structure.

Basis vectors: The position of each atom in the primitive cell is defined by its

1. *Lattice Vector*: The label $\mathbf{B}_N$, where N is the number of the atom in the primitive cell.
2. *Lattice Coordinates:* Lattice coordinates are determined from the Cartesian coordinates of the system using (11).
3. *Cartesian Coordinates:* These are determined from the Wyckoff positions and the lattice parameters of the conventional primitive cell. If the Wyckoff position of a particular site is (x_n, y_n, z_n), the Cartesian coordinates will be determined from the position

$$x_n \mathbf{A}_1 + y_n \mathbf{A}_2 + z_n \mathbf{A}_3,$$

where the $\mathbf{A}_i$, describe the conventional unit cell. An exception is again made for rhombohedral structures, where we use the rhombohedral setting of the space group and vectors (48) to expand into Cartesian coordinates.

Each Wyckoff position in the crystal is given a subscript, *e.g.* the third Wyckoff position in a given structure will have coordinates (x_3, y_3, z_3). A coordinate fixed by symmetry is replaced by its value, so x_2 is replaced by zero in (68).

4. *The Wyckoff Position:* From the International Tables. There may be multiple instances of a given Wyckoff position in a structure. Although the number in the Wyckoff position indicates the number of atoms in the conventional cell, we will only give the basis vectors for atoms in the primitive cell.
5. *The Atomic Label:* The chemical symbol for the atom at the current site. If there are multiple Wyckoff positions with the same species of atom, a Roman numeral appears after the atom type. For example, if a structure has oxygen atoms on (2e) and (4f) Wyckoff positions, the oxygen atoms on the (2e) site will be labeled "O I," while the atoms on the (4f) site will be labeled "O II."

12.2. Visualization

Each structure is accompanied by a graphic showing the conventional unit cell of the structure looking down each of the cell's primitive vectors, and in an oblique representation which provides an overall view of the structure. These figures were drawn from the accompanying CIF file using `Jmol` [45].

12.3. The Crystallographic Information File (CIF)

The Crystallographic Information File [31] (CIF) is the standard method for crystallographic information interchange. There is a CIF file for the prototype material of each structure, generated by `FINDSYM` [46], and modified by us to include the references in CIF format. The CIF file can be used for visualization, and programs such as CIF2cell [47] can use it to generate input for electronic structure programs. Note, the coordinates in the CIF may not exactly match the coordinates in the reference. Some coordinates may have been shifted for visualization purposes. We use the following features of the CIF format:

_chemical_name_mineral: The common name of the structure, if one exists

_chemical_formula_sum: The chemical formula of the structure, in computer readable form, *e.g.* $KClO_3$ would be written K Cl O3.

_publ_author_name: The authors of the reference

[10] Generation of the prototypes presented in this article is supported by the AFLOW software v3.2 and above.

journal...: Entries describing the journal reference, including name, and publication year, first and last page.

_publ_Section_title: The title of the article.

 # Found in: If we found the reference via another source, that source is given here. This is not part of the CIF standard, hence the hashtag.

_aflow_proto: The AFLOW command to generate the structure.

_aflow_params: The AFLOW parameters indicating the degrees of freedom required to generate the structure.

_aflow_params_values: The values of the AFLOW parameters used to generate the particular structure prototype.

_aflow_Strukturbericht: The Strukturbericht designation of the structure.

_aflow_Pearson: The Pearson symbol of the structure.

_symmetry_space_group_name_Hall: The name of the space group in Hall notation.

_symmetry_space_group_name_H-M: The name of the space group in Hermann-Mauguin notation.

_symmetry_Int_Tables_number: The number of the space group in the International Tables.

_cell_length_(abc): The lengths (13) of the primitive vectors of the unit cell, in Ångstroms.

_cell_angle_(alpha beta gamma): The angles (14) between the primitive vectors, in degrees.

_space_group_symop_operation_xyz: The combination of rotations, reflections, and translations allowed for the space group. For example, an entry for the two-dimensional $c1m1$ space group in Table 16 would have the form

```
1 x,y
2 -x,y
3 x+1/2,y+1/2
4 -x+1/2,y+1/2
```

so that the complete crystal structure can be determined from this table and the atomic Wyckoff positions at the end of the CIF file.

_atom_site_...: This describes the atomic positions of the atoms at each Wyckoff site in the crystal. There is one entry for each occupied Wyckoff position, the remaining atoms are derived from the space group operations above. Each line contains:

1. A label, usually the atom type with a number.
2. The atomic symbol for the atom occupying this position in the crystal.
3. The multiplicity of the Wyckoff site, for example, if the site was "2e" the number here would be "2."
4. The Wyckoff label, in our example "e."
5. The x, y, and z coordinates of the atom, usually written to five decimal places.
6. The occupancy, to allow for partially filled sites.

A proper CIF file completely describes a crystal. The standard even allows for a complete article to be submitted as a CIF file.

12.4. The POSCAR File

By default, the prototype is generated in the POSCAR format, which is the standard description of a crystallographic system used in VASP [32]. While the information it provides is identical to that in the CIF file, we list it here because it explicitly shows the construction of the primitive unit cell and the positions of all the atoms in the unit cell. The POSCAR files provided in the database are an annotated version of the VASP format for the prototype material, and can easily be edited for use with other materials with the same space group and occupied Wyckoff positions. A typical example is for pyrite, FeS_2:

```
AB2_cP12_205_a_c & \\
a,x2 --params=5.417,0.3851 & Pa-3 T_h^6 \\
#205 (ac) & cP12 & C2 & FeS2 & Pyrite & \\
Bayliss, Am. Min. 62, 1168-72 (1977)
1.0000000000000000
5.41700 0.00000 0.00000
0.00000 5.41700 0.00000
0.00000 0.00000 5.41700
Fe S
4 8
Direct
0.00000 0.00000 0.00000 Fe (4a)
0.00000 0.50000 0.50000 Fe (4a)
0.50000 0.00000 0.50000 Fe (4a)
0.50000 0.50000 0.00000 Fe (4a)
0.11490 0.61490 0.88510 S (8c)
0.11490 0.88510 0.38510 S (8c)
0.38510 0.11490 0.88510 S (8c)
0.38510 0.38510 0.38510 S (8c)
0.61490 0.61490 0.61490 S (8c)
0.61490 0.88510 0.11490 S (8c)
0.88510 0.11490 0.61490 S (8c)
0.88510 0.38510 0.11490 S (8c)
```

1. The first line, separated into four lines here, has eight fields, separated by ampersands:

1.1. The first field contains the AFLOW prototype label for this structure.

1.2. The second field contains the AFLOW parameters that have degrees of freedom and the values needed to create this structure.

1.3. The third field contains the space group name, both in International and Schönflies formats, the space group number, and the Wyckoff positions occupied in this structure.

1.4. The fourth field is the Pearson symbol.

1.5. The fifth field is the *Strukturbericht* designation, if any.

1.6. The sixth field is the prototype's chemical formula.

1.7. The seventh field is the mineral name, if known; or, in the case of substances with multiple phases, the phase name, *e.g.* "alpha" or "beta".

1.8. The final field is an abbreviated reference for the structure.

2. The second line is a scale factor. All Cartesian components in the lines below are multiplied by this factor.

3. The third, fourth, and fifth lines contain the Cartesian components of the primitive vectors, one per line. If the scale factor in line two is unity, these distances are in Ångstroms.

4. The sixth line (only in VASP version 5 and above) gives the names of the elements in the unit cell. We list the elements in alphabetical order by chemical symbol. The VASP POTCAR file must also list the elements in this order.

5. The seventh line contains the number of atoms of each element type, in the same order as the previous line.

6. `Direct` in line eight indicates that the atomic positions are in lattice coordinates. We will always use this form.

7. The remaining lines list the positions of the atoms in the primitive cell, one line per atom. The three numbers are the lattice coordinates. In our annotated file this is followed by the atomic label, and then the Wyckoff position occupied. The atoms are ordered by species, in agreement with lines six and seven.

While the POSCAR file is unique to VASP other electronic structure codes use similar formats and the information in the POSCAR can be easily converted into the required form. If this is not possible, programs such as CIF2cell [47] can use the CIF file to generate the electronic structure input in a variety of forms.

12.5. Quantum ESPRESSO*, ABINIT, and FHI-AIMS Formats*

The user can generate prototypes in the Quantum ESPRESSO[48], ABINIT [49], and FHI-AIMS [50] formats with the keywords `--qe`, `--abinit`, or `--aims`, respectively. Example: `aflow --proto=label --params=... --qe`. Other formats will be added in the future.

13. Conclusion

This article presents *The AFLOW Library of Crystallographic Prototypes*, an updated version of the original *Crystal Lattice Structures* web page. We present a complete description of 288 crystal structures, including the space group, Pearson and *Strukturbericht* symbols, primitive vectors, basis vectors, and references to the literature.

14. Acknowledgments

The authors would like to thank D. A. Papaconstantopoulos, who first proposed the *Crystal Lattice Structures* database, and R. Benjamin Young, who help set up the original web site in the summer of 1995. Special thanks are due to the H. Stokes, for providing updates to the `FINDSYM` code, and to the librarians at the U.S. Naval Research Laboratory Ruth H. Hooker Research Library, who tracked down many dozens of research articles which are not yet available online. M. J. Mehl is supported under contract from Duke University. We also acknowledge support by the by DOD-ONR (N00014-13-1-0635, N00014-15-1-2863, N00014-16-1-2781). C. Toher and S. Curtarolo acknowledge partial support from the DOE (DE-AC02-05CH11231), specifically the Basic Energy Sciences program under Grant #ED-CBEE. D. Hicks acknowledges support from the Department of Defense through the National Defense Science and Engineering Graduate (NDSEG) Fellowship Program. The AFLOW consortium would like to acknowledge the Duke University Center for Materials Genomics and the CRAY corporation for computational support.

References

[1] W. H. Bragg and W. L. Bragg, *The Structure of Diamond*, Proc. R. Soc. A Math. Phys. Eng. Sci. **89**, 277–291 (1913), doi:10.1098/rspa.1913.0084.

[2] W. P. Davey, *The Lattice Parameter and Density of Pure Tungsten*, Phys. Rev. **26**, 736–738 (1925), doi:10.1103/PhysRev.26.736.

[3] P. P. Ewald, K. Herrman, C. Herman, O. Lohrmann, H. Philipp, G. Gottfried, and F. Schossberger, eds., *Strukturbericht 1913-1939*, vol. I-VII (Akademische Verlagsgesellschaft M. B. H., 1931-1943).

[4] E. A. Owen and Y. H. Liu, *The Thermal Expansion of the Gold-Copper Alloy* $AuCu_3$, Philos. Mag. **38**, 354–360 (1947), doi:10.1080/14786444708521607.

[5] K. Remschnig, T. Le Bihan, H. Noël, and P. Rogl, *Structural chemistry and magnetic behavior of binary uranium silicides*, J. Solid State Chem. **97**, 391–399 (1992), doi:10.1016/0022-4596(92)90048-Z.

[6] A. J. C. Wilson, W. B. Pearson, J. Trotter, G. Ferguson, et al., eds., *Structure Reports*, vol. 8-57 (International Union of Crystallography, 1940-1990).

[7] R. W. G. Wyckoff, *The Structure of Crystals*, vol. I-VI (John Wiley & Sons, New York, London, Sydney, 1963 - 1971), 2nd edn.

[8] B. J. Skinner, *Unit-Cell Edges of Natural and Synthetic Sphalerites*, Am. Mineral. **46**, 1399–1411 (1961).

[9] W. B. Pearson, *A handbook of lattice spacings and structures of metals and alloys* (Pergamon Press, New York, 1958).

[10] P. Villars and L. D. Calvert, eds., *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, Ohio, 1991), 2nd edn.

[11] W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley-Interscience, New York, London, Sydney, Toronto, 1972).

[12] FIZ Karlsruhe, *Inorganic Crystal Structure Database*, http://icsd.fiz-karlsruhe.de/icsd/.

[13] R. T. Downs and M. Hall-Wallace, *The American Mineralogist crystal structure database*, Am. Mineral. **88**, 247–250 (2003).

[14] P. Villars, *Linus Pauling File* Materials Phases Data System (MPDS).

[15] M. D. Graef and M. McHenry, *The Structure of Materials*, http://som.web.cmu.edu/frames2.html.

[16] T. Hahn, ed., *International Tables for Crystallography*, vol. A: Space-group symmetry (International Union of Crystallography, 2006), doi:10.1107/97809553602060000100.

[17] M. I. Aroyo, J. M. Perez-Mato, D. Orobengoa, E. Tasci, G. de la Flor, and A. Kirov, *Crystallography online: Bilbao crystallographic server*, Bulg. Chem. Commun. **43**, 183–197 (2011).

[18] M. I. Aroyo, J. M. Perez-Mato, C. Capillas, E. Kroumova, S. Ivantchev, G. Madariaga, A. Kirov, and H. Wondratschek, *Bilbao Crystallographic Server: I. Databases and crystallographic computing programs*, Zeitschrift für Kristallographie - Crystalline Materials **221**, 15–27 (2006), doi:10.1524/zkri.2006.221.1.15.

[19] M. I. Aroyo, A. Kirov, C. Capillas, J. M. Perez-Mato, and H. Wondratschek, *Bilbao Crystallographic Server. II. Representations of crystallographic point groups and space groups*, Acta Crystallogr. Sect. A **62**, 115–128 (2006), doi:10.1107/S0108767305040286.

[20] S. Curtarolo, G. L. W. Hart, M. Buongiorno Nardelli, N. Mingo, S. Sanvito, and O. Levy, *The high-throughput highway to computational materials design*, Nat. Mater. **12**, 191–201 (2013), doi:10.1038/nmat3568.

[21] S. Curtarolo, W. Setyawan, G. L. W. Hart, M. Jahnátek, R. V. Chepulskii, R. H. Taylor, S. Wang, J. Xue, K. Yang, O. Levy, M. J. Mehl, H. T. Stokes, D. O. Demchenko, and D. Morgan, *AFLOW: an automatic framework for high-throughput materials discovery*, Comput. Mater. Sci. **58**, 218–226 (2012), doi:10.1016/j.commatsci.2012.02.005.

[22] S. Curtarolo, W. Setyawan, S. Wang, J. Xue, K. Yang, R. H. Taylor, L. J. Nelson, G. L. W. Hart, S. Sanvito, M. Buongiorno Nardelli, N. Mingo, and O. Levy, *AFLOWLIB.ORG: A distributed materials properties repository from high-throughput ab initio calculations*, Comput. Mater. Sci. **58**, 227–235 (2012), doi:10.1016/j.commatsci.2012.02.002.

[23] C. E. Calderon, J. J. Plata, C. Toher, C. Oses, O. Levy, M. Fornari, A. Natan, M. J. Mehl, G. L. W. Hart, M. Buongiorno Nardelli, and S. Curtarolo, *The AFLOW standard for high-throughput materials science calculations*, Comput. Mater. Sci. **108 Part A**, 233–238 (2015), doi:10.1016/j.commatsci.2015.07.019.

[24] O. Levy, G. L. W. Hart, and S. Curtarolo, *Uncovering Compounds by Synergy of Cluster Expansion and High-Throughput Methods*, J. Am. Chem. Soc. **132**, 4830–4833 (2010).

[25] A. Jain, G. Hautier, C. J. Moore, S. P. Ong, C. C. Fischer, T. Mueller, K. A. Persson, and G. Ceder, *A high-throughput infrastructure for density functional theory calculations*, Comput. Mater. Sci. **50**, 2295–2310 (2011), doi:10.1016/j.commatsci.2011.02.023.

[26] J. E. Saal, S. Kirklin, M. Aykol, B. Meredig, and C. Wolverton, *Materials Design and Discovery with High-Throughput Density Functional Theory: The Open Quantum Materials Database (OQMD)*, JOM **65**, 1501–1509 (2013), doi:10.1007/s11837-013-0755-4.

[27] M. Scheffler, C. Draxl, and Computer Center of the Max-Planck Society, Garching, *The NoMaD Repository*: http://nomad-repository.eu (2014).

[28] G. Pizzi, A. Cepellotti, R. Sabatini, N. Marzari, and B. Kozinsky, *AiiDA: automated interactive infrastructure and database for computational science*, Comput. Mater. Sci. **111**, 218–230 (2016).

[29] M. de Jong, W. Chen, T. Angsten, A. Jain, R. Notestine, A. Gamst, M. Sluiter, C. K. Ande, S. van der Zwaag, J. J. Plata, C. Toher, S. Curtarolo, G. Ceder, K. A. Persson, and M. D. Asta, *Charting the Complete Elastic properties of Inorganic Crystalline Compounds*, Sci. Data **2**, 150009 (2015), doi:10.1038/sdata.2015.9.

[30] C. Toher, J. J. Plata, O. Levy, M. de Jong, M. D. Asta, M. Buongiorno Nardelli, and S. Curtarolo, *High-throughput computational screening of thermal conductivity, Debye temperature and Grüneisen parameter using a quasi-harmonic Debye model*, Phys. Rev. B **90**, 174107 (2014), doi:10.1103/PhysRevB.90.174107.

[31] S. R. Hall and B. McMahon, eds., *International Tables for Crystallography*, vol. G: Definition and exchange of crystallographic data (International Union of Crystallography, 2006), doi:10.1107/97809553602060000107.

[32] G. Kresse and J. Hafner, Ab initio *molecular dynamics for open-shell transition metals*, Phys. Rev. B **48**, 13115–13118 (1993), doi:10.1103/PhysRevB.48.13115.

[33] M. Lax, *Symmetry Principles in Solid State and Molecular Physics* (J. Wiley, New York, 1974).

[34] N. W. Ashcroft and N. D. Mermin, *Solid State Physics* (Holt, Reinhart and Winston, New York, 1976).

[35] C. Barrett and T. B. Massalski, *Structure of Metals – Crystallographic Methods, Principles, and Data*, *International Series on Materials Science and Technology*, vol. 35 (Pergammon Press, Oxford, New York, 1980), 3rd revised edn.

[36] C. Kittel, *Introduction to Solid State Physics* (John Wiley & Sons, New York, 1996), 7th edn.

[37] M. Lax, *Symmetry Principles in Solid State and Molecular Physics* (J. Wiley, New York, 1974), chap. 6, pp. 169–175.

[38] E. S. Fedorov, *Symmetry of Crystals*, no. 7 in American Crystallographic Association Monograph (American Crystallographic Association, Buffalo NY, 1971). Translated from the original 1891 Russian publication by David and Katherine Harker.

[39] A. M. Schönflies, *Theorie der Kristallstruktur* (Gebr. Bornträger, Berlin, 1891).

[40] R. W. G. Wyckoff, *The Analytical Expression of the Results of the Theory of Space Groups*, vol. 318 (Carnegie Institution of Washington, Washington DC, 1922).

[41] J. K. Cockcroft, *A Hypertext Book of Crystallographic Space Group Diagrams and Tables* (Birkbeck College, University of London, 1999).

[42] W. Setyawan and S. Curtarolo, *High-throughput electronic band structure calculations: Challenges and tools*, Comput. Mater. Sci. **49**, 299–312 (2010), doi:10.1016/j.commatsci.2010.05.010.

[43] N. W. Ashcroft and N. D. Mermin, *Solid State Physics* (Holt, Reinhart and Winston, 1976), chap. 7, pp. 115–117.

[44] A. Nelson, H. Newman, and M. Shipley, *17 Plane Symmetry Groups* (2012). From the Andres Caicedo Teaching Blog.

[45] R. M. Hanson, J. Prilusky, Z. Renjian, T. Nakane, and J. L. Sussman, *Jmol* An open-source Java viewer for chemical structures in 3D.

[46] H. T. Stokes and D. M. Hatch, FINDSYM*: program for identifying the space-group symmetry of a crystal*, J. Appl. Crystallogr. **38**, 237–238 (2005), doi:10.1107/S0021889804031528.

[47] T. Björkman, `CIF2Cell` Available from SourceForge.

[48] P. Giannozzi, S. Baroni, N. Bonini, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, G. L. Chiarotti, M. Cococcioni, I. Dabo, A. D. Corso, S. de Gironcoli, S. Fabris, G. Fratesi, R. Gebauer, U. Gerstmann, C. Gougoussis, A. Kokalj, M. Lazzeri, L. Martin-Samos, N. Marzari, F. Mauri, R. Mazzarello, S. Paolini, A. Pasquarello, L. Paulatto, C. Sbraccia1, S. Scandolo, G. Sclauzero, A. P. Seitsonen, A. Smogunov, P. Umari, and R. M. Wentzcovitch, *QUANTUM ESPRESSO: a modular and open-source software project for quantum simulations of materials*, J. Phys. Condens. Matter **21**, 395502 (2009).

[49] X. Gonze, J. M. Beuken, R. Caracas, F. Detraux, M. Fuchs, G. M. Rignanese, L. Sindic, M. Verstraete, G. Zerah, F. Jollet, M. Torrent, A. Roy, M. Mikami, P. Ghosez, J. Y. Raty, and D. Allan, *First-principles computation of material properties: the ABINIT software project*, Comput. Mater. Sci. **25**, 478–492 (2002), doi:10.1016/S0927-0256(02)00325-7.

[50] V. Blum, R. Gehrke, F. Hanke, P. Havu, V. Havu, X. Ren, K. Reuter, and M. Scheffler, *Ab initio molecular simulations with numeric atom-centered orbitals*, Comput. Phys. Commun. **180**, 2175–2196 (2009), doi:10.1016/j.cpc.2009.06.022.

FeS_2 (P1) Structure: AB2_aP12_1_4a_8a

Prototype	:	FeS_2
AFLOW prototype label	:	AB2_aP12_1_4a_8a
***Strukturbericht* designation**	:	None
Pearson symbol	:	aP12
Space group number	:	1
Space group symbol	:	P1
AFLOW prototype command	:	`aflow --proto=AB2_aP12_1_4a_8a` `--params=`$a, b/a, c/a, \alpha, \beta, \gamma, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8, x_9, y_9, z_9, x_{10}, y_{10}, z_{10}, x_{11}, y_{11}, z_{11}, x_{12}, y_{12}, z_{12}$

- This structure is just a slightly distorted version of pyrite (C2), with no rotational symmetry whatsoever.

Triclinic primitive vectors:

$$\mathbf{a}_1 = a\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\cos\gamma\,\hat{\mathbf{x}} + b\sin\gamma\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c_x\hat{\mathbf{x}} + c_y\,\hat{\mathbf{y}} + c_z\,\hat{\mathbf{z}}$$

$$c_x = c\,\cos\beta$$
$$c_y = c\,(\cos\alpha - \cos\beta\cos\gamma)/\sin\gamma$$
$$c_z = \sqrt{c^2 - c_x^2 - c_y^2}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + y_1\,b\,\cos\gamma + z_1\,c_x)\,\hat{\mathbf{x}} + \left(y_1\,b\,\sin\gamma + z_1\,c_y\right)\hat{\mathbf{y}} + z_1\,c_z\,\hat{\mathbf{z}}$	$(1a)$	Fe I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + y_2\,b\,\cos\gamma + z_2\,c_x)\,\hat{\mathbf{x}} + \left(y_2\,b\,\sin\gamma + z_2\,c_y\right)\hat{\mathbf{y}} + z_2\,c_z\,\hat{\mathbf{z}}$	$(1a)$	Fe II

$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + y_3\,b\,\cos\gamma + z_3\,c_x)\,\hat{\mathbf{x}} + \left(y_3\,b\,\sin\gamma + z_3\,c_y\right)\,\hat{\mathbf{y}} + z_3\,c_z\,\hat{\mathbf{z}}$	(1a)	Fe III
$\mathbf{B_4}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + y_4\,b\,\cos\gamma + z_4\,c_x)\,\hat{\mathbf{x}} + \left(y_4\,b\,\sin\gamma + z_4\,c_y\right)\,\hat{\mathbf{y}} + z_4\,c_z\,\hat{\mathbf{z}}$	(1a)	Fe IV
$\mathbf{B_5}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$(x_5\,a + y_5\,b\,\cos\gamma + z_5\,c_x)\,\hat{\mathbf{x}} + \left(y_5\,b\,\sin\gamma + z_5\,c_y\right)\,\hat{\mathbf{y}} + z_5\,c_z\,\hat{\mathbf{z}}$	(1a)	S I
$\mathbf{B_6}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + y_6\,b\,\cos\gamma + z_6\,c_x)\,\hat{\mathbf{x}} + \left(y_6\,b\,\sin\gamma + z_6\,c_y\right)\,\hat{\mathbf{y}} + z_6\,c_z\,\hat{\mathbf{z}}$	(1a)	S II
$\mathbf{B_7}$	=	$x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + y_7\,b\,\cos\gamma + z_7\,c_x)\,\hat{\mathbf{x}} + \left(y_7\,b\,\sin\gamma + z_7\,c_y\right)\,\hat{\mathbf{y}} + z_7\,c_z\,\hat{\mathbf{z}}$	(1a)	S III
$\mathbf{B_8}$	=	$x_8\,\mathbf{a_1} + y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$(x_8\,a + y_8\,b\,\cos\gamma + z_8\,c_x)\,\hat{\mathbf{x}} + \left(y_8\,b\,\sin\gamma + z_8\,c_y\right)\,\hat{\mathbf{y}} + z_8\,c_z\,\hat{\mathbf{z}}$	(1a)	S IV
$\mathbf{B_9}$	=	$x_9\,\mathbf{a_1} + y_9\,\mathbf{a_2} + z_9\,\mathbf{a_3}$	=	$(x_9\,a + y_9\,b\,\cos\gamma + z_9\,c_x)\,\hat{\mathbf{x}} + \left(y_9\,b\,\sin\gamma + z_9\,c_y\right)\,\hat{\mathbf{y}} + z_9\,c_z\,\hat{\mathbf{z}}$	(1a)	S V
$\mathbf{B_{10}}$	=	$x_{10}\,\mathbf{a_1} + y_{10}\,\mathbf{a_2} + z_{10}\,\mathbf{a_3}$	=	$(x_{10}\,a + y_{10}\,b\,\cos\gamma + z_{10}\,c_x)\,\hat{\mathbf{x}} + \left(y_{10}\,b\,\sin\gamma + z_{10}\,c_y\right)\,\hat{\mathbf{y}} + z_{10}\,c_z\,\hat{\mathbf{z}}$	(1a)	S VI
$\mathbf{B_{11}}$	=	$x_{11}\,\mathbf{a_1} + y_{11}\,\mathbf{a_2} + z_{11}\,\mathbf{a_3}$	=	$(x_{11}\,a + y_{11}\,b\,\cos\gamma + z_{11}\,c_x)\,\hat{\mathbf{x}} + \left(y_{11}\,b\,\sin\gamma + z_{11}\,c_y\right)\,\hat{\mathbf{y}} + z_{11}\,c_z\,\hat{\mathbf{z}}$	(1a)	S VII
$\mathbf{B_{12}}$	=	$x_{12}\,\mathbf{a_1} + y_{12}\,\mathbf{a_2} + z_{12}\,\mathbf{a_3}$	=	$(x_{12}\,a + y_{12}\,b\,\cos\gamma + z_{12}\,c_x)\,\hat{\mathbf{x}} + \left(y_{12}\,b\,\sin\gamma + z_{12}\,c_y\right)\,\hat{\mathbf{y}} + z_{12}\,c_z\,\hat{\mathbf{z}}$	(1a)	S VIII

References:

- P. Bayliss, *Crystal structure refinement of a weakly anisotropic pyrite*, Am. Mineral. **62**, 1168–1172 (1977).

Geometry files:

- CIF: pp. S638
- POSCAR: pp. S638

$AsKSe_2$ (P1) Structure: ABC2_aP16_1_4a_4a_8a

Prototype	:	$AsKSe_2$
AFLOW prototype label	:	ABC2_aP16_1_4a_4a_8a
***Strukturbericht* designation**	:	None
Pearson symbol	:	aP16
Space group number	:	1
Space group symbol	:	P1
AFLOW prototype command	:	`aflow --proto=ABC2_aP16_1_4a_4a_8a` `--params=`$a, b/a, c/a, \alpha, \beta, \gamma, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8, x_9, y_9, z_9, x_{10}, y_{10}, z_{10}, x_{11}, y_{11}, z_{11}, x_{12}, y_{12}, z_{12}, x_{13}, y_{13}, z_{13}, x_{14}, y_{14}, z_{14}, x_{15}, y_{15}, z_{15}, x_{16}, y_{16}, z_{16}$

Triclinic primitive vectors:

$$\mathbf{a}_1 = a\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\cos\gamma\,\hat{\mathbf{x}} + b\sin\gamma\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c_x\hat{\mathbf{x}} + c_y\,\hat{\mathbf{y}} + c_z\,\hat{\mathbf{z}}$$

$$c_x = c\,\cos\beta$$
$$c_y = c\,(\cos\alpha - \cos\beta\cos\gamma)/\sin\gamma$$
$$c_z = \sqrt{c^2 - c_x^2 - c_y^2}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + y_1\,b\,\cos\gamma + z_1\,c_x)\,\hat{\mathbf{x}} + \left(y_1\,b\,\sin\gamma + z_1\,c_y\right)\hat{\mathbf{y}} + z_1\,c_z\,\hat{\mathbf{z}}$	$(1a)$	As I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + y_2\,b\,\cos\gamma + z_2\,c_x)\,\hat{\mathbf{x}} + \left(y_2\,b\,\sin\gamma + z_2\,c_y\right)\hat{\mathbf{y}} + z_2\,c_z\,\hat{\mathbf{z}}$	$(1a)$	As II
$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + y_3\,b\,\cos\gamma + z_3\,c_x)\,\hat{\mathbf{x}} + \left(y_3\,b\,\sin\gamma + z_3\,c_y\right)\hat{\mathbf{y}} + z_3\,c_z\,\hat{\mathbf{z}}$	$(1a)$	As III
$\mathbf{B_4}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + y_4\,b\,\cos\gamma + z_4\,c_x)\,\hat{\mathbf{x}} + \left(y_4\,b\,\sin\gamma + z_4\,c_y\right)\hat{\mathbf{y}} + z_4\,c_z\,\hat{\mathbf{z}}$	$(1a)$	As IV

$\mathbf{B_5}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$(x_5\,a + y_5\,b\,\cos\gamma + z_5\,c_x)\,\hat{\mathbf{x}} + \left(y_5\,b\,\sin\gamma + z_5\,c_y\right)\,\hat{\mathbf{y}} + z_5\,c_z\,\hat{\mathbf{z}}$	(1a)	K I
$\mathbf{B_6}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + y_6\,b\,\cos\gamma + z_6\,c_x)\,\hat{\mathbf{x}} + \left(y_6\,b\,\sin\gamma + z_6\,c_y\right)\,\hat{\mathbf{y}} + z_6\,c_z\,\hat{\mathbf{z}}$	(1a)	K II
$\mathbf{B_7}$	=	$x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + y_7\,b\,\cos\gamma + z_7\,c_x)\,\hat{\mathbf{x}} + \left(y_7\,b\,\sin\gamma + z_7\,c_y\right)\,\hat{\mathbf{y}} + z_7\,c_z\,\hat{\mathbf{z}}$	(1a)	K III
$\mathbf{B_8}$	=	$x_8\,\mathbf{a_1} + y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$(x_8\,a + y_8\,b\,\cos\gamma + z_8\,c_x)\,\hat{\mathbf{x}} + \left(y_8\,b\,\sin\gamma + z_8\,c_y\right)\,\hat{\mathbf{y}} + z_8\,c_z\,\hat{\mathbf{z}}$	(1a)	K IV
$\mathbf{B_9}$	=	$x_9\,\mathbf{a_1} + y_9\,\mathbf{a_2} + z_9\,\mathbf{a_3}$	=	$(x_9\,a + y_9\,b\,\cos\gamma + z_9\,c_x)\,\hat{\mathbf{x}} + \left(y_9\,b\,\sin\gamma + z_9\,c_y\right)\,\hat{\mathbf{y}} + z_9\,c_z\,\hat{\mathbf{z}}$	(1a)	Se I
$\mathbf{B_{10}}$	=	$x_{10}\,\mathbf{a_1} + y_{10}\,\mathbf{a_2} + z_{10}\,\mathbf{a_3}$	=	$(x_{10}\,a + y_{10}\,b\,\cos\gamma + z_{10}\,c_x)\,\hat{\mathbf{x}} + \left(y_{10}\,b\,\sin\gamma + z_{10}\,c_y\right)\,\hat{\mathbf{y}} + z_{10}\,c_z\,\hat{\mathbf{z}}$	(1a)	Se II
$\mathbf{B_{11}}$	=	$x_{11}\,\mathbf{a_1} + y_{11}\,\mathbf{a_2} + z_{11}\,\mathbf{a_3}$	=	$(x_{11}\,a + y_{11}\,b\,\cos\gamma + z_{11}\,c_x)\,\hat{\mathbf{x}} + \left(y_{11}\,b\,\sin\gamma + z_{11}\,c_y\right)\,\hat{\mathbf{y}} + z_{11}\,c_z\,\hat{\mathbf{z}}$	(1a)	Se III
$\mathbf{B_{12}}$	=	$x_{12}\,\mathbf{a_1} + y_{12}\,\mathbf{a_2} + z_{12}\,\mathbf{a_3}$	=	$(x_{12}\,a + y_{12}\,b\,\cos\gamma + z_{12}\,c_x)\,\hat{\mathbf{x}} + \left(y_{12}\,b\,\sin\gamma + z_{12}\,c_y\right)\,\hat{\mathbf{y}} + z_{12}\,c_z\,\hat{\mathbf{z}}$	(1a)	Se IV
$\mathbf{B_{13}}$	=	$x_{13}\,\mathbf{a_1} + y_{13}\,\mathbf{a_2} + z_{13}\,\mathbf{a_3}$	=	$(x_{13}\,a + y_{13}\,b\,\cos\gamma + z_{13}\,c_x)\,\hat{\mathbf{x}} + \left(y_{13}\,b\,\sin\gamma + z_{13}\,c_y\right)\,\hat{\mathbf{y}} + z_{13}\,c_z\,\hat{\mathbf{z}}$	(1a)	Se V
$\mathbf{B_{14}}$	=	$x_{14}\,\mathbf{a_1} + y_{14}\,\mathbf{a_2} + z_{14}\,\mathbf{a_3}$	=	$(x_{14}\,a + y_{14}\,b\,\cos\gamma + z_{14}\,c_x)\,\hat{\mathbf{x}} + \left(y_{14}\,b\,\sin\gamma + z_{14}\,c_y\right)\,\hat{\mathbf{y}} + z_{14}\,c_z\,\hat{\mathbf{z}}$	(1a)	Se VI
$\mathbf{B_{15}}$	=	$x_{15}\,\mathbf{a_1} + y_{15}\,\mathbf{a_2} + z_{15}\,\mathbf{a_3}$	=	$(x_{15}\,a + y_{15}\,b\,\cos\gamma + z_{15}\,c_x)\,\hat{\mathbf{x}} + \left(y_{15}\,b\,\sin\gamma + z_{15}\,c_y\right)\,\hat{\mathbf{y}} + z_{15}\,c_z\,\hat{\mathbf{z}}$	(1a)	Se VII
$\mathbf{B_{16}}$	=	$x_{16}\,\mathbf{a_1} + y_{16}\,\mathbf{a_2} + z_{16}\,\mathbf{a_3}$	=	$(x_{16}\,a + y_{16}\,b\,\cos\gamma + z_{16}\,c_x)\,\hat{\mathbf{x}} + \left(y_{16}\,b\,\sin\gamma + z_{16}\,c_y\right)\,\hat{\mathbf{y}} + z_{16}\,c_z\,\hat{\mathbf{z}}$	(1a)	Se VIII

References:

- W. S. Sheldrick and H. J. Häusler, *Zur Kenntnis von Alkalimetaselenoarseniten Darstellung und Kristallstrukturen von $MAsSe_2$, M = K, Rb, Cs*, Z. Anorg. Allg. Chem. **561**, 139–148 (1988), doi:10.1002/zaac.19885610115.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1165.

Geometry files:

- CIF: pp. S638
- POSCAR: pp. S638

P_2I_4 Structure: A2B_aP6_2_2i_i

Prototype	:	P_2I_4
AFLOW prototype label	:	A2B_aP6_2_2i_i
***Strukturbericht* designation**	:	None
Pearson symbol	:	aP6
Space group number	:	2
Space group symbol	:	$P\bar{1}$
AFLOW prototype command	:	`aflow --proto=A2B_aP6_2_2i_i` `--params=`$a, b/a, c/a, \alpha, \beta, \gamma, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3$

Triclinic primitive vectors:

$$\mathbf{a}_1 = a\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\cos\gamma\,\hat{\mathbf{x}} + b\sin\gamma\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c_x\hat{\mathbf{x}} + c_y\,\hat{\mathbf{y}} + c_z\,\hat{\mathbf{z}}$$

$$c_x = c\,\cos\beta$$
$$c_y = c\,(\cos\alpha - \cos\beta\cos\gamma)/\sin\gamma$$
$$c_z = \sqrt{c^2 - c_x^2 - c_y^2}$$

Basis vectors:

	Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	$= x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	$= (x_1\,a + y_1\,b\,\cos\gamma + z_1\,c_x)\,\hat{\mathbf{x}} + \left(y_1\,b\,\sin\gamma + z_1\,c_y\right)\hat{\mathbf{y}} + z_1\,c_z\,\hat{\mathbf{z}}$	$(2i)$	I I
$\mathbf{B_2}$	$= -x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	$= -(x_1\,a + y_1\,b\,\cos\gamma + z_1\,c_x)\,\hat{\mathbf{x}} - \left(y_1\,b\,\sin\gamma + z_1\,c_y\right)\hat{\mathbf{y}} - z_1\,c_z\,\hat{\mathbf{z}}$	$(2i)$	I I
$\mathbf{B_3}$	$= x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	$= (x_2\,a + y_2\,b\,\cos\gamma + z_2\,c_x)\,\hat{\mathbf{x}} + \left(y_2\,b\,\sin\gamma + z_2\,c_y\right)\hat{\mathbf{y}} + z_2\,c_z\,\hat{\mathbf{z}}$	$(2i)$	I II

$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-\left(x_2\,a + y_2\,b\,\cos\gamma + z_2\,c_x\right)\,\hat{\mathbf{x}} - \left(y_2\,b\,\sin\gamma + z_2\,c_y\right)\,\hat{\mathbf{y}} - z_2\,c_z\,\hat{\mathbf{z}}$	$(2i)$	I II
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\left(x_3\,a + y_3\,b\,\cos\gamma + z_3\,c_x\right)\,\hat{\mathbf{x}} + \left(y_3\,b\,\sin\gamma + z_3\,c_y\right)\,\hat{\mathbf{y}} + z_3\,c_z\,\hat{\mathbf{z}}$	$(2i)$	P
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-\left(x_3\,a + y_3\,b\,\cos\gamma + z_3\,c_x\right)\,\hat{\mathbf{x}} - \left(y_3\,b\,\sin\gamma + z_3\,c_y\right)\,\hat{\mathbf{y}} - z_3\,c_z\,\hat{\mathbf{z}}$	$(2i)$	P

References:

- Y. Chu Leung and J. Waser, *The Crystal Structure of Phosphorus Diiodide, P_2I_4*, J. Phys. Chem. **60**, 539–543 (1956), doi:10.1021/j150539a007.

Geometry files:

- CIF: pp. S639
- POSCAR: pp. S639

Cf Structure: A_aP4_2_aci

Prototype	:	Cf
AFLOW prototype label	:	A_aP4_2_aci
***Strukturbericht* designation**	:	None
Pearson symbol	:	aP4
Space group number	:	2
Space group symbol	:	$P\bar{1}$
AFLOW prototype command	:	`aflow --proto=A_aP4_2_aci` `--params=`$a, b/a, c/a, \alpha, \beta, \gamma, x_3, y_3, z_3$

- This is a high-pressure phase, observed between 30 and 40 GPa.

Triclinic primitive vectors:

$$\mathbf{a}_1 = a\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\cos\gamma\,\hat{\mathbf{x}} + b\sin\gamma\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c_x\hat{\mathbf{x}} + c_y\,\hat{\mathbf{y}} + c_z\,\hat{\mathbf{z}}$$

$$c_x = c\,\cos\beta$$
$$c_y = c\,(\cos\alpha - \cos\beta\cos\gamma)/\sin\gamma$$
$$c_z = \sqrt{c^2 - c_x^2 - c_y^2}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cf I
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_2}$	=	$\frac{1}{2}\,b\,\cos\gamma\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\sin\gamma\,\hat{\mathbf{y}}$	$(1c)$	Cf II
$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + y_3\,b\,\cos\gamma + z_3\,c_x)\,\hat{\mathbf{x}} + \left(y_3\,b\,\sin\gamma + z_3\,c_y\right)\hat{\mathbf{y}} + z_3\,c_z\,\hat{\mathbf{z}}$	$(2i)$	Cf III
$\mathbf{B_4}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + y_3\,b\,\cos\gamma + z_3\,c_x)\,\hat{\mathbf{x}} - \left(y_3\,b\,\sin\gamma + z_3\,c_y\right)\hat{\mathbf{y}} - z_3\,c_z\,\hat{\mathbf{z}}$	$(2i)$	Cf III

References:

- R. B. Roof, *Concerning the Structure of a High Pressure Phase in Californium Metal*, J. Less-Common Met. **120**, 345–349 (1986), doi:10.1016/0022-5088(86)90660-0.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 2332.

Geometry files:

- CIF: pp. S639
- POSCAR: pp. S639

SiO_2 (P2) Structure: A2B_mP12_3_bc3e_2e

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_mP12_3_bc3e_2e
***Strukturbericht* designation**	:	None
Pearson symbol	:	mP12
Space group number	:	3
Space group symbol	:	P2
AFLOW prototype command	:	`aflow --proto=A2B_mP12_3_bc3e_2e` `--params=`$a, b/a, c/a, \beta, y_1, y_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7$

- This structure is the result of simulations of SiO_2 structures from a potential fitted to the $H_6Si_2O_7$ molecule. As such, we do not believe it has been seen in nature. It does, however, describe a structure in space group P2 (#3).

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$y_1\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\cos\beta\,\hat{\mathbf{x}} + y_1 b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(1b)$	O I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + y_2\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_2 b\,\hat{\mathbf{y}}$	$(1c)$	O II
$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	O III
$\mathbf{B_4}$	=	$-x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	O III
$\mathbf{B_5}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	O IV
$\mathbf{B_6}$	=	$-x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	O IV

$\mathbf{B_7}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	O V
$\mathbf{B_8}$	=	$-x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} - z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	O V
$\mathbf{B_9}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Si I
$\mathbf{B_{10}}$	=	$-x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Si I
$\mathbf{B_{11}}$	=	$x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Si II
$\mathbf{B_{12}}$	=	$-x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$-(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} - z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Si II

References:

- M. B. Boisen, Jr., G. V. Gibbs, and M. S. T. Bukowinski, *Framework silica structures generated using simulated annealing with a potential energy function based on an $H_6Si_2O_7$ molecule*, Phys. Chem. Miner. **21**, 269–284 (1994), doi:10.1007/BF00202091.

Geometry files:

- CIF: pp. S639
- POSCAR: pp. S640

High-Pressure Te Structure: A_mP4_4_2a

Prototype	:	Te
AFLOW prototype label	:	A_mP4_4_2a
***Strukturbericht* designation**	:	None
Pearson symbol	:	mP4
Space group number	:	4
Space group symbol	:	$P2_1$
AFLOW prototype command	:	`aflow --proto=A_mP4_4_2a` `--params=`$a, b/a, c/a, \beta, x_1, y_1, z_1, x_2, y_2, z_2$

- This is a high-pressure phase of Te, stable in the 4-7 GPa range. The ground state of Te appears to be γ-Se (A8).

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2a)$	Te I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2a)$	Te I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2a)$	Te II
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2a)$	Te II

References:

- K. Aoki, O. Shimomura, and S. Minomura, *Crystal Structure of the High-Pressure Phase of Tellurium*, J. Phys. Soc. Jpn. **48**, 551–556 (1980), doi:10.1143/JPSJ.48.551.

Geometry files:

- CIF: pp. S640
- POSCAR: pp. S640

Po (A19) Structure: A_mC12_5_3c

Prototype	:	Po
AFLOW prototype label	:	A_mC12_5_3c
***Strukturbericht* designation**	:	A19
Pearson symbol	:	mC12
Space group number	:	5
Space group symbol	:	C2
AFLOW prototype command	:	`aflow --proto=A_mC12_5_3c` `--params=`$a, b/a, c/a, \beta, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3$

- This was the original determination of the structure of Po, and given the Strukturbericht designation A19 (Gottfried, 1938, pp. 4-5). Eventually it was determined that the sample used here was a mixture of α-Po (A_h) and β-Po (A_i) (Donohue, 1982, pp. 390). We retain the A19 page for historical interest.

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

	Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	$= (x_1 - y_1)\,\mathbf{a_1} + (x_1 + y_1)\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	$=$	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4c)$	Po I
$\mathbf{B_2}$	$= -(x_1 + y_1)\,\mathbf{a_1} + (y_1 - x_1)\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	$=$	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4c)$	Po I
$\mathbf{B_3}$	$= (x_2 - y_2)\,\mathbf{a_1} + (x_2 + y_2)\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	$=$	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4c)$	Po II

$\mathbf{B_4}$	=	$-(x_2+y_2)\ \mathbf{a_1}+(y_2-x_2)\ \mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$-(x_2\,a+z_2\,c\ \cos\beta)\ \hat{\mathbf{x}}+y_2\,b\,\hat{\mathbf{y}}-z_2\,c\ \sin\beta\,\hat{\mathbf{z}}$	(4c)	Po II
$\mathbf{B_5}$	=	$(x_3-y_3)\ \mathbf{a_1}+(x_3+y_3)\ \mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$(x_3\,a+z_3\,c\ \cos\beta)\ \hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+z_3\,c\ \sin\beta\,\hat{\mathbf{z}}$	(4c)	Po III
$\mathbf{B_6}$	=	$-(x_3+y_3)\ \mathbf{a_1}+(y_3-x_3)\ \mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-(x_3\,a+z_3\,c\ \cos\beta)\ \hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}-z_3\,c\ \sin\beta\,\hat{\mathbf{z}}$	(4c)	Po III

References:

- M. A. Rollier, S. B. Hendricks, and L. R. Maxwell, *The Crystal Structure of Polonium by Electron Diffraction*, J. Chem. Phys. **4**, 648–652 (1936), doi:10.1063/1.1749762.
- C. Gottfried, *Strukturbericht Band IV, 1936* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1938).
- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S640
- POSCAR: pp. S641

Monoclinic PZT [$Pb(Zr_xTi_{1-x})O_3$] Structure: A3BC_mC10_8_ab_a_a

Prototype	:	$Pb(Zr_{0.52}Ti_{0.48})O_3$
AFLOW prototype label	:	A3BC_mC10_8_ab_a_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	mC10
Space group number	:	8
Space group symbol	:	Cm
AFLOW prototype command	:	`aflow --proto=A3BC_mC10_8_ab_a_a` `--params=`$a, b/a, c/a, \beta, x_1, z_1, x_2, z_2, x_3, z_3, x_4, y_4, z_4$

- This is a monoclinic ferroelectric distortion of the perovskite structure. In $Pb(Zr_xTi_{1-x})O_3$ (aka PZT) it is found only when $x = 0.52$. Although the second (2a) site is nearly equally occupied by Zr and Ti atoms, the pictures use Zr atoms. Compare this to the tetragonal PZT structure.

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2a)$	O I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2a)$	Pb

$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2a)$	Zr
$\mathbf{B_4}$	=	$(x_4 - y_4)\,\mathbf{a_1} + (x_4 + y_4)\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4b)$	O II
$\mathbf{B_5}$	=	$(x_4 + y_4)\,\mathbf{a_1} + (x_4 - y_4)\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4b)$	O II

References:

- B. Noheda, J. A. Gonzalo, L. E. Cross, R. Guo, S.-E. Park, D. E. Cox, and G. Shirane, *Tetragonal-to-monoclinic phase transition in a ferroelectric perovskite: The structure of* $PbZr_{0.52}Ti_{0.48}O_3$, Phys. Rev. B **61**, 8687–8695 (2000), doi:10.1103/PhysRevB.61.8687.

Geometry files:

- CIF: pp. S641
- POSCAR: pp. S641

Monoclinic (Cc) Low Tridymite (SiO_2) Structure: A2B_mC144_9_24a_12a

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_mC144_9_24a_12a
***Strukturbericht* designation**	:	None
Pearson symbol	:	mC144
Space group number	:	9
Space group symbol	:	Cc
AFLOW prototype command	:	`aflow --proto=A2B_mC144_9_24a_12a` `--params=`$a, b/a, c/a, \beta, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8, x_9, y_9, z_9, x_{10}, y_{10}, z_{10}, x_{11}, y_{11}, z_{11}, x_{12}, y_{12}, z_{12}, x_{13}, y_{13}, z_{13}, x_{14}, y_{14}, z_{14}, x_{15}, y_{15}, z_{15}, x_{16}, y_{16}, z_{16}, x_{17}, y_{17}, z_{17}, x_{18}, y_{18}, z_{18}, x_{19}, y_{19}, z_{19}, x_{20}, y_{20}, z_{20}, x_{21}, y_{21}, z_{21}, x_{22}, y_{22}, z_{22}, x_{23}, y_{23}, z_{23}, x_{24}, y_{24}, z_{24}, x_{25}, y_{25}, z_{25}, x_{26}, y_{26}, z_{26}, x_{27}, y_{27}, z_{27}, x_{28}, y_{28}, z_{28}, x_{29}, y_{29}, z_{29}, x_{30}, y_{30}, z_{30}, x_{31}, y_{31}, z_{31}, x_{32}, y_{32}, z_{32}, x_{33}, y_{33}, z_{33}, x_{34}, y_{34}, z_{34}, x_{35}, y_{35}, z_{35}, x_{36}, y_{36}, z_{36}$

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{x}} - \frac{1}{2}b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$(x_1 - y_1)\,\mathbf{a_1} + (x_1 + y_1)\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O I
$\mathbf{B_2}$	=	$(x_1 + y_1)\,\mathbf{a_1} + (x_1 - y_1)\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(x_1\,a + \left(\frac{1}{2} + z_1\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O I
$\mathbf{B_3}$	=	$(x_2 - y_2)\,\mathbf{a_1} + (x_2 + y_2)\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O II
$\mathbf{B_4}$	=	$(x_2 + y_2)\,\mathbf{a_1} + (x_2 - y_2)\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(x_2\,a + \left(\frac{1}{2} + z_2\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O II
$\mathbf{B_5}$	=	$(x_3 - y_3)\,\mathbf{a_1} + (x_3 + y_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O III
$\mathbf{B_6}$	=	$(x_3 + y_3)\,\mathbf{a_1} + (x_3 - y_3)\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(x_3\,a + \left(\frac{1}{2} + z_3\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O III
$\mathbf{B_7}$	=	$(x_4 - y_4)\,\mathbf{a_1} + (x_4 + y_4)\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O IV
$\mathbf{B_8}$	=	$(x_4 + y_4)\,\mathbf{a_1} + (x_4 - y_4)\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\left(x_4\,a + \left(\frac{1}{2} + z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O IV
$\mathbf{B_9}$	=	$(x_5 - y_5)\,\mathbf{a_1} + (x_5 + y_5)\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O V
$\mathbf{B_{10}}$	=	$(x_5 + y_5)\,\mathbf{a_1} + (x_5 - y_5)\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(x_5\,a + \left(\frac{1}{2} + z_5\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O V
$\mathbf{B_{11}}$	=	$(x_6 - y_6)\,\mathbf{a_1} + (x_6 + y_6)\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O VI
$\mathbf{B_{12}}$	=	$(x_6 + y_6)\,\mathbf{a_1} + (x_6 - y_6)\,\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\mathbf{a_3}$	=	$\left(x_6\,a + \left(\frac{1}{2} + z_6\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O VI
$\mathbf{B_{13}}$	=	$(x_7 - y_7)\,\mathbf{a_1} + (x_7 + y_7)\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O VII
$\mathbf{B_{14}}$	=	$(x_7 + y_7)\,\mathbf{a_1} + (x_7 - y_7)\,\mathbf{a_2} + \left(\frac{1}{2} + z_7\right)\mathbf{a_3}$	=	$\left(x_7\,a + \left(\frac{1}{2} + z_7\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_7\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O VII
$\mathbf{B_{15}}$	=	$(x_8 - y_8)\,\mathbf{a_1} + (x_8 + y_8)\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O VIII
$\mathbf{B_{16}}$	=	$(x_8 + y_8)\,\mathbf{a_1} + (x_8 - y_8)\,\mathbf{a_2} + \left(\frac{1}{2} + z_8\right)\mathbf{a_3}$	=	$\left(x_8\,a + \left(\frac{1}{2} + z_8\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_8\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O VIII
$\mathbf{B_{17}}$	=	$(x_9 - y_9)\,\mathbf{a_1} + (x_9 + y_9)\,\mathbf{a_2} + z_9\,\mathbf{a_3}$	=	$(x_9\,a + z_9\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_9\,b\,\hat{\mathbf{y}} + z_9\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O IX
$\mathbf{B_{18}}$	=	$(x_9 + y_9)\,\mathbf{a_1} + (x_9 - y_9)\,\mathbf{a_2} + \left(\frac{1}{2} + z_9\right)\mathbf{a_3}$	=	$\left(x_9\,a + \left(\frac{1}{2} + z_9\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_9\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_9\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O IX
$\mathbf{B_{19}}$	=	$(x_{10} - y_{10})\,\mathbf{a_1} + (x_{10} + y_{10})\,\mathbf{a_2} + z_{10}\,\mathbf{a_3}$	=	$(x_{10}\,a + z_{10}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{10}\,b\,\hat{\mathbf{y}} + z_{10}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O X
$\mathbf{B_{20}}$	=	$(x_{10} + y_{10})\,\mathbf{a_1} + (x_{10} - y_{10})\,\mathbf{a_2} + \left(\frac{1}{2} + z_{10}\right)\mathbf{a_3}$	=	$\left(x_{10}\,a + \left(\frac{1}{2} + z_{10}\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_{10}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{10}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O X
$\mathbf{B_{21}}$	=	$(x_{11} - y_{11})\,\mathbf{a_1} + (x_{11} + y_{11})\,\mathbf{a_2} + z_{11}\,\mathbf{a_3}$	=	$(x_{11}\,a + z_{11}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{11}\,b\,\hat{\mathbf{y}} + z_{11}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4a)$	O XI

$\mathbf{B_{22}}$	=	$(x_{11}+y_{11})\,\mathbf{a_1}+(x_{11}-y_{11})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{11}\right)\mathbf{a_3}$	=	$\left(x_{11}\,a+\left(\frac{1}{2}+z_{11}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{11}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{11}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XI
$\mathbf{B_{23}}$	=	$(x_{12}-y_{12})\,\mathbf{a_1}+(x_{12}+y_{12})\,\mathbf{a_2}+z_{12}\,\mathbf{a_3}$	=	$(x_{12}\,a+z_{12}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{12}\,b\,\hat{\mathbf{y}}+z_{12}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XII
$\mathbf{B_{24}}$	=	$(x_{12}+y_{12})\,\mathbf{a_1}+(x_{12}-y_{12})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{12}\right)\mathbf{a_3}$	=	$\left(x_{12}\,a+\left(\frac{1}{2}+z_{12}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{12}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{12}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XII
$\mathbf{B_{25}}$	=	$(x_{13}-y_{13})\,\mathbf{a_1}+(x_{13}+y_{13})\,\mathbf{a_2}+z_{13}\,\mathbf{a_3}$	=	$(x_{13}\,a+z_{13}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{13}\,b\,\hat{\mathbf{y}}+z_{13}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XIII
$\mathbf{B_{26}}$	=	$(x_{13}+y_{13})\,\mathbf{a_1}+(x_{13}-y_{13})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{13}\right)\mathbf{a_3}$	=	$\left(x_{13}\,a+\left(\frac{1}{2}+z_{13}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{13}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{13}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XIII
$\mathbf{B_{27}}$	=	$(x_{14}-y_{14})\,\mathbf{a_1}+(x_{14}+y_{14})\,\mathbf{a_2}+z_{14}\,\mathbf{a_3}$	=	$(x_{14}\,a+z_{14}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{14}\,b\,\hat{\mathbf{y}}+z_{14}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XIV
$\mathbf{B_{28}}$	=	$(x_{14}+y_{14})\,\mathbf{a_1}+(x_{14}-y_{14})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{14}\right)\mathbf{a_3}$	=	$\left(x_{14}\,a+\left(\frac{1}{2}+z_{14}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{14}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{14}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XIV
$\mathbf{B_{29}}$	=	$(x_{15}-y_{15})\,\mathbf{a_1}+(x_{15}+y_{15})\,\mathbf{a_2}+z_{15}\,\mathbf{a_3}$	=	$(x_{15}\,a+z_{15}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{15}\,b\,\hat{\mathbf{y}}+z_{15}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XV
$\mathbf{B_{30}}$	=	$(x_{15}+y_{15})\,\mathbf{a_1}+(x_{15}-y_{15})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{15}\right)\mathbf{a_3}$	=	$\left(x_{15}\,a+\left(\frac{1}{2}+z_{15}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{15}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{15}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XV
$\mathbf{B_{31}}$	=	$(x_{16}-y_{16})\,\mathbf{a_1}+(x_{16}+y_{16})\,\mathbf{a_2}+z_{16}\,\mathbf{a_3}$	=	$(x_{16}\,a+z_{16}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{16}\,b\,\hat{\mathbf{y}}+z_{16}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XVI
$\mathbf{B_{32}}$	=	$(x_{16}+y_{16})\,\mathbf{a_1}+(x_{16}-y_{16})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{16}\right)\mathbf{a_3}$	=	$\left(x_{16}\,a+\left(\frac{1}{2}+z_{16}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{16}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{16}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XVI
$\mathbf{B_{33}}$	=	$(x_{17}-y_{17})\,\mathbf{a_1}+(x_{17}+y_{17})\,\mathbf{a_2}+z_{17}\,\mathbf{a_3}$	=	$(x_{17}\,a+z_{17}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{17}\,b\,\hat{\mathbf{y}}+z_{17}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XVII
$\mathbf{B_{34}}$	=	$(x_{17}+y_{17})\,\mathbf{a_1}+(x_{17}-y_{17})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{17}\right)\mathbf{a_3}$	=	$\left(x_{17}\,a+\left(\frac{1}{2}+z_{17}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{17}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{17}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XVII
$\mathbf{B_{35}}$	=	$(x_{18}-y_{18})\,\mathbf{a_1}+(x_{18}+y_{18})\,\mathbf{a_2}+z_{18}\,\mathbf{a_3}$	=	$(x_{18}\,a+z_{18}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{18}\,b\,\hat{\mathbf{y}}+z_{18}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XVIII
$\mathbf{B_{36}}$	=	$(x_{18}+y_{18})\,\mathbf{a_1}+(x_{18}-y_{18})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{18}\right)\mathbf{a_3}$	=	$\left(x_{18}\,a+\left(\frac{1}{2}+z_{18}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{18}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{18}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XVIII
$\mathbf{B_{37}}$	=	$(x_{19}-y_{19})\,\mathbf{a_1}+(x_{19}+y_{19})\,\mathbf{a_2}+z_{19}\,\mathbf{a_3}$	=	$(x_{19}\,a+z_{19}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{19}\,b\,\hat{\mathbf{y}}+z_{19}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XIX
$\mathbf{B_{38}}$	=	$(x_{19}+y_{19})\,\mathbf{a_1}+(x_{19}-y_{19})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{19}\right)\mathbf{a_3}$	=	$\left(x_{19}\,a+\left(\frac{1}{2}+z_{19}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{19}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{19}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XIX
$\mathbf{B_{39}}$	=	$(x_{20}-y_{20})\,\mathbf{a_1}+(x_{20}+y_{20})\,\mathbf{a_2}+z_{20}\,\mathbf{a_3}$	=	$(x_{20}\,a+z_{20}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{20}\,b\,\hat{\mathbf{y}}+z_{20}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XX
$\mathbf{B_{40}}$	=	$(x_{20}+y_{20})\,\mathbf{a_1}+(x_{20}-y_{20})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{20}\right)\mathbf{a_3}$	=	$\left(x_{20}\,a+\left(\frac{1}{2}+z_{20}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{20}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{20}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XX
$\mathbf{B_{41}}$	=	$(x_{21}-y_{21})\,\mathbf{a_1}+(x_{21}+y_{21})\,\mathbf{a_2}+z_{21}\,\mathbf{a_3}$	=	$(x_{21}\,a+z_{21}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{21}\,b\,\hat{\mathbf{y}}+z_{21}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XXI
$\mathbf{B_{42}}$	=	$(x_{21}+y_{21})\,\mathbf{a_1}+(x_{21}-y_{21})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{21}\right)\mathbf{a_3}$	=	$\left(x_{21}\,a+\left(\frac{1}{2}+z_{21}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{21}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{21}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XXI
$\mathbf{B_{43}}$	=	$(x_{22}-y_{22})\,\mathbf{a_1}+(x_{22}+y_{22})\,\mathbf{a_2}+z_{22}\,\mathbf{a_3}$	=	$(x_{22}\,a+z_{22}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{22}\,b\,\hat{\mathbf{y}}+z_{22}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XXII

$\mathbf{B_{44}}$	=	$(x_{22}+y_{22})\,\mathbf{a_1}+(x_{22}-y_{22})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{22}\right)\mathbf{a_3}$	=	$\left(x_{22}\,a+\left(\frac{1}{2}+z_{22}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{22}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{22}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XXII
$\mathbf{B_{45}}$	=	$(x_{23}-y_{23})\,\mathbf{a_1}+(x_{23}+y_{23})\,\mathbf{a_2}+z_{23}\,\mathbf{a_3}$	=	$(x_{23}\,a+z_{23}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{23}\,b\,\hat{\mathbf{y}}+z_{23}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XXIII
$\mathbf{B_{46}}$	=	$(x_{23}+y_{23})\,\mathbf{a_1}+(x_{23}-y_{23})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{23}\right)\mathbf{a_3}$	=	$\left(x_{23}\,a+\left(\frac{1}{2}+z_{23}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{23}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{23}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XXIII
$\mathbf{B_{47}}$	=	$(x_{24}-y_{24})\,\mathbf{a_1}+(x_{24}+y_{24})\,\mathbf{a_2}+z_{24}\,\mathbf{a_3}$	=	$(x_{24}\,a+z_{24}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{24}\,b\,\hat{\mathbf{y}}+z_{24}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XXIV
$\mathbf{B_{48}}$	=	$(x_{24}+y_{24})\,\mathbf{a_1}+(x_{24}-y_{24})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{24}\right)\mathbf{a_3}$	=	$\left(x_{24}\,a+\left(\frac{1}{2}+z_{24}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{24}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{24}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	O XXIV
$\mathbf{B_{49}}$	=	$(x_{25}-y_{25})\,\mathbf{a_1}+(x_{25}+y_{25})\,\mathbf{a_2}+z_{25}\,\mathbf{a_3}$	=	$(x_{25}\,a+z_{25}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{25}\,b\,\hat{\mathbf{y}}+z_{25}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si I
$\mathbf{B_{50}}$	=	$(x_{25}+y_{25})\,\mathbf{a_1}+(x_{25}-y_{25})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{25}\right)\mathbf{a_3}$	=	$\left(x_{25}\,a+\left(\frac{1}{2}+z_{25}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{25}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{25}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si I
$\mathbf{B_{51}}$	=	$(x_{26}-y_{26})\,\mathbf{a_1}+(x_{26}+y_{26})\,\mathbf{a_2}+z_{26}\,\mathbf{a_3}$	=	$(x_{26}\,a+z_{26}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{26}\,b\,\hat{\mathbf{y}}+z_{26}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si II
$\mathbf{B_{52}}$	=	$(x_{26}+y_{26})\,\mathbf{a_1}+(x_{26}-y_{26})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{26}\right)\mathbf{a_3}$	=	$\left(x_{26}\,a+\left(\frac{1}{2}+z_{26}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{26}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{26}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si II
$\mathbf{B_{53}}$	=	$(x_{27}-y_{27})\,\mathbf{a_1}+(x_{27}+y_{27})\,\mathbf{a_2}+z_{27}\,\mathbf{a_3}$	=	$(x_{27}\,a+z_{27}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{27}\,b\,\hat{\mathbf{y}}+z_{27}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si III
$\mathbf{B_{54}}$	=	$(x_{27}+y_{27})\,\mathbf{a_1}+(x_{27}-y_{27})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{27}\right)\mathbf{a_3}$	=	$\left(x_{27}\,a+\left(\frac{1}{2}+z_{27}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{27}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{27}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si III
$\mathbf{B_{55}}$	=	$(x_{28}-y_{28})\,\mathbf{a_1}+(x_{28}+y_{28})\,\mathbf{a_2}+z_{28}\,\mathbf{a_3}$	=	$(x_{28}\,a+z_{28}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{28}\,b\,\hat{\mathbf{y}}+z_{28}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si IV
$\mathbf{B_{56}}$	=	$(x_{28}+y_{28})\,\mathbf{a_1}+(x_{28}-y_{28})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{28}\right)\mathbf{a_3}$	=	$\left(x_{28}\,a+\left(\frac{1}{2}+z_{28}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{28}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{28}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si IV
$\mathbf{B_{57}}$	=	$(x_{29}-y_{29})\,\mathbf{a_1}+(x_{29}+y_{29})\,\mathbf{a_2}+z_{29}\,\mathbf{a_3}$	=	$(x_{29}\,a+z_{29}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{29}\,b\,\hat{\mathbf{y}}+z_{29}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si V
$\mathbf{B_{58}}$	=	$(x_{29}+y_{29})\,\mathbf{a_1}+(x_{29}-y_{29})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{29}\right)\mathbf{a_3}$	=	$\left(x_{29}\,a+\left(\frac{1}{2}+z_{29}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{29}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{29}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si V
$\mathbf{B_{59}}$	=	$(x_{30}-y_{30})\,\mathbf{a_1}+(x_{30}+y_{30})\,\mathbf{a_2}+z_{30}\,\mathbf{a_3}$	=	$(x_{30}\,a+z_{30}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{30}\,b\,\hat{\mathbf{y}}+z_{30}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si VI
$\mathbf{B_{60}}$	=	$(x_{30}+y_{30})\,\mathbf{a_1}+(x_{30}-y_{30})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{30}\right)\mathbf{a_3}$	=	$\left(x_{30}\,a+\left(\frac{1}{2}+z_{30}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{30}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{30}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si VI
$\mathbf{B_{61}}$	=	$(x_{31}-y_{31})\,\mathbf{a_1}+(x_{31}+y_{31})\,\mathbf{a_2}+z_{31}\,\mathbf{a_3}$	=	$(x_{31}\,a+z_{31}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{31}\,b\,\hat{\mathbf{y}}+z_{31}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si VII
$\mathbf{B_{62}}$	=	$(x_{31}+y_{31})\,\mathbf{a_1}+(x_{31}-y_{31})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{31}\right)\mathbf{a_3}$	=	$\left(x_{31}\,a+\left(\frac{1}{2}+z_{31}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{31}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{31}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si VII
$\mathbf{B_{63}}$	=	$(x_{32}-y_{32})\,\mathbf{a_1}+(x_{32}+y_{32})\,\mathbf{a_2}+z_{32}\,\mathbf{a_3}$	=	$(x_{32}\,a+z_{32}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{32}\,b\,\hat{\mathbf{y}}+z_{32}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si VIII
$\mathbf{B_{64}}$	=	$(x_{32}+y_{32})\,\mathbf{a_1}+(x_{32}-y_{32})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{32}\right)\mathbf{a_3}$	=	$\left(x_{32}\,a+\left(\frac{1}{2}+z_{32}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{32}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{32}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si VIII
$\mathbf{B_{65}}$	=	$(x_{33}-y_{33})\,\mathbf{a_1}+(x_{33}+y_{33})\,\mathbf{a_2}+z_{33}\,\mathbf{a_3}$	=	$(x_{33}\,a+z_{33}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{33}\,b\,\hat{\mathbf{y}}+z_{33}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si IX

$\mathbf{B_{66}}$	=	$(x_{33}+y_{33})\,\mathbf{a_1}+(x_{33}-y_{33})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{33}\right)\mathbf{a_3}$	=	$\left(x_{33}\,a+\left(\frac{1}{2}+z_{33}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{33}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{33}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si IX
$\mathbf{B_{67}}$	=	$(x_{34}-y_{34})\,\mathbf{a_1}+(x_{34}+y_{34})\,\mathbf{a_2}+z_{34}\,\mathbf{a_3}$	=	$(x_{34}\,a+z_{34}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{34}\,b\,\hat{\mathbf{y}}+z_{34}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si X
$\mathbf{B_{68}}$	=	$(x_{34}+y_{34})\,\mathbf{a_1}+(x_{34}-y_{34})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{34}\right)\mathbf{a_3}$	=	$\left(x_{34}\,a+\left(\frac{1}{2}+z_{34}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{34}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{34}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si X
$\mathbf{B_{69}}$	=	$(x_{35}-y_{35})\,\mathbf{a_1}+(x_{35}+y_{35})\,\mathbf{a_2}+z_{35}\,\mathbf{a_3}$	=	$(x_{35}\,a+z_{35}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{35}\,b\,\hat{\mathbf{y}}+z_{35}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si XI
$\mathbf{B_{70}}$	=	$(x_{35}+y_{35})\,\mathbf{a_1}+(x_{35}-y_{35})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{35}\right)\mathbf{a_3}$	=	$\left(x_{35}\,a+\left(\frac{1}{2}+z_{35}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{35}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{35}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si XI
$\mathbf{B_{71}}$	=	$(x_{36}-y_{36})\,\mathbf{a_1}+(x_{36}+y_{36})\,\mathbf{a_2}+z_{36}\,\mathbf{a_3}$	=	$(x_{36}\,a+z_{36}\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_{36}\,b\,\hat{\mathbf{y}}+z_{36}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si XII
$\mathbf{B_{72}}$	=	$(x_{36}+y_{36})\,\mathbf{a_1}+(x_{36}-y_{36})\,\mathbf{a_2}+\left(\frac{1}{2}+z_{36}\right)\mathbf{a_3}$	=	$\left(x_{36}\,a+\left(\frac{1}{2}+z_{36}\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_{36}\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_{36}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*a*)	Si XII

References:

- W. A. Dollase and W. H. Baur, *The superstructure of meteoritic low tridymite solved by computer simulation*, Am. Mineral. **61**, 971–978 (1976).

Geometry files:

- CIF: pp. S641
- POSCAR: pp. S642

NiTi Structure: AB_mP4_11_e_e

Prototype	:	NiTi
AFLOW prototype label	:	AB_mP4_11_e_e
***Strukturbericht* designation**	:	None
Pearson symbol	:	mP4
Space group number	:	11
Space group symbol	:	$P2_1/m$
AFLOW prototype command	:	`aflow --proto=AB_mP4_11_e_e` `--params=`$a, b/a, c/a, \beta, x_1, z_1, x_2, z_2$

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Ni
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Ni
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Ti
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Ti

References:

- H. Sitepu, W. W. Schmahl, and J. K. Stalick, *Correction of intensities for preferred orientation in neutron-diffraction data of NiTi shape-memory alloy using the generalized spherical-harmonic description*, Appl. Phys. A **74**, S1719–S1721 (2002), doi:10.1007/s003390201840.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S642
- POSCAR: pp. S643

$KClO_3$ ($G0_6$) Structure: ABC3_mP10_11_e_e_ef

Prototype	:	$KClO_3$
AFLOW prototype label	:	ABC3_mP10_11_e_e_ef
***Strukturbericht* designation**	:	$G0_6$
Pearson symbol	:	mP10
Space group number	:	11
Space group symbol	:	$P2_1/m$
AFLOW prototype command	:	`aflow --proto=ABC3_mP10_11_e_e_ef` `--params=`$a, b/a, c/a, \beta, x_1, z_1, x_2, z_2, x_3, z_3, x_4, y_4, z_4$

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Cl
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Cl
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	K
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	K
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	O I
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	O I
$\mathbf{B_7}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4f)$	O II

$\mathbf{B_8}$	=	$-x_4\,\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4f)$	O II
$\mathbf{B_9}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4f)$	O II
$\mathbf{B_{10}}$	=	$x_4\,\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4f)$	O II

References:

- J. Danielsen, A. Hazell, and F. K. Larsen, *The Structure of Potassium Chlorate at 77 and 298 K*, Acta Crystallogr. Sect. B Struct. Sci. **37**, 913–915 (1981), doi:10.1107/S0567740881004573.

Geometry files:

- CIF: pp. S643
- POSCAR: pp. S643

α-Pu Structure: A_mP16_11_8e

Prototype	:	α-Pu
AFLOW prototype label	:	A_mP16_11_8e
***Strukturbericht* designation**	:	None
Pearson symbol	:	mP16
Space group number	:	11
Space group symbol	:	$P2_1/m$
AFLOW prototype command	:	`aflow --proto=A_mP16_11_8e` `--params=`$a, b/a, c/a, \beta, x_1, z_1, x_2, z_2, x_3, z_3, x_4, z_4, x_5, z_5, x_6, z_6, x_7, z_7, x_8, z_8$

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu II
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu II
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu III
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu III
$\mathbf{B_7}$	=	$x_4\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu IV
$\mathbf{B_8}$	=	$-x_4\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu IV

$\mathbf{B_9}$	=	$x_5\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu V
$\mathbf{B_{10}}$	=	$-x_5\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu V
$\mathbf{B_{11}}$	=	$x_6\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu VI
$\mathbf{B_{12}}$	=	$-x_6\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu VI
$\mathbf{B_{13}}$	=	$x_7\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu VII
$\mathbf{B_{14}}$	=	$-x_7\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$-(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu VII
$\mathbf{B_{15}}$	=	$x_8\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu VIII
$\mathbf{B_{16}}$	=	$-x_8\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_8\,\mathbf{a_3}$	=	$-(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Pu VIII

References:

- W. H. Zachariasen and F. H. Ellinger, *The Crystal Structure of Alpha Plutonium Metal*, Acta Cryst. **16**, 777–783 (1963), doi:10.1107/S0365110X63002012.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 159-162.

Geometry files:

- CIF: pp. S643
- POSCAR: pp. S643

Calaverite ($AuTe_2$, C34) Structure: AB2_mC6_12_a_i

Prototype	:	$AuTe_2$
AFLOW prototype label	:	AB2_mC6_12_a_i
***Strukturbericht* designation**	:	C34
Pearson symbol	:	mC6
Space group number	:	12
Space group symbol	:	C2/m
AFLOW prototype command	:	`aflow --proto=AB2_mC6_12_a_i` `--params=`$a, b/a, c/a, \beta, x_2, z_2$

Other compounds with this structure:

- $Au_{10}Se_3Te_{17}$

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Au
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Te
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Te

References:

- K. Reithmayer, W. Steurer, H. Schulz, and J. L. de Boer, *High-pressure single-crystal structure study on calaverite, $AuTe_2$*, Acta Crystallogr. Sect. B Struct. Sci. **49**, 6–11 (1993), doi:10.1107/S0108768192007286.

Geometry files:
- CIF: pp. S644
- POSCAR: pp. S644

β-Pu Structure: A_mC34_12_ah3i2j

Prototype	:	β-Pu
AFLOW prototype label	:	A_mC34_12_ah3i2j
***Strukturbericht* designation**	:	None
Pearson symbol	:	mC34
Space group number	:	12
Space group symbol	:	C2/m
AFLOW prototype command	:	`aflow --proto=A_mC34_12_ah3i2j` `--params=`$a, b/a, c/a, \beta, y_2, x_3, z_3, x_4, z_4, x_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7$

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Pu I
$\mathbf{B_2}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\cos\beta\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4h)$	Pu II
$\mathbf{B_3}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\cos\beta\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4h)$	Pu II
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Pu III
$\mathbf{B_5}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Pu III

$\mathbf{B_6}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Pu IV
$\mathbf{B_7}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Pu IV
$\mathbf{B_8}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Pu V
$\mathbf{B_9}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} - z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Pu V
$\mathbf{B_{10}}$	=	$(x_6 - y_6)\,\mathbf{a_1} + (x_6 + y_6)\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Pu VI
$\mathbf{B_{11}}$	=	$(x_6 + y_6)\,\mathbf{a_1} + (x_6 - y_6)\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Pu VI
$\mathbf{B_{12}}$	=	$(y_6 - x_6)\,\mathbf{a_1} - (x_6 + y_6)\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Pu VI
$\mathbf{B_{13}}$	=	$-(x_6 + y_6)\,\mathbf{a_1} + (y_6 - x_6)\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Pu VI
$\mathbf{B_{14}}$	=	$(x_7 - y_7)\,\mathbf{a_1} + (x_7 + y_7)\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Pu VII
$\mathbf{B_{15}}$	=	$(x_7 + y_7)\,\mathbf{a_1} + (x_7 - y_7)\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Pu VII
$\mathbf{B_{16}}$	=	$(y_7 - x_7)\,\mathbf{a_1} - (x_7 + y_7)\,\mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$-(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} - z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Pu VII
$\mathbf{B_{17}}$	=	$-(x_7 + y_7)\,\mathbf{a_1} + (y_7 - x_7)\,\mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$-(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} - z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Pu VII

References:

- W. H. Zachariasen and F. H. Ellinger, *The Crystal Structure of Beta Plutonium Metal*, Acta Cryst. **16**, 369–375 (1963), doi:10.1107/S0365110X63000992.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 162-165.
- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 5022.

Geometry files:

- CIF: pp. S644
- POSCAR: pp. S644

$AlCl_3$ ($D0_{15}$) Structure: AB3_mC16_12_g_ij

Prototype	:	$AlCl_3$
AFLOW prototype label	:	AB3_mC16_12_g_ij
***Strukturbericht* designation**	:	$D0_{15}$
Pearson symbol	:	mC16
Space group number	:	12
Space group symbol	:	C2/m
AFLOW prototype command	:	`aflow --proto=AB3_mC16_12_g_ij` `--params=`$a, b/a, c/a, \beta, y_1, x_2, z_2, x_3, y_3, z_3$

Other compounds with this structure:

- $DyCl_3$, $ErCl_3$, $HoCl_3$, $InCl_3$, $LuCl_3$, $TlCl_3$, $TmCl_3$, $YbCl_3$

- This structure has a somewhat complicated history. Strukturbericht Volume II lists the space group as either $P3_112$ or $P3_212$. This structure was later refined by Ketelaar in space group C2/m. See (Villars, 2008) for more information.

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2}$	=	$y_1\,b\,\hat{\mathbf{y}}$	$(4g)$	Al
$\mathbf{B_2}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2}$	=	$-y_1\,b\,\hat{\mathbf{y}}$	$(4g)$	Al

$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Cl I
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Cl I
$\mathbf{B_5}$	=	$(x_3 - y_3)\,\mathbf{a_1} + (x_3 + y_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Cl II
$\mathbf{B_6}$	=	$-(x_3 + y_3)\,\mathbf{a_1} + (y_3 - x_3)\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Cl II
$\mathbf{B_7}$	=	$(y_3 - x_3)\,\mathbf{a_1} - (x_3 + y_3)\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Cl II
$\mathbf{B_8}$	=	$(x_3 + y_3)\,\mathbf{a_1} + (x_3 - y_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8j)$	Cl II

References:

- S. I. Troyanov, *The crystal structure of titanium(II) tetrachloroaluminate $Ti(AlCl_4)_2$ and refinement of the crystal structure of $AlCl_3$*, (Russian) Journal of Inorganic Chemistry (translated from Zhurnal Neorganicheskoi Khimii) **37**, 121–124 (1992).
- C. Hermann, O. Lohrmann, and H. Philipp, *Strukturbericht Band II, 1928-1932* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937).
- P. Villars, K. Cenzual, J. Daams, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, N. Melnichenko-Koblyuk, O. Pavlyuk, I. Savesyuk, S. Stoiko, and L. Sysa, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag GmbH, Heidelberg, 2008). Accessed through the Springer Materials site.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S645
- POSCAR: pp. S645

Au_5Mn_2 Structure: A5B2_mC14_12_a2i_i

Prototype	:	Au_5Mn_2
AFLOW prototype label	:	A5B2_mC14_12_a2i_i
***Strukturbericht* designation**	:	None
Pearson symbol	:	mC14
Space group number	:	12
Space group symbol	:	C2/m
AFLOW prototype command	:	`aflow --proto=A5B2_mC14_12_a2i_i` `--params=`$a, b/a, c/a, \beta, x_2, z_2, x_3, z_3, x_4, z_4$

- As noted by (Pearson, 1972), this structure is very nearly cubic close-packed. As such, it is frequently used for cluster expansion models.

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Au I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Au II
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Au II
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	Au III

$\mathbf{B_5}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a\ +\ z_3\,c\ \cos\beta)\ \hat{\mathbf{x}} - z_3\,c\ \sin\beta\,\hat{\mathbf{z}}$	(4*i*)	Au III
$\mathbf{B_6}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a\ +\ z_4\,c\ \cos\beta)\ \hat{\mathbf{x}} + z_4\,c\ \sin\beta\,\hat{\mathbf{z}}$	(4*i*)	Mn
$\mathbf{B_7}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a\ +\ z_4\,c\ \cos\beta)\ \hat{\mathbf{x}} - z_4\,c\ \sin\beta\,\hat{\mathbf{z}}$	(4*i*)	Mn

References:

- S. G. Humble, *Establishment of an ordered phase of composition Au_5Mn_2 in the gold-manganese system*, Acta Cryst. **17**, 1485–1486 (1964), doi:10.1107/S0365110X64003723.

Found in:

- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 346-348.

Geometry files:

- CIF: pp. S645
- POSCAR: pp. S645

α-O Structure: A_mC4_12_i

Prototype	:	α-O
AFLOW prototype label	:	A_mC4_12_i
***Strukturbericht* designation**	:	None
Pearson symbol	:	mC4
Space group number	:	12
Space group symbol	:	C2/m
AFLOW prototype command	:	`aflow --proto=A_mC4_12_i` `--params=`$a, b/a, c/a, \beta, x_1, z_1$

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	O
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4i)$	O

References:

- R. J. Meier and R. B. Helmholdt, *Neutron-diffraction study of α- and β-oxygen*, Phys. Rev. B **29**, 1387–1393 (1984), doi:10.1103/PhysRevB.29.1387.

Geometry files:

- CIF: pp. S645
- POSCAR: pp. S646

Sylvanite ($AgAuTe_4$, $E1_b$) Structure: ABC4_mP12_13_e_a_2g

Prototype	:	$AgAuTe_4$
AFLOW prototype label	:	ABC4_mP12_13_e_a_2g
***Strukturbericht* designation**	:	$E1_b$
Pearson symbol	:	mP12
Space group number	:	13
Space group symbol	:	P2/c
AFLOW prototype command	:	`aflow --proto=ABC4_mP12_13_e_a_2g` `--params=`$a, b/a, c/a, \beta, y_2, x_3, y_3, z_3, x_4, y_4, z_4$

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Au
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\cos\beta\,\hat{\mathbf{x}} + \frac{1}{2}\,c\sin\beta\,\hat{\mathbf{z}}$	$(2a)$	Au
$\mathbf{B_3}$	=	$y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\cos\beta\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Ag
$\mathbf{B_4}$	=	$-y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\cos\beta\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\sin\beta\,\hat{\mathbf{z}}$	$(2e)$	Ag
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	Te I
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\,\mathbf{a_3}$	=	$\left(-x_3\,a + \left(\frac{1}{2} - z_3\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	Te I
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	Te I
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\left(x_3\,a + \left(\frac{1}{2} + z_3\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	Te I
$\mathbf{B_9}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	Te II
$\mathbf{B_{10}}$	=	$-x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\left(-x_4\,a + \left(\frac{1}{2} - z_4\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	Te II

$\mathbf{B_{11}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	Te II
$\mathbf{B_{12}}$	=	$x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\left(x_4\,a + \left(\frac{1}{2} + z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	Te II

References:

- F. Pertlik, *Kristallchemie natürlicher Telluride I: Verfeinerung der Kristallstruktur des Sylvanits, $AuAgTe_4$*, Tschermaks mineralogische und petrographische Mitteilungen **33**, 203–212 (1984), doi:10.1007/BF01081381.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S646
- POSCAR: pp. S646

Monoclinic (Hittorf's) Phosphorus Structure: A_mP84_13_21g

Prototype	:	P
AFLOW prototype label	:	A_mP84_13_21g
***Strukturbericht* designation**	:	None
Pearson symbol	:	mP84
Space group number	:	13
Space group symbol	:	P2/c
AFLOW prototype command	:	`aflow --proto=A_mP84_13_21g` `--params=`$a, b/a, c/a, \beta, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8, x_9, y_9, z_9, x_{10}, y_{10}, z_{10}, x_{11}, y_{11}, z_{11}, x_{12}, y_{12}, z_{12}, x_{13}, y_{13}, z_{13}, x_{14}, y_{14}, z_{14}, x_{15}, y_{15}, z_{15}, x_{16}, y_{16}, z_{16}, x_{17}, y_{17}, z_{17}, x_{18}, y_{18}, z_{18}, x_{19}, y_{19}, z_{19}, x_{20}, y_{20}, z_{20}, x_{21}, y_{21}, z_{21}$

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	P I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(-x_1\,a + \left(\frac{1}{2} - z_1\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	P I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	P I
$\mathbf{B_4}$	=	$x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(x_1\,a + \left(\frac{1}{2} + z_1\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	P I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4g)$	P II

$$\mathbf{B_6} = -x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \left(\tfrac{1}{2} - z_2\right)\mathbf{a_3} = \left(-x_2\,a + \left(\tfrac{1}{2} - z_2\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} - z_2\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P II}$$

$$\mathbf{B_7} = -x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - z_2\,\mathbf{a_3} = -\left(x_2\,a + z_2\,c\,\cos\beta\right)\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P II}$$

$$\mathbf{B_8} = x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\tfrac{1}{2} + z_2\right)\mathbf{a_3} = \left(x_2\,a + \left(\tfrac{1}{2} + z_2\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} + z_2\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P II}$$

$$\mathbf{B_9} = x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3} = \left(x_3\,a + z_3\,c\,\cos\beta\right)\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P III}$$

$$\mathbf{B_{10}} = -x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + \left(\tfrac{1}{2} - z_3\right)\mathbf{a_3} = \left(-x_3\,a + \left(\tfrac{1}{2} - z_3\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} - z_3\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P III}$$

$$\mathbf{B_{11}} = -x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3} = -\left(x_3\,a + z_3\,c\,\cos\beta\right)\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P III}$$

$$\mathbf{B_{12}} = x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \left(\tfrac{1}{2} + z_3\right)\mathbf{a_3} = \left(x_3\,a + \left(\tfrac{1}{2} + z_3\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} + z_3\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P III}$$

$$\mathbf{B_{13}} = x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3} = \left(x_4\,a + z_4\,c\,\cos\beta\right)\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P IV}$$

$$\mathbf{B_{14}} = -x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + \left(\tfrac{1}{2} - z_4\right)\mathbf{a_3} = \left(-x_4\,a + \left(\tfrac{1}{2} - z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} - z_4\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P IV}$$

$$\mathbf{B_{15}} = -x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3} = -\left(x_4\,a + z_4\,c\,\cos\beta\right)\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P IV}$$

$$\mathbf{B_{16}} = x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\tfrac{1}{2} + z_4\right)\mathbf{a_3} = \left(x_4\,a + \left(\tfrac{1}{2} + z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} + z_4\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P IV}$$

$$\mathbf{B_{17}} = x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3} = \left(x_5\,a + z_5\,c\,\cos\beta\right)\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P V}$$

$$\mathbf{B_{18}} = -x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + \left(\tfrac{1}{2} - z_5\right)\mathbf{a_3} = \left(-x_5\,a + \left(\tfrac{1}{2} - z_5\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} - z_5\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P V}$$

$$\mathbf{B_{19}} = -x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} - z_5\,\mathbf{a_3} = -\left(x_5\,a + z_5\,c\,\cos\beta\right)\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} - z_5\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P V}$$

$$\mathbf{B_{20}} = x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \left(\tfrac{1}{2} + z_5\right)\mathbf{a_3} = \left(x_5\,a + \left(\tfrac{1}{2} + z_5\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} + z_5\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P V}$$

$$\mathbf{B_{21}} = x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3} = \left(x_6\,a + z_6\,c\,\cos\beta\right)\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P VI}$$

$$\mathbf{B_{22}} = -x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + \left(\tfrac{1}{2} - z_6\right)\mathbf{a_3} = \left(-x_6\,a + \left(\tfrac{1}{2} - z_6\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} - z_6\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P VI}$$

$$\mathbf{B_{23}} = -x_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} - z_6\,\mathbf{a_3} = -\left(x_6\,a + z_6\,c\,\cos\beta\right)\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P VI}$$

$$\mathbf{B_{24}} = x_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} + \left(\tfrac{1}{2} + z_6\right)\mathbf{a_3} = \left(x_6\,a + \left(\tfrac{1}{2} + z_6\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} + z_6\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P VI}$$

$$\mathbf{B_{25}} = x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3} = \left(x_7\,a + z_7\,c\,\cos\beta\right)\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P VII}$$

$$\mathbf{B_{26}} = -x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + \left(\tfrac{1}{2} - z_7\right)\mathbf{a_3} = \left(-x_7\,a + \left(\tfrac{1}{2} - z_7\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} - z_7\right)c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P VII}$$

$$\mathbf{B_{27}} = -x_7\,\mathbf{a_1} - y_7\,\mathbf{a_2} - z_7\,\mathbf{a_3} = -\left(x_7\,a + z_7\,c\,\cos\beta\right)\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} - z_7\,c\,\sin\beta\,\hat{\mathbf{z}} \quad (4g) \quad \text{P VII}$$

$\mathbf{B_{28}}$	=	$x_7\,\mathbf{a_1} - y_7\,\mathbf{a_2} + \left(\frac{1}{2} + z_7\right)\,\mathbf{a_3}$	=	$\left(x_7\,a + \left(\frac{1}{2} + z_7\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_7\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P VII
$\mathbf{B_{29}}$	=	$x_8\,\mathbf{a_1} + y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P VIII
$\mathbf{B_{30}}$	=	$-x_8\,\mathbf{a_1} + y_8\,\mathbf{a_2} + \left(\frac{1}{2} - z_8\right)\,\mathbf{a_3}$	=	$\left(-x_8\,a + \left(\frac{1}{2} - z_8\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_8\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P VIII
$\mathbf{B_{31}}$	=	$-x_8\,\mathbf{a_1} - y_8\,\mathbf{a_2} - z_8\,\mathbf{a_3}$	=	$-(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} - z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P VIII
$\mathbf{B_{32}}$	=	$x_8\,\mathbf{a_1} - y_8\,\mathbf{a_2} + \left(\frac{1}{2} + z_8\right)\,\mathbf{a_3}$	=	$\left(x_8\,a + \left(\frac{1}{2} + z_8\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_8\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P VIII
$\mathbf{B_{33}}$	=	$x_9\,\mathbf{a_1} + y_9\,\mathbf{a_2} + z_9\,\mathbf{a_3}$	=	$(x_9\,a + z_9\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_9\,b\,\hat{\mathbf{y}} + z_9\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P IX
$\mathbf{B_{34}}$	=	$-x_9\,\mathbf{a_1} + y_9\,\mathbf{a_2} + \left(\frac{1}{2} - z_9\right)\,\mathbf{a_3}$	=	$\left(-x_9\,a + \left(\frac{1}{2} - z_9\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_9\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_9\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P IX
$\mathbf{B_{35}}$	=	$-x_9\,\mathbf{a_1} - y_9\,\mathbf{a_2} - z_9\,\mathbf{a_3}$	=	$-(x_9\,a + z_9\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_9\,b\,\hat{\mathbf{y}} - z_9\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P IX
$\mathbf{B_{36}}$	=	$x_9\,\mathbf{a_1} - y_9\,\mathbf{a_2} + \left(\frac{1}{2} + z_9\right)\,\mathbf{a_3}$	=	$\left(x_9\,a + \left(\frac{1}{2} + z_9\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_9\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_9\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P IX
$\mathbf{B_{37}}$	=	$x_{10}\,\mathbf{a_1} + y_{10}\,\mathbf{a_2} + z_{10}\,\mathbf{a_3}$	=	$(x_{10}\,a + z_{10}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{10}\,b\,\hat{\mathbf{y}} + z_{10}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P X
$\mathbf{B_{38}}$	=	$-x_{10}\,\mathbf{a_1} + y_{10}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{10}\right)\,\mathbf{a_3}$	=	$\left(-x_{10}\,a + \left(\frac{1}{2} - z_{10}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{10}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{10}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P X
$\mathbf{B_{39}}$	=	$-x_{10}\,\mathbf{a_1} - y_{10}\,\mathbf{a_2} - z_{10}\,\mathbf{a_3}$	=	$-(x_{10}\,a + z_{10}\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_{10}\,b\,\hat{\mathbf{y}} - z_{10}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P X
$\mathbf{B_{40}}$	=	$x_{10}\,\mathbf{a_1} - y_{10}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{10}\right)\,\mathbf{a_3}$	=	$\left(x_{10}\,a + \left(\frac{1}{2} + z_{10}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{10}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{10}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P X
$\mathbf{B_{41}}$	=	$x_{11}\,\mathbf{a_1} + y_{11}\,\mathbf{a_2} + z_{11}\,\mathbf{a_3}$	=	$(x_{11}\,a + z_{11}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{11}\,b\,\hat{\mathbf{y}} + z_{11}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XI
$\mathbf{B_{42}}$	=	$-x_{11}\,\mathbf{a_1} + y_{11}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{11}\right)\,\mathbf{a_3}$	=	$\left(-x_{11}\,a + \left(\frac{1}{2} - z_{11}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{11}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{11}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XI
$\mathbf{B_{43}}$	=	$-x_{11}\,\mathbf{a_1} - y_{11}\,\mathbf{a_2} - z_{11}\,\mathbf{a_3}$	=	$-(x_{11}\,a + z_{11}\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_{11}\,b\,\hat{\mathbf{y}} - z_{11}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XI
$\mathbf{B_{44}}$	=	$x_{11}\,\mathbf{a_1} - y_{11}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{11}\right)\,\mathbf{a_3}$	=	$\left(x_{11}\,a + \left(\frac{1}{2} + z_{11}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{11}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{11}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XI
$\mathbf{B_{45}}$	=	$x_{12}\,\mathbf{a_1} + y_{12}\,\mathbf{a_2} + z_{12}\,\mathbf{a_3}$	=	$(x_{12}\,a + z_{12}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{12}\,b\,\hat{\mathbf{y}} + z_{12}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XII
$\mathbf{B_{46}}$	=	$-x_{12}\,\mathbf{a_1} + y_{12}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{12}\right)\,\mathbf{a_3}$	=	$\left(-x_{12}\,a + \left(\frac{1}{2} - z_{12}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{12}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{12}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XII
$\mathbf{B_{47}}$	=	$-x_{12}\,\mathbf{a_1} - y_{12}\,\mathbf{a_2} - z_{12}\,\mathbf{a_3}$	=	$-(x_{12}\,a + z_{12}\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_{12}\,b\,\hat{\mathbf{y}} - z_{12}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XII
$\mathbf{B_{48}}$	=	$x_{12}\,\mathbf{a_1} - y_{12}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{12}\right)\,\mathbf{a_3}$	=	$\left(x_{12}\,a + \left(\frac{1}{2} + z_{12}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{12}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{12}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XII
$\mathbf{B_{49}}$	=	$x_{13}\,\mathbf{a_1} + y_{13}\,\mathbf{a_2} + z_{13}\,\mathbf{a_3}$	=	$(x_{13}\,a + z_{13}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{13}\,b\,\hat{\mathbf{y}} + z_{13}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIII

$\mathbf{B_{50}}$	=	$-x_{13}\,\mathbf{a_1} + y_{13}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{13}\right)\,\mathbf{a_3}$	=	$\left(-x_{13}\,a + \left(\frac{1}{2} - z_{13}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{13}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{13}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIII
$\mathbf{B_{51}}$	=	$-x_{13}\,\mathbf{a_1} - y_{13}\,\mathbf{a_2} - z_{13}\,\mathbf{a_3}$	=	$-\left(x_{13}\,a + z_{13}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{13}\,b\,\hat{\mathbf{y}} - z_{13}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIII
$\mathbf{B_{52}}$	=	$x_{13}\,\mathbf{a_1} - y_{13}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{13}\right)\,\mathbf{a_3}$	=	$\left(x_{13}\,a + \left(\frac{1}{2} + z_{13}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{13}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{13}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIII
$\mathbf{B_{53}}$	=	$x_{14}\,\mathbf{a_1} + y_{14}\,\mathbf{a_2} + z_{14}\,\mathbf{a_3}$	=	$\left(x_{14}\,a + z_{14}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{14}\,b\,\hat{\mathbf{y}} + z_{14}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIV
$\mathbf{B_{54}}$	=	$-x_{14}\,\mathbf{a_1} + y_{14}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{14}\right)\,\mathbf{a_3}$	=	$\left(-x_{14}\,a + \left(\frac{1}{2} - z_{14}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{14}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{14}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIV
$\mathbf{B_{55}}$	=	$-x_{14}\,\mathbf{a_1} - y_{14}\,\mathbf{a_2} - z_{14}\,\mathbf{a_3}$	=	$-\left(x_{14}\,a + z_{14}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{14}\,b\,\hat{\mathbf{y}} - z_{14}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIV
$\mathbf{B_{56}}$	=	$x_{14}\,\mathbf{a_1} - y_{14}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{14}\right)\,\mathbf{a_3}$	=	$\left(x_{14}\,a + \left(\frac{1}{2} + z_{14}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{14}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{14}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIV
$\mathbf{B_{57}}$	=	$x_{15}\,\mathbf{a_1} + y_{15}\,\mathbf{a_2} + z_{15}\,\mathbf{a_3}$	=	$\left(x_{15}\,a + z_{15}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{15}\,b\,\hat{\mathbf{y}} + z_{15}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XV
$\mathbf{B_{58}}$	=	$-x_{15}\,\mathbf{a_1} + y_{15}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{15}\right)\,\mathbf{a_3}$	=	$\left(-x_{15}\,a + \left(\frac{1}{2} - z_{15}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{15}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{15}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XV
$\mathbf{B_{59}}$	=	$-x_{15}\,\mathbf{a_1} - y_{15}\,\mathbf{a_2} - z_{15}\,\mathbf{a_3}$	=	$-\left(x_{15}\,a + z_{15}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{15}\,b\,\hat{\mathbf{y}} - z_{15}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XV
$\mathbf{B_{60}}$	=	$x_{15}\,\mathbf{a_1} - y_{15}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{15}\right)\,\mathbf{a_3}$	=	$\left(x_{15}\,a + \left(\frac{1}{2} + z_{15}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{15}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{15}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XV
$\mathbf{B_{61}}$	=	$x_{16}\,\mathbf{a_1} + y_{16}\,\mathbf{a_2} + z_{16}\,\mathbf{a_3}$	=	$\left(x_{16}\,a + z_{16}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{16}\,b\,\hat{\mathbf{y}} + z_{16}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVI
$\mathbf{B_{62}}$	=	$-x_{16}\,\mathbf{a_1} + y_{16}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{16}\right)\,\mathbf{a_3}$	=	$\left(-x_{16}\,a + \left(\frac{1}{2} - z_{16}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{16}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{16}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVI
$\mathbf{B_{63}}$	=	$-x_{16}\,\mathbf{a_1} - y_{16}\,\mathbf{a_2} - z_{16}\,\mathbf{a_3}$	=	$-\left(x_{16}\,a + z_{16}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{16}\,b\,\hat{\mathbf{y}} - z_{16}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVI
$\mathbf{B_{64}}$	=	$x_{16}\,\mathbf{a_1} - y_{16}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{16}\right)\,\mathbf{a_3}$	=	$\left(x_{16}\,a + \left(\frac{1}{2} + z_{16}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{16}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{16}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVI
$\mathbf{B_{65}}$	=	$x_{17}\,\mathbf{a_1} + y_{17}\,\mathbf{a_2} + z_{17}\,\mathbf{a_3}$	=	$\left(x_{17}\,a + z_{17}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{17}\,b\,\hat{\mathbf{y}} + z_{17}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVII
$\mathbf{B_{66}}$	=	$-x_{17}\,\mathbf{a_1} + y_{17}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{17}\right)\,\mathbf{a_3}$	=	$\left(-x_{17}\,a + \left(\frac{1}{2} - z_{17}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{17}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{17}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVII
$\mathbf{B_{67}}$	=	$-x_{17}\,\mathbf{a_1} - y_{17}\,\mathbf{a_2} - z_{17}\,\mathbf{a_3}$	=	$-\left(x_{17}\,a + z_{17}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{17}\,b\,\hat{\mathbf{y}} - z_{17}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVII
$\mathbf{B_{68}}$	=	$x_{17}\,\mathbf{a_1} - y_{17}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{17}\right)\,\mathbf{a_3}$	=	$\left(x_{17}\,a + \left(\frac{1}{2} + z_{17}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{17}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{17}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVII
$\mathbf{B_{69}}$	=	$x_{18}\,\mathbf{a_1} + y_{18}\,\mathbf{a_2} + z_{18}\,\mathbf{a_3}$	=	$\left(x_{18}\,a + z_{18}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{18}\,b\,\hat{\mathbf{y}} + z_{18}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVIII
$\mathbf{B_{70}}$	=	$-x_{18}\,\mathbf{a_1} + y_{18}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{18}\right)\,\mathbf{a_3}$	=	$\left(-x_{18}\,a + \left(\frac{1}{2} - z_{18}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{18}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{18}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVIII
$\mathbf{B_{71}}$	=	$-x_{18}\,\mathbf{a_1} - y_{18}\,\mathbf{a_2} - z_{18}\,\mathbf{a_3}$	=	$-\left(x_{18}\,a + z_{18}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{18}\,b\,\hat{\mathbf{y}} - z_{18}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVIII

$\mathbf{B_{72}}$	=	$x_{18}\,\mathbf{a_1} - y_{18}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{18}\right)\,\mathbf{a_3}$	=	$\left(x_{18}\,a + \left(\frac{1}{2} + z_{18}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{18}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{18}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XVIII
$\mathbf{B_{73}}$	=	$x_{19}\,\mathbf{a_1} + y_{19}\,\mathbf{a_2} + z_{19}\,\mathbf{a_3}$	=	$(x_{19}\,a + z_{19}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{19}\,b\,\hat{\mathbf{y}} + z_{19}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIX
$\mathbf{B_{74}}$	=	$-x_{19}\,\mathbf{a_1} + y_{19}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{19}\right)\,\mathbf{a_3}$	=	$\left(-x_{19}\,a + \left(\frac{1}{2} - z_{19}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{19}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{19}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIX
$\mathbf{B_{75}}$	=	$-x_{19}\,\mathbf{a_1} - y_{19}\,\mathbf{a_2} - z_{19}\,\mathbf{a_3}$	=	$-(x_{19}\,a + z_{19}\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_{19}\,b\,\hat{\mathbf{y}} - z_{19}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIX
$\mathbf{B_{76}}$	=	$x_{19}\,\mathbf{a_1} - y_{19}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{19}\right)\,\mathbf{a_3}$	=	$\left(x_{19}\,a + \left(\frac{1}{2} + z_{19}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{19}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{19}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XIX
$\mathbf{B_{77}}$	=	$x_{20}\,\mathbf{a_1} + y_{20}\,\mathbf{a_2} + z_{20}\,\mathbf{a_3}$	=	$(x_{20}\,a + z_{20}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{20}\,b\,\hat{\mathbf{y}} + z_{20}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XX
$\mathbf{B_{78}}$	=	$-x_{20}\,\mathbf{a_1} + y_{20}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{20}\right)\,\mathbf{a_3}$	=	$\left(-x_{20}\,a + \left(\frac{1}{2} - z_{20}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{20}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{20}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XX
$\mathbf{B_{79}}$	=	$-x_{20}\,\mathbf{a_1} - y_{20}\,\mathbf{a_2} - z_{20}\,\mathbf{a_3}$	=	$-(x_{20}\,a + z_{20}\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_{20}\,b\,\hat{\mathbf{y}} - z_{20}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XX
$\mathbf{B_{80}}$	=	$x_{20}\,\mathbf{a_1} - y_{20}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{20}\right)\,\mathbf{a_3}$	=	$\left(x_{20}\,a + \left(\frac{1}{2} + z_{20}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{20}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{20}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XX
$\mathbf{B_{81}}$	=	$x_{21}\,\mathbf{a_1} + y_{21}\,\mathbf{a_2} + z_{21}\,\mathbf{a_3}$	=	$(x_{21}\,a + z_{21}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{21}\,b\,\hat{\mathbf{y}} + z_{21}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XXI
$\mathbf{B_{82}}$	=	$-x_{21}\,\mathbf{a_1} + y_{21}\,\mathbf{a_2} + \left(\frac{1}{2} - z_{21}\right)\,\mathbf{a_3}$	=	$\left(-x_{21}\,a + \left(\frac{1}{2} - z_{21}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{21}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{21}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XXI
$\mathbf{B_{83}}$	=	$-x_{21}\,\mathbf{a_1} - y_{21}\,\mathbf{a_2} - z_{21}\,\mathbf{a_3}$	=	$-(x_{21}\,a + z_{21}\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_{21}\,b\,\hat{\mathbf{y}} - z_{21}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XXI
$\mathbf{B_{84}}$	=	$x_{21}\,\mathbf{a_1} - y_{21}\,\mathbf{a_2} + \left(\frac{1}{2} + z_{21}\right)\,\mathbf{a_3}$	=	$\left(x_{21}\,a + \left(\frac{1}{2} + z_{21}\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{21}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{21}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4g)	P XXI

References:

- H. Thurn and H. Krebs, *Über Struktur und Eigenschaften der Halbmetalle. XXII. Die Kristallstruktur des Hittorfschen Phosphors*, Acta Crystallogr. Sect. B Struct. Sci. **25**, 125–135 (1969), doi:10.1107/S0567740869001853.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 292-295.

Geometry files:

- CIF: pp. S646
- POSCAR: pp. S647

Baddeleyite (ZrO_2, C43) Structure: A2B_mP12_14_2e_e

Prototype	:	ZrO_2
AFLOW prototype label	:	A2B_mP12_14_2e_e
***Strukturbericht* designation**	:	C43
Pearson symbol	:	mP12
Space group number	:	14
Space group symbol	:	$P2_1/c$
AFLOW prototype command	:	`aflow --proto=A2B_mP12_14_2e_e` `--params=`$a, b/a, c/a, \beta, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3$

Other compounds with this structure:

- HfO_2, $CoSb_2$, Ag_2Te

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	O I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_1\right)c\,\cos\beta - x_1\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	O I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	O I

$\mathbf{B_4}$	=	$x_1\,\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_1\right) c\,\cos\beta + x_1\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right) c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	O I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	O II
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_2\right) c\,\cos\beta - x_2\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right) c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	O II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	O II
$\mathbf{B_8}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_2\right) c\,\cos\beta + x_2\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right) c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	O II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Zr
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} + y_3\right)\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_3\right) c\,\cos\beta - x_3\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right) c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Zr
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Zr
$\mathbf{B_{12}}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} - y_3\right)\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_3\right) c\,\cos\beta + x_3\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right) c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Zr

References:

- C. J. Howard, R. J. Hill, and B. E. Reichert, *Structures of ZrO_2 polymorphs at room temperature by high-resolution neutron powder diffraction*, Acta Crystallogr. Sect. B Struct. Sci. **44**, 116–120 (1988), doi:10.1107/S0108768187010279.

Geometry files:

- CIF: pp. S647
- POSCAR: pp. S648

β-Se (A_l) Structure: A_mP32_14_8e

Prototype	:	β-Se
AFLOW prototype label	:	A_mP32_14_8e
***Strukturbericht* designation**	:	A_l
Pearson symbol	:	mP32
Space group number	:	14
Space group symbol	:	$P2_1/c$
AFLOW prototype command	:	`aflow --proto=A_mP32_14_8e` `--params=`$a, b/a, c/a, \beta, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8$

- Donohue (1982) refers to this as the "monoclinic β-Se structure".

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_1\right)c\,\cos\beta - x_1\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se I

$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-\left(x_1\,a + z_1\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se I
$\mathbf{B_4}$	=	$x_1\,\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_1\right)\,c\,\cos\beta + x_1\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\left(x_2\,a + z_2\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se II
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_2\right)\,c\,\cos\beta - x_2\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-\left(x_2\,a + z_2\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se II
$\mathbf{B_8}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_2\right)\,c\,\cos\beta + x_2\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\left(x_3\,a + z_3\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se III
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} + y_3\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_3\right)\,c\,\cos\beta - x_3\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se III
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-\left(x_3\,a + z_3\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se III
$\mathbf{B_{12}}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} - y_3\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_3\right)\,c\,\cos\beta + x_3\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se III
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\left(x_4\,a + z_4\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se IV
$\mathbf{B_{14}}$	=	$-x_4\,\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_4\right)\,c\,\cos\beta - x_4\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se IV
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-\left(x_4\,a + z_4\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se IV
$\mathbf{B_{16}}$	=	$x_4\,\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_4\right)\,c\,\cos\beta + x_4\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se IV
$\mathbf{B_{17}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\left(x_5\,a + z_5\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se V
$\mathbf{B_{18}}$	=	$-x_5\,\mathbf{a_1} + \left(\frac{1}{2} + y_5\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_5\right)\,c\,\cos\beta - x_5\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_5\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se V
$\mathbf{B_{19}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-\left(x_5\,a + z_5\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} - z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se V
$\mathbf{B_{20}}$	=	$x_5\,\mathbf{a_1} + \left(\frac{1}{2} - y_5\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_5\right)\,c\,\cos\beta + x_5\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_5\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se V
$\mathbf{B_{21}}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$\left(x_6\,a + z_6\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VI
$\mathbf{B_{22}}$	=	$-x_6\,\mathbf{a_1} + \left(\frac{1}{2} + y_6\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_6\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_6\right)\,c\,\cos\beta - x_6\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_6\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_6\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VI
$\mathbf{B_{23}}$	=	$-x_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-\left(x_6\,a + z_6\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VI
$\mathbf{B_{24}}$	=	$x_6\,\mathbf{a_1} + \left(\frac{1}{2} - y_6\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_6\right)\,c\,\cos\beta + x_6\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_6\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VI

$\mathbf{B_{25}}$	=	$x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4e)	Se VII
$\mathbf{B_{26}}$	=	$-x_7\,\mathbf{a_1} + \left(\frac{1}{2} + y_7\right)\mathbf{a_2} + \left(\frac{1}{2} - z_7\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_7\right)c\,\cos\beta - x_7\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_7\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_7\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4e)	Se VII
$\mathbf{B_{27}}$	=	$-x_7\,\mathbf{a_1} - y_7\,\mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$-(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} - z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4e)	Se VII
$\mathbf{B_{28}}$	=	$x_7\,\mathbf{a_1} + \left(\frac{1}{2} - y_7\right)\mathbf{a_2} + \left(\frac{1}{2} + z_7\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_7\right)c\,\cos\beta + x_7\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_7\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_7\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4e)	Se VII
$\mathbf{B_{29}}$	=	$x_8\,\mathbf{a_1} + y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4e)	Se VIII
$\mathbf{B_{30}}$	=	$-x_8\,\mathbf{a_1} + \left(\frac{1}{2} + y_8\right)\mathbf{a_2} + \left(\frac{1}{2} - z_8\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_8\right)c\,\cos\beta - x_8\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_8\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_8\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4e)	Se VIII
$\mathbf{B_{31}}$	=	$-x_8\,\mathbf{a_1} - y_8\,\mathbf{a_2} - z_8\,\mathbf{a_3}$	=	$-(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} - z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4e)	Se VIII
$\mathbf{B_{32}}$	=	$x_8\,\mathbf{a_1} + \left(\frac{1}{2} - y_8\right)\mathbf{a_2} + \left(\frac{1}{2} + z_8\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_8\right)c\,\cos\beta + x_8\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_8\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_8\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4e)	Se VIII

References:

- R. E. Marsh, L. Pauling, and J. D. McCullough, *The Crystal Structure of β Selenium*, Acta Cryst. **6**, 71–75 (1953), doi:10.1107/S0365110X53000168.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 379-384.

Geometry files:

- CIF: pp. S648
- POSCAR: pp. S648

Se (A_k) Structure: A_mP64_14_16e

Prototype	:	Se
AFLOW prototype label	:	A_mP64_14_16e
***Strukturbericht* designation**	:	A_k
Pearson symbol	:	mP64
Space group number	:	14
Space group symbol	:	$P2_1/c$
AFLOW prototype command	:	`aflow --proto=A_mP64_14_16e` `--params=`$a, b/a, c/a, \beta, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8, x_9, y_9, z_9, x_{10}, y_{10}, z_{10}, x_{11}, y_{11}, z_{11}, x_{12}, y_{12}, z_{12}, x_{13}, y_{13}, z_{13}, x_{14}, y_{14}, z_{14}, x_{15}, y_{15}, z_{15}, x_{16}, y_{16}, z_{16}$

- We follow Villars (1991) and give this structure the A_k designation. As noted in Villars (1991), the atomic coordinates are not provided in the referenced paper, but were given to the editors by the authors. We use those coordinates. Downs (2003) has the notation "gamma-monoclinic selenium is allotrope of cyclo-octaselenium". Despite that, note that this is not what we refer to as γ-Se.

Simple Monoclinic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2}+y_1\right)\mathbf{a_2} + \left(\frac{1}{2}-z_1\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2}-z_1\right)c\,\cos\beta - x_1\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2}+y_1\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2}-z_1\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-(x_1\,a + z_1\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} - z_1\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se I
$\mathbf{B_4}$	=	$x_1\,\mathbf{a_1} + \left(\frac{1}{2}-y_1\right)\mathbf{a_2} + \left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2}+z_1\right)c\,\cos\beta + x_1\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2}-y_1\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2}+z_1\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se II
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2}+y_2\right)\mathbf{a_2} + \left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2}-z_2\right)c\,\cos\beta - x_2\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2}+y_2\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2}-z_2\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se II
$\mathbf{B_8}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2}-y_2\right)\mathbf{a_2} + \left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2}+z_2\right)c\,\cos\beta + x_2\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2}-y_2\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2}+z_2\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se III
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2}+y_3\right)\mathbf{a_2} + \left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2}-z_3\right)c\,\cos\beta - x_3\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2}+y_3\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2}-z_3\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se III
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se III
$\mathbf{B_{12}}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2}-y_3\right)\mathbf{a_2} + \left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2}+z_3\right)c\,\cos\beta + x_3\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2}-y_3\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2}+z_3\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se III
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se IV
$\mathbf{B_{14}}$	=	$-x_4\,\mathbf{a_1} + \left(\frac{1}{2}+y_4\right)\mathbf{a_2} + \left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2}-z_4\right)c\,\cos\beta - x_4\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2}+y_4\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2}-z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se IV
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se IV
$\mathbf{B_{16}}$	=	$x_4\,\mathbf{a_1} + \left(\frac{1}{2}-y_4\right)\mathbf{a_2} + \left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2}+z_4\right)c\,\cos\beta + x_4\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2}-y_4\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2}+z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Se IV

$\mathbf{B_{17}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se V
$\mathbf{B_{18}}$	=	$-x_5\,\mathbf{a_1} + \left(\frac{1}{2} + y_5\right)\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_5\right)c\,\cos\beta - x_5\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_5\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se V
$\mathbf{B_{19}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} - z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se V
$\mathbf{B_{20}}$	=	$x_5\,\mathbf{a_1} + \left(\frac{1}{2} - y_5\right)\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_5\right)c\,\cos\beta + x_5\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_5\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se V
$\mathbf{B_{21}}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VI
$\mathbf{B_{22}}$	=	$-x_6\,\mathbf{a_1} + \left(\frac{1}{2} + y_6\right)\mathbf{a_2} + \left(\frac{1}{2} - z_6\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_6\right)c\,\cos\beta - x_6\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_6\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_6\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VI
$\mathbf{B_{23}}$	=	$-x_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VI
$\mathbf{B_{24}}$	=	$x_6\,\mathbf{a_1} + \left(\frac{1}{2} - y_6\right)\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_6\right)c\,\cos\beta + x_6\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_6\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VI
$\mathbf{B_{25}}$	=	$x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VII
$\mathbf{B_{26}}$	=	$-x_7\,\mathbf{a_1} + \left(\frac{1}{2} + y_7\right)\mathbf{a_2} + \left(\frac{1}{2} - z_7\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_7\right)c\,\cos\beta - x_7\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_7\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_7\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VII
$\mathbf{B_{27}}$	=	$-x_7\,\mathbf{a_1} - y_7\,\mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$-(x_7\,a + z_7\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} - z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VII
$\mathbf{B_{28}}$	=	$x_7\,\mathbf{a_1} + \left(\frac{1}{2} - y_7\right)\mathbf{a_2} + \left(\frac{1}{2} + z_7\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_7\right)c\,\cos\beta + x_7\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_7\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_7\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VII
$\mathbf{B_{29}}$	=	$x_8\,\mathbf{a_1} + y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VIII
$\mathbf{B_{30}}$	=	$-x_8\,\mathbf{a_1} + \left(\frac{1}{2} + y_8\right)\mathbf{a_2} + \left(\frac{1}{2} - z_8\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_8\right)c\,\cos\beta - x_8\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_8\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_8\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VIII
$\mathbf{B_{31}}$	=	$-x_8\,\mathbf{a_1} - y_8\,\mathbf{a_2} - z_8\,\mathbf{a_3}$	=	$-(x_8\,a + z_8\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} - z_8\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VIII
$\mathbf{B_{32}}$	=	$x_8\,\mathbf{a_1} + \left(\frac{1}{2} - y_8\right)\mathbf{a_2} + \left(\frac{1}{2} + z_8\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_8\right)c\,\cos\beta + x_8\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_8\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_8\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se VIII
$\mathbf{B_{33}}$	=	$x_9\,\mathbf{a_1} + y_9\,\mathbf{a_2} + z_9\,\mathbf{a_3}$	=	$(x_9\,a + z_9\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_9\,b\,\hat{\mathbf{y}} + z_9\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se IX
$\mathbf{B_{34}}$	=	$-x_9\,\mathbf{a_1} + \left(\frac{1}{2} + y_9\right)\mathbf{a_2} + \left(\frac{1}{2} - z_9\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_9\right)c\,\cos\beta - x_9\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_9\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_9\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se IX
$\mathbf{B_{35}}$	=	$-x_9\,\mathbf{a_1} - y_9\,\mathbf{a_2} - z_9\,\mathbf{a_3}$	=	$-(x_9\,a + z_9\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_9\,b\,\hat{\mathbf{y}} - z_9\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se IX
$\mathbf{B_{36}}$	=	$x_9\,\mathbf{a_1} + \left(\frac{1}{2} - y_9\right)\mathbf{a_2} + \left(\frac{1}{2} + z_9\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_9\right)c\,\cos\beta + x_9\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_9\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_9\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se IX
$\mathbf{B_{37}}$	=	$x_{10}\,\mathbf{a_1} + y_{10}\,\mathbf{a_2} + z_{10}\,\mathbf{a_3}$	=	$(x_{10}\,a + z_{10}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{10}\,b\,\hat{\mathbf{y}} + z_{10}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se X
$\mathbf{B_{38}}$	=	$-x_{10}\,\mathbf{a_1} + \left(\frac{1}{2} + y_{10}\right)\mathbf{a_2} + \left(\frac{1}{2} - z_{10}\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_{10}\right)c\,\cos\beta - x_{10}\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_{10}\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{10}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se X

$\mathbf{B_{39}}$	=	$-x_{10}\,\mathbf{a_1} - y_{10}\,\mathbf{a_2} - z_{10}\,\mathbf{a_3}$	=	$-\left(x_{10}\,a + z_{10}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{10}\,b\,\hat{\mathbf{y}} - z_{10}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se X
$\mathbf{B_{40}}$	=	$x_{10}\,\mathbf{a_1} + \left(\frac{1}{2} - y_{10}\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_{10}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_{10}\right)\,c\,\cos\beta + x_{10}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_{10}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{10}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se X
$\mathbf{B_{41}}$	=	$x_{11}\,\mathbf{a_1} + y_{11}\,\mathbf{a_2} + z_{11}\,\mathbf{a_3}$	=	$\left(x_{11}\,a + z_{11}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{11}\,b\,\hat{\mathbf{y}} + z_{11}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XI
$\mathbf{B_{42}}$	=	$-x_{11}\,\mathbf{a_1} + \left(\frac{1}{2} + y_{11}\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_{11}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_{11}\right)\,c\,\cos\beta - x_{11}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_{11}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{11}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XI
$\mathbf{B_{43}}$	=	$-x_{11}\,\mathbf{a_1} - y_{11}\,\mathbf{a_2} - z_{11}\,\mathbf{a_3}$	=	$-\left(x_{11}\,a + z_{11}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{11}\,b\,\hat{\mathbf{y}} - z_{11}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XI
$\mathbf{B_{44}}$	=	$x_{11}\,\mathbf{a_1} + \left(\frac{1}{2} - y_{11}\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_{11}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_{11}\right)\,c\,\cos\beta + x_{11}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_{11}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{11}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XI
$\mathbf{B_{45}}$	=	$x_{12}\,\mathbf{a_1} + y_{12}\,\mathbf{a_2} + z_{12}\,\mathbf{a_3}$	=	$\left(x_{12}\,a + z_{12}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{12}\,b\,\hat{\mathbf{y}} + z_{12}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XII
$\mathbf{B_{46}}$	=	$-x_{12}\,\mathbf{a_1} + \left(\frac{1}{2} + y_{12}\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_{12}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_{12}\right)\,c\,\cos\beta - x_{12}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_{12}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{12}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XII
$\mathbf{B_{47}}$	=	$-x_{12}\,\mathbf{a_1} - y_{12}\,\mathbf{a_2} - z_{12}\,\mathbf{a_3}$	=	$-\left(x_{12}\,a + z_{12}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{12}\,b\,\hat{\mathbf{y}} - z_{12}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XII
$\mathbf{B_{48}}$	=	$x_{12}\,\mathbf{a_1} + \left(\frac{1}{2} - y_{12}\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_{12}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_{12}\right)\,c\,\cos\beta + x_{12}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_{12}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{12}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XII
$\mathbf{B_{49}}$	=	$x_{13}\,\mathbf{a_1} + y_{13}\,\mathbf{a_2} + z_{13}\,\mathbf{a_3}$	=	$\left(x_{13}\,a + z_{13}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{13}\,b\,\hat{\mathbf{y}} + z_{13}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XIII
$\mathbf{B_{50}}$	=	$-x_{13}\,\mathbf{a_1} + \left(\frac{1}{2} + y_{13}\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_{13}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_{13}\right)\,c\,\cos\beta - x_{13}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_{13}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{13}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XIII
$\mathbf{B_{51}}$	=	$-x_{13}\,\mathbf{a_1} - y_{13}\,\mathbf{a_2} - z_{13}\,\mathbf{a_3}$	=	$-\left(x_{13}\,a + z_{13}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{13}\,b\,\hat{\mathbf{y}} - z_{13}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XIII
$\mathbf{B_{52}}$	=	$x_{13}\,\mathbf{a_1} + \left(\frac{1}{2} - y_{13}\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_{13}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_{13}\right)\,c\,\cos\beta + x_{13}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_{13}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{13}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XIII
$\mathbf{B_{53}}$	=	$x_{14}\,\mathbf{a_1} + y_{14}\,\mathbf{a_2} + z_{14}\,\mathbf{a_3}$	=	$\left(x_{14}\,a + z_{14}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{14}\,b\,\hat{\mathbf{y}} + z_{14}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XIV
$\mathbf{B_{54}}$	=	$-x_{14}\,\mathbf{a_1} + \left(\frac{1}{2} + y_{14}\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_{14}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_{14}\right)\,c\,\cos\beta - x_{14}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_{14}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{14}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XIV
$\mathbf{B_{55}}$	=	$-x_{14}\,\mathbf{a_1} - y_{14}\,\mathbf{a_2} - z_{14}\,\mathbf{a_3}$	=	$-\left(x_{14}\,a + z_{14}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{14}\,b\,\hat{\mathbf{y}} - z_{14}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XIV
$\mathbf{B_{56}}$	=	$x_{14}\,\mathbf{a_1} + \left(\frac{1}{2} - y_{14}\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_{14}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_{14}\right)\,c\,\cos\beta + x_{14}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_{14}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{14}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XIV
$\mathbf{B_{57}}$	=	$x_{15}\,\mathbf{a_1} + y_{15}\,\mathbf{a_2} + z_{15}\,\mathbf{a_3}$	=	$\left(x_{15}\,a + z_{15}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_{15}\,b\,\hat{\mathbf{y}} + z_{15}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XV
$\mathbf{B_{58}}$	=	$-x_{15}\,\mathbf{a_1} + \left(\frac{1}{2} + y_{15}\right)\,\mathbf{a_2} + \left(\frac{1}{2} - z_{15}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_{15}\right)\,c\,\cos\beta - x_{15}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_{15}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{15}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XV
$\mathbf{B_{59}}$	=	$-x_{15}\,\mathbf{a_1} - y_{15}\,\mathbf{a_2} - z_{15}\,\mathbf{a_3}$	=	$-\left(x_{15}\,a + z_{15}\,c\,\cos\beta\right)\,\hat{\mathbf{x}} - y_{15}\,b\,\hat{\mathbf{y}} - z_{15}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XV
$\mathbf{B_{60}}$	=	$x_{15}\,\mathbf{a_1} + \left(\frac{1}{2} - y_{15}\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_{15}\right)\,\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_{15}\right)\,c\,\cos\beta + x_{15}\,a\right)\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_{15}\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{15}\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XV

$\mathbf{B_{61}}$	=	$x_{16}\,\mathbf{a_1} + y_{16}\,\mathbf{a_2} + z_{16}\,\mathbf{a_3}$	=	$(x_{16}\,a + z_{16}\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_{16}\,b\,\hat{\mathbf{y}} + z_{16}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XVI
$\mathbf{B_{62}}$	=	$-x_{16}\,\mathbf{a_1} + \left(\frac{1}{2} + y_{16}\right)\mathbf{a_2} + \left(\frac{1}{2} - z_{16}\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} - z_{16}\right)c\,\cos\beta - x_{16}\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} + y_{16}\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_{16}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XVI
$\mathbf{B_{63}}$	=	$-x_{16}\,\mathbf{a_1} - y_{16}\,\mathbf{a_2} - z_{16}\,\mathbf{a_3}$	=	$-(x_{16}\,a + z_{16}\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_{16}\,b\,\hat{\mathbf{y}} - z_{16}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XVI
$\mathbf{B_{64}}$	=	$x_{16}\,\mathbf{a_1} + \left(\frac{1}{2} - y_{16}\right)\mathbf{a_2} + \left(\frac{1}{2} + z_{16}\right)\mathbf{a_3}$	=	$\left(\left(\frac{1}{2} + z_{16}\right)c\,\cos\beta + x_{16}\,a\right)\hat{\mathbf{x}} + \left(\frac{1}{2} - y_{16}\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_{16}\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Se XVI

References:

- O. Foss and V. Janickis, *X-Ray crystal structure of a new red, monoclinic form of cyclo-octaselenium, Se_8*, J. Chem. Soc., Chem. Commun. pp. 834–835 (1977), doi:10.1039/C39770000834.
- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 5716.

Geometry files:

- CIF: pp. S648
- POSCAR: pp. S649

B_2Pd_5 Structure: A2B5_mC28_15_f_e2f

Prototype	:	B_2Pd_5
AFLOW prototype label	:	A2B5_mC28_15_f_e2f
***Strukturbericht* designation**	:	None
Pearson symbol	:	mC28
Space group number	:	15
Space group symbol	:	C2/c
AFLOW prototype command	:	`aflow --proto=A2B5_mC28_15_f_e2f` `--params=`$a, b/a, c/a, \beta, y_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4$

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Pd I
$\mathbf{B_2}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Pd I
$\mathbf{B_3}$	=	$(x_2 - y_2)\,\mathbf{a_1} + (x_2 + y_2)\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	B
$\mathbf{B_4}$	=	$-(x_2 + y_2)\,\mathbf{a_1} + (y_2 - x_2)\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(-x_2\,a + \left(\frac{1}{2} - z_2\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	B
$\mathbf{B_5}$	=	$(y_2 - x_2)\,\mathbf{a_1} - (x_2 + y_2)\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-(x_2\,a + z_2\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} - z_2\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	B
$\mathbf{B_6}$	=	$(x_2 + y_2)\,\mathbf{a_1} + (x_2 - y_2)\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(x_2\,a + \left(\frac{1}{2} + z_2\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	B
$\mathbf{B_7}$	=	$(x_3 - y_3)\,\mathbf{a_1} + (x_3 + y_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Pd II

$\mathbf{B_8}$	=	$-(x_3+y_3)\,\mathbf{a_1}+(y_3-x_3)\,\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(-x_3\,a+\left(\frac{1}{2}-z_3\right)c\,\cos\beta\right)\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Pd II
$\mathbf{B_9}$	=	$(y_3-x_3)\,\mathbf{a_1}-(x_3+y_3)\,\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-(x_3\,a+z_3\,c\,\cos\beta)\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}-z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Pd II
$\mathbf{B_{10}}$	=	$(x_3+y_3)\,\mathbf{a_1}+(x_3-y_3)\,\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(x_3\,a+\left(\frac{1}{2}+z_3\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Pd II
$\mathbf{B_{11}}$	=	$(x_4-y_4)\,\mathbf{a_1}+(x_4+y_4)\,\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$(x_4\,a+z_4\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_4\,b\,\hat{\mathbf{y}}+z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Pd III
$\mathbf{B_{12}}$	=	$-(x_4+y_4)\,\mathbf{a_1}+(y_4-x_4)\,\mathbf{a_2}+\left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\left(-x_4\,a+\left(\frac{1}{2}-z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}}+y_4\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Pd III
$\mathbf{B_{13}}$	=	$(y_4-x_4)\,\mathbf{a_1}-(x_4+y_4)\,\mathbf{a_2}-z_4\,\mathbf{a_3}$	=	$-(x_4\,a+z_4\,c\,\cos\beta)\,\hat{\mathbf{x}}-y_4\,b\,\hat{\mathbf{y}}-z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Pd III
$\mathbf{B_{14}}$	=	$(x_4+y_4)\,\mathbf{a_1}+(x_4-y_4)\,\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\left(x_4\,a+\left(\frac{1}{2}+z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_4\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Pd III

References:

- E. Stenberg, *The Crystal Structures of Pd_5B_2, (Mn_5C_2), and Pd_3B*, Acta Chem. Scand. **15**, 861–870 (1961), doi:10.3891/acta.chem.scand.15-0861.

Geometry files:

- CIF: pp. S649
- POSCAR: pp. S650

Tenorite (CuO, B26) Structure: AB_mC8_15_c_e

Prototype	:	CuO
AFLOW prototype label	:	AB_mC8_15_c_e
***Strukturbericht* designation**	:	B26
Pearson symbol	:	mC8
Space group number	:	15
Space group symbol	:	C2/c
AFLOW prototype command	:	`aflow --proto=AB_mC8_15_c_e` `--params=`$a, b/a, c/a, \beta, y_2$

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}}$	$(4c)$	Cu
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{4}\,a + \frac{1}{2}\,c\,\cos\beta\right)\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4c)$	Cu
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	O
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	O

References:

- S. Åsbrink and L. -J. Norrby, *A refinement of the crystal structure of copper(II) oxide with a discussion of some exceptional e.s.d.'s*, Acta Crystallogr. Sect. B Struct. Sci. **26**, 8–15 (1970), doi:10.1107/S0567740870001838.

Geometry files:

- CIF: pp. S650
- POSCAR: pp. S650

Coesite (SiO_2) Structure: A2B_mC48_15_ae3f_2f

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_mC48_15_ae3f_2f
***Strukturbericht* designation**	:	None
Pearson symbol	:	mC48
Space group number	:	15
Space group symbol	:	C2/c
AFLOW prototype command	:	`aflow --proto=A2B_mC48_15_ae3f_2f` `--params=`$a, b/a, c/a, \beta, y_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7$

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	O I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\cos\beta\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\sin\beta\hat{\mathbf{z}}$	$(4a)$	O I
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	O II
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	O II
$\mathbf{B_5}$	=	$(x_3 - y_3)\,\mathbf{a_1} + (x_3 + y_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O III
$\mathbf{B_6}$	=	$-(x_3 + y_3)\,\mathbf{a_1} + (y_3 - x_3)\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\,\mathbf{a_3}$	=	$\left(-x_3\,a + \left(\frac{1}{2} - z_3\right)\,c\,\cos\beta\right)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O III
$\mathbf{B_7}$	=	$(y_3 - x_3)\,\mathbf{a_1} - (x_3 + y_3)\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O III

$\mathbf{B_8}$	=	$(x_3+y_3)\,\mathbf{a_1}+(x_3-y_3)\,\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(x_3\,a+\left(\frac{1}{2}+z_3\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O III
$\mathbf{B_9}$	=	$(x_4-y_4)\,\mathbf{a_1}+(x_4+y_4)\,\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$(x_4\,a+z_4\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_4\,b\,\hat{\mathbf{y}}+z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O IV
$\mathbf{B_{10}}$	=	$-(x_4+y_4)\,\mathbf{a_1}+(y_4-x_4)\,\mathbf{a_2}+\left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\left(-x_4\,a+\left(\frac{1}{2}-z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}}+y_4\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O IV
$\mathbf{B_{11}}$	=	$(y_4-x_4)\,\mathbf{a_1}-(x_4+y_4)\,\mathbf{a_2}-z_4\,\mathbf{a_3}$	=	$-(x_4\,a+z_4\,c\,\cos\beta)\,\hat{\mathbf{x}}-y_4\,b\,\hat{\mathbf{y}}-z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O IV
$\mathbf{B_{12}}$	=	$(x_4+y_4)\,\mathbf{a_1}+(x_4-y_4)\,\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\left(x_4\,a+\left(\frac{1}{2}+z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_4\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O IV
$\mathbf{B_{13}}$	=	$(x_5-y_5)\,\mathbf{a_1}+(x_5+y_5)\,\mathbf{a_2}+z_5\,\mathbf{a_3}$	=	$(x_5\,a+z_5\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_5\,b\,\hat{\mathbf{y}}+z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O V
$\mathbf{B_{14}}$	=	$-(x_5+y_5)\,\mathbf{a_1}+(y_5-x_5)\,\mathbf{a_2}+\left(\frac{1}{2}-z_5\right)\mathbf{a_3}$	=	$\left(-x_5\,a+\left(\frac{1}{2}-z_5\right)c\,\cos\beta\right)\hat{\mathbf{x}}+y_5\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_5\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O V
$\mathbf{B_{15}}$	=	$(y_5-x_5)\,\mathbf{a_1}-(x_5+y_5)\,\mathbf{a_2}-z_5\,\mathbf{a_3}$	=	$-(x_5\,a+z_5\,c\,\cos\beta)\,\hat{\mathbf{x}}-y_5\,b\,\hat{\mathbf{y}}-z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O V
$\mathbf{B_{16}}$	=	$(x_5+y_5)\,\mathbf{a_1}+(x_5-y_5)\,\mathbf{a_2}+\left(\frac{1}{2}+z_5\right)\mathbf{a_3}$	=	$\left(x_5\,a+\left(\frac{1}{2}+z_5\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_5\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_5\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	O V
$\mathbf{B_{17}}$	=	$(x_6-y_6)\,\mathbf{a_1}+(x_6+y_6)\,\mathbf{a_2}+z_6\,\mathbf{a_3}$	=	$(x_6\,a+z_6\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_6\,b\,\hat{\mathbf{y}}+z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Si I
$\mathbf{B_{18}}$	=	$-(x_6+y_6)\,\mathbf{a_1}+(y_6-x_6)\,\mathbf{a_2}+\left(\frac{1}{2}-z_6\right)\mathbf{a_3}$	=	$\left(-x_6\,a+\left(\frac{1}{2}-z_6\right)c\,\cos\beta\right)\hat{\mathbf{x}}+y_6\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_6\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Si I
$\mathbf{B_{19}}$	=	$(y_6-x_6)\,\mathbf{a_1}-(x_6+y_6)\,\mathbf{a_2}-z_6\,\mathbf{a_3}$	=	$-(x_6\,a+z_6\,c\,\cos\beta)\,\hat{\mathbf{x}}-y_6\,b\,\hat{\mathbf{y}}-z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Si I
$\mathbf{B_{20}}$	=	$(x_6+y_6)\,\mathbf{a_1}+(x_6-y_6)\,\mathbf{a_2}+\left(\frac{1}{2}+z_6\right)\mathbf{a_3}$	=	$\left(x_6\,a+\left(\frac{1}{2}+z_6\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_6\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_6\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Si I
$\mathbf{B_{21}}$	=	$(x_7-y_7)\,\mathbf{a_1}+(x_7+y_7)\,\mathbf{a_2}+z_7\,\mathbf{a_3}$	=	$(x_7\,a+z_7\,c\,\cos\beta)\,\hat{\mathbf{x}}+y_7\,b\,\hat{\mathbf{y}}+z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Si II
$\mathbf{B_{22}}$	=	$-(x_7+y_7)\,\mathbf{a_1}+(y_7-x_7)\,\mathbf{a_2}+\left(\frac{1}{2}-z_7\right)\mathbf{a_3}$	=	$\left(-x_7\,a+\left(\frac{1}{2}-z_7\right)c\,\cos\beta\right)\hat{\mathbf{x}}+y_7\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_7\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Si II
$\mathbf{B_{23}}$	=	$(y_7-x_7)\,\mathbf{a_1}-(x_7+y_7)\,\mathbf{a_2}-z_7\,\mathbf{a_3}$	=	$-(x_7\,a+z_7\,c\,\cos\beta)\,\hat{\mathbf{x}}-y_7\,b\,\hat{\mathbf{y}}-z_7\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Si II
$\mathbf{B_{24}}$	=	$(x_7+y_7)\,\mathbf{a_1}+(x_7-y_7)\,\mathbf{a_2}+\left(\frac{1}{2}+z_7\right)\mathbf{a_3}$	=	$\left(x_7\,a+\left(\frac{1}{2}+z_7\right)c\,\cos\beta\right)\hat{\mathbf{x}}-y_7\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_7\right)c\,\sin\beta\,\hat{\mathbf{z}}$	$(8f)$	Si II

References:

- L. Levien and C. T. Prewitt, *High-pressure crystal structure and compressibility of coesite*, Am. Mineral. **66**, 324–333 (1981).

Geometry files:

- CIF: pp. S650
- POSCAR: pp. S650

Esseneite Structure: ABC6D2_mC40_15_e_e_3f_f

Prototype	:	$CaFeO_6Si_2$
AFLOW prototype label	:	ABC6D2_mC40_15_e_e_3f_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	mC40
Space group number	:	15
Space group symbol	:	C2/c
AFLOW prototype command	:	`aflow --proto=ABC6D2_mC40_15_e_e_3f_f` `--params=`$a, b/a, c/a, \beta, y_1, y_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6$

- Named for University of Michigan geologist Eric Essene (1939-2010). (Cosca, 1987) gives the composition as $(Ca_{0.97}Fe_{0.03})(Fe_{0.58}Al_{0.42})O_6(Si_{0.54}Al_{0.46})_2$. We will use the majority atom at each site to draw the structure.

Base-centered Monoclinic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\cos\beta\,\hat{\mathbf{x}} + c\sin\beta\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Ca
$\mathbf{B_2}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	$(4e)$	Ca

$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Fe
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\cos\beta\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\sin\beta\,\hat{\mathbf{z}}$	(4*e*)	Fe
$\mathbf{B_5}$	=	$(x_3 - y_3)\,\mathbf{a_1} + (x_3 + y_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O I
$\mathbf{B_6}$	=	$-(x_3 + y_3)\,\mathbf{a_1} + (y_3 - x_3)\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$\left(-x_3\,a + \left(\frac{1}{2} - z_3\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O I
$\mathbf{B_7}$	=	$(y_3 - x_3)\,\mathbf{a_1} - (x_3 + y_3)\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-(x_3\,a + z_3\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O I
$\mathbf{B_8}$	=	$(x_3 + y_3)\,\mathbf{a_1} + (x_3 - y_3)\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(x_3\,a + \left(\frac{1}{2} + z_3\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O I
$\mathbf{B_9}$	=	$(x_4 - y_4)\,\mathbf{a_1} + (x_4 + y_4)\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O II
$\mathbf{B_{10}}$	=	$-(x_4 + y_4)\,\mathbf{a_1} + (y_4 - x_4)\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$\left(-x_4\,a + \left(\frac{1}{2} - z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O II
$\mathbf{B_{11}}$	=	$(y_4 - x_4)\,\mathbf{a_1} - (x_4 + y_4)\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-(x_4\,a + z_4\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O II
$\mathbf{B_{12}}$	=	$(x_4 + y_4)\,\mathbf{a_1} + (x_4 - y_4)\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\left(x_4\,a + \left(\frac{1}{2} + z_4\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O II
$\mathbf{B_{13}}$	=	$(x_5 - y_5)\,\mathbf{a_1} + (x_5 + y_5)\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O III
$\mathbf{B_{14}}$	=	$-(x_5 + y_5)\,\mathbf{a_1} + (y_5 - x_5)\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\left(-x_5\,a + \left(\frac{1}{2} - z_5\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O III
$\mathbf{B_{15}}$	=	$(y_5 - x_5)\,\mathbf{a_1} - (x_5 + y_5)\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-(x_5\,a + z_5\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} - z_5\,c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O III
$\mathbf{B_{16}}$	=	$(x_5 + y_5)\,\mathbf{a_1} + (x_5 - y_5)\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(x_5\,a + \left(\frac{1}{2} + z_5\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	O III
$\mathbf{B_{17}}$	=	$(x_6 - y_6)\,\mathbf{a_1} + (x_6 + y_6)\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	Si
$\mathbf{B_{18}}$	=	$-(x_6 + y_6)\,\mathbf{a_1} + (y_6 - x_6)\,\mathbf{a_2} + \left(\frac{1}{2} - z_6\right)\mathbf{a_3}$	=	$\left(-x_6\,a + \left(\frac{1}{2} - z_6\right)c\,\cos\beta\right)\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_6\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	Si
$\mathbf{B_{19}}$	=	$(y_6 - x_6)\,\mathbf{a_1} - (x_6 + y_6)\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-(x_6\,a + z_6\,c\,\cos\beta)\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	Si
$\mathbf{B_{20}}$	=	$(x_6 + y_6)\,\mathbf{a_1} + (x_6 - y_6)\,\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\mathbf{a_3}$	=	$\left(x_6\,a + \left(\frac{1}{2} + z_6\right)c\,\cos\beta\right)\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)c\,\sin\beta\,\hat{\mathbf{z}}$	(8*f*)	Si

References:

- M. A. Cosca and D. R. Peacor, *Chemistry and structure of esseneite ($CaFe^{3+}AlSiO_6$), a new pyroxene produced by pyrometamorphism*, Am. Mineral. **72**, 148–156 (1987).

Geometry files:

- CIF: pp. S651
- POSCAR: pp. S651

$AlPS_4$ Structure: ABC4_oP12_16_ag_cd_2u

Prototype	:	$AlPS_4$
AFLOW prototype label	:	ABC4_oP12_16_ag_cd_2u
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP12
Space group number	:	16
Space group symbol	:	P222
AFLOW prototype command	:	`aflow --proto=ABC4_oP12_16_ag_cd_2u --params=`$a, b/a, c/a, x_5, y_5, z_5, x_6, y_6, z_6$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Al I
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_2}$	=	$\frac{1}{2}\,b\,\hat{\mathbf{y}}$	$(1c)$	P I
$\mathbf{B_3}$	=	$\frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1d)$	P II
$\mathbf{B_4}$	=	$\frac{1}{2}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1g)$	Al II
$\mathbf{B_5}$	=	$x_5\mathbf{a_1} + y_5\mathbf{a_2} + z_5\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4u)$	S I
$\mathbf{B_6}$	=	$-x_5\mathbf{a_1} - y_5\mathbf{a_2} + z_5\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4u)$	S I
$\mathbf{B_7}$	=	$-x_5\mathbf{a_1} + y_5\mathbf{a_2} - z_5\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(4u)$	S I

$\mathbf{B_8}$	=	$x_5\mathbf{a_1} - y_5\mathbf{a_2} - z_5\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(4u)$	S I
$\mathbf{B_9}$	=	$x_6\mathbf{a_1} + y_6\mathbf{a_2} + z_6\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(4u)$	S II
$\mathbf{B_{10}}$	=	$-x_6\mathbf{a_1} - y_6\mathbf{a_2} + z_6\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(4u)$	S II
$\mathbf{B_{11}}$	=	$-x_6\mathbf{a_1} + y_6\mathbf{a_2} - z_6\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\hat{\mathbf{z}}$	$(4u)$	S II
$\mathbf{B_{12}}$	=	$x_6\mathbf{a_1} - y_6\mathbf{a_2} - z_6\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} - z_6\,c\,\hat{\mathbf{z}}$	$(4u)$	S II

References:

- A. Weiss and H. Schäfer, *Zur Kenntnis von Aluminiumthiophosphat* $AlPS_4$, Naturwissenschaften **47**, 495 (1960), doi:10.1007/BF00631053.

Geometry files:

- CIF: pp. S651
- POSCAR: pp. S652

BaS_3 Structure: AB3_oP16_18_ab_3c

Prototype	:	BaS_3
AFLOW prototype label	:	AB3_oP16_18_ab_3c
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP16
Space group number	:	18
Space group symbol	:	$P2_12_12$
AFLOW prototype command	:	`aflow --proto=AB3_oP16_18_ab_3c` `--params=`$a, b/a, c/a, z_1, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5$

- Not to be confused with the other BaS_3 ($D0_{17}$) structure, which has space group $P\bar{4}2_1m$ (#113).

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Ba I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Ba I

$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,b\,\hat{y} + z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	Ba II
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	Ba II
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4c)$	S I
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4c)$	S I
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \left(\frac{1}{2} + y_3\right)\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4c)$	S I
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \left(\frac{1}{2} - y_3\right)\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4c)$	S I
$\mathbf{B_9}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(4c)$	S II
$\mathbf{B_{10}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(4c)$	S II
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)b\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(4c)$	S II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)b\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(4c)$	S II
$\mathbf{B_{13}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4c)$	S III
$\mathbf{B_{14}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4c)$	S III
$\mathbf{B_{15}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + \left(\frac{1}{2} + y_5\right)\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_5\right)b\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(4c)$	S III
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} + \left(\frac{1}{2} - y_5\right)\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_5\right)b\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(4c)$	S III

References:

- W. S. Miller and A. J. King, *The Structure of Polysulfides: I. Barium Trisulfide*, Zeitschrift für Kristallographie - Crystalline Materials **94**, 439–446 (1936), doi:10.1524/zkri.1936.94.1.439.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1701.

Geometry files:

- CIF: pp. S652
- POSCAR: pp. S652

Naumannite (Ag_2Se) Structure: A2B_oP12_19_2a_a

Prototype	:	Ag_2Se
AFLOW prototype label	:	A2B_oP12_19_2a_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP12
Space group number	:	19
Space group symbol	:	$P2_12_12_1$
AFLOW prototype command	:	`aflow --proto=A2B_oP12_19_2a_a` `--params=`$a, b/a, c/a, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3$

Simple Orthorhombic primitive vectors:

$$\mathbf{a_1} = a\,\hat{\mathbf{x}}$$
$$\mathbf{a_2} = b\,\hat{\mathbf{y}}$$
$$\mathbf{a_3} = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4a)$	Ag I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4a)$	Ag I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(4a)$	Ag I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right)b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4a)$	Ag I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4a)$	Ag II

$\mathbf{B_6}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-y_2\,\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}-y_2\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(4*a*)	Ag II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+y_2\right)\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(4*a*)	Ag II
$\mathbf{B_8}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-y_2\right)\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)b\,\hat{\mathbf{y}}-z_2\,c\,\hat{\mathbf{z}}$	(4*a*)	Ag II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1}+y_3\,\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(4*a*)	Se
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}-y_3\,\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(4*a*)	Se
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(4*a*)	Se
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(4*a*)	Se

References:

- G. A. Wiegers, *The Crystal Structure of the Low-Temperature Form of Silver Selenide*, Am. Mineral. **56**, 1882–1888 (1971).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 626.

Geometry files:

- CIF: pp. S652
- POSCAR: pp. S652

Orthorhombic Tridymite (SiO_2) Structure: A2B_oC24_20_abc_c

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_oC24_20_abc_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	oC24
Space group number	:	20
Space group symbol	:	$C222_1$
AFLOW prototype command	:	`aflow --proto=A2B_oC24_20_abc_c` `--params=`$a, b/a, c/a, x_1, y_2, x_3, y_3, z_3, x_4, y_4, z_4$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}}$	$(4a)$	O I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\hat{\mathbf{z}}$	$(4a)$	O I
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4b)$	O II
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4b)$	O II

$\mathbf{B_5}$	=	$(x_3 - y_3)\ \mathbf{a_1} + (x_3 + y_3)\ \mathbf{a_2} + z_3\ \mathbf{a_3}$	=	$x_3\ a\hat{\mathbf{x}} + y_3\ b\ \hat{\mathbf{y}} + z_3\ c\hat{\mathbf{z}}$	(8c)	O III
$\mathbf{B_6}$	=	$(y_3 - x_3)\ \mathbf{a_1} - (x_3 + y_3)\ \mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\ \mathbf{a_3}$	=	$-x_3\ a\hat{\mathbf{x}} - y_3\ b\ \hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\ c\hat{\mathbf{z}}$	(8c)	O III
$\mathbf{B_7}$	=	$-(x_3 + y_3)\ \mathbf{a_1} + (y_3 - x_3)\ \mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\ \mathbf{a_3}$	=	$-x_3\ a\hat{\mathbf{x}} + y_3\ b\ \hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\ c\hat{\mathbf{z}}$	(8c)	O III
$\mathbf{B_8}$	=	$(x_3 + y_3)\ \mathbf{a_1} + (x_3 - y_3)\ \mathbf{a_2} - z_3\ \mathbf{a_3}$	=	$x_3\ a\hat{\mathbf{x}} - y_3\ b\ \hat{\mathbf{y}} - z_3\ c\hat{\mathbf{z}}$	(8c)	O III
$\mathbf{B_9}$	=	$(x_4 - y_4)\ \mathbf{a_1} + (x_4 + y_4)\ \mathbf{a_2} + z_4\ \mathbf{a_3}$	=	$x_4\ a\hat{\mathbf{x}} + y_4\ b\ \hat{\mathbf{y}} + z_4\ c\hat{\mathbf{z}}$	(8c)	Si
$\mathbf{B_{10}}$	=	$(y_4 - x_4)\ \mathbf{a_1} - (x_4 + y_4)\ \mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\ \mathbf{a_3}$	=	$-x_4\ a\hat{\mathbf{x}} - y_4\ b\ \hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\ c\hat{\mathbf{z}}$	(8c)	Si
$\mathbf{B_{11}}$	=	$-(x_4 + y_4)\ \mathbf{a_1} + (y_4 - x_4)\ \mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\ \mathbf{a_3}$	=	$-x_4\ a\hat{\mathbf{x}} + y_4\ b\ \hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\ c\hat{\mathbf{z}}$	(8c)	Si
$\mathbf{B_{12}}$	=	$(x_4 + y_4)\ \mathbf{a_1} + (x_4 - y_4)\ \mathbf{a_2} - z_4\ \mathbf{a_3}$	=	$x_4\ a\hat{\mathbf{x}} - y_4\ b\ \hat{\mathbf{y}} - z_4\ c\hat{\mathbf{z}}$	(8c)	Si

References:

- W. A. Dollase, *The crystal structure at 220°C of orthorhombic high tridymite from the Steinbach meteorite*, Acta Cryst. **23**, 617–623 (1967), doi:10.1107/S0365110X67003287.

Geometry files:

- CIF: pp. S653
- POSCAR: pp. S653

High-Pressure CdTe Structure: AB_oP2_25_b_a

Prototype	:	CdTe
AFLOW prototype label	:	AB_oP2_25_b_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP2
Space group number	:	25
Space group symbol	:	Pmm2
AFLOW prototype command	:	`aflow --proto=AB_oP2_25_b_a` `--params=`$a, b/a, c/a, z_1, z_2$

- This is a high-pressure phase of CdTe. We use the data given for a pressure of 19.3 GPa.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(1a)$	Te
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(1b)$	Cd

References:
- J. Zhu Hu, *A New High Pressure Phase of CdTe*, Solid State Commun. **63**, 471–474 (1987), doi:10.1016/0038-1098(87)90273-0.

Found in:
- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 2816.

Geometry files:
- CIF: pp. S653
- POSCAR: pp. S653

Krennerite ($AuTe_2$, C46) Structure: AB2_oP24_28_acd_2c3d

Prototype	:	$AuTe_2$
AFLOW prototype label	:	AB2_oP24_28_acd_2c3d
***Strukturbericht* designation**	:	C46
Pearson symbol	:	oP24
Space group number	:	28
Space group symbol	:	Pma2
AFLOW prototype command	:	`aflow --proto=AB2_oP24_28_acd_2c3d` `--params=`$a, b/a, c/a, z_1, y_2, z_2, y_3, z_3, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8$

- The sample studied had composition ($Au_{0.88}$,$Ag_{0.12}$)Te_2. For simplicity we make all of the Au/Ag sites Au. (Pearson, 1972) states that this is a distortion of the trigonal ω phase. Note that $AuTe_2$ also exists in the C34 structure.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Au I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + z_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Au I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Au II
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} - y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Au II
$\mathbf{B_5}$	=	$\frac{1}{4}\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(2c)$	Te I

$\mathbf{B_6}$	=	$\frac{3}{4}\,\mathbf{a_1} - y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(2c)$	Te I
$\mathbf{B_7}$	=	$\frac{1}{4}\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(2c)$	Te II
$\mathbf{B_8}$	=	$\frac{3}{4}\,\mathbf{a_1} - y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(2c)$	Te II
$\mathbf{B_9}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4d)$	Au III
$\mathbf{B_{10}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4d)$	Au III
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} - y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4d)$	Au III
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4d)$	Au III
$\mathbf{B_{13}}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(4d)$	Te III
$\mathbf{B_{14}}$	=	$-x_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(4d)$	Te III
$\mathbf{B_{15}}$	=	$\left(\frac{1}{2} + x_6\right)\mathbf{a_1} - y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_6\right)a\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(4d)$	Te III
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} - x_6\right)\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_6\right)a\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(4d)$	Te III
$\mathbf{B_{17}}$	=	$x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\hat{\mathbf{z}}$	$(4d)$	Te IV
$\mathbf{B_{18}}$	=	$-x_7\,\mathbf{a_1} - y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\hat{\mathbf{z}}$	$(4d)$	Te IV
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2} + x_7\right)\mathbf{a_1} - y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_7\right)a\,\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\hat{\mathbf{z}}$	$(4d)$	Te IV
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} - x_7\right)\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_7\right)a\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\hat{\mathbf{z}}$	$(4d)$	Te IV
$\mathbf{B_{21}}$	=	$x_8\,\mathbf{a_1} + y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$x_8\,a\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\hat{\mathbf{z}}$	$(4d)$	Te V
$\mathbf{B_{22}}$	=	$-x_8\,\mathbf{a_1} - y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$-x_8\,a\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\hat{\mathbf{z}}$	$(4d)$	Te V
$\mathbf{B_{23}}$	=	$\left(\frac{1}{2} + x_8\right)\mathbf{a_1} - y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_8\right)a\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\hat{\mathbf{z}}$	$(4d)$	Te V
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2} - x_8\right)\mathbf{a_1} + y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_8\right)a\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\hat{\mathbf{z}}$	$(4d)$	Te V

References:

- G. Tunell and K. J. Murata, *The Atomic Arrangement and Chemical Composition of Krennerite*, The American Mineralogist **35**, 959–984 (1950).
- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972).

Geometry files:

- CIF: pp. S653
- POSCAR: pp. S654

Enargite ($AsCu_3S_4$, $H2_5$) Structure: AB3C4_oP16_31_a_ab_2ab

Prototype	:	$AsCu_3S_4$
AFLOW prototype label	:	AB3C4_oP16_31_a_ab_2ab
***Strukturbericht* designation**	:	$H2_5$
Pearson symbol	:	oP16
Space group number	:	31
Space group symbol	:	$Pmn2_1$
AFLOW prototype command	:	`aflow --proto=AB3C4_oP16_31_a_ab_2ab` `--params=`$a, b/a, c/a, y_1, z_1, y_2, z_2, y_3, z_3, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6$

- This structure should not be confused with the lazarevićite form of $AsCu_3S_4$, which is related to an sp^3 cubic structure.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	As
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)\,c\,\hat{\mathbf{z}}$	$(2a)$	As
$\mathbf{B_3}$	=	$y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2a)$	Cu I
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	$(2a)$	Cu I

$\mathbf{B_5}$	=	$y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(2a)$	S I
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\hat{\mathbf{z}}$	$(2a)$	S I
$\mathbf{B_7}$	=	$y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(2a)$	S II
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(2a)$	S II
$\mathbf{B_9}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4b)$	Cu II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - x_5\right)\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)\,a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)\,c\,\hat{\mathbf{z}}$	$(4b)$	Cu II
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2} + x_5\right)\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)\,a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)\,c\,\hat{\mathbf{z}}$	$(4b)$	Cu II
$\mathbf{B_{12}}$	=	$-x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4b)$	Cu II
$\mathbf{B_{13}}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(4b)$	S III
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2} - x_6\right)\,\mathbf{a_1} - y_6\,\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_6\right)\,a\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)\,c\,\hat{\mathbf{z}}$	$(4b)$	S III
$\mathbf{B_{15}}$	=	$\left(\frac{1}{2} + x_6\right)\,\mathbf{a_1} - y_6\,\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_6\right)\,a\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)\,c\,\hat{\mathbf{z}}$	$(4b)$	S III
$\mathbf{B_{16}}$	=	$-x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(4b)$	S III

References:

- G. Adiwidjaja and J. Löhn, *Strukturverfeinerung von Enargit, Cu_3AsS_4*, Acta Crystallogr. Sect. B Struct. Sci. **26**, 1878–1879 (1970), doi:10.1107/S0567740870005034.

Geometry files:

- CIF: pp. S654
- POSCAR: pp. S654

Modderite (CoAs) Structure: AB_oP8_33_a_a

Prototype	:	CoAs
AFLOW prototype label	:	AB_oP8_33_a_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP8
Space group number	:	33
Space group symbol	:	$Pna2_1$
AFLOW prototype command	:	`aflow --proto=AB_oP8_33_a_a` `--params=`$a, b/a, c/a, x_1, y_1, z_1, x_2, y_2, z_2$

Other compounds with this structure:

- FeAs

- (Lyman, 1984) arbitrarily set $z_2 = 1/4$, which is allowed for this space group. When $z_1 = z_2 = 1/4$, the space group becomes Pnma and the structure is equivalent to MnP (B31). (Lyman, 1984) lists both space groups for both CoAs and FeAs, and prefers the MnP structure for these compounds.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4a)$	As

$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)\,c\,\hat{\mathbf{z}}$	(4*a*)	As
$\mathbf{B_3}$	=	$\left(\frac{1}{2} + x_1\right)\,\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right)\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	(4*a*)	As
$\mathbf{B_4}$	=	$\left(\frac{1}{2} - x_1\right)\,\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)\,c\,\hat{\mathbf{z}}$	(4*a*)	As
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4*a*)	Co
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	(4*a*)	Co
$\mathbf{B_7}$	=	$\left(\frac{1}{2} + x_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4*a*)	Co
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - x_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	(4*a*)	Co

References:

- P. S. Lyman and C. T. Prewitt, *Room- and high-pressure crystal chemistry of CoAs and FeAs*, Acta Crystallogr. Sect. B Struct. Sci. **40**, 14–20 (1984), doi:10.1107/S0108768184001695.

Geometry files:

- CIF: pp. S655
- POSCAR: pp. S655

AsK_3S_4 Structure: AB3C4_oP32_33_a_3a_4a

Prototype	:	AsK_3S_4
AFLOW prototype label	:	AB3C4_oP32_33_a_3a_4a
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP32
Space group number	:	33
Space group symbol	:	$Pna2_1$
AFLOW prototype command	:	`aflow --proto=AB3C4_oP32_33_a_3a_4a` `--params=`$a, b/a, c/a, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8$

- Note that the authors arbitrarily set $z_2 = 1/4$, as is allowed by this space group.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4a)$	As

$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	(4*a*)	As
$\mathbf{B_3}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right)b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	(4*a*)	As
$\mathbf{B_4}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	(4*a*)	As
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4*a*)	K I
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(4*a*)	K I
$\mathbf{B_7}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4*a*)	K I
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(4*a*)	K I
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(4*a*)	K II
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	(4*a*)	K II
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \left(\frac{1}{2} - y_3\right)\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(4*a*)	K II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \left(\frac{1}{2} + y_3\right)\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	(4*a*)	K II
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(4*a*)	K III
$\mathbf{B_{14}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	(4*a*)	K III
$\mathbf{B_{15}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(4*a*)	K III
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	(4*a*)	K III
$\mathbf{B_{17}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(4*a*)	S I
$\mathbf{B_{18}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(4*a*)	S I
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} + \left(\frac{1}{2} - y_5\right)\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_5\right)b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(4*a*)	S I
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + \left(\frac{1}{2} + y_5\right)\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_5\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(4*a*)	S I
$\mathbf{B_{21}}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} + y_6\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	(4*a*)	S II
$\mathbf{B_{22}}$	=	$-x_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} - y_6\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)c\,\hat{\mathbf{z}}$	(4*a*)	S II
$\mathbf{B_{23}}$	=	$\left(\frac{1}{2} + x_6\right)\mathbf{a_1} + \left(\frac{1}{2} - y_6\right)\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_6\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_6\right)b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	(4*a*)	S II
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2} - x_6\right)\mathbf{a_1} + \left(\frac{1}{2} + y_6\right)\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_6\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_6\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)c\,\hat{\mathbf{z}}$	(4*a*)	S II
$\mathbf{B_{25}}$	=	$x_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}} + y_7\,b\,\hat{\mathbf{y}} + z_7\,c\,\hat{\mathbf{z}}$	(4*a*)	S III
$\mathbf{B_{26}}$	=	$-x_7\,\mathbf{a_1} - y_7\,\mathbf{a_2} + \left(\frac{1}{2} + z_7\right)\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}} - y_7\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_7\right)c\,\hat{\mathbf{z}}$	(4*a*)	S III
$\mathbf{B_{27}}$	=	$\left(\frac{1}{2} + x_7\right)\mathbf{a_1} + \left(\frac{1}{2} - y_7\right)\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_7\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_7\right)b\,\hat{\mathbf{y}} + z_7\,c\,\hat{\mathbf{z}}$	(4*a*)	S III
$\mathbf{B_{28}}$	=	$\left(\frac{1}{2} - x_7\right)\mathbf{a_1} + \left(\frac{1}{2} + y_7\right)\mathbf{a_2} + \left(\frac{1}{2} + z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_7\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_7\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_7\right)c\,\hat{\mathbf{z}}$	(4*a*)	S III
$\mathbf{B_{29}}$	=	$x_8\,\mathbf{a_1} + y_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$x_8\,a\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\,\hat{\mathbf{z}}$	(4*a*)	S IV
$\mathbf{B_{30}}$	=	$-x_8\,\mathbf{a_1} - y_8\,\mathbf{a_2} + \left(\frac{1}{2} + z_8\right)\mathbf{a_3}$	=	$-x_8\,a\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_8\right)c\,\hat{\mathbf{z}}$	(4*a*)	S IV
$\mathbf{B_{31}}$	=	$\left(\frac{1}{2} + x_8\right)\mathbf{a_1} + \left(\frac{1}{2} - y_8\right)\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_8\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_8\right)b\,\hat{\mathbf{y}} + z_8\,c\,\hat{\mathbf{z}}$	(4*a*)	S IV

$$\mathbf{B_{32}} = \left(\tfrac{1}{2} - x_8\right)\mathbf{a_1} + \left(\tfrac{1}{2} + y_8\right)\mathbf{a_2} + \left(\tfrac{1}{2} + z_8\right)\mathbf{a_3} = \left(\tfrac{1}{2} - x_8\right) a\,\hat{\mathbf{x}} + \left(\tfrac{1}{2} + y_8\right) b\,\hat{\mathbf{y}} + \left(\tfrac{1}{2} + z_8\right) c\,\hat{\mathbf{z}} \quad (4a) \quad \text{S IV}$$

References:

- M. Palazzi, S. Jaulmes, and P. Laruelle, *Structure cristalline de K_3AsS_4*, Acta Crystallogr. Sect. B Struct. Sci. **30**, 2378–2381 (1974), doi:10.1107/S0567740874007151.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1164.

Geometry files:

- CIF: pp. S655
- POSCAR: pp. S655

$HgBr_2$ (C24) Structure: A2B_oC12_36_2a_a

Prototype	:	$HgBr_2$
AFLOW prototype label	:	A2B_oC12_36_2a_a
***Strukturbericht* designation**	:	C24
Pearson symbol	:	oC12
Space group number	:	36
Space group symbol	:	$Cmc2_1$
AFLOW prototype command	:	`aflow --proto=A2B_oC12_36_2a_a` `--params=`$a, b/a, c/a, y_1, z_1, y_2, z_2, y_3, z_3$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + z_1\,c\hat{\mathbf{z}}$	$(4a)$	Br I
$\mathbf{B_2}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$-y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\hat{\mathbf{z}}$	$(4a)$	Br I
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$y_2\,b\,\hat{\mathbf{y}} + z_2\,c\hat{\mathbf{z}}$	$(4a)$	Br II
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$-y_2\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\hat{\mathbf{z}}$	$(4a)$	Br II
$\mathbf{B_5}$	=	$-y_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$y_3\,b\,\hat{\mathbf{y}} + z_3\,c\hat{\mathbf{z}}$	$(4a)$	Hg
$\mathbf{B_6}$	=	$y_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$-y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\hat{\mathbf{z}}$	$(4a)$	Hg

References:

- H. Braekken, *Zur Kristallstruktur des Quecksilberbromids* $HgBr_2$, Zeitschrift für Kristallographie - Crystalline Materials **81**, 152–154 (1932), doi:10.1524/zkri.1932.81.1.152.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S656
- POSCAR: pp. S656

C_2CeNi Structure: A2BC_oC8_38_e_a_b

Prototype	:	C_2CeNi
AFLOW prototype label	:	A2BC_oC8_38_e_a_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	oC8
Space group number	:	38
Space group symbol	:	Amm2
AFLOW prototype command	:	`aflow --proto=A2BC_oC8_38_e_a_b` `--params=`$a, b/a, c/a, z_1, z_2, y_3, z_3$

Other compounds with this structure:

- C_2CoDy, C_2ErFe, C_2FeSm, C_2NiPa, C_2NiYb, C_2PrRh, many other C_2XY

Base-centered Orthorhombic primitive vectors:

$$\begin{aligned}
\mathbf{a}_1 &= a\,\hat{\mathbf{x}} \\
\mathbf{a}_2 &= \tfrac{1}{2}\,b\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}} \\
\mathbf{a}_3 &= \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}
\end{aligned}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-z_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Ce
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} - z_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	Ni
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + (y_3 - z_3)\,\mathbf{a_2} + (y_3 + z_3)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	C
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} - (y_3 + z_3)\,\mathbf{a_2} + (z_3 - y_3)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	C

References:

- O. Y. Bodak and J. P. Marusin, *The Crystal Structure of $RNiC_2$ Compounds (R=Ce,La,Pr)*, Dopovidi Akademii Nauk Ukrains'koj RSR Seriya A, Fiziko-Tekhnichni ta Matematichni Nauki **12**, 1048–1050 (1979).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1858-1859.

Geometry files:

- CIF: pp. S656
- POSCAR: pp. S656

Au_2V Structure: A2B_oC12_38_de_ab

Prototype	:	Au_2V
AFLOW prototype label	:	A2B_oC12_38_de_ab
***Strukturbericht* designation**	:	None
Pearson symbol	:	oC12
Space group number	:	38
Space group symbol	:	Amm2
AFLOW prototype command	:	`aflow --proto=A2B_oC12_38_de_ab` `--params=`$a, b/a, c/a, z_1, z_2, y_3, z_3, y_4, z_4$

Other compounds with this structure:

- Cu_2Ti, Pt_2Ta

- Note that the published atomic positions put the system in the Cmcm space group, despite the author's statement that the system is in the Amm2 space group. We forced this system into the Amm2 space group by slightly shifting the y_4 coordinate. If $y_3 = y_4$ then the space group becomes Cmcm.

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,b\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-z_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	V I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} - z_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	V II

$\mathbf{B_3}$	=	$(y_3 - z_3)\ \mathbf{a_2} + (y_3 + z_3)\ \mathbf{a_3}$	=	$y_3\, b\, \hat{\mathbf{y}} + z_3\, c\, \hat{\mathbf{z}}$	(4*d*)	Au I
$\mathbf{B_4}$	=	$-(y_3 + z_3)\ \mathbf{a_2} + (z_3 - y_3)\ \mathbf{a_3}$	=	$-y_3\, b\, \hat{\mathbf{y}} + z_3\, c\, \hat{\mathbf{z}}$	(4*d*)	Au I
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + (y_4 - z_4)\ \mathbf{a_2} + (y_4 + z_4)\ \mathbf{a_3}$	=	$\frac{1}{2}\, a\, \hat{\mathbf{x}} + y_4\, b\, \hat{\mathbf{y}} + z_4\, c\, \hat{\mathbf{z}}$	(4*e*)	Au II
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} - (y_4 + z_4)\ \mathbf{a_2} + (z_4 - y_4)\ \mathbf{a_3}$	=	$\frac{1}{2}\, a\, \hat{\mathbf{x}} - y_4\, b\, \hat{\mathbf{y}} + z_4\, c\, \hat{\mathbf{z}}$	(4*e*)	Au II

References:

- E. Stolz and K. Schubert, *Strukturuntersuchungen in einigen zu T^4-B^1 homologen und quasihomologen Systemen*, Z. Metallkd. **53**, 433–444 (1962).

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S656
- POSCAR: pp. S657

$PtSn_4$ Structure: AB4_oC20_41_a_2b

Prototype	:	$PtSn_4$
AFLOW prototype label	:	AB4_oC20_41_a_2b
***Strukturbericht* designation**	:	$D1_c$
Pearson symbol	:	oC20
Space group number	:	41
Space group symbol	:	Aba2
AFLOW prototype command	:	`aflow --proto=AB4_oC20_41_a_2b` `--params=`$a, b/a, c/a, z_1, x_2, y_2, z_2, x_3, y_3, z_3$

Other compounds with this structure:

- $AuSn_4$, $IrSn_4$, $PdSn_4$

- The published atomic positions have $x_2 = y_3$, $x_3 = y_2$ and $z_2 = -z_3$. This puts the system into space group Ccca. To get space group Aba2 we shifted the z_3 position slightly.

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,b\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-z_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(4a)$	Pt
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - z_1\right)\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4a)$	Pt

$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + (y_2 - z_2)\,\mathbf{a_2} + (y_2 + z_2)\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn I
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - (y_2 + z_2)\,\mathbf{a_2} + (z_2 - y_2)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn I
$\mathbf{B_5}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2 - z_2\right)\mathbf{a_2} + \left(\frac{1}{2} - y_2 + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn I
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + y_2 - z_2\right)\mathbf{a_2} + \left(\frac{1}{2} + y_2 + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn I
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + (y_3 - z_3)\,\mathbf{a_2} + (y_3 + z_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn II
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} - (y_3 + z_3)\,\mathbf{a_2} + (z_3 - y_3)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn II
$\mathbf{B_9}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \left(\frac{1}{2} - y_3 - z_3\right)\mathbf{a_2} + \left(\frac{1}{2} - y_3 + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \left(\frac{1}{2} + y_3 - z_3\right)\mathbf{a_2} + \left(\frac{1}{2} + y_3 + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn II

References:

- K. Schubert and U. Rösler, *Die Kristallstruktur von $PtSn_4$*, Z. Metallkd. **41**, 298–300 (1950).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 5001.

Geometry files:

- CIF: pp. S657
- POSCAR: pp. S657

$PdSn_2$ (C_e) Structure: AB2_oC24_41_2a_2b

Prototype	:	$PdSn_2$
AFLOW prototype label	:	AB2_oC24_41_2a_2b
***Strukturbericht* designation**	:	C_e
Pearson symbol	:	oC24
Space group number	:	41
Space group symbol	:	Aba2
AFLOW prototype command	:	`aflow --proto=AB2_oC24_41_2a_2b` `--params=`$a, b/a, c/a, z_1, z_2, x_3, y_3, z_3, x_4, y_4, z_4$

Other compounds with this structure:

- $CoGe_2$, $GaGe_3Ni_2$, $RhSn_2$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,b\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-z_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(4a)$	Pd I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - z_1\right)\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4a)$	Pd I
$\mathbf{B_3}$	=	$-z_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$z_2\,c\,\hat{\mathbf{z}}$	$(4a)$	Pd II
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - z_2\right)\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4a)$	Pd II
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + (y_3 - z_3)\,\mathbf{a_2} + (y_3 + z_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(8b)$	Sn I

$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - (y_3 + z_3)\,\mathbf{a_2} + (z_3 - y_3)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn I
$\mathbf{B_7}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \left(\frac{1}{2} - y_3 - z_3\right)\mathbf{a_2} + \left(\frac{1}{2} - y_3 + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn I
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \left(\frac{1}{2} + y_3 - z_3\right)\mathbf{a_2} + \left(\frac{1}{2} + y_3 + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn I
$\mathbf{B_9}$	=	$x_4\,\mathbf{a_1} + (y_4 - z_4)\,\mathbf{a_2} + (y_4 + z_4)\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn II
$\mathbf{B_{10}}$	=	$-x_4\,\mathbf{a_1} - (y_4 + z_4)\,\mathbf{a_2} + (z_4 - y_4)\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn II
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + \left(\frac{1}{2} - y_4 - z_4\right)\mathbf{a_2} + \left(\frac{1}{2} - y_4 + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + \left(\frac{1}{2} + y_4 - z_4\right)\mathbf{a_2} + \left(\frac{1}{2} + y_4 + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8*b*)	Sn II

References:

- K. Schubert and H. Pfisterer, *Zur Kristallchemie der B-Metall-reichsten Phasen in Legierungen von Übergangsmetallen der Eisen- und Platintriaden mit Elementen der vierten Nebengruppe*, Z. Metallkd. **41**, 433–441 (1950).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4929-4930.

Geometry files:

- CIF: pp. S657
- POSCAR: pp. S658

GeS_2 (C44) Structure: AB2_oF72_43_ab_3b

Prototype	:	GeS_2
AFLOW prototype label	:	AB2_oF72_43_ab_3b
***Strukturbericht* designation**	:	C44
Pearson symbol	:	oF72
Space group number	:	43
Space group symbol	:	Fdd2
AFLOW prototype command	:	`aflow --proto=AB2_oF72_43_ab_3b` `--params=`$a, b/a, c/a, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5$

Face-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\, b\, \hat{\mathbf{y}} + \tfrac{1}{2}\, c\, \hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\, a\, \hat{\mathbf{x}} + \tfrac{1}{2}\, c\, \hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\, a\, \hat{\mathbf{x}} + \tfrac{1}{2}\, b\, \hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\, \mathbf{a_1} + z_1\, \mathbf{a_2} - z_1\, \mathbf{a_3}$	=	$z_1\, c\, \hat{\mathbf{z}}$	$(8a)$	Ge I
$\mathbf{B_2}$	=	$\left(\frac{1}{4} + z_1\right) \mathbf{a_1} + \left(\frac{1}{4} + z_1\right) \mathbf{a_2} + \left(\frac{1}{4} - z_1\right) \mathbf{a_3}$	=	$\frac{1}{4}\, a\, \hat{\mathbf{x}} + \frac{1}{4}\, b\, \hat{\mathbf{y}} + \left(\frac{1}{4} + z_1\right) c\, \hat{\mathbf{z}}$	$(8a)$	Ge I
$\mathbf{B_3}$	=	$(-x_2 + y_2 + z_2)\, \mathbf{a_1} + (x_2 - y_2 + z_2)\, \mathbf{a_2} + (x_2 + y_2 - z_2)\, \mathbf{a_3}$	=	$x_2\, a\, \hat{\mathbf{x}} + y_2\, b\, \hat{\mathbf{y}} + z_2\, c\, \hat{\mathbf{z}}$	$(16b)$	Ge II
$\mathbf{B_4}$	=	$(x_2 - y_2 + z_2)\, \mathbf{a_1} + (-x_2 + y_2 + z_2)\, \mathbf{a_2} - (x_2 + y_2 + z_2)\, \mathbf{a_3}$	=	$-x_2\, a\, \hat{\mathbf{x}} - y_2\, b\, \hat{\mathbf{y}} + z_2\, c\, \hat{\mathbf{z}}$	$(16b)$	Ge II

$\mathbf{B_5}$	=	$\left(\frac{1}{4} - x_2 - y_2 + z_2\right)\mathbf{a_1} + \left(\frac{1}{4} + x_2 + y_2 + z_2\right)\mathbf{a_2} + \left(\frac{1}{4} + x_2 - y_2 - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_2\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_2\right) c\,\hat{\mathbf{z}}$	(16*b*)	Ge II
$\mathbf{B_6}$	=	$\left(\frac{1}{4} + x_2 + y_2 + z_2\right)\mathbf{a_1} + \left(\frac{1}{4} - x_2 - y_2 + z_2\right)\mathbf{a_2} + \left(\frac{1}{4} - x_2 + y_2 - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_2\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_2\right) c\,\hat{\mathbf{z}}$	(16*b*)	Ge II
$\mathbf{B_7}$	=	$(-x_3 + y_3 + z_3)\,\mathbf{a_1} + (x_3 - y_3 + z_3)\,\mathbf{a_2} + (x_3 + y_3 - z_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(16*b*)	S I
$\mathbf{B_8}$	=	$(x_3 - y_3 + z_3)\,\mathbf{a_1} + (-x_3 + y_3 + z_3)\,\mathbf{a_2} - (x_3 + y_3 + z_3)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(16*b*)	S I
$\mathbf{B_9}$	=	$\left(\frac{1}{4} - x_3 - y_3 + z_3\right)\mathbf{a_1} + \left(\frac{1}{4} + x_3 + y_3 + z_3\right)\mathbf{a_2} + \left(\frac{1}{4} + x_3 - y_3 - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_3\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right) c\,\hat{\mathbf{z}}$	(16*b*)	S I
$\mathbf{B_{10}}$	=	$\left(\frac{1}{4} + x_3 + y_3 + z_3\right)\mathbf{a_1} + \left(\frac{1}{4} - x_3 - y_3 + z_3\right)\mathbf{a_2} + \left(\frac{1}{4} - x_3 + y_3 - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_3\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right) c\,\hat{\mathbf{z}}$	(16*b*)	S I
$\mathbf{B_{11}}$	=	$(-x_4 + y_4 + z_4)\,\mathbf{a_1} + (x_4 - y_4 + z_4)\,\mathbf{a_2} + (x_4 + y_4 - z_4)\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(16*b*)	S II
$\mathbf{B_{12}}$	=	$(x_4 - y_4 + z_4)\,\mathbf{a_1} + (-x_4 + y_4 + z_4)\,\mathbf{a_2} - (x_4 + y_4 + z_4)\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(16*b*)	S II
$\mathbf{B_{13}}$	=	$\left(\frac{1}{4} - x_4 - y_4 + z_4\right)\mathbf{a_1} + \left(\frac{1}{4} + x_4 + y_4 + z_4\right)\mathbf{a_2} + \left(\frac{1}{4} + x_4 - y_4 - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_4\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_4\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right) c\,\hat{\mathbf{z}}$	(16*b*)	S II
$\mathbf{B_{14}}$	=	$\left(\frac{1}{4} + x_4 + y_4 + z_4\right)\mathbf{a_1} + \left(\frac{1}{4} - x_4 - y_4 + z_4\right)\mathbf{a_2} + \left(\frac{1}{4} - x_4 + y_4 - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_4\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_4\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right) c\,\hat{\mathbf{z}}$	(16*b*)	S II
$\mathbf{B_{15}}$	=	$(-x_5 + y_5 + z_5)\,\mathbf{a_1} + (x_5 - y_5 + z_5)\,\mathbf{a_2} + (x_5 + y_5 - z_5)\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(16*b*)	S III
$\mathbf{B_{16}}$	=	$(x_5 - y_5 + z_5)\,\mathbf{a_1} + (-x_5 + y_5 + z_5)\,\mathbf{a_2} - (x_5 + y_5 + z_5)\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - y_5\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(16*b*)	S III
$\mathbf{B_{17}}$	=	$\left(\frac{1}{4} - x_5 - y_5 + z_5\right)\mathbf{a_1} + \left(\frac{1}{4} + x_5 + y_5 + z_5\right)\mathbf{a_2} + \left(\frac{1}{4} + x_5 - y_5 - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_5\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_5\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_5\right) c\,\hat{\mathbf{z}}$	(16*b*)	S III
$\mathbf{B_{18}}$	=	$\left(\frac{1}{4} + x_5 + y_5 + z_5\right)\mathbf{a_1} + \left(\frac{1}{4} - x_5 - y_5 + z_5\right)\mathbf{a_2} + \left(\frac{1}{4} - x_5 + y_5 - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_5\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_5\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_5\right) c\,\hat{\mathbf{z}}$	(16*b*)	S III

References:

- W. H. Zachariasen, *The Crystal Structure of Germanium Disulphide*, J. Chem. Phys. **4**, 618–619 (1936),

doi:10.1063/1.1749915.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S658
- POSCAR: pp. S658

High-pressure GaAs Structure: AB_oI4_44_a_b

Prototype	:	GaAs
AFLOW prototype label	:	AB_oI4_44_a_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	oI4
Space group number	:	44
Space group symbol	:	Imm2
AFLOW prototype command	:	`aflow --proto=AB_oI4_44_a_b` `--params=`$a, b/a, c/a, z_1, z_2$

- This is a high-pressure phase of GaAs, stable above 24 GPa. The experimental data used here was taken at a pressure of 28.1 GPa. Without loss of generality we can take $z_1 = 0$. When $a = b$ and $z_2 = z_1 + 1/4$ this structure becomes the β-Sn (A5) structure.

Body-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_1} + z_1\,\mathbf{a_2}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	As
$\mathbf{B_2}$	=	$\left(\frac{1}{2} + z_2\right)\mathbf{a_1} + z_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	Ga

References:

- S. T. Weir, Y. K. Vohra, C. A. Vanderborgh, and A. L. Ruoff, *Structural phase transitions in GaAs to 108 GPa*, Phys. Rev. B **39**, 1280–1285 (1989), doi:10.1103/PhysRevB.39.1280.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1135.

Geometry files:

- CIF: pp. S658
- POSCAR: pp. S659

1212C [$YBa_2Cu_3O_{7-x}$] High-T_c Structure: A2B3C7D_oP13_47_t_aq_eqrs_h

Prototype	:	$YBa_2Cu_3O_{7-x}$
AFLOW prototype label	:	A2B3C7D_oP13_47_t_aq_eqrs_h
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP13
Space group number	:	47
Space group symbol	:	Pmmm
AFLOW prototype command	:	`aflow --proto=A2B3C7D_oP13_47_t_aq_eqrs_h` `--params=`$a, b/a, c/a, z_4, z_5, z_6, z_7, z_8$

Other compounds with this structure:

- $GaSr_2(Y,Ca)Cu_2O_7$

- The designation 1212C is from (Shaked, 1994). We will assume that the oxygen concentration is exactly 7. In experiment the O (2s) site is 92% occupied.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cu I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,b\,\hat{\mathbf{y}}$	$(1e)$	O I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1h)$	Y
$\mathbf{B_4}$	=	$z_4\,\mathbf{a_3}$	=	$z_4\,c\,\hat{\mathbf{z}}$	$(2q)$	Cu II

$\mathbf{B_5}$	=	$-z_4\,\mathbf{a_3}$	=	$-z_4\,c\,\hat{\mathbf{z}}$	$(2q)$	Cu II
$\mathbf{B_6}$	=	$z_5\,\mathbf{a_3}$	=	$z_5\,c\,\hat{\mathbf{z}}$	$(2q)$	O II
$\mathbf{B_7}$	=	$-z_5\,\mathbf{a_3}$	=	$-z_5\,c\,\hat{\mathbf{z}}$	$(2q)$	O II
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,b\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(2r)$	O III
$\mathbf{B_9}$	=	$\frac{1}{2}\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,b\,\hat{\mathbf{y}} - z_6\,c\,\hat{\mathbf{z}}$	$(2r)$	O III
$\mathbf{B_{10}}$	=	$\frac{1}{2}\,\mathbf{a_1} + z_7\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + z_7\,c\,\hat{\mathbf{z}}$	$(2s)$	O IV
$\mathbf{B_{11}}$	=	$\frac{1}{2}\,\mathbf{a_1} - z_7\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - z_7\,c\,\hat{\mathbf{z}}$	$(2s)$	O IV
$\mathbf{B_{12}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + z_8\,c\,\hat{\mathbf{z}}$	$(2t)$	Ba
$\mathbf{B_{13}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - z_8\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} - z_8\,c\,\hat{\mathbf{z}}$	$(2t)$	Ba

References:

- W. I. F. David, W. T. A. Harrison, J. M. F. Gunn, O. Moze, A. K. Soper, P. Day, J. D. Jorgensen, D. G. Hinks, M. A. Beno, L. Soderholm, D. W. Capone II, I. K. Schuller, C. U. Segre, K. Zhang, and J. D. Grace, *Structure and crystal chemistry of the high-T_c superconductor $YBa_2Cu_3O_{7-x}$*, Nature **327**, 310–312 (1987), doi:10.1038/327310a0.
- H. Shaked, P. M. Keane, J. C. Rodrigues, F. F. Owen, R. L. Hitterman, and J. D. Jorgensen, *Crystal Structures of the High-T_c Superconducting Copper-Oxides* (Elsevier Science B. V., Amsterdam, 1994).

Geometry files:

- CIF: pp. S659
- POSCAR: pp. S659

β'-AuCd (B19) Structure: AB_oP4_51_e_f

Prototype	:	β'-AuCd
AFLOW prototype label	:	AB_oP4_51_e_f
***Strukturbericht* designation**	:	B19
Pearson symbol	:	oP4
Space group number	:	51
Space group symbol	:	Pmma
AFLOW prototype command	:	`aflow --proto=AB_oP4_51_e_f --params=`$a, b/a, c/a, z_1, z_2$

- When $a = b = c$, $z_1 = 1/4$, and $z_2 = 3/4$ the atoms are on the sites of a face-centered cubic lattice. When $a = c$, $z_1 = 1/4$, and $z_2 = 3/4$ the system reduces to the $L1_0$ (AuCu) structure. When $a/b = (8/3)^{2/3}$, $c/b = 3^{1/2}$, $z_1 = 1/3$, and $z_2 = 5/6$, the atoms are on the sites of the hcp structure. Finally, when $z_2 = 1/2 + z_1$ the atoms are at the positions of the α-U structure.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + z_1\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + z_1\,c\,\hat{\mathbf{z}}$	$(2e)$	Au
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} - z_1\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} - z_1\,c\,\hat{\mathbf{z}}$	$(2e)$	Au
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2f)$	Cd
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2f)$	Cd

References:

- L.-C. Chang, *Atomic displacements and crystallographic mechanisms in diffusionless transformation of gold-cadium single crystals containing 47.5 atomic percent cadmium*, Acta Cryst. **4**, 320–324 (1951), doi:10.1107/S0365110X51001057.

Found in:

- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 313-314.

Geometry files:

- CIF: pp. S659
- POSCAR: pp. S660

Sb_2O_3 ($D5_{11}$) Structure: A3B2_oP20_56_ce_e

Prototype	:	Sb_2O_3
AFLOW prototype label	:	A3B2_oP20_56_ce_e
***Strukturbericht* designation**	:	$D5_{11}$
Pearson symbol	:	oP20
Space group number	:	56
Space group symbol	:	Pccn
AFLOW prototype command	:	`aflow --proto=A3B2_oP20_56_ce_e` `--params=`$a, b/a, c/a, z_1, x_2, y_2, z_2, x_3, y_3, z_3$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	($4c$)	O I
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	($4c$)	O I
$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	($4c$)	O I
$\mathbf{B_4}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	($4c$)	O I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	($8e$)	O II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	($8e$)	O II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	($8e$)	O II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	($8e$)	O II
$\mathbf{B_9}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	($8e$)	O II

$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}+y_2\right)\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)b\,\hat{\mathbf{y}}-z_2\,c\,\hat{\mathbf{z}}$	(8*e*)	O II
$\mathbf{B_{11}}$	=	$x_2\,\mathbf{a_1}+\left(\frac{1}{2}-y_2\right)\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(8*e*)	O II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}+y_2\,\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}+y_2\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(8*e*)	O II
$\mathbf{B_{13}}$	=	$x_3\,\mathbf{a_1}+y_3\,\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(8*e*)	Sb
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(8*e*)	Sb
$\mathbf{B_{15}}$	=	$-x_3\,\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(8*e*)	Sb
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}-y_3\,\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(8*e*)	Sb
$\mathbf{B_{17}}$	=	$-x_3\,\mathbf{a_1}-y_3\,\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(8*e*)	Sb
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(8*e*)	Sb
$\mathbf{B_{19}}$	=	$x_3\,\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(8*e*)	Sb
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}+y_3\,\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(8*e*)	Sb

References:

- C. Svensson, *The crystal structure of orthorhombic antimony trioxide, Sb_2O_3*, Acta Crystallogr. Sect. B Struct. Sci. **30**, 458–461 (1974), doi:10.1107/S0567740874002986.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S660
- POSCAR: pp. S660

KCNS ($F5_9$) Structure: ABCD_oP16_57_d_c_d_d

Prototype	:	KCNS
AFLOW prototype label	:	ABCD_oP16_57_d_c_d_d
***Strukturbericht* designation**	:	$F5_9$
Pearson symbol	:	oP16
Space group number	:	57
Space group symbol	:	Pbcm
AFLOW prototype command	:	`aflow --proto=ABCD_oP16_57_d_c_d_d` `--params=`$a, b/a, c/a, x_1, x_2, y_2, x_3, y_3, x_4, y_4$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}}$	$(4c)$	K
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4c)$	K
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}}$	$(4c)$	K
$\mathbf{B_4}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4c)$	K
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	C
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	C

$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	C
$\mathbf{B_8}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	C
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	N
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	N
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} + y_3\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	N
$\mathbf{B_{12}}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} - y_3\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	N
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	S
$\mathbf{B_{14}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	S
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	S
$\mathbf{B_{16}}$	=	$x_4\,\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	S

References:

- D. J. Cookson, M. M. Elcombe, and T. R. Finlayson, *Phonon dispersion relations for potassium thiocyanate at and above room temperature*, J. Phys.: Condens. Matter **4**, 7851–7864 (1992), doi:10.1088/0953-8984/4/39/001.

Found in:

- E. Nakamura, Y. Shiozaki, E. Nakamura, and T. Mitsui, *SpringerMaterials* (Springer-Verlag GmbH, Heidelberg, 2005).

Geometry files:

- CIF: pp. S660
- POSCAR: pp. S661

TlF-II Structure: AB_oP8_57_d_d

Prototype	:	TlF
AFLOW prototype label	:	AB_oP8_57_d_d
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP8
Space group number	:	57
Space group symbol	:	Pbcm
AFLOW prototype command	:	`aflow --proto=AB_oP8_57_d_d` `--params=`$a, b/a, c/a, x_1, y_1, x_2, y_2$

- This is the true low-temperature ground state of TlF. Like the B24 structure, it is a distortion of the rock salt (B1) structure.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	F
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	F
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	F
$\mathbf{B_4}$	=	$x_1\,\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right)\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	F

$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	Tl
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	Tl
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	Tl
$\mathbf{B_8}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	Tl

References:

- P. Berastegui and S. Hull, *The Crystal Structures of Thallium(I) Fluoride*, J. Solid State Chem. **150**, 266–275 (2000), doi:10.1006/jssc.1999.8587.

Geometry files:

- CIF: pp. S661
- POSCAR: pp. S661

Hydrophilite ($CaCl_2$, C35) Structure: AB2_oP6_58_a_g

Prototype	:	$CaCl_2$
AFLOW prototype label	:	AB2_oP6_58_a_g
***Strukturbericht* designation**	:	C35
Pearson symbol	:	oP6
Space group number	:	58
Space group symbol	:	Pnnm
AFLOW prototype command	:	`aflow --proto=AB2_oP6_58_a_g` `--params=`$a, b/a, c/a, x_2, y_2$

- Note that hydrophilite (pp. S130), η-Fe_2C (pp. S132), and marcasite (pp. S134) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ca
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	Ca
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}}$	$(4g)$	Cl

$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}}$	$(4g)$	Cl
$\mathbf{B_5}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4g)$	Cl
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4g)$	Cl

References:

- A. K. van Bever and W. Nieuwenkamp, *Die Kristallstruktur von Calciumchlorid, $CaCl_2$*, Zeitschrift für Kristallographie - Crystalline Materials **90**, 374–376 (1935), doi:10.1524/zkri.1935.90.1.374.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S661
- POSCAR: pp. S662

η-Fe_2C Structure: AB2_oP6_58_a_g

Prototype	:	η-Fe_2C
AFLOW prototype label	:	AB2_oP6_58_a_g
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP6
Space group number	:	58
Space group symbol	:	Pnnm
AFLOW prototype command	:	`aflow --proto=AB2_oP6_58_a_g` `--params=`$a, b/a, c/a, x_2, y_2$

- Classified as bcc-related by Hellner and Schwarz (Westbrook, 1995), Vol. I, Chap. 13. Note that hydrophilite (pp. S130), η-Fe_2C (pp. S132), and marcasite (pp. S134) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	C
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	C
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}}$	$(4g)$	Fe
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}}$	$(4g)$	Fe
$\mathbf{B_5}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4g)$	Fe
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4g)$	Fe

References:

- Y. Hirotsu and S. Nagakura, *Crystal structure and morphology of the carbide precipitated from martensitic high carbon steel during the first stage of tempering*, Acta Metallurgica **20**, 645–655 (1972), doi:10.1016/0001-6160(72)90020-X.
- J. H. Westbrook and R. L. Fleischer, *Intermetallic Compounds: Principles and Practice* (John Wiley & Sons, Chichester, New York, Brisbane, Toronto, Singapore, 1995).

Geometry files:

- CIF: pp. S662
- POSCAR: pp. S662

Marcasite (FeS_2, C18) Structure: AB2_oP6_58_a_g

Prototype	:	FeS_2
AFLOW prototype label	:	AB2_oP6_58_a_g
***Strukturbericht* designation**	:	C18
Pearson symbol	:	oP6
Space group number	:	58
Space group symbol	:	Pnnm
AFLOW prototype command	:	`aflow --proto=AB2_oP6_58_a_g` `--params=`$a, b/a, c/a, x_2, y_2$

Other compounds with this structure:

- As_2Co, $CrSb_2$, $NiSb_2$, CuS_2, FeP_2, $RuTe_2$, many more

- Note that hydrophilite (pp. S130), η-Fe_2C (pp. S132), and marcasite (pp. S134) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Fe
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	Fe

$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}}$	(4g)	S
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}}$	(4g)	S
$\mathbf{B_5}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(4g)	S
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(4g)	S

References:

- M. Rieder, J. C. Crelling, O. Šustai, M. Drábek, Z. Weiss, and M. Klementová, *Arsenic in iron disulfides in a brown coal from the North Bohemian Basin, Czech Republic*, Int. J. Coal Geol. **71**, 115–121 (2007), doi:10.1016/j.coal.2006.07.003.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S662
- POSCAR: pp. S662

Vulcanite (CuTe) Structure: AB_oP4_59_a_b

Prototype	:	CuTe
AFLOW prototype label	:	AB_oP4_59_a_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP4
Space group number	:	59
Space group symbol	:	Pmmn
AFLOW prototype command	:	`aflow --proto=AB_oP4_59_a_b` `--params=`$a, b/a, c/a, z_1, z_2$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Cu
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Cu
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	Te
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	Te

References:

- E. N. Cameron and I. M. Threadgold, *Vulcanite, a new copper telluride from Colorado, with notes on certain associated minerals*, Am. Mineral. **46**, 258–268 (1961).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:
- CIF: pp. S662
- POSCAR: pp. S663

CNCl Structure: ABC_oP6_59_a_a_a

Prototype	:	CNCl
AFLOW prototype label	:	ABC_oP6_59_a_a_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP6
Space group number	:	59
Space group symbol	:	Pmmn
AFLOW prototype command	:	`aflow --proto=ABC_oP6_59_a_a_a` `--params=`$a, b/a, c/a, z_1, z_2, z_3$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	C
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	C
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2a)$	Cl
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2a)$	Cl
$\mathbf{B_5}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(2a)$	N
$\mathbf{B_6}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(2a)$	N

References:

- R. B. Heiart and G. B. Carpenter, *The crystal structure of cyanogen chloride*, Acta Cryst. **9**, 889–895 (1956), doi:10.1107/S0365110X56002527.

Found in:

- R. W. G. Wyckoff, *Crystal Structures Vol. 1* (Wiley, 1963), 2nd edn, pp. 173-174.

Geometry files:

- CIF: pp. S663
- POSCAR: pp. S663

β-TiCu$_3$ (D0$_a$) Structure: A3B_oP8_59_bf_a

Prototype	:	β-TiCu$_3$
AFLOW prototype label	:	A3B_oP8_59_bf_a
***Strukturbericht* designation**	:	D0$_a$
Pearson symbol	:	oP8
Space group number	:	59
Space group symbol	:	Pmmn
AFLOW prototype command	:	`aflow --proto=A3B_oP8_59_bf_a` `--params=`$a, b/a, c/a, z_1, z_2, x_3, z_3$

- We have been so far unable to obtain the original reference (Karlsson, 1951), and Pearson does not give the exact atomic coordinates. Wyckoff positions have been deduced from the structure of Cu$_3$Sb, which Villars (1991) lists as having the TiCu$_3$ structure. Atomic positions are set to give the approximate nearest-neighbor distances listed in Pearson. (Giessen, 1971) says that (Karlsson, 1951) structure of β-TiCu$_3$ is mistaken. They do find a metastable β-TiCu$_3$ phase which has the same space group and Wyckoff positions, but substantially different lattice constants than the original determination for β-TiCu$_3$.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Ti
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Ti

$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	Cu I
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	Cu I
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Cu II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Cu II
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Cu II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Cu II

References:

- B. C. Giessen and D. Szymanski, *A metastable phase $TiCu_3$(m)*, J. Appl. Crystallogr. **4**, 257–259 (1971), doi:10.1107/S0021889871006824.
- N. Karlsson, -, J. Inst. Met. **79**, 391 (1951).

Found in:

- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 329-331.

Geometry files:

- CIF: pp. S663
- POSCAR: pp. S664

CdSb (B_e) Structure: AB_oP16_61_c_c

Prototype	:	CdSb
AFLOW prototype label	:	AB_oP16_61_c_c
***Strukturbericht* designation**	:	B_e
Pearson symbol	:	oP16
Space group number	:	61
Space group symbol	:	Pbca
AFLOW prototype command	:	`aflow --proto=AB_oP16_61_c_c` `--params=`$a, b/a, c/a, x_1, y_1, z_1, x_2, y_2, z_2$

Other compounds with this structure:

- AsCd, AsZn, SbZn

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(8c)$	Cd
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(8c)$	Cd

$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1}+\left(\frac{1}{2}+y_1\right)\mathbf{a_2}+\left(\frac{1}{2}-z_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_1\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_1\right)c\,\hat{\mathbf{z}}$	(8c)	Cd
$\mathbf{B_4}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}-y_1\right)\mathbf{a_2}-z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_1\right)b\,\hat{\mathbf{y}}-z_1\,c\,\hat{\mathbf{z}}$	(8c)	Cd
$\mathbf{B_5}$	=	$-x_1\,\mathbf{a_1}-y_1\,\mathbf{a_2}-z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}}-y_1\,b\,\hat{\mathbf{y}}-z_1\,c\,\hat{\mathbf{z}}$	(8c)	Cd
$\mathbf{B_6}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+y_1\,\mathbf{a_2}+\left(\frac{1}{2}-z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+y_1\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_1\right)c\,\hat{\mathbf{z}}$	(8c)	Cd
$\mathbf{B_7}$	=	$x_1\,\mathbf{a_1}+\left(\frac{1}{2}-y_1\right)\mathbf{a_2}+\left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_1\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_1\right)c\,\hat{\mathbf{z}}$	(8c)	Cd
$\mathbf{B_8}$	=	$\left(\frac{1}{2}-x_1\right)\mathbf{a_1}+\left(\frac{1}{2}+y_1\right)\mathbf{a_2}+z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_1\right)b\,\hat{\mathbf{y}}+z_1\,c\,\hat{\mathbf{z}}$	(8c)	Cd
$\mathbf{B_9}$	=	$x_2\,\mathbf{a_1}+y_2\,\mathbf{a_2}+z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+y_2\,b\,\hat{\mathbf{y}}+z_2\,c\,\hat{\mathbf{z}}$	(8c)	Sb
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-y_2\,\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}-y_2\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(8c)	Sb
$\mathbf{B_{11}}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+y_2\right)\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(8c)	Sb
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-y_2\right)\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)b\,\hat{\mathbf{y}}-z_2\,c\,\hat{\mathbf{z}}$	(8c)	Sb
$\mathbf{B_{13}}$	=	$-x_2\,\mathbf{a_1}-y_2\,\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}-y_2\,b\,\hat{\mathbf{y}}-z_2\,c\,\hat{\mathbf{z}}$	(8c)	Sb
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+y_2\,\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+y_2\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(8c)	Sb
$\mathbf{B_{15}}$	=	$x_2\,\mathbf{a_1}+\left(\frac{1}{2}-y_2\right)\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(8c)	Sb
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}+\left(\frac{1}{2}+y_2\right)\mathbf{a_2}+z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)b\,\hat{\mathbf{y}}+z_2\,c\,\hat{\mathbf{z}}$	(8c)	Sb

References:

- K. E. Almin, *The Crystal Structure of CdSb and ZnSb*, Acta Chem. Scand. **2**, 400–407 (1948), doi:10.3891/acta.chem.scand.02-0400.

Geometry files:

- CIF: pp. S664
- POSCAR: pp. S664

Brookite (TiO_2, C21) Structure: A2B_oP24_61_2c_c

Prototype	:	TiO_2
AFLOW prototype label	:	A2B_oP24_61_2c_c
***Strukturbericht* designation**	:	C21
Pearson symbol	:	oP24
Space group number	:	61
Space group symbol	:	Pbca
AFLOW prototype command	:	`aflow --proto=A2B_oP24_61_2c_c` `--params=`$a, b/a, c/a, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3$

Other compounds with this structure:

- TeO_2 tellurite

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(8c)$	O I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(8c)$	O I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(8c)$	O I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right)b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(8c)$	O I
$\mathbf{B_5}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(8c)$	O I

$\mathbf{B_6}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+y_1\,\mathbf{a_2}+\left(\frac{1}{2}-z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+y_1\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_1\right)c\,\hat{\mathbf{z}}$	(8*c*)	O I
$\mathbf{B_7}$	=	$x_1\,\mathbf{a_1}+\left(\frac{1}{2}-y_1\right)\mathbf{a_2}+\left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_1\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_1\right)c\,\hat{\mathbf{z}}$	(8*c*)	O I
$\mathbf{B_8}$	=	$\left(\frac{1}{2}-x_1\right)\mathbf{a_1}+\left(\frac{1}{2}+y_1\right)\mathbf{a_2}+z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_1\right)b\,\hat{\mathbf{y}}+z_1\,c\,\hat{\mathbf{z}}$	(8*c*)	O I
$\mathbf{B_9}$	=	$x_2\,\mathbf{a_1}+y_2\,\mathbf{a_2}+z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+y_2\,b\,\hat{\mathbf{y}}+z_2\,c\,\hat{\mathbf{z}}$	(8*c*)	O II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-y_2\,\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}-y_2\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(8*c*)	O II
$\mathbf{B_{11}}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+y_2\right)\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(8*c*)	O II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-y_2\right)\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)b\,\hat{\mathbf{y}}-z_2\,c\,\hat{\mathbf{z}}$	(8*c*)	O II
$\mathbf{B_{13}}$	=	$-x_2\,\mathbf{a_1}-y_2\,\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}-y_2\,b\,\hat{\mathbf{y}}-z_2\,c\,\hat{\mathbf{z}}$	(8*c*)	O II
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+y_2\,\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+y_2\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(8*c*)	O II
$\mathbf{B_{15}}$	=	$x_2\,\mathbf{a_1}+\left(\frac{1}{2}-y_2\right)\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(8*c*)	O II
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}+\left(\frac{1}{2}+y_2\right)\mathbf{a_2}+z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)b\,\hat{\mathbf{y}}+z_2\,c\,\hat{\mathbf{z}}$	(8*c*)	O II
$\mathbf{B_{17}}$	=	$x_3\,\mathbf{a_1}+y_3\,\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(8*c*)	Ti
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}-y_3\,\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(8*c*)	Ti
$\mathbf{B_{19}}$	=	$-x_3\,\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(8*c*)	Ti
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(8*c*)	Ti
$\mathbf{B_{21}}$	=	$-x_3\,\mathbf{a_1}-y_3\,\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(8*c*)	Ti
$\mathbf{B_{22}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+y_3\,\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(8*c*)	Ti
$\mathbf{B_{23}}$	=	$x_3\,\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(8*c*)	Ti
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(8*c*)	Ti

References:

- E. P. Meagher and G. A. Lager, *Polyhedral thermal expansion in the TiO_2 polymorphs; refinement of the crystal structures of rutile and brookite at high temperature*, Can. Mineral. **17**, 77–85 (1979).

Geometry files:

- CIF: pp. S664
- POSCAR: pp. S665

Stibnite (Sb_2S_3, $D5_8$) Structure: A3B2_oP20_62_3c_2c

Prototype	:	Sb_2S_3
AFLOW prototype label	:	A3B2_oP20_62_3c_2c
***Strukturbericht* designation**	:	$D5_8$
Pearson symbol	:	oP20
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=A3B2_oP20_62_3c_2c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, z_3, x_4, z_4, x_5, z_5$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	S I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	S I

$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	(4c)	S I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)\,c\,\hat{\mathbf{z}}$	(4c)	S I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4c)	S II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	(4c)	S II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(4c)	S II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\hat{\mathbf{z}}$	(4c)	S II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(4c)	S III
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - x_3\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\hat{\mathbf{z}}$	(4c)	S III
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(4c)	S III
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_3\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,c\,\hat{\mathbf{z}}$	(4c)	S III
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(4c)	Sb I
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2} - x_4\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	(4c)	Sb I
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(4c)	Sb I
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} + x_4\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	(4c)	Sb I
$\mathbf{B_{17}}$	=	$x_5\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(4c)	Sb II
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} - x_5\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)\,c\,\hat{\mathbf{z}}$	(4c)	Sb II
$\mathbf{B_{19}}$	=	$-x_5\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(4c)	Sb II
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} + x_5\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)\,c\,\hat{\mathbf{z}}$	(4c)	Sb II

References:

- A. Kyono and M. Kimata, *Structural variations induced by difference of the inert pair effect in the stibnite-bismuthinite solid solution series (Sb,Bi)$_2$S$_3$*, Am. Mineral. **89**, 932–940 (2004).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S665
- POSCAR: pp. S665

$CaTiO_3$ Pnma Perovskite Structure: AB3C_oP20_62_c_cd_a

Prototype	:	$CaTiO_3$
AFLOW prototype label	:	AB3C_oP20_62_c_cd_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP20
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=AB3C_oP20_62_c_cd_a` `--params=`$a, b/a, c/a, x_2, z_2, x_3, z_3, x_4, y_4, z_4$

Other compounds with this structure:

- $LaMnO_3$, $YAlO_3$, $RFeO_3$ (R = La, Pr, Nd, Sm, Eu, Y)

- This is the true ground state of the prototype perovskite, $CaTiO_3$. The standard cubic structure, $E2_1$, is a high-temperature phase.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Ti
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4a)$	Ti

$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,b\,\hat{\mathbf{y}}$	$(4a)$	Ti
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4a)$	Ti
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Ca
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	Ca
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Ca
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	Ca
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4c)$	O I
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	$(4c)$	O I
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4c)$	O I
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)c\,\hat{\mathbf{z}}$	$(4c)$	O I
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(8d)$	O II
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	$(8d)$	O II
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)b\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(8d)$	O II
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\hat{\mathbf{z}}$	$(8d)$	O II
$\mathbf{B_{17}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(8d)$	O II
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + y_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\hat{\mathbf{z}}$	$(8d)$	O II
$\mathbf{B_{19}}$	=	$x_4\,\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(8d)$	O II
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	$(8d)$	O II

References:

- T. Yamanaka, N. Hirai, and Y. Komatsu, *Structure change of $Ca_{1-x}Sr_xTiO_3$ perovskite with composition and pressure*, Am. Mineral. **87**, 1183–1189 (2002).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S665
- POSCAR: pp. S666

MgB_4 Structure: A4B_oP20_62_2cd_c

Prototype	:	MgB_4
AFLOW prototype label	:	A4B_oP20_62_2cd_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	oP20
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=A4B_oP20_62_2cd_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, z_3, x_4, y_4, z_4$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	B I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	B I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	B I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	B I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	B II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	B II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	B II

$\mathbf{B_8}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(4*c*)	B II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(4*c*)	Mg
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(4*c*)	Mg
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(4*c*)	Mg
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(4*c*)	Mg
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1}+y_4\,\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}}+y_4\,b\,\hat{\mathbf{y}}+z_4\,c\,\hat{\mathbf{z}}$	(8*d*)	B III
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}-x_4\right)\mathbf{a_1}-y_4\,\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_4\right)a\,\hat{\mathbf{x}}-y_4\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\,\hat{\mathbf{z}}$	(8*d*)	B III
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1}+\left(\frac{1}{2}+y_4\right)\mathbf{a_2}-z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_4\right)b\,\hat{\mathbf{y}}-z_4\,c\,\hat{\mathbf{z}}$	(8*d*)	B III
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2}+x_4\right)\mathbf{a_1}+\left(\frac{1}{2}-y_4\right)\mathbf{a_2}+\left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_4\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_4\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_4\right)c\,\hat{\mathbf{z}}$	(8*d*)	B III
$\mathbf{B_{17}}$	=	$-x_4\,\mathbf{a_1}-y_4\,\mathbf{a_2}-z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}}-y_4\,b\,\hat{\mathbf{y}}-z_4\,c\,\hat{\mathbf{z}}$	(8*d*)	B III
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2}+x_4\right)\mathbf{a_1}+y_4\,\mathbf{a_2}+\left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_4\right)a\,\hat{\mathbf{x}}+y_4\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_4\right)c\,\hat{\mathbf{z}}$	(8*d*)	B III
$\mathbf{B_{19}}$	=	$x_4\,\mathbf{a_1}+\left(\frac{1}{2}-y_4\right)\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_4\right)b\,\hat{\mathbf{y}}+z_4\,c\,\hat{\mathbf{z}}$	(8*d*)	B III
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2}-x_4\right)\mathbf{a_1}+\left(\frac{1}{2}+y_4\right)\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_4\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_4\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\,\hat{\mathbf{z}}$	(8*d*)	B III

References:

- R. Naslain, A. Guette, and M. Barret, *Sur le diborure et le tétraborure de magnésium. Considérations cristallochimiques sur les tétraborures*, J. Solid State Chem. **8**, 68–85 (1973), doi:10.1016/0022-4596(73)90022-4.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S666
- POSCAR: pp. S666

Chalcostibite ($CuSbS_2$, $F5_6$): AB2C_oP16_62_c_2c_c

Prototype	:	$CuSbS_2$
AFLOW prototype label	:	AB2C_oP16_62_c_2c_c
***Strukturbericht* designation**	:	$F5_6$
Pearson symbol	:	oP16
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=AB2C_oP16_62_c_2c_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, z_3, x_4, z_4$

Other compounds with this structure:

- $CuBiS_2$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Cu
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	Cu
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Cu
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	Cu
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	S I
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	S I
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	S I

$\mathbf{B_8}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(4c)	S I
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(4c)	S II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(4c)	S II
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(4c)	S II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(4c)	S II
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+z_4\,c\,\hat{\mathbf{z}}$	(4c)	Sb
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}-x_4\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_4\right)a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\,\hat{\mathbf{z}}$	(4c)	Sb
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}-z_4\,c\,\hat{\mathbf{z}}$	(4c)	Sb
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2}+x_4\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_4\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_4\right)c\,\hat{\mathbf{z}}$	(4c)	Sb

References:

- A. Kyono and M. Kimata, *Crystal structures of chalcostibite ($CuSbS_2$) and emplectite ($CuBiS_2$): Structural relationship of stereochemical activity between chalcostibite and emplectite*, Am. Mineral. **90**, 162–165 (2005).

Geometry files:

- CIF: pp. S666
- POSCAR: pp. S667

Co_2Si (C37) Structure: A2B_oP12_62_2c_c

Prototype	:	Co_2Si
AFLOW prototype label	:	A2B_oP12_62_2c_c
***Strukturbericht* designation**	:	C37
Pearson symbol	:	oP12
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=A2B_oP12_62_2c_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, z_3$

- Note that Co_2Si (pp. S154), $HgCl_2$ (pp. S156), and cotunnite (pp. S158) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Co I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	Co I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Co I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	Co I

$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4c)	Co II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(4c)	Co II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(4c)	Co II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	(4c)	Co II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(4c)	Si
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	(4c)	Si
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(4c)	Si
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)c\,\hat{\mathbf{z}}$	(4c)	Si

References:

- S. Geller and V. M. Wolontis, *The Crystal Structure of Co_2Si*, Acta Cryst. **8**, 83–87 (1955), doi:10.1107/S0365110X55000352.

Geometry files:

- CIF: pp. S667
- POSCAR: pp. S667

$HgCl_2$ (C25) Structure: A2B_oP12_62_2c_c

Prototype	:	$HgCl_2$
AFLOW prototype label	:	A2B_oP12_62_2c_c
***Strukturbericht* designation**	:	C25
Pearson symbol	:	oP12
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=A2B_oP12_62_2c_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, z_3$

Other compounds with this structure:

- FeO_2 (Goethite)

- Note that Co_2Si (pp. S154), $HgCl_2$ (pp. S156), and cotunnite (pp. S158) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Cl I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	Cl I

$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	(4c)	Cl I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	(4c)	Cl I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4c)	Cl II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(4c)	Cl II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(4c)	Cl II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	(4c)	Cl II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(4c)	Hg
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	(4c)	Hg
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(4c)	Hg
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)c\,\hat{\mathbf{z}}$	(4c)	Hg

References:

- H. Braekken and W. Scholten, *Die Kristallstruktur des Quecksilberchloride $HgCl_2$*, Zeitschrift für Kristallographie - Crystalline Materials **89**, 448–455 (1934), doi:10.1524/zkri.1934.89.1.448.

Geometry files:

- CIF: pp. S667
- POSCAR: pp. S668

Cotunnite ($PbCl_2$, C23) Structure: A2B_oP12_62_2c_c

Prototype	:	$PbCl_2$
AFLOW prototype label	:	A2B_oP12_62_2c_c
***Strukturbericht* designation**	:	C23
Pearson symbol	:	oP12
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=A2B_oP12_62_2c_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, z_3$

Other compounds with this structure:

- PbO_2, ZrO_2, TiO_2

- Note that Co_2Si (pp. S154), $HgCl_2$ (pp. S156), and cotunnite (pp. S158) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	(4c)	Cl I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	(4c)	Cl I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	(4c)	Cl I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	(4c)	Cl I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4c)	Cl II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(4c)	Cl II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(4c)	Cl II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	(4c)	Cl II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(4c)	Pb
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	(4c)	Pb
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(4c)	Pb
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)c\,\hat{\mathbf{z}}$	(4c)	Pb

References:

- R. L. Sass, E. B. Brackett, and T. E. Brackett, *The Crystal Structure of Lead Chloride*, J. Phys. Chem. **67**, 2863–2864 (1963), doi:10.1021/j100806a517.

Geometry files:

- CIF: pp. S668
- POSCAR: pp. S668

GeS (B16) Structure: AB_oP8_62_c_c

Prototype	:	GeS
AFLOW prototype label	:	AB_oP8_62_c_c
***Strukturbericht* designation**	:	B16
Pearson symbol	:	oP8
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=AB_oP8_62_c_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2$

Other compounds with this structure:

- GeSe, GeS, GeTe, PbS, PbSe, PbTe, SnS, SnSe, SnTe

- Also see the closely related B29 (SnS) structure. (Parthé, 1993) prefers the B16 designation for both structures. Note that GeS (pp. S160), MnP (pp. S162), FeB (pp. S171), and SnS (pp. S173) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Ge
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)\,c\,\hat{\mathbf{z}}$	$(4c)$	Ge
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Ge

$\mathbf{B_4}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_1\right)c\,\hat{\mathbf{z}}$	(4*c*)	Ge
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+z_2\,c\,\hat{\mathbf{z}}$	(4*c*)	S
$\mathbf{B_6}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(4*c*)	S
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}-z_2\,c\,\hat{\mathbf{z}}$	(4*c*)	S
$\mathbf{B_8}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(4*c*)	S

References:

- W. H. Zachariasen, *The Crystal Lattice of Germano Sulphide, GeS*, Phys. Rev. **40**, 917–922 (1932), doi:10.1103/PhysRev.40.917.
- E. Parthé, L. M. Gelato, B. Chabot, M. Penzo, K. Cenzula, and R. Gladyshevskii, *Gmelin Handbook of Inorganic and Organometallic Chemistry: Standardized Data and Crystal Chemical Characterization of Inorganic Structure Types* (Springer-Verlag, Berlin and Heidelberg, 1993), 8th edn., doi:10.1007/978-3-662-02909-1_3. Online edition available at DOI. See Table 4.3, pp. 363-371, for a comprehensive compilation of Strukturbericht symbols.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S668
- POSCAR: pp. S669

MnP (B31) Structure: AB_oP8_62_c_c

Prototype	:	MnP
AFLOW prototype label	:	AB_oP8_62_c_c
***Strukturbericht* designation**	:	B31
Pearson symbol	:	oP8
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=AB_oP8_62_c_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2$

Other compounds with this structure:

- AsCo, AsCr, AsFe, AsV, AsMo, CoP, CrP, FeP, FeS, GeNi, GeIr, GeRh, IrSi, RhSi, SeTi, many more

- (Hermann, 1937), pp. 7, assigns the prototype FeAs and the Strukturbericht designation B14 to this structure. This was superseded by the similar MnP structure in (Gottfried, 1937) pp. 17-18, where it is designated B31. Note that (Parthé, 1993) prefers the B14 designation. Note that GeS (pp. S160), MnP (pp. S162), FeB (pp. S171), and SnS (pp. S173) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	(4*c*)	Mn
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	(4*c*)	Mn
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	(4*c*)	Mn
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	(4*c*)	Mn
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(4*c*)	P
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(4*c*)	P
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(4*c*)	P
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	(4*c*)	P

References:

- H. Fjellvåg and A. Kjekshus, *Magnetic and Structural Properties of Transition Metal Substituted MnP. I. $Mn_{1-t}Co_tP$ (*0.00 ≤*t*≤ 0.30*)*, Acta Chemica Scandinvaca A **38**, 563–573 (1984), doi:10.3891/acta.chem.scand.38a-0563.
- C. Hermann, O. Lohrmann, and H. Philipp, *Strukturbericht Band II, 1928-1932* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937).
- C. Gottfried and F. Schossberger, *Strukturbericht Band III, 1933-1935* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937).
- E. Parthé, L. M. Gelato, B. Chabot, M. Penzo, K. Cenzula, and R. Gladyshevskii, *Gmelin Handbook of Inorganic and Organometallic Chemistry: Standardized Data and Crystal Chemical Characterization of Inorganic Structure Types* (Springer-Verlag, Berlin and Heidelberg, 1993), 8th edn., doi:10.1007/978-3-662-02909-1_3. Online edition available at DOI. See Table 4.3, pp. 363-371, for a comprehensive compilation of Strukturbericht symbols.

Geometry files:

- CIF: pp. S669
- POSCAR: pp. S669

Cementite (Fe_3C, $D0_{11}$) Structure: AB3_oP16_62_c_cd

Prototype	:	Fe_3C
AFLOW prototype label	:	AB3_oP16_62_c_cd
***Strukturbericht* designation**	:	$D0_{11}$
Pearson symbol	:	oP16
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=AB3_oP16_62_c_cd` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, y_3, z_3$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	C
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	C
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	C
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	C
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Fe I
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	Fe I
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Fe I

$\mathbf{B_8}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(4*c*)	Fe I
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1}+y_3\,\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(8*d*)	Fe II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}-y_3\,\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(8*d*)	Fe II
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(8*d*)	Fe II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(8*d*)	Fe II
$\mathbf{B_{13}}$	=	$-x_3\,\mathbf{a_1}-y_3\,\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(8*d*)	Fe II
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+y_3\,\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(8*d*)	Fe II
$\mathbf{B_{15}}$	=	$x_3\,\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(8*d*)	Fe II
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(8*d*)	Fe II

References:

- F. H. Herbstein and J. Smuts, *Comparison of X-ray and neutron-diffraction refinements of the structure of cementite Fe_3C*, Acta Cryst. **17**, 1331–1332 (1964), doi:10.1107/S0365110X64003346.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S669
- POSCAR: pp. S669

C_3Cr_7 ($D10_1$) Structure: A3B7_oP40_62_cd_3c2d

Prototype	:	C_3Cr_7
AFLOW prototype label	:	A3B7_oP40_62_cd_3c2d
***Strukturbericht* designation**	:	$D10_1$
Pearson symbol	:	oP40
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=A3B7_oP40_62_cd_3c2d` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, z_3, x_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6, x_7, y_7, z_7$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	C I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	C I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	C I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	C I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Cr I
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	Cr I
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Cr I

$\mathbf{B_8}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(4c)	Cr I
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(4c)	Cr II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	(4c)	Cr II
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(4c)	Cr II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	(4c)	Cr II
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+z_4\,c\,\hat{\mathbf{z}}$	(4c)	Cr III
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}-x_4\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_4\right)a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\,\hat{\mathbf{z}}$	(4c)	Cr III
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}-z_4\,c\,\hat{\mathbf{z}}$	(4c)	Cr III
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2}+x_4\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_4\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_4\right)c\,\hat{\mathbf{z}}$	(4c)	Cr III
$\mathbf{B_{17}}$	=	$x_5\,\mathbf{a_1}+y_5\,\mathbf{a_2}+z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}}+y_5\,b\,\hat{\mathbf{y}}+z_5\,c\,\hat{\mathbf{z}}$	(8d)	C II
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2}-x_5\right)\mathbf{a_1}-y_5\,\mathbf{a_2}+\left(\frac{1}{2}+z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_5\right)a\,\hat{\mathbf{x}}-y_5\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_5\right)c\,\hat{\mathbf{z}}$	(8d)	C II
$\mathbf{B_{19}}$	=	$-x_5\,\mathbf{a_1}+\left(\frac{1}{2}+y_5\right)\mathbf{a_2}-z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_5\right)b\,\hat{\mathbf{y}}-z_5\,c\,\hat{\mathbf{z}}$	(8d)	C II
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2}+x_5\right)\mathbf{a_1}+\left(\frac{1}{2}-y_5\right)\mathbf{a_2}+\left(\frac{1}{2}-z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_5\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_5\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_5\right)c\,\hat{\mathbf{z}}$	(8d)	C II
$\mathbf{B_{21}}$	=	$-x_5\,\mathbf{a_1}-y_5\,\mathbf{a_2}-z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}}-y_5\,b\,\hat{\mathbf{y}}-z_5\,c\,\hat{\mathbf{z}}$	(8d)	C II
$\mathbf{B_{22}}$	=	$\left(\frac{1}{2}+x_5\right)\mathbf{a_1}+y_5\,\mathbf{a_2}+\left(\frac{1}{2}-z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_5\right)a\,\hat{\mathbf{x}}+y_5\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_5\right)c\,\hat{\mathbf{z}}$	(8d)	C II
$\mathbf{B_{23}}$	=	$x_5\,\mathbf{a_1}+\left(\frac{1}{2}-y_5\right)\mathbf{a_2}+z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_5\right)b\,\hat{\mathbf{y}}+z_5\,c\,\hat{\mathbf{z}}$	(8d)	C II
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2}-x_5\right)\mathbf{a_1}+\left(\frac{1}{2}+y_5\right)\mathbf{a_2}+\left(\frac{1}{2}+z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_5\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_5\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_5\right)c\,\hat{\mathbf{z}}$	(8d)	C II
$\mathbf{B_{25}}$	=	$x_6\,\mathbf{a_1}+y_6\,\mathbf{a_2}+z_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}}+y_6\,b\,\hat{\mathbf{y}}+z_6\,c\,\hat{\mathbf{z}}$	(8d)	Cr IV
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2}-x_6\right)\mathbf{a_1}-y_6\,\mathbf{a_2}+\left(\frac{1}{2}+z_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_6\right)a\,\hat{\mathbf{x}}-y_6\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_6\right)c\,\hat{\mathbf{z}}$	(8d)	Cr IV
$\mathbf{B_{27}}$	=	$-x_6\,\mathbf{a_1}+\left(\frac{1}{2}+y_6\right)\mathbf{a_2}-z_6\,\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_6\right)b\,\hat{\mathbf{y}}-z_6\,c\,\hat{\mathbf{z}}$	(8d)	Cr IV
$\mathbf{B_{28}}$	=	$\left(\frac{1}{2}+x_6\right)\mathbf{a_1}+\left(\frac{1}{2}-y_6\right)\mathbf{a_2}+\left(\frac{1}{2}-z_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_6\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_6\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_6\right)c\,\hat{\mathbf{z}}$	(8d)	Cr IV
$\mathbf{B_{29}}$	=	$-x_6\,\mathbf{a_1}-y_6\,\mathbf{a_2}-z_6\,\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}}-y_6\,b\,\hat{\mathbf{y}}-z_6\,c\,\hat{\mathbf{z}}$	(8d)	Cr IV
$\mathbf{B_{30}}$	=	$\left(\frac{1}{2}+x_6\right)\mathbf{a_1}+y_6\,\mathbf{a_2}+\left(\frac{1}{2}-z_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_6\right)a\,\hat{\mathbf{x}}+y_6\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_6\right)c\,\hat{\mathbf{z}}$	(8d)	Cr IV
$\mathbf{B_{31}}$	=	$x_6\,\mathbf{a_1}+\left(\frac{1}{2}-y_6\right)\mathbf{a_2}+z_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_6\right)b\,\hat{\mathbf{y}}+z_6\,c\,\hat{\mathbf{z}}$	(8d)	Cr IV
$\mathbf{B_{32}}$	=	$\left(\frac{1}{2}-x_6\right)\mathbf{a_1}+\left(\frac{1}{2}+y_6\right)\mathbf{a_2}+\left(\frac{1}{2}+z_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_6\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_6\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_6\right)c\,\hat{\mathbf{z}}$	(8d)	Cr IV
$\mathbf{B_{33}}$	=	$x_7\,\mathbf{a_1}+y_7\,\mathbf{a_2}+z_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}}+y_7\,b\,\hat{\mathbf{y}}+z_7\,c\,\hat{\mathbf{z}}$	(8d)	Cr V
$\mathbf{B_{34}}$	=	$\left(\frac{1}{2}-x_7\right)\mathbf{a_1}-y_7\,\mathbf{a_2}+\left(\frac{1}{2}+z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_7\right)a\,\hat{\mathbf{x}}-y_7\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_7\right)c\,\hat{\mathbf{z}}$	(8d)	Cr V
$\mathbf{B_{35}}$	=	$-x_7\,\mathbf{a_1}+\left(\frac{1}{2}+y_7\right)\mathbf{a_2}-z_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_7\right)b\,\hat{\mathbf{y}}-z_7\,c\,\hat{\mathbf{z}}$	(8d)	Cr V
$\mathbf{B_{36}}$	=	$\left(\frac{1}{2}+x_7\right)\mathbf{a_1}+\left(\frac{1}{2}-y_7\right)\mathbf{a_2}+\left(\frac{1}{2}-z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_7\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_7\right)b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_7\right)c\,\hat{\mathbf{z}}$	(8d)	Cr V
$\mathbf{B_{37}}$	=	$-x_7\,\mathbf{a_1}-y_7\,\mathbf{a_2}-z_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}}-y_7\,b\,\hat{\mathbf{y}}-z_7\,c\,\hat{\mathbf{z}}$	(8d)	Cr V
$\mathbf{B_{38}}$	=	$\left(\frac{1}{2}+x_7\right)\mathbf{a_1}+y_7\,\mathbf{a_2}+\left(\frac{1}{2}-z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_7\right)a\,\hat{\mathbf{x}}+y_7\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_7\right)c\,\hat{\mathbf{z}}$	(8d)	Cr V
$\mathbf{B_{39}}$	=	$x_7\,\mathbf{a_1}+\left(\frac{1}{2}-y_7\right)\mathbf{a_2}+z_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_7\right)b\,\hat{\mathbf{y}}+z_7\,c\,\hat{\mathbf{z}}$	(8d)	Cr V

$\mathbf{B_{40}}$	=	$\left(\frac{1}{2} - x_7\right)\mathbf{a_1} + \left(\frac{1}{2} + y_7\right)\mathbf{a_2} + \left(\frac{1}{2} + z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_7\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_7\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_7\right) c\,\hat{\mathbf{z}}$	(8*d*)	Cr V

References:

- M. A. Rouault, P. Herpin, and M. R. Fruchart, *Etude Cristallographique des Carbures Cr_7C_3 et Mn_7C_3*, Annales de Chimie (Paris) **5**, 461–470 (1970).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1873.

Geometry files:

- CIF: pp. S670
- POSCAR: pp. S670

α-Np (A_c) Structure: A_oP8_62_2c

Prototype	:	α-Np
AFLOW prototype label	:	A_oP8_62_2c
***Strukturbericht* designation**	:	A_c
Pearson symbol	:	oP8
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=A_oP8_62_2c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2$

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Np I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	Np I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	Np I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	Np I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Np II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	Np II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Np II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	Np II

References:

- W. H. Zachariasen, *Crystal chemical studies of the 5f-series of elements. XVII. The crystal structure of neptunium metal*, Acta Cryst. **5**, 660–664 (1952), doi:10.1107/S0365110X52001799.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 151-153.

Geometry files:

- CIF: pp. S670
- POSCAR: pp. S671

FeB (B27) Structure: AB_oP8_62_c_c

Prototype	:	FeB
AFLOW prototype label	:	AB_oP8_62_c_c
***Strukturbericht* designation**	:	B27
Pearson symbol	:	oP8
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=AB_oP8_62_c_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2$

Other compounds with this structure:

- GeSe, GeS, GeTe, PbS, PbSe, PbTe, SnS, SnSe, SnTe

- (Hermann, 1937), pp. 7, assigns the Strukturbericht designation B15 to this structure. This was superseded by the current B27 structure in in (Gottfried, 1937) pp. 12. Here we follow (Parthé, 1993), who prefers the B27 designation. Note that GeS (pp. S160), MnP (pp. S162), FeB (pp. S171), and SnS (pp. S173) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	B

$\mathbf{B_2}$	=	$\left(\frac{1}{2}-x_1\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_1\right)c\,\hat{\mathbf{z}}$	(4*c*)	B
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}-z_1\,c\,\hat{\mathbf{z}}$	(4*c*)	B
$\mathbf{B_4}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_1\right)c\,\hat{\mathbf{z}}$	(4*c*)	B
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+z_2\,c\,\hat{\mathbf{z}}$	(4*c*)	Fe
$\mathbf{B_6}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	(4*c*)	Fe
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\frac{3}{4}b\,\hat{\mathbf{y}}-z_2\,c\,\hat{\mathbf{z}}$	(4*c*)	Fe
$\mathbf{B_8}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\frac{1}{4}b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)c\,\hat{\mathbf{z}}$	(4*c*)	Fe

References:

- S. B. Hendricks and P. R. Kosting, *The Crystal Structure of Fe_2P, Fe_2N, Fe_3N and FeB*, Zeitschrift für Kristallographie - Crystalline Materials **74**, 511–533 (1930), doi:10.1524/zkri.1930.74.1.511.
- C. Hermann, O. Lohrmann, and H. Philipp, *Strukturbericht Band II, 1928-1932* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937).
- C. Gottfried and F. Schossberger, *Strukturbericht Band III, 1933-1935* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937).
- E. Parthé, L. M. Gelato, B. Chabot, M. Penzo, K. Cenzula, and R. Gladyshevskii, *Gmelin Handbook of Inorganic and Organometallic Chemistry: Standardized Data and Crystal Chemical Characterization of Inorganic Structure Types* (Springer-Verlag, Berlin and Heidelberg, 1993), 8th edn., doi:10.1007/978-3-662-02909-1_3. Online edition available at DOI. See Table 4.3, pp. 363-371, for a comprehensive compilation of Strukturbericht symbols.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S671
- POSCAR: pp. S671

SnS (B29) Structure: AB_oP8_62_c_c

Prototype	:	SnS
AFLOW prototype label	:	AB_oP8_62_c_c
***Strukturbericht* designation**	:	B29
Pearson symbol	:	oP8
Space group number	:	62
Space group symbol	:	Pnma
AFLOW prototype command	:	`aflow --proto=AB_oP8_62_c_c` `--params=`$a, b/a, c/a, x_1, z_1, x_2, z_2$

- This structure is closely related to the B16 (GeS) structure. (Parthé, 1993) prefers the B16 designation for this structure. Note that GeS (pp. S160), MnP (pp. S162), FeB (pp. S171), and SnS (pp. S173) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Orthorhombic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	S
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	S
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4c)$	S
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(4c)$	S
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4c)$	Sn
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(4c)$	Sn

$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(4c)	Sn
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\hat{\mathbf{z}}$	(4c)	Sn

References:

- S. Del Bucchia, J. C. Jumas, and M. Maurin, *Contribution à l'étude de composés sulfurés d'étain(II): affinement de la structure de SnS*, Acta Crystallogr. Sect. B Struct. Sci. **37**, 1903–1905 (1981), doi:10.1107/S0567740881007528.
- E. Parthé, L. M. Gelato, B. Chabot, M. Penzo, K. Cenzula, and R. Gladyshevskii, *Gmelin Handbook of Inorganic and Organometallic Chemistry: Standardized Data and Crystal Chemical Characterization of Inorganic Structure Types* (Springer-Verlag, Berlin and Heidelberg, 1993), 8th edn., doi:10.1007/978-3-662-02909-1_3. Online edition available at DOI. See Table 4.3, pp. 363-371, for a comprehensive compilation of Strukturbericht symbols.

Geometry files:

- CIF: pp. S671
- POSCAR: pp. S672

$SrCuO_2$ Structure: AB2C_oC16_63_c_2c_c

Prototype	:	$SrCuO_2$
AFLOW prototype label	:	AB2C_oC16_63_c_2c_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	oC16
Space group number	:	63
Space group symbol	:	Cmcm
AFLOW prototype command	:	`aflow --proto=AB2C_oC16_63_c_2c_c` `--params=`$a, b/a, c/a, y_1, y_2, y_3, y_4$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Cu
$\mathbf{B_2}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_1\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Cu
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	O I
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	O I
$\mathbf{B_5}$	=	$-y_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_3\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	O II
$\mathbf{B_6}$	=	$y_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_3\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	O II
$\mathbf{B_7}$	=	$-y_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_4\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Sr
$\mathbf{B_8}$	=	$y_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_4\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Sr

References:

- Y. Matsushita, Y. Oyama, M. Hasegawa, and H. Takei, *Growth and Structural Refinement of Orthorhombic $SrCuO_2$ Crystals*, J. Solid State Chem. **114**, 289–293 (1994), doi:10.1006/jssc.1995.1043.

Geometry files:
- CIF: pp. S672
- POSCAR: pp. S672

$ZrSi_2$ (C49) Structure: A2B_oC12_63_2c_c

Prototype	:	$ZrSi_2$
AFLOW prototype label	:	A2B_oC12_63_2c_c
***Strukturbericht* designation**	:	C49
Pearson symbol	:	oC12
Space group number	:	63
Space group symbol	:	Cmcm
AFLOW prototype command	:	`aflow --proto=A2B_oC12_63_2c_c` `--params=`$a, b/a, c/a, y_1, y_2, y_3$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Si I
$\mathbf{B_2}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_1\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Si I
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Si II
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Si II
$\mathbf{B_5}$	=	$-y_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_3\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Zr
$\mathbf{B_6}$	=	$y_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_3\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Zr

References:

- P. G. Cotter, J. A. Kohn, and R. A. Potter, *Physical and X-Ray Study of the Disilicides of Titanium, Zirconium, and Hafnium*, J. Am. Ceram. Soc. **39**, 11–12 (1956), doi:10.1111/j.1151-2916.1956.tb15590.x.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S672
- POSCAR: pp. S673

CrB (B33) Structure: AB_oC8_63_c_c

Prototype	:	CrB
AFLOW prototype label	:	AB_oC8_63_c_c
***Strukturbericht* designation**	:	B33
Pearson symbol	:	oC8
Space group number	:	63
Space group symbol	:	Cmcm
AFLOW prototype command	:	`aflow --proto=AB_oC8_63_c_c` `--params=`$a, b/a, c/a, y_1, y_2$

- Note that removing either the Cr or B atoms transforms this into the α-U (A20) structure.

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	B
$\mathbf{B_2}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_1\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	B
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_2\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Cr
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_2\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	Cr

References:

- S. Okada, T. Atoda, and I. Higashi, *Structural investigation of Cr_2B_3, Cr_3B_4, and CrB by single-crystal diffractometry*, J. Solid State Chem. **68**, 61–67 (1987), doi:10.1016/0022-4596(87)90285-4.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:
- CIF: pp. S673
- POSCAR: pp. S673

α-U (A20) Structure: A_oC4_63_c

Prototype	:	α-U
AFLOW prototype label	:	A_oC4_63_c
***Strukturbericht* designation**	:	A20
Pearson symbol	:	oC4
Space group number	:	63
Space group symbol	:	Cmcm
AFLOW prototype command	:	`aflow --proto=A_oC4_63_c --params=`$a, b/a, c/a, y_1$

Other elements and compounds with this structure:

- Tb, Dy, Ge (metastable), AgCd (random alloy), γ-Ti

- Using data for the α-U structure at 4.2K. (Vohra, 2001) showed that at pressures above 116 GPa titanium transforms from the hexagonal omega (C32) phase to this phase. This structure was studied by (Wentzcovitch, 1987) as a possible pathway for the pressure-induced transformation of magnesium from the hcp (A3) to the bcc (A2) phase. Much like the trigonal omega phase (C6), we can generate several high-symmetry structures from this phase by the appropriate choice of parameters.

Lattice parameter	**hcp**	**bcc**	**fcc**	**simple cubic**
a	a_{hcp}	a_{bcc}	a_{fcc}	a_{sc}
b	$\sqrt{3}a_{hcp}$	$\sqrt{2}a_{bcc}$	a_{fcc}	a_{sc}
c	c_{hcp}	$\sqrt{2}a_{bcc}$	a_{fcc}	$2a_{sc}$
y	$\frac{1}{6}$	$\frac{1}{4}$	$\frac{1}{4}$	0

Lattice parameter	**hcp**	**bcc**	**fcc**	**simple cubic**
Strukturbericht	A3	A2	A1	A_h
Pearson symbol	hP2	cI2	cF4	cP1
Space group	$P6_3/mmc$	$Im\bar{3}m$	$Fm\bar{3}m$	$Pm\bar{3}m$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + \frac{1}{4}\,c\hat{\mathbf{z}}$	$(4c)$	U
$\mathbf{B_2}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-y_1\,b\,\hat{\mathbf{y}} + \frac{3}{4}\,c\hat{\mathbf{z}}$	$(4c)$	U

References:

- C. S. Barrett, M. H. Mueller, and R. L. Hitterman, *Crystal Structure Variations in Alpha Uranium at Low Temperatures*, Phys. Rev. **129**, 625–629 (1963), doi:10.1103/PhysRev.129.625.
- Y. K. Vohra and P. T. Spencer, *Novel γ-Phase of Titanium Metal at Megabar Pressures*, Phys. Rev. Lett. **86**, 3068–3071 (2001), doi:10.1103/PhysRevLett.86.3068.
- R. M. Wentzcovitch and M. L. Cohen, *Theoretical model for the hcp-bcc transition in Mg*, Phys. Rev. B **37**, 5571–5576 (1988), doi:10.1103/PhysRevB.37.5571.

Geometry files:

- CIF: pp. S673
- POSCAR: pp. S673

α-Ga (A11) Structure: A_oC8_64_f

Prototype	:	α-Ga
AFLOW prototype label	:	A_oC8_64_f
***Strukturbericht* designation**	:	A11
Pearson symbol	:	oC8
Space group number	:	64
Space group symbol	:	Cmca
AFLOW prototype command	:	`aflow --proto=A_oC8_64_f` `--params=`$a, b/a, c/a, y_1, z_1$

- Note that α-Ga (pp. S183), black phosphorus (pp. S188), and molecular iodine (pp. S190) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + z_1\,c\hat{\mathbf{z}}$	$(8f)$	Ga
$\mathbf{B_2}$	=	$\left(\frac{1}{2}+y_1\right)\mathbf{a_1} + \left(\frac{1}{2}-y_1\right)\mathbf{a_2} + \left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2}+z_1\right)c\hat{\mathbf{z}}$	$(8f)$	Ga
$\mathbf{B_3}$	=	$\left(\frac{1}{2}-y_1\right)\mathbf{a_1} + \left(\frac{1}{2}+y_1\right)\mathbf{a_2} + \left(\frac{1}{2}-z_1\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2}-z_1\right)c\hat{\mathbf{z}}$	$(8f)$	Ga
$\mathbf{B_4}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-y_1\,b\,\hat{\mathbf{y}} - z_1\,c\hat{\mathbf{z}}$	$(8f)$	Ga

References:

- B. D. Sharma and J. Donohue, *A refinement of the crystal structure of gallium*, Zeitschrift für Kristallographie **117**, 293–300 (1962), doi:10.1524/zkri.1962.117.4.293.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S674
- POSCAR: pp. S674

MgB_2C_2 Crystal Structure: A2B2C_oC80_64_efg_efg_df

Prototype	:	MgB_2C_2
AFLOW prototype label	:	A2B2C_oC80_64_efg_efg_df
***Strukturbericht* designation**	:	None
Pearson symbol	:	oC80
Space group number	:	64
Space group symbol	:	Cmca
AFLOW prototype command	:	`aflow --proto=A2B2C_oC80_64_efg_efg_df` `--params=`$a, b/a, c/a, x_1, y_2, y_3, y_4, z_4, y_5, z_5, y_6, z_6, x_7, y_7, z_7, x_8, y_8, z_8$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}}$	$(8d)$	Mg I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8d)$	Mg I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}}$	$(8d)$	Mg I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8d)$	Mg I

$\mathbf{B_5}$	=	$\left(\frac{1}{4}-y_2\right)\mathbf{a_1}+\left(\frac{1}{4}+y_2\right)\mathbf{a_2}+\frac{1}{4}\mathbf{a_3}$	=	$\frac{1}{4}a\,\hat{\mathbf{x}}+y_2\,b\,\hat{\mathbf{y}}+\frac{1}{4}c\hat{\mathbf{z}}$	(8e)	B I
$\mathbf{B_6}$	=	$\left(\frac{1}{4}+y_2\right)\mathbf{a_1}+\left(\frac{1}{4}-y_2\right)\mathbf{a_2}+\frac{3}{4}\mathbf{a_3}$	=	$\frac{1}{4}a\,\hat{\mathbf{x}}-y_2\,b\,\hat{\mathbf{y}}+\frac{3}{4}c\hat{\mathbf{z}}$	(8e)	B I
$\mathbf{B_7}$	=	$\left(\frac{3}{4}+y_2\right)\mathbf{a_1}+\left(\frac{3}{4}-y_2\right)\mathbf{a_2}+\frac{3}{4}\mathbf{a_3}$	=	$\frac{3}{4}a\,\hat{\mathbf{x}}-y_2\,b\,\hat{\mathbf{y}}+\frac{3}{4}c\hat{\mathbf{z}}$	(8e)	B I
$\mathbf{B_8}$	=	$\left(\frac{3}{4}-y_2\right)\mathbf{a_1}+\left(\frac{3}{4}+y_2\right)\mathbf{a_2}+\frac{1}{4}\mathbf{a_3}$	=	$\frac{3}{4}a\,\hat{\mathbf{x}}+y_2\,b\,\hat{\mathbf{y}}+\frac{1}{4}c\hat{\mathbf{z}}$	(8e)	B I
$\mathbf{B_9}$	=	$\left(\frac{1}{4}-y_3\right)\mathbf{a_1}+\left(\frac{1}{4}+y_3\right)\mathbf{a_2}+\frac{1}{4}\mathbf{a_3}$	=	$\frac{1}{4}a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+\frac{1}{4}c\hat{\mathbf{z}}$	(8e)	C I
$\mathbf{B_{10}}$	=	$\left(\frac{1}{4}+y_3\right)\mathbf{a_1}+\left(\frac{1}{4}-y_3\right)\mathbf{a_2}+\frac{3}{4}\mathbf{a_3}$	=	$\frac{1}{4}a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}+\frac{3}{4}c\hat{\mathbf{z}}$	(8e)	C I
$\mathbf{B_{11}}$	=	$\left(\frac{3}{4}+y_3\right)\mathbf{a_1}+\left(\frac{3}{4}-y_3\right)\mathbf{a_2}+\frac{3}{4}\mathbf{a_3}$	=	$\frac{3}{4}a\,\hat{\mathbf{x}}-y_3\,b\,\hat{\mathbf{y}}+\frac{3}{4}c\hat{\mathbf{z}}$	(8e)	C I
$\mathbf{B_{12}}$	=	$\left(\frac{3}{4}-y_3\right)\mathbf{a_1}+\left(\frac{3}{4}+y_3\right)\mathbf{a_2}+\frac{1}{4}\mathbf{a_3}$	=	$\frac{3}{4}a\,\hat{\mathbf{x}}+y_3\,b\,\hat{\mathbf{y}}+\frac{1}{4}c\hat{\mathbf{z}}$	(8e)	C I
$\mathbf{B_{13}}$	=	$-y_4\,\mathbf{a_1}+y_4\,\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$y_4\,b\,\hat{\mathbf{y}}+z_4\,c\hat{\mathbf{z}}$	(8f)	B II
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}+y_4\right)\mathbf{a_1}+\left(\frac{1}{2}-y_4\right)\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}-y_4\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\hat{\mathbf{z}}$	(8f)	B II
$\mathbf{B_{15}}$	=	$\left(\frac{1}{2}-y_4\right)\mathbf{a_1}+\left(\frac{1}{2}+y_4\right)\mathbf{a_2}+\left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}+y_4\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_4\right)c\hat{\mathbf{z}}$	(8f)	B II
$\mathbf{B_{16}}$	=	$y_4\,\mathbf{a_1}-y_4\,\mathbf{a_2}-z_4\,\mathbf{a_3}$	=	$-y_4\,b\,\hat{\mathbf{y}}-z_4\,c\hat{\mathbf{z}}$	(8f)	B II
$\mathbf{B_{17}}$	=	$-y_5\,\mathbf{a_1}+y_5\,\mathbf{a_2}+z_5\,\mathbf{a_3}$	=	$y_5\,b\,\hat{\mathbf{y}}+z_5\,c\hat{\mathbf{z}}$	(8f)	C II
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2}+y_5\right)\mathbf{a_1}+\left(\frac{1}{2}-y_5\right)\mathbf{a_2}+\left(\frac{1}{2}+z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}-y_5\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_5\right)c\hat{\mathbf{z}}$	(8f)	C II
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2}-y_5\right)\mathbf{a_1}+\left(\frac{1}{2}+y_5\right)\mathbf{a_2}+\left(\frac{1}{2}-z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}+y_5\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_5\right)c\hat{\mathbf{z}}$	(8f)	C II
$\mathbf{B_{20}}$	=	$y_5\,\mathbf{a_1}-y_5\,\mathbf{a_2}-z_5\,\mathbf{a_3}$	=	$-y_5\,b\,\hat{\mathbf{y}}-z_5\,c\hat{\mathbf{z}}$	(8f)	C II
$\mathbf{B_{21}}$	=	$-y_6\,\mathbf{a_1}+y_6\,\mathbf{a_2}+z_6\,\mathbf{a_3}$	=	$y_6\,b\,\hat{\mathbf{y}}+z_6\,c\hat{\mathbf{z}}$	(8f)	Mg II
$\mathbf{B_{22}}$	=	$\left(\frac{1}{2}+y_6\right)\mathbf{a_1}+\left(\frac{1}{2}-y_6\right)\mathbf{a_2}+\left(\frac{1}{2}+z_6\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}-y_6\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_6\right)c\hat{\mathbf{z}}$	(8f)	Mg II
$\mathbf{B_{23}}$	=	$\left(\frac{1}{2}-y_6\right)\mathbf{a_1}+\left(\frac{1}{2}+y_6\right)\mathbf{a_2}+\left(\frac{1}{2}-z_6\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}+y_6\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_6\right)c\hat{\mathbf{z}}$	(8f)	Mg II
$\mathbf{B_{24}}$	=	$y_6\,\mathbf{a_1}-y_6\,\mathbf{a_2}-z_6\,\mathbf{a_3}$	=	$-y_6\,b\,\hat{\mathbf{y}}-z_6\,c\hat{\mathbf{z}}$	(8f)	Mg II
$\mathbf{B_{25}}$	=	$(x_7-y_7)\,\mathbf{a_1}+(x_7+y_7)\,\mathbf{a_2}+z_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}}+y_7\,b\,\hat{\mathbf{y}}+z_7\,c\hat{\mathbf{z}}$	(16g)	B III
$\mathbf{B_{26}}$	=	$\left(y_7-x_7+\frac{1}{2}\right)\mathbf{a_1}+\left(\frac{1}{2}-x_7-y_7\right)\mathbf{a_2}+\left(\frac{1}{2}+z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_7\right)a\,\hat{\mathbf{x}}-y_7\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_7\right)c\hat{\mathbf{z}}$	(16g)	B III
$\mathbf{B_{27}}$	=	$\left(\frac{1}{2}-x_7-y_7\right)\mathbf{a_1}+\left(\frac{1}{2}-x_7+y_7\right)\mathbf{a_2}+\left(\frac{1}{2}-z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_7\right)a\,\hat{\mathbf{x}}+y_7\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_7\right)c\hat{\mathbf{z}}$	(16g)	B III
$\mathbf{B_{28}}$	=	$(x_7+y_7)\,\mathbf{a_1}+(x_7-y_7)\,\mathbf{a_2}-z_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}}-y_7\,b\,\hat{\mathbf{y}}-z_7\,c\hat{\mathbf{z}}$	(16g)	B III
$\mathbf{B_{29}}$	=	$(y_7-x_7)\,\mathbf{a_1}-(x_7+y_7)\,\mathbf{a_2}-z_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}}-y_7\,b\,\hat{\mathbf{y}}-z_7\,c\hat{\mathbf{z}}$	(16g)	B III
$\mathbf{B_{30}}$	=	$\left(\frac{1}{2}+x_7-y_7\right)\mathbf{a_1}+\left(\frac{1}{2}+x_7+y_7\right)\mathbf{a_2}+\left(\frac{1}{2}-z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_7\right)a\,\hat{\mathbf{x}}+y_7\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_7\right)c\hat{\mathbf{z}}$	(16g)	B III
$\mathbf{B_{31}}$	=	$\left(\frac{1}{2}+x_7+y_7\right)\mathbf{a_1}+\left(\frac{1}{2}+x_7-y_7\right)\mathbf{a_2}+\left(\frac{1}{2}+z_7\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_7\right)a\,\hat{\mathbf{x}}-y_7\,b\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_7\right)c\hat{\mathbf{z}}$	(16g)	B III
$\mathbf{B_{32}}$	=	$-(x_7+y_7)\,\mathbf{a_1}+(y_7-x_7)\,\mathbf{a_2}+z_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}}+y_7\,b\,\hat{\mathbf{y}}+z_7\,c\hat{\mathbf{z}}$	(16g)	B III

$\mathbf{B_{33}}$	=	$(x_8 - y_8)\,\mathbf{a_1} + (x_8 + y_8)\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$x_8\,a\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\hat{\mathbf{z}}$	$(16g)$	C III
$\mathbf{B_{34}}$	=	$\left(\frac{1}{2} + y_8 - x_8\right)\mathbf{a_1} + \left(\frac{1}{2} - x_8 - y_8\right)\mathbf{a_2} + \left(\frac{1}{2} + z_8\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_8\right)a\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_8\right)c\hat{\mathbf{z}}$	$(16g)$	C III
$\mathbf{B_{35}}$	=	$\left(\frac{1}{2} - x_8 - y_8\right)\mathbf{a_1} + \left(\frac{1}{2} - x_8 + y_8\right)\mathbf{a_2} + \left(\frac{1}{2} - z_8\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_8\right)a\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_8\right)c\hat{\mathbf{z}}$	$(16g)$	C III
$\mathbf{B_{36}}$	=	$(x_8 + y_8)\,\mathbf{a_1} + (x_8 - y_8)\,\mathbf{a_2} - z_8\,\mathbf{a_3}$	=	$x_8\,a\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} - z_8\,c\hat{\mathbf{z}}$	$(16g)$	C III
$\mathbf{B_{37}}$	=	$(y_8 - x_8)\,\mathbf{a_1} - (x_8 + y_8)\,\mathbf{a_2} - z_8\,\mathbf{a_3}$	=	$-x_8\,a\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} - z_8\,c\hat{\mathbf{z}}$	$(16g)$	C III
$\mathbf{B_{38}}$	=	$\left(\frac{1}{2} + x_8 - y_8\right)\mathbf{a_1} + \left(\frac{1}{2} + x_8 + y_8\right)\mathbf{a_2} + \left(\frac{1}{2} - z_8\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_8\right)a\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_8\right)c\hat{\mathbf{z}}$	$(16g)$	C III
$\mathbf{B_{39}}$	=	$\left(\frac{1}{2} + x_8 + y_8\right)\mathbf{a_1} + \left(\frac{1}{2} + x_8 - y_8\right)\mathbf{a_2} + \left(\frac{1}{2} + z_8\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_8\right)a\,\hat{\mathbf{x}} - y_8\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_8\right)c\hat{\mathbf{z}}$	$(16g)$	C III
$\mathbf{B_{40}}$	=	$-(x_8 + y_8)\,\mathbf{a_1} + (y_8 - x_8)\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$-x_8\,a\,\hat{\mathbf{x}} + y_8\,b\,\hat{\mathbf{y}} + z_8\,c\hat{\mathbf{z}}$	$(16g)$	C III

References:

- M. Wörle and R. Nesper, *MgB_2C_2, a new graphite-related refractory compound*, J. Alloys Compd. **216**, 75–83 (1994), doi:10.1016/0925-8388(94)91045-6.

Geometry files:

- CIF: pp. S674
- POSCAR: pp. S674

Black Phosphorus (A17) Crystal Structure: A_oC8_64_f

Prototype	:	P
AFLOW prototype label	:	A_oC8_64_f
***Strukturbericht* designation**	:	A17
Pearson symbol	:	oC8
Space group number	:	64
Space group symbol	:	Cmca
AFLOW prototype command	:	`aflow --proto=A_oC8_64_f` `--params=`$a, b/a, c/a, y_1, z_1$

- Note that α-Ga (pp. S183), black phosphorus (pp. S188), and molecular iodine (pp. S190) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + z_1\,c\hat{\mathbf{z}}$	$(8f)$	P
$\mathbf{B_2}$	=	$\left(\frac{1}{2}+y_1\right)\mathbf{a_1} + \left(\frac{1}{2}-y_1\right)\mathbf{a_2} + \left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2}+z_1\right)c\hat{\mathbf{z}}$	$(8f)$	P
$\mathbf{B_3}$	=	$\left(\frac{1}{2}-y_1\right)\mathbf{a_1} + \left(\frac{1}{2}+y_1\right)\mathbf{a_2} + \left(\frac{1}{2}-z_1\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2}-z_1\right)c\hat{\mathbf{z}}$	$(8f)$	P
$\mathbf{B_4}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-y_1\,b\,\hat{\mathbf{y}} - z_1\,c\hat{\mathbf{z}}$	$(8f)$	P

References:

- A. Brown and S. Rundqvist, *Refinement of the crystal structure of black phosphorus*, Acta Cryst. **19**, 684–685 (1965), doi:10.1107/S0365110X65004140.

Geometry files:
- CIF: pp. S675
- POSCAR: pp. S675

Molecular Iodine (I) Crystal Structure (A14): A_oC8_64_f

Prototype	:	I
AFLOW prototype label	:	A_oC8_64_f
***Strukturbericht* designation**	:	A14
Pearson symbol	:	oC8
Space group number	:	64
Space group symbol	:	Cmca
AFLOW prototype command	:	`aflow --proto=A_oC8_64_f` `--params=`$a, b/a, c/a, y_1, z_1$

- Note that α-Ga (pp. S183), black phosphorus (pp. S188), and molecular iodine (pp. S190) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$-y_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$y_1\,b\,\hat{\mathbf{y}} + z_1\,c\hat{\mathbf{z}}$	$(8f)$	I
$\mathbf{B_2}$	=	$\left(\frac{1}{2}+y_1\right)\mathbf{a_1} + \left(\frac{1}{2}-y_1\right)\mathbf{a_2} + \left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2}+z_1\right)c\hat{\mathbf{z}}$	$(8f)$	I

$\mathbf{B_3}$	=	$\left(\frac{1}{2} - y_1\right)\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_1\,b\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\hat{\mathbf{z}}$	$(8f)$	I
$\mathbf{B_4}$	=	$y_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-y_1\,b\,\hat{\mathbf{y}} - z_1\,c\hat{\mathbf{z}}$	$(8f)$	I

References:

- C. Petrillo, O. Moze, and R. M. Ibberson, *High resolution neutron powder diffraction investigation of the low temperature crystal structure of molecular iodine (I_2)*, Physica B **180-181**, 639–641 (1992), doi:10.1016/0921-4526(92)90420-W.

Found in:

- M. Winter, *WebElements: the periodic table on the WWW* (1993-2015). The University of Sheffield and WebElements Ltd.

Geometry files:

- CIF: pp. S675
- POSCAR: pp. S675

α-IrV Crystal Structure: AB_oC8_65_j_g

Prototype	:	α-IrV
AFLOW prototype label	:	AB_oC8_65_j_g
***Strukturbericht* designation**	:	None
Pearson symbol	:	oC8
Space group number	:	65
Space group symbol	:	Cmmm
AFLOW prototype command	:	`aflow --proto=AB_oC8_65_j_g` `--params=`$a, b/a, c/a, x_1, y_2$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}}$	$(4g)$	V
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}}$	$(4g)$	V
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$y_2\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4j)$	Ir
$\mathbf{B_4}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-y_2\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4j)$	Ir

References:

- B. C. Giessen and N. J. Grant, *New intermediate phases in transition metal systems, III*, Acta Cryst. **18**, 1080–1081 (1965), doi:10.1107/S0365110X65002566.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4139.

Geometry files:

- CIF: pp. S676
- POSCAR: pp. S676

Ga_3Pt_5 Structure: A3B5_oC16_65_ah_bej

Prototype	:	Ga_3Pt_5
AFLOW prototype label	:	A3B5_oC16_65_ah_bej
***Strukturbericht* designation**	:	None
Pearson symbol	:	oC16
Space group number	:	65
Space group symbol	:	Cmmm
AFLOW prototype command	:	`aflow --proto=A3B5_oC16_65_ah_bej --params=`$a, b/a, c/a, x_4, y_5$

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ga I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(2b)$	Pt I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}}$	$(4e)$	Pt II
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}}$	$(4e)$	Pt II
$\mathbf{B_5}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\hat{\mathbf{z}}$	$(4h)$	Ga II

$\mathbf{B_6}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\hat{\mathbf{z}}$	$(4h)$	Ga II
$\mathbf{B_7}$	=	$-y_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$y_5\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\hat{\mathbf{z}}$	$(4j)$	Pt III
$\mathbf{B_8}$	=	$y_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-y_5\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\hat{\mathbf{z}}$	$(4j)$	Pt III

References:

- K. Schubert, S. Bhan, W. Burkhardt, R. Gohle, H. G. Meissner, M. Pötzschke, and E. Stolz, *Einige strukturelle Ergebnisse an metallischen Phasen (5)*, Naturwissenschaften **47**, 303 (1960).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 3540.

Geometry files:

- CIF: pp. S676
- POSCAR: pp. S676

Predicted $CdPt_3$ ("$L1_3$") Structure: AB3_oC8_65_a_bf

Prototype	:	$CdPt_3$
AFLOW prototype label	:	AB3_oC8_65_a_bf
***Strukturbericht* designation**	:	$L1_3$
Pearson symbol	:	oC8
Space group number	:	65
Space group symbol	:	Cmmm
AFLOW prototype command	:	`aflow --proto=AB3_oC8_65_a_bf` `--params=`$a, b/a, c/a$

- This structure has not been experimentally confirmed, but it has frequently been predicted as a low energy structure. (Hart, 2009) has a review of these calculations. The $L1_3$ designation is not official, but we use it here for consistency with previous literature. Data for this structure comes from the supplemental material of (Hart, 2013).

Base-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Cd
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(2b)$	Pt I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	Pt II
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	Pt II

References:

- G. L. W. Hart, *Verifying predictions of the $L1_3$ crystal structure in Cd-Pt and Pd-Pt by exhaustive enumeration*, Phys. Rev. B **80**, 014106 (2009), doi:10.1103/PhysRevB.80.014106.
- G. L. W. Hart, S. Curtarolo, T. B. Massalski, and O. Levy, *Comprehensive Search for New Phases and Compounds in Binary Alloy Systems Based on Platinum-Group Metals, Using a Computational First-Principles Approach*, Phys. Rev. X **3**, 041035 (2013), doi:10.1103/PhysRevX.3.041035. Data in supplementary material.

Geometry files:

- CIF: pp. S677
- POSCAR: pp. S677

TlF (B24) Structure: AB_oF8_69_a_b

Prototype	:	TlF
AFLOW prototype label	:	AB_oF8_69_a_b
***Strukturbericht* designation**	:	B24
Pearson symbol	:	oF8
Space group number	:	69
Space group symbol	:	Fmmm
AFLOW prototype command	:	`aflow --proto=AB_oF8_69_a_b --params=`$a, b/a, c/a$

- Although this is the B24 structure defined in Strukturbericht, it is not the currently accepted structure for TlF. See (Berastegui, 2000) and the TlF-II page. This is a slight distortion of the rock salt (B1) structure.

Face-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	F
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4b)$	Tl

References:

- J. A. A. Ketelaar, *Die Kristallstruktur des Thallofluorids*, Zeitschrift für Kristallographie - Crystalline Materials **92**, 30–38 (1935), doi:10.1524/zkri.1935.92.1.30.

Found in:

- P. Berastegui and S. Hull, *The Crystal Structures of Thallium(I) Fluoride*, J. Solid State Chem. **150**, 266–275 (2000), doi:10.1006/jssc.1999.8587.

Geometry files:

- CIF: pp. S677
- POSCAR: pp. S677

γ-Pu Structure: A_oF8_70_a

Prototype	:	γ-Pu
AFLOW prototype label	:	A_oF8_70_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	oF8
Space group number	:	70
Space group symbol	:	Fddd
AFLOW prototype command	:	`aflow --proto=A_oF8_70_a --params=`$a, b/a, c/a$

- It is obvious from the coordinates that this is an extremely distorted diamond (A4) structure, but, as noted by (Donohue, 1982), it can also be considered as a distorted hcp (A3) structure.

Face-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\, b\, \hat{\mathbf{y}} + \tfrac{1}{2}\, c\, \hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\, a\, \hat{\mathbf{x}} + \tfrac{1}{2}\, c\, \hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\, a\, \hat{\mathbf{x}} + \tfrac{1}{2}\, b\, \hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B}_1$	=	$\frac{1}{8}\,\mathbf{a}_1 + \frac{1}{8}\,\mathbf{a}_2 + \frac{1}{8}\,\mathbf{a}_3$	=	$\frac{1}{8}\, a\, \hat{\mathbf{x}} + \frac{1}{8}\, b\, \hat{\mathbf{y}} + \frac{1}{8}\, c\, \hat{\mathbf{z}}$	$(8a)$	Pu
$\mathbf{B}_2$	=	$\frac{7}{8}\,\mathbf{a}_1 + \frac{7}{8}\,\mathbf{a}_2 + \frac{7}{8}\,\mathbf{a}_3$	=	$\frac{7}{8}\, a\, \hat{\mathbf{x}} + \frac{7}{8}\, b\, \hat{\mathbf{y}} + \frac{7}{8}\, c\, \hat{\mathbf{z}}$	$(8a)$	Pu

References:

- W. H. Zachariasen and F. H. Ellinger, *Crystal chemical studies of the 5f-series of elements. XXIV. The crystal structure*

and thermal expansion of γ-plutonium, Acta Cryst. **8**, 431–433 (1955), doi:10.1107/S0365110X55001357.
- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982).

Geometry files:
- CIF: pp. S677
- POSCAR: pp. S678

$TiSi_2$ (C54) Structure: A2B_oF24_70_e_a

Prototype	:	$TiSi_2$
AFLOW prototype label	:	A2B_oF24_70_e_a
***Strukturbericht* designation**	:	C54
Pearson symbol	:	oF24
Space group number	:	70
Space group symbol	:	Fddd
AFLOW prototype command	:	`aflow --proto=A2B_oF24_70_e_a --params=`$a, b/a, c/a, x_2$

Face-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\, b\, \hat{\mathbf{y}} + \tfrac{1}{2}\, c\, \hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\, a\, \hat{\mathbf{x}} + \tfrac{1}{2}\, c\, \hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\, a\, \hat{\mathbf{x}} + \tfrac{1}{2}\, b\, \hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{1}{8}\,\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,b\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(8a)$	Ti
$\mathbf{B_2}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{7}{8}\,\mathbf{a_3}$	=	$\frac{7}{8}\,a\,\hat{\mathbf{x}} + \frac{7}{8}\,b\,\hat{\mathbf{y}} + \frac{7}{8}\,c\,\hat{\mathbf{z}}$	$(8a)$	Ti
$\mathbf{B_3}$	=	$\left(\frac{1}{4} - x_2\right)\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,b\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(16e)$	Si
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{4} - x_2\right)\,\mathbf{a_2} + \left(\frac{1}{4} - x_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,b\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(16e)$	Si

$\mathbf{B_5}$	=	$\left(\frac{3}{4}+x_2\right)\mathbf{a_1} - x_2\,\mathbf{a_2} + -x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,b\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	(16*e*)	Si
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{3}{4}+x_2\right)\mathbf{a_2} + \left(\frac{3}{4}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{3}{4}+x_2\right)a\,\hat{\mathbf{x}} + \frac{3}{8}\,b\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	(16*e*)	Si

References:

- W. Jeitschko, *Refinement of the crystal structure of $TiSi_2$ and some comments on bonding in $TiSi_2$ and related compounds*, Acta Crystallogr. Sect. B Struct. Sci. **33**, 2347–2348 (1977), doi:10.1107/S0567740877008462.

Geometry files:

- CIF: pp. S678
- POSCAR: pp. S678

α-S (A16) Structure: A_oF128_70_4h

Prototype	:	α-S
AFLOW prototype label	:	A_oF128_70_4h
***Strukturbericht* designation**	:	A16
Pearson symbol	:	oF128
Space group number	:	70
Space group symbol	:	Fddd
AFLOW prototype command	:	`aflow --proto=A_oF128_70_4h` `--params=`$a, b/a, c/a, x_1, y_1, z_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4$

Face-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\, b\, \hat{\mathbf{y}} + \tfrac{1}{2}\, c\, \hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\, a\, \hat{\mathbf{x}} + \tfrac{1}{2}\, c\, \hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\, a\, \hat{\mathbf{x}} + \tfrac{1}{2}\, b\, \hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$(y_1 + z_1 - x_1)\ \mathbf{a_1} + (z_1 + x_1 - y_1)\ \mathbf{a_2} + (x_1 + y_1 - z_1)\ \mathbf{a_3}$	=	$x_1\, a\, \hat{\mathbf{x}} + y_1\, b\, \hat{\mathbf{y}} + z_1\, c\, \hat{\mathbf{z}}$	$(32h)$	S I
$\mathbf{B_2}$	=	$(x_1 - y_1 + z_1)\ \mathbf{a_1} + (y_1 + z_1 - x_1)\ \mathbf{a_2} + \left(\frac{1}{2} - x_1 - y_1 - z_1\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{4} - x_1\right)\, a\, \hat{\mathbf{x}} + \left(\frac{1}{4} - y_1\right)\, b\, \hat{\mathbf{y}} + z_1\, c\, \hat{\mathbf{z}}$	$(32h)$	S I
$\mathbf{B_3}$	=	$(x_1 + y_1 - z_1)\ \mathbf{a_1} + \left(\frac{1}{2} - x_1 - y_1 - z_1\right)\ \mathbf{a_2} + (y_1 + z_1 - x_1)\ \mathbf{a_3}$	=	$\left(\frac{1}{4} - x_1\right)\, a\, \hat{\mathbf{x}} + y_1\, b\, \hat{\mathbf{y}} + \left(\frac{1}{4} - z_1\right)\, c\, \hat{\mathbf{z}}$	$(32h)$	S I

$\mathbf{B_4}$	=	$\left(\frac{1}{2} - x_1 - y_1 - z_1\right)\mathbf{a_1} + (x_1 + y_1 - z_1)\mathbf{a_2} + (x_1 - y_1 + z_1)\mathbf{a_3}$	=	$x_1\, a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_1\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_1\right) c\,\hat{\mathbf{z}}$	(32h)	S I
$\mathbf{B_5}$	=	$(x_1 - y_1 - z_1)\mathbf{a_1} + (y_1 - z_1 - x_1)\mathbf{a_2} + (z_1 - x_1 - y_1)\mathbf{a_3}$	=	$-x_1\, a\,\hat{\mathbf{x}} - y_1\, b\,\hat{\mathbf{y}} - z_1\, c\,\hat{\mathbf{z}}$	(32h)	S I
$\mathbf{B_6}$	=	$(y_1 - z_1 - x_1)\mathbf{a_1} + (x_1 - y_1 - z_1)\mathbf{a_2} + \left(\frac{1}{2} + x_1 + y_1 + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_1\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_1\right) b\,\hat{\mathbf{y}} - z_1\, c\,\hat{\mathbf{z}}$	(32h)	S I
$\mathbf{B_7}$	=	$(z_1 - x_1 - y_1)\mathbf{a_1} + \left(\frac{1}{2} + x_1 + y_1 + z_1\right)\mathbf{a_2} + (x_1 - y_1 - z_1)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_1\right) a\,\hat{\mathbf{x}} - y_1\, b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_1\right) c\,\hat{\mathbf{z}}$	(32h)	S I
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_1 + y_1 + z_1\right)\mathbf{a_1} + (z_1 - x_1 - y_1)\mathbf{a_2} + (y_1 - z_1 - x_1)\mathbf{a_3}$	=	$-x_1\, a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_1\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_1\right) c\,\hat{\mathbf{z}}$	(32h)	S I
$\mathbf{B_9}$	=	$(y_2 + z_2 - x_2)\mathbf{a_1} + (z_2 + x_2 - y_2)\mathbf{a_2} + (x_2 + y_2 - z_2)\mathbf{a_3}$	=	$x_2\, a\,\hat{\mathbf{x}} + y_2\, b\,\hat{\mathbf{y}} + z_2\, c\,\hat{\mathbf{z}}$	(32h)	S II
$\mathbf{B_{10}}$	=	$(x_2 - y_2 + z_2)\mathbf{a_1} + (y_2 + z_2 - x_2)\mathbf{a_2} + \left(\frac{1}{2} - x_2 - y_2 - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_2\right) b\,\hat{\mathbf{y}} + z_2\, c\,\hat{\mathbf{z}}$	(32h)	S II
$\mathbf{B_{11}}$	=	$(x_2 + y_2 - z_2)\mathbf{a_1} + \left(\frac{1}{2} - x_2 - y_2 - z_2\right)\mathbf{a_2} + (y_2 + z_2 - x_2)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right) a\,\hat{\mathbf{x}} + y_2\, b\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_2\right) c\,\hat{\mathbf{z}}$	(32h)	S II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - x_2 - y_2 - z_2\right)\mathbf{a_1} + (x_2 + y_2 - z_2)\mathbf{a_2} + (x_2 - y_2 + z_2)\mathbf{a_3}$	=	$x_2\, a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_2\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_2\right) c\,\hat{\mathbf{z}}$	(32h)	S II
$\mathbf{B_{13}}$	=	$(x_2 - y_2 - z_2)\mathbf{a_1} + (y_2 - z_2 - x_2)\mathbf{a_2} + (z_2 - x_2 - y_2)\mathbf{a_3}$	=	$-x_2\, a\,\hat{\mathbf{x}} - y_2\, b\,\hat{\mathbf{y}} - z_2\, c\,\hat{\mathbf{z}}$	(32h)	S II
$\mathbf{B_{14}}$	=	$(y_2 - z_2 - x_2)\mathbf{a_1} + (x_2 - y_2 - z_2)\mathbf{a_2} + \left(\frac{1}{2} + x_2 + y_2 + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_2\right) b\,\hat{\mathbf{y}} - z_2\, c\,\hat{\mathbf{z}}$	(32h)	S II
$\mathbf{B_{15}}$	=	$(z_2 - x_2 - y_2)\mathbf{a_1} + \left(\frac{1}{2} + x_2 + y_2 + z_2\right)\mathbf{a_2} + (x_2 - y_2 - z_2)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right) a\,\hat{\mathbf{x}} - y_2\, b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_2\right) c\,\hat{\mathbf{z}}$	(32h)	S II
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} + x_2 + y_2 + z_2\right)\mathbf{a_1} + (z_2 - x_2 - y_2)\mathbf{a_2} + (y_2 - z_2 - x_2)\mathbf{a_3}$	=	$-x_2\, a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_2\right) b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_2\right) c\,\hat{\mathbf{z}}$	(32h)	S II
$\mathbf{B_{17}}$	=	$(y_3 + z_3 - x_3)\mathbf{a_1} + (z_3 + x_3 - y_3)\mathbf{a_2} + (x_3 + y_3 - z_3)\mathbf{a_3}$	=	$x_3\, a\,\hat{\mathbf{x}} + y_3\, b\,\hat{\mathbf{y}} + z_3\, c\,\hat{\mathbf{z}}$	(32h)	S III
$\mathbf{B_{18}}$	=	$(x_3 - y_3 + z_3)\mathbf{a_1} + (y_3 + z_3 - x_3)\mathbf{a_2} + \left(\frac{1}{2} - x_3 - y_3 - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right) a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_3\right) b\,\hat{\mathbf{y}} + z_3\, c\,\hat{\mathbf{z}}$	(32h)	S III
$\mathbf{B_{19}}$	=	$(x_3 + y_3 - z_3)\mathbf{a_1} + \left(\frac{1}{2} - x_3 - y_3 - z_3\right)\mathbf{a_2} + (y_3 + z_3 - x_3)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right) a\,\hat{\mathbf{x}} + y_3\, b\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_3\right) c\,\hat{\mathbf{z}}$	(32h)	S III

$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} - x_3 - y_3 - z_3\right)\mathbf{a_1} + (x_3 + y_3 - z_3)\mathbf{a_2} + (x_3 - y_3 + z_3)\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_3\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_3\right)c\,\hat{\mathbf{z}}$	(32h)	S III
$\mathbf{B_{21}}$	=	$(x_3 - y_3 - z_3)\mathbf{a_1} + (y_3 - z_3 - x_3)\mathbf{a_2} + (z_3 - x_3 - y_3)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(32h)	S III
$\mathbf{B_{22}}$	=	$(y_3 - z_3 - x_3)\mathbf{a_1} + (x_3 - y_3 - z_3)\mathbf{a_2} + \left(\frac{1}{2} + x_3 + y_3 + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_3\right)b\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(32h)	S III
$\mathbf{B_{23}}$	=	$(z_3 - x_3 - y_3)\mathbf{a_1} + \left(\frac{1}{2} + x_3 + y_3 + z_3\right)\mathbf{a_2} + (x_3 - y_3 - z_3)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{x}} - y_3\,b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right)c\,\hat{\mathbf{z}}$	(32h)	S III
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2} + x_3 + y_3 + z_3\right)\mathbf{a_1} + (z_3 - x_3 - y_3)\mathbf{a_2} + (y_3 - z_3 - x_3)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_3\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right)c\,\hat{\mathbf{z}}$	(32h)	S III
$\mathbf{B_{25}}$	=	$(y_4 + z_4 - x_4)\mathbf{a_1} + (z_4 + x_4 - y_4)\mathbf{a_2} + (x_4 + y_4 - z_4)\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(32h)	S IV
$\mathbf{B_{26}}$	=	$(x_4 - y_4 + z_4)\mathbf{a_1} + (y_4 + z_4 - x_4)\mathbf{a_2} + \left(\frac{1}{2} - x_4 - y_4 - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_4\right)b\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(32h)	S IV
$\mathbf{B_{27}}$	=	$(x_4 + y_4 - z_4)\mathbf{a_1} + \left(\frac{1}{2} - x_4 - y_4 - z_4\right)\mathbf{a_2} + (y_4 + z_4 - x_4)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_4\right)a\,\hat{\mathbf{x}} + y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_4\right)c\,\hat{\mathbf{z}}$	(32h)	S IV
$\mathbf{B_{28}}$	=	$\left(\frac{1}{2} - x_4 - y_4 - z_4\right)\mathbf{a_1} + (x_4 + y_4 - z_4)\mathbf{a_2} + (x_4 - y_4 + z_4)\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - y_4\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_4\right)c\,\hat{\mathbf{z}}$	(32h)	S IV
$\mathbf{B_{29}}$	=	$(x_4 - y_4 - z_4)\mathbf{a_1} + (y_4 - z_4 - x_4)\mathbf{a_2} + (z_4 - x_4 - y_4)\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(32h)	S IV
$\mathbf{B_{30}}$	=	$(y_4 - z_4 - x_4)\mathbf{a_1} + (x_4 - y_4 - z_4)\mathbf{a_2} + \left(\frac{1}{2} + x_4 + y_4 + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_4\right)b\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(32h)	S IV
$\mathbf{B_{31}}$	=	$(z_4 - x_4 - y_4)\mathbf{a_1} + \left(\frac{1}{2} + x_4 + y_4 + z_4\right)\mathbf{a_2} + (x_4 - y_4 - z_4)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_4\right)a\,\hat{\mathbf{x}} - y_4\,b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right)c\,\hat{\mathbf{z}}$	(32h)	S IV
$\mathbf{B_{32}}$	=	$\left(\frac{1}{2} + x_4 + y_4 + z_4\right)\mathbf{a_1} + (z_4 - x_4 - y_4)\mathbf{a_2} + (y_4 - z_4 - x_4)\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + y_4\right)b\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right)c\,\hat{\mathbf{z}}$	(32h)	S IV

References:

- S. J. Rettig and J. Trotter, *Refinement of the structure of orthorhombic sulfur, α-S_8*, Acta Crystallographic C **43**, 2260–2262 (1987), doi:10.1107/S0108270187088152.

Geometry files:

- CIF: pp. S679
- POSCAR: pp. S679

$ReSi_2$ Structure: AB2_oI6_71_a_i

Prototype	:	$ReSi_2$
AFLOW prototype label	:	AB2_oI6_71_a_i
***Strukturbericht* designation**	:	None
Pearson symbol	:	oI6
Space group number	:	71
Space group symbol	:	Immm
AFLOW prototype command	:	`aflow --proto=AB2_oI6_71_a_i` `--params=`$a, b/a, c/a, z_2$

Body-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Re
$\mathbf{B_2}$	=	$z_2\,\mathbf{a_1} + z_2\,\mathbf{a_2}$	=	$z_2\,c\,\hat{\mathbf{z}}$	$(4i)$	Si
$\mathbf{B_3}$	=	$-z_2\,\mathbf{a_1} - z_2\,\mathbf{a_2}$	=	$-z_2\,c\,\hat{\mathbf{z}}$	$(4i)$	Si

References:

- T. Siegrist, F. Hulliger, and G. Travaglini, *The crystal structure and some properties of $ReSi_2$*, J. Less-Common Met. **92**, 119–129 (1983), doi:10.1016/0022-5088(83)90233-3.

Geometry files:

- CIF: pp. S679
- POSCAR: pp. S680

$MoPt_2$ Structure: AB2_oI6_71_a_g

Prototype	:	$MoPt_2$
AFLOW prototype label	:	AB2_oI6_71_a_g
***Strukturbericht* designation**	:	None
Pearson symbol	:	oI6
Space group number	:	71
Space group symbol	:	Immm
AFLOW prototype command	:	`aflow --proto=AB2_oI6_71_a_g` `--params=`$a, b/a, c/a, y_2$

Body-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Mo
$\mathbf{B_2}$	=	$y_2\,\mathbf{a_1} + y_2\,\mathbf{a_3}$	=	$y_2\,b\,\hat{\mathbf{y}}$	$(4g)$	Pt
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} - y_2\,\mathbf{a_3}$	=	$-y_2\,b\,\hat{\mathbf{y}}$	$(4g)$	Pt

References:

- K. Schubert, W. Burkhardt, P. Esslinger, E. Günzel, H. G. Meissner, W. Schütt, J. Wegst, and M. Wilkens, *Einige strukturelle Ergebnisse an metallischen Phasen*, Naturwissenschaften **43**, 248–249 (1956), doi:10.1007/BF00617585.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:
- CIF: pp. S680
- POSCAR: pp. S680

SiS_2 Structure: A2B_oI12_72_j_a

Prototype	:	SiS_2
AFLOW prototype label	:	A2B_oI12_72_j_a
***Strukturbericht* designation**	:	C42
Pearson symbol	:	oI12
Space group number	:	72
Space group symbol	:	Ibam
AFLOW prototype command	:	`aflow --proto=A2B_oI12_72_j_a --params=`$a, b/a, c/a, x_2, y_2$

Other compounds with this structure:

- SeS_2

Body-centered Orthorhombic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,b\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,b\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Si
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Si
$\mathbf{B_3}$	=	$y_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + (x_2 + y_2)\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,b\,\hat{\mathbf{y}}$	$(8j)$	S
$\mathbf{B_4}$	=	$-y_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - (x_2 + y_2)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}}$	$(8j)$	S
$\mathbf{B_5}$	=	$\left(\frac{1}{2} + y_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_2} + (-x_2 + y_2)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} y_2\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8j)$	S
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - y_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_2} + (x_2 - y_2)\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} - y_2\,b\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8j)$	S

References:

- J. Peters and B. Krebs, *Silicon disulphide and silicon diselenide: a reinvestigation*, Acta Crystallographic B **38**, 1270–1272 (1982), doi:10.1107/S0567740882005469.

Geometry files:

- CIF: pp. S680
- POSCAR: pp. S681

BPO_4 ($H0_7$) Structure: AB4C_tI12_82_c_g_a

Prototype	:	BPO_4
AFLOW prototype label	:	AB4C_tI12_82_c_g_a
***Strukturbericht* designation**	:	$H0_7$
Pearson symbol	:	tI12
Space group number	:	82
Space group symbol	:	$I\bar{4}$
AFLOW prototype command	:	`aflow --proto=AB4C_tI12_82_c_g_a` `--params=`$a, c/a, x_3, y_3, z_3$

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	P
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	B
$\mathbf{B_3}$	=	$(y_3 + z_3)\,\mathbf{a_1} + (z_3 + x_3)\,\mathbf{a_2} + (x_3 + y_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(8g)$	O
$\mathbf{B_4}$	=	$(z_3 - y_3)\,\mathbf{a_1} + (z_3 - x_3)\,\mathbf{a_2} - (x_3 + y_3)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(8g)$	O
$\mathbf{B_5}$	=	$-(z_3 + x_3)\,\mathbf{a_1} + (y_3 - z_3)\,\mathbf{a_2} + (y_3 - x_3)\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(8g)$	O
$\mathbf{B_6}$	=	$(x_3 - z_3)\,\mathbf{a_1} - (y_3 + z_3)\,\mathbf{a_2} + (x_3 - y_3)\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(8g)$	O

References:

- M. Schmidt, B. Ewald, Y. Prots, R. Cardoso-Gil, M. Armbrüster, I. Loa, L. Zhang, Y.-X. Huang, U. Schwarz, and R. Kniep, *Growth and Characterization of BPO_4 Single Crystals*, Z. Anorg. Allg. Chem. **630**, 655–662 (2004), doi:10.1002/zaac.200400002.

Geometry files:
- CIF: pp. S681
- POSCAR: pp. S681

$CdAl_2S_4$ (E3) Structure: A2BC4_tI14_82_bc_a_g

Prototype	:	$CdAl_2S_4$
AFLOW prototype label	:	A2BC4_tI14_82_bc_a_g
***Strukturbericht* designation**	:	E3
Pearson symbol	:	tI14
Space group number	:	82
Space group symbol	:	$I\bar{4}$
AFLOW prototype command	:	`aflow --proto=A2BC4_tI14_82_bc_a_g` `--params=`$a, c/a, x_4, y_4, z_4$

Other compounds with this structure:

- $CoGa_2S_4$, $FeGa_2S_4$, $HgGa_2Te_4$, $ZnGa_2S_4$, $HgAl_2S_4$, numerous others.

- When $c = 2a$ and $x = y = 1/4$, and $z = 1/8$ the atoms are on the sites of the diamond (A4) structure, but of course there are defects. Removing the Al-I (2b) atom transforms this to the BPO_4 ($H0_7$) structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Cd
$\mathbf{B_2}$	=	$\tfrac{1}{2}\,\mathbf{a_1} + \tfrac{1}{2}\,\mathbf{a_2}$	=	$\tfrac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2b)$	Al I

$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(2c)	Al II
$\mathbf{B_4}$	=	$(y_4 + z_4)\,\mathbf{a_1} + (z_4 + x_4)\,\mathbf{a_2} + (x_4 + y_4)\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8g)	S
$\mathbf{B_5}$	=	$(z_4 - y_4)\,\mathbf{a_1} + (z_4 - x_4)\,\mathbf{a_2} - (x_4 + y_4)\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8g)	S
$\mathbf{B_6}$	=	$-(z_4 + x_4)\,\mathbf{a_1} + (y_4 - z_4)\,\mathbf{a_2} + (y_4 - x_4)\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(8g)	S
$\mathbf{B_7}$	=	$(x_4 - z_4)\,\mathbf{a_1} - (y_4 + z_4)\,\mathbf{a_2} + (x_4 - y_4)\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(8g)	S

References:

- H. Hahn, G. Frank, W. Klingler, A. Störger, and G. Störger, *Untersuchungen über ternäre Chalkogenide. VI. Über ternäre Chalogenide des Aluminiums, Galliums und Indiums mit Zink, Cadmium und Quecksilber*, Z. Anorg. Allg. Chem. **279**, 241–270 (1955), doi:10.1002/zaac.19552790502.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S681
- POSCAR: pp. S681

PdS (B34) Structure: AB_tP16_84_cej_k

Prototype	:	PdS
AFLOW prototype label	:	AB_tP16_84_cej_k
***Strukturbericht* designation**	:	B34
Pearson symbol	:	tP16
Space group number	:	84
Space group symbol	:	$P4_2/m$
AFLOW prototype command	:	`aflow --proto=AB_tP16_84_cej_k` `--params=`$a, c/a, x_3, y_3, x_4, y_4, z_4$

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(2c)$	Pd I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2c)$	Pd I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2e)$	Pd II
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2e)$	Pd II
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}}$	$(4j)$	Pd III
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}}$	$(4j)$	Pd III

$\mathbf{B_7}$	=	$-y_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4j)$	Pd III
$\mathbf{B_8}$	=	$y_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4j)$	Pd III
$\mathbf{B_9}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(8k)$	S
$\mathbf{B_{10}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(8k)$	S
$\mathbf{B_{11}}$	=	$-y_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(8k)$	S
$\mathbf{B_{12}}$	=	$y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(8k)$	S
$\mathbf{B_{13}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(8k)$	S
$\mathbf{B_{14}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(8k)$	S
$\mathbf{B_{15}}$	=	$y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(8k)$	S
$\mathbf{B_{16}}$	=	$-y_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(8k)$	S

References:

- N. E. Brese, P. J. Squattrito, and J. A. Ibers, *Reinvestigation of the structure of PdS*, Acta Crystallogr. C **41**, 1829–1830 (1985), doi:10.1107/S0108270185009623.

Geometry files:

- CIF: pp. S682
- POSCAR: pp. S682

Ti_5Te_4 Structure: A4B5_tI18_87_h_ah

Prototype	:	Ti_5Te_4
AFLOW prototype label	:	A4B5_tI18_87_h_ah
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI18
Space group number	:	87
Space group symbol	:	I4/m
AFLOW prototype command	:	`aflow --proto=A4B5_tI18_87_h_ah` `--params=`$a, c/a, x_2, y_2, x_3, y_3$

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ti I
$\mathbf{B_2}$	=	$y_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + (x_2 + y_2)\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Te

$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - (x_2 + y_2)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{y}}$	(8*h*)	Te
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + (x_2 - y_2)\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	(8*h*)	Te
$\mathbf{B_5}$	=	$-x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + (y_2 - x_2)\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	(8*h*)	Te
$\mathbf{B_6}$	=	$y_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + (x_3 + y_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}}$	(8*h*)	Ti II
$\mathbf{B_7}$	=	$-y_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - (x_3 + y_3)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}}$	(8*h*)	Ti II
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + (x_3 - y_3)\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}}$	(8*h*)	Ti II
$\mathbf{B_9}$	=	$-x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + (y_3 - x_3)\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}}$	(8*h*)	Ti II

References:

- F. Grønvold, A. Kjekshus, and F. Raaum, *The crystal structure of Ti_5Te_4*, Acta Cryst. **14**, 930–934 (1961), doi:10.1107/S0365110X61002722.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 5321.

Geometry files:

- CIF: pp. S682
- POSCAR: pp. S682

Ni_4Mo ($D1_a$) Structure: AB4_tI10_87_a_h

Prototype	:	Ni_4Mo
AFLOW prototype label	:	AB4_tI10_87_a_h
***Strukturbericht* designation**	:	$D1_a$
Pearson symbol	:	tI10
Space group number	:	87
Space group symbol	:	I4/m
AFLOW prototype command	:	`aflow --proto=AB4_tI10_87_a_h` `--params=`$a, c/a, x_2, y_2$

Other compounds with this structure:

- Ag_4Lu, Ag_4Sc, Au_4Cr, Au_4Er, Au_4Ho, Au_4Lu, Au_4Mn, Au_4V, Au_4Yb, Ni_4W

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Mo
$\mathbf{B_2}$	=	$y_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + (x_2 + y_2)\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Ni
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - (x_2 + y_2)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Ni
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + (x_2 - y_2)\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Ni
$\mathbf{B_5}$	=	$-x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + (y_2 - x_2)\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Ni

References:

- D. Harker, *The Crystal Structure of* Ni_4Mo, J. Chem. Phys. **12**, 315 (1944), doi:10.1063/1.1723945.

Geometry files:

- CIF: pp. S683
- POSCAR: pp. S683

α-Cristobalite (SiO_2, low) Structure: A2B_tP12_92_b_a

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_tP12_92_b_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP12
Space group number	:	92
Space group symbol	:	$P4_12_12$
AFLOW prototype command	:	`aflow --proto=A2B_tP12_92_b_a` `--params=`$a, c/a, x_1, x_2, y_2, z_2$

Other compounds with this structure:

- TeO_2 paratellurite, BeF_2

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}}$	$(4a)$	Si
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4a)$	Si
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - x_1\right)\,\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Si
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\,\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Si
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(8b)$	O

$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	O
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - y_2\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \left(\frac{1}{4} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	O
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + y_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \left(\frac{3}{4} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	O
$\mathbf{B_9}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \left(\frac{1}{4} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	O
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + \left(\frac{3}{4} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	O
$\mathbf{B_{11}}$	=	$y_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(8*b*)	O
$\mathbf{B_{12}}$	=	$-y_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	O

References:

- J. J. Pluth, J. V. Smith, and J. Faber Jr., *Crystal structure of low cristobalite at 10, 293, and 473 K: Variation of framework geometry with temperature*, J. Appl. Phys. **57**, 1045–1049 (1985), doi:10.1063/1.334545.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4759.

Geometry files:

- CIF: pp. S683
- POSCAR: pp. S683

Keatite (SiO_2) Structure: A2B_tP36_96_3b_ab

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_tP36_96_3b_ab
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP36
Space group number	:	96
Space group symbol	:	$P4_32_12$
AFLOW prototype command	:	`aflow --proto=A2B_tP36_96_3b_ab` `--params=`$a, c/a, x_1, x_2, y_2, z_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5$

- All references, including (Wyckoff, 1963), (Shropshire, 1959) and (Demuth, 1999) note that keatite can exist in both space group $P4_12_12$-D_4^4 (#92) and its enantiomorph $P4_32_12$-D_4^8 (#96). Wyckoff uses the coordinates proposed by Shropshire and assumes the space group is $P4_12_12$. He then notes that one of the Si-O bonds in this structure is very long (3.69 Å), and is "so improbable that there is something wrong either with the parameters as stated or the structure itself". If we use space group $P4_32_12$ while retaining Shropshire's coordinates we obtain a much more convincing structure, one that looks much like the structure in Shropshire's Fig. 3. For this reason we place this structure in $P4_32_12$.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}}$	(4a)	Si I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(4a)	Si I
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(4a)	Si I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4a)	Si I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(8b)	O I
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(8b)	O I
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - y_2\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \left(\frac{3}{4} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_2\right)c\,\hat{\mathbf{z}}$	(8b)	O I
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + y_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \left(\frac{1}{4} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_2\right)c\,\hat{\mathbf{z}}$	(8b)	O I
$\mathbf{B_9}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \left(\frac{3}{4} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_2\right)c\,\hat{\mathbf{z}}$	(8b)	O I
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + \left(\frac{1}{4} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_2\right)c\,\hat{\mathbf{z}}$	(8b)	O I
$\mathbf{B_{11}}$	=	$y_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(8b)	O I
$\mathbf{B_{12}}$	=	$-y_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	(8b)	O I
$\mathbf{B_{13}}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(8b)	O II
$\mathbf{B_{14}}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	(8b)	O II
$\mathbf{B_{15}}$	=	$\left(\frac{1}{2} - y_3\right)\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\mathbf{a_2} + \left(\frac{3}{4} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_3\right)c\,\hat{\mathbf{z}}$	(8b)	O II
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} + y_3\right)\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\mathbf{a_2} + \left(\frac{1}{4} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right)c\,\hat{\mathbf{z}}$	(8b)	O II
$\mathbf{B_{17}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \left(\frac{1}{2} + y_3\right)\mathbf{a_2} + \left(\frac{3}{4} - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_3\right)c\,\hat{\mathbf{z}}$	(8b)	O II
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \left(\frac{1}{2} - y_3\right)\mathbf{a_2} + \left(\frac{1}{4} - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_3\right)c\,\hat{\mathbf{z}}$	(8b)	O II
$\mathbf{B_{19}}$	=	$y_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(8b)	O II
$\mathbf{B_{20}}$	=	$-y_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)c\,\hat{\mathbf{z}}$	(8b)	O II
$\mathbf{B_{21}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8b)	O III
$\mathbf{B_{22}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	(8b)	O III
$\mathbf{B_{23}}$	=	$\left(\frac{1}{2} - y_4\right)\mathbf{a_1} + \left(\frac{1}{2} + x_4\right)\mathbf{a_2} + \left(\frac{3}{4} + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_4\right)c\,\hat{\mathbf{z}}$	(8b)	O III
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2} + y_4\right)\mathbf{a_1} + \left(\frac{1}{2} - x_4\right)\mathbf{a_2} + \left(\frac{1}{4} + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right)c\,\hat{\mathbf{z}}$	(8b)	O III
$\mathbf{B_{25}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} + \left(\frac{3}{4} - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_4\right)c\,\hat{\mathbf{z}}$	(8b)	O III
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + \left(\frac{1}{4} - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_4\right)c\,\hat{\mathbf{z}}$	(8b)	O III
$\mathbf{B_{27}}$	=	$y_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(8b)	O III

$\mathbf{B_{28}}$	=	$-y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\hat{\mathbf{z}}$	(8*b*)	O III
$\mathbf{B_{29}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{30}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{31}}$	=	$\left(\frac{1}{2} - y_5\right)\mathbf{a_1} + \left(\frac{1}{2} + x_5\right)\mathbf{a_2} + \left(\frac{3}{4} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_5\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{32}}$	=	$\left(\frac{1}{2} + y_5\right)\mathbf{a_1} + \left(\frac{1}{2} - x_5\right)\mathbf{a_2} + \left(\frac{1}{4} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_5\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{33}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + \left(\frac{1}{2} + y_5\right)\mathbf{a_2} + \left(\frac{3}{4} - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_5\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_5\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{34}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} + \left(\frac{1}{2} - y_5\right)\mathbf{a_2} + \left(\frac{1}{4} - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_5\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{35}}$	=	$y_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{36}}$	=	$-y_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II

References:

- J. Shropshire, P. P. Keat, and P. A. Vaughan, *The crystal structure of keatite, a new form of silica*, Zeitschrift für Kristallographie **112**, 409–413 (1959), doi:10.1524/zkri.1959.112.1-6.409.
- R. W. G. Wyckoff, *Crystal Structures Vol. 1* (Wiley, 1963), 2nd edn.

Found in:

- T. Demuth, Y. Jeanvoine, J. Hafner, and J. G. Ángyán, *Polymorphism in silica studied in the local density and generalized-gradient approximations*, J. Phys. Condens. Matter **11**, 3833–3874 (1999), doi:10.1088/0953-8984/11/19/306.

Geometry files:

- CIF: pp. S683
- POSCAR: pp. S684

"ST12" Structure of Si: A_tP12_96_ab

Prototype	:	Si
AFLOW prototype label	:	A_tP12_96_ab
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP12
Space group number	:	96
Space group symbol	:	$P4_32_12$
AFLOW prototype command	:	`aflow --proto=A_tP12_96_ab` `--params=`$a, c/a, x_1, x_2, y_2, z_2$

- This is a tetragonally bonded structure which packs more efficiently than diamond. It is seen experimentally in some silicon and germanium samples and is a staple for testing silicon potentials and first-principles calculations. The structure shown here is taken from the calculations in (Crain, 1994).

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}}$	$(4a)$	Si I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4a)$	Si I
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Si I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Si I

$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - y_2\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \left(\frac{3}{4} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + y_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \left(\frac{1}{4} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_9}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + y_2\right)\mathbf{a_2} + \left(\frac{3}{4} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - y_2\right)\mathbf{a_2} + \left(\frac{1}{4} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{11}}$	=	$y_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(8*b*)	Si II
$\mathbf{B_{12}}$	=	$-y_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	(8*b*)	Si II

References:

- J. Crain, S. J. Clark, G. J. Ackland, M. C. Payne, V. Milman, P. D. Hatton, and B. J. Reid, *Theoretical study of high-density phases of covalent semiconductors. I. Ab initio treatment*, Phys. Rev. B **49**, 5329–5340 (1994), doi:10.1103/PhysRevB.49.5329.

Geometry files:

- CIF: pp. S684
- POSCAR: pp. S684

Tetragonal PZT [$Pb(Zr_xTi_{1-x})O_3$] Structure: A3BC_tP5_99_bc_a_b

Prototype	:	$Pb(Zr_{0.52}Ti_{0.48})O_3$
AFLOW prototype label	:	A3BC_tP5_99_bc_a_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP5
Space group number	:	99
Space group symbol	:	P4mm
AFLOW prototype command	:	`aflow --proto=A3BC_tP5_99_bc_a_b --params=`$a, c/a, z_1, z_2, z_3, z_4$

- This is a tetragonal ferroelectric distortion of the perovskite structure. In $PbZr_xTi_{1-x}O_3$ (aka PZT) it is found for $x < 0.52$. Although the first (2b) site is nearly equally occupied by Zr and Ti atoms, the pictures use Zr atoms. Compare this to the monoclinic PZT structure. To recover the cubic perovskite structure, take $c = a$, $z_1 = 0$, $z_2 = 1/2$, $z_3 = 0$, $z_4 = 1/2$.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(1a)$	Pb
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(1b)$	O I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(1b)$	Zr

$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + z_4\,c\,\hat{\mathbf{z}}$	$(2c)$	O II
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(2c)$	O II

References:

- B. Noheda, J. A. Gonzalo, L. E. Cross, R. Guo, S.-E. Park, D. E. Cox, and G. Shirane, *Tetragonal-to-monoclinic phase transition in a ferroelectric perovskite: The structure of* $PbZr_{0.52}Ti_{0.48}O_3$, Phys. Rev. B **61**, 8687–8695 (2000), doi:10.1103/PhysRevB.61.8687.

Geometry files:

- CIF: pp. S685
- POSCAR: pp. S685

BaS_3 ($D0_{17}$) Structure: AB3_tP8_113_a_ce

Prototype	:	BaS_3
AFLOW prototype label	:	AB3_tP8_113_a_ce
***Strukturbericht* designation**	:	$D0_{17}$
Pearson symbol	:	tP8
Space group number	:	113
Space group symbol	:	$P\bar{4}2_1m$
AFLOW prototype command	:	`aflow --proto=AB3_tP8_113_a_ce` `--params=`$a, c/a, z_2, x_3, z_3$

Other compounds with this structure:

- $AgDyTe_2$, $AgHgTe_2$, $AgErTe_2$, $AgTe_2Tm$, $AgGdTe_2$, $AgTe_2Y$, $BaSe_3$, $BaTe_3$

- Not to be confused with the other BaS_3 structure, which has space group $P2_12_12$ (#18).

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ba

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	(2a)	Ba
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(2c)	S I
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - z_2\,c\,\hat{\mathbf{z}}$	(2c)	S I
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(4e)	S II
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(4e)	S II
$\mathbf{B_7}$	=	$\left(\frac{1}{2} + x_3\right)\,\mathbf{a_1} - x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(4e)	S II
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - x_3\right)\,\mathbf{a_1} + x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(4e)	S II

References:

- S. Yamaoka, J. T. Lemley, J. M. Jenks, and H. Steinfink, *Structural chemistry of the polysulfides dibarium trisulfide and monobarium trisulfide*, Inorg. Chem. **14**, 129–131 (1975), doi:10.1021/ic50143a027.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1071-1072.

Geometry files:

- CIF: pp. S685
- POSCAR: pp. S685

Stannite (Cu_2FeS_4Sn, $H2_6$) Structure: A2BC4D_tI16_121_d_a_i_b

Prototype	:	Cu_2FeS_4Sn
AFLOW prototype label	:	A2BC4D_tI16_121_d_a_i_b
***Strukturbericht* designation**	:	$H2_6$
Pearson symbol	:	tI16
Space group number	:	121
Space group symbol	:	$I\bar{4}2m$
AFLOW prototype command	:	`aflow --proto=A2BC4D_tI16_121_d_a_i_b` `--params=`$a, c/a, x_4, z_4$

Other compounds with this structure:

- Cu_2CdSe_4Sn, $CoCu_2S_4Sn$, Cu_2GeHgS_4, Cu_2HgS_4Sn, Ag_2FeS_4Sn

- If $c = 2a$, $x = 1/4$, and $z = 3/8$, the atoms are on the sites of the diamond (A4) structure. If, in addition, the Cu, Fe, and Sn atoms are replaced by a single atom type, the crystal reduces to the zincblende (B3) structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Fe
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$+\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2b)$	Sn

$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	Cu
$\mathbf{B_4}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*d*)	Cu
$\mathbf{B_5}$	=	$(x_4 + z_4)\,\mathbf{a_1} + (x_4 + z_4)\,\mathbf{a_2} + 2x_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8*i*)	S
$\mathbf{B_6}$	=	$(z_4 - x_4)\,\mathbf{a_1} + (z_4 - x_4)\,\mathbf{a_2} - 2x_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(8*i*)	S
$\mathbf{B_7}$	=	$-(x_4 + z_4)\,\mathbf{a_1} + (x_4 - z_4)\,\mathbf{a_2}$	=	$x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(8*i*)	S
$\mathbf{B_8}$	=	$(x_4 - z_4)\,\mathbf{a_1} - (x_4 + z_4)\,\mathbf{a_2}$	=	$-x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(8*i*)	S

References:

- L. O. Brockway, *The Crystal Structure of Stannite, Cu_2FeSnS_4*, Zeitschrift für Kristallographie - Crystalline Materials **89**, 434–441 (1934), doi:10.1524/zkri.1934.89.1.434.

Geometry files:

- CIF: pp. S685
- POSCAR: pp. S686

Chalcopyrite ($CuFeS_2$, $E1_1$) Structure: ABC2_tI16_122_a_b_d

Prototype	:	$CuFeS_2$
AFLOW prototype label	:	ABC2_tI16_122_a_b_d
***Strukturbericht* designation**	:	$E1_1$
Pearson symbol	:	tI16
Space group number	:	122
Space group symbol	:	$I\bar{4}2d$
AFLOW prototype command	:	`aflow --proto=ABC2_tI16_122_a_b_d` `--params=`$a, c/a, x_3$

Other compounds with this structure:

- $CuInS_2$, $CuInSe_2$

- When $c = 2a$ and $x_3 = 1/8$ the atoms are on the sites of the diamond (A4) structure. In this case, if we replace the Fe atoms by Cu, we get the zincblende (B3) structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Cu
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Cu
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4b)$	Fe

$\mathbf{B_4}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*b*)	Fe
$\mathbf{B_5}$	=	$\frac{3}{8}\,\mathbf{a_1} + \left(\frac{1}{8} + x_3\right)\mathbf{a_2} + \left(\frac{1}{4} + x_3\right)\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	(8*d*)	S
$\mathbf{B_6}$	=	$\frac{7}{8}\,\mathbf{a_1} + \left(\frac{1}{8} - x_3\right)\mathbf{a_2} + \left(\frac{3}{4} - x_3\right)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	(8*d*)	S
$\mathbf{B_7}$	=	$\left(\frac{7}{8} - x_3\right)\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \left(\frac{1}{4} - x_3\right)\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	(8*d*)	S
$\mathbf{B_8}$	=	$\left(\frac{7}{8} + x_3\right)\mathbf{a_1} + \frac{5}{8}\,\mathbf{a_2} + \left(\frac{3}{4} + x_3\right)\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	(8*d*)	S

References:

- S. R. Hall and J. M. Stewart, *The Crystal Structure Refinement of Chalcopyrite, $CuFeS_2$*, Acta Crystallogr. Sect. B Struct. Sci. **29**, 579–585 (1973), doi:10.1107/S0567740873002943.
- S. C. Abrahams and J. L. Bernstein, *Piezoelectric nonlinear optic CuGaS2 and CuInS2 crystal structure: Sublattice distortion in $A^{I}B^{II}C_2^{VI}$ and $A^{II}B^{IV}C_2^{V}$ type chalcopyrites*, J. Chem. Phys. **59**, 5415–5422 (1973), doi:10.1063/1.1679891.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 2808.

Geometry files:

- CIF: pp. S686
- POSCAR: pp. S686

$HoCoGa_5$ Structure: AB5C_tP7_123_b_ci_a

Prototype	:	$HoCoGa_5$
AFLOW prototype label	:	AB5C_tP7_123_b_ci_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP7
Space group number	:	123
Space group symbol	:	P4/mmm
AFLOW prototype command	:	`aflow --proto=AB5C_tP7_123_b_ci_a --params=`$a, c/a, z_4$

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Ho
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	Co
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(1c)$	Ga I
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(4i)$	Ga II
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + z_4\,c\,\hat{\mathbf{z}}$	$(4i)$	Ga II
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(4i)$	Ga II
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_1} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - z_4\,c\,\hat{\mathbf{z}}$	$(4i)$	Ga II

References:

- Y. Grin, Y. P. Yarmolyuk, and E. I. Gladyshevskii, *Kristallicheskie struktury soedinenij R_2COGa_8 (R = Sm, Gd, Tb, Dy, Ho, Er, Tm, Lu, Y) i RCoGa5 (R = Gd, Tb, Dy, Ho, Er, Tm, Lu, Y)*, Kristallografiya **24**, 242–246 (1979).

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S686
- POSCAR: pp. S687

$CuTi_3$ ($L6_0$) Structure: AB3_tP4_123_a_ce

Prototype	:	$CuTi_3$
AFLOW prototype label	:	AB3_tP4_123_a_ce
***Strukturbericht* designation**	:	$L6_0$
Pearson symbol	:	tP4
Space group number	:	123
Space group symbol	:	P4/mmm
AFLOW prototype command	:	`aflow --proto=AB3_tP4_123_a_ce --params=`$a, c/a$

- This is a tetragonal distortion of the $L1_2$ (Cu_3Au) structure. When $c = a$ the atoms are at the positions of a face-centered cubic lattice. If we replace the Ti I atom by Cu, then the system reduces to the $L1_0$ (CuAu) structure. Interestingly, (Massalski, 1986) lists no stable or metastable structures with composition $CuTi_3$.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cu
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(1c)$	Ti I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2e)$	Ti II
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2e)$	Ti II

References:

- N. Karlsson, *An X-ray study of the phases in the copper-titanium system*, J. Inst. Met. **79**, 391–405 (1951).
- T. B. Massalski, H. Okamoto, P. R. Subramanian, and L. Kacprzak, eds., *Binary Alloy Phase Diagrams* (American Society for Metals, Materials Park, OH, 1990).

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S687
- POSCAR: pp. S687

CuAu ($L1_0$) Structure: AB_tP2_123_a_d

Prototype	:	CuAu
AFLOW prototype label	:	AB_tP2_123_a_d
***Strukturbericht* designation**	:	$L1_0$
Pearson symbol	:	tP2
Space group number	:	123
Space group symbol	:	P4/mmm
AFLOW prototype command	:	`aflow --proto=AB_tP2_123_a_d --params=`$a, c/a$

- When $c = \sqrt{2}a$ the atoms are at the positions of a face-centered cubic lattice. When $c = a$ the atoms are at the positions of a body-centered cubic lattice.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Au
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1d)$	Cu

References:

- P. Bayliss, *Revised Unit-Cell Dimensions, Space Group, and Chemical Formula of Some Metallic Materials*, Can. Mineral. **28**, 751–755 (1990).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:
- CIF: pp. S687
- POSCAR: pp. S688

$CaCuO_2$ Structure: ABC2_tP4_123_d_a_f

Prototype	:	$CaCuO_2$
AFLOW prototype label	:	ABC2_tP4_123_d_a_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP4
Space group number	:	123
Space group symbol	:	P4/mmm
AFLOW prototype command	:	`aflow --proto=ABC2_tP4_123_d_a_f --params=`$a, c/a$

- As noted in (Siegrist, 1988) this is the parent structure of the high-temperature cuprate superconductors.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cu
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1d)$	Ca
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(2f)$	O
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(2f)$	O

References:

- T. Siegrist, S. M. Zahurak, D. W. Murphy, and R. S. Roth, *The parent structure of the layered high-temperature superconductors*, Nature **334**, 231–232 (1988), doi:10.1038/334231a0.

Geometry files:
- CIF: pp. S688
- POSCAR: pp. S688

Si_2U_3 ($D5_a$) Structure: A2B3_tP10_127_g_ah

Prototype	:	Si_2U_3
AFLOW prototype label	:	A2B3_tP10_127_g_ah
***Strukturbericht* designation**	:	$D5_a$
Pearson symbol	:	tP10
Space group number	:	127
Space group symbol	:	P4/mbm
AFLOW prototype command	:	`aflow --proto=A2B3_tP10_127_g_ah` `--params=`$a, c/a, x_2, x_3$

- If we consider the Si_2 dimers as a pseudo-atom, then this is a tetragonal distortion of the Cu_3Au ($L1_2$) structure.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	U I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(2a)$	U I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{y}}$	$(4g)$	Si

$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}}$	(4g)	Si
$\mathbf{B_5}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + x_2\,\mathbf{a_2}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	(4g)	Si
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	(4g)	Si
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}c\,\hat{\mathbf{z}}$	(4h)	U II
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}c\,\hat{\mathbf{z}}$	(4h)	U II
$\mathbf{B_9}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + x_3\,\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + \frac{1}{2}c\,\hat{\mathbf{z}}$	(4h)	U II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} - x_3\,\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + \frac{1}{2}c\,\hat{\mathbf{z}}$	(4h)	U II

References:

- K. Remschnig, T. Le Bihan, H. Noël, and P. Rogl, *Structural chemistry and magnetic behavior of binary uranium silicides*, J. Solid State Chem. **97**, 391–399 (1992), doi:10.1016/0022-4596(92)90048-Z.

Found in:

- P. Villars, K. Cenzual, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, V. Kuprysyuk, I. Savesyuk, and R. Zaremba, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag GmbH, Heidelberg, 2012). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S688
- POSCAR: pp. S689

AsCuSiZr Structure: ABCD_tP8_129_c_b_a_c

Prototype	:	AsCuSiZr
AFLOW prototype label	:	ABCD_tP8_129_c_b_a_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP8
Space group number	:	129
Space group symbol	:	P4/nmm
AFLOW prototype command	:	`aflow --proto=ABCD_tP8_129_c_b_a_c --params=`$a, c/a, z_3, z_4$

Other compounds with this structure:

- LaOFeAs, AsCuHfSi, As_2CuU, Bi_2CuMn, $CoLiSb_2$, $CuGe_2Hf$, $LaMnSb_2$, $NiPrSb_2$

- This is the parent structure for the iron-pnictide superconductors.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	Si
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	Si
$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2b)$	Cu
$\mathbf{B_4}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2b)$	Cu
$\mathbf{B_5}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(2c)$	As

$\mathbf{B_6}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(2c)$	As
$\mathbf{B_7}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(2c)$	Zr
$\mathbf{B_8}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(2c)$	Zr

References:

- V. Johnson and W. Jeitschko, *ZrCuSiAs: A "filled" PbFCl type*, J. Solid State Chem. **11**, 161–166 (1974), doi:10.1016/0022-4596(74)90111-X.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1116.

Geometry files:

- CIF: pp. S689
- POSCAR: pp. S689

β-Np (A_d) Structure: A_tP4_129_ac

Prototype	:	β-Np
AFLOW prototype label	:	A_tP4_129_ac
***Strukturbericht* designation**	:	A_d
Pearson symbol	:	tP4
Space group number	:	129
Space group symbol	:	P4/nmm
AFLOW prototype command	:	`aflow --proto=A_tP4_129_ac --params=`$a, c/a, z_2$

- When $z = 1/2$ the atoms in this structure are in the $L1_0$ (CuAu) or the A6 (indium) structure. This structure is identical to the B10 (PbO) structure. Pearson's Handbook, along with the original papers, give the space group as $P42_1$. However, as noted by Structure Reports 15, 121 (1951), the correct space group is P4/nmm. $P42_1$ is a subgroup of P4/nmm.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	Np I
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	Np I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Np II
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Np II

References:

- W. H. Zachariasen, *Crystal chemical studies of the 5f-series of elements. XVIII. Crystal structure studies of neptunium metal at elevated temperatures*, Acta Cryst. **5**, 664–667 (1952), doi:10.1107/S0365110X52001805.
- A. J. C. Wilson, *Structure Reports Vol. 15: Structure Reports for 1951* (N.V.A. Oosthoek's Uitgevers, Utrecht, 1958).

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 154-156.

Geometry files:

- CIF: pp. S689
- POSCAR: pp. S690

Matlockite ($E0_1$, PbFCl) Structure: ABC_tP6_129_c_a_c

Prototype	:	PbFCl
AFLOW prototype label	:	ABC_tP6_129_c_a_c
***Strukturbericht* designation**	:	$E0_1$
Pearson symbol	:	tP6
Space group number	:	129
Space group symbol	:	P4/nmm
AFLOW prototype command	:	`aflow --proto=ABC_tP6_129_c_a_c --params=`$a, c/a, z_2, z_3$

Other compounds with this structure:

- AcOBr, AmOCl, BaHCl, BiOBr, BiOI, CaHBr, CeOCl, DyOCl, LaOI, NdOCl, NpOS, PbFBr, PrOCl, SmOI, SrHI, ThOTe, UOS, UTe_2, YbOI, others.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	F
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	F
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Cl
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Cl
$\mathbf{B_5}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(2c)$	Pb
$\mathbf{B_6}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(2c)$	Pb

References:

- N. Pasero and N. Perchiazzi, *Crystal structure refinement of matlockite*, Mineral. Mag. **60**, 833–836 (1996).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S690
- POSCAR: pp. S690

Cu_2Sb (C38) Structure: A2B_tP6_129_ac_c

Prototype	:	Cu_2Sb
AFLOW prototype label	:	A2B_tP6_129_ac_c
***Strukturbericht* designation**	:	C38
Pearson symbol	:	tP6
Space group number	:	129
Space group symbol	:	P4/nmm
AFLOW prototype command	:	`aflow --proto=A2B_tP6_129_ac_c` `--params=`$a, c/a, z_2, z_3$

Other compounds with this structure:

- $AsCu_2$, As_2U, $CeSe_2$, $HoSe_2$, GdO_2, $HFSb_2$, Te_2U, S_2Yb, KMgP, AsKMn, AlGeMn, GeNbSb, SnTeU, numerous others

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	Cu I
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	Cu I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Cu II
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Cu II
$\mathbf{B_5}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(2c)$	Sb
$\mathbf{B_6}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(2c)$	Sb

References:

- W. B. Pearson, *The Cu_2Sb and related structures*, Zeitschrift für Kristallographie **171**, 23–39 (1985).

Geometry files:

- CIF: pp. S690
- POSCAR: pp. S691

PbO (B10) Structure: AB_tP4_129_a_c

Prototype	:	PbO
AFLOW prototype label	:	AB_tP4_129_a_c
***Strukturbericht* designation**	:	B10
Pearson symbol	:	tP4
Space group number	:	129
Space group symbol	:	P4/nmm
AFLOW prototype command	:	`aflow --proto=AB_tP4_129_a_c --params=`$a, c/a, z_2$

- When $z = 1/2$ the atoms in this structure are in the $L1_0$ (CuAu) or the A6 (indium) structure. This structure is identical to the A_d (β-Np) structure.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	O
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}}$	$(2a)$	O
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Pb
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Pb

References:

- P. Boher, P. Garnier, J. R. Gavarri, and A. W. Hewat, *Monoxyde quadratique PbOα(I): Description de la transition structurale ferroélastique*, J. Solid State Chem. **57**, 343–350 (1985), doi:10.1016/0022-4596(85)90197-5.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4745.

Geometry files:

- CIF: pp. S691
- POSCAR: pp. S691

γ-CuTi (B11) Structure: AB_tP4_129_c_c

Prototype	:	γ-CuTi
AFLOW prototype label	:	AB_tP4_129_c_c
***Strukturbericht* designation**	:	B11
Pearson symbol	:	tP4
Space group number	:	129
Space group symbol	:	P4/nmm
AFLOW prototype command	:	`aflow --proto=AB_tP4_129_c_c --params=`$a, c/a, z_1, z_2$

Other compounds with this structure:

- AuCu, AlRe, TlF-I (high-temperature)

- When $c = 2a$, $z_1 = 1/8$, and $z_2 = 5/8$, the atoms are on the sites of a body-centered cubic lattice. If, on the other hand, $c = 2\sqrt{2}a$, with the same x_i, the atoms are on the site of a face-centered cubic lattice. This is the phase that Lu et al. refer to as "Z2".

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(2c)$	Cu
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(2c)$	Cu
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Ti
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Ti

References:

- V. N. Eremenko, Y. I. Buyanov, and S. B. Prima, *Phase diagram of the system titanium-copper*, Soviet Powder Metallurgy and Metal Ceramics **5**, 494–502 (1966), doi:10.1007/BF00775543.
- Z. W. Lu., S.-H. Wei, and A. Zunger, *Long-range order in binary late-transition-metal alloys*, Phys. Rev. Lett. **66**, 1753 (1991), doi:10.1103/PhysRevLett.66.1753.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 3021.

Geometry files:

- CIF: pp. S691
- POSCAR: pp. S691

PtS (B17) Structure: AB_tP4_131_c_e

Prototype	:	PtS
AFLOW prototype label	:	AB_tP4_131_c_e
***Strukturbericht* designation**	:	B17
Pearson symbol	:	tP4
Space group number	:	131
Space group symbol	:	$P4_2/mmc$
AFLOW prototype command	:	`aflow --proto=AB_tP4_131_c_e --params=`$a, c/a$

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(2c)$	Pt
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2c)$	Pt
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2e)$	S
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2e)$	S

References:

- F. Grønvold, H. Haraldsen, and A. Kjekshus, *On the Sulfides, Selenides and Tellurides of Platinum*, Acta Chem. Scand. **14**, 1879–1893 (1960), doi:10.3891/acta.chem.scand.14-1879.

Geometry files:
- CIF: pp. S692
- POSCAR: pp. S692

T-50 B (A_g) Structure: A_tP50_134_b2m2n

Prototype	:	B
AFLOW prototype label	:	A_tP50_134_b2m2n
***Strukturbericht* designation**	:	A_g
Pearson symbol	:	tP50
Space group number	:	134
Space group symbol	:	$P4_2/nnm$
AFLOW prototype command	:	`aflow --proto=A_tP50_134_b2m2n` `--params=`$a, c/a, x_2, z_2, x_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5$

- This is apparently the most common form of boron. At least, it's listed first in (Donohue, 1982). Note that the basic building block is a slightly distorted icosahedron. This icosahedron also appears in α-B (R12) and β-B (R105).

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	B I

$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	B I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(8m)$	B II
$\mathbf{B_4}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(8m)$	B II
$\mathbf{B_5}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + x_2\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(8m)$	B II
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)c\,\hat{\mathbf{z}}$	$(8m)$	B II
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	$(8m)$	B II
$\mathbf{B_8}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)c\,\hat{\mathbf{z}}$	$(8m)$	B II
$\mathbf{B_9}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(8m)$	B II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(8m)$	B II
$\mathbf{B_{11}}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(8m)$	B III
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(8m)$	B III
$\mathbf{B_{13}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + x_3\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	$(8m)$	B III
$\mathbf{B_{14}}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	$(8m)$	B III
$\mathbf{B_{15}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} - x_3\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)c\,\hat{\mathbf{z}}$	$(8m)$	B III
$\mathbf{B_{16}}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)c\,\hat{\mathbf{z}}$	$(8m)$	B III
$\mathbf{B_{17}}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(8m)$	B III
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(8m)$	B III
$\mathbf{B_{19}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{21}}$	=	$\left(\frac{1}{2} - y_4\right)\mathbf{a_1} + x_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{22}}$	=	$y_4\,\mathbf{a_1} + \left(\frac{1}{2} - x_4\right)\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{23}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + y_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{24}}$	=	$x_4\,\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{25}}$	=	$y_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2} - y_4\right)\mathbf{a_1} + \left(\frac{1}{2} - x_4\right)\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{27}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{28}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{29}}$	=	$\left(\frac{1}{2} + y_4\right)\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{30}}$	=	$-y_4\,\mathbf{a_1} + \left(\frac{1}{2} + x_4\right)\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{31}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{32}}$	=	$-x_4\,\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{33}}$	=	$-y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{34}}$	=	$\left(\frac{1}{2} + y_4\right)\mathbf{a_1} + \left(\frac{1}{2} + x_4\right)\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(16n)$	B IV
$\mathbf{B_{35}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(16n)$	B V
$\mathbf{B_{36}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + \left(\frac{1}{2} - y_5\right)\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_5\right)a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(16n)$	B V
$\mathbf{B_{37}}$	=	$\left(\frac{1}{2} - y_5\right)\mathbf{a_1} + x_5\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_5\right)a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	$(16n)$	B V

$\mathbf{B_{38}}$	=	$y_5\,\mathbf{a_1} + \left(\frac{1}{2} - x_5\right)\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{39}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + y_5\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{40}}$	=	$x_5\,\mathbf{a_1} + \left(\frac{1}{2} - y_5\right)\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{41}}$	=	$y_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{42}}$	=	$\left(\frac{1}{2} - y_5\right)\mathbf{a_1} + \left(\frac{1}{2} - x_5\right)\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{43}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{44}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} + \left(\frac{1}{2} + y_5\right)\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_5\right)a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{45}}$	=	$\left(\frac{1}{2} + y_5\right)\mathbf{a_1} - x_5\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_5\right)a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{46}}$	=	$-y_5\,\mathbf{a_1} + \left(\frac{1}{2} + x_5\right)\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{47}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} - y_5\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{48}}$	=	$-x_5\,\mathbf{a_1} + \left(\frac{1}{2} + y_5\right)\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{49}}$	=	$-y_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(16n)	B V
$\mathbf{B_{50}}$	=	$\left(\frac{1}{2} + y_5\right)\mathbf{a_1} + \left(\frac{1}{2} + x_5\right)\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(16n)	B V

References:

- J. L. Hoard, R. E. Hughes, and D. E. Sands, *The Structure of Tetragonal Boron*, J. Am. Chem. Soc. **80**, 4507–4515 (1958), doi:10.1021/ja01550a019.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 48-56.

Geometry files:

- CIF: pp. S692
- POSCAR: pp. S692

β-U (A_b) Structure: A_tP30_136_bf2ij

Prototype	:	β-U
AFLOW prototype label	:	A_tP30_136_bf2ij
***Strukturbericht* designation**	:	A_b
Pearson symbol	:	tP30
Space group number	:	136
Space group symbol	:	$P4_2/mnm$
AFLOW prototype command	:	`aflow --proto=A_tP30_136_bf2ij` `--params=`$a, c/a, x_2, x_3, y_3, x_4, y_4, x_5, z_5$

- According to (Donohue, 1982), there are three possible space groups which fit the diffraction data for β-U. This is the highest symmetry space group of the three. Except for a shift of the origin, this structure is crystallographically equivalent to σ-CrFe ($D8_b$).

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}c\,\hat{\mathbf{z}}$	$(2b)$	U I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(2b)$	U I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(4f)$	U II
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(4f)$	U II
$\mathbf{B_5}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	U II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	U II
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}}$	$(8i)$	U III
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}}$	$(8i)$	U III
$\mathbf{B_9}$	=	$\left(\frac{1}{2} - y_3\right)\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	U III
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + y_3\right)\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	U III
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \left(\frac{1}{2} + y_3\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	U III
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \left(\frac{1}{2} - y_3\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	U III
$\mathbf{B_{13}}$	=	$y_3\,\mathbf{a_1} + x_3\,\mathbf{a_2}$	=	$y_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	U III
$\mathbf{B_{14}}$	=	$-y_3\,\mathbf{a_1} - x_3\,\mathbf{a_2}$	=	$-y_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	U III
$\mathbf{B_{15}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}}$	$(8i)$	U IV
$\mathbf{B_{16}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}}$	$(8i)$	U IV
$\mathbf{B_{17}}$	=	$\left(\frac{1}{2} - y_4\right)\mathbf{a_1} + \left(\frac{1}{2} + x_4\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	U IV
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} + y_4\right)\mathbf{a_1} + \left(\frac{1}{2} - x_4\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	U IV
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	U IV
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	U IV
$\mathbf{B_{21}}$	=	$y_4\,\mathbf{a_1} + x_4\,\mathbf{a_2}$	=	$y_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}}$	$(8i)$	U IV
$\mathbf{B_{22}}$	=	$-y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2}$	=	$-y_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}}$	$(8i)$	U IV
$\mathbf{B_{23}}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(8j)$	U V
$\mathbf{B_{24}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(8j)$	U V
$\mathbf{B_{25}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + \left(\frac{1}{2} + x_5\right)\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	$(8j)$	U V
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} + \left(\frac{1}{2} - x_5\right)\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	$(8j)$	U V
$\mathbf{B_{27}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + \left(\frac{1}{2} + x_5\right)\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	$(8j)$	U V
$\mathbf{B_{28}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} + \left(\frac{1}{2} - x_5\right)\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	$(8j)$	U V
$\mathbf{B_{29}}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(8j)$	U V
$\mathbf{B_{30}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(8j)$	U V

References:

- C. W. Tucker, Jr., and P. Senio, *An improved determination of the crystal structure of β-uranium*, Acta Cryst. **6**, 753–760

(1953), doi:10.1107/S0365110X53002167.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 134-147.

Geometry files:

- CIF: pp. S693
- POSCAR: pp. S693

β-BeO Structure: AB_tP8_136_g_f

Prototype	:	β-BeO
AFLOW prototype label	:	AB_tP8_136_g_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP8
Space group number	:	136
Space group symbol	:	$P4_2/mnm$
AFLOW prototype command	:	`aflow --proto=AB_tP8_136_g_f` `--params=`$a, c/a, x_1, x_2$

Other compounds with this structure:

- ZnO

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}}$	$(4f)$	O
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}}$	$(4f)$	O
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	O
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	O
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(4g)$	Be

$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	(4g)	Be
$\mathbf{B_7}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(4g)	Be
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(4g)	Be

References:

- D. K. Smith, C. F. Cline, and S. B. Austerman, *The Crystal Structure of β-Beryllia*, Acta Cryst. **18**, 393–397 (1965), doi:10.1107/S0365110X65000877.

Geometry files:

- CIF: pp. S693
- POSCAR: pp. S694

Rutile (TiO_2, C4) Structure: A2B_tP6_136_f_a

Prototype	:	TiO_2
AFLOW prototype label	:	A2B_tP6_136_f_a
***Strukturbericht* designation**	:	C4
Pearson symbol	:	tP6
Space group number	:	136
Space group symbol	:	$P4_2/mnm$
AFLOW prototype command	:	`aflow --proto=A2B_tP6_136_f_a` `--params=`$a, c/a, x_2$

Other compounds with this structure:

- CoF_2, MgF_2, MnF_2, NiF_2, ZnF_2, GeO_2, IrO_2, MoO_2, PbO_2, SiO_2 (stishovite), SnO_2 (cassiterite), TaO_2, WO_2

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ti
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	Ti
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(4f)$	O
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(4f)$	O
$\mathbf{B_5}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	O
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	O

References:

- R. Jeffrey Swope, J. R. Smyth, and A. C. Larson, *H in rutile-type compounds: I. Single-crystal neutron and X-ray diffraction study of H in rutile*, Am. Mineral. **80**, 448–453 (1995).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S694
- POSCAR: pp. S694

σ-CrFe (D8$_b$) Structure: sigma_tP30_136_bf2ij

Prototype	:	σ-CrFe
AFLOW prototype label	:	sigma_tP30_136_bf2ij
***Strukturbericht* designation**	:	D8$_b$
Pearson symbol	:	tP30
Space group number	:	136
Space group symbol	:	P4$_2$/mnm
AFLOW prototype command	:	`aflow --proto=sigma_tP30_136_bf2ij` `--params=`$a, c/a, x_2, x_3, y_3, x_4, y_4, x_5, z_5$

Other compounds with this structure:

- Al_3CoNb_6, $AlCrNb_3$, Co_2Mo_3, Ta_3V_7, $PdTa_3$, $IrMo_2$, IrW_3, many others.

- The atoms in this lattice are completely disordered, that is, the Cr and Fe atoms are distributed randomly on the sites in the unit cell. This seems to be the case for all of the compounds listed below. We have chosen several of the atoms near Fe and Cr in the periodic table to color the above pictures. Except for a shift of the origin, this structure is crystallographically equivalent to β-U (A$_b$).

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}c\,\hat{\mathbf{z}}$	$(2b)$	M I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(2b)$	M I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(4f)$	M II
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(4f)$	M II
$\mathbf{B_5}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	M II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	M II
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}}$	$(8i)$	M III
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2}$	=	$-x_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}}$	$(8i)$	M III
$\mathbf{B_9}$	=	$\left(\frac{1}{2} - y_3\right)\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	M III
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + y_3\right)\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	M III
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \left(\frac{1}{2} + y_3\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	M III
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \left(\frac{1}{2} - y_3\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	M III
$\mathbf{B_{13}}$	=	$y_3\,\mathbf{a_1} + x_3\,\mathbf{a_2}$	=	$y_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	M III
$\mathbf{B_{14}}$	=	$-y_3\,\mathbf{a_1} - x_3\,\mathbf{a_2}$	=	$-y_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	M III
$\mathbf{B_{15}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}}$	$(8i)$	M IV
$\mathbf{B_{16}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}}$	$(8i)$	M IV
$\mathbf{B_{17}}$	=	$\left(\frac{1}{2} - y_4\right)\mathbf{a_1} + \left(\frac{1}{2} + x_4\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	M IV
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} + y_4\right)\mathbf{a_1} + \left(\frac{1}{2} - x_4\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	M IV
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2} - x_4\right)\mathbf{a_1} + \left(\frac{1}{2} + y_4\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	M IV
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} + x_4\right)\mathbf{a_1} + \left(\frac{1}{2} - y_4\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8i)$	M IV
$\mathbf{B_{21}}$	=	$y_4\,\mathbf{a_1} + x_4\,\mathbf{a_2}$	=	$y_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}}$	$(8i)$	M IV
$\mathbf{B_{22}}$	=	$-y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2}$	=	$-y_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}}$	$(8i)$	M IV
$\mathbf{B_{23}}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(8j)$	M V
$\mathbf{B_{24}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(8j)$	M V
$\mathbf{B_{25}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + \left(\frac{1}{2} + x_5\right)\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	$(8j)$	M V
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} + \left(\frac{1}{2} - x_5\right)\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	$(8j)$	M V
$\mathbf{B_{27}}$	=	$\left(\frac{1}{2} - x_5\right)\mathbf{a_1} + \left(\frac{1}{2} + x_5\right)\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	$(8j)$	M V
$\mathbf{B_{28}}$	=	$\left(\frac{1}{2} + x_5\right)\mathbf{a_1} + \left(\frac{1}{2} - x_5\right)\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_5\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_5\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	$(8j)$	M V
$\mathbf{B_{29}}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(8j)$	M V
$\mathbf{B_{30}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(8j)$	M V

References:

- H. L. Yakel, *Atom distributions in sigma phases. I. Fe and Cr atom distributions in a binary sigma phase equilibrated at*

1063, 1013 and 923 K, Acta Crystallogr. Sect. B Struct. Sci. **B39**, 20–28 (1983), doi:10.1107/S0108768183001974.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 2639.

Geometry files:

- CIF: pp. S694
- POSCAR: pp. S695

γ-N Structure: A_tP4_136_f

Prototype	:	γ-N
AFLOW prototype label	:	A_tP4_136_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	tP4
Space group number	:	136
Space group symbol	:	$P4_2/mnm$
AFLOW prototype command	:	`aflow --proto=A_tP4_136_f --params=`$a, c/a, x_1$

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}}$	$(4f)$	N
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}}$	$(4f)$	N
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	N
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(4f)$	N

References:

- R. L. Mills and A. F. Schuch, *Crystal Structure of Gamma Nitrogen*, Phys. Rev. Lett. **23**, 1154–1156 (1969), doi:10.1103/PhysRevLett.23.1154.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 207-208.

Geometry files:
- CIF: pp. S695
- POSCAR: pp. S695

Cl (A18) Structure: A_tP16_138_j

Prototype	:	Cl
AFLOW prototype label	:	A_tP16_138_j
***Strukturbericht* designation**	:	A18
Pearson symbol	:	tP16
Space group number	:	138
Space group symbol	:	$P4_2/ncm$
AFLOW prototype command	:	`aflow --proto=A_tP16_138_j` `--params=`$a, c/a, x_1, y_1, z_1$

- As given, this structure has a Cl-Cl bond distance of 1.82Å, far too small for chlorine. The structure was eventually reanalyzed, and found to be similar to molecular iodine (A14). See (Donohue, 1982, pp. 396) for details. We retain this structure for its historical interest. Note that all atoms are on the general sites of space group $P4_2/ncm$.

Simple Tetragonal primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + y_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + y_1\,a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right)a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - y_1\right)\mathbf{a_1} + x_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_1\right)a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_4}$	=	$y_1\,\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$y_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_5}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} - y_1\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} - y_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_7}$	=	$\left(\frac{1}{2} + y_1\right)\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_8}$	=	$-y_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-y_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_9}$	=	$-x_1\,\mathbf{a_1} - y_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - y_1\,a\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} + y_1\right)\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_1\right)a\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2} + y_1\right)\mathbf{a_1} - x_1\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_1\right)a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_{12}}$	=	$-y_1\,\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\mathbf{a_3}$	=	$-y_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_{13}}$	=	$x_1\,\mathbf{a_1} + \left(\frac{1}{2} - y_1\right)\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_1\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + y_1\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} + y_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_{15}}$	=	$\left(\frac{1}{2} - y_1\right)\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(16j)$	Cl
$\mathbf{B_{16}}$	=	$y_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$y_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(16j)$	Cl

References:

- W. H. Keesom and K. W. Taconis, *On the crystal structure of chlorine*, Physica **3**, 237–242 (1936), doi:10.1016/S0031-8914(36)80226-2.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 396.

Geometry files:

- CIF: pp. S695
- POSCAR: pp. S696

Al_3Zr ($D0_{23}$) Structure: A3B_tI16_139_cde_e

Prototype	:	Al_3Zr
AFLOW prototype label	:	A3B_tI16_139_cde_e
***Strukturbericht* designation**	:	$D0_{23}$
Pearson symbol	:	tI16
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A3B_tI16_139_cde_e` `--params=`$a, c/a, z_3, z_4$

- When $c = 4a$, $z_3 = 3/8$, and $z_4 = 1/8$ the atoms are on the sites of a face-centered cubic lattice. This phase can also be described as a set of alternating $L1_2$ and $D0_{22}$ lattices.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(4c)$	Al I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(4c)$	Al I
$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	Al II
$\mathbf{B_4}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	Al II
$\mathbf{B_5}$	=	$z_3\,\mathbf{a_1} + z_3\,\mathbf{a_2}$	=	$+z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	Al III
$\mathbf{B_6}$	=	$-z_3\,\mathbf{a_1} - z_3\,\mathbf{a_2}$	=	$-z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	Al III
$\mathbf{B_7}$	=	$z_4\,\mathbf{a_1} + z_4\,\mathbf{a_2}$	=	$+z_4\,c\,\hat{\mathbf{z}}$	$(4e)$	Zr
$\mathbf{B_8}$	=	$-z_4\,\mathbf{a_1} - z_4\,\mathbf{a_2}$	=	$-z_4\,c\,\hat{\mathbf{z}}$	$(4e)$	Zr

References:

- Y. Ma, C. Rømming, B. Lebech, J. Gjønnes, and J. Taftø, *Structure Refinement of Al_3Zr using Single-Crystal X-ray Diffraction, Powder Neutron Diffraction and CBED*, Acta Crystallogr. Sect. B Struct. Sci. **B48**, 11–16 (1992), doi:10.1107/S0108768191010467.

Found in:

- G. Ghosh and M. Asta, *First-principles calculation of structural energetics of Al-TM (TM = Ti, Zr, Hf) intermetallics*, Acta Mater. **53**, 3225–3252 (2005), doi:10.1016/j.actamat.2005.03.028.

Geometry files:

- CIF: pp. S696
- POSCAR: pp. S696

Hypothetical BCT5 Si Structure: A_tI4_139_e

Prototype	:	Si
AFLOW prototype label	:	A_tI4_139_e
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI4
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A_tI4_139_e` `--params=`$a, c/a, z_1$

- The bct5 structure is a tetragonal analog of the diamond (A4) structure, with 5-fold coordination. It was proposed in (Boyer, 1991) as a low energy, metastable phase of silicon, based on first-principles calculations and model potentials. To the best of our knowledge, this has not been observed experimentally. A search of Pearson's Handbook does not show any compound with this structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_1} + z_1\,\mathbf{a_2}$	=	$+z_1\,c\,\hat{\mathbf{z}}$	$(4e)$	Si
$\mathbf{B_2}$	=	$-z_1\,\mathbf{a_1} - z_1\,\mathbf{a_2}$	=	$-z_1\,c\,\hat{\mathbf{z}}$	$(4e)$	Si

References:

- L. L. Boyer, E. Kaxiras, J. L. Feldman, J. Q. Broughton, and M. J. Mehl, *New low-energy crystal structure for silicon*, Phys. Rev. Lett. **67**, 715–718 (1991), doi:10.1103/PhysRevLett.67.715.

Geometry files:

- CIF: pp. S696
- POSCAR: pp. S697

0201 [$(La,Ba)_2CuO_4$] High-T_c Structure: AB2C4_tI14_139_a_e_ce

Prototype	:	$(La,Ba)_2CuO_4$
AFLOW prototype label	:	AB2C4_tI14_139_a_e_ce
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI14
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=AB2C4_tI14_139_a_e_ce` `--params=`$a, c/a, z_3, z_4$

- The original "high"-temperature (30K) superconductor found by Bednorz and Mueller. Barium and lanthanum atoms are distributed randomly on the lanthanum sublattice. The ground state structure of the parent compound, La_2CuO_4, is an orthorhombic distortion of this unit cell.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Cu
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(4c)$	O I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(4c)$	O I
$\mathbf{B_4}$	=	$z_3\,\mathbf{a_1} + z_3\,\mathbf{a_2}$	=	$z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	La/Ba
$\mathbf{B_5}$	=	$-z_3\,\mathbf{a_1} - z_3\,\mathbf{a_2}$	=	$-z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	La/Ba
$\mathbf{B_6}$	=	$z_4\,\mathbf{a_1} + z_4\,\mathbf{a_2}$	=	$z_4\,c\,\hat{\mathbf{z}}$	$(4e)$	O II
$\mathbf{B_7}$	=	$-z_4\,\mathbf{a_1} - z_4\,\mathbf{a_2}$	=	$-z_4\,c\,\hat{\mathbf{z}}$	$(4e)$	O II

References:

- J. D. Jorgensen, H.-B. Schüttler, D. G. Hinks, D. W. Capone, II, K. Zhang, M. B. Brodsky, and D. J. Scalapino, *Lattice instability and high-T_c superconductivity in $La_{2-x}Ba_xCuO_4$*, Phys. Rev. Lett. **58**, 1024–1029 (1987), doi:10.1103/PhysRevLett.58.1024.

Found in:

- H. Shaked, P. M. Keane, J. C. Rodrigues, F. F. Owen, R. L. Hitterman, and J. D. Jorgensen, *Crystal Structures of the High-T_c Superconducting Copper-Oxides* (Elsevier Science B. V., Amsterdam, 1994).

Geometry files:

- CIF: pp. S697
- POSCAR: pp. S697

$Mn_{12}Th$ ($D2_b$) Structure: A12B_tI26_139_fij_a

Prototype	:	$Mn_{12}Th$
AFLOW prototype label	:	A12B_tI26_139_fij_a
***Strukturbericht* designation**	:	$D2_b$
Pearson symbol	:	tI26
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A12B_tI26_139_fij_a` `--params=`$a, c/a, x_3, x_4$

Other compounds with this structure:

- $AgBe_{12}$, Al_8Cr_4Er, Fe_4Mn_8, Fe_7Mn_5, others.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Th

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(8f)$	Mn I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(8f)$	Mn I
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(8f)$	Mn I
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(8f)$	Mn I
$\mathbf{B_6}$	=	$x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}$	$(8i)$	Mn II
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}$	$(8i)$	Mn II
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	Mn II
$\mathbf{B_9}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	Mn II
$\mathbf{B_{10}}$	=	$\frac{1}{2}\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \left(\frac{1}{2} + x_4\right)\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(8j)$	Mn III
$\mathbf{B_{11}}$	=	$\frac{1}{2}\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{1}{2} - x_4\right)\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(8j)$	Mn III
$\mathbf{B_{12}}$	=	$x_4\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \left(\frac{1}{2} + x_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}}$	$(8j)$	Mn III
$\mathbf{B_{13}}$	=	$-x_4\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \left(\frac{1}{2} - x_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}}$	$(8j)$	Mn III

References:

- J. V. Florio, R. E. Rundle, and A. I. Snow, *Compounds of thorium with transition metals. I. The thorium-manganese system*, Acta Cryst. **5**, 449–457 (1952), doi:10.1107/S0365110X52001337.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4396.

Geometry files:

- CIF: pp. S697
- POSCAR: pp. S698

In (A6) Structure: A_tI2_139_a

Prototype	:	In
AFLOW prototype label	:	A_tI2_139_a
***Strukturbericht* designation**	:	A6
Pearson symbol	:	tI2
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A_tI2_139_a` `--params=`$a, c/a$

- This is an example of a "face"-centered tetragonal (fct) lattice, a distortion of the fcc lattice. Note that this structure is actually a body-centered tetragonal lattice, since in the tetragonal system there is no distinction between face- and body-centered structures. In the A6 structure, c/a is near the fcc ratio of $\sqrt{2}$, while in the A_a structure, c/a is near the bcc ratio of 1. Note that In (pp. S286) and α-Pa (pp. S302) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	In

References:

- V. T. Deshpande and R. R. Pawar, *Anisotropic Thermal Expansion of Indium*, Acta Crystallogr. Sect. A **25**, 415–416 (1969), doi:10.1107/S0567739469000830.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 244-246.

Geometry files:

- CIF: pp. S698
- POSCAR: pp. S699

Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h

Prototype	:	C
AFLOW prototype label	:	A_tI8_139_h
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI8
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A_tI8_139_h --params=`$a, c/a, x_1$

- This structure was proposed in (Schultz, 1999) to show that it was energetically possible to form four-member rings in amorphous sp^3 carbon structures.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + 2x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}}$	$(8h)$	C
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - 2x_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}}$	$(8h)$	C
$\mathbf{B_3}$	=	$x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}}$	$(8h)$	C
$\mathbf{B_4}$	=	$-x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}}$	$(8h)$	C

References:

- P. A. Schultz, K. Leung, and E. B. Stechel, *Small rings and amorphous tetrahedral carbon*, Phys. Rev. B **59**, 733–741 (1999), doi:10.1103/PhysRevB.59.733.

Geometry files:

- CIF: pp. S699
- POSCAR: pp. S699

Al_3Ti ($D0_{22}$) Structure: A3B_tI8_139_bd_a

Prototype	:	Al_3Ti
AFLOW prototype label	:	A3B_tI8_139_bd_a
***Strukturbericht* designation**	:	$D0_{22}$
Pearson symbol	:	tI8
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A3B_tI8_139_bd_a` `--params=`$a, c/a$

- When $c = 2a$ the atoms are on the sites of a face-centered cubic lattice. When $c/a = 1/\sqrt{2}$, this becomes the cubic $D0_3$ structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ti
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2b)$	Al I
$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	Al II
$\mathbf{B_4}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	Al II

References:

- J. P. Nic, S. Zhang, and D. E. Mikkola, *Observations on the systematic alloying of Al_3Ti with fourth period elements to*

yield cubic phases, Scripta Metallurgica et Materialia **24**, 1099–1104 (1990), doi:10.1016/0956-716X(90)90306-2.
- P. Norby and A. N. Christensen, *Preparation and Structure of Al_3Ti*, Acta Chem. Scand. **A40**, 157–159 (1986), doi:10.3891/acta.chem.scand.40a-0157.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1023.

Geometry files:
- CIF: pp. S699
- POSCAR: pp. S700

$MoSi_2$ ($C11_b$) Structure: AB2_tI6_139_a_e

Prototype	:	$MoSi_2$
AFLOW prototype label	:	AB2_tI6_139_a_e
***Strukturbericht* designation**	:	$C11_b$
Pearson symbol	:	tI6
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=AB2_tI6_139_a_e` `--params=`$a, c/a, z_2$

Other compounds with this structure:

- CaC_2, $CdTi_2$

- When $c = 3a$ and $z_2 = 1/3$ the atoms are on the sites of a body-centered cubic lattice. For $MoSi_2$ itself, (Harada, 1998) gives $c/a = 2.45$ and $z_2 = 0.3353$. Other compounds in this structure have very different values of c/a and even z_2.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Mo
$\mathbf{B_2}$	=	$z_2\,\mathbf{a_1} + z_2\,\mathbf{a_2}$	=	$z_2\,c\,\hat{\mathbf{z}}$	$(4e)$	Si
$\mathbf{B_3}$	=	$-z_2\,\mathbf{a_1} - z_2\,\mathbf{a_2}$	=	$-z_2\,c\,\hat{\mathbf{z}}$	$(4e)$	Si

References:

- Y. Harada, M. Morinaga, D. Saso, M. Takata, and M. Sakata, *Refinement of crystal structure in $MoSi_2$*, Intermetallics **6**, 523–527 (1998), doi:10.1016/S0966-9795(97)00102-7.

Geometry files:
- CIF: pp. S700
- POSCAR: pp. S700

V_4Zn_5 Structure: A4B5_tI18_139_i_ah

Prototype	:	V_4Zn_5
AFLOW prototype label	:	A4B5_tI18_139_i_ah
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI18
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A4B5_tI18_139_i_ah --params=`$a, c/a, x_2, x_3$

Other compounds with this structure:

- Pt_8Ti

- This is very similar to the Pt_8Ti structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Zn I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + 2x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Zn II
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - 2x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Zn II
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Zn II
$\mathbf{B_5}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Zn II
$\mathbf{B_6}$	=	$x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}$	$(8i)$	V
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}$	$(8i)$	V
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	V
$\mathbf{B_9}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	V

References:

- K. Schubert, H. G. Meissner, A. Raman, and W. Rossteutscher, *Einige Strukturdaten metallischer Phasen (9)*, Naturwissenschaften **51**, 287 (1964).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 5154.

Geometry files:

- CIF: pp. S700
- POSCAR: pp. S701

Al_4Ba ($D1_3$) Structure: A4B_tI10_139_de_a

Prototype	:	Al_4Ba
AFLOW prototype label	:	A4B_tI10_139_de_a
***Strukturbericht* designation**	:	$D1_3$
Pearson symbol	:	tI10
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A4B_tI10_139_de_a` `--params=`$a, c/a, z_3$

Other compounds with this structure:

- $ThCu_2Si_2$, $ThCr_2Si_2$, $BaFe_2As_2$, KFe_2As_2, hundreds more

- Removing the Al-I atoms transforms this to the $MoSi_2$ ($C11_b$) structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	($2a$)	Ba
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	($4d$)	Al I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	($4d$)	Al I
$\mathbf{B_4}$	=	$z_3\,\mathbf{a_1} + z_3\,\mathbf{a_2}$	=	$z_3\,c\,\hat{\mathbf{z}}$	($4e$)	Al II
$\mathbf{B_5}$	=	$-z_3\,\mathbf{a_1} - z_3\,\mathbf{a_2}$	=	$-z_3\,c\,\hat{\mathbf{z}}$	($4e$)	Al II

References:

- K. R. Andress and E. Alberti, *Röntgenographische Untersuchung der Legierungsreihe Aluminium-Barium*, Z. Metallkd. **27**, 126–128 (1935).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 670.

Geometry files:

- CIF: pp. S701
- POSCAR: pp. S701

Pt_8Ti Structure: A8B_tI18_139_hi_a

Prototype	:	Pt_8Ti
AFLOW prototype label	:	A8B_tI18_139_hi_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI18
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A8B_tI18_139_hi_a --params=`$a, c/a, x_2, x_3$

Other compounds with this structure:

- $NbNi_8$

- $a = 3/\left(\sqrt{2}\right)a_{fcc}$, $c = a_{fcc}$, $x_2 = 1/3$, and $x_3 = 1/3$, the atoms are on the sites of the fcc lattice. The pictures here are drawn with these parameters, with a_{fcc} appropriate for nickel. Compare this to the very similar V_4Zn_5 structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ti
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + 2x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Pt I
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - 2x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Pt I
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Pt I
$\mathbf{B_5}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Pt I
$\mathbf{B_6}$	=	$x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}$	$(8i)$	Pt II
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}$	$(8i)$	Pt II
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	Pt II
$\mathbf{B_9}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{y}}$	$(8i)$	Pt II

References:

- P. Pietrokowsky, *Novel Ordered Phase, Pt_8Ti*, Nature **206**, 291 (1965), doi:10.1038/206291a0.
- R. H. Taylor, S. Curtarolo, and G. L. W. Hart, *Predictions of the Pt_8Ti phase in unexpected systems*, J. Am. Chem. Soc. **132**, 6851–6854 (2010), doi:10.1021/ja101890k.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 5011.

Geometry files:

- CIF: pp. S701
- POSCAR: pp. S702

ThH_2 (L'2) Structure: A2B_tI6_139_d_a

Prototype	:	ThH_2
AFLOW prototype label	:	A2B_tI6_139_d_a
***Strukturbericht* designation**	:	L'2
Pearson symbol	:	tI6
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A2B_tI6_139_d_a --params=`$a, c/a$

Other compounds with this structure:

- $SiPt_2$, TiH_2, ZrH_2

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Th
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	H
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4d)$	H

References:

- R. E. Rundle, C. G. Shull, and E. O. Wollan, *The crystal structure of thorium and zirconium dihydrides by X-ray and neutron diffraction*, Acta Cryst. **5**, 22–26 (1952), doi:10.1107/S0365110X52000071.

Geometry files:
- CIF: pp. S702
- POSCAR: pp. S702

α-Pa (A_a) Structure: A_tI2_139_a

Prototype	:	α-Pa
AFLOW prototype label	:	A_tI2_139_a
***Strukturbericht* designation**	:	A_a
Pearson symbol	:	tI2
Space group number	:	139
Space group symbol	:	I4/mmm
AFLOW prototype command	:	`aflow --proto=A_tI2_139_a` `--params=`$a, c/a$

- This is an example of a body-centered tetragonal (bct) lattice, a distortion of the bcc lattice. Note that In (pp. S286) and α-Pa (pp. S302) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files. In the A6 structure, c/a is near the fcc ratio of $\sqrt{2}$, while in the A_a structure, c/a is near the bcc ratio of 1. When $c/a = \sqrt{2/3} \approx 0.816$ the coordination number of this system is 10. In Pa the c/a ratio is 0.827.

Body-centered Tetragonal primitive vectors:

$$\begin{aligned}
\mathbf{a}_1 &= -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}} \\
\mathbf{a}_2 &= \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}} \\
\mathbf{a}_3 &= \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}
\end{aligned}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Pa

References:

- W. H. Zachariasen, *On the crystal structure of protactinium metal*, Acta Cryst. **12**, 698–700 (1959), doi:10.1107/S0365110X59002043.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 125-127.

Geometry files:

- CIF: pp. S702
- POSCAR: pp. S703

Khatyrkite (Al_2Cu, C16) Structure: A2B_tI12_140_h_a

Prototype	:	Al_2Cu
AFLOW prototype label	:	A2B_tI12_140_h_a
***Strukturbericht* designation**	:	C16
Pearson symbol	:	tI12
Space group number	:	140
Space group symbol	:	I4/mcm
AFLOW prototype command	:	`aflow --proto=A2B_tI12_140_h_a` `--params=`$a, c/a, x_2$

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Cu
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(4a)$	Cu
$\mathbf{B_3}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + x_2\,\mathbf{a_2} + \left(\frac{1}{2} + 2x_2\right)\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}}$	$(8h)$	Al
$\mathbf{B_4}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{1}{2} - 2x_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{y}}$	$(8h)$	Al
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Al
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(8h)$	Al

References:

- J. B. Friauf, *The Crystal Structures of Two Intermetallic Compounds*, J. Am. Chem. Soc. **49**, 3107–3114 (1927), doi:10.1021/ja01411a017.

Geometry files:

- CIF: pp. S703
- POSCAR: pp. S703

SiU_3 ($D0_c$) Structure: AB3_tI16_140_b_ah

Prototype	:	SiU_3
AFLOW prototype label	:	AB3_tI16_140_b_ah
***Strukturbericht* designation**	:	$D0_c$
Pearson symbol	:	tI16
Space group number	:	140
Space group symbol	:	I4/mcm
AFLOW prototype command	:	`aflow --proto=AB3_tI16_140_b_ah` `--params=`$a, c/a, x_3$

Other compounds with this structure:

- $AlPt_3$, $GaPt_3$, Pt_3Si, $GePt_3$, Ir_3Si

- When $c = \sqrt{2}a$ and $x_3 = 1/4$ the atoms are at the positions of the Cu_3Au ($L1_2$) structure. Many references define both a $D0_c$ and a $D0'_3$ (Ir_3Si) structure. The primary difference seems to be positioning the Si atoms on the (2a) or (2b) sites. Since this is merely an origin shift we will ignore the $D0'_3$ structure.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}a\,\hat{\mathbf{x}} - \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} - \tfrac{1}{2}c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\mathbf{a_1} + \frac{1}{4}\mathbf{a_2}$	=	$\frac{1}{4}c\,\hat{\mathbf{z}}$	($4a$)	U I

$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	(4*a*)	U I
$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*b*)	Si
$\mathbf{B_4}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*b*)	Si
$\mathbf{B_5}$	=	$\left(\frac{1}{2} + x_3\right)\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \left(\frac{1}{2} + 2x_3\right)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)\,a\,\hat{\mathbf{y}}$	(8*h*)	U II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_3\right)\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \left(\frac{1}{2} - 2x_3\right)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{y}}$	(8*h*)	U II
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}}$	(8*h*)	U II
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}}$	(8*h*)	U II

References:

- W. H. Zachariasen, *Crystal chemical studies of the 5f-series of elements. VIII. Crystal structure studies of uranium silicides and of $CeSi_2$, $NpSi_2$, and $PuSi_2$*, Acta Cryst. **2**, 94–99 (1949), doi:10.1107/S0365110X49000217.

Geometry files:

- CIF: pp. S703
- POSCAR: pp. S704

SeTl (B37) Structure: AB_tI16_140_ab_h

Prototype	:	SeTl
AFLOW prototype label	:	AB_tI16_140_ab_h
***Strukturbericht* designation**	:	B37
Pearson symbol	:	tI16
Space group number	:	140
Space group symbol	:	I4/mcm
AFLOW prototype command	:	`aflow --proto=AB_tI16_140_ab_h --params=`$a, c/a, x_3$

Other compounds with this structure:

- $AlKTe_2$, $AlNaSe_2$, $AlNaTe_2$, $GaNaTe_2$, $InKTe_2$, InS_2Te, $InNaTe_2$, $GaTe_2Tl$

- When $c = a$ and $x = 1/4$ the atoms are at the positions of the body-centered cubic (A2) lattice.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*a*)	Se I
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	(4*a*)	Se I
$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*b*)	Se II
$\mathbf{B_4}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(4*b*)	Se II
$\mathbf{B_5}$	=	$\left(\frac{1}{2} + x_3\right)\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \left(\frac{1}{2} + 2x_3\right)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)\,a\,\hat{\mathbf{y}}$	(8*h*)	Tl
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_3\right)\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \left(\frac{1}{2} - 2x_3\right)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{y}}$	(8*h*)	Tl
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}}$	(8*h*)	Tl
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}}$	(8*h*)	Tl

References:

- R. R. Yadav, R. P. Ram, and S. Bhan, *On the Thallium-Selenium-Tellurium System*, Z. Metallkd. **67**, 173–177 (1976).

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S704
- POSCAR: pp. S704

Zircon ($ZrSiO_4$) Structure: A4BC_tI24_141_h_b_a

Prototype	:	$ZrSiO_4$
AFLOW prototype label	:	A4BC_tI24_141_h_b_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI24
Space group number	:	141
Space group symbol	:	$I4_1/amd$
AFLOW prototype command	:	`aflow --proto=A4BC_tI24_141_h_b_a` `--params=`$a, c/a, y_3, z_3$

- We have filed this under quartz and related structures since the Si atoms have the same type of Si-O bonding.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Zr
$\mathbf{B_2}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Zr
$\mathbf{B_3}$	=	$\frac{5}{8}\,\mathbf{a_1} + \frac{3}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(4b)$	Si
$\mathbf{B_4}$	=	$\frac{3}{8}\,\mathbf{a_1} + \frac{5}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(4b)$	Si

$\mathbf{B_5}$	=	$(y_3 + z_3)\ \mathbf{a_1} + z_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(16h)	O
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - y_3 + z_3\right)\ \mathbf{a_1} + z_3\,\mathbf{a_2} + \left(\frac{1}{2} - y_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{2} - y_3\right)\ a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(16h)	O
$\mathbf{B_7}$	=	$z_3\,\mathbf{a_1} + \left(\frac{1}{2} - y_3 + z_3\right)\ \mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_3\right)\ a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right)\ c\,\hat{\mathbf{z}}$	(16h)	O
$\mathbf{B_8}$	=	$z_3\,\mathbf{a_1} + (y_3 + z_3)\ \mathbf{a_2} + \left(\frac{1}{2} + y_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{4} + y_3\right)\ a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_3\right)\ c\,\hat{\mathbf{z}}$	(16h)	O
$\mathbf{B_9}$	=	$\left(\frac{1}{2} + y_3 - z_3\right)\ \mathbf{a_1} - z_3\,\mathbf{a_2} + \left(\frac{1}{2} + y_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{2} + y_3\right)\ a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(16h)	O
$\mathbf{B_{10}}$	=	$-(y_3 + z_3)\ \mathbf{a_1} - z_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(16h)	O
$\mathbf{B_{11}}$	=	$-z_3\,\mathbf{a_1} + \left(\frac{1}{2} + y_3 - z_3\right)\ \mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_3\right)\ a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_3\right)\ c\,\hat{\mathbf{z}}$	(16h)	O
$\mathbf{B_{12}}$	=	$-z_3\,\mathbf{a_1} - (y_3 + z_3)\ \mathbf{a_2} + \left(\frac{1}{2} - y_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{4} - y_3\right)\ a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_3\right)\ c\,\hat{\mathbf{z}}$	(16h)	O

References:

- R. M. Hazen and L. W. Finger, *Crystal structure and compressibility of zircon at high pressure*, Am. Mineral. **64**, 196–201 (1979).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S705
- POSCAR: pp. S705

β-Sn (A5) Structure: A_tI4_141_a

Prototype	:	β-Sn
AFLOW prototype label	:	A_tI4_141_a
***Strukturbericht* designation**	:	A5
Pearson symbol	:	tI4
Space group number	:	141
Space group symbol	:	$I4_1/amd$
AFLOW prototype command	:	`aflow --proto=A_tI4_141_a --params=`$a, c/a$

- When $c/a = \sqrt{2}$ this structure is equivalent to diamond (A4).

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Sn
$\mathbf{B_2}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Sn

References:

- V. T. Deshpande and D. B. Sirdeshmukh, *Thermal Expansion of Tetragonal Tin*, Acta Cryst. **14**, 355–356 (1961), doi:10.1107/S0365110X61001212.

Found in:

- M. Winter, *WebElements: the periodic table on the WWW* (1993-2015). The University of Sheffield and WebElements Ltd.

Geometry files:

- CIF: pp. S705
- POSCAR: pp. S706

Hausmannite (Mn_3O_4) Structure: A3B4_tI28_141_ad_h

Prototype	:	Mn_3O_4
AFLOW prototype label	:	A3B4_tI28_141_ad_h
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI28
Space group number	:	141
Space group symbol	:	$I4_1/amd$
AFLOW prototype command	:	`aflow --proto=A3B4_tI28_141_ad_h` `--params=`$a, c/a, y_3, z_3$

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Mn I
$\mathbf{B_2}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Mn I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(8d)$	Mn II
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(8d)$	Mn II
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(8d)$	Mn II
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(8d)$	Mn II
$\mathbf{B_7}$	=	$(y_3 + z_3)\,\mathbf{a_1} + z_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(16h)$	O

$\mathbf{B_8}$	=	$\left(\frac{1}{2}-y_3+z_3\right)\mathbf{a_1}+z_3\,\mathbf{a_2}+\left(\frac{1}{2}-y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(16*h*)	O
$\mathbf{B_9}$	=	$z_3\,\mathbf{a_1}+\left(\frac{1}{2}-y_3+z_3\right)\mathbf{a_2}-y_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{x}}+\frac{3}{4}a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+z_3\right)c\,\hat{\mathbf{z}}$	(16*h*)	O
$\mathbf{B_{10}}$	=	$z_3\,\mathbf{a_1}+(y_3+z_3)\,\mathbf{a_2}+\left(\frac{1}{2}+y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{x}}+\frac{1}{4}a\,\hat{\mathbf{y}}+\left(\frac{3}{4}+z_3\right)c\,\hat{\mathbf{z}}$	(16*h*)	O
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2}+y_3-z_3\right)\mathbf{a_1}-z_3\,\mathbf{a_2}+\left(\frac{1}{2}+y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(16*h*)	O
$\mathbf{B_{12}}$	=	$-(y_3+z_3)\,\mathbf{a_1}-z_3\,\mathbf{a_2}-y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(16*h*)	O
$\mathbf{B_{13}}$	=	$-z_3\,\mathbf{a_1}+\left(\frac{1}{2}+y_3-z_3\right)\mathbf{a_2}+y_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{x}}+\frac{3}{4}a\,\hat{\mathbf{y}}+\left(\frac{1}{4}-z_3\right)c\,\hat{\mathbf{z}}$	(16*h*)	O
$\mathbf{B_{14}}$	=	$-z_3\,\mathbf{a_1}-(y_3+z_3)\,\mathbf{a_2}+\left(\frac{1}{2}-y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{x}}+\frac{1}{4}a\,\hat{\mathbf{y}}+\left(\frac{3}{4}-z_3\right)c\,\hat{\mathbf{z}}$	(16*h*)	O

References:

- D. Jarosch, *Crystal structure refinement and reflectance measurements of hausmannite, Mn_3O_4*, Mineral. Petrol. **37**, 15–23 (1987), doi:10.1007/BF01163155.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4374.

Geometry files:

- CIF: pp. S706
- POSCAR: pp. S706

Anatase (TiO_2, C5) Structure: A2B_tI12_141_e_a

Prototype	:	TiO_2
AFLOW prototype label	:	A2B_tI12_141_e_a
***Strukturbericht* designation**	:	C5
Pearson symbol	:	tI12
Space group number	:	141
Space group symbol	:	$I4_1/amd$
AFLOW prototype command	:	`aflow --proto=A2B_tI12_141_e_a` `--params=`$a, c/a, z_2$

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Ti
$\mathbf{B_2}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Ti
$\mathbf{B_3}$	=	$\left(\frac{1}{4} + z_2\right)\mathbf{a_1} + z_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(8e)$	O
$\mathbf{B_4}$	=	$z_2\,\mathbf{a_1} + \left(\frac{1}{4} + z_2\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_2\right)c\,\hat{\mathbf{z}}$	$(8e)$	O
$\mathbf{B_5}$	=	$\left(\frac{3}{4} - z_2\right)\mathbf{a_1} - z_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(8e)$	O
$\mathbf{B_6}$	=	$-z_2\,\mathbf{a_1} + \left(\frac{3}{4} - z_2\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_2\right)c\,\hat{\mathbf{z}}$	$(8e)$	O

References:

- C. J. Howard, T. M. Sabine, and F. Dickson, *Structural and thermal parameters for rutile and anatase*, Acta Crystallogr. Sect. B Struct. Sci. **47**, 462–468 (1991), doi:10.1107/S010876819100335X.

Geometry files:

- CIF: pp. S706
- POSCAR: pp. S707

MoB (B_g) Structure: AB_tI16_141_e_e

Prototype	:	MoB
AFLOW prototype label	:	AB_tI16_141_e_e
***Strukturbericht* designation**	:	B_g
Pearson symbol	:	tI16
Space group number	:	141
Space group symbol	:	$I4_1/amd$
AFLOW prototype command	:	`aflow --proto=AB_tI16_141_e_e` `--params=`$a, c/a, z_1, z_2$

Other compounds with this structure:

- BCr, GaZr, $B_5Re_3V_2$, $Co_3Er_5Ni_2$, Ga_3Hf_2Sc

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\left(\frac{1}{4}+z_1\right)\mathbf{a_1} + z_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(8e)$	B
$\mathbf{B_2}$	=	$z_1\,\mathbf{a_1} + \left(\frac{1}{4}+z_1\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4}+z_1\right)c\,\hat{\mathbf{z}}$	$(8e)$	B
$\mathbf{B_3}$	=	$\left(\frac{3}{4}-z_1\right)\mathbf{a_1} - z_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(8e)$	B
$\mathbf{B_4}$	=	$-z_1\,\mathbf{a_1} + \left(\frac{3}{4}-z_1\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4}-z_1\right)c\,\hat{\mathbf{z}}$	$(8e)$	B
$\mathbf{B_5}$	=	$\left(\frac{1}{4}+z_2\right)\mathbf{a_1} + z_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(8e)$	Mo
$\mathbf{B_6}$	=	$z_2\,\mathbf{a_1} + \left(\frac{1}{4}+z_2\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4}+z_2\right)c\,\hat{\mathbf{z}}$	$(8e)$	Mo
$\mathbf{B_7}$	=	$\left(\frac{3}{4}-z_2\right)\mathbf{a_1} - z_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(8e)$	Mo
$\mathbf{B_8}$	=	$-z_2\,\mathbf{a_1} + \left(\frac{3}{4}-z_2\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4}-z_2\right)c\,\hat{\mathbf{z}}$	$(8e)$	Mo

References:

- R. Kiessling, *The Crystal Structure of Molybdenum and Tungsten Borides*, Acta Chem. Scand. **1**, 893–916 (1947), doi:10.3891/acta.chem.scand.01-0893.

Geometry files:
- CIF: pp. S707
- POSCAR: pp. S707

Ga_2Hf Structure: A2B_tI24_141_2e_e

Prototype	:	Ga_2Hf
AFLOW prototype label	:	A2B_tI24_141_2e_e
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI24
Space group number	:	141
Space group symbol	:	$I4_1/amd$
AFLOW prototype command	:	`aflow --proto=A2B_tI24_141_2e_e` `--params=`$a, c/a, z_1, z_2, z_3$

Other compounds with this structure:

- Al_2Mg, Al_2Ti, Ga_2Ti, In_2Zr, Pb_2Pr, Pb_2Pu, $PuSn_2$

- When $z_1 = 1/4$, $z_2 = 5/12$, and $z_3 = 1/12$, the atoms are on the sites of the indium (A6) lattice. If, in this case, $c = 6a$, the atoms are on the sites of a face-centered cubic lattice, and if $c = a/\sqrt{2}$, the atoms are on the site of a body-centered cubic lattice. This lattice is placed with the face-centered cubic lattices because most known structures have c near $6a$.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\left(\frac{1}{4}+z_1\right)\mathbf{a_1} + z_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(8e)$	Ga I
$\mathbf{B_2}$	=	$z_1\,\mathbf{a_1} + \left(\frac{1}{4}+z_1\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4}+z_1\right)c\,\hat{\mathbf{z}}$	$(8e)$	Ga I
$\mathbf{B_3}$	=	$\left(\frac{3}{4}-z_1\right)\mathbf{a_1} - z_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(8e)$	Ga I
$\mathbf{B_4}$	=	$-z_1\,\mathbf{a_1} + \left(\frac{3}{4}-z_1\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4}-z_1\right)c\,\hat{\mathbf{z}}$	$(8e)$	Ga I
$\mathbf{B_5}$	=	$\left(\frac{1}{4}+z_2\right)\mathbf{a_1} + z_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(8e)$	Ga II
$\mathbf{B_6}$	=	$z_2\,\mathbf{a_1} + \left(\frac{1}{4}+z_2\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4}+z_2\right)c\,\hat{\mathbf{z}}$	$(8e)$	Ga II
$\mathbf{B_7}$	=	$\left(\frac{3}{4}-z_2\right)\mathbf{a_1} - z_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(8e)$	Ga II
$\mathbf{B_8}$	=	$-z_2\,\mathbf{a_1} + \left(\frac{3}{4}-z_2\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4}-z_2\right)c\,\hat{\mathbf{z}}$	$(8e)$	Ga II

$\mathbf{B_9}$	=	$\left(\frac{1}{4}+z_3\right)\mathbf{a_1}+z_3\,\mathbf{a_2}+\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	(8*e*)	Hf
$\mathbf{B_{10}}$	=	$z_3\,\mathbf{a_1}+\left(\frac{1}{4}+z_3\right)\mathbf{a_2}+\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}+\frac{1}{4}\,a\,\hat{\mathbf{y}}+\left(\frac{3}{4}+z_3\right)c\,\hat{\mathbf{z}}$	(8*e*)	Hf
$\mathbf{B_{11}}$	=	$\left(\frac{3}{4}-z_3\right)\mathbf{a_1}-z_3\,\mathbf{a_2}+\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}}-z_3\,c\,\hat{\mathbf{z}}$	(8*e*)	Hf
$\mathbf{B_{12}}$	=	$-z_3\,\mathbf{a_1}+\left(\frac{3}{4}-z_3\right)\mathbf{a_2}+\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}+\frac{3}{4}\,a\,\hat{\mathbf{y}}+\left(\frac{1}{4}-z_3\right)c\,\hat{\mathbf{z}}$	(8*e*)	Hf

References:

- K. Schubert, H. G. Meissner, M. Pötzschke, W. Rossteutscher, and E. Stolz, *Einige Strukturdaten metallischer Phasen (7)*, Naturwissenschaften **49**, 57 (1962).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 3436.

Geometry files:

- CIF: pp. S707
- POSCAR: pp. S708

NbP ("40") Structure: AB_tI8_141_a_b

Prototype	:	NbP
AFLOW prototype label	:	AB_tI8_141_a_b
***Strukturbericht* designation**	:	"40"
Pearson symbol	:	tI8
Space group number	:	141
Space group symbol	:	$I4_1/amd$
AFLOW prototype command	:	`aflow --proto=AB_tI8_141_a_b` `--params=`$a, c/a$

- When $c/a = 2$, the atoms in this lattice are on the sites of the face-centered cubic lattice. Thus (Lu, 1991) use this lattice for their structural stability studies, and arbitrarily assign this lattice a Strukturbericht designation of "40". Note that (Schönberg, 1954) gives the space group as $I4_122$, but as (Villars, 1991) notes, the coordinates given increase the symmetry to $I4_1/amd$

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Nb
$\mathbf{B_2}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(4a)$	Nb
$\mathbf{B_3}$	=	$\frac{5}{8}\,\mathbf{a_1} + \frac{3}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(4b)$	P
$\mathbf{B_4}$	=	$\frac{3}{8}\,\mathbf{a_1} + \frac{5}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(4b)$	P

References:

- N. Schönberg, *An X-Ray Investigation of Transition Metal Phosphides*, Acta Chem. Scand. **8**, 226–239 (1954),

doi:10.3891/acta.chem.scand.08-0226.
- Z. W. Lu., S.-H. Wei, and A. Zunger, *Long-range order in binary late-transition-metal alloys*, Phys. Rev. Lett. **66**, 1753 (1991), doi:10.1103/PhysRevLett.66.1753.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4511.

Geometry files:
- CIF: pp. S708
- POSCAR: pp. S708

β-In_2S_3 Crystal Structure: A2B3_tI80_141_ceh_3h

Prototype	:	β-In_2S_3
AFLOW prototype label	:	A2B3_tI80_141_ceh_3h
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI80
Space group number	:	141
Space group symbol	:	$I4_1/amd$
AFLOW prototype command	:	`aflow --proto=A2B3_tI80_141_ceh_3h` `--params=`$a, c/a, z_2, y_3, z_3, y_4, z_4, y_5, z_5, y_6, z_6$

- This is a spinel structure with ordered defects.

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(8c)$	In I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(8c)$	In I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(8c)$	In I
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(8c)$	In I
$\mathbf{B_5}$	=	$\left(\frac{1}{4} + z_2\right)\mathbf{a_1} + z_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(8e)$	In II
$\mathbf{B_6}$	=	$z_2\,\mathbf{a_1} + \left(\frac{1}{4} + z_2\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_2\right)c\,\hat{\mathbf{z}}$	$(8e)$	In II
$\mathbf{B_7}$	=	$\left(\frac{3}{4} - z_2\right)\mathbf{a_1} - z_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(8e)$	In II
$\mathbf{B_8}$	=	$-z_2\,\mathbf{a_1} + \left(\frac{3}{4} - z_2\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_2\right)c\,\hat{\mathbf{z}}$	$(8e)$	In II
$\mathbf{B_9}$	=	$(y_3 + z_3)\,\mathbf{a_1} + z_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(16h)$	In III
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - y_3 + z_3\right)\mathbf{a_1} + z_3\,\mathbf{a_2} + \left(\frac{1}{2} - y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_3\right)a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(16h)$	In III

$\mathbf{B_{11}}$	=	$z_3\,\mathbf{a_1} + \left(\frac{1}{2} - y_3 + z_3\right)\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_3\right) a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right) c\,\hat{\mathbf{z}}$	(16h)	In III
$\mathbf{B_{12}}$	=	$z_3\,\mathbf{a_1} + (y_3 + z_3)\,\mathbf{a_2} + \left(\frac{1}{2} + y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_3\right) a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_3\right) c\,\hat{\mathbf{z}}$	(16h)	In III
$\mathbf{B_{13}}$	=	$\left(\frac{1}{2} + y_3 - z_3\right)\mathbf{a_1} - z_3\,\mathbf{a_2} + \left(\frac{1}{2} + y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_3\right) a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(16h)	In III
$\mathbf{B_{14}}$	=	$-(y_3 + z_3)\,\mathbf{a_1} - z_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(16h)	In III
$\mathbf{B_{15}}$	=	$-z_3\,\mathbf{a_1} + \left(\frac{1}{2} + y_3 - z_3\right)\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_3\right) a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_3\right) c\,\hat{\mathbf{z}}$	(16h)	In III
$\mathbf{B_{16}}$	=	$-z_3\,\mathbf{a_1} - (y_3 + z_3)\,\mathbf{a_2} + \left(\frac{1}{2} - y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_3\right) a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_3\right) c\,\hat{\mathbf{z}}$	(16h)	In III
$\mathbf{B_{17}}$	=	$(y_4 + z_4)\,\mathbf{a_1} + z_4\,\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(16h)	S I
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} - y_4 + z_4\right)\mathbf{a_1} + z_4\,\mathbf{a_2} + \left(\frac{1}{2} - y_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_4\right) a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(16h)	S I
$\mathbf{B_{19}}$	=	$z_4\,\mathbf{a_1} + \left(\frac{1}{2} - y_4 + z_4\right)\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_4\right) a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right) c\,\hat{\mathbf{z}}$	(16h)	S I
$\mathbf{B_{20}}$	=	$z_4\,\mathbf{a_1} + (y_4 + z_4)\,\mathbf{a_2} + \left(\frac{1}{2} + y_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_4\right) a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_4\right) c\,\hat{\mathbf{z}}$	(16h)	S I
$\mathbf{B_{21}}$	=	$\left(\frac{1}{2} + y_4 - z_4\right)\mathbf{a_1} - z_4\,\mathbf{a_2} + \left(\frac{1}{2} + y_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_4\right) a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(16h)	S I
$\mathbf{B_{22}}$	=	$-(y_4 + z_4)\,\mathbf{a_1} - z_4\,\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(16h)	S I
$\mathbf{B_{23}}$	=	$-z_4\,\mathbf{a_1} + \left(\frac{1}{2} + y_4 - z_4\right)\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_4\right) a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_4\right) c\,\hat{\mathbf{z}}$	(16h)	S I
$\mathbf{B_{24}}$	=	$-z_4\,\mathbf{a_1} - (y_4 + z_4)\,\mathbf{a_2} + \left(\frac{1}{2} - y_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_4\right) a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_4\right) c\,\hat{\mathbf{z}}$	(16h)	S I
$\mathbf{B_{25}}$	=	$(y_5 + z_5)\,\mathbf{a_1} + z_5\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(16h)	S II
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2} - y_5 + z_5\right)\mathbf{a_1} + z_5\,\mathbf{a_2} + \left(\frac{1}{2} - y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_5\right) a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(16h)	S II
$\mathbf{B_{27}}$	=	$z_5\,\mathbf{a_1} + \left(\frac{1}{2} - y_5 + z_5\right)\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_5\right) a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_5\right) c\,\hat{\mathbf{z}}$	(16h)	S II
$\mathbf{B_{28}}$	=	$z_5\,\mathbf{a_1} + (y_5 + z_5)\,\mathbf{a_2} + \left(\frac{1}{2} + y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_5\right) a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_5\right) c\,\hat{\mathbf{z}}$	(16h)	S II
$\mathbf{B_{29}}$	=	$\left(\frac{1}{2} + y_5 - z_5\right)\mathbf{a_1} - z_5\,\mathbf{a_2} + \left(\frac{1}{2} + y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_5\right) a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(16h)	S II
$\mathbf{B_{30}}$	=	$-(y_5 + z_5)\,\mathbf{a_1} - z_5\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(16h)	S II
$\mathbf{B_{31}}$	=	$-z_5\,\mathbf{a_1} + \left(\frac{1}{2} + y_5 - z_5\right)\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_5\right) a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_5\right) c\,\hat{\mathbf{z}}$	(16h)	S II
$\mathbf{B_{32}}$	=	$-z_5\,\mathbf{a_1} - (y_5 + z_5)\,\mathbf{a_2} + \left(\frac{1}{2} - y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_5\right) a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_5\right) c\,\hat{\mathbf{z}}$	(16h)	S II
$\mathbf{B_{33}}$	=	$(y_6 + z_6)\,\mathbf{a_1} + z_6\,\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	(16h)	S III
$\mathbf{B_{34}}$	=	$\left(\frac{1}{2} - y_6 + z_6\right)\mathbf{a_1} + z_6\,\mathbf{a_2} + \left(\frac{1}{2} - y_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - y_6\right) a\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	(16h)	S III
$\mathbf{B_{35}}$	=	$z_6\,\mathbf{a_1} + \left(\frac{1}{2} - y_6 + z_6\right)\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_6\right) a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_6\right) c\,\hat{\mathbf{z}}$	(16h)	S III
$\mathbf{B_{36}}$	=	$z_6\,\mathbf{a_1} + (y_6 + z_6)\,\mathbf{a_2} + \left(\frac{1}{2} + y_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_6\right) a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_6\right) c\,\hat{\mathbf{z}}$	(16h)	S III
$\mathbf{B_{37}}$	=	$\left(\frac{1}{2} + y_6 - z_6\right)\mathbf{a_1} - z_6\,\mathbf{a_2} + \left(\frac{1}{2} + y_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + y_6\right) a\,\hat{\mathbf{y}} - z_6\,c\,\hat{\mathbf{z}}$	(16h)	S III
$\mathbf{B_{38}}$	=	$-(y_6 + z_6)\,\mathbf{a_1} - z_6\,\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{y}} - z_6\,c\,\hat{\mathbf{z}}$	(16h)	S III
$\mathbf{B_{39}}$	=	$-z_6\,\mathbf{a_1} + \left(\frac{1}{2} + y_6 - z_6\right)\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_6\right) a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_6\right) c\,\hat{\mathbf{z}}$	(16h)	S III
$\mathbf{B_{40}}$	=	$-z_6\,\mathbf{a_1} - (y_6 + z_6)\,\mathbf{a_2} + \left(\frac{1}{2} - y_6\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_6\right) a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_6\right) c\,\hat{\mathbf{z}}$	(16h)	S III

References:

- N. S. Rampersadh, A. M. Venter, and D. G. Billing, *Rietveld refinement of In_2S_3 using neutron and X-ray powder diffraction data*, Physica B **350**, e383–e385 (2004), doi:10.1016/j.physb.2004.03.102.

Geometry files:

- CIF: pp. S708
- POSCAR: pp. S709

$PPrS_4$ Structure: ABC4_tI96_142_e_ab_2g

Prototype	:	$PPrS_4$
AFLOW prototype label	:	ABC4_tI96_142_e_ab_2g
***Strukturbericht* designation**	:	None
Pearson symbol	:	tI96
Space group number	:	142
Space group symbol	:	$I4_1/acd$
AFLOW prototype command	:	`aflow --proto=ABC4_tI96_142_e_ab_2g` `--params=`$a, c/a, x_3, x_4, y_4, z_4, x_5, y_5, z_5$

Body-centered Tetragonal primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{5}{8}\,\mathbf{a_1} + \frac{3}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(8a)$	Pr I
$\mathbf{B_2}$	=	$\frac{3}{8}\,\mathbf{a_1} + \frac{5}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(8a)$	Pr I
$\mathbf{B_3}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(8a)$	Pr I
$\mathbf{B_4}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(8a)$	Pr I
$\mathbf{B_5}$	=	$\frac{3}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,c\,\hat{\mathbf{z}}$	$(8b)$	Pr II
$\mathbf{B_6}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{3}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{7}{8}\,c\,\hat{\mathbf{z}}$	$(8b)$	Pr II
$\mathbf{B_7}$	=	$\frac{5}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,c\,\hat{\mathbf{z}}$	$(8b)$	Pr II
$\mathbf{B_8}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{5}{8}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{5}{8}\,c\,\hat{\mathbf{z}}$	$(8b)$	Pr II

$\mathbf{B_9}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(\frac{1}{4} + x_3\right)\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(16e)	P
$\mathbf{B_{10}}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{1}{4} - x_3\right)\,\mathbf{a_2} + \left(\frac{1}{2} - x_3\right)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(16e)	P
$\mathbf{B_{11}}$	=	$\left(\frac{1}{4} + x_3\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{3}{4} + x_3\right)\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(16e)	P
$\mathbf{B_{12}}$	=	$\left(\frac{1}{4} - x_3\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - x_3\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}}$	(16e)	P
$\mathbf{B_{13}}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{3}{4} - x_3\right)\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(16e)	P
$\mathbf{B_{14}}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(\frac{3}{4} + x_3\right)\,\mathbf{a_2} + \left(\frac{1}{2} + x_3\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(16e)	P
$\mathbf{B_{15}}$	=	$\left(\frac{3}{4} - x_3\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(16e)	P
$\mathbf{B_{16}}$	=	$\left(\frac{3}{4} + x_3\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + x_3\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(16e)	P
$\mathbf{B_{17}}$	=	$(y_4 + z_4)\,\mathbf{a_1} + (x_4 + z_4)\,\mathbf{a_2} + (x_4 + y_4)\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} - y_4 + z_4\right)\,\mathbf{a_1} + (z_4 - x_4)\,\mathbf{a_2} + \left(\frac{1}{2} - x_4 - y_4\right)\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_4\right)\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{19}}$	=	$(x_4 + z_4)\,\mathbf{a_1} + \left(\frac{1}{2} - y_4 + z_4\right)\,\mathbf{a_2} + (x_4 - y_4)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_4\right)\,a\,\hat{\mathbf{x}} + \left(\frac{3}{4} + x_4\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{20}}$	=	$(z_4 - x_4)\,\mathbf{a_1} + (y_4 + z_4)\,\mathbf{a_2} + \left(\frac{1}{2} - x_4 + y_4\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_4\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_4\right)\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{21}}$	=	$(y_4 - z_4)\,\mathbf{a_1} + \left(\frac{1}{2} - x_4 - z_4\right)\,\mathbf{a_2} + \left(\frac{1}{2} - x_4 + y_4\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_4\right)\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{22}}$	=	$\left(\frac{1}{2} - y_4 - z_4\right)\,\mathbf{a_1} + \left(\frac{1}{2} + x_4 - z_4\right)\,\mathbf{a_2} + (x_4 - y_4)\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{23}}$	=	$\left(\frac{1}{2} + x_4 - z_4\right)\,\mathbf{a_1} + (y_4 - z_4)\,\mathbf{a_2} + (x_4 + y_4)\,\mathbf{a_3}$	=	$\left(\frac{3}{4} + y_4\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_4\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2} - x_4 - z_4\right)\,\mathbf{a_1} + \left(\frac{1}{2} - y_4 - z_4\right)\,\mathbf{a_2} + \left(\frac{1}{2} - x_4 - y_4\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_4\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_4\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{25}}$	=	$-(y_4 + z_4)\,\mathbf{a_1} - (x_4 + z_4)\,\mathbf{a_2} - (x_4 + y_4)\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2} + y_4 - z_4\right)\,\mathbf{a_1} + (x_4 - z_4)\,\mathbf{a_2} + \left(\frac{1}{2} + x_4 + y_4\right)\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_4\right)\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{27}}$	=	$-(x_4 + z_4)\,\mathbf{a_1} + \left(\frac{1}{2} + y_4 - z_4\right)\,\mathbf{a_2} + (y_4 - x_4)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_4\right)\,a\,\hat{\mathbf{x}} + \left(\frac{3}{4} - x_4\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{28}}$	=	$(x_4 - z_4)\,\mathbf{a_1} - (y_4 + z_4)\,\mathbf{a_2} + \left(\frac{1}{2} + x_4 - y_4\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - y_4\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_4\right)\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{29}}$	=	$(z_4 - y_4)\,\mathbf{a_1} + \left(\frac{1}{2} + x_4 + z_4\right)\,\mathbf{a_2} + \left(\frac{1}{2} + x_4 - y_4\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_4\right)\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{30}}$	=	$\left(\frac{1}{2} + y_4 + z_4\right)\,\mathbf{a_1} + \left(\frac{1}{2} - x_4 + z_4\right)\,\mathbf{a_2} + (y_4 - x_4)\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{31}}$	=	$\left(\frac{1}{2} - x_4 + z_4\right)\,\mathbf{a_1} + (z_4 - y_4)\,\mathbf{a_2} - (x_4 + y_4)\,\mathbf{a_3}$	=	$\left(\frac{3}{4} - y_4\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_4\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I
$\mathbf{B_{32}}$	=	$\left(\frac{1}{2} + x_4 + z_4\right)\,\mathbf{a_1} + \left(\frac{1}{2} + y_4 + z_4\right)\,\mathbf{a_2} + \left(\frac{1}{2} + x_4 + y_4\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + y_4\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_4\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_4\right)\,c\,\hat{\mathbf{z}}$	(32g)	S I

$\mathbf{B_{33}}$	=	$(y_5+z_5)\,\mathbf{a_1}+(x_5+z_5)\,\mathbf{a_2}+(x_5+y_5)\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}}+y_5\,a\,\hat{\mathbf{y}}+z_5\,c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{34}}$	=	$\left(\frac{1}{2}-y_5+z_5\right)\mathbf{a_1}+(z_5-x_5)\,\mathbf{a_2}+\left(\frac{1}{2}-x_5-y_5\right)\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_5\right)a\,\hat{\mathbf{y}}+z_5\,c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{35}}$	=	$(x_5+z_5)\,\mathbf{a_1}+\left(\frac{1}{2}-y_5+z_5\right)\mathbf{a_2}+(x_5-y_5)\,\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_5\right)a\,\hat{\mathbf{x}}+\left(\frac{3}{4}+x_5\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{36}}$	=	$(z_5-x_5)\,\mathbf{a_1}+(y_5+z_5)\,\mathbf{a_2}+\left(\frac{1}{2}-x_5+y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_5\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-x_5\right)a\,\hat{\mathbf{y}}+\left(\frac{3}{4}+z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{37}}$	=	$(y_5-z_5)\,\mathbf{a_1}+\left(\frac{1}{2}-x_5-z_5\right)\mathbf{a_2}+\left(\frac{1}{2}-x_5+y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_5\right)a\,\hat{\mathbf{x}}+y_5\,a\,\hat{\mathbf{y}}-z_5\,c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{38}}$	=	$\left(\frac{1}{2}-y_5-z_5\right)\mathbf{a_1}+\left(\frac{1}{2}+x_5-z_5\right)\mathbf{a_2}+(x_5-y_5)\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}}-y_5\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{39}}$	=	$\left(\frac{1}{2}+x_5-z_5\right)\mathbf{a_1}+(y_5-z_5)\,\mathbf{a_2}+(x_5+y_5)\,\mathbf{a_3}$	=	$\left(\frac{3}{4}+y_5\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}+x_5\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}-z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{40}}$	=	$\left(\frac{1}{2}-x_5-z_5\right)\mathbf{a_1}+\left(\frac{1}{2}-y_5-z_5\right)\mathbf{a_2}+\left(\frac{1}{2}-x_5-y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_5\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-x_5\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}-z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{41}}$	=	$-(y_5+z_5)\,\mathbf{a_1}-(x_5+z_5)\,\mathbf{a_2}-(x_5+y_5)\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}}-y_5\,a\,\hat{\mathbf{y}}-z_5\,c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{42}}$	=	$\left(\frac{1}{2}+y_5-z_5\right)\mathbf{a_1}+(x_5-z_5)\,\mathbf{a_2}+\left(\frac{1}{2}+x_5+y_5\right)\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_5\right)a\,\hat{\mathbf{y}}-z_5\,c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{43}}$	=	$-(x_5+z_5)\,\mathbf{a_1}+\left(\frac{1}{2}+y_5-z_5\right)\mathbf{a_2}+(y_5-x_5)\,\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_5\right)a\,\hat{\mathbf{x}}+\left(\frac{3}{4}-x_5\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}-z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{44}}$	=	$(x_5-z_5)\,\mathbf{a_1}-(y_5+z_5)\,\mathbf{a_2}+\left(\frac{1}{2}+x_5-y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_5\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}+x_5\right)a\,\hat{\mathbf{y}}+\left(\frac{3}{4}-z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{45}}$	=	$(z_5-y_5)\,\mathbf{a_1}+\left(\frac{1}{2}+x_5+z_5\right)\mathbf{a_2}+\left(\frac{1}{2}+x_5-y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_5\right)a\,\hat{\mathbf{x}}-y_5\,a\,\hat{\mathbf{y}}+z_5\,c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{46}}$	=	$\left(\frac{1}{2}+y_5+z_5\right)\mathbf{a_1}+\left(\frac{1}{2}-x_5+z_5\right)\mathbf{a_2}+(y_5-x_5)\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}}+y_5\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{47}}$	=	$\left(\frac{1}{2}-x_5+z_5\right)\mathbf{a_1}+(z_5-y_5)\,\mathbf{a_2}-(x_5+y_5)\,\mathbf{a_3}$	=	$\left(\frac{3}{4}-y_5\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-x_5\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II
$\mathbf{B_{48}}$	=	$\left(\frac{1}{2}+x_5+z_5\right)\mathbf{a_1}+\left(\frac{1}{2}+y_5+z_5\right)\mathbf{a_2}+\left(\frac{1}{2}+x_5+y_5\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_5\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}+x_5\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+z_5\right)c\,\hat{\mathbf{z}}$	(32g)	S II

References:
- C. Wibbelmann, W. Brockner, B. Eisenmann, and H. Schäfer, *Kristallstruktur und Schwingungsspektrum des Praseodym-ortho-Thiophosphates $PrPS_4$*, Z. Naturforsch. **39 a**, 190–194 (1983).

Found in:
- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S709
- POSCAR: pp. S710

ζ-AgZn (B_b) Structure: A2B_hP9_147_g_ad

Prototype	:	ζ-AgZn
AFLOW prototype label	:	A2B_hP9_147_g_ad
***Strukturbericht* designation**	:	B_b
Pearson symbol	:	hP9
Space group number	:	147
Space group symbol	:	$P\bar{3}$
AFLOW prototype command	:	`aflow --proto=A2B_hP9_147_g_ad` `--params=`$a, c/a, z_2, x_3, y_3, z_3$

Other compounds with this structure:

- $Ag_{10}CdZn_9$, $Ag_{50}MgZn_{49}$

- When $z_2 = 0$, $x_3 = 1/3$, $y_3 = 0$, and $z_3 = 1/2$, this structure becomes the hexagonal omega (C32) structure. This is an alloy phase. The (1a) and (2d) sites are pure Zn, but the (6g) site is a mixture of Ag and Zn, so we designate it as "M". If the system is stoichiometric then M = ($Ag_{4.5}$,$Zn_{1.5}$).

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Zn
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2d)$	Zn
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2d)$	Zn
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 + y_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_3 - x_3)\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(6g)$	M
$\mathbf{B_5}$	=	$-y_3\,\mathbf{a_1} + (x_3 - y_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - 2y_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(6g)$	M
$\mathbf{B_6}$	=	$(y_3 - x_3)\,\mathbf{a_1} - x_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_3 - 2x_3)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(6g)$	M
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_3 + y_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(x_3 - y_3)\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(6g)$	M
$\mathbf{B_8}$	=	$y_3\,\mathbf{a_1} + (y_3 - x_3)\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_3 - x_3)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(6g)$	M
$\mathbf{B_9}$	=	$(x_3 - y_3)\,\mathbf{a_1} + x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_3 - y_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,y_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(6g)$	M

References:

- G. Bergman and R. W. Jaross, *On the Crystal Structure of the ζ Phase in the Silver-Zinc System and the Mechanism of the β − ζ Transformation*, Acta Cryst. **8**, 232–235 (1955), doi:10.1107/S0365110X55000765.

Geometry files:

- CIF: pp. S710
- POSCAR: pp. S710

Solid Cubane (C_8H_8) Structure: AB_hR16_148_cf_cf

Prototype	:	C_8H_8
AFLOW prototype label	:	AB_hR16_148_cf_cf
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR16
Space group number	:	148
Space group symbol	:	$R\bar{3}$
AFLOW prototype command	:	`aflow --proto=AB_hR16_148_cf_cf [--hex]` `--params=`$a, c/a, x_1, x_2, x_3, y_3, z_3, x_4, y_4, z_4$

- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	C I
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	C I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	H I
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	H I
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - z_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_3 - z_3 - x_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	C II
$\mathbf{B_6}$	=	$z_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_3 - y_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_3 - y_3 - z_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	C II
$\mathbf{B_7}$	=	$y_3\,\mathbf{a_1} + z_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_3 - x_3 - y_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	C II
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_3 + x_3 - 2y_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	C II
$\mathbf{B_9}$	=	$-z_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_3 - z_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_3 + z_3 - 2x_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	C II
$\mathbf{B_{10}}$	=	$-y_3\,\mathbf{a_1} - z_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - y_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_3 + y_3 - 2z_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	C II
$\mathbf{B_{11}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - z_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_4 - z_4 - x_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	H II
$\mathbf{B_{12}}$	=	$z_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_4 - y_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_4 - y_4 - z_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	H II
$\mathbf{B_{13}}$	=	$y_4\,\mathbf{a_1} + z_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - x_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_4 - x_4 - y_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	H II
$\mathbf{B_{14}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_4 - x_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_4 + x_4 - 2y_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	H II
$\mathbf{B_{15}}$	=	$-z_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - z_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_4 + z_4 - 2x_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	H II
$\mathbf{B_{16}}$	=	$-y_4\,\mathbf{a_1} - z_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - y_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_4 + y_4 - 2z_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	H II

References:

- E. B. Fleischer, *X-Ray Structure Determination of Cubane*, J. Am. Chem. Soc. **86**, 3889–3890 (1964), doi:10.1021/ja01072a069.

Geometry files:

- CIF: pp. S710
- POSCAR: pp. S711

BiI_3 ($D0_5$) Structure: AB3_hR8_148_c_f

Prototype	:	BiI_3
AFLOW prototype label	:	AB3_hR8_148_c_f
***Strukturbericht* designation**	:	$D0_5$
Pearson symbol	:	hR8
Space group number	:	148
Space group symbol	:	$R\bar{3}$
AFLOW prototype command	:	`aflow --proto=AB3_hR8_148_c_f [--hex]` `--params=`$a, c/a, x_1, x_2, y_2, z_2$

Other compounds with this structure:

- SbI_3, AsI_3, $FeCl_3$, $CrBr_3$

- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	Bi
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	Bi
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 - z_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_2 - z_2 - x_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_2 + y_2 + z_2)\,c\,\hat{\mathbf{z}}$	$(6f)$	I
$\mathbf{B_4}$	=	$z_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + y_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_2 - y_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_2 - y_2 - z_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_2 + y_2 + z_2)\,c\,\hat{\mathbf{z}}$	$(6f)$	I
$\mathbf{B_5}$	=	$y_2\,\mathbf{a_1} + z_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_2 - x_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_2 - x_2 - y_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_2 + y_2 + z_2)\,c\,\hat{\mathbf{z}}$	$(6f)$	I
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_2 - x_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_2 + x_2 - 2y_2)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_2 + y_2 + z_2)\,c\,\hat{\mathbf{z}}$	$(6f)$	I
$\mathbf{B_7}$	=	$-z_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - y_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_2 - z_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_2 + z_2 - 2x_2)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_2 + y_2 + z_2)\,c\,\hat{\mathbf{z}}$	$(6f)$	I
$\mathbf{B_8}$	=	$-y_2\,\mathbf{a_1} - z_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 - y_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_2 + y_2 - 2z_2)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_2 + y_2 + z_2)\,c\,\hat{\mathbf{z}}$	$(6f)$	I

References:

- H. Braekken, *Die Kristallstruktur der Trijodide von Arsen, Antimon und Wismut*, Zeitschrift für Kristallographie - Crystalline Materials **74**, 67–72 (1930), doi:10.1524/zkri.1930.74.1.67.

Found in:

- C. Hermann, O. Lohrmann, and H. Philipp, *Strukturbericht Band II, 1928-1932* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937), pp. 25-27.

Geometry files:

- CIF: pp. S711
- POSCAR: pp. S711

PdAl Structure: AB_hR26_148_b2f_a2f

Prototype	:	PdAl
AFLOW prototype label	:	AB_hR26_148_b2f_a2f
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR26
Space group number	:	148
Space group symbol	:	$R\bar{3}$
AFLOW prototype command	:	`aflow --proto=AB_hR26_148_b2f_a2f [--hex]` `--params=`$a, c/a, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6$

- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Pd I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	Al I
$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - z_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_3 - z_3 - x_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al II
$\mathbf{B_4}$	=	$z_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_3 - y_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_3 - y_3 - z_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al II
$\mathbf{B_5}$	=	$y_3\,\mathbf{a_1} + z_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_3 - x_3 - y_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al II
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_3 + x_3 - 2y_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al II
$\mathbf{B_7}$	=	$-z_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_3 - z_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_3 + z_3 - 2x_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al II
$\mathbf{B_8}$	=	$-y_3\,\mathbf{a_1} - z_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - y_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_3 + y_3 - 2z_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al II
$\mathbf{B_9}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - z_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_4 - z_4 - x_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al III
$\mathbf{B_{10}}$	=	$z_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_4 - y_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_4 - y_4 - z_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al III
$\mathbf{B_{11}}$	=	$y_4\,\mathbf{a_1} + z_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - x_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_4 - x_4 - y_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al III
$\mathbf{B_{12}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_4 - x_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_4 + x_4 - 2y_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al III
$\mathbf{B_{13}}$	=	$-z_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - z_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_4 + z_4 - 2x_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al III
$\mathbf{B_{14}}$	=	$-y_4\,\mathbf{a_1} - z_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - y_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_4 + y_4 - 2z_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_4 + y_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6f)$	Al III
$\mathbf{B_{15}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - z_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_5 - z_5 - x_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_5 + y_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd II
$\mathbf{B_{16}}$	=	$z_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_5 - y_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_5 - y_5 - z_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_5 + y_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd II
$\mathbf{B_{17}}$	=	$y_5\,\mathbf{a_1} + z_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_5 - x_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_5 - x_5 - y_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_5 + y_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd II

$\mathbf{B_{18}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_5 - x_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_5 + x_5 - 2y_5)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_5 + y_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd II
$\mathbf{B_{19}}$	=	$-z_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_5 - z_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_5 + z_5 - 2x_5)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_5 + y_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd II
$\mathbf{B_{20}}$	=	$-y_5\,\mathbf{a_1} - z_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - y_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_5 + y_5 - 2z_5)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_5 + y_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd II
$\mathbf{B_{21}}$	=	$x_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_6 - z_6)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_6 - z_6 - x_6)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_6 + y_6 + z_6)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd III
$\mathbf{B_{22}}$	=	$z_6\,\mathbf{a_1} + x_6\,\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_6 - y_6)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_6 - y_6 - z_6)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_6 + y_6 + z_6)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd III
$\mathbf{B_{23}}$	=	$y_6\,\mathbf{a_1} + z_6\,\mathbf{a_2} + x_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_6 - x_6)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_6 - x_6 - y_6)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_6 + y_6 + z_6)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd III
$\mathbf{B_{24}}$	=	$-x_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_6 - x_6)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_6 + x_6 - 2y_6)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_6 + y_6 + z_6)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd III
$\mathbf{B_{25}}$	=	$-z_6\,\mathbf{a_1} - x_6\,\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_6 - z_6)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_6 + z_6 - 2x_6)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_6 + y_6 + z_6)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd III
$\mathbf{B_{26}}$	=	$-y_6\,\mathbf{a_1} - z_6\,\mathbf{a_2} - x_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_6 - y_6)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_6 + y_6 - 2z_6)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_6 + y_6 + z_6)\,c\,\hat{\mathbf{z}}$	$(6f)$	Pd III

References:

- T. Matković and K. Schubert, *Kristallstruktur von PdAl.r*, J. Less-Common Met. **55**, 45–52 (1977), doi:10.1016/0022-5088(77)90258-2.

Found in:

- P. Villars, K. Cenzual, J. Daams, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, V. Kuprysyuk, and I. Savesyuk, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag GmbH, Heidelberg, 2010). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S711
- POSCAR: pp. S712

Ilmenite ($FeTiO_3$) Structure: AB3C_hR10_148_c_f_c

Prototype	:	$FeTiO_3$
AFLOW prototype label	:	AB3C_hR10_148_c_f_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR10
Space group number	:	148
Space group symbol	:	$R\bar{3}$
AFLOW prototype command	:	`aflow --proto=AB3C_hR10_148_c_f_c [--hex]` `--params=`$a, c/a, x_1, x_2, x_3, y_3, z_3$

- The oxygen atoms form a nearly close-packed system, hence the classifications of this structure. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	Fe
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	Fe
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Ti

$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Ti
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - z_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_3 - z_3 - x_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	O
$\mathbf{B_6}$	=	$z_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_3 - y_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_3 - y_3 - z_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	O
$\mathbf{B_7}$	=	$y_3\,\mathbf{a_1} + z_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_3 - x_3 - y_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	O
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_3 + x_3 - 2y_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	O
$\mathbf{B_9}$	=	$-z_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_3 - z_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_3 + z_3 - 2x_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	O
$\mathbf{B_{10}}$	=	$-y_3\,\mathbf{a_1} - z_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - y_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_3 + y_3 - 2z_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_3 + y_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6f)$	O

References:

- B. A. Wechsler and C. T. Prewitt, *Crystal Structure of Ilmenite ($FeTiO_3$) at high temperature and high pressure*, Am. Mineral. **69**, 176–185 (1984).

Geometry files:

- CIF: pp. S712
- POSCAR: pp. S712

Original Fe_2P (C22) Structure: A2B_hP9_150_ef_bd

Prototype	:	Fe_2P
AFLOW prototype label	:	A2B_hP9_150_ef_bd
***Strukturbericht* designation**	:	C22
Pearson symbol	:	hP9
Space group number	:	150
Space group symbol	:	P321
AFLOW prototype command	:	`aflow --proto=A2B_hP9_150_ef_bd` `--params=`$a, c/a, z_2, x_3, x_4$

- This is the structure given in Strukturbericht Vol. II. As noted by Wyckoff, the structure, which was "generally accepted for years, has recently been shown to be incorrect." (Vol I., pp. 360) This corrected structure, as given in Pearson's Handbook, is given in the revised Fe_2P page. When z_2 is set to zero this structure reverts to the revised Fe_2P structure.

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	P I
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2d)$	P II
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2d)$	P II
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1}$	=	$\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}}$	$(3e)$	Fe I
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_2}$	=	$\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}}$	$(3e)$	Fe I
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2}$	=	$-x_3\,a\,\hat{\mathbf{x}}$	$(3e)$	Fe I
$\mathbf{B_7}$	=	$x_4\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_4\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3f)$	Fe II
$\mathbf{B_8}$	=	$x_4\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_4\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3f)$	Fe II
$\mathbf{B_9}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3f)$	Fe II

References:

- S. B. Hendricks and P. R. Kosting, *The Crystal Structure of Fe_2P, Fe_2N, Fe_3N and FeB*, Zeitschrift für Kristallographie - Crystalline Materials **74**, 511–533 (1930), doi:10.1524/zkri.1930.74.1.511.
- R. W. G. Wyckoff, *Crystal Structures Vol. 2, Inorganic Compounds RXn, RnMX2, RnMX3* (Wiley, 1964), 2nd edn.
- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn.

Found in:

- C. Hermann, O. Lohrmann, and H. Philipp, *Strukturbericht Band II, 1928-1932* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937), pp. 15.

Geometry files:

- CIF: pp. S712
- POSCAR: pp. S713

$CrCl_3$ ($D0_4$) Crystal Structure: A3B_hP24_151_3c_2a

Prototype	:	$CrCl_3$
AFLOW prototype label	:	A3B_hP24_151_3c_2a
***Strukturbericht* designation**	:	$D0_4$
Pearson symbol	:	hP24
Space group number	:	151
Space group symbol	:	$P3_112$
AFLOW prototype command	:	`aflow --proto=A3B_hP24_151_3c_2a` `--params=`$a, c/a, x_1, x_2, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5$

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} + \frac{1}{3}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_1\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$	$(3a)$	Cr I
$\mathbf{B_2}$	=	$x_1\,\mathbf{a_1} + 2x_1\,\mathbf{a_2} + \frac{2}{3}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_1\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{2}{3}\,c\,\hat{\mathbf{z}}$	$(3a)$	Cr I
$\mathbf{B_3}$	=	$-2x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-\frac{3}{2}\,x_1\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}}$	$(3a)$	Cr I
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{3}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$	$(3a)$	Cr II
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + 2x_2\,\mathbf{a_2} + \frac{2}{3}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{2}{3}\,c\,\hat{\mathbf{z}}$	$(3a)$	Cr II

$\mathbf{B_6}$	=	$-2x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$-\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}}$	(3a)	Cr II
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 + y_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_3 - x_3)\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	(6c)	Cl I
$\mathbf{B_8}$	=	$-y_3\,\mathbf{a_1} + (x_3 - y_3)\,\mathbf{a_2} + \left(\frac{1}{3} + z_3\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - 2y_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{3} + z_3\right)c\,\hat{\mathbf{z}}$	(6c)	Cl I
$\mathbf{B_9}$	=	$(y_3 - x_3)\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \left(\frac{2}{3} + z_3\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(y_3 - 2x_3)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_3\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} + z_3\right)c\,\hat{\mathbf{z}}$	(6c)	Cl I
$\mathbf{B_{10}}$	=	$-y_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \left(\frac{2}{3} - z_3\right)\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_3 + y_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_3 - x_3)\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} - z_3\right)c\,\hat{\mathbf{z}}$	(6c)	Cl I
$\mathbf{B_{11}}$	=	$(y_3 - x_3)\,\mathbf{a_1} + y_3\,\mathbf{a_2} + \left(\frac{1}{3} - z_3\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{3} - z_3\right)c\,\hat{\mathbf{z}}$	(6c)	Cl I
$\mathbf{B_{12}}$	=	$x_3\,\mathbf{a_1} + (x_3 - y_3)\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_3 - y_3)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	(6c)	Cl I
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_4 - x_4)\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(6c)	Cl II
$\mathbf{B_{14}}$	=	$-y_4\,\mathbf{a_1} + (x_4 - y_4)\,\mathbf{a_2} + \left(\frac{1}{3} + z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - 2y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{3} + z_4\right)c\,\hat{\mathbf{z}}$	(6c)	Cl II
$\mathbf{B_{15}}$	=	$(y_4 - x_4)\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{2}{3} + z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - 2x_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_4\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} + z_4\right)c\,\hat{\mathbf{z}}$	(6c)	Cl II
$\mathbf{B_{16}}$	=	$-y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{2}{3} - z_4\right)\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_4 - x_4)\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} - z_4\right)c\,\hat{\mathbf{z}}$	(6c)	Cl II
$\mathbf{B_{17}}$	=	$(y_4 - x_4)\,\mathbf{a_1} + y_4\,\mathbf{a_2} + \left(\frac{1}{3} - z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_4 - x_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{3} - z_4\right)c\,\hat{\mathbf{z}}$	(6c)	Cl II
$\mathbf{B_{18}}$	=	$x_4\,\mathbf{a_1} + (x_4 - y_4)\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_4 - y_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	(6c)	Cl II
$\mathbf{B_{19}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 + y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_5 - x_5)\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(6c)	Cl III
$\mathbf{B_{20}}$	=	$-y_5\,\mathbf{a_1} + (x_5 - y_5)\,\mathbf{a_2} + \left(\frac{1}{3} + z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - 2y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{3} + z_5\right)c\,\hat{\mathbf{z}}$	(6c)	Cl III
$\mathbf{B_{21}}$	=	$(y_5 - x_5)\,\mathbf{a_1} - x_5\,\mathbf{a_2} + \left(\frac{2}{3} + z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(y_5 - 2x_5)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_5\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} + z_5\right)c\,\hat{\mathbf{z}}$	(6c)	Cl III
$\mathbf{B_{22}}$	=	$-y_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + \left(\frac{2}{3} - z_5\right)\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_5 + y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_5 - x_5)\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} - z_5\right)c\,\hat{\mathbf{z}}$	(6c)	Cl III
$\mathbf{B_{23}}$	=	$(y_5 - x_5)\,\mathbf{a_1} + y_5\,\mathbf{a_2} + \left(\frac{1}{3} - z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_5 - x_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{3} - z_5\right)c\,\hat{\mathbf{z}}$	(6c)	Cl III
$\mathbf{B_{24}}$	=	$x_5\,\mathbf{a_1} + (x_5 - y_5)\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_5 - y_5)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(6c)	Cl III

References:

- N. Wooster, *The Structure of Chromium Trichloride $CrCl_3$*, Zeitschrift für Kristallographie - Crystalline Materials **74**, 363–374 (1930), doi:10.1524/zkri.1930.74.1.363.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:
- CIF: pp. S713
- POSCAR: pp. S713

α-Quartz (low Quartz) Structure: A2B_hP9_152_c_a

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_hP9_152_c_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP9
Space group number	:	152
Space group symbol	:	$P3_121$
AFLOW prototype command	:	`aflow --proto=A2B_hP9_152_c_a` `--params=`$a, c/a, x_1, x_2, y_2, z_2$

- When $x_1 = 1/2$, $y_2 = 2x_2$, and $z_2 = 1/2$, this tranforms into the high quartz (C8) structure. This structure is sometimes given using the enantiomorphic space groups $P3_221$ (#154).

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_1\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$	(3a)	Si
$\mathbf{B_2}$	=	$x_1\,\mathbf{a_2} + \frac{2}{3}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_1\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{2}{3}\,c\,\hat{\mathbf{z}}$	(3a)	Si
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}}$	(3a)	Si
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 + y_2)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_2 - x_2)\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(6c)	O
$\mathbf{B_5}$	=	$-y_2\,\mathbf{a_1} + (x_2 - y_2)\,\mathbf{a_2} + \left(\frac{1}{3} + z_2\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 - 2y_2)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{3} + z_2\right)c\,\hat{\mathbf{z}}$	(6c)	O
$\mathbf{B_6}$	=	$(y_2 - x_2)\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{2}{3} + z_2\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(y_2 - 2x_2)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}y_2\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} + z_2\right)c\,\hat{\mathbf{z}}$	(6c)	O
$\mathbf{B_7}$	=	$y_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 + y_2)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(x_2 - y_2)\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(6c)	O
$\mathbf{B_8}$	=	$(x_2 - y_2)\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \left(\frac{2}{3} - z_2\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 - 2y_2)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}x_2\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} - z_2\right)c\,\hat{\mathbf{z}}$	(6c)	O
$\mathbf{B_9}$	=	$-x_2\,\mathbf{a_1} + (y_2 - x_2)\,\mathbf{a_2} + \left(\frac{1}{3} - z_2\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(y_2 - 2x_2)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}y_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{3} - z_2\right)c\,\hat{\mathbf{z}}$	(6c)	O

References:

- R. M. Hazen, L. W. Finger, R. J. Hemley, and H. K. Mao, *High-pressure crystal chemistry and amorphization of α-quartz*, Solid State Commun. **72**, 507–511 (1989), doi:10.1016/0038-1098(89)90607-8.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S713
- POSCAR: pp. S714

γ-Se (A8) Structure: A_hP3_152_a

Prototype	:	γ-Se
AFLOW prototype label	:	A_hP3_152_a
***Strukturbericht* designation**	:	A8
Pearson symbol	:	hP3
Space group number	:	152
Space group symbol	:	$P3_121$
AFLOW prototype command	:	`aflow --proto=A_hP3_152_a` `--params=`$a, c/a, x_1$

Other compounds with this structure:

- Te, SeTe, Se_3Te

- (Donohue, 1982) refers to this as the α-Se structure, calling what we note as α-Se and β-Se as "monoclinic α" and "monoclinic β," respectively. When $x = 1/3$ this reduces to the A_i (β-Po) or A10 (α-Hg) structure. If, in addition, $c = \sqrt{6}a$, then the structure becomes fcc (A1). On the other hand, if $c = \sqrt{3/2}a$, then the structure becomes simple cubic (A_h).

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_1\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$	$(3a)$	Se
$\mathbf{B_2}$	=	$x_1\,\mathbf{a_2} + \frac{2}{3}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_1\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{2}{3}\,c\,\hat{\mathbf{z}}$	$(3a)$	Se
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}}$	$(3a)$	Se

References:

- P. Cherin and P. Unger, *The Crystal Structure of Trigonal Selenium*, Inorg. Chem. **6**, 1589–1591 (1967), doi:10.1021/ic50054a037.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 370-372 (as α-Se).

Geometry files:

- CIF: pp. S714
- POSCAR: pp. S714

Cinnabar (B9) Structure: AB_hP6_154_a_b

Prototype	:	HgS
AFLOW prototype label	:	AB_hP6_154_a_b
***Strukturbericht* designation**	:	B9
Pearson symbol	:	hP6
Space group number	:	154
Space group symbol	:	$P3_221$
AFLOW prototype command	:	`aflow --proto=AB_hP6_154_a_b` `--params=`$a, c/a, x_1, x_2$

Other compounds with this structure:

- HgO

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_1\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{2}{3}\,c\,\hat{\mathbf{z}}$	$(3a)$	Hg

$\mathbf{B_2}$	=	$x_1\,\mathbf{a_2} + \frac{1}{3}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_1\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$	(3*a*)	Hg
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}}$	(3*a*)	Hg
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + \frac{1}{6}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	(3*b*)	S
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_2} + \frac{5}{6}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{5}{6}\,c\,\hat{\mathbf{z}}$	(3*b*)	S
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(3*b*)	S

References:

- P. Auvray and F. Genet, *Affinement de la structure cristalline du cinabre α-HgS*, Bull. Soc. fr. Minéral. Crystallogr. **96**, 218–219 (1973).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S714
- POSCAR: pp. S715

AlF_3 ($D0_{14}$) Structure: AB3_hR8_155_c_de

Prototype	:	AlF_3
AFLOW prototype label	:	AB3_hR8_155_c_de
***Strukturbericht* designation**	:	$D0_{14}$
Pearson symbol	:	hR8
Space group number	:	155
Space group symbol	:	R32
AFLOW prototype command	:	`aflow --proto=AB3_hR8_155_c_de [--hex]` `--params=`$a, c/a, x_1, y_2, y_3$

Other compounds with this structure:

- FeF_3

- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	Al
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	Al
$\mathbf{B_3}$	=	$y_2\,\mathbf{a_2} - y_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,y_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,y_2\,a\,\hat{\mathbf{y}}$	$(3d)$	F I
$\mathbf{B_4}$	=	$-y_2\,\mathbf{a_1} + y_2\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}}$	$(3d)$	F I
$\mathbf{B_5}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2}$	=	$\frac{1}{2}\,y_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_2\,a\,\hat{\mathbf{y}}$	$(3d)$	F I
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + y_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,(2\,y_3 + 1)\,a\,\hat{\mathbf{x}} + \frac{1}{4\sqrt{3}}\,(6\,y_3 - 1)\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(3e)$	F II
$\mathbf{B_7}$	=	$-y_3\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(3e)$	F II
$\mathbf{B_8}$	=	$y_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,(2\,y_3 - 1)\,a\,\hat{\mathbf{x}} - \frac{1}{4\sqrt{3}}\,(6\,y_3 + 1)\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(3e)$	F II

References:

- J. A. A. Ketelaar, *Die Kristallstruktur der Aluminiumhalogenide: I. Die Kristallstruktur von AlF_3*, Zeitschrift für Kristallographie - Crystalline Materials **85**, 119–131 (1933), doi:10.1524/zkri.1933.85.1.119.
- R. Hoppe and D. Kissel, *Zur kenntnis von AlF_3 und InF_3 [1]*, Journal of Fluorine Chemistry **24**, 327–340 (1984), doi:10.1016/S0022-1139(00)81321-4.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S715
- POSCAR: pp. S715

Hazelwoodite (Ni_3S_2, $D5_e$) Structure: A3B2_hR5_155_e_c

Prototype	:	Ni_3S_2
AFLOW prototype label	:	A3B2_hR5_155_e_c
***Strukturbericht* designation**	:	$D5_e$
Pearson symbol	:	hR5
Space group number	:	155
Space group symbol	:	R32
AFLOW prototype command	:	`aflow --proto=A3B2_hR5_155_e_c [--hex]` `--params=`$a, c/a, x_1, y_2$

Other compounds with this structure:

- Ni_3Se_2

- This can be considered as a prototype for a high concentration of ordered vacancies in the hcp structure. We get the ideal hcp atomic positions when $z_1 = 1/3$ and $y_2 = 1/6$, leaving a vacancy at the origin. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	S
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	S
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + y_2\,\mathbf{a_2} - y_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,(1+2\,y_2)\,a\,\hat{\mathbf{x}} + \frac{1}{4\sqrt{3}}\,(6\,y_2-1)\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(3e)$	Ni
$\mathbf{B_4}$	=	$-y_2\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + y_2\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(3e)$	Ni
$\mathbf{B_5}$	=	$y_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,(2\,y_2-1)\,a\,\hat{\mathbf{x}} - \frac{1}{4\sqrt{3}}\,(1+6\,y_2)\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(3e)$	Ni

References:

- J. B. Parise, *Structure of Hazelwoodite (Ni_3S_2)*, Acta Crystallogr. Sect. B Struct. Sci. **B36**, 1179–1180 (1980), doi:10.1107/S0567740880005523.

Geometry files:

- CIF: pp. S715
- POSCAR: pp. S716

Millerite (NiS, B13) Structure: AB_hR6_160_b_b

Prototype	:	NiS
AFLOW prototype label	:	AB_hR6_160_b_b
***Strukturbericht* designation**	:	B13
Pearson symbol	:	hR6
Space group number	:	160
Space group symbol	:	R3m
AFLOW prototype command	:	`aflow --proto=AB_hR6_160_b_b [--hex]` `--params=`$a, c/a, x_1, z_1, x_2, z_2$

Other compounds with this structure:

- β-FeS

- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_1 - z_1)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_1 - z_1)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	(3*b*)	Ni
$\mathbf{B_2}$	=	$z_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_1 - x_1)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_1 - z_1)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	(3*b*)	Ni
$\mathbf{B_3}$	=	$x_1\,\mathbf{a_1} + z_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_1 - x_1)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	(3*b*)	Ni
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 - z_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_2 - z_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(3*b*)	S
$\mathbf{B_5}$	=	$z_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_2 - x_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_2 - z_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(3*b*)	S
$\mathbf{B_6}$	=	$x_2\,\mathbf{a_1} + z_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_2 - x_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(3*b*)	S

References:

- V. Rajamani and C. T. Prewitt, *The Crystal Structure of Millerite*, Can. Mineral. **12**, 253–257 (1974).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S716
- POSCAR: pp. S716

Moissanite 9R Crystal Structure: AB_hR6_160_3a_3a

Prototype	:	CSi
AFLOW prototype label	:	AB_hR6_160_3a_3a
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR6
Space group number	:	160
Space group symbol	:	R3m
AFLOW prototype command	:	`aflow --proto=AB_hR6_160_3a_3a [--hex]` `--params=`$a, c/a, x_1, x_2, x_3, x_4, x_5, x_6$

- We will loosely use the name moissanite to describe any tetrahedrally bonded silicon carbide compound that does not have another name. The labels 4H, 6H, 9R, etc., refer to the repeat stacking distance in the hexagonal unit cell, while H and R refer to the primitive hexagonal and rhombohedral lattices, respectively. The label C refers to a cubic unit cell, which is a special case of R. Note that 2, 3, 6, 9, etc., refers to the number of C-Si dimers that are stacked. Moissanite 9R is a hypothetical alternate stacking (ABCBCACAB) for tetrahedral structures. Compare this to wurtzite (ABABAB, 2H), zincblende (ABCABC, 3C), moissanite 4H (ABAC) and moissanite 6H (ABCACB). Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(1a)$	C I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(1a)$	C II
$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,c\,\hat{\mathbf{z}}$	$(1a)$	C III
$\mathbf{B_4}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$x_4\,c\,\hat{\mathbf{z}}$	$(1a)$	Si I
$\mathbf{B_5}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$x_5\,c\,\hat{\mathbf{z}}$	$(1a)$	Si II
$\mathbf{B_6}$	=	$x_6\,\mathbf{a_1} + x_6\,\mathbf{a_2} + x_6\,\mathbf{a_3}$	=	$x_6\,c\,\hat{\mathbf{z}}$	$(1a)$	Si III

References:

- M. J. Mehl, Hypothetical SiO2 Structure with 9R stacking.

Geometry files:

- CIF: pp. S716
- POSCAR: pp. S716

Ferroelectric $LiNbO_3$ Structure: ABC3_hR10_161_a_a_b

Prototype	:	$LiNbO_3$
AFLOW prototype label	:	ABC3_hR10_161_a_a_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR10
Space group number	:	161
Space group symbol	:	R3c
AFLOW prototype command	:	`aflow --proto=ABC3_hR10_161_a_a_b [--hex]` `--params=`$a, c/a, x_1, x_2, x_3, y_3, z_3$

- This is the ferroelectric phase of $LiNbO_3$, which exists below 1430K. There is also a high-temperature paraelectric phase. This reduces to a double unit cell version of the cubic perovskite structure in the special case:
  - $c/a = \sqrt{6}$: This sets the angle between the rhombohedral primitive vectors to 60°. Experimentally the value is about 56°.
  - $z_1 = 1/4$
  - $z_2 = 0$
  - $x_3 = 1/2$
  - $y_3 = 0$
  - $z_3 = 0$

  Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Li
$\mathbf{B_2}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1} + \left(\frac{1}{2}+x_1\right)\mathbf{a_2} + \left(\frac{1}{2}+x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)c\,\hat{\mathbf{z}}$	$(2a)$	Li
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(2a)$	Nb
$\mathbf{B_4}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1} + \left(\frac{1}{2}+x_2\right)\mathbf{a_2} + \left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)c\,\hat{\mathbf{z}}$	$(2a)$	Nb
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}(x_3-z_3)\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}(x_3-2y_3+z_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}(x_3+y_3+z_3)\,c\,\hat{\mathbf{z}}$	$(6b)$	O
$\mathbf{B_6}$	=	$z_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$\frac{1}{2}(z_3-y_3)\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}(z_3-2x_3+y_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}(x_3+y_3+z_3)\,c\,\hat{\mathbf{z}}$	$(6b)$	O
$\mathbf{B_7}$	=	$y_3\,\mathbf{a_1} + z_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{2}(y_3-x_3)\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}(y_3-2z_3+x_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}(x_3+y_3+z_3)\,c\,\hat{\mathbf{z}}$	$(6b)$	O
$\mathbf{B_8}$	=	$\left(\frac{1}{2}+y_3\right)\mathbf{a_1} + \left(\frac{1}{2}+x_3\right)\mathbf{a_2} + \left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\frac{1}{2}(y_3-z_3)\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}(z3-2x_3+y_3)\,a\,\hat{\mathbf{y}} + \frac{1}{6}(3+2x_3+2y_3+2z_3)\,c\,\hat{\mathbf{z}}$	$(6b)$	O
$\mathbf{B_9}$	=	$\left(\frac{1}{2}+x_3\right)\mathbf{a_1} + \left(\frac{1}{2}+z_3\right)\mathbf{a_2} + \left(\frac{1}{2}+y_3\right)\mathbf{a_3}$	=	$\frac{1}{2}(x_3-y_3)\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}(y_3-2z_3+x_3)\,a\,\hat{\mathbf{y}} + \frac{1}{6}(3+2x_3+2y_3+2z_3)\,c\,\hat{\mathbf{z}}$	$(6b)$	O
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}+z_3\right)\mathbf{a_1} + \left(\frac{1}{2}+y_3\right)\mathbf{a_2} + \left(\frac{1}{2}+x_3\right)\mathbf{a_3}$	=	$\frac{1}{2}(z_3-x_3)\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}(x_3-2y_3+z_3)\,a\,\hat{\mathbf{y}} + \frac{1}{6}(3+2x_3+2y_3+2z_3)\,c\,\hat{\mathbf{z}}$	$(6b)$	O

References:

- H. Boysen and F. Altorfer, *A neutron powder investigation of the high-temperature structure and phase transition in $LiNbO_3$*, Acta Crystallogr. Sect. B Struct. Sci. **50**, 405–414 (1994), doi:10.1107/S0108768193012820.

Geometry files:

- CIF: pp. S717
- POSCAR: pp. S717

β-V_2N Structure: AB2_hP9_162_ad_k

Prototype	:	β-V_2N
AFLOW prototype label	:	AB2_hP9_162_ad_k
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP9
Space group number	:	162
Space group symbol	:	$P\bar{3}1m$
AFLOW prototype command	:	`aflow --proto=AB2_hP9_162_ad_k` `--params=`$a, c/a, x_3, z_3$

- Note that our reference (Christensen, 1979) states that ϵ-Fe_2N is the prototype for this structure. We will instead follow (Villars, 1991), which uses β-V_2N as the prototype.

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	N I
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2d)$	N II
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2d)$	N II
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(6k)$	V
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(6k)$	V
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + z_3\,c\,\hat{\mathbf{z}}$	$(6k)$	V
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(6k)$	V
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} - z_3\,\mathbf{a_3}$	=	$-\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(6k)$	V
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - z_3\,c\,\hat{\mathbf{z}}$	$(6k)$	V

References:

- A. Nørlund Christensen and B. Lebech, *The structure of β-Vanadium Nitride*, Acta Crystallogr. Sect. B Struct. Sci. **35**, 2677–2678 (1979), doi:10.1107/S0567740879010141.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4503.

Geometry files:

- CIF: pp. S717
- POSCAR: pp. S717

$KAg(CN)_2$ ($F5_{10}$) Structure: AB2CD2_hP36_163_h_i_bf_i

Prototype	:	$KAg(CN)_2$
AFLOW prototype label	:	AB2CD2_hP36_163_h_i_bf_i
***Strukturbericht* designation**	:	$F5_{10}$
Pearson symbol	:	hP36
Space group number	:	163
Space group symbol	:	$P\bar{3}1c$
AFLOW prototype command	:	`aflow --proto=AB2CD2_hP36_163_h_i_bf_i` `--params=`$a, c/a, z_2, x_3, x_4, y_4, z_4, x_5, y_5, z_5$

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B}_1$	=	$0\,\mathbf{a}_1 + 0\,\mathbf{a}_2 + 0\,\mathbf{a}_3$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2b)$	K I
$\mathbf{B}_2$	=	$\frac{1}{2}\,\mathbf{a}_3$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2b)$	K I

$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	K II
$\mathbf{B_4}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	K II
$\mathbf{B_5}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	K II
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	K II
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_3\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ag
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} + 2x_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_3\,a\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ag
$\mathbf{B_9}$	=	$-2x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_3\,a\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ag
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\sqrt{3}\,x_3\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ag
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} - 2x_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_3\,a\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ag
$\mathbf{B_{12}}$	=	$2x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_3\,a\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ag
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_4 - x_4)\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{14}}$	=	$-y_4\,\mathbf{a_1} + (x_4 - y_4)\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - 2y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{15}}$	=	$(y_4 - x_4)\,\mathbf{a_1} - x_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - 2x_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{16}}$	=	$-y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_4 - x_4)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{17}}$	=	$(y_4 - x_4)\,\mathbf{a_1} + y_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_4 - x_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{18}}$	=	$x_4\,\mathbf{a_1} + (x_4 - y_4)\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_4 - y_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{19}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(x_4 - y_4)\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{20}}$	=	$y_4\,\mathbf{a_1} + (y_4 - x_4)\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_4 - x_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{21}}$	=	$(x_4 - y_4)\,\mathbf{a_1} + x_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_4 - y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{22}}$	=	$y_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(x_4 - y_4)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{23}}$	=	$(x_4 - y_4)\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - 2y_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{24}}$	=	$-x_4\,\mathbf{a_1} + (y_4 - x_4)\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - 2x_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(12i)$	C
$\mathbf{B_{25}}$	=	$x_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 + y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_5 - x_5)\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(12i)$	N
$\mathbf{B_{26}}$	=	$-y_5\,\mathbf{a_1} + (x_5 - y_5)\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - 2y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(12i)$	N
$\mathbf{B_{27}}$	=	$(y_5 - x_5)\,\mathbf{a_1} - x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_5 - 2x_5)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_5\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(12i)$	N
$\mathbf{B_{28}}$	=	$-y_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\,\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_5 + y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_5 - x_5)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)\,c\,\hat{\mathbf{z}}$	$(12i)$	N
$\mathbf{B_{29}}$	=	$(y_5 - x_5)\,\mathbf{a_1} + y_5\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_5 - x_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)\,c\,\hat{\mathbf{z}}$	$(12i)$	N

$\mathbf{B_{30}}$	=	$x_5\,\mathbf{a_1} + (x_5 - y_5)\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_5 - y_5)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,y_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	(12i)	N
$\mathbf{B_{31}}$	=	$-x_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_5 + y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(x_5 - y_5)\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(12i)	N
$\mathbf{B_{32}}$	=	$y_5\,\mathbf{a_1} + (y_5 - x_5)\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_5 - x_5)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(12i)	N
$\mathbf{B_{33}}$	=	$(x_5 - y_5)\,\mathbf{a_1} + x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_5 - y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,y_5\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	(12i)	N
$\mathbf{B_{34}}$	=	$y_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 + y_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(x_5 - y_5)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(12i)	N
$\mathbf{B_{35}}$	=	$(x_5 - y_5)\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - 2y_5)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(12i)	N
$\mathbf{B_{36}}$	=	$-x_5\,\mathbf{a_1} + (y_5 - x_5)\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(y_5 - 2x_5)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,y_5\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	(12i)	N

References:

- J. L. Hoard, *The Crystal Structure of Potassium Silver Cyanide*, Zeitschrift für Kristallographie - Crystalline Materials **84**, 231–255 (1933), doi:10.1524/zkri.1933.84.1.231.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S718
- POSCAR: pp. S718

Al_3Ni_2 ($D5_{13}$) Structure: A3B2_hP5_164_ad_d

Prototype	:	Al_3Ni_2
AFLOW prototype label	:	A3B2_hP5_164_ad_d
***Strukturbericht* designation**	:	$D5_{13}$
Pearson symbol	:	hP5
Space group number	:	164
Space group symbol	:	$P\bar{3}m1$
AFLOW prototype command	:	`aflow --proto=A3B2_hP5_164_ad_d` `--params=`$a, c/a, z_2, z_3$

Other compounds with this structure:

- Al_3Cu_2, Al_3Pd_2, Al_3Pt_2, Al_3In_2, Al_3Tc_2, In_3Al_2, In_3Pd_2, In_3Pt_2, Ga_3Pt_2

- Either the 3 Al atoms or Al (1a) and the Ni atoms form a trigonal omega structure. Using the choices of internal parameters for Al_3Ni_2, this can be viewed as a five-layer close-packed unit cell with stacking ABCBCA.

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Al I
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2d)$	Al II
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2d)$	Al II
$\mathbf{B_4}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(2d)$	Ni
$\mathbf{B_5}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(2d)$	Ni

References:

- A. J. Bradley and A. Taylor, *The crystal structures of Ni_2Al_3 and $NiAl_3$*, Phil. Mag. **23**, 1049–1067 (1937), doi:10.1080/14786443708561875.

Found in:

- P. Villars, K. Cenzual, J. Daams, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, N. Melnichenko-Koblyuk, O. Pavlyuk, I. Savesyuk, S. Stoiko, and L. Sysa, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag GmbH, Heidelberg, 2008). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S718
- POSCAR: pp. S718

ω (C6) Phase: AB2_hP3_164_a_d

Prototype	:	CdI_2
AFLOW prototype label	:	AB2_hP3_164_a_d
***Strukturbericht* designation**	:	C6
Pearson symbol	:	hP3
Space group number	:	164
Space group symbol	:	$P\bar{3}m1$
AFLOW prototype command	:	`aflow --proto=AB2_hP3_164_a_d --params=`$a, c/a, z_2$

Other compounds with this structure:

- Ti, Zr, Hf, ZrNb, TiNb, TiV

- The ω phase can be either hexagonal or trigonal (shown here). The trigonal ω phase transforms into several high-symmetry structures under certain conditions:

c/a	z	**Lattice**
Arbitrary	0	Ideal Omega (C32)
$\sqrt{\frac{3}{8}}$	$\frac{1}{6}$	Body-Centered Cubic (A2)
$\sqrt{\frac{3}{2}}$	$\frac{1}{6}$	Simple Cubic(A_h)
$\sqrt{6}$	$\frac{1}{6}$	Face-Centered Cubic (A1)
Arbitrary	$\frac{1}{2}$	Simple Hexagonal Structure (A_f)

For more details about the omega phase and materials which form in the omega phase, see (Sikka, 1982) . As noted there, most omega phase intermetallic alloys are disordered. Although the "ω" label comes from ω-CrTi, (Ewald, 1931) lists the prototype for Strukturbericht designation C6 as CdI2.

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cd
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2d)$	I
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(2d)$	I

References:

- R. M. Bozorth, *The Crystal Structure of Cadmium Iodide*, J. Am. Chem. Soc. **44**, 2232–2236 (1922), doi:10.1021/ja01431a019.
- S. K. Sikka, Y. K. Vohra, and R. Chidambaram, *Omega phase in materials*, Prog. Mater. Sci. **27**, 245–310 (1982), doi:10.1016/0079-6425(82)90002-0.

Found in:

- P. P. Ewald and C. Hermann, *Strukturbericht Band I, 1913-1928* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1931), pp. 161-163.

Geometry files:

- CIF: pp. S719
- POSCAR: pp. S719

H_3Ho Structure: A3B_hP24_165_adg_f

Prototype	:	H_3Ho
AFLOW prototype label	:	A3B_hP24_165_adg_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP24
Space group number	:	165
Space group symbol	:	$P\bar{3}c1$
AFLOW prototype command	:	`aflow --proto=A3B_hP24_165_adg_f` `--params=`$a, c/a, z_2, x_3, x_4, y_4, z_4$

Other compounds with this structure:

- H_3Dy, H_3Er, H_3Gd, H_3Lu, H_3Sm, H_3Tb, H_3Tm, H_3Y, $AuCu_3$, $AuMg_3$, Cu_3P

- As with all compounds involving hydrogen, structural determinations were made with deuterium.

Trigonal Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2a)$	H I
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2a)$	H I
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4d)$	H II
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\hat{\mathbf{z}}$	$(4d)$	H II
$\mathbf{B_5}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4d)$	H II
$\mathbf{B_6}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	$(4d)$	H II
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6f)$	Ho
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6f)$	Ho
$\mathbf{B_9}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6f)$	Ho
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6f)$	Ho
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6f)$	Ho
$\mathbf{B_{12}}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6f)$	Ho
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_4 - x_4)\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{14}}$	=	$-y_4\,\mathbf{a_1} + (x_4 - y_4)\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - 2y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}x_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{15}}$	=	$(y_4 - x_4)\,\mathbf{a_1} - x_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - 2x_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}y_4\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{16}}$	=	$y_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(x_4 - y_4)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{17}}$	=	$(x_4 - y_4)\,\mathbf{a_1} - y_4\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - 2y_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{18}}$	=	$-x_4\,\mathbf{a_1} + (y_4 - x_4)\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_4 - 2x_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{19}}$	=	$-x_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(x_4 - y_4)\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{20}}$	=	$y_4\,\mathbf{a_1} + (y_4 - x_4)\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_4 - x_4)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}x_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{21}}$	=	$(x_4 - y_4)\,\mathbf{a_1} + x_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_4 - y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}y_4\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(12g)$	H III
$\mathbf{B_{22}}$	=	$-y_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$-\frac{1}{2}\,(x_4 + y_4)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,(y_4 - x_4)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(12g)$	H III

$\mathbf{B_{23}}$	=	$(y_4 - x_4)\ \mathbf{a_1} + y_4\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(2y_4 - x_4)\ a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}x_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	(12g)	H III
$\mathbf{B_{24}}$	=	$x_4\,\mathbf{a_1} + (x_4 - y_4)\ \mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,(2x_4 - y_4)\ a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}y_4\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	(12g)	H III

References:

- M. Mansmann and W. E. Wallace, *The Structure of HoD_3*, Le Journal de Physique **25**, 454–459 (1964), doi:10.1051/jphys:01964002505045400.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 3829.

Geometry files:

- CIF: pp. S719
- POSCAR: pp. S719

CuPt ($L1_1$) Structure: AB_hR2_166_a_b

Prototype	:	CuPt
AFLOW prototype label	:	AB_hR2_166_a_b
***Strukturbericht* designation**	:	$L1_1$
Pearson symbol	:	hR2
Space group number	:	166
Space group symbol	:	$R\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB_hR2_166_a_b [--hex]` `--params=`$a, c/a$

- For notes on this structure, see the original reference, (Johansson, 1927), and the discussion in (Villars, 2007). We use the structure deduced by Villars et. al. As noted by (Barrett, 1980), even slight additions of Pt above stoichiometry will cause a change in the crystal structure. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cu
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	Pt

References:

- C. H. Johansson and J. O. Linde, *Gitterstruktur und elektrisches Leitvermögen der Mischkristallreihen Au-Cu, Pd-Cu und Pt-Cu*, Annalen der Physik **387**, 449–478 (1927), doi:10.1002/andp.19273870402.

Found in:

- P. P. Ewald and C. Hermann, *Strukturbericht Band I, 1913-1928* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1931), pp. 485.
- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 311-312.
- C. S. Barrett and T. B. Massalski, *Structure of Metals: Crystallographic Methods, Principles, and Data* (Pergamon Press, Oxford, 1980), 3rd revised edn, pp. 275.
- P. Villars, K. Cenzual, J. Daams, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, N. Melnichenko-Koblyuk, O. Pavlyuk, I. Savesyuk, S. Stoiko, and L. Sysa, *Landolt-Börnstein - Group III Condensed Matter 43A5 (Structure Types. Part 5: Space Groups (173) P63 - (166) R-3m)* (Springer-Verlag, 2007). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S720
- POSCAR: pp. S720

α-As (A7) Structure: A_hR2_166_c

Prototype	:	α-As
AFLOW prototype label	:	A_hR2_166_c
***Strukturbericht* designation**	:	A7
Pearson symbol	:	hR2
Space group number	:	166
Space group symbol	:	R$\bar{3}$m
AFLOW prototype command	:	`aflow --proto=A_hR2_166_c [--hex]` `--params=`$a, c/a, x_1$

Other elements with this structure:

- Sb, Bi

- When $c/a = \sqrt{6}$ and $z_1 = 1/8$ this becomes the diamond (A4) structure. Note that α-As (pp. S375), rhombohedral graphite (pp. S389), and β-O (pp. S395) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	As
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	As

References:

- D. Schiferl and C. S. Barrett, *The crystal structure of arsenic at 4.2, 78 and 299°K*, J. Appl. Crystallogr. **2**, 30–36 (1969), doi:10.1107/S0021889869006443.
- R. J. Meier and R. B. Helmholdt, *Neutron-diffraction study of α- and β-oxygen*, Phys. Rev. B **29**, 1387–1393 (1984), doi:10.1103/PhysRevB.29.1387.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S720
- POSCAR: pp. S721

β-Po (A_i) Structure: A_hR1_166_a

Prototype	:	β-Po
AFLOW prototype label	:	A_hR1_166_a
***Strukturbericht* designation**	:	A_i
Pearson symbol	:	hR1
Space group number	:	166
Space group symbol	:	$R\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A_hR1_166_a [--hex]` `--params=`$a, c/a$

- This rhombohedral structure becomes cubic at various values of c/a (or α) to wit,

c/a	α	**Cubic Lattice**
$\sqrt{6}$	60°	Face-Centered Cubic
$\sqrt{\frac{3}{2}}$	90°	Simple Cubic
$\sqrt{\frac{3}{8}}$	109.47^o	Body-Centered Cubic

Note that β-Po (pp. S377) and α-Hg (pp. S385) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files. Experimentally, β-Po (A_i) has c/a near 1, or $\alpha > 90^o$, while α-Hg (A10) has c/a near 2, or $\alpha < 90^o$. Originally, Po was assigned Strukturbericht designation: A19, which is now considered to be incorrect (Donohue, 1982, pp. 390). Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Po

References:

- W. H. Beamer and C. R. Maxwell, *Physical Properties of Polonium. II. X-Ray Studies and Crystal Structure*, J. Chem. Phys. **17**, 1293–1298 (1949), doi:10.1063/1.1747155.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 392.

Geometry files:

- CIF: pp. S721
- POSCAR: pp. S721

Fe_7W_6 ($D8_5$) μ-phase: A7B6_hR13_166_ah_3c

Prototype	:	Fe_7W_6
AFLOW prototype label	:	A7B6_hR13_166_ah_3c
***Strukturbericht* designation**	:	$D8_5$
Pearson symbol	:	hR13
Space group number	:	166
Space group symbol	:	$R\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A7B6_hR13_166_ah_3c [--hex]` `--params=`$a, c/a, x_2, x_3, x_4, x_5, z_5$

Other compounds with this structure:

- Co_7Mo_6, Co_6Mo_7, Co_7W_6, Co_6Re_6Si, Fe_6Ta_7, Fe_7Nb_6, Fe_7Mo_6, Fe_7Ta_6, Ta_6Zn_7, Mn_6Si_7, etc.

- For more information on the μ-phase, see (Pearson, 1972) pp. 664. There it is referred to as a tetrahedrally close-packed Frank-Kasper structure. We have been unable to obtain a copy of the original reference for this structure, (Arnfeldt, 1935), so we use the structure from (Villars, 1991) pp. 3415, which itself is taken from a secondary reference. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Fe I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	W I
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	W I

$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,c\,\hat{\mathbf{z}}$	(2c)	W II
$\mathbf{B_5}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,c\,\hat{\mathbf{z}}$	(2c)	W II
$\mathbf{B_6}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$x_4\,c\,\hat{\mathbf{z}}$	(2c)	W III
$\mathbf{B_7}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$-x_4\,c\,\hat{\mathbf{z}}$	(2c)	W III
$\mathbf{B_8}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - z_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}(x_5 - z_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	(6h)	Fe II
$\mathbf{B_9}$	=	$z_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_5 - x_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}(x_5 - z_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	(6h)	Fe II
$\mathbf{B_{10}}$	=	$x_5\,\mathbf{a_1} + z_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}(z_5 - x_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	(6h)	Fe II
$\mathbf{B_{11}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_5 - x_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}(z_5 - x_5)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	(6h)	Fe II
$\mathbf{B_{12}}$	=	$-z_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - z_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}(z_5 - x_5)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	(6h)	Fe II
$\mathbf{B_{13}}$	=	$-x_5\,\mathbf{a_1} - z_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}(x_5 - z_5)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	(6h)	Fe II

References:

- H. Arnfelt, *Crystal Structure of Fe_7W_6*, Jernkontorets Annaler **119**, 185–187 (1935).
- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 3415.

Geometry files:

- CIF: pp. S721
- POSCAR: pp. S722

α-Sm (C19) Structure: A_hR3_166_ac

Prototype	:	α-Sm
AFLOW prototype label	:	A_hR3_166_ac
***Strukturbericht* designation**	:	C19
Pearson symbol	:	hR3
Space group number	:	166
Space group symbol	:	R$\bar{3}$m
AFLOW prototype command	:	`aflow --proto=A_hR3_166_ac [--hex]` `--params=`$a, c/a, x_2$

Other elements with this structure:

- Li (Overhauser, 1984).

- Note that this is a close-packed system, with stacking ABCBCACAB, in contrast to the ABAB stacking of the hexagonal close-packed structure and the ABCABC stacking of the face-centered cubic structure. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Sm I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Sm II
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Sm II

References:

- A. W. Overhauser, *Crystal Structure of Lithium at 4.2 K*, Phys. Rev. Lett. **53**, 64–65 (1984), doi:10.1103/PhysRevLett.53.64.
- A. H. Daane, R. E. Rundle, H. G. Smith, and F. H. Spedding, *The crystal structure of samarium*, Acta Cryst. **7**, 532–535 (1954), doi:10.1107/S0365110X54001818.

Geometry files:
- CIF: pp. S722
- POSCAR: pp. S722

Bi_2Te_3 Structure (C33): A2B3_hR5_166_c_ac

Prototype	:	Bi_2Te_3
AFLOW prototype label	:	A2B3_hR5_166_c_ac
***Strukturbericht* designation**	:	C33
Pearson symbol	:	hR5
Space group number	:	166
Space group symbol	:	$R\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A2B3_hR5_166_c_ac [--hex]` `--params=`$a, c/a, x_2, x_3$

Other compounds with this structure:

- Be_2Te_2S, Sb_2Te_3, Bi_2Te_2Se, Bi_2Te_3, Bi_2Se_3

- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Te I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Bi
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	Bi
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,c\,\hat{\mathbf{z}}$	$(2c)$	Te II
$\mathbf{B_5}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,c\,\hat{\mathbf{z}}$	$(2c)$	Te II

References:

- P. W. Lange, *Ein Vergleich zwischen Bi_2Te_3 und Bi_2Te_2S*, Naturwissenschaften **27**, 133–134 (1939), doi:10.1007/BF01490284.

Geometry files:

- CIF: pp. S722
- POSCAR: pp. S723

α-Hg (A10) Structure: A_hR1_166_a

Prototype	:	α-Hg
AFLOW prototype label	:	A_hR1_166_a
***Strukturbericht* designation**	:	A10
Pearson symbol	:	hR1
Space group number	:	166
Space group symbol	:	R$\bar{3}$m
AFLOW prototype command	:	`aflow --proto=A_hR1_166_a [--hex]` `--params=`$a, c/a$

- This rhombohedral structure becomes cubic at various values of c/a (or α) to wit,

c/a	α	**Cubic Lattice**
$\sqrt{6}$	60°	Face-Centered Cubic
$\sqrt{\frac{3}{2}}$	90°	Simple Cubic
$\sqrt{\frac{3}{8}}$	109.47^o	Body-Centered Cubic

Note that β-Po (pp. S377) and α-Hg (pp. S385) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files. Experimentally, β-Po (A_i) has c/a near 1, or $\alpha > 90^o$, while α-Hg (A10) has c/a near 2, or $\alpha < 90^o$. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Hg

References:

- C. S. Barrett, *The structure of mercury at low temperatures*, Acta Cryst. **10**, 58–60 (1957), doi:10.1107/S0365110X57000134.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 231-233.

Geometry files:

- CIF: pp. S723
- POSCAR: pp. S723

Mo_2B_5 ($D8_i$) Structure: A5B2_hR7_166_a2c_c

Prototype	:	Mo_2B_5
AFLOW prototype label	:	A5B2_hR7_166_a2c_c
***Strukturbericht* designation**	:	$D8_i$
Pearson symbol	:	hR7
Space group number	:	166
Space group symbol	:	$R\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A5B2_hR7_166_a2c_c [--hex]` `--params=`$a, c/a, x_2, x_3, x_4$

Other compounds with this structure:

- V_2B_5, InL_5Tl, Li_5Sn_2, Li_5Tl_2

- The boron atoms form buckled graphitic sheets, making this the rhombohedral form of $D8_h$. (Frotscher, 2007) suggest that the stable composition in this part of the molybdenum nitride system might be Mo_2B_4, but here we will describe the $D8_i$ structure, with the warning that this might not be the experimental structure. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	B I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	B II
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	B II
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,c\,\hat{\mathbf{z}}$	$(2c)$	B III

$\mathbf{B_5}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,c\,\hat{\mathbf{z}}$	(2c)	B III
$\mathbf{B_6}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$x_4\,c\,\hat{\mathbf{z}}$	(2c)	Mo
$\mathbf{B_7}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$-x_4\,c\,\hat{\mathbf{z}}$	(2c)	Mo

References:

- R. Kiessling, *The Crystal Structures of Molybdenum and Tungsten Borides*, Acta Chem. Scand. **1**, 893–916 (1947), doi:10.3891/acta.chem.scand.01-0893.
- M. Frotscher, W. Klein, J. Bauer, C. Fang, J. Halet, A. Senyshyn, C. Baehtz, and B. Albert, *M_2B_5 or M_2B_4? A Reinvestigation of the Mo/B and W/B System*, Z. Anorg. Allg. Chem. **633**, 2626–2630 (2007), doi:10.1002/zaac.200700376.

Geometry files:

- CIF: pp. S723
- POSCAR: pp. S724

Rhombohedral Graphite Structure: A_hR2_166_c

Prototype	:	C
AFLOW prototype label	:	A_hR2_166_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR2
Space group number	:	166
Space group symbol	:	$R\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A_hR2_166_c [--hex]` `--params=`$a, c/a, x_1$

- Graphite also comes in a hexagonal form, which may be either flat (A9) or buckled. When $x_1 = 1/6$ the graphite sheets are flat. However this does not produce a change in symmetry, as it does in the hexagonal graphite structures. Note that α-As (pp. S375), rhombohedral graphite (pp. S389), and β-O (pp. S395) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	C
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	C

References:

- H. Lipson and A. R. Stokes, *The structure of graphite*, Proc. R. Soc. A Math. Phys. Eng. Sci. **181**, 101–105 (1942), doi:10.1098/rspa.1942.0063.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 258-260.

Geometry files:

- CIF: pp. S724
- POSCAR: pp. S724

α-B (hR12) Structure: A_hR12_166_2h

Prototype	:	α-B
AFLOW prototype label	:	A_hR12_166_2h
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR12
Space group number	:	166
Space group symbol	:	R$\bar{3}$m
AFLOW prototype command	:	`aflow --proto=A_hR12_166_2h [--hex]` `--params=`$a, c/a, x_1, z_1, x_2, z_2$

- This is a metastable phase of boron, and the simplest known phase (the ground state, β-B, has 105 or 320 atoms in the unit cell). Note the relationship between the icosahedra in this structure, in T-50 B, and in β-B. (Donohue, 1982) refers to this as rhombohedral-12 boron. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

	Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$ =	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + z_1\,\mathbf{a_3}$ =	$\frac{1}{2}\,(x_1 - z_1)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_1 - z_1)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	$(6h)$	B I

$\mathbf{B_2}$	=	$z_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_1 - x_1)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_1 - z_1)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	(6*h*)	B I
$\mathbf{B_3}$	=	$x_1\,\mathbf{a_1} + z_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_1 - x_1)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	(6*h*)	B I
$\mathbf{B_4}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_1 - x_1)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_1 - x_1)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	(6*h*)	B I
$\mathbf{B_5}$	=	$-z_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_1 - z_1)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_1 - x_1)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	(6*h*)	B I
$\mathbf{B_6}$	=	$-x_1\,\mathbf{a_1} - z_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_1 - z_1)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_1 + z_1)\,c\,\hat{\mathbf{z}}$	(6*h*)	B I
$\mathbf{B_7}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 - z_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_2 - z_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(6*h*)	B II
$\mathbf{B_8}$	=	$z_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_2 - x_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_2 - z_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(6*h*)	B II
$\mathbf{B_9}$	=	$x_2\,\mathbf{a_1} + z_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_2 - x_2)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(6*h*)	B II
$\mathbf{B_{10}}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_2 - x_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_2 - x_2)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(6*h*)	B II
$\mathbf{B_{11}}$	=	$-z_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_2 - z_2)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_2 - x_2)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(6*h*)	B II
$\mathbf{B_{12}}$	=	$-x_2\,\mathbf{a_1} - z_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_2 - z_2)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_2 + z_2)\,c\,\hat{\mathbf{z}}$	(6*h*)	B II

References:

- B. F. Decker and J. S. Kasper, *The crystal structure of a simple rhombohedral form of boron*, Acta Cryst. **12**, 503–506 (1959), doi:10.1107/S0365110X59001529.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 57-60.

Geometry files:

- CIF: pp. S724
- POSCAR: pp. S725

Caswellsilverite ($CrNaS_2$, $F5_1$) Crystal Structure: ABC2_hR4_166_a_b_c

Prototype	:	$CrNaS_2$
AFLOW prototype label	:	ABC2_hR4_166_a_b_c
***Strukturbericht* designation**	:	$F5_1$
Pearson symbol	:	hR4
Space group number	:	166
Space group symbol	:	$R\bar{3}m$
AFLOW prototype command	:	`aflow --proto=ABC2_hR4_166_a_b_c [--hex] --params=`$a, c/a, x_3$

Other compounds with this structure:

- $AgAsSe_2$, HoS_2Tl, $AlCV_2$, Te_2TlY, many others

- This mineral did not obtain a name until it was discovered in nature (Okada, 1982). Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cr
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	Na
$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,c\,\hat{\mathbf{z}}$	$(2c)$	S
$\mathbf{B_4}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,c\,\hat{\mathbf{z}}$	$(2c)$	S

References:

- A. Okada and K. Keil, *Caswellsilverite, $NaCrS_2$: a new mineral in the Norton County enstatite achondrite*, Am. Mineral. **67**, 132–136 (1982).
- F. M. R. Engelsman, G. A. Wiegers, F. Jellinek, and B. Van Laar, *Crystal structures and magnetic structures of some metal(I) chromium(III) sulfides and selenides*, J. Solid State Chem. **6**, 574–582 (1973), doi:10.1016/S0022-4596(73)80018-0.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S725
- POSCAR: pp. S726

β-O Structure: A_hR2_166_c

Prototype	:	β-O
AFLOW prototype label	:	A_hR2_166_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR2
Space group number	:	166
Space group symbol	:	R$\bar{3}$m
AFLOW prototype command	:	`aflow --proto=A_hR2_166_c [--hex]` `--params=`$a, c/a, x_1$

- Note that α-As (pp. S375), rhombohedral graphite (pp. S389), and β-O (pp. S395) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	O
$\mathbf{B_2}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1\,c\,\hat{\mathbf{z}}$	$(2c)$	O

References:

- R. J. Meier and R. B. Helmholdt, *Neutron-diffraction study of α- and β-oxygen*, Phys. Rev. B **29**, 1387–1393 (1984), doi:10.1103/PhysRevB.29.1387.

Geometry files:

- CIF: pp. S726
- POSCAR: pp. S726

β-B (R-105) Structure: A_hR105_166_bc9h4i

Prototype	:	β-B
AFLOW prototype label	:	A_hR105_166_bc9h4i
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR105
Space group number	:	166
Space group symbol	:	R$\bar{3}$m
AFLOW prototype command	:	`aflow --proto=A_hR105_166_bc9h4i [--hex]` `--params=`$a, c/a, x_2, x_3, z_3, x_4, z_4, x_5, z_5, x_6, z_6, x_7, z_7, x_8, z_8, x_9, z_9, x_{10}, z_{10}, x_{11}, z_{11}, x_{12}, y_{12}, z_{12}, x_{13}, y_{13}, z_{13}, x_{14}, y_{14}, z_{14}, x_{15}, y_{15}, z_{15}$

- This is apparently the ground state of boron, with 105 atoms in the unit cell. Note the relationship between the icosahedra in this structure, α-B and T-50 B. (Donohue, 1982) gives two possible sets of internal coordinates for the atoms on page 64. We use the second set (Geist, 1970), as it has no partially filled sites. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	B I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	B II
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,c\,\hat{\mathbf{z}}$	$(2c)$	B II
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - z_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_3 - z_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6h)$	B III
$\mathbf{B_5}$	=	$z_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_3 - z_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6h)$	B III
$\mathbf{B_6}$	=	$x_3\,\mathbf{a_1} + z_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_3 - x_3)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6h)$	B III
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_3 - x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_3 - x_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6h)$	B III
$\mathbf{B_8}$	=	$-z_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_3 - z_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_3 - x_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6h)$	B III
$\mathbf{B_9}$	=	$-x_3\,\mathbf{a_1} - z_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_3 - z_3)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_3 + z_3)\,c\,\hat{\mathbf{z}}$	$(6h)$	B III
$\mathbf{B_{10}}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - z_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_4 - z_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6h)$	B IV
$\mathbf{B_{11}}$	=	$z_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_4 - x_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_4 - z_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6h)$	B IV
$\mathbf{B_{12}}$	=	$x_4\,\mathbf{a_1} + z_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_4 - x_4)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6h)$	B IV
$\mathbf{B_{13}}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_4 - x_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_4 - x_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6h)$	B IV
$\mathbf{B_{14}}$	=	$-z_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_4 - z_4)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_4 - x_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6h)$	B IV
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1} - z_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_4 - z_4)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_4 + z_4)\,c\,\hat{\mathbf{z}}$	$(6h)$	B IV
$\mathbf{B_{16}}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - z_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_5 - z_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6h)$	B V
$\mathbf{B_{17}}$	=	$z_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_5 - x_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_5 - z_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6h)$	B V
$\mathbf{B_{18}}$	=	$x_5\,\mathbf{a_1} + z_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_5 - x_5)\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6h)$	B V
$\mathbf{B_{19}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_5 - x_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_5 - x_5)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6h)$	B V
$\mathbf{B_{20}}$	=	$-z_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_5 - z_5)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_5 - x_5)\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(2x_5 + z_5)\,c\,\hat{\mathbf{z}}$	$(6h)$	B V

$\mathbf{B_{21}}$	=	$-x_5\,\mathbf{a_1} - z_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_5 - z_5)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_5 + z_5)\;c\,\hat{\mathbf{z}}$	(6h)	B V
$\mathbf{B_{22}}$	=	$x_6\,\mathbf{a_1} + x_6\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_6 - z_6)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_6 - z_6)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_6 + z_6)\;c\,\hat{\mathbf{z}}$	(6h)	B VI
$\mathbf{B_{23}}$	=	$z_6\,\mathbf{a_1} + x_6\,\mathbf{a_2} + x_6\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_6 - x_6)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_6 - z_6)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_6 + z_6)\;c\,\hat{\mathbf{z}}$	(6h)	B VI
$\mathbf{B_{24}}$	=	$x_6\,\mathbf{a_1} + z_6\,\mathbf{a_2} + x_6\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_6 - x_6)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_6 + z_6)\;c\,\hat{\mathbf{z}}$	(6h)	B VI
$\mathbf{B_{25}}$	=	$-x_6\,\mathbf{a_1} - x_6\,\mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_6 - x_6)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_6 - x_6)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_6 + z_6)\;c\,\hat{\mathbf{z}}$	(6h)	B VI
$\mathbf{B_{26}}$	=	$-z_6\,\mathbf{a_1} - x_6\,\mathbf{a_2} - x_6\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_6 - z_6)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_6 - x_6)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_6 + z_6)\;c\,\hat{\mathbf{z}}$	(6h)	B VI
$\mathbf{B_{27}}$	=	$-x_6\,\mathbf{a_1} - z_6\,\mathbf{a_2} - x_6\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_6 - z_6)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_6 + z_6)\;c\,\hat{\mathbf{z}}$	(6h)	B VI
$\mathbf{B_{28}}$	=	$x_7\,\mathbf{a_1} + x_7\,\mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_7 - z_7)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_7 - z_7)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_7 + z_7)\;c\,\hat{\mathbf{z}}$	(6h)	B VII
$\mathbf{B_{29}}$	=	$z_7\,\mathbf{a_1} + x_7\,\mathbf{a_2} + x_7\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_7 - x_7)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_7 - z_7)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_7 + z_7)\;c\,\hat{\mathbf{z}}$	(6h)	B VII
$\mathbf{B_{30}}$	=	$x_7\,\mathbf{a_1} + z_7\,\mathbf{a_2} + x_7\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_7 - x_7)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_7 + z_7)\;c\,\hat{\mathbf{z}}$	(6h)	B VII
$\mathbf{B_{31}}$	=	$-x_7\,\mathbf{a_1} - x_7\,\mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_7 - x_7)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_7 - x_7)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_7 + z_7)\;c\,\hat{\mathbf{z}}$	(6h)	B VII
$\mathbf{B_{32}}$	=	$-z_7\,\mathbf{a_1} - x_7\,\mathbf{a_2} - x_7\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_7 - z_7)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_7 - x_7)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_7 + z_7)\;c\,\hat{\mathbf{z}}$	(6h)	B VII
$\mathbf{B_{33}}$	=	$-x_7\,\mathbf{a_1} - z_7\,\mathbf{a_2} - x_7\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_7 - z_7)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_7 + z_7)\;c\,\hat{\mathbf{z}}$	(6h)	B VII
$\mathbf{B_{34}}$	=	$x_8\,\mathbf{a_1} + x_8\,\mathbf{a_2} + z_8\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_8 - z_8)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_8 - z_8)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_8 + z_8)\;c\,\hat{\mathbf{z}}$	(6h)	B VIII
$\mathbf{B_{35}}$	=	$z_8\,\mathbf{a_1} + x_8\,\mathbf{a_2} + x_8\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_8 - x_8)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_8 - z_8)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_8 + z_8)\;c\,\hat{\mathbf{z}}$	(6h)	B VIII
$\mathbf{B_{36}}$	=	$x_8\,\mathbf{a_1} + z_8\,\mathbf{a_2} + x_8\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_8 - x_8)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_8 + z_8)\;c\,\hat{\mathbf{z}}$	(6h)	B VIII
$\mathbf{B_{37}}$	=	$-x_8\,\mathbf{a_1} - x_8\,\mathbf{a_2} - z_8\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_8 - x_8)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_8 - x_8)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_8 + z_8)\;c\,\hat{\mathbf{z}}$	(6h)	B VIII
$\mathbf{B_{38}}$	=	$-z_8\,\mathbf{a_1} - x_8\,\mathbf{a_2} - x_8\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_8 - z_8)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_8 - x_8)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_8 + z_8)\;c\,\hat{\mathbf{z}}$	(6h)	B VIII
$\mathbf{B_{39}}$	=	$-x_8\,\mathbf{a_1} - z_8\,\mathbf{a_2} - x_8\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_8 - z_8)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_8 + z_8)\;c\,\hat{\mathbf{z}}$	(6h)	B VIII
$\mathbf{B_{40}}$	=	$x_9\,\mathbf{a_1} + x_9\,\mathbf{a_2} + z_9\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_9 - z_9)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_9 - z_9)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_9 + z_9)\;c\,\hat{\mathbf{z}}$	(6h)	B IX
$\mathbf{B_{41}}$	=	$z_9\,\mathbf{a_1} + x_9\,\mathbf{a_2} + x_9\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_9 - x_9)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_9 - z_9)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_9 + z_9)\;c\,\hat{\mathbf{z}}$	(6h)	B IX
$\mathbf{B_{42}}$	=	$x_9\,\mathbf{a_1} + z_9\,\mathbf{a_2} + x_9\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_9 - x_9)\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_9 + z_9)\;c\,\hat{\mathbf{z}}$	(6h)	B IX
$\mathbf{B_{43}}$	=	$-x_9\,\mathbf{a_1} - x_9\,\mathbf{a_2} - z_9\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_9 - x_9)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_9 - x_9)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_9 + z_9)\;c\,\hat{\mathbf{z}}$	(6h)	B IX
$\mathbf{B_{44}}$	=	$-z_9\,\mathbf{a_1} - x_9\,\mathbf{a_2} - x_9\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_9 - z_9)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_9 - x_9)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_9 + z_9)\;c\,\hat{\mathbf{z}}$	(6h)	B IX

$\mathbf{B_{45}}$	=	$-x_9\,\mathbf{a_1} - z_9\,\mathbf{a_2} - x_9\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_9 - z_9)\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_9 + z_9)\;c\,\hat{\mathbf{z}}$	$(6h)$	B IX
$\mathbf{B_{46}}$	=	$x_{10}\,\mathbf{a_1} + x_{10}\,\mathbf{a_2} + z_{10}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_{10} - z_{10})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{10} - z_{10})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_{10} + z_{10})\;c\,\hat{\mathbf{z}}$	$(6h)$	B X
$\mathbf{B_{47}}$	=	$z_{10}\,\mathbf{a_1} + x_{10}\,\mathbf{a_2} + x_{10}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_{10} - x_{10})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{10} - z_{10})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_{10} + z_{10})\;c\,\hat{\mathbf{z}}$	$(6h)$	B X
$\mathbf{B_{48}}$	=	$x_{10}\,\mathbf{a_1} + z_{10}\,\mathbf{a_2} + x_{10}\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_{10} - x_{10})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_{10} + z_{10})\;c\,\hat{\mathbf{z}}$	$(6h)$	B X
$\mathbf{B_{49}}$	=	$-x_{10}\,\mathbf{a_1} - x_{10}\,\mathbf{a_2} - z_{10}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_{10} - x_{10})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_{10} - x_{10})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_{10} + z_{10})\;c\,\hat{\mathbf{z}}$	$(6h)$	B X
$\mathbf{B_{50}}$	=	$-z_{10}\,\mathbf{a_1} - x_{10}\,\mathbf{a_2} - x_{10}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_{10} - z_{10})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_{10} - x_{10})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_{10} + z_{10})\;c\,\hat{\mathbf{z}}$	$(6h)$	B X
$\mathbf{B_{51}}$	=	$-x_{10}\,\mathbf{a_1} - z_{10}\,\mathbf{a_2} - x_{10}\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_{10} - z_{10})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_{10} + z_{10})\;c\,\hat{\mathbf{z}}$	$(6h)$	B X
$\mathbf{B_{52}}$	=	$x_{11}\,\mathbf{a_1} + x_{11}\,\mathbf{a_2} + z_{11}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_{11} - z_{11})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{11} - z_{11})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_{11} + z_{11})\;c\,\hat{\mathbf{z}}$	$(6h)$	B XI
$\mathbf{B_{53}}$	=	$z_{11}\,\mathbf{a_1} + x_{11}\,\mathbf{a_2} + x_{11}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_{11} - x_{11})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{11} - z_{11})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_{11} + z_{11})\;c\,\hat{\mathbf{z}}$	$(6h)$	B XI
$\mathbf{B_{54}}$	=	$x_{11}\,\mathbf{a_1} + z_{11}\,\mathbf{a_2} + x_{11}\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(z_{11} - x_{11})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(2x_{11} + z_{11})\;c\,\hat{\mathbf{z}}$	$(6h)$	B XI
$\mathbf{B_{55}}$	=	$-x_{11}\,\mathbf{a_1} - x_{11}\,\mathbf{a_2} - z_{11}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_{11} - x_{11})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_{11} - x_{11})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_{11} + z_{11})\;c\,\hat{\mathbf{z}}$	$(6h)$	B XI
$\mathbf{B_{56}}$	=	$-z_{11}\,\mathbf{a_1} - x_{11}\,\mathbf{a_2} - x_{11}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_{11} - z_{11})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(z_{11} - x_{11})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_{11} + z_{11})\;c\,\hat{\mathbf{z}}$	$(6h)$	B XI
$\mathbf{B_{57}}$	=	$-x_{11}\,\mathbf{a_1} - z_{11}\,\mathbf{a_2} - x_{11}\,\mathbf{a_3}$	=	$\frac{1}{\sqrt{3}}\,(x_{11} - z_{11})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(2x_{11} + z_{11})\;c\,\hat{\mathbf{z}}$	$(6h)$	B XI
$\mathbf{B_{58}}$	=	$x_{12}\,\mathbf{a_1} + y_{12}\,\mathbf{a_2} + z_{12}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_{12} - z_{12})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\;(2y_{12} - x_{12} - z_{12})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(x_{12} + y_{12} + z_{12})\;c\,\hat{\mathbf{z}}$	$(12i)$	B XII
$\mathbf{B_{59}}$	=	$z_{12}\,\mathbf{a_1} + x_{12}\,\mathbf{a_2} + y_{12}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_{12} - y_{12})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\;(2x_{12} - y_{12} - z_{12})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(x_{12} + y_{12} + z_{12})\;c\,\hat{\mathbf{z}}$	$(12i)$	B XII
$\mathbf{B_{60}}$	=	$y_{12}\,\mathbf{a_1} + z_{12}\,\mathbf{a_2} + x_{12}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(y_{12} - x_{12})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\;(2z_{12} - x_{12} - y_{12})\;a\,\hat{\mathbf{y}} + \frac{1}{3}\;(x_{12} + y_{12} + z_{12})\;c\,\hat{\mathbf{z}}$	$(12i)$	B XII
$\mathbf{B_{61}}$	=	$-y_{12}\,\mathbf{a_1} - x_{12}\,\mathbf{a_2} - z_{12}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_{12} - y_{12})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\;(y_{12} + z_{12} - 2x_{12})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(x_{12} + y_{12} + z_{12})\;c\,\hat{\mathbf{z}}$	$(12i)$	B XII
$\mathbf{B_{62}}$	=	$-x_{12}\,\mathbf{a_1} - z_{12}\,\mathbf{a_2} - y_{12}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(y_{12} - x_{12})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\;(x_{12} + y_{12} - 2z_{12})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(x_{12} + y_{12} + z_{12})\;c\,\hat{\mathbf{z}}$	$(12i)$	B XII
$\mathbf{B_{63}}$	=	$-z_{12}\,\mathbf{a_1} - y_{12}\,\mathbf{a_2} - x_{12}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(x_{12} - z_{12})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\;(x_{12} + z_{12} - 2y_{12})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(x_{12} + y_{12} + z_{12})\;c\,\hat{\mathbf{z}}$	$(12i)$	B XII
$\mathbf{B_{64}}$	=	$-x_{12}\,\mathbf{a_1} - y_{12}\,\mathbf{a_2} - z_{12}\,\mathbf{a_3}$	=	$\frac{1}{2}\;(z_{12} - x_{12})\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\;(x_{12} + z_{12} - 2y_{12})\;a\,\hat{\mathbf{y}} - \frac{1}{3}\;(x_{12} + y_{12} + z_{12})\;c\,\hat{\mathbf{z}}$	$(12i)$	B XII

$$\mathbf{B_{65}} = -z_{12}\,\mathbf{a_1} - x_{12}\,\mathbf{a_2} - y_{12}\,\mathbf{a_3} = \frac{1}{2}\,(y_{12} - z_{12})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_{12} + z_{12} - 2x_{12})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{12} + y_{12} + z_{12})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XII}$$

$$\mathbf{B_{66}} = -y_{12}\,\mathbf{a_1} - z_{12}\,\mathbf{a_2} - x_{12}\,\mathbf{a_3} = \frac{1}{2}\,(x_{12} - y_{12})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{12} + y_{12} - 2z_{12})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{12} + y_{12} + z_{12})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XII}$$

$$\mathbf{B_{67}} = y_{12}\,\mathbf{a_1} + x_{12}\,\mathbf{a_2} + z_{12}\,\mathbf{a_3} = \frac{1}{2}\,(y_{12} - z_{12})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_{12} - y_{12} - z_{12})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{12} + y_{12} + z_{12})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XII}$$

$$\mathbf{B_{68}} = x_{12}\,\mathbf{a_1} + z_{12}\,\mathbf{a_2} + y_{12}\,\mathbf{a_3} = \frac{1}{2}\,(x_{12} - y_{12})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_{12} - x_{12} - y_{12})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{12} + y_{12} + z_{12})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XII}$$

$$\mathbf{B_{69}} = z_{12}\,\mathbf{a_1} + y_{12}\,\mathbf{a_2} + x_{12}\,\mathbf{a_3} = \frac{1}{2}\,(z_{12} - x_{12})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_{12} - x_{12} - z_{12})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{12} + y_{12} + z_{12})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XII}$$

$$\mathbf{B_{70}} = x_{13}\,\mathbf{a_1} + y_{13}\,\mathbf{a_2} + z_{13}\,\mathbf{a_3} = \frac{1}{2}\,(x_{13} - z_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_{13} - x_{13} - z_{13})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{71}} = z_{13}\,\mathbf{a_1} + x_{13}\,\mathbf{a_2} + y_{13}\,\mathbf{a_3} = \frac{1}{2}\,(z_{13} - y_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_{13} - y_{13} - z_{13})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{72}} = y_{13}\,\mathbf{a_1} + z_{13}\,\mathbf{a_2} + x_{13}\,\mathbf{a_3} = \frac{1}{2}\,(y_{13} - x_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_{13} - x_{13} - y_{13})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{73}} = -y_{13}\,\mathbf{a_1} - x_{13}\,\mathbf{a_2} - z_{13}\,\mathbf{a_3} = \frac{1}{2}\,(z_{13} - y_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_{13} + z_{13} - 2x_{13})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{74}} = -x_{13}\,\mathbf{a_1} - z_{13}\,\mathbf{a_2} - y_{13}\,\mathbf{a_3} = \frac{1}{2}\,(y_{13} - x_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{13} + y_{13} - 2z_{13})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{75}} = -z_{13}\,\mathbf{a_1} - y_{13}\,\mathbf{a_2} - x_{13}\,\mathbf{a_3} = \frac{1}{2}\,(x_{13} - z_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{13} + z_{13} - 2y_{13})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{76}} = -x_{13}\,\mathbf{a_1} - y_{13}\,\mathbf{a_2} - z_{13}\,\mathbf{a_3} = \frac{1}{2}\,(z_{13} - x_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{13} + z_{13} - 2y_{13})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{77}} = -z_{13}\,\mathbf{a_1} - x_{13}\,\mathbf{a_2} - y_{13}\,\mathbf{a_3} = \frac{1}{2}\,(y_{13} - z_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_{13} + z_{13} - 2x_{13})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{78}} = -y_{13}\,\mathbf{a_1} - z_{13}\,\mathbf{a_2} - x_{13}\,\mathbf{a_3} = \frac{1}{2}\,(x_{13} - y_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{13} + y_{13} - 2z_{13})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{79}} = y_{13}\,\mathbf{a_1} + x_{13}\,\mathbf{a_2} + z_{13}\,\mathbf{a_3} = \frac{1}{2}\,(y_{13} - z_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_{13} - y_{13} - z_{13})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{80}} = x_{13}\,\mathbf{a_1} + z_{13}\,\mathbf{a_2} + y_{13}\,\mathbf{a_3} = \frac{1}{2}\,(x_{13} - y_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_{13} - x_{13} - y_{13})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{81}} = z_{13}\,\mathbf{a_1} + y_{13}\,\mathbf{a_2} + x_{13}\,\mathbf{a_3} = \frac{1}{2}\,(z_{13} - x_{13})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_{13} - x_{13} - z_{13})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{13} + y_{13} + z_{13})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIII}$$

$$\mathbf{B_{82}} = x_{14}\,\mathbf{a_1} + y_{14}\,\mathbf{a_2} + z_{14}\,\mathbf{a_3} = \frac{1}{2}\,(x_{14} - z_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_{14} - x_{14} - z_{14})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{83}} = z_{14}\,\mathbf{a_1} + x_{14}\,\mathbf{a_2} + y_{14}\,\mathbf{a_3} = \frac{1}{2}\,(z_{14} - y_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_{14} - y_{14} - z_{14})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{84}} = y_{14}\,\mathbf{a_1} + z_{14}\,\mathbf{a_2} + x_{14}\,\mathbf{a_3} = \frac{1}{2}\,(y_{14} - x_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_{14} - x_{14} - y_{14})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{85}} = -y_{14}\,\mathbf{a_1} - x_{14}\,\mathbf{a_2} - z_{14}\,\mathbf{a_3} = \frac{1}{2}\,(z_{14} - y_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_{14} + z_{14} - 2x_{14})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{86}} = -x_{14}\,\mathbf{a_1} - z_{14}\,\mathbf{a_2} - y_{14}\,\mathbf{a_3} = \frac{1}{2}\,(y_{14} - x_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{14} + y_{14} - 2z_{14})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{87}} = -z_{14}\,\mathbf{a_1} - y_{14}\,\mathbf{a_2} - x_{14}\,\mathbf{a_3} = \frac{1}{2}\,(x_{14} - z_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{14} + z_{14} - 2y_{14})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{88}} = -x_{14}\,\mathbf{a_1} - y_{14}\,\mathbf{a_2} - z_{14}\,\mathbf{a_3} = \frac{1}{2}\,(z_{14} - x_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{14} + z_{14} - 2y_{14})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{89}} = -z_{14}\,\mathbf{a_1} - x_{14}\,\mathbf{a_2} - y_{14}\,\mathbf{a_3} = \frac{1}{2}\,(y_{14} - z_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_{14} + z_{14} - 2x_{14})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{90}} = -y_{14}\,\mathbf{a_1} - z_{14}\,\mathbf{a_2} - x_{14}\,\mathbf{a_3} = \frac{1}{2}\,(x_{14} - y_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{14} + y_{14} - 2z_{14})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{91}} = y_{14}\,\mathbf{a_1} + x_{14}\,\mathbf{a_2} + z_{14}\,\mathbf{a_3} = \frac{1}{2}\,(y_{14} - z_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_{14} - y_{14} - z_{14})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{92}} = x_{14}\,\mathbf{a_1} + z_{14}\,\mathbf{a_2} + y_{14}\,\mathbf{a_3} = \frac{1}{2}\,(x_{14} - y_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_{14} - x_{14} - y_{14})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{93}} = z_{14}\,\mathbf{a_1} + y_{14}\,\mathbf{a_2} + x_{14}\,\mathbf{a_3} = \frac{1}{2}\,(z_{14} - x_{14})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_{14} - x_{14} - z_{14})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{14} + y_{14} + z_{14})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XIV}$$

$$\mathbf{B_{94}} = x_{15}\,\mathbf{a_1} + y_{15}\,\mathbf{a_2} + z_{15}\,\mathbf{a_3} = \frac{1}{2}\,(x_{15} - z_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_{15} - x_{15} - z_{15})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}} \quad (12i) \quad \text{B XV}$$

$\mathbf{B_{95}}$	=	$z_{15}\,\mathbf{a_1} + x_{15}\,\mathbf{a_2} + y_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_{15} - y_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_{15} - y_{15} - z_{15})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{96}}$	=	$y_{15}\,\mathbf{a_1} + z_{15}\,\mathbf{a_2} + x_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_{15} - x_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_{15} - x_{15} - y_{15})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{97}}$	=	$-y_{15}\,\mathbf{a_1} - x_{15}\,\mathbf{a_2} - z_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_{15} - y_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_{15} + z_{15} - 2x_{15})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{98}}$	=	$-x_{15}\,\mathbf{a_1} - z_{15}\,\mathbf{a_2} - y_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_{15} - x_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{15} + y_{15} - 2z_{15})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{99}}$	=	$-z_{15}\,\mathbf{a_1} - y_{15}\,\mathbf{a_2} - x_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_{15} - z_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{15} + z_{15} - 2y_{15})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{100}}$	=	$-x_{15}\,\mathbf{a_1} - y_{15}\,\mathbf{a_2} - z_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_{15} - x_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{15} + z_{15} - 2y_{15})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{101}}$	=	$-z_{15}\,\mathbf{a_1} - x_{15}\,\mathbf{a_2} - y_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_{15} - z_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(y_{15} + z_{15} - 2x_{15})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{102}}$	=	$-y_{15}\,\mathbf{a_1} - z_{15}\,\mathbf{a_2} - x_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_{15} - y_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(x_{15} + y_{15} - 2z_{15})\,a\,\hat{\mathbf{y}} - \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{103}}$	=	$y_{15}\,\mathbf{a_1} + x_{15}\,\mathbf{a_2} + z_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(y_{15} - z_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2x_{15} - y_{15} - z_{15})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{104}}$	=	$x_{15}\,\mathbf{a_1} + z_{15}\,\mathbf{a_2} + y_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(x_{15} - y_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2z_{15} - x_{15} - y_{15})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV
$\mathbf{B_{105}}$	=	$z_{15}\,\mathbf{a_1} + y_{15}\,\mathbf{a_2} + x_{15}\,\mathbf{a_3}$	=	$\frac{1}{2}\,(z_{15} - x_{15})\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,(2y_{15} - x_{15} - z_{15})\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,(x_{15} + y_{15} + z_{15})\,c\,\hat{\mathbf{z}}$	(12i)	B XV

References:

- D. Geist, R. Kloss, and H. Follner, *Verfeinerung des β-rhomboedrischen Bors*, Acta Crystallogr. Sect. B Struct. Sci. **26**, 1800–1802 (1970), doi:10.1107/S0567740870004910.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 61-78.

Geometry files:

- CIF: pp. S726
- POSCAR: pp. S727

CaC_6 Structure: A6B_hR7_166_g_a

Prototype	:	CaC_6
AFLOW prototype label	:	A6B_hR7_166_g_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR7
Space group number	:	166
Space group symbol	:	$R\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A6B_hR7_166_g_a [--hex]` `--params=`$a, c/a, x_2$

- Superconducting structure, T_c = 11.5K. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \tfrac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Ca
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2}x_2 + \frac{3}{4}\right)a\,\hat{\mathbf{x}} - \frac{1}{4\sqrt{3}}(1+6x_2)\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(6g)$	C
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}x_2 + \frac{1}{4}\right)a\,\hat{\mathbf{x}} - \frac{1}{4\sqrt{3}}(1-6x_2)\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(6g)$	C
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(6g)$	C
$\mathbf{B_5}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{3}{4} - \frac{1}{2}x_2\right)a\,\hat{\mathbf{x}} - \frac{1}{4\sqrt{3}}(1-6x_2)\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(6g)$	C

$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} - x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - \frac{1}{2}x_2\right)\,a\,\hat{\mathbf{x}} - \frac{1}{4\sqrt{3}}\,(1 + 6x_2)\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	(6g)	C
$\mathbf{B_7}$	=	$x_2\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	(6g)	C

References:

- N. Emery, C. Hérold, M. d'Astuto, V. Garcia, C. Bellin, J. F. Marêché, P. Lagrange, and G. Loupias, *Superconductivity of Bulk CaC6*, Phys. Rev. Lett. **95**, 087003 (2005), doi:10.1103/PhysRevLett.95.087003.

Geometry files:

- CIF: pp. S727
- POSCAR: pp. S728

Paraelectric $LiNbO_3$ Structure: ABC3_hR10_167_a_b_e

Prototype	:	$LiNbO_3$
AFLOW prototype label	:	ABC3_hR10_167_a_b_e
***Strukturbericht* designation**	:	None
Pearson symbol	:	hR10
Space group number	:	167
Space group symbol	:	$R\bar{3}c$
AFLOW prototype command	:	`aflow --proto=ABC3_hR10_167_a_b_e [--hex]` `--params=`$a, c/a, x_3$

- This is the paraelectric phase, which exists above 1430K. There is also a ferroelectric phase. Note that paraelectric $LiNbO_3$ (pp. S406) and calcite (pp. S408) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}a\,\hat{\mathbf{y}} + \frac{1}{3}c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}a\,\hat{\mathbf{y}} + \frac{1}{3}c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}a\,\hat{\mathbf{y}} + \frac{1}{3}c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\mathbf{a_1} + \frac{1}{4}\mathbf{a_2} + \frac{1}{4}\mathbf{a_3}$	=	$\frac{1}{4}c\,\hat{\mathbf{z}}$	$(2a)$	Li

$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}c\,\hat{\mathbf{z}}$	$(2a)$	Li
$\mathbf{B_3}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2b)$	Nb
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}c\,\hat{\mathbf{z}}$	$(2b)$	Nb
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\frac{1}{8}\,(1-4x_3)\;a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{8}\,(1-4x_3)\;a\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_6}$	=	$\frac{1}{4}\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \left(\frac{1}{2} - x_3\right)\mathbf{a_3}$	=	$-\frac{1}{8}\,(1-4x_3)\;a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{8}\,(1-4x_3)\;a\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,(1-4x_3)\;a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{1}{8}\,(3+4x_3)\;a\,\hat{\mathbf{x}} + \frac{1}{8\sqrt{3}}\,(1+12x_3)\;a\hat{\mathbf{y}} + \frac{5}{12}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_9}$	=	$\frac{3}{4}\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \left(\frac{1}{2} + x_3\right)\mathbf{a_3}$	=	$\frac{1}{8}\,(1-4x_3)\;a\,\hat{\mathbf{x}} - \frac{1}{8\sqrt{3}}\,(5+12x_3)\;a\hat{\mathbf{y}} + \frac{5}{12}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,(1+4x_3)\;a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\hat{\mathbf{y}} + \frac{5}{12}\,c\,\hat{\mathbf{z}}$	$(6e)$	O

References:

- H. Boysen and F. Altorfer, *A neutron powder investigation of the high-temperature structure and phase transition in* $LiNbO_3$, Acta Crystallogr. Sect. B Struct. Sci. **50**, 405–414 (1994), doi:10.1107/S0108768193012820.

Geometry files:

- CIF: pp. S728
- POSCAR: pp. S728

Calcite ($CaCO_3$, $G0_1$) Structure: ABC3_hR10_167_a_b_e

Prototype	:	$CaCO_3$
AFLOW prototype label	:	ABC3_hR10_167_a_b_e
***Strukturbericht* designation**	:	$G0_1$
Pearson symbol	:	hR10
Space group number	:	167
Space group symbol	:	$R\bar{3}c$
AFLOW prototype command	:	`aflow --proto=ABC3_hR10_167_a_b_e [--hex]` `--params=`$a, c/a, x_3$

- Strukturbericht Band I, (Ewald, 1931), pp. 292-295, gives this the designation G1, but the index in Band II, (Hermann, 1937) lists this as $G0_1$. Note that paraelectric $LiNbO_3$ (pp. S406) and calcite (pp. S408) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files. Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}c\,\hat{\mathbf{z}}$	$(2a)$	C
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}c\,\hat{\mathbf{z}}$	$(2a)$	C

$\mathbf{B_3}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2b)$	Ca
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}c\,\hat{\mathbf{z}}$	$(2b)$	Ca
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\frac{1}{8}\,(1-4x_3)\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{8}\,(1-4x_3)\,a\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_6}$	=	$\frac{1}{4}\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \left(\frac{1}{2} - x_3\right)\mathbf{a_3}$	=	$-\frac{1}{8}\,(1-4x_3)\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{8}\,(1-4x_3)\,a\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - x_3\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,(1-4x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{1}{8}\,(3+4x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{8\sqrt{3}}\,(1+12x_3)\,a\hat{\mathbf{y}} + \frac{5}{12}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_9}$	=	$\frac{3}{4}\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \left(\frac{1}{2} + x_3\right)\mathbf{a_3}$	=	$\frac{1}{8}\,(1-4x_3)\,a\,\hat{\mathbf{x}} - \frac{1}{8\sqrt{3}}\,(5+12x_3)\,a\hat{\mathbf{y}} + \frac{5}{12}\,c\,\hat{\mathbf{z}}$	$(6e)$	O
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_3\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,(1+4x_3)\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\hat{\mathbf{y}} + \frac{5}{12}\,c\,\hat{\mathbf{z}}$	$(6e)$	O

References:

- S. A. Markgraf and R. J. Reeder, *High-temperature structure refinements of calcite and magnesite*, Am. Mineral. **70**, 590–600 (1985).
- P. P. Ewald and C. Hermann, *Strukturbericht Band I, 1913-1928* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1931).
- C. Hermann, O. Lohrmann, and H. Philipp, *Strukturbericht Band II, 1928-1932* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S728
- POSCAR: pp. S729

Corundum (Al_2O_3, $D5_1$) Structure: A2B3_hR10_167_c_e

Prototype	:	Al_2O_3
AFLOW prototype label	:	A2B3_hR10_167_c_e
***Strukturbericht* designation**	:	$D5_1$
Pearson symbol	:	hR10
Space group number	:	167
Space group symbol	:	$R\bar{3}c$
AFLOW prototype command	:	`aflow --proto=A2B3_hR10_167_c_e [--hex]` `--params=`$a, c/a, x_1, x_2$

- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = -\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1 c\,\hat{\mathbf{z}}$	$(4c)$	Al
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} + \left(\frac{1}{2} - x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right) c\,\hat{\mathbf{z}}$	$(4c)$	Al
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$-x_1 c\,\hat{\mathbf{z}}$	$(4c)$	Al

$\mathbf{B_4}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}+x_1\right)\mathbf{a_2}+\left(\frac{1}{2}+x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)c\,\hat{\mathbf{z}}$	(4*c*)	Al
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}+\frac{1}{4}\mathbf{a_3}$	=	$\frac{1}{8}(4\,x_2-1)\,a\,\hat{\mathbf{x}}+\frac{\sqrt{3}}{8}(1-4x_2)\,a\hat{\mathbf{y}}+\frac{1}{4}c\,\hat{\mathbf{z}}$	(6*e*)	O
$\mathbf{B_6}$	=	$\frac{1}{4}\mathbf{a_1}+x_2\,\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$\frac{1}{8}(4x_2-1)\,a\,\hat{\mathbf{x}}-\frac{\sqrt{3}}{8}(1-4x_2)\,a\hat{\mathbf{y}}+\frac{1}{4}c\,\hat{\mathbf{z}}$	(6*e*)	O
$\mathbf{B_7}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+x_2\,\mathbf{a_3}$	=	$-\frac{1}{4}(4x_2-1)\,a\,\hat{\mathbf{x}}+\frac{1}{4}c\,\hat{\mathbf{z}}$	(6*e*)	O
$\mathbf{B_8}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+x_2\right)\mathbf{a_2}+\frac{3}{4}\mathbf{a_3}$	=	$-\frac{1}{8}(4x_2+3)\,a\,\hat{\mathbf{x}}+\frac{1}{8\sqrt{3}}(1+12x_2)\,a\hat{\mathbf{y}}+\frac{5}{12}c\,\hat{\mathbf{z}}$	(6*e*)	O
$\mathbf{B_9}$	=	$\frac{3}{4}\mathbf{a_1}-x_2\,\mathbf{a_2}+\left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$-\frac{1}{8}(4x_2-1)\,a\,\hat{\mathbf{x}}-\frac{1}{8\sqrt{3}}(5+12x_2)\,a\hat{\mathbf{y}}+\frac{5}{12}c\,\hat{\mathbf{z}}$	(6*e*)	O
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}-x_2\,\mathbf{a_3}$	=	$\frac{1}{4}(4x_2+1)\,a\,\hat{\mathbf{x}}+\frac{1}{2\sqrt{3}}a\hat{\mathbf{y}}+\frac{5}{12}c\,\hat{\mathbf{z}}$	(6*e*)	O

References:

- L. W. Finger and R. M. Hazen, *Crystal structure and compression of ruby to 46 kbar*, J. Appl. Phys. **49**, 5823–5826 (1978), doi:10.1063/1.324598.

Geometry files:

- CIF: pp. S729
- POSCAR: pp. S730

Mg_2Ni (C_a) Structure: A2B_hP18_180_fi_bd

Prototype	:	Mg_2Ni
AFLOW prototype label	:	A2B_hP18_180_fi_bd
***Strukturbericht* designation**	:	C_a
Pearson symbol	:	hP18
Space group number	:	180
Space group symbol	:	$P6_222$
AFLOW prototype command	:	`aflow --proto=A2B_hP18_180_fi_bd` `--params=`$a, c/a, z_3, x_4$

Other compounds with this structure:

- $CuMg_4Ni$

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3b)$	Ni I
$\mathbf{B_2}$	=	$\frac{1}{6}\,\mathbf{a_3}$	=	$\frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(3b)$	Ni I
$\mathbf{B_3}$	=	$\frac{5}{6}\,\mathbf{a_3}$	=	$\frac{5}{6}\,c\,\hat{\mathbf{z}}$	$(3b)$	Ni I

$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3d)$	Ni II
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{6}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(3d)$	Ni II
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{5}{6}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{5}{6}\,c\,\hat{\mathbf{z}}$	$(3d)$	Ni II
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_1} + z_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(6f)$	Mg I
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_2} + \left(\frac{2}{3} + z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} + z_3\right)\,c\,\hat{\mathbf{z}}$	$(6f)$	Mg I
$\mathbf{B_9}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \left(\frac{1}{3} + z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{3} + z_3\right)\,c\,\hat{\mathbf{z}}$	$(6f)$	Mg I
$\mathbf{B_{10}}$	=	$\frac{1}{2}\,\mathbf{a_1} - z_3\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(6f)$	Mg I
$\mathbf{B_{11}}$	=	$\frac{1}{2}\,\mathbf{a_2} + \left(\frac{2}{3} - z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{2}{3} - z_3\right)\,c\,\hat{\mathbf{z}}$	$(6f)$	Mg I
$\mathbf{B_{12}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \left(\frac{1}{3} - z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{3} - z_3\right)\,c\,\hat{\mathbf{z}}$	$(6f)$	Mg I
$\mathbf{B_{13}}$	=	$x_4\,\mathbf{a_1} + 2x_4\,\mathbf{a_2}$	=	$\frac{3}{2}\,x_4\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}}$	$(6i)$	Mg II
$\mathbf{B_{14}}$	=	$-2x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \frac{2}{3}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_4\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \frac{2}{3}\,c\,\hat{\mathbf{z}}$	$(6i)$	Mg II
$\mathbf{B_{15}}$	=	$x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \frac{1}{3}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_4\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$	$(6i)$	Mg II
$\mathbf{B_{16}}$	=	$-x_4\,\mathbf{a_1} - 2x_4\,\mathbf{a_2}$	=	$-\frac{3}{2}\,x_4\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}}$	$(6i)$	Mg II
$\mathbf{B_{17}}$	=	$2x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \frac{2}{3}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_4\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \frac{2}{3}\,c\,\hat{\mathbf{z}}$	$(6i)$	Mg II
$\mathbf{B_{18}}$	=	$-x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \frac{1}{3}\,\mathbf{a_3}$	=	$\sqrt{3}\,x_4\,a\,\hat{\mathbf{y}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$	$(6i)$	Mg II

References:

- J. Schefer, P. Fischer, W. Hälg, F. Stucki, L. Schlapbach, J. J. Didisheim, K. Yvon, and A. F. Andresen, *New structure results for hydrides and deuterides of the hydrogen storage material Mg_2Ni*, J. Less-Common Met. **74**, 65–73 (1980), doi:10.1016/0022-5088(80)90074-0.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S730
- POSCAR: pp. S730

$CrSi_2$ (C40) Structure: AB2_hP9_180_d_j

Prototype	:	$CrSi_2$
AFLOW prototype label	:	AB2_hP9_180_d_j
***Strukturbericht* designation**	:	C40
Pearson symbol	:	hP9
Space group number	:	180
Space group symbol	:	$P6_222$
AFLOW prototype command	:	`aflow --proto=AB2_hP9_180_d_j` `--params=`$a, c/a, x_2$

Other compounds with this structure:

- Ge_2Ta, Ge_2V, $HfSn_2$, Ge_2Nb, $MoSi_2$, Si_2Ta, Si_2V, Si_2W

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3d)$	Cr

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{6}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	(3*d*)	Cr
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{5}{6}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{5}{6}\,c\,\hat{\mathbf{z}}$	(3*d*)	Cr
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + 2x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(6*j*)	Si
$\mathbf{B_5}$	=	$-2x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{6}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	(6*j*)	Si
$\mathbf{B_6}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{5}{6}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_2\,a\,\hat{\mathbf{y}} + \frac{5}{6}\,c\,\hat{\mathbf{z}}$	(6*j*)	Si
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} - 2x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	(6*j*)	Si
$\mathbf{B_8}$	=	$2x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{6}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	(6*j*)	Si
$\mathbf{B_9}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{5}{6}\,\mathbf{a_3}$	=	$\sqrt{3}\,x_2\,a\,\hat{\mathbf{y}} + \frac{5}{6}\,c\,\hat{\mathbf{z}}$	(6*j*)	Si

References:

- T. Dasgupta, J. Etourneau, B. Chevalier, S. F. Matar, and A. M. Umarji, *Structural, thermal, and electrical properties of $CrSi_2$*, J. Appl. Phys. **103**, 113516 (2008), doi:10.1063/1.2917347.

Geometry files:

- CIF: pp. S730
- POSCAR: pp. S731

β-Quartz (SiO_2, C8): A2B_hP9_180_j_c

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_hP9_180_j_c
***Strukturbericht* designation**	:	C8
Pearson symbol	:	hP9
Space group number	:	180
Space group symbol	:	$P6_222$
AFLOW prototype command	:	`aflow --proto=A2B_hP9_180_j_c` `--params=`$a, c/a, x_2$

- This is the high-temperature phase of α-quartz.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}}$	$(3c)$	Si
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{2}{3}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{2}{3}\,c\,\hat{\mathbf{z}}$	$(3c)$	Si
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{3}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{3}\,c\,\hat{\mathbf{z}}$	$(3c)$	Si
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + 2x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6j)$	O
$\mathbf{B_5}$	=	$-2x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{6}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(6j)$	O
$\mathbf{B_6}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{5}{6}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_2\,a\,\hat{\mathbf{y}} + \frac{5}{6}\,c\,\hat{\mathbf{z}}$	$(6j)$	O
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} - 2x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6j)$	O
$\mathbf{B_8}$	=	$2x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{6}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{6}\,c\,\hat{\mathbf{z}}$	$(6j)$	O
$\mathbf{B_9}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{5}{6}\,\mathbf{a_3}$	=	$\sqrt{3}\,x_2\,a\,\hat{\mathbf{y}} + \frac{5}{6}\,c\,\hat{\mathbf{z}}$	$(6j)$	O

References:

- A. F. Wright and M. S. Lehmann, *The Structure of Quartz at 25 and 590°C Determined by Neutron Diffraction*, J. Solid State Chem. **36**, 371–380 (1981), doi:10.1016/0022-4596(81)90449-7.

Geometry files:

- CIF: pp. S731
- POSCAR: pp. S731

Bainite (Fe_3C) Structure: AB3_hP8_182_c_g

Prototype	:	Fe_3C
AFLOW prototype label	:	AB3_hP8_182_c_g
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP8
Space group number	:	182
Space group symbol	:	$P6_322$
AFLOW prototype command	:	`aflow --proto=AB3_hP8_182_c_g --params=`$a, c/a, x_2$

- Strictly speaking, bainite is a microstructure. However, (Villars, 1991) Vol. II, pp. 1894, refers to this crystal structure as upper bainite, and (Villars, 2014) refers to this as bainite.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	C
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	C
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1}$	=	$\frac{1}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\hat{\mathbf{y}}$	$(6g)$	Fe
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_2}$	=	$\frac{1}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\hat{\mathbf{y}}$	$(6g)$	Fe
$\mathbf{B_5}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}}$	$(6g)$	Fe
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$-\frac{1}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	Fe
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-\frac{1}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	Fe
$\mathbf{B_8}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$+x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	Fe

References:

- M. Reibold, A. A. Levin, D. C. Meyer, P. Paufler, and W. Kochmann, *Microstructure of a Damascene sabre after annealing*, Int. J. Mater. Res. **97**, 1172–1182 (2006), doi:10.3139/146.101355.
- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S731
- POSCAR: pp. S731

Buckled Graphite Structure: A_hP4_186_ab

Prototype	:	C
AFLOW prototype label	:	A_hP4_186_ab
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP4
Space group number	:	186
Space group symbol	:	$P6_3mc$
AFLOW prototype command	:	`aflow --proto=A_hP4_186_ab` `--params=`$a, c/a, z_1, z_2$

- According to (Wyckoff, 1963), hexagonal graphite may be either flat, space group $P6_3/mmc$ (#194) or buckled, space group $P6_3mc$ (#186). "If it is buckled, the buckling parameter is small, less than 1/20 of the 'c' parameter of the hexagonal unit cell." We will assign the A9 *Strukturbericht* designation to the unbuckled structure. Experimentally, a rhombohedral ($R\bar{3}m$) graphite structure is also observed. In the pictures above we give z_2 the exaggerated value of 0.1 When $z_2 = 0$, this structure is equivalent to unbuckled (A9) hexagonal graphite.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	C I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} + z_1\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + z_1\right)\,c\,\hat{\mathbf{z}}$	$(2a)$	C I

$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	C II
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	$(2b)$	C II

References:

- A. W. Hull, *A New Method of X-Ray Crystal Analysis*, Phys. Rev. **10**, 661–696 (1917), doi:10.1103/PhysRev.10.661.

Found in:

- R. W. G. Wyckoff, *Crystal Structures Vol. 1* (Wiley, 1963), 2nd edn, pp. 254.

Geometry files:

- CIF: pp. S732
- POSCAR: pp. S732

Moissanite-4H SiC (B5) Structure: AB_hP8_186_ab_ab

Prototype	:	SiC
AFLOW prototype label	:	AB_hP8_186_ab_ab
***Strukturbericht* designation**	:	B5
Pearson symbol	:	hP8
Space group number	:	186
Space group symbol	:	$P6_3mc$
AFLOW prototype command	:	`aflow --proto=AB_hP8_186_ab_ab` `--params=`$a, c/a, z_1, z_2, z_3, z_4$

- This is one possible stacking (ABAC) for tetrahedral structures. Compare this to zincblende (ABCABC), wurtzite (ABABAB), 6H (ABCACB), and 9R (ABCBCACAB). The 4H refers to the fact that there are 4 CSi dimers in a hexagonal unit cell. Zincblende is denoted 3C, and wurtzite is 2H. This structure is related to the α-La (A3') structure in the same way that zincblende (B3) is related to the fcc (A1) lattice. Without loss of generality, we can take any of the z_i to be zero. In the pictures here we take $z_1 = 0$.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	C I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} + z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + z_1\right)c\,\hat{\mathbf{z}}$	$(2a)$	C I

$\mathbf{B_3}$	=	$z_2\,\mathbf{a_3}$	=	$z_2\,c\,\hat{\mathbf{z}}$	$(2a)$	Si I
$\mathbf{B_4}$	=	$\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	$(2a)$	Si I
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1}+\frac{2}{3}\,\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}+\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	$(2b)$	C II
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1}+\frac{1}{3}\,\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}-\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	$(2b)$	C II
$\mathbf{B_7}$	=	$\frac{1}{3}\,\mathbf{a_1}+\frac{2}{3}\,\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}+\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+z_4\,c\,\hat{\mathbf{z}}$	$(2b)$	Si II
$\mathbf{B_8}$	=	$\frac{2}{3}\,\mathbf{a_1}+\frac{1}{3}\,\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}-\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\,\hat{\mathbf{z}}$	$(2b)$	Si II

References:

- A. Bauer, P. Reischauer, J. Kräusslich, N. Schell, W. Matz, and K. Goetz, *Structure refinement of the silicon carbide polytypes 4H and 6H: unambiguous determination of the refinement parameters*, Acta Crystallogr. Sect. A **57**, 60–67 (2001), doi:10.1107/S0108767300012915.

Geometry files:

- CIF: pp. S732
- POSCAR: pp. S732

Wurtzite (ZnS, B4) Structure: AB_hP4_186_b_b

Prototype	:	ZnS
AFLOW prototype label	:	AB_hP4_186_b_b
***Strukturbericht* designation**	:	B4
Pearson symbol	:	hP4
Space group number	:	186
Space group symbol	:	$P6_3mc$
AFLOW prototype command	:	`aflow --proto=AB_hP4_186_b_b` `--params=`$a, c/a, z_1, z_2$

Other compounds with this structure:

- ZnO, SiC, AlN, CdSe, BN, C (hexagonal diamond)

- This is the hexagonal analog of the zincblende lattice, i.e. the stacking of the ZnS dimers is ABABAB... Replacing both the Zn and S atoms by C (or Si) gives the hexagonal diamond structure. The "ideal" structure, where the nearest-neighbor environment of each atom is the same as in zincblende, is achieved when we take $c/a = \sqrt{8/3}$ and $z_2 = 1/8$. In the extreme case $z_2 = 1/2$ this structure becomes the B_k (BN) structure. Note that we have arbitrarily chosen the z_1 parameter for the zinc atoms to be zero.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	(2*b*)	S
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)\,c\,\hat{\mathbf{z}}$	(2*b*)	S
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	(2*b*)	Zn
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	(2*b*)	Zn

References:

- E. H. Kisi and M. M. Elcombe, *u parameters for the wurtzite structure of ZnS and ZnO using powder neutron diffraction*, Acta Crystallogr. C **45**, 1867–1870 (1989), doi:10.1107/S0108270189004269.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S733
- POSCAR: pp. S733

Moissanite-6H SiC (B6) Structure: AB_hP12_186_a2b_a2b

Prototype	:	SiC
AFLOW prototype label	:	AB_hP12_186_a2b_a2b
***Strukturbericht* designation**	:	B6
Pearson symbol	:	hP12
Space group number	:	186
Space group symbol	:	$P6_3mc$
AFLOW prototype command	:	`aflow --proto=AB_hP12_186_a2b_a2b` `--params=`$a, c/a, z_1, z_2, z_3, z_4, z_5, z_6$

- This is an alternate stacking (ABCACB) for tetrahedral structures. Compare this to zincblende (ABCABC), moissanite-4H (ABAC), and wurtzite (ABABAB). The 6H refers to the fact that there are 6 CSi dimers in a hexagonal unit cell. Zincblende is denoted 3C, and wurtzite is 2H. Without loss of generality, we can take any of the z_i to be zero. In the pictures here we take $z_1 = 0$.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	C I
$\mathbf{B_2}$	=	$\left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_1\right)c\,\hat{\mathbf{z}}$	$(2a)$	C I
$\mathbf{B_3}$	=	$z_2\,\mathbf{a_3}$	=	$z_2\,c\,\hat{\mathbf{z}}$	$(2a)$	Si I
$\mathbf{B_4}$	=	$\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	$(2a)$	Si I
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1}+\frac{2}{3}\,\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}+\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+z_3\,c\,\hat{\mathbf{z}}$	$(2b)$	C II

$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\hat{\mathbf{z}}$	(2*b*)	C II
$\mathbf{B_7}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	(2*b*)	C III
$\mathbf{B_8}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	(2*b*)	C III
$\mathbf{B_9}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	(2*b*)	Si II
$\mathbf{B_{10}}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)\,c\,\hat{\mathbf{z}}$	(2*b*)	Si II
$\mathbf{B_{11}}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	(2*b*)	Si III
$\mathbf{B_{12}}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)\,c\,\hat{\mathbf{z}}$	(2*b*)	Si III

References:

- A. Bauer, P. Reischauer, J. Kräusslich, N. Schell, W. Matz, and K. Goetz, *Structure refinement of the silicon carbide polytypes 4H and 6H: unambiguous determination of the refinement parameters*, Acta Crystallogr. Sect. A **57**, 60–67 (2001), doi:10.1107/S0108767300012915.

Geometry files:

- CIF: pp. S733
- POSCAR: pp. S733

Al_5C_3N ($E9_4$) Structure: A5B3C_hP18_186_2a3b_2ab_b

Prototype	:	Al_5C_3N
AFLOW prototype label	:	A5B3C_hP18_186_2a3b_2ab_b
***Strukturbericht* designation**	:	$E9_4$
Pearson symbol	:	hP18
Space group number	:	186
Space group symbol	:	$P6_3mc$
AFLOW prototype command	:	`aflow --proto=A5B3C_hP18_186_2a3b_2ab_b` `--params=`$a, c/a, z_1, z_2, z_3, z_4, z_5, z_6, z_7, z_8, z_9$

- Since space group #186 has no $z = 0$ mirror plane, we are free to uniformly shift the z coordinates of the atoms. We have done this so that the first carbon atom is at the origin.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	Al I
$\mathbf{B_2}$	=	$\left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_1\right)c\,\hat{\mathbf{z}}$	$(2a)$	Al I
$\mathbf{B_3}$	=	$z_2\,\mathbf{a_3}$	=	$z_2\,c\,\hat{\mathbf{z}}$	$(2a)$	Al II
$\mathbf{B_4}$	=	$\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	$(2a)$	Al II
$\mathbf{B_5}$	=	$z_3\,\mathbf{a_3}$	=	$z_3\,c\,\hat{\mathbf{z}}$	$(2a)$	C I
$\mathbf{B_6}$	=	$\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	$(2a)$	C I
$\mathbf{B_7}$	=	$z_4\,\mathbf{a_3}$	=	$z_4\,c\,\hat{\mathbf{z}}$	$(2a)$	C II
$\mathbf{B_8}$	=	$\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_4\right)c\,\hat{\mathbf{z}}$	$(2a)$	C II

$\mathbf{B_9}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_5\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(2b)$	Al III
$\mathbf{B_{10}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)\,c\,\hat{\mathbf{z}}$	$(2b)$	Al III
$\mathbf{B_{11}}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_6\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_6\,c\,\hat{\mathbf{z}}$	$(2b)$	Al IV
$\mathbf{B_{12}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \left(\frac{1}{2} + z_6\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_6\right)\,c\,\hat{\mathbf{z}}$	$(2b)$	Al IV
$\mathbf{B_{13}}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_7\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_7\,c\,\hat{\mathbf{z}}$	$(2b)$	Al V
$\mathbf{B_{14}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \left(\frac{1}{2} + z_7\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_7\right)\,c\,\hat{\mathbf{z}}$	$(2b)$	Al V
$\mathbf{B_{15}}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_8\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_8\,c\,\hat{\mathbf{z}}$	$(2b)$	C III
$\mathbf{B_{16}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \left(\frac{1}{2} + z_8\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_8\right)\,c\,\hat{\mathbf{z}}$	$(2b)$	C III
$\mathbf{B_{17}}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_9\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_9\,c\,\hat{\mathbf{z}}$	$(2b)$	N
$\mathbf{B_{18}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \left(\frac{1}{2} + z_9\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_9\right)\,c\,\hat{\mathbf{z}}$	$(2b)$	N

References:

- G. A. Jeffrey and V. Y. Wu, *The structure of the aluminum carbonitrides. II*, Acta Cryst. **20**, 538–547 (1966), doi:10.1107/S0365110X66001208.

Found in:

- P. Villars, K. Cenzual, J. Daams, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, N. Melnichenko-Koblyuk, O. Pavlyuk, I. Savesyuk, S. Stoiko, and L. Sysa, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag Berlin Heidelberg, 2006). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S733
- POSCAR: pp. S734

Original BN (B12) Structure: AB_hP4_186_b_a

Prototype	:	BN
AFLOW prototype label	:	AB_hP4_186_b_a
***Strukturbericht* designation**	:	B12
Pearson symbol	:	hP4
Space group number	:	186
Space group symbol	:	$P6_3mc$
AFLOW prototype command	:	`aflow --proto=AB_hP4_186_b_a` `--params=`$a, c/a, z_1, z_2$

- This is the BN structure found in (Ewald, 1931) pp. 95 and (Wilson, 1961) pp. 125-126. (Pease, 1950) later determined that the true boron nitride structure is what is now known as the B_k structure. We leave this structure here for historical reasons. Note that it is crystallographically equivalent to the buckled graphite structure.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2a)$	N
$\mathbf{B_2}$	=	$\left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_1\right)c\,\hat{\mathbf{z}}$	$(2a)$	N
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1}+\frac{2}{3}\,\mathbf{a_2}+z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}+\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+z_2\,c\,\hat{\mathbf{z}}$	$(2b)$	B
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1}+\frac{1}{3}\,\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}-\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)c\,\hat{\mathbf{z}}$	$(2b)$	B

References:

- A. Brager, *X-ray examination of the structure of boron nitride*, Acta Physicochimica URSS **7**, 699–706 (1937).
- R. S. Pease, *Crystal Structure of Boron Nitride*, Nature **165**, 722–723 (1950), doi:10.1038/165722b0.
- P. P. Ewald and C. Hermann, *Strukturbericht Band I, 1913-1928* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1931).
- A. J. C. Wilson, *Structure Reports Vol. 18: Structure Reports for 1947-1948* (N.V.A. Oosthoek's Uitgevers, Utrecht, 1961).

Geometry files:

- CIF: pp. S734
- POSCAR: pp. S734

BaPtSb Structure: ABC_hP3_187_a_d_f

Prototype	:	BaPtSb
AFLOW prototype label	:	ABC_hP3_187_a_d_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP3
Space group number	:	187
Space group symbol	:	$P\bar{6}m2$
AFLOW prototype command	:	`aflow --proto=ABC_hP3_187_a_d_f` `--params=`$a, c/a$

Other compounds with this structure:

- AsKZn, PtSbSr, DyPPt, GdPPt, KSbZn, LuPPt, PPtSm, PPtTb, PPtTm, PPtY, PPtYb

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Ba
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1d)$	Pt
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1f)$	Sb

References:

- G. Wenski and A. Mewis, *Trigonal-planar koordiniertes Platin: Darstellung und Struktur von SrPtAs (Sb), BaPtP (As, Sb), $SrPt_xP_{2-x}$, $SrPt_xAs_{0.90}$ und $BaPt_xAs_{0.90}$*, Z. Anorg. Allg. Chem. **535**, 110–122 (1986), doi:10.1002/zaac.19865350413.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S734
- POSCAR: pp. S735

Tungsten Carbide (B_h) Structure: AB_hP2_187_d_a

Prototype	:	WC
AFLOW prototype label	:	AB_hP2_187_d_a
***Strukturbericht* designation**	:	B_h
Pearson symbol	:	hP2
Space group number	:	187
Space group symbol	:	$P\bar{6}m2$
AFLOW prototype command	:	`aflow --proto=AB_hP2_187_d_a --params=`$a, c/a$

Other compounds with this structure:

- AlSn, BIr, MoC, MoP, NbS, WN, TaS, TiS, TeZr

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	W
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1d)$	C

References:

- J. Leciejewicz, *A note on the structure of tungsten carbide*, Acta Cryst. **14**, 200 (1961), doi:10.1107/S0365110X6100067X.

Found in:

- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 479.

Geometry files:

- CIF: pp. S735
- POSCAR: pp. S735

Revised Fe_2P (C22) Crystal Structure: A2B_hP9_189_fg_bc

Prototype	:	Fe_2P
AFLOW prototype label	:	A2B_hP9_189_fg_bc
***Strukturbericht* designation**	:	C22
Pearson symbol	:	hP9
Space group number	:	189
Space group symbol	:	$P\bar{6}2m$
AFLOW prototype command	:	`aflow --proto=A2B_hP9_189_fg_bc` `--params=`$a, c/a, x_3, x_4$

Other compounds with this structure:

- AgAsCa, AgSiYb, AlCoPu, AlCuTm, AlNiTb, FeNiP, FeGaU, Mn_2P, Ni_2P, Ni_6Si_2B, Pt_2Si, RhSnZr, hundreds more

- This is not the structure given in (Hermann, 1937) Strukturbericht Vol. II, pp. 95. As noted by (Wyckoff, 1963) pp. 360, the structure which was "generally accepted for years, has recently been shown to be incorrect". This is the corrected structure, as given in Wyckoff and (Villars, 1991). See the original Fe_2P (C22) page for the Strukturbericht version of this crystal.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	P I
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}$	$(2c)$	P II
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}$	$(2c)$	P II
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1}$	=	$\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}}$	$(3f)$	Fe I
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_2}$	=	$\frac{1}{2}\,x_3\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}}$	$(3f)$	Fe I
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2}$	=	$-x_3\,a\,\hat{\mathbf{x}}$	$(3f)$	Fe I
$\mathbf{B_7}$	=	$x_4\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_4\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3g)$	Fe II
$\mathbf{B_8}$	=	$x_4\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,x_4\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_4\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3g)$	Fe II
$\mathbf{B_9}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3g)$	Fe II

References:

- H. Fujii, S. Komura, T. Takeda, T. Okamoto, Y. Ito, and J. Akimitsu, *Polarized Neutron Diffraction Study of Fe_2P Single Crystal*, J. Phys. Soc. Jpn. **46**, 1616–1621 (1979), doi:10.1143/JPSJ.46.1616.
- C. Hermann, O. Lohrmann, and H. Philipp, *Strukturbericht Band II, 1928-1932* (Akademsiche Verlagsgesellschaft M. B. H., Leipzig, 1937).
- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn.

Found in:

- R. W. G. Wyckoff, *Crystal Structures Vol. 1* (Wiley, 1963), 2nd edn, pp. 360.

Geometry files:

- CIF: pp. S735
- POSCAR: pp. S736

AlB_4Mg Structure: AB4C_hP6_191_a_h_b

Prototype	:	AlB_4Mg
AFLOW prototype label	:	AB4C_hP6_191_a_h_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP6
Space group number	:	191
Space group symbol	:	P6/mmm
AFLOW prototype command	:	`aflow --proto=AB4C_hP6_191_a_h_b --params=`$a, c/a, z_3$

- Note that Table I of (Margadonna, 2002) mislabels the (1a) and (1b) Wyckoff positions.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Al
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	Mg
$\mathbf{B_3}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4h)$	B
$\mathbf{B_4}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4h)$	B

$\mathbf{B_5}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4h)$	B
$\mathbf{B_6}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4h)$	B

References:

- S. Margadonna, K. Prassides, I. Arvanitidis, M. Pissas, G. Papavassiliou, and A. N. Fitch, *Crystal structure of the $Mg_{1-x}Al_xB_2$ superconductors near $x \approx 0.5$*, Phys. Rev. B **66**, 014518 (2002), doi:10.1103/PhysRevB.66.014518.

Geometry files:

- CIF: pp. S736
- POSCAR: pp. S736

$CaCu_5$ ($D2_d$) Structure: AB5_hP6_191_a_cg

Prototype	:	$CaCu_5$
AFLOW prototype label	:	AB5_hP6_191_a_cg
***Strukturbericht* designation**	:	$D2_d$
Pearson symbol	:	hP6
Space group number	:	191
Space group symbol	:	P6/mmm
AFLOW prototype command	:	`aflow --proto=AB5_hP6_191_a_cg --params=`$a, c/a$

Other compounds with this structure:

- Au_5Sr, Ag_3Al_2La, Ag_5Ba, $CePt_5$, Co_5Sm, Co_5Tb, Co_5Y, $EuZn_5$, $GdRh_5$, Ir_5Nd, $LaNi_5$, $SmZn_5$, many others

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Ca
$\mathbf{B_2}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}$	$(2c)$	Cu I
$\mathbf{B_3}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}$	$(2c)$	Cu I
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3g)$	Cu II
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3g)$	Cu II
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(3g)$	Cu II

References:

- W. Haucke, *Kristallstruktur von $CaZn_5$ und $CaCu_5$*, Z. Anorg. Allg. Chem. **244**, 17–22 (1940), doi:10.1002/zaac.19402440103.

Found in:

- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 645.

Geometry files:

- CIF: pp. S736
- POSCAR: pp. S737

Simple Hexagonal Lattice (A_f): A_hP1_191_a

Prototype	:	γ-$HgSn_{6-10}$
AFLOW prototype label	:	A_hP1_191_a
***Strukturbericht* designation**	:	A_f
Pearson symbol	:	hP1
Space group number	:	191
Space group symbol	:	P6/mmm
AFLOW prototype command	:	`aflow --proto=A_hP1_191_a --params=`$a, c/a$

Other compounds with this structure:

- Si (metastable) disordered phases of BiIn, $CdSn_{19}$, In_7Sb_3, InSb

- Unlike the simple cubic lattice, there are no elements which take this structure as the ground state. There is a metastable silicon phase with this structure. The prototype state is a mercury-tin alloy. Thus the atom type "M" represents an average of Hg and Sn atoms.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	M

References:

- G. V. Raynor and J. A. Lee, *The tin-rich intermediate phases in the alloys of tin with cadmium, indium and mercury*, Acta Metallurgica **2**, 616–620 (1954), doi:10.1016/0001-6160(54)90197-2.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 3947.

Geometry files:

- CIF: pp. S737
- POSCAR: pp. S737

Li_3N Structure: A3B_hP4_191_bc_a

Prototype	:	Li_3N
AFLOW prototype label	:	A3B_hP4_191_bc_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP4
Space group number	:	191
Space group symbol	:	P6/mmm
AFLOW prototype command	:	`aflow --proto=A3B_hP4_191_bc_a --params=`$a, c/a$

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	N
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(1b)$	Li I
$\mathbf{B_3}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}$	$(2c)$	Li II
$\mathbf{B_4}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}$	$(2c)$	Li II

References:

- D. H. Gregory, P. M. O'Meara, A. G. Gordon, J. P. Hodges, S. Short, and J. D. Jorgensen, *Structure of Lithium Nitride and Transition-Metal-Doped Derivatives, $Li_{3-x-y}M_xN$ (M = Ni, Cu): A Powder Neutron Diffraction Study*, Chem. Mater. **14**, 2063–2070 (2002), doi:10.1021/cm010718t.

Found in:

- P. Villars, K. Cenzual, J. Daams, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, N. Melnichenko-Koblyuk, O. Pavlyuk, I. Savesyuk, S. Stoiko, and L. Sysa, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag Berlin Heidelberg, 2006). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S737
- POSCAR: pp. S738

Hexagonal ω (C32) Structure: AB2_hP3_191_a_d

Prototype	:	AlB_2
AFLOW prototype label	:	AB2_hP3_191_a_d
***Strukturbericht* designation**	:	C32
Pearson symbol	:	hP3
Space group number	:	191
Space group symbol	:	P6/mmm
AFLOW prototype command	:	`aflow --proto=AB2_hP3_191_a_d --params=`$a, c/a$

Other compounds with this structure:

- Ti (metastable), MgB_2, Be_2Hf, $CeHg_2$

- This is the hexagonal ω phase. There is also a trigonal ω (C6) phase. For more details about the ω phase and materials which form in the ω phase, see (Sikka, 1982). Most ω phase intermetallic alloys are disordered. In this structure the B-B distance is smaller than the Al-B distance for every c/a ratio. If c/a is small enough the structure looks like a set of inter-penetrating boron triangular planes and aluminium chains. If $c/a = 1/\sqrt{3}$ the Al-Al distance along (001) is the same as the B-B distance in the plane, and, for that matter, the B-B distance in the (001) direction. This value 0.577 is close to the value $\sqrt{3/8}$ (≈ 0.612) where the trigonal ω phase can transform to the body-centered cubic (A2) lattice, which probably explains the close connection between the ω and bcc phases.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Al
$\mathbf{B_2}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2d)$	B
$\mathbf{B_3}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2d)$	B

References:

- U. Burkhardt, V. Gurin, F. Haarmann, H. Borrmann, W. Schnelle, A. Yaresko, and Y. Grin, *On the electronic and structural properties of aluminum diboride* $Al_{0.9}B_2$, J. Solid State Chem. **177**, 389–394 (2004), doi:10.1016/j.jssc.2002.12.001.
- S. K. Sikka, Y. K. Vohra, and R. Chidambaram, *Omega phase in materials*, Prog. Mater. Sci. **27**, 245–310 (1982), doi:10.1016/0079-6425(82)90002-0.

Geometry files:

- CIF: pp. S738
- POSCAR: pp. S738

Cu_2Te (C_h) Structure: A2B_hP6_191_h_e

Prototype	:	Cu_2Te
AFLOW prototype label	:	A2B_hP6_191_h_e
***Strukturbericht* designation**	:	C_h
Pearson symbol	:	hP6
Space group number	:	191
Space group symbol	:	P6/mmm
AFLOW prototype command	:	`aflow --proto=A2B_hP6_191_h_e` `--params=`$a, c/a, z_1, z_2$

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(2e)$	Te
$\mathbf{B_2}$	=	$-z_1\,\mathbf{a_3}$	=	$-z_1\,c\,\hat{\mathbf{z}}$	$(2e)$	Te
$\mathbf{B_3}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4h)$	Cu
$\mathbf{B_4}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4h)$	Cu

$\mathbf{B_5}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(4*h*)	Cu
$\mathbf{B_6}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	(4*h*)	Cu

References:

- H. Nowotny, *Die Kristallstruktur von Cu_2Te*, Z. Metallkd. **37**, 40–42 (1946).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 3014.

Geometry files:

- CIF: pp. S738
- POSCAR: pp. S739

CoSn (B35) Structure: AB_hP6_191_f_ad

Prototype	:	CoSn
AFLOW prototype label	:	AB_hP6_191_f_ad
***Strukturbericht* designation**	:	B35
Pearson symbol	:	hP6
Space group number	:	191
Space group symbol	:	P6/mmm
AFLOW prototype command	:	`aflow --proto=AB_hP6_191_f_ad --params=`$a, c/a$

Other compounds with this structure:

- FeGe, PbRh, NTa, PtTl, InNi, OTi_2

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Sn I
$\mathbf{B_2}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2d)$	Sn II
$\mathbf{B_3}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2d)$	Sn II
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}}$	$(3f)$	Co
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}}$	$(3f)$	Co
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(3f)$	Co

References:

- A. K. Larsson, M. Haeberlein, S. Lidin, and U. Schwarz, *Single crystal structure refinement and high-pressure properties of CoSn*, J. Alloys Compd. **240**, 79–84 (1996), doi:10.1016/0925-8388(95)02189-2.

Geometry files:

- CIF: pp. S739
- POSCAR: pp. S739

AsTi (B_i) Structure: AB_hP8_194_ad_f

Prototype	:	AsTi
AFLOW prototype label	:	AB_hP8_194_ad_f
***Strukturbericht* designation**	:	B_i
Pearson symbol	:	hP8
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB_hP8_194_ad_f --params=`$a, c/a, z_3$

Other compounds with this structure:

- CMo, $CSTi_2$, $CSZr_2$, PTi, PZr

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	As I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	As I
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	As II
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	As II

$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Ti
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Ti
$\mathbf{B_7}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Ti
$\mathbf{B_8}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Ti

References:

- K. Bachmayer, H. Nowotny, and A. Kohl, *Die Struktur von TiAs*, Monatsh. Chem. Verw. Tl. **86**, 39–43 (1955), doi:10.1007/BF00899271.

Found in:

- R. W. G. Wyckoff, *Crystal Structures Vol. 1* (Wiley, 1963), 2nd edn, pp. 146-149.

Geometry files:

- CIF: pp. S739
- POSCAR: pp. S740

Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h

Prototype	:	C
AFLOW prototype label	:	A_hP6_194_h
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP6
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=A_hP6_194_h` `--params=`$a, c/a, x_1$

- This structure was proposed in (Schultz, 1999) to show that it was energetically possible to form three-member rings in amorphous sp^3 carbon structures.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + 2\,x_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_1\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(6*h*)	C
$\mathbf{B_2}$	=	$-2\,x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_1\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(6*h*)	C
$\mathbf{B_3}$	=	$x_1\,\mathbf{a_1} - x_1\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_1\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(6*h*)	C
$\mathbf{B_4}$	=	$-x_1\,\mathbf{a_1} - 2\,x_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_1\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(6*h*)	C
$\mathbf{B_5}$	=	$2\,x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_1\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_1\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(6*h*)	C
$\mathbf{B_6}$	=	$-x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$+\sqrt{3}\,x_1\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(6*h*)	C

References:

- P. A. Schultz, K. Leung, and E. B. Stechel, *Small rings and amorphous tetrahedral carbon*, Phys. Rev. B **59**, 733–741 (1999), doi:10.1103/PhysRevB.59.733.

Geometry files:

- CIF: pp. S740
- POSCAR: pp. S740

CMo Structure: AB_hP12_194_af_bf

Prototype	:	CMo
AFLOW prototype label	:	AB_hP12_194_af_bf
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP12
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB_hP12_194_af_bf` `--params=`$a, c/a, z_3, z_4$

Other compounds with this structure:

- CRe, C_2GeTi_3, C_2SiTi_3, AlC_2Ti_3, others.

- Note that all of the atoms sit on close packed <0001> planes. The stacking sequence may be written:

Atom	Mo-II	C-II	C-I	C-II	Mo-II	Mo-I	Mo-II	C-II	C-I	C-II	Mo-II	Mo-I
Position	B	C	A	B	C	A	C	B	A	C	B	A

Thus the Mo-II atoms and all of the C atoms are always in an fcc-like local environment, while the Mo-I atoms are in an hcp-like local environment. Like AlN3Ti4, this is a MAX phase. For more information, see (Radovic, 2013).

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	C I

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	C I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	Mo I
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	Mo I
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	C II
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	C II
$\mathbf{B_7}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	C II
$\mathbf{B_8}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	C II
$\mathbf{B_9}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(4f)$	Mo II
$\mathbf{B_{10}}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Mo II
$\mathbf{B_{11}}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(4f)$	Mo II
$\mathbf{B_{12}}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Mo II

References:

- H. Nowotny, R. Parthé, R. Kieffer, and F. Benesovsky, *Das Dreistoffsystem: Molybdän–Silizium–Kohlenstoff*, Monatsh. Chem. Verw. Tl. **85**, 255–272 (1954).
- M. Radovic and M. W. Barsoum, *MAX phases: Bridging the gap between metals and ceramics*, American Ceramic Society Bulletin **92**, 20–27 (2013).

Geometry files:

- CIF: pp. S740
- POSCAR: pp. S741

α-La (A3') Structure: A_hP4_194_ac

Prototype	:	α-La
AFLOW prototype label	:	A_hP4_194_ac
***Strukturbericht* designation**	:	A3'
Pearson symbol	:	hP4
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=A_hP4_194_ac --params=`$a, c/a$

Other elements with this structure:

- Pr, Nd, Pm, Ce, Am, Cm, Bk, Cf.

- This crystal is close-packed, with stacking ABACABAC..., as opposed to ABAB... for the hcp (A3) lattice and ABCABC... for the fcc (A1) lattice. The (2a) crystallographic sites (the A's) form a simple hexagonal lattice. The (2c) sites (the B's and C's) form an hcp structure.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	La I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	La I
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	La II
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	La II

References:

- F. H. Spedding, J. J. Hanak, and A. H. Daane, *High temperature allotropy and thermal expansion of the rare-earth metals*, J. Less-Common Met. **3**, 110–124 (1961), doi:10.1016/0022-5088(61)90003-0.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 83-86.

Geometry files:

- CIF: pp. S741
- POSCAR: pp. S741

Na_3As ($D0_{18}$) Structure: AB3_hP8_194_c_bf

Prototype	:	Na_3As
AFLOW prototype label	:	AB3_hP8_194_c_bf
***Strukturbericht* designation**	:	$D0_{18}$
Pearson symbol	:	hP8
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB3_hP8_194_c_bf` `--params=`$a, c/a, z_3$

- (Hafner, 1994) argue that this is not the correct structure for Na_3As. We will keep the $D0_{18}$ designation for this structure, and add a page for the new Na_3As structure in a future update.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	Na I
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	Na I
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	As
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	As
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Na II
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Na II
$\mathbf{B_7}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Na II
$\mathbf{B_8}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Na II

References:

- P. Hafner and K.-J. Range, *Na3As revisited: high-pressure synthesis of single crystals and structure refinement*, J. Alloys Compd. **216**, 7–10 (1994), doi:10.1016/0925-8388(94)91033-2.
- G. Brauer and E. Zintl, *Konstitution von Phosphiden, Arseniden, Antimoniden und Wismutiden des Lithiums, Natriums und Kaliums*, Zeitschrift für Physikalische Chemie **37B**, 323–352 (1937).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1187.

Geometry files:

- CIF: pp. S741
- POSCAR: pp. S742

$CaIn_2$ Structure: AB2_hP6_194_b_f

Prototype	:	$CaIn_2$
AFLOW prototype label	:	AB2_hP6_194_b_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP6
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB2_hP6_194_b_f` `--params=`$a, c/a, z_2$

- When $z_2 = 0$ this reduces to the AlB_2 (C32), aka the hexagonal ω phase.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	Ca

$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	Ca
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	In
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	In
$\mathbf{B_5}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	In
$\mathbf{B_6}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	In

References:

- A. Iandelli, *MX_2-Verbindungen der Erdalkali- und Seltenen Erdmetalle mit Gallium, Indium und Thallium*, Z. Anorg. Allg. Chem. **330**, 221–232 (1964), doi:10.1002/zaac.19643300315.

Found in:

- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 499-501.

Geometry files:

- CIF: pp. S742
- POSCAR: pp. S742

BN (B_k) Structure: AB_hP4_194_c_d

Prototype	:	BN
AFLOW prototype label	:	AB_hP4_194_c_d
***Strukturbericht* designation**	:	B_k
Pearson symbol	:	hP4
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB_hP4_194_c_d` `--params=`$a, c/a$

Other compounds with this structure:

- ZnO nanowires

- This is the corrected boron nitride structure found by (Pease, 1950) and (Pease, 1952). See further discussion on the B12 page.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	B
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	B

$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	N
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	N

References:

- R. S. Pease, *An X-ray study of boron nitride*, Acta Cryst. **5**, 356–361 (1952), doi:10.1107/S0365110X52001064.
- R. S. Pease, *Crystal Structure of Boron Nitride*, Nature **165**, 722–723 (1950), doi:10.1038/165722b0.

Found in:

- R. W. G. Wyckoff, *Crystal Structures Vol. 1* (Wiley, 1963), 2nd edn, pp. 184-5.

Geometry files:

- CIF: pp. S743
- POSCAR: pp. S743

$AlCCr_2$ Structure: ABC2_hP8_194_d_a_f

Prototype	:	$AlCCr_2$
AFLOW prototype label	:	ABC2_hP8_194_d_a_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP8
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=ABC2_hP8_194_d_a_f` `--params=`$a, c/a, z_3$

Other compounds with this structure:

- Cr_2GaN, $CeGeLi_2$, $AlCNb_2$, $AlCTi_2$, $AlNTi_2$, $AsCNb_2$, $CCrGe_2$, $AlCV_2$, many others.

- Note that all of the atoms sit on close-packed <0001> planes. The stacking sequence may be written:

Atom	Cr	C	Cr	Al	Cr	C	Cr	Al
Position	B	A	C	B	C	A	B	C

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	C

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	C
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	Al
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	Al
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Cr
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Cr
$\mathbf{B_7}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Cr
$\mathbf{B_8}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Cr

References:

- W. Jeitschko, H. Nowotny, and F. Benesovsky, *Kohlenstoffhaltige ternäre Verbindungen (H-Phase)*, Monatsh. Chem. Verw. Tl. **94**, 672–676 (1963), doi:10.1007/BF00913068.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 677.

Geometry files:

- CIF: pp. S743
- POSCAR: pp. S743

Ni_3Sn ($D0_{19}$) Structure: A3B_hP8_194_h_c

Prototype	:	Ni_3Sn
AFLOW prototype label	:	A3B_hP8_194_h_c
***Strukturbericht* designation**	:	$D0_{19}$
Pearson symbol	:	hP8
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=A3B_hP8_194_h_c` `--params=`$a, c/a, x_2$

Other compounds with this structure:

- Ti_3Sn, Ti_3Al, Mn_3Sn, Cd_3Mg, Mg_3In, Hg_3Y

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	Sn
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	Sn
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + 2\,x_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni
$\mathbf{B_4}$	=	$-2\,x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_2\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - 2\,x_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni
$\mathbf{B_7}$	=	$2\,x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_2\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_2\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni
$\mathbf{B_8}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$+\sqrt{3}\,x_2\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni

References:

- A. L. Lyubimtsev, A. I. Baranov, A. Fischer, L. Kloo, and B. A. Popovkin, *The structure and bonding of Ni_3Sn*, J. Alloys Compd. **340**, 167–172 (2002), doi:10.1016/S0925-8388(02)00047-6.

Geometry files:

- CIF: pp. S744
- POSCAR: pp. S744

Hexagonal Graphite (A9) Crystal Structure: A_hP4_194_bc

Prototype	:	C
AFLOW prototype label	:	A_hP4_194_bc
***Strukturbericht* designation**	:	A9
Pearson symbol	:	hP4
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=A_hP4_194_bc --params=`$a, c/a$

Other compounds with this structure:

- LiB

- According to (Wyckoff, 1963), hexagonal graphite may be either flat, space group $P6_3/mmc$ (#194) or buckled, space group $P6_3mc$ (#186). If it is buckled, the buckling parameter is small, less than 1/20 of the "c" parameter of the hexagonal unit cell. We will assign the A9 Strukturbericht designation to the unbuckled structure. Experimentally, a rhombohedral ($R\bar{3}m$) graphite structure is also observed.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	(2*b*)	C I
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	(2*b*)	C I
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	(2*c*)	C II
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	(2*c*)	C II

References:

- P. Trucano and R. Chen, *Structure of graphite by neutron diffraction*, Nature **258**, 136–137 (1975), doi:10.1038/258136a0.
- R. W. G. Wyckoff, *Crystal Structures Vol. 1* (Wiley, 1963), 2nd edn.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S744
- POSCAR: pp. S744

Molybdenite (MoS_2, C7) Structure: AB2_hP6_194_c_f

Prototype	:	MoS_2
AFLOW prototype label	:	AB2_hP6_194_c_f
***Strukturbericht* designation**	:	C7
Pearson symbol	:	hP6
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB2_hP6_194_c_f` `--params=`$a, c/a, z_2$

Other compounds with this structure:

- AlS_6Ta_3, CdS_2Ta, BPt_2, $MoSe_2$, $MoTe_2$, $NbSe_2$, S_2Ta, S_2W, Se_2Ta, Se_2W, Te_2W, many more.

- Note that the stacking here is B**A**BA**B**A, where the layers in bold text are the Mo atoms.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	Mo
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	Mo
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	S

$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	S
$\mathbf{B_5}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	S
$\mathbf{B_6}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	S

References:

- B. Schönfeld, J. J. Huang, and S. C. Moss, *Anisotropic Mean-Square Displacements (MSD) in single Crystals of 2H- and 3R-MoS_2*, Acta Crystallogr. Sect. B Struct. Sci. **39**, 404–407 (1983), doi:10.1107/S0108768183002645.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S745
- POSCAR: pp. S745

W_2B_5 ($D8_h$) Structure: A5B2_hP14_194_abdf_f

Prototype	:	W_2B_5
AFLOW prototype label	:	A5B2_hP14_194_abdf_f
***Strukturbericht* designation**	:	$D8_h$
Pearson symbol	:	hP14
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=A5B2_hP14_194_abdf_f` `--params=`$a, c/a, z_4, z_5$

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	B I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	B I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	B II
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2b)$	B II
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	B III
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	B III
$\mathbf{B_7}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(4f)$	B IV
$\mathbf{B_8}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	B IV
$\mathbf{B_9}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(4f)$	B IV

$\mathbf{B_{10}}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	B IV
$\mathbf{B_{11}}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4f)$	W
$\mathbf{B_{12}}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	W
$\mathbf{B_{13}}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(4f)$	W
$\mathbf{B_{14}}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	W

References:

- R. Kiessling, *The Crystal Structures of Molybdenum and Tungsten Borides*, Acta Chem. Scand. **1**, 893–916 (1947), doi:10.3891/acta.chem.scand.01-0893.

Found in:

- R. W. G. Wyckoff, *Crystal Structures Vol. 2, Inorganic Compounds RXn, RnMX2, RnMX3* (Wiley, 1964), 2nd edn, pp. 188-189.

Geometry files:

- CIF: pp. S745
- POSCAR: pp. S745

$MgZn_2$ Hexagonal Laves (C14) Structure: AB2_hP12_194_f_ah

Prototype	:	$MgZn_2$
AFLOW prototype label	:	AB2_hP12_194_f_ah
***Strukturbericht* designation**	:	C14
Pearson symbol	:	hP12
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB2_hP12_194_f_ah` `--params=`$a, c/a, z_2, x_3$

Other compounds with this structure:

- $CaMg_2$, $ZrRe_2$, KNa_2, $TaFe_2$, $NbMn_2$, UNi_2

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Zn I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	Zn I
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	Mg
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Mg
$\mathbf{B_5}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	Mg
$\mathbf{B_6}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Mg
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + 2\,x_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_3\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Zn II
$\mathbf{B_8}$	=	$-2\,x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_3\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Zn II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_3\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Zn II
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} - 2\,x_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_3\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Zn II
$\mathbf{B_{11}}$	=	$2\,x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_3\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_3\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Zn II
$\mathbf{B_{12}}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$+\sqrt{3}\,x_3\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Zn II

References:

- T. Ohba, Y. Kitano, and Y. Komura, *The charge-density study of the Laves phases, $MgZn_2$ and $MgCu_2$*, Acta Crystallographic C **40**, 1–5 (1984), doi:10.1107/S0108270184002791.

Geometry files:

- CIF: pp. S746
- POSCAR: pp. S746

LiBC Structure: ABC_hP6_194_c_d_a

Prototype	:	LiBC
AFLOW prototype label	:	ABC_hP6_194_c_d_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP6
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=ABC_hP6_194_c_d_a --params=`$a, c/a$

Other compounds with this structure:

- ZrBeSi

- This is the parent structure of the $Li_{1-x}BC$ Structure

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Li
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	Li

$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	B
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	B
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	C
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	C

References:

- M. Wörle, R. Nesper, G. Mair, M. Schwarz, and H. G. Von Schnering, *LiBC – ein vollständig interkalierter Heterographit*, Z. Anorg. Allg. Chem. **621**, 1153–1159 (1995), doi:10.1002/zaac.19956210707.

Geometry files:

- CIF: pp. S746
- POSCAR: pp. S747

Lonsdaleite (Hexagonal Diamond) Structure: A_hP4_194_f

Prototype	:	C
AFLOW prototype label	:	A_hP4_194_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP4
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=A_hP4_194_f` `--params=`$a, c/a, z_1$

Other elements with this structure:

- Si (Hexagonal)

- Hexagonal diamond was named lonsdaleite in honor of Kathleen Lonsdale. This is related to the hcp (A3) lattice in the same way that diamond (A4) is related to the fcc lattice (A1). It can also be obtained from wurtzite (B4) by replacing both the Zn and S atoms by carbon. The "ideal" structure, where the nearest-neighbor environment of each atom is the same as in diamond, is achieved when we take $c/a = \sqrt{8/3}$ and $z_1 = 1/16$. Alternatively, we can take $z_1 = 3/16$, in which case the origin is at the center of a C-C bond aligned in the [0001] direction. When $z_1 = 0$ this structure becomes a set of graphitic sheets, but not true hexagonal graphite (A9).

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_1\,c\,\hat{\mathbf{z}}$	$(4f)$	C
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_1\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_1\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	C
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_1\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_1\,c\,\hat{\mathbf{z}}$	$(4f)$	C
$\mathbf{B_4}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_1\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_1\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	C

References:

- A. Yoshiasa, Y. Murai, O. Ohtaka, and T. Katsura, *Detailed Structures of Hexagonal Diamond (lonsdaleite) and Wurtzite-type BN*, Jpn. J. Appl. Phys **42**, 1694–1704 (2003), doi:10.1143/JJAP.42.1694.

Geometry files:

- CIF: pp. S747
- POSCAR: pp. S747

Ni_2In ($B8_2$) Structure: AB2_hP6_194_c_ad

Prototype	:	Ni_2In
AFLOW prototype label	:	AB2_hP6_194_c_ad
***Strukturbericht* designation**	:	$B8_2$
Pearson symbol	:	hP6
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB2_hP6_194_c_ad --params=`$a, c/a$

Other compounds with this structure:

- AgAsBa, BeSiZr, CuKSe, LiBC, Fe_2Sn, GaMnPt, more

- Replacing the Ni-II atoms with In transforms the crystal into the C32 (hexagonal ω) phase.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ni I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	Ni I
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	In
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	In
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	Ni II
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	Ni II

References:

- M. Ellner, *Über die kristallchemischen parameter der Ni-, Co- und Fe-haltigen phasen vom NiAs-Typ*, J. Less-Common Met. **48**, 21–52 (1976), doi:10.1016/0022-5088(76)90231-9.

Found in:

- P. Villars, K. Cenzual, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, V. Kuprysyuk, I. Savesyuk, and R. Zaremba, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag GmbH, Heidelberg, 2012). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S747
- POSCAR: pp. S748

AlN_3Ti_4 Structure: AB3C4_hP16_194_c_af_ef

Prototype	:	AlN_3Ti_4
AFLOW prototype label	:	AB3C4_hP16_194_c_af_ef
***Strukturbericht* designation**	:	None
Pearson symbol	:	hP16
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB3C4_hP16_194_c_af_ef` `--params=`$a, c/a, z_3, z_4, z_5$

- This is a so-called MAX phase. For more information, see (Radovic, 2013).

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	N I
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	N I
$\mathbf{B_3}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + \frac{1}{4}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	Al
$\mathbf{B_4}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \frac{3}{4}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	Al
$\mathbf{B_5}$	=	$z_3\,\mathbf{a_3}$	=	$z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	Ti I
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + z_3\right)c\,\hat{\mathbf{z}}$	$(4e)$	Ti I
$\mathbf{B_7}$	=	$-z_3\,\mathbf{a_3}$	=	$-z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	Ti I
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - z_3\right)c\,\hat{\mathbf{z}}$	$(4e)$	Ti I
$\mathbf{B_9}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_4\,c\,\hat{\mathbf{z}}$	$(4f)$	N II

$\mathbf{B_{10}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \left(\frac{1}{2} + z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_4\right)c\,\hat{\mathbf{z}}$	$(4f)$	N II
$\mathbf{B_{11}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} - z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_4\,c\,\hat{\mathbf{z}}$	$(4f)$	N II
$\mathbf{B_{12}}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + \left(\frac{1}{2} - z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_4\right)c\,\hat{\mathbf{z}}$	$(4f)$	N II
$\mathbf{B_13}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_5\,c\,\hat{\mathbf{z}}$	$(4f)$	Ti II
$\mathbf{B_{14}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} + \left(\frac{1}{2} + z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_5\right)c\,\hat{\mathbf{z}}$	$(4f)$	Ti II
$\mathbf{B_{15}}$	=	$\frac{2}{3}\mathbf{a_1} + \frac{1}{3}\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_5\,c\,\hat{\mathbf{z}}$	$(4f)$	Ti II
$\mathbf{B_{16}}$	=	$\frac{1}{3}\mathbf{a_1} + \frac{2}{3}\mathbf{a_2} + \left(\frac{1}{2} - z_5\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_5\right)c\,\hat{\mathbf{z}}$	$(4f)$	Ti II

References:

- M. W. Barsoum, C. J. Rawn, T. El-Raghy, A. T. Procopio, W. D. Porter, H. Wang, and C. R. Hubbard, *Thermal Properties of Ti_4AlN_3*, J. Appl. Phys. **87**, 8407–8414 (2000), doi:10.1063/1.373555.
- M. Radovic and M. W. Barsoum, *MAX phases: Bridging the gap between metals and ceramics*, American Ceramic Society Bulletin **92**, 20–27 (2013).

Geometry files:

- CIF: pp. S748
- POSCAR: pp. S748

Hexagonal Close Packed (Mg, A3) Structure: A_hP2_194_c

Prototype	:	Mg
AFLOW prototype label	:	A_hP2_194_c
***Strukturbericht* designation**	:	A3
Pearson symbol	:	hP2
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=A_hP2_194_c --params=`$a, c/a$

Other elements with this structure:

- Be, Sc, Ti, Co, Zn, Y, Zr, Tc, Ru, Cd, Gd, Tb, Dy, Ho, Er, Tm, Lu, Hf, Re, Os, Tl

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	Mg
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	Mg

References:

- F. W. von Batchelder and R. F. Raeuchle, *Lattice Constants and Brillouin Zone Overlap in Dilute Magnesium Alloys*, Phys. Rev. **105**, 59–61 (1957), doi:10.1103/PhysRev.105.59.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 39-40.

Geometry files:

- CIF: pp. S748
- POSCAR: pp. S749

$MgNi_2$ Hexagonal Laves (C36) Structure: AB2_hP24_194_ef_fgh

Prototype	:	$MgNi_2$
AFLOW prototype label	:	AB2_hP24_194_ef_fgh
***Strukturbericht* designation**	:	C36
Pearson symbol	:	hP24
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB2_hP24_194_ef_fgh` `--params=`$a, c/a, z_1, z_2, z_3, x_5$

Other compounds with this structure:

- $NbZn_2$, $ScFe_2$, $ThMg_2$, $HfCr_2$, UPt_2

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$z_1\,\mathbf{a_3}$	=	$z_1\,c\,\hat{\mathbf{z}}$	$(4e)$	Mg I
$\mathbf{B_2}$	=	$-z_1\,\mathbf{a_3}$	=	$-z_1\,c\,\hat{\mathbf{z}}$	$(4e)$	Mg I
$\mathbf{B_3}$	=	$\left(\frac{1}{2}+z_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_1\right)c\,\hat{\mathbf{z}}$	$(4e)$	Mg I

$\mathbf{B_4}$	=	$\left(\frac{1}{2} - z_1\right) \mathbf{a_3}$	=	$\left(\frac{1}{2} - z_1\right) c\,\hat{\mathbf{z}}$	$(4e)$	Mg I
$\mathbf{B_5}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	Mg II
$\mathbf{B_6}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right) \mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right) c\,\hat{\mathbf{z}}$	$(4f)$	Mg II
$\mathbf{B_7}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	Mg II
$\mathbf{B_8}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right) \mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right) c\,\hat{\mathbf{z}}$	$(4f)$	Mg II
$\mathbf{B_9}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Ni I
$\mathbf{B_{10}}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_3\right) \mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right) c\,\hat{\mathbf{z}}$	$(4f)$	Ni I
$\mathbf{B_{11}}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_3\,c\,\hat{\mathbf{z}}$	$(4f)$	Ni I
$\mathbf{B_{12}}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_3\right) \mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right) c\,\hat{\mathbf{z}}$	$(4f)$	Ni I
$\mathbf{B_{13}}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}}$	$(6g)$	Ni II
$\mathbf{B_{14}}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}}$	$(6g)$	Ni II
$\mathbf{B_{15}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(6g)$	Ni II
$\mathbf{B_{16}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	Ni II
$\mathbf{B_{17}}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	Ni II
$\mathbf{B_{18}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	Ni II
$\mathbf{B_{19}}$	=	$x_5\,\mathbf{a_1} + 2\,x_5\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_5\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni III
$\mathbf{B_{20}}$	=	$-2\,x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_5\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni III
$\mathbf{B_{21}}$	=	$x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$-\sqrt{3}\,x_5\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni III
$\mathbf{B_{22}}$	=	$-x_5\,\mathbf{a_1} - 2\,x_5\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$-\frac{3}{2}\,x_5\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni III
$\mathbf{B_{23}}$	=	$2\,x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{2}\,x_5\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,x_5\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni III
$\mathbf{B_{24}}$	=	$-x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$+\sqrt{3}\,x_5\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(6h)$	Ni III

References:

- Y. Komura and K. Tokunaga, *Structural studies of stacking variants in Mg-base Friauf-Laves phases*, Acta Crystallogr. Sect. B Struct. Sci. **36**, 1548–1554 (1980), doi:10.1107/S0567740880006565.

Geometry files:

- CIF: pp. S749
- POSCAR: pp. S749

Covellite (CuS, B18) Structure: AB_hP12_194_df_ce

Prototype	:	CuS
AFLOW prototype label	:	AB_hP12_194_df_ce
***Strukturbericht* designation**	:	B18
Pearson symbol	:	hP12
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB_hP12_194_df_ce` `--params=`$a, c/a, z_3, z_4$

Other compounds with this structure:

- CuSe

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	S I
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	S I
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	Cu I
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2d)$	Cu I
$\mathbf{B_5}$	=	$z_3\,\mathbf{a_3}$	=	$z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	S II

$\mathbf{B_6}$	=	$-z_3\,\mathbf{a_3}$	=	$-z_3\,c\,\hat{\mathbf{z}}$	$(4e)$	S II
$\mathbf{B_7}$	=	$\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_3\right)c\,\hat{\mathbf{z}}$	$(4e)$	S II
$\mathbf{B_8}$	=	$\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-z_3\right)c\,\hat{\mathbf{z}}$	$(4e)$	S II
$\mathbf{B_9}$	=	$\frac{1}{3}\,\mathbf{a_1}+\frac{2}{3}\,\mathbf{a_2}+z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}+\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+z_4\,c\,\hat{\mathbf{z}}$	$(4f)$	Cu II
$\mathbf{B_{10}}$	=	$\frac{2}{3}\,\mathbf{a_1}+\frac{1}{3}\,\mathbf{a_2}+\left(\frac{1}{2}+z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}-\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_4\right)c\,\hat{\mathbf{z}}$	$(4f)$	Cu II
$\mathbf{B_{11}}$	=	$\frac{2}{3}\,\mathbf{a_1}+\frac{1}{3}\,\mathbf{a_2}-z_4\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}-\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}-z_4\,c\,\hat{\mathbf{z}}$	$(4f)$	Cu II
$\mathbf{B_{12}}$	=	$\frac{1}{3}\,\mathbf{a_1}+\frac{2}{3}\,\mathbf{a_2}+\left(\frac{1}{2}-z_4\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}+\frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_4\right)c\,\hat{\mathbf{z}}$	$(4f)$	Cu II

References:

- M. Ohmasa, M. Suzuki, and Y. Takéuchi, *A refinement of the crystal structure of covellite, CuS*, Mineralogical Journal **8**, 311–319 (1977), doi:10.2465/minerj.8.311.

Geometry files:

- CIF: pp. S749
- POSCAR: pp. S750

NiAs ($B8_1$) Structure: AB_hP4_194_c_a

Prototype	:	NiAs
AFLOW prototype label	:	AB_hP4_194_c_a
***Strukturbericht* designation**	:	$B8_1$
Pearson symbol	:	hP4
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=AB_hP4_194_c_a` `--params=`$a, c/a$

Other compounds with this structure:

- AuSn, CoTe, CrSe, CuSn, FeS, IrS, MnAs, NiSn, PdSb, PtB, RhSn, VP, ZrTe

- Note that the stacking is ABACABAC, with the Ni atoms on the A sites and As on B and C. The environment of the Ni atoms is fcc-like, and the environment of the As atoms is hcp-like.

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Ni
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(2a)$	Ni
$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	As
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	As

References:

- P. Brand and J. Briest, *Das quasi-binäre System NiAs–$Ni_{1.5}Sn$*, Z. Anorg. Allg. Chem. **337**, 209–213 (1965), doi:10.1002/zaac.19653370314.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1192.

Geometry files:

- CIF: pp. S750
- POSCAR: pp. S750

β-Tridymite (SiO_2) Structure (C10): A2B_hP12_194_cg_f

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_hP12_194_cg_f
***Strukturbericht* designation**	:	C10
Pearson symbol	:	hP12
Space group number	:	194
Space group symbol	:	$P6_3/mmc$
AFLOW prototype command	:	`aflow --proto=A2B_hP12_194_cg_f` `--params=`$a, c/a, z_2$

Hexagonal primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}\,a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = c\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	O I
$\mathbf{B_2}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,c\,\hat{\mathbf{z}}$	$(2c)$	O I

$\mathbf{B_3}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	Si
$\mathbf{B_4}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} + \left(\frac{1}{2} + z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Si
$\mathbf{B_5}$	=	$\frac{2}{3}\,\mathbf{a_1} + \frac{1}{3}\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} - z_2\,c\,\hat{\mathbf{z}}$	$(4f)$	Si
$\mathbf{B_6}$	=	$\frac{1}{3}\,\mathbf{a_1} + \frac{2}{3}\,\mathbf{a_2} + \left(\frac{1}{2} - z_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2\sqrt{3}}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_2\right)\,c\,\hat{\mathbf{z}}$	$(4f)$	Si
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}}$	$(6g)$	O II
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}}$	$(6g)$	O II
$\mathbf{B_9}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(6g)$	O II
$\mathbf{B_{10}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	O II
$\mathbf{B_{11}}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	O II
$\mathbf{B_{12}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,c\,\hat{\mathbf{z}}$	$(6g)$	O II

References:

- K. Kihara, *Thermal change in unit-cell dimensions, and a hexagonal structure of tridymite*, Zeitschrift für Kristallographie **148**, 237–253 (1978), doi:10.1524/zkri.1978.148.3-4.237.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4759.

Geometry files:

- CIF: pp. S750
- POSCAR: pp. S751

Ga_4Ni Structure: A4B_cI40_197_cde_c

Prototype	:	Ga_4Ni
AFLOW prototype label	:	A4B_cI40_197_cde_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI40
Space group number	:	197
Space group symbol	:	I23
AFLOW prototype command	:	`aflow --proto=A4B_cI40_197_cde_c --params=`a, x_1, x_2, x_3, x_4

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$2x_1\,\mathbf{a_1} + 2x_1\,\mathbf{a_2} + 2x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(8c)$	Ga I
$\mathbf{B_2}$	=	$-2x_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(8c)$	Ga I
$\mathbf{B_3}$	=	$-2x_1\,\mathbf{a_2}$	=	$-x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} - x_1\,a\,\hat{\mathbf{z}}$	$(8c)$	Ga I
$\mathbf{B_4}$	=	$-2x_1\,\mathbf{a_1}$	=	$x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} - x_1\,a\,\hat{\mathbf{z}}$	$(8c)$	Ga I

$\mathbf{B_5}$	=	$2x_2\,\mathbf{a_1} + 2x_2\,\mathbf{a_2} + 2x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(8*c*)	Ni
$\mathbf{B_6}$	=	$-2x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(8*c*)	Ni
$\mathbf{B_7}$	=	$-2x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(8*c*)	Ni
$\mathbf{B_8}$	=	$-2x_2\,\mathbf{a_1}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(8*c*)	Ni
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}$	(12*d*)	Ga II
$\mathbf{B_{10}}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{y}}$	(12*d*)	Ga II
$\mathbf{B_{11}}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2}$	=	$x_3\,a\,\hat{\mathbf{z}}$	(12*d*)	Ga II
$\mathbf{B_{12}}$	=	$-x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}$	(12*d*)	Ga II
$\mathbf{B_{13}}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{y}}$	(12*d*)	Ga II
$\mathbf{B_{14}}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2}$	=	$-x_3\,a\,\hat{\mathbf{z}}$	(12*d*)	Ga II
$\mathbf{B_{15}}$	=	$\frac{1}{2}\,\mathbf{a_1} + x_4\,\mathbf{a_2} + \left(\frac{1}{2} + x_4\right)\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	(12*e*)	Ga III
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} + x_4\right)\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(12*e*)	Ga III
$\mathbf{B_{17}}$	=	$x_4\,\mathbf{a_1} + \left(\frac{1}{2} + x_4\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{z}}$	(12*e*)	Ga III
$\mathbf{B_{18}}$	=	$\frac{1}{2}\,\mathbf{a_1} - x_4\,\mathbf{a_2} + \left(\frac{1}{2} - x_4\right)\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	(12*e*)	Ga III
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2} - x_4\right)\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(12*e*)	Ga III
$\mathbf{B_{20}}$	=	$-x_4\,\mathbf{a_1} + \left(\frac{1}{2} - x_4\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{z}}$	(12*e*)	Ga III

References:

- L. Jingkui and X. Sishen, *The Structure of $NiGa_4$ Crystal – A New Vacancy Controlled γ-Brass Phase*, Scientia Sinica, Series A: Mathematical, Physical, Astronomical and Technical Sciences, English Edition **26**, 1305–1313 (1983).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn.

Geometry files:

- CIF: pp. S751
- POSCAR: pp. S751

Ullmanite (NiSSb, $F0_1$) Structure: ABC_cP12_198_a_a_a

Prototype	:	NiSSb
AFLOW prototype label	:	ABC_cP12_198_a_a_a
***Strukturbericht* designation**	:	$F0_1$
Pearson symbol	:	cP12
Space group number	:	198
Space group symbol	:	$P2_13$
AFLOW prototype command	:	`aflow --proto=ABC_cP12_198_a_a_a` `--params=`a, x_1, x_2, x_3

Other compounds with this structure:

- AsBaPt, AsPdS, BiIrS, BiRhSe, CaPtSi, CrPtSb, EuPtSi, IrLaSi, IrSbSe, many others

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(4a)$	Ni
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - x_1\,\mathbf{a_2} + \left(\frac{1}{2} + x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{z}}$	$(4a)$	Ni
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \left(\frac{1}{2} - x_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{z}}$	$(4a)$	Ni

$\mathbf{B_4}$	=	$+\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{y}}-x_1\,a\,\hat{\mathbf{z}}$	(4*a*)	Ni
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1}+x_2\,\mathbf{a_2}+x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+x_2\,a\,\hat{\mathbf{y}}+x_2\,a\,\hat{\mathbf{z}}$	(4*a*)	S
$\mathbf{B_6}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-x_2\,\mathbf{a_2}+\left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}-x_2\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	(4*a*)	S
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+x_2\right)\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	(4*a*)	S
$\mathbf{B_8}$	=	$+\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}-x_2\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}}-x_2\,a\,\hat{\mathbf{z}}$	(4*a*)	S
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1}+x_3\,\mathbf{a_2}+x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}+x_3\,a\,\hat{\mathbf{y}}+x_3\,a\,\hat{\mathbf{z}}$	(4*a*)	Sb
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_3\right)\mathbf{a_1}-x_3\,\mathbf{a_2}+\left(\frac{1}{2}+x_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{x}}-x_3\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{z}}$	(4*a*)	Sb
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1}+\left(\frac{1}{2}+x_3\right)\mathbf{a_2}+\left(\frac{1}{2}-x_3\right)\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{z}}$	(4*a*)	Sb
$\mathbf{B_{12}}$	=	$+\left(\frac{1}{2}+x_3\right)\mathbf{a_1}+\left(\frac{1}{2}-x_3\right)\mathbf{a_2}-x_3\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_3\right)a\,\hat{\mathbf{y}}-x_3\,a\,\hat{\mathbf{z}}$	(4*a*)	Sb

References:

- Y. Takéuchi, *The Absolute Structure of Ullmanite, NiSbS*, Mineralogical Journal **2**, 90–102 (1957), doi:10.2465/minerj1953.2.90.

Geometry files:

- CIF: pp. S751
- POSCAR: pp. S752

Ammonia (NH_3, D1) Structure: A3B_cP16_198_b_a

Prototype	:	NH_3
AFLOW prototype label	:	A3B_cP16_198_b_a
***Strukturbericht* designation**	:	D1
Pearson symbol	:	cP16
Space group number	:	198
Space group symbol	:	$P2_13$
AFLOW prototype command	:	`aflow --proto=A3B_cP16_198_b_a` `--params=`a, x_1, x_2, y_2, z_2

Other compounds with this structure:

- AsH_3, PH_3

- The positions of the hydrogen atoms are taken from neutron diffraction data on fully deuterated ND_3.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(4a)$	N
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - x_1\,\mathbf{a_2} + \left(\frac{1}{2} + x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{z}}$	$(4a)$	N

$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1}+\left(\frac{1}{2}+x_1\right)\mathbf{a_2}+\left(\frac{1}{2}-x_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{z}}$	(4*a*)	N
$\mathbf{B_4}$	=	$+\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{y}}-x_1\,a\,\hat{\mathbf{z}}$	(4*a*)	N
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1}+y_2\,\mathbf{a_2}+z_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+y_2\,a\,\hat{\mathbf{y}}+z_2\,a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_6}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-y_2\,\mathbf{a_2}+\left(\frac{1}{2}+z_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}-y_2\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_2\right)a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+y_2\right)\mathbf{a_2}+\left(\frac{1}{2}-z_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_2\right)a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_8}$	=	$+\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-y_2\right)\mathbf{a_2}-z_2\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)a\,\hat{\mathbf{y}}-z_2\,a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_9}$	=	$z_2\,\mathbf{a_1}+x_2\,\mathbf{a_2}+y_2\,\mathbf{a_3}$	=	$z_2\,a\,\hat{\mathbf{x}}+x_2\,a\,\hat{\mathbf{y}}+y_2\,a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-z_2\right)\mathbf{a_1}-x_2\,\mathbf{a_2}+\left(\frac{1}{2}+y_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-z_2\right)a\,\hat{\mathbf{x}}-x_2\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+y_2\right)a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_{11}}$	=	$-z_2\,\mathbf{a_1}+\left(\frac{1}{2}+x_2\right)\mathbf{a_2}+\left(\frac{1}{2}-y_2\right)\mathbf{a_3}$	=	$-z_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-y_2\right)a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_{12}}$	=	$+\left(\frac{1}{2}+z_2\right)\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}-y_2\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+z_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}}-y_2\,a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_{13}}$	=	$y_2\,\mathbf{a_1}+z_2\,\mathbf{a_2}+x_2\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}}+z_2\,a\,\hat{\mathbf{y}}+x_2\,a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}-y_2\right)\mathbf{a_1}-z_2\,\mathbf{a_2}+\left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_2\right)a\,\hat{\mathbf{x}}-z_2\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_{15}}$	=	$-y_2\,\mathbf{a_1}+\left(\frac{1}{2}+z_2\right)\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+z_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	(12*b*)	H
$\mathbf{B_{16}}$	=	$+\left(\frac{1}{2}+y_2\right)\mathbf{a_1}+\left(\frac{1}{2}-z_2\right)\mathbf{a_2}-x_2\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+y_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-z_2\right)a\,\hat{\mathbf{y}}-x_2\,a\,\hat{\mathbf{z}}$	(12*b*)	H

References:

- R. Boese, N. Niederprüm, D. Bläser, A. Maulitz, M. Y. Antipin, and P. R. Mallinson, *Single-Crystal Structure and Electron Density Distribution of Ammonia at 160 K on the Basis of X-ray Diffraction Data*, J. Phys. Chem. B **101**, 5794–5799 (1997), doi:10.1021/jp970580v.

Geometry files:

- CIF: pp. S752
- POSCAR: pp. S752

α-N ($P2_13$) Structure: A_cP8_198_2a

Prototype	:	α-N
AFLOW prototype label	:	A_cP8_198_2a
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP8
Space group number	:	198
Space group symbol	:	$P2_13$
AFLOW prototype command	:	`aflow --proto=A_cP8_198_2a --params=`a, x_1, x_2

- There is considerable controversy about the crystal structure of α-N, as outlined in (Donohue, 1982) pp. 280-285. This page assumes the non-centrosymmetric $P2_13$ structure. The other possibility is the $Pa\bar{3}$ structure, where the N_2 dimers are not centered on an inversion site. (Venables, 1974) makes a convincing case that the ground state is $Pa\bar{3}$, but we present both structures. Density Functional Theory calculations show no appreciable difference in energy between the $Pa\bar{3}$ and $P2_13$ structures (Mehl, 2015).

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(4a)$	N I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - x_1\,\mathbf{a_2} + \left(\frac{1}{2} + x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{z}}$	$(4a)$	N I

$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1}+\left(\frac{1}{2}+x_1\right)\mathbf{a_2}+\left(\frac{1}{2}-x_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{z}}$	(4*a*)	N I
$\mathbf{B_4}$	=	$+\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{y}}-x_1\,a\,\hat{\mathbf{z}}$	(4*a*)	N I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1}+x_2\,\mathbf{a_2}+x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+x_2\,a\,\hat{\mathbf{y}}+x_2\,a\,\hat{\mathbf{z}}$	(4*a*)	N II
$\mathbf{B_6}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-x_2\,\mathbf{a_2}+\left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}-x_2\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	(4*a*)	N II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+x_2\right)\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	(4*a*)	N II
$\mathbf{B_8}$	=	$+\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}-x_2\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}}-x_2\,a\,\hat{\mathbf{z}}$	(4*a*)	N II

References:

- S. J. La Placa and W. C Hamilton, *Refinement of the crystal structure of α-N_2*, Acta Crystallogr. Sect. B Struct. Sci. **28**, 984–985 (1972), doi:10.1107/S0567740872003541.
- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982).
- J. A. Venables and C. A. English, *Electron diffraction and the structure of α-N2*, Acta Crystallogr. Sect. B Struct. Sci. **30**, 929–935 (1974), doi:10.1107/S0567740874004067.
- M. J. Mehl, D. Finkenstadt, C. Dane, G. L. W. Hart, and S. Curtarolo, *Finding the stable structures of $N_{1-x}W_x$ with an ab initio high-throughput approach*, Phys. Rev. B **91**, 184110 (2015), doi:10.1103/PhysRevB.91.184110.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 280-285.

Geometry files:

- CIF: pp. S752
- POSCAR: pp. S753

α-CO (B21) Structure: AB_cP8_198_a_a

Prototype	:	α-CO
AFLOW prototype label	:	AB_cP8_198_a_a
***Strukturbericht* designation**	:	B21
Pearson symbol	:	cP8
Space group number	:	198
Space group symbol	:	$P2_13$
AFLOW prototype command	:	`aflow --proto=AB_cP8_198_a_a` `--params=`a, x_1, x_2

- The molecules sit on the sites of a face-centered cubic lattice. Note that α-CO (pp. S504) and FeSi (pp. S506) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(4a)$	C
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - x_1\,\mathbf{a_2} + \left(\frac{1}{2} + x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{z}}$	$(4a)$	C
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \left(\frac{1}{2} - x_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{z}}$	$(4a)$	C

$\mathbf{B_4}$	=	$+\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{y}}-x_1\,a\,\hat{\mathbf{z}}$	(4*a*)	C
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1}+x_2\,\mathbf{a_2}+x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+x_2\,a\,\hat{\mathbf{y}}+x_2\,a\,\hat{\mathbf{z}}$	(4*a*)	O
$\mathbf{B_6}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-x_2\,\mathbf{a_2}+\left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}-x_2\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	(4*a*)	O
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+x_2\right)\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	(4*a*)	O
$\mathbf{B_8}$	=	$+\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}-x_2\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}}-x_2\,a\,\hat{\mathbf{z}}$	(4*a*)	O

References:

- L. Vegard, *Struktur und Leuchtfähigkeit von festem Kohlenoxyd*, Z. Phys. **61**, 185–190 (1930).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S753
- POSCAR: pp. S753

FeSi (B20) Structure: AB_cP8_198_a_a

Prototype	:	FeSi
AFLOW prototype label	:	AB_cP8_198_a_a
***Strukturbericht* designation**	:	B20
Pearson symbol	:	cP8
Space group number	:	198
Space group symbol	:	$P2_13$
AFLOW prototype command	:	`aflow --proto=AB_cP8_198_a_a` `--params=`a, x_1, x_2

Other compounds with this structure:

- AlPt, AuBe, CoGe, CoSi, FeGe, GaPd, GeMn, GeRh, HfSb, HfSn, RhS, SbZr, SiTc

- When $x_1 = 0$ and $x_2 = 1/2$, or $x_1 = 1/4$ and $x_2 = 3/4$, this lattice reduces to the rock salt (B1) structure. When $x_1 = -x_2 = 1/8\left(\sqrt{5}-1\right)$ we have an "ideal" structure where every atom is seven-fold coordinated. Note that α-CO (pp. S504) and FeSi (pp. S506) have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(4a)$	Fe

$\mathbf{B_2}$	=	$\left(\frac{1}{2}-x_1\right)\mathbf{a_1}-x_1\,\mathbf{a_2}+\left(\frac{1}{2}+x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{x}}-x_1\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{z}}$	(4*a*)	Fe
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1}+\left(\frac{1}{2}+x_1\right)\mathbf{a_2}+\left(\frac{1}{2}-x_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{z}}$	(4*a*)	Fe
$\mathbf{B_4}$	=	$+\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{y}}-x_1\,a\,\hat{\mathbf{z}}$	(4*a*)	Fe
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1}+x_2\,\mathbf{a_2}+x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}+x_2\,a\,\hat{\mathbf{y}}+x_2\,a\,\hat{\mathbf{z}}$	(4*a*)	Si
$\mathbf{B_6}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-x_2\,\mathbf{a_2}+\left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}}-x_2\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	(4*a*)	Si
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+x_2\right)\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	(4*a*)	Si
$\mathbf{B_8}$	=	$+\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}-x_2\,\mathbf{a_3}$	=	$+\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}}-x_2\,a\,\hat{\mathbf{z}}$	(4*a*)	Si

References:

- L. Vočadlo, K. S. Knight, G. D. Price, and I. G. Wood, *Thermal expansion and crystal structure of FeSi between 4 and 1173 K determined by time-of-flight neutron powder diffraction*, Phys. Chem. Miner. **29**, 132–139 (2002), doi:10.1007/s002690100202.

Geometry files:

- CIF: pp. S753
- POSCAR: pp. S754

CoU (B_a) Structure: AB_cI16_199_a_a

Prototype	:	CoU
AFLOW prototype label	:	AB_cI16_199_a_a
***Strukturbericht* designation**	:	B_a
Pearson symbol	:	cI16
Space group number	:	199
Space group symbol	:	$I2_13$
AFLOW prototype command	:	`aflow --proto=AB_cI16_199_a_a` `--params=`a, x_1, x_2

Other compounds with this structure:

- Ga_2Pu_3

- When $x_1 = 1/4$ and $x_2 = 0$, or visa versa, this structure reduces to CsCl (B2) with $a_{B2} = 1/2a$.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

	Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$ =	$2x_1\,\mathbf{a_1} + 2x_1\,\mathbf{a_2} + 2x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	($8a$)	Co

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	(8a)	Co
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} - x_1\,a\,\hat{\mathbf{z}}$	(8a)	Co
$\mathbf{B_4}$	=	$\left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{z}}$	(8a)	Co
$\mathbf{B_5}$	=	$2x_2\,\mathbf{a_1} + 2x_2\,\mathbf{a_2} + 2x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(8a)	U
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - 2x_2\right)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(8a)	U
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - 2x_2\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(8a)	U
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - 2x_2\right)\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{z}}$	(8a)	U

References:

- N. C. Baenziger, R. E. Rundle, A. I. Snow, and A. S. Wilson, *Compounds of uranium with the transition metals of the first long period*, Acta Cryst. **3**, 34–40 (1950), doi:10.1107/S0365110X50000082.

Found in:

- F. A. Rough and A. A. Bauer, *Constitution of Uranium and Thorium Alloys, Report No. BMI-1300* (UC-25 Metallurgy and Ceramics, TID-4500, 1958), 13th edn.

Geometry files:

- CIF: pp. S754
- POSCAR: pp. S754

Bergman [$Mg_{32}(Al,Zn)_{49}$] Structure: AB32C48_cI162_204_a_2efg_2gh

Prototype	:	$Mg_{32}(Al,Zn)_{49}$
AFLOW prototype label	:	AB32C48_cI162_204_a_2efg_2gh
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI162
Space group number	:	204
Space group symbol	:	$Im\bar{3}$
AFLOW prototype command	:	`aflow --proto=AB32C48_cI162_204_a_2efg_2gh` `--params=`$a, x_2, x_3, x_4, y_5, z_5, y_6, z_6, y_7, z_7, x_8, y_8, z_8$

- Most of the sites in this lattice have random occupancy. In particular, according to (Bergman, 1957): The Al-I (2a) site is only occupied 80% of the time, the Zn-I (24g) site is occupied by Al 19% of the time, the Zn-II (24g) site is occupied by Al 43% of the time, and the Zn-III (48h) site is occupied by Al 36% of the time.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Al
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12e)$	Mg I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12e)$	Mg I
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(12e)$	Mg I
$\mathbf{B_5}$	=	$-x_2\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(12e)$	Mg I
$\mathbf{B_6}$	=	$\left(\frac{1}{2} + x_2\right)\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(12e)$	Mg I
$\mathbf{B_7}$	=	$\left(\frac{1}{2} - x_2\right)\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(12e)$	Mg I
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} + x_3\right)\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12e)$	Mg II
$\mathbf{B_9}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - x_3\right)\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12e)$	Mg II
$\mathbf{B_{10}}$	=	$x_3\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \left(\frac{1}{2} + x_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}}$	$(12e)$	Mg II
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \left(\frac{1}{2} - x_3\right)\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}}$	$(12e)$	Mg II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + x_3\right)\,\mathbf{a_1} + x_3\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(12e)$	Mg II
$\mathbf{B_{13}}$	=	$\left(\frac{1}{2} - x_3\right)\,\mathbf{a_1} - x_3\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(12e)$	Mg II
$\mathbf{B_{14}}$	=	$2x_4\,\mathbf{a_1} + 2x_4\,\mathbf{a_2} + 2x_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	$(16f)$	Mg III
$\mathbf{B_{15}}$	=	$2x_4\,\mathbf{a_1}$	=	$-x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	$(16f)$	Mg III
$\mathbf{B_{16}}$	=	$2x_4\,\mathbf{a_2}$	=	$x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	$(16f)$	Mg III
$\mathbf{B_{17}}$	=	$2x_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	$(16f)$	Mg III
$\mathbf{B_{18}}$	=	$-2x_4\,\mathbf{a_1} - 2x_4\,\mathbf{a_2} - 2x_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	$(16f)$	Mg III
$\mathbf{B_{19}}$	=	$-2x_4\,\mathbf{a_1}$	=	$x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	$(16f)$	Mg III
$\mathbf{B_{20}}$	=	$-2x_4\,\mathbf{a_2}$	=	$-x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	$(16f)$	Mg III
$\mathbf{B_{21}}$	=	$-2x_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	$(16f)$	Mg III
$\mathbf{B_{22}}$	=	$(y_5 + z_5)\,\mathbf{a_1} + z_5\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{y}} + z_5\,a\,\hat{\mathbf{z}}$	$(24g)$	Mg IV
$\mathbf{B_{23}}$	=	$(z_5 - y_5)\,\mathbf{a_1} + z_5\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{y}} + z_5\,a\,\hat{\mathbf{z}}$	$(24g)$	Mg IV
$\mathbf{B_{24}}$	=	$(y_5 - z_5)\,\mathbf{a_1} - z_5\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{y}} - z_5\,a\,\hat{\mathbf{z}}$	$(24g)$	Mg IV
$\mathbf{B_{25}}$	=	$-(y_5 + z_5)\,\mathbf{a_1} - z_5\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{y}} - z_5\,a\,\hat{\mathbf{z}}$	$(24g)$	Mg IV
$\mathbf{B_{26}}$	=	$y_5\,\mathbf{a_1} + (y_5 + z_5)\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$z_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{z}}$	$(24g)$	Mg IV
$\mathbf{B_{27}}$	=	$y_5\,\mathbf{a_1} + (y_5 - z_5)\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-z_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{z}}$	$(24g)$	Mg IV
$\mathbf{B_{28}}$	=	$-y_5\,\mathbf{a_1} + (z_5 - y_5)\,\mathbf{a_2} + z_5\,\mathbf{a_3}$	=	$z_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{z}}$	$(24g)$	Mg IV
$\mathbf{B_{29}}$	=	$-y_5\,\mathbf{a_1} - (y_5 + z_5)\,\mathbf{a_2} - z_5\,\mathbf{a_3}$	=	$-z_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{z}}$	$(24g)$	Mg IV
$\mathbf{B_{30}}$	=	$z_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + (y_5 + z_5)\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + z_5\,a\,\hat{\mathbf{y}}$	$(24g)$	Mg IV
$\mathbf{B_{31}}$	=	$z_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + (z_5 - y_5)\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} + z_5\,a\,\hat{\mathbf{y}}$	$(24g)$	Mg IV
$\mathbf{B_{32}}$	=	$-z_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + (y_5 - z_5)\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} - z_5\,a\,\hat{\mathbf{y}}$	$(24g)$	Mg IV
$\mathbf{B_{33}}$	=	$-z_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} - (y_5 + z_5)\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} - z_5\,a\,\hat{\mathbf{y}}$	$(24g)$	Mg IV
$\mathbf{B_{34}}$	=	$(y_6 + z_6)\,\mathbf{a_1} + z_6\,\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{y}} + z_6\,a\,\hat{\mathbf{z}}$	$(24g)$	Zn I
$\mathbf{B_{35}}$	=	$(z_6 - y_6)\,\mathbf{a_1} + z_6\,\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{y}} + z_6\,a\,\hat{\mathbf{z}}$	$(24g)$	Zn I

$\mathbf{B_{36}}$	=	$(y_6 - z_6)\ \mathbf{a_1} - z_6\,\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{y}} - z_6\,a\,\hat{\mathbf{z}}$	(24g)	Zn I
$\mathbf{B_{37}}$	=	$-(y_6 + z_6)\ \mathbf{a_1} - z_6\,\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{y}} - z_6\,a\,\hat{\mathbf{z}}$	(24g)	Zn I
$\mathbf{B_{38}}$	=	$y_6\,\mathbf{a_1} + (y_6 + z_6)\ \mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$z_6\,a\,\hat{\mathbf{x}} + y_6\,a\,\hat{\mathbf{z}}$	(24g)	Zn I
$\mathbf{B_{39}}$	=	$y_6\,\mathbf{a_1} + (y_6 - z_6)\ \mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-z_6\,a\,\hat{\mathbf{x}} + y_6\,a\,\hat{\mathbf{z}}$	(24g)	Zn I
$\mathbf{B_{40}}$	=	$-y_6\,\mathbf{a_1} + (z_6 - y_6)\ \mathbf{a_2} + z_6\,\mathbf{a_3}$	=	$z_6\,a\,\hat{\mathbf{x}} - y_6\,a\,\hat{\mathbf{z}}$	(24g)	Zn I
$\mathbf{B_{41}}$	=	$-y_6\,\mathbf{a_1} - (y_6 + z_6)\ \mathbf{a_2} - z_6\,\mathbf{a_3}$	=	$-z_6\,a\,\hat{\mathbf{x}} - y_6\,a\,\hat{\mathbf{z}}$	(24g)	Zn I
$\mathbf{B_{42}}$	=	$z_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + (y_6 + z_6)\ \mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{x}} + z_6\,a\,\hat{\mathbf{y}}$	(24g)	Zn I
$\mathbf{B_{43}}$	=	$z_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} + (z_6 - y_6)\ \mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{x}} + z_6\,a\,\hat{\mathbf{y}}$	(24g)	Zn I
$\mathbf{B_{44}}$	=	$-z_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + (y_6 - z_6)\ \mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{x}} - z_6\,a\,\hat{\mathbf{y}}$	(24g)	Zn I
$\mathbf{B_{45}}$	=	$-z_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} - (y_6 + z_6)\ \mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{x}} - z_6\,a\,\hat{\mathbf{y}}$	(24g)	Zn I
$\mathbf{B_{46}}$	=	$(y_7 + z_7)\ \mathbf{a_1} + z_7\,\mathbf{a_2} + y_7\,\mathbf{a_3}$	=	$y_7\,a\,\hat{\mathbf{y}} + z_7\,a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{47}}$	=	$(z_7 - y_7)\ \mathbf{a_1} + z_7\,\mathbf{a_2} - y_7\,\mathbf{a_3}$	=	$-y_7\,a\,\hat{\mathbf{y}} + z_7\,a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{48}}$	=	$(y_7 - z_7)\ \mathbf{a_1} - z_7\,\mathbf{a_2} + y_7\,\mathbf{a_3}$	=	$y_7\,a\,\hat{\mathbf{y}} - z_7\,a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{49}}$	=	$-(y_7 + z_7)\ \mathbf{a_1} - z_7\,\mathbf{a_2} - y_7\,\mathbf{a_3}$	=	$-y_7\,a\,\hat{\mathbf{y}} - z_7\,a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{50}}$	=	$y_7\,\mathbf{a_1} + (y_7 + z_7)\ \mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$z_7\,a\,\hat{\mathbf{x}} + y_7\,a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{51}}$	=	$y_7\,\mathbf{a_1} + (y_7 - z_7)\ \mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$-z_7\,a\,\hat{\mathbf{x}} + y_7\,a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{52}}$	=	$-y_7\,\mathbf{a_1} + (z_7 - y_7)\ \mathbf{a_2} + z_7\,\mathbf{a_3}$	=	$z_7\,a\,\hat{\mathbf{x}} - y_7\,a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{53}}$	=	$-y_7\,\mathbf{a_1} - (y_7 + z_7)\ \mathbf{a_2} - z_7\,\mathbf{a_3}$	=	$-z_7\,a\,\hat{\mathbf{x}} - y_7\,a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{54}}$	=	$z_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + (y_7 + z_7)\ \mathbf{a_3}$	=	$y_7\,a\,\hat{\mathbf{x}} + z_7\,a\,\hat{\mathbf{y}}$	(24g)	Zn II
$\mathbf{B_{55}}$	=	$z_7\,\mathbf{a_1} - y_7\,\mathbf{a_2} + (z_7 - y_7)\ \mathbf{a_3}$	=	$-y_7\,a\,\hat{\mathbf{x}} + z_7\,a\,\hat{\mathbf{y}}$	(24g)	Zn II
$\mathbf{B_{56}}$	=	$-z_7\,\mathbf{a_1} + y_7\,\mathbf{a_2} + (y_7 - z_7)\ \mathbf{a_3}$	=	$y_7\,a\,\hat{\mathbf{x}} - z_7\,a\,\hat{\mathbf{y}}$	(24g)	Zn II
$\mathbf{B_{57}}$	=	$-z_7\,\mathbf{a_1} - y_7\,\mathbf{a_2} - (y_7 + z_7)\ \mathbf{a_3}$	=	$-y_7\,a\,\hat{\mathbf{x}} - z_7\,a\,\hat{\mathbf{y}}$	(24g)	Zn II
$\mathbf{B_{58}}$	=	$(y_8 + z_8)\ \mathbf{a_1} + (z_8 + x_8)\ \mathbf{a_2} + (x_8 + y_8)\ \mathbf{a_3}$	=	$x_8\,a\,\hat{\mathbf{x}} + y_8\,a\,\hat{\mathbf{y}} + z_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{59}}$	=	$(z_8 - y_8)\ \mathbf{a_1} + (z_8 - x_8)\ \mathbf{a_2} - (x_8 + y_8)\ \mathbf{a_3}$	=	$-x_8\,a\,\hat{\mathbf{x}} - y_8\,a\,\hat{\mathbf{y}} + z_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{60}}$	=	$(y_8 - z_8)\ \mathbf{a_1} - (z_8 + x_8)\ \mathbf{a_2} + (y_8 - x_8)\ \mathbf{a_3}$	=	$-x_8\,a\,\hat{\mathbf{x}} + y_8\,a\,\hat{\mathbf{y}} - z_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{61}}$	=	$-(y_8 + z_8)\ \mathbf{a_1} + (x_8 - z_8)\ \mathbf{a_2} + (x_8 - y_8)\ \mathbf{a_3}$	=	$x_8\,a\,\hat{\mathbf{x}} - y_8\,a\,\hat{\mathbf{y}} - z_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{62}}$	=	$-(y_8 + z_8)\ \mathbf{a_1} - (z_8 + x_8)\ \mathbf{a_2} - (x_8 + y_8)\ \mathbf{a_3}$	=	$-x_8\,a\,\hat{\mathbf{x}} - y_8\,a\,\hat{\mathbf{y}} - z_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{63}}$	=	$(y_8 - z_8)\ \mathbf{a_1} + (x_8 - z_8)\ \mathbf{a_2} + (x_8 + y_8)\ \mathbf{a_3}$	=	$+x_8\,a\,\hat{\mathbf{x}} + y_8\,a\,\hat{\mathbf{y}} - z_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{64}}$	=	$(z_8 - y_8)\ \mathbf{a_1} + (z_8 + x_8)\ \mathbf{a_2} + (x_8 - y_8)\ \mathbf{a_3}$	=	$+x_8\,a\,\hat{\mathbf{x}} - y_8\,a\,\hat{\mathbf{y}} + z_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{65}}$	=	$(y_8 + z_8)\ \mathbf{a_1} + (z_8 - x_8)\ \mathbf{a_2} + (y_8 - x_8)\ \mathbf{a_3}$	=	$-x_8\,a\,\hat{\mathbf{x}} + y_8\,a\,\hat{\mathbf{y}} + z_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{66}}$	=	$(x_8 + y_8)\ \mathbf{a_1} + (y_8 + z_8)\ \mathbf{a_2} + (z_8 + x_8)\ \mathbf{a_3}$	=	$z_8\,a\,\hat{\mathbf{x}} + x_8\,a\,\hat{\mathbf{y}} + y_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{67}}$	=	$(y_8 - x_8)\ \mathbf{a_1} + (y_8 - z_8)\ \mathbf{a_2} - (z_8 + x_8)\ \mathbf{a_3}$	=	$-z_8\,a\,\hat{\mathbf{x}} - x_8\,a\,\hat{\mathbf{y}} + y_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{68}}$	=	$(x_8 - y_8)\ \mathbf{a_1} - (y_8 + z_8)\ \mathbf{a_2} + (x_8 - z_8)\ \mathbf{a_3}$	=	$-z_8\,a\,\hat{\mathbf{x}} + x_8\,a\,\hat{\mathbf{y}} - y_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{69}}$	=	$-(x_8 + y_8)\ \mathbf{a_1} + (z_8 - y_8)\ \mathbf{a_2} + (z_8 - x_8)\ \mathbf{a_3}$	=	$z_8\,a\,\hat{\mathbf{x}} - x_8\,a\,\hat{\mathbf{y}} - y_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{70}}$	=	$-(x_8 + y_8)\ \mathbf{a_1} - (y_8 + z_8)\ \mathbf{a_2} - (z_8 + x_8)\ \mathbf{a_3}$	=	$-z_8\,a\,\hat{\mathbf{x}} - x_8\,a\,\hat{\mathbf{y}} - y_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{71}}$	=	$(x_8 - y_8)\ \mathbf{a_1} + (z_8 - y_8)\ \mathbf{a_2} + (z_8 + x_8)\ \mathbf{a_3}$	=	$+z_8\,a\,\hat{\mathbf{x}} + x_8\,a\,\hat{\mathbf{y}} - y_8\,a\,\hat{\mathbf{z}}$	(48h)	Zn III

$\mathbf{B_{72}}$	=	$(y_8 - x_8)\ \mathbf{a_1} + (y_8 + z_8)\ \mathbf{a_2} + (z_8 - x_8)\ \mathbf{a_3}$	=	$+z_8\, a\, \hat{\mathbf{x}} - x_8\, a\, \hat{\mathbf{y}} + y_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{73}}$	=	$(x_8 + y_8)\ \mathbf{a_1} + (y_8 - z_8)\ \mathbf{a_2} + (x_8 - z_8)\ \mathbf{a_3}$	=	$-z_8\, a\, \hat{\mathbf{x}} + x_8\, a\, \hat{\mathbf{y}} + y_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{74}}$	=	$(z_8 + x_8)\ \mathbf{a_1} + (x_8 + y_8)\ \mathbf{a_2} + (y_8 + z_8)\ \mathbf{a_3}$	=	$y_8\, a\, \hat{\mathbf{x}} + z_8\, a\, \hat{\mathbf{y}} + x_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{75}}$	=	$(x_8 - z_8)\ \mathbf{a_1} + (x_8 - y_8)\ \mathbf{a_2} - (y_8 + z_8)\ \mathbf{a_3}$	=	$-y_8\, a\, \hat{\mathbf{x}} - z_8\, a\, \hat{\mathbf{y}} + x_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{76}}$	=	$(z_8 - x_8)\ \mathbf{a_1} - (x_8 + y_8)\ \mathbf{a_2} + (z_8 - y_8)\ \mathbf{a_3}$	=	$-y_8\, a\, \hat{\mathbf{x}} + z_8\, a\, \hat{\mathbf{y}} - x_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{77}}$	=	$-(z_8 + x_8)\ \mathbf{a_1} + (y_8 - x_8)\ \mathbf{a_2} + (y_8 - z_8)\ \mathbf{a_3}$	=	$y_8\, a\, \hat{\mathbf{x}} - z_8\, a\, \hat{\mathbf{y}} - x_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{78}}$	=	$-(z_8 + x_8)\ \mathbf{a_1} - (x_8 + y_8)\ \mathbf{a_2} - (y_8 + z_8)\ \mathbf{a_3}$	=	$-y_8\, a\, \hat{\mathbf{x}} - z_8\, a\, \hat{\mathbf{y}} - x_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{79}}$	=	$(z_8 - x_8)\ \mathbf{a_1} + (y_8 - x_8)\ \mathbf{a_2} + (y_8 + z_8)\ \mathbf{a_3}$	=	$+y_8\, a\, \hat{\mathbf{x}} + z_8\, a\, \hat{\mathbf{y}} - x_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{80}}$	=	$(x_8 - z_8)\ \mathbf{a_1} + (x_8 + y_8)\ \mathbf{a_2} + (y_8 - z_8)\ \mathbf{a_3}$	=	$+y_8\, a\, \hat{\mathbf{x}} - z_8\, a\, \hat{\mathbf{y}} + x_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III
$\mathbf{B_{81}}$	=	$(z_8 + x_8)\ \mathbf{a_1} + (x_8 - y_8)\ \mathbf{a_2} + (z_8 - y_8)\ \mathbf{a_3}$	=	$-y_8\, a\, \hat{\mathbf{x}} + z_8\, a\, \hat{\mathbf{y}} + x_8\, a\, \hat{\mathbf{z}}$	(48h)	Zn III

References:

- G. Bergman, J. L. T. Waugh, and L. Pauling, *The crystal structure of the metallic phase $Mg_{32}(Al, Zn)_{49}$*, Acta Cryst. **10**, 254–259 (1957), doi:10.1107/S0365110X57000808.

Geometry files:

- CIF: pp. S754
- POSCAR: pp. S755

Skutterudite ($CoAs_3$, $D0_2$) Structure: A3B_cI32_204_g_c

Prototype	:	$CoAs_3$
AFLOW prototype label	:	A3B_cI32_204_g_c
***Strukturbericht* designation**	:	$D0_2$
Pearson symbol	:	cI32
Space group number	:	204
Space group symbol	:	$Im\bar{3}$
AFLOW prototype command	:	`aflow --proto=A3B_cI32_204_g_c --params=`a, y_2, z_2

- Useful skutterudites have iron and nickel alloyed with cobalt.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	Co
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	Co
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	Co

$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	Co
$\mathbf{B_5}$	=	$(y_2 + z_2)\,\mathbf{a_1} + z_2\,\mathbf{a_2} + y_2\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{y}} + z_2\,a\,\hat{\mathbf{z}}$	$(24g)$	As
$\mathbf{B_6}$	=	$(z_2 - y_2)\,\mathbf{a_1} + z_2\,\mathbf{a_2} - y_2\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{y}} + z_2\,a\,\hat{\mathbf{z}}$	$(24g)$	As
$\mathbf{B_7}$	=	$(y_2 - z_2)\,\mathbf{a_1} - z_2\,\mathbf{a_2} + y_2\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{y}} - z_2\,a\,\hat{\mathbf{z}}$	$(24g)$	As
$\mathbf{B_8}$	=	$-(y_2 + z_2)\,\mathbf{a_1} - z_2\,\mathbf{a_2} - y_2\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{y}} - z_2\,a\,\hat{\mathbf{z}}$	$(24g)$	As
$\mathbf{B_9}$	=	$y_2\,\mathbf{a_1} + (y_2 + z_2)\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$z_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{z}}$	$(24g)$	As
$\mathbf{B_{10}}$	=	$-y_2\,\mathbf{a_1} + (z_2 - y_2)\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$z_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{z}}$	$(24g)$	As
$\mathbf{B_{11}}$	=	$y_2\,\mathbf{a_1} + (y_2 - z_2)\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-z_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{z}}$	$(24g)$	As
$\mathbf{B_{12}}$	=	$-y_2\,\mathbf{a_1} - (y_2 + z_2)\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-z_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{z}}$	$(24g)$	As
$\mathbf{B_{13}}$	=	$z_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + (y_2 + z_2)\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} + z_2\,a\,\hat{\mathbf{y}}$	$(24g)$	As
$\mathbf{B_{14}}$	=	$z_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + (z_2 - y_2)\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} + z_2\,a\,\hat{\mathbf{y}}$	$(24g)$	As
$\mathbf{B_{15}}$	=	$-z_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + (y_2 - z_2)\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} - z_2\,a\,\hat{\mathbf{y}}$	$(24g)$	As
$\mathbf{B_{16}}$	=	$-z_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - (y_2 + z_2)\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} - z_2\,a\,\hat{\mathbf{y}}$	$(24g)$	As

References:

- N. Mandel and J. Donohue, *The refinement of the crystal structure of skutterudite, $CoAs_3$*, Acta Crystallogr. Sect. B Struct. Sci. **27**, 2288–2289 (1971), doi:10.1107/S0567740871005727.

Geometry files:

- CIF: pp. S755
- POSCAR: pp. S756

$Al_{12}W$ Structure: A12B_cI26_204_g_a

Prototype	:	$Al_{12}W$
AFLOW prototype label	:	A12B_cI26_204_g_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI26
Space group number	:	204
Space group symbol	:	$Im\bar{3}$
AFLOW prototype command	:	`aflow --proto=A12B_cI26_204_g_a` `--params=`a, y_2, z_2

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	W
$\mathbf{B_2}$	=	$(y_2 + z_2)\,\mathbf{a_1} + z_2\,\mathbf{a_2} + y_2\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{y}} + z_2\,a\,\hat{\mathbf{z}}$	$(24g)$	Al
$\mathbf{B_3}$	=	$(z_2 - y_2)\,\mathbf{a_1} + z_2\,\mathbf{a_2} - y_2\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{y}} + z_2\,a\,\hat{\mathbf{z}}$	$(24g)$	Al
$\mathbf{B_4}$	=	$(y_2 - z_2)\,\mathbf{a_1} - z_2\,\mathbf{a_2} + y_2\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{y}} - z_2\,a\,\hat{\mathbf{z}}$	$(24g)$	Al
$\mathbf{B_5}$	=	$-(y_2 + z_2)\,\mathbf{a_1} - z_2\,\mathbf{a_2} - y_2\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{y}} - z_2\,a\,\hat{\mathbf{z}}$	$(24g)$	Al

$\mathbf{B_6}$	=	$y_2\,\mathbf{a_1} + (y_2 + z_2)\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$z_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{z}}$	(24g)	Al
$\mathbf{B_7}$	=	$-y_2\,\mathbf{a_1} + (z_2 - y_2)\,\mathbf{a_2} + z_2\,\mathbf{a_3}$	=	$z_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{z}}$	(24g)	Al
$\mathbf{B_8}$	=	$y_2\,\mathbf{a_1} + (y_2 - z_2)\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-z_2\,a\,\hat{\mathbf{x}} + y_2\,a\,\hat{\mathbf{z}}$	(24g)	Al
$\mathbf{B_9}$	=	$-y_2\,\mathbf{a_1} - (y_2 + z_2)\,\mathbf{a_2} - z_2\,\mathbf{a_3}$	=	$-z_2\,a\,\hat{\mathbf{x}} - y_2\,a\,\hat{\mathbf{z}}$	(24g)	Al
$\mathbf{B_{10}}$	=	$z_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + (y_2 + z_2)\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} + z_2\,a\,\hat{\mathbf{y}}$	(24g)	Al
$\mathbf{B_{11}}$	=	$z_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} + (z_2 - y_2)\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} + z_2\,a\,\hat{\mathbf{y}}$	(24g)	Al
$\mathbf{B_{12}}$	=	$-z_2\,\mathbf{a_1} + y_2\,\mathbf{a_2} + (y_2 - z_2)\,\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}} - z_2\,a\,\hat{\mathbf{y}}$	(24g)	Al
$\mathbf{B_{13}}$	=	$-z_2\,\mathbf{a_1} - y_2\,\mathbf{a_2} - (y_2 + z_2)\,\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}} - z_2\,a\,\hat{\mathbf{y}}$	(24g)	Al

References:

- J. Adam and J. B. Rich, *The crystal structure of WAl_{12}, $MoAl_{12}$ and (Mn, Cr)Al_{12}*, Acta Cryst. **7**, 813–816 (1954), doi:10.1107/S0365110X54002514.

Geometry files:

- CIF: pp. S756
- POSCAR: pp. S756

α-N (Pa$\bar{3}$) Structure: A_cP8_205_c

Prototype	:	α-N
AFLOW prototype label	:	A_cP8_205_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP8
Space group number	:	205
Space group symbol	:	Pa$\bar{3}$
AFLOW prototype command	:	`aflow --proto=A_cP8_205_c --params=`a, x_1

- There is considerable controversy about the crystal structure of α-N, as outlined in (Donohue, 1982) pp. 280-285. This page assumes the centrosymmetric Pa$\bar{3}$ structure. The other possibility is the P2$_1$3 structure, where the N_2 dimers are not centered on an inversion site. (Venables, 1974) makes a convincing case that the ground state is Pa$\bar{3}$, but we present both structures. Density Functional Theory calculations show no appreciable difference in energy between the Pa$\bar{3}$ and P2$_1$3 structures (Mehl, 2015).

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	($8c$)	N
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - x_1\,\mathbf{a_2} + \left(\frac{1}{2} + x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{z}}$	($8c$)	N

$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1}+\left(\frac{1}{2}+x_1\right)\mathbf{a_2}+\left(\frac{1}{2}-x_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{z}}$	(8*c*)	N
$\mathbf{B_4}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{y}}-x_1\,a\,\hat{\mathbf{z}}$	(8*c*)	N
$\mathbf{B_5}$	=	$-x_1\,\mathbf{a_1}-x_1\,\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}}-x_1\,a\,\hat{\mathbf{y}}-x_1\,a\,\hat{\mathbf{z}}$	(8*c*)	N
$\mathbf{B_6}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+x_1\,\mathbf{a_2}+\left(\frac{1}{2}-x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{x}}+x_1\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{z}}$	(8*c*)	N
$\mathbf{B_7}$	=	$x_1\,\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}+\left(\frac{1}{2}+x_1\right)\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{z}}$	(8*c*)	N
$\mathbf{B_8}$	=	$\left(\frac{1}{2}-x_1\right)\mathbf{a_1}+\left(\frac{1}{2}+x_1\right)\mathbf{a_2}+x_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_1\right)a\,\hat{\mathbf{y}}+x_1\,a\,\hat{\mathbf{z}}$	(8*c*)	N

References:

- M. Ruhemann, *Röntgenographische Untersuchungen an festem Stickstoff und Sauerstoff*, Z. Phys. **76**, 368–385 (1932).
- T. H. Jordan, H. Warren Smith, W. E. Streib, and W. N. Lipscomb, *Single-Crystal X-Ray Diffractions Studies of α-N_2 and β-N_2*, J. Chem. Phys. **41**, 756–759 (1964), doi:10.1063/1.1725956.
- J. A. Venables and C. A. English, *Electron diffraction and the structure of α-N2*, Acta Crystallogr. Sect. B Struct. Sci. **30**, 929–935 (1974), doi:10.1107/S0567740874004067.
- M. J. Mehl, D. Finkenstadt, C. Dane, G. L. W. Hart, and S. Curtarolo, *Finding the stable structures of $N_{1-x}W_x$ with an ab initio high-throughput approach*, Phys. Rev. B **91**, 184110 (2015), doi:10.1103/PhysRevB.91.184110.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 280-285.

Geometry files:

- CIF: pp. S757
- POSCAR: pp. S757

SC16 (CuCl) Structure: AB_cP16_205_c_c

Prototype	:	CuCl
AFLOW prototype label	:	AB_cP16_205_c_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP16
Space group number	:	205
Space group symbol	:	$Pa\bar{3}$
AFLOW prototype command	:	`aflow --proto=AB_cP16_205_c_c` `--params=`a, x_1, x_2

- This is a tetragonally bonded structure which packs more efficiently than diamond. This structure is related to BC8 in the same way that zincblende (B3) is related to diamond (A4): we replace half of the atoms by another species, such that the four nearest neighbors of each atom are of the other species. See (Crain, 1995) and references therein. The reference compound chosen here, found in (Hull, 1994), is stable at about 5 GPa.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(8c)$	Cl
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - x_1\,\mathbf{a_2} + \left(\frac{1}{2} + x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{z}}$	$(8c)$	Cl

$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1}+\left(\frac{1}{2}+x_1\right)\mathbf{a_2}+\left(\frac{1}{2}-x_1\right)\mathbf{a_3}$	=	$-x_1\ a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_1\right)\ a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_1\right)\ a\,\hat{\mathbf{z}}$	(8*c*)	Cl
$\mathbf{B_4}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)\ a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)\ a\,\hat{\mathbf{y}}-x_1\ a\,\hat{\mathbf{z}}$	(8*c*)	Cl
$\mathbf{B_5}$	=	$-x_1\,\mathbf{a_1}-x_1\,\mathbf{a_2}-x_1\,\mathbf{a_3}$	=	$-x_1\ a\,\hat{\mathbf{x}}-x_1\ a\,\hat{\mathbf{y}}-x_1\ a\,\hat{\mathbf{z}}$	(8*c*)	Cl
$\mathbf{B_6}$	=	$\left(\frac{1}{2}+x_1\right)\mathbf{a_1}+x_1\,\mathbf{a_2}+\left(\frac{1}{2}-x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_1\right)\ a\,\hat{\mathbf{x}}+x_1\ a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_1\right)\ a\,\hat{\mathbf{z}}$	(8*c*)	Cl
$\mathbf{B_7}$	=	$x_1\,\mathbf{a_1}+\left(\frac{1}{2}-x_1\right)\mathbf{a_2}+\left(\frac{1}{2}+x_1\right)\mathbf{a_3}$	=	$x_1\ a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_1\right)\ a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_1\right)\ a\,\hat{\mathbf{z}}$	(8*c*)	Cl
$\mathbf{B_8}$	=	$\left(\frac{1}{2}-x_1\right)\mathbf{a_1}+\left(\frac{1}{2}+x_1\right)\mathbf{a_2}+x_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_1\right)\ a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_1\right)\ a\,\hat{\mathbf{y}}+x_1\ a\,\hat{\mathbf{z}}$	(8*c*)	Cl
$\mathbf{B_9}$	=	$x_2\,\mathbf{a_1}+x_2\,\mathbf{a_2}+x_2\,\mathbf{a_3}$	=	$x_2\ a\,\hat{\mathbf{x}}+x_2\ a\,\hat{\mathbf{y}}+x_2\ a\,\hat{\mathbf{z}}$	(8*c*)	Cu
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}-x_2\,\mathbf{a_2}+\left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)\ a\,\hat{\mathbf{x}}-x_2\ a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_2\right)\ a\,\hat{\mathbf{z}}$	(8*c*)	Cu
$\mathbf{B_{11}}$	=	$-x_2\,\mathbf{a_1}+\left(\frac{1}{2}+x_2\right)\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$-x_2\ a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_2\right)\ a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_2\right)\ a\,\hat{\mathbf{z}}$	(8*c*)	Cu
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}-x_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)\ a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_2\right)\ a\,\hat{\mathbf{y}}-x_2\ a\,\hat{\mathbf{z}}$	(8*c*)	Cu
$\mathbf{B_{13}}$	=	$-x_2\,\mathbf{a_1}-x_2\,\mathbf{a_2}-x_2\,\mathbf{a_3}$	=	$-x_2\ a\,\hat{\mathbf{x}}-x_2\ a\,\hat{\mathbf{y}}-x_2\ a\,\hat{\mathbf{z}}$	(8*c*)	Cu
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+x_2\,\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)\ a\,\hat{\mathbf{x}}+x_2\ a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_2\right)\ a\,\hat{\mathbf{z}}$	(8*c*)	Cu
$\mathbf{B_{15}}$	=	$x_2\,\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}+\left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$x_2\ a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_2\right)\ a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+x_2\right)\ a\,\hat{\mathbf{z}}$	(8*c*)	Cu
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1}+\left(\frac{1}{2}+x_2\right)\mathbf{a_2}+x_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)\ a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+x_2\right)\ a\,\hat{\mathbf{y}}+x_2\ a\,\hat{\mathbf{z}}$	(8*c*)	Cu

References:

- S. Hull and D. A. Keen, *High-pressure polymorphism of the copper(I) halides: A neutron-diffraction study to ~10 GPa*, Phys. Rev. B **50**, 5868–5885 (1994), doi:10.1103/PhysRevB.50.5868.
- J. Crain, G. J. Ackland, and S. J. Clark, *Exotic structures of tetrahedral semiconductors*, Rep. Prog. Phys. **58**, 705–754 (1995), doi:10.1088/0034-4885/58/7/001.

Geometry files:

- CIF: pp. S757
- POSCAR: pp. S758

Pyrite (FeS_2, C2) Structure: AB2_cP12_205_a_c

Prototype	:	FeS_2
AFLOW prototype label	:	AB2_cP12_205_a_c
***Strukturbericht* designation**	:	C2
Pearson symbol	:	cP12
Space group number	:	205
Space group symbol	:	$Pa\bar{3}$
AFLOW prototype command	:	`aflow --proto=AB2_cP12_205_a_c --params=`a, x_2

Other compounds with this structure:

- $AuSb_2$, CaC_2, CoS_2, MnS_2, NiS_2, $NiSe_2$, OsS_2, $OsTe_2$, $PdAs_2$, $PtAs_2$, $PtBi_2$, $RhSe_2$, RuS_2

- (Bayliss, 1997) gives crystalline data for "weakly anisotropic pyrite" which we have tabulated as P1 FeS_2. He also gives crystallographic data for the cubic pyrite structure, which we report here. Also see the C18 (marcasite) FeS_2 structure.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Fe

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(4a)	Fe
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(4a)	Fe
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	(4a)	Fe
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(8c)	S
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - x_2\right)\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{z}}$	(8c)	S
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_2} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{z}}$	(8c)	S
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + x_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(8c)	S
$\mathbf{B_9}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(8c)	S
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + x_2\right)\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{z}}$	(8c)	S
$\mathbf{B_{11}}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_2} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{z}}$	(8c)	S
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - x_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(8c)	S

References:

- P. Bayliss, *Crystal structure refinement of a weakly anisotropic pyrite*, Am. Mineral. **62**, 1168–1172 (1977).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S758
- POSCAR: pp. S758

Bixbyite (Mn_2O_3, $D5_3$) Structure: AB3C6_cI80_206_a_d_e

Prototype	:	$(Mn,Fe)_2O_3$
AFLOW prototype label	:	AB3C6_cI80_206_a_d_e
***Strukturbericht* designation**	:	$D5_3$
Pearson symbol	:	cI80
Space group number	:	206
Space group symbol	:	$Ia\bar{3}$
AFLOW prototype command	:	`aflow --proto=AB3C6_cI80_206_a_d_e` `--params=`a, x_2, x_3, y_3, z_3

Other compounds with this structure:

- Am_2O_3, As_2Mg_3, As_2Zn_3, Cd_3P_2, Ce_2O_3, Fe_2O_3, La_2O_3, Lu_2O_3, Tb_2O_3, Tm_2O_3, P_2Zn_3, many others.

- A search for "bixbyite" on the American Mineralogist Crystal Structure Database (Downs, 2003) shows two structures with the Mn atoms on the (8a) sites and one with Mn on the (8b) site. We use the structure that agrees with the data for pure Mn_2O_3 bixbyite in (Villars, 1991) Vol. IV, pp. 4346-7. The referenced data is for $(Mn,Fe)_2O_3$, with Mn and Fe randomly populating the (8a) and (24d) sites. The pictures and the CIF file put Fe atoms on the (8a) sites and Mn atoms on the (24d) sites in order to better delineate the difference in the crystallographic behavior of the sites, but both sites are randomly occupied.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8a)$	Fe
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8a)$	Fe
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8a)$	Fe
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(8a)$	Fe
$\mathbf{B_5}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(\frac{1}{4} + x_2\right)\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_6}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{1}{4} - x_2\right)\,\mathbf{a_2} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_7}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{4} + x_2\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(24d)$	Mn
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - x_2\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{4} - x_2\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_9}$	=	$\left(\frac{1}{4} + x_2\right)\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_{10}}$	=	$\left(\frac{1}{4} - x_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}\frac{1}{4}\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_{11}}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{3}{4} - x_2\right)\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_{12}}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(\frac{3}{4} + x_2\right)\,\mathbf{a_2} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_{13}}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{3}{4} - x_2\right)\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(24d)$	Mn
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2} + x_2\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{3}{4} + x_2\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{y}}$	$(24d)$	Mn
$\mathbf{B_{15}}$	=	$\left(\frac{3}{4} - x_2\right)\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_{16}}$	=	$\left(\frac{3}{4} + x_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_2\right)\,a\,\hat{\mathbf{z}}$	$(24d)$	Mn
$\mathbf{B_{17}}$	=	$(y_3 + z_3)\,\mathbf{a_1} + (x_3 + z_3)\,\mathbf{a_2} + (x_3 + y_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}} + z_3\,a\,\hat{\mathbf{z}}$	$(48e)$	O
$\mathbf{B_{18}}$	=	$\left(\frac{1}{2} - y_3 + z_3\right)\,\mathbf{a_1} + (z_3 - x_3)\,\mathbf{a_2} + \left(\frac{1}{2} - x_3 - y_3\right)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)\,a\,\hat{\mathbf{y}} + z_3\,a\,\hat{\mathbf{z}}$	$(48e)$	O
$\mathbf{B_{19}}$	=	$(y_3 - z_3)\,\mathbf{a_1} + \left(\frac{1}{2} - x_3 - z_3\right)\,\mathbf{a_2} + \left(\frac{1}{2} - x_3 + y_3\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}} - z_3\,a\,\hat{\mathbf{z}}$	$(48e)$	O
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2} - y_3 - z_3\right)\,\mathbf{a_1} + \left(\frac{1}{2} + x_3 - z_3\right)\,\mathbf{a_2} + (x_3 - y_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - z_3\right)\,a\,\hat{\mathbf{z}}$	$(48e)$	O
$\mathbf{B_{21}}$	=	$(x_3 + y_3)\,\mathbf{a_1} + (y_3 + z_3)\,\mathbf{a_2} + (z_3 + x_3)\,\mathbf{a_3}$	=	$z_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + y_3\,a\,\hat{\mathbf{z}}$	$(48e)$	O
$\mathbf{B_{22}}$	=	$\left(\frac{1}{2} - x_3 + y_3\right)\,\mathbf{a_1} + (y_3 - z_3)\,\mathbf{a_2} + \left(\frac{1}{2} - z_3 - x_3\right)\,\mathbf{a_3}$	=	$-z_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)\,a\,\hat{\mathbf{y}} + y_3\,a\,\hat{\mathbf{z}}$	$(48e)$	O

$\mathbf{B_{23}}$	=	$(x_3 - y_3)\ \mathbf{a_1} + \left(\frac{1}{2} - z_3 - y_3\right)\ \mathbf{a_2} + \left(\frac{1}{2} - z_3 + x_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{2} - z_3\right)\ a\,\hat{\mathbf{x}} + x_3\ a\,\hat{\mathbf{y}} - y_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2} - x_3 - y_3\right)\ \mathbf{a_1} + \left(\frac{1}{2} + z_3 - y_3\right)\ \mathbf{a_2} + (z_3 - x_3)\ \mathbf{a_3}$	=	$z_3\ a\,\hat{\mathbf{x}} - x_3\ a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - y_3\right)\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{25}}$	=	$(z_3 + x_3)\ \mathbf{a_1} + (x_3 + y_3)\ \mathbf{a_2} + (y_3 + z_3)\ \mathbf{a_3}$	=	$y_3\ a\,\hat{\mathbf{x}} + z_3\ a\,\hat{\mathbf{y}} + x_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2} - z_3 + x_3\right)\ \mathbf{a_1} + (x_3 - y_3)\ \mathbf{a_2} + \left(\frac{1}{2} - y_3 - z_3\right)\ \mathbf{a_3}$	=	$-y_3\ a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - z_3\right)\ a\,\hat{\mathbf{y}} + x_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{27}}$	=	$(z_3 - x_3)\ \mathbf{a_1} + \left(\frac{1}{2} - y_3 - x_3\right)\ \mathbf{a_2} + \left(\frac{1}{2} - y_3 + z_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{2} - y_3\right)\ a\,\hat{\mathbf{x}} + z_3\ a\,\hat{\mathbf{y}} - x_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{28}}$	=	$\left(\frac{1}{2} - z_3 - x_3\right)\ \mathbf{a_1} + \left(\frac{1}{2} + y_3 - x_3\right)\ \mathbf{a_2} + (y_3 - z_3)\ \mathbf{a_3}$	=	$y_3\ a\,\hat{\mathbf{x}} - z_3\ a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_3\right)\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{29}}$	=	$-(y_3 + z_3)\ \mathbf{a_1} - (x_3 + z_3)\ \mathbf{a_2} - (x_3 + y_3)\ \mathbf{a_3}$	=	$-x_3\ a\,\hat{\mathbf{x}} - y_3\ a\,\hat{\mathbf{y}} - z_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{30}}$	=	$\left(\frac{1}{2} + y_3 - z_3\right)\ \mathbf{a_1} + (x_3 - z_3)\ \mathbf{a_2} + \left(\frac{1}{2} + x_3 + y_3\right)\ \mathbf{a_3}$	=	$x_3\ a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_3\right)\ a\,\hat{\mathbf{y}} - z_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{31}}$	=	$(z_3 - y_3)\ \mathbf{a_1} + \left(\frac{1}{2} + x_3 + z_3\right)\ \mathbf{a_2} + \left(\frac{1}{2} + x_3 - y_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)\ a\,\hat{\mathbf{x}} - y_3\ a\,\hat{\mathbf{y}} + z_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{32}}$	=	$\left(\frac{1}{2} + y_3 + z_3\right)\ \mathbf{a_1} + \left(\frac{1}{2} - x_3 + z_3\right)\ \mathbf{a_2} + (y_3 - x_3)\ \mathbf{a_3}$	=	$-x_3\ a\,\hat{\mathbf{x}} + y_3\ a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + z_3\right)\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{33}}$	=	$-(x_3 + y_3)\ \mathbf{a_1} - (y_3 + z_3)\ \mathbf{a_2} - (z_3 + x_3)\ \mathbf{a_3}$	=	$-z_3\ a\,\hat{\mathbf{x}} - x_3\ a\,\hat{\mathbf{y}} - y_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{34}}$	=	$\left(\frac{1}{2} + x_3 - y_3\right)\ \mathbf{a_1} + (z_3 - y_3)\ \mathbf{a_2} + \left(\frac{1}{2} + x_3 + z_3\right)\ \mathbf{a_3}$	=	$z_3\ a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)\ a\,\hat{\mathbf{y}} - y_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{35}}$	=	$(y_3 - x_3)\ \mathbf{a_1} + \left(\frac{1}{2} + y_3 + z_3\right)\ \mathbf{a_2} + \left(\frac{1}{2} + z_3 - x_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{2} + z_3\right)\ a\,\hat{\mathbf{x}} - x_3\ a\,\hat{\mathbf{y}} + y_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{36}}$	=	$\left(\frac{1}{2} + x_3 + y_3\right)\ \mathbf{a_1} + \left(\frac{1}{2} - z_3 + y_3\right)\ \mathbf{a_2} + (x_3 - z_3)\ \mathbf{a_3}$	=	$-z_3\ a\,\hat{\mathbf{x}} + x_3\ a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + y_3\right)\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{37}}$	=	$-(x_3 + z_3)\ \mathbf{a_1} - (x_3 + y_3)\ \mathbf{a_2} - (y_3 + z_3)\ \mathbf{a_3}$	=	$-y_3\ a\,\hat{\mathbf{x}} - z_3\ a\,\hat{\mathbf{y}} - x_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{38}}$	=	$\left(\frac{1}{2} + z_3 - x_3\right)\ \mathbf{a_1} + (y_3 - x_3)\ \mathbf{a_2} + \left(\frac{1}{2} + y_3 + z_3\right)\ \mathbf{a_3}$	=	$y_3\ a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + z_3\right)\ a\,\hat{\mathbf{y}} - x_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{39}}$	=	$(x_3 - z_3)\ \mathbf{a_1} + \left(\frac{1}{2} + y_3 + x_3\right)\ \mathbf{a_2} + \left(\frac{1}{2} + y_3 - z_3\right)\ \mathbf{a_3}$	=	$\left(\frac{1}{2} + y_3\right)\ a\,\hat{\mathbf{x}} - z_3\ a\,\hat{\mathbf{y}} + x_3\ a\,\hat{\mathbf{z}}$	(48*e*)	O
$\mathbf{B_{40}}$	=	$\left(\frac{1}{2} + x_3 + z_3\right)\ \mathbf{a_1} + \left(\frac{1}{2} + x_3 - y_3\right)\ \mathbf{a_2} + (z_3 - y_3)\ \mathbf{a_3}$	=	$-y_3\ a\,\hat{\mathbf{x}} + z_3\ a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_3\right)\ a\,\hat{\mathbf{z}}$	(48*e*)	O

References:

- H. Dachs, *Die Kristallstruktur des Bixbyits (Fe,Mn)$_2$O$_3$*, Zeitschrift für Kristallographie - Crystalline Materials **107**, 370–395 (1956), doi:10.1524/zkri.1956.107.16.370.
- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S758
- POSCAR: pp. S759

BC8 (Si) Structure: A_cI16_206_c

Prototype	:	Si
AFLOW prototype label	:	A_cI16_206_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI16
Space group number	:	206
Space group symbol	:	$Ia\bar{3}$
AFLOW prototype command	:	`aflow --proto=A_cI16_206_c --params=`a, x_1

- This is a tetragonally bonded structure which packs more efficiently than diamond. See (Crain, 1995) and references therein. The reference compound chosen here, found in (Wentorf, 1963), is stable in the range 11-16 GPa.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$2x_1\,\mathbf{a_1} + 2x_1\,\mathbf{a_2} + 2x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(16c)$	Si
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(16c)$	Si
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} - x_1\,a\,\hat{\mathbf{z}}$	$(16c)$	Si
$\mathbf{B_4}$	=	$\left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}}\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{z}}$	$(16c)$	Si
$\mathbf{B_5}$	=	$-2x_1\,\mathbf{a_1} - 2x_1\,\mathbf{a_2} - 2x_1\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} - x_1\,a\,\hat{\mathbf{z}}$	$(16c)$	Si

$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_3}$	=	$x_1\ a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)\ a\,\hat{\mathbf{y}} - x_1\ a\,\hat{\mathbf{z}}$	(16*c*)	Si
$\mathbf{B_7}$	=	$\left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)\ a\,\hat{\mathbf{x}} - x_1\ a\,\hat{\mathbf{y}} + x_1\ a\,\hat{\mathbf{z}}$	(16*c*)	Si
$\mathbf{B_8}$	=	$\left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$-x_1\ a\,\hat{\mathbf{x}} + x_1\ a\,\hat{\mathbf{y}}\left(\frac{1}{2} + x_1\right)\ a\,\hat{\mathbf{z}}$	(16*c*)	Si

References:

- R. H. Wentorf, Jr., and J. S. Kasper, *Two New Forms of Silicon*, Science **139**, 338–339 (1963), doi:10.1126/science.139.3552.338-a.
- J. Crain, G. J. Ackland, and S. J. Clark, *Exotic structures of tetrahedral semiconductors*, Rep. Prog. Phys. **58**, 705–754 (1995), doi:10.1088/0034-4885/58/7/001.

Geometry files:

- CIF: pp. S759
- POSCAR: pp. S760

β-Mn (A13) Structure: A_cP20_213_cd

Prototype	:	β-Mn
AFLOW prototype label	:	A_cP20_213_cd
***Strukturbericht* designation**	:	A13
Pearson symbol	:	cP20
Space group number	:	213
Space group symbol	:	$P4_132$
AFLOW prototype command	:	`aflow --proto=A_cP20_213_cd --params=`a, x_1, y_2

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$x_1\,\mathbf{a_1} + x_1\,\mathbf{a_2} + x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	$(8c)$	Mn I
$\mathbf{B_2}$	=	$\left(\frac{1}{2} - x_1\right)\mathbf{a_1} - x_1\,\mathbf{a_2} + \left(\frac{1}{2} + x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{z}}$	$(8c)$	Mn I
$\mathbf{B_3}$	=	$-x_1\,\mathbf{a_1} + \left(\frac{1}{2} + x_1\right)\mathbf{a_2} + \left(\frac{1}{2} - x_1\right)\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{z}}$	$(8c)$	Mn I
$\mathbf{B_4}$	=	$\left(\frac{1}{2} + x_1\right)\mathbf{a_1} + \left(\frac{1}{2} - x_1\right)\mathbf{a_2} - x_1\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)a\,\hat{\mathbf{y}} - x_1\,a\,\hat{\mathbf{z}}$	$(8c)$	Mn I
$\mathbf{B_5}$	=	$\left(\frac{3}{4} + x_1\right)\mathbf{a_1} + \left(\frac{1}{4} + x_1\right)\mathbf{a_2} + \left(\frac{1}{4} - x_1\right)\mathbf{a_3}$	=	$\left(\frac{3}{4} + x_1\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_1\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_1\right)a\,\hat{\mathbf{z}}$	$(8c)$	Mn I

$\mathbf{B_6}$	=	$\left(\frac{3}{4}-x_1\right)\mathbf{a_1}+\left(\frac{3}{4}-x_1\right)\mathbf{a_2}+\left(\frac{3}{4}-x_1\right)\mathbf{a_3}$	=	$\left(\frac{3}{4}-x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{3}{4}-x_1\right)a\,\hat{\mathbf{y}}+\left(\frac{3}{4}-x_1\right)a\,\hat{\mathbf{z}}$	(8*c*)	Mn I
$\mathbf{B_7}$	=	$\left(\frac{1}{4}+x_1\right)\mathbf{a_1}+\left(\frac{1}{4}-x_1\right)\mathbf{a_2}+\left(\frac{3}{4}+x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}+x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-x_1\right)a\,\hat{\mathbf{y}}+\left(\frac{3}{4}+x_1\right)a\,\hat{\mathbf{z}}$	(8*c*)	Mn I
$\mathbf{B_8}$	=	$\left(\frac{1}{4}-x_1\right)\mathbf{a_1}+\left(\frac{3}{4}+x_1\right)\mathbf{a_2}+\left(\frac{1}{4}+x_1\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-x_1\right)a\,\hat{\mathbf{x}}+\left(\frac{3}{4}+x_1\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+x_1\right)a\,\hat{\mathbf{z}}$	(8*c*)	Mn I
$\mathbf{B_9}$	=	$\frac{1}{8}\mathbf{a_1}+y_2\,\mathbf{a_2}+\left(\frac{1}{4}+y_2\right)\mathbf{a_3}$	=	$\frac{1}{8}a\,\hat{\mathbf{x}}+y_2\,a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+y_2\right)a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{10}}$	=	$\frac{3}{8}\mathbf{a_1}-y_2\,\mathbf{a_2}+\left(\frac{3}{4}+y_2\right)\mathbf{a_3}$	=	$\frac{3}{8}a\,\hat{\mathbf{x}}-y_2\,a\,\hat{\mathbf{y}}+\left(\frac{3}{4}+y_2\right)a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{11}}$	=	$\frac{7}{8}\mathbf{a_1}+\left(\frac{1}{2}+y_2\right)\mathbf{a_2}+\left(\frac{1}{4}-y_2\right)\mathbf{a_3}$	=	$\frac{7}{8}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}-y_2\right)a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{12}}$	=	$\frac{5}{8}\mathbf{a_1}+\left(\frac{1}{2}-y_2\right)\mathbf{a_2}+\left(\frac{3}{4}-y_2\right)\mathbf{a_3}$	=	$\frac{5}{8}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)a\,\hat{\mathbf{y}}+\left(\frac{3}{4}-y_2\right)a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{13}}$	=	$\left(\frac{1}{4}+y_2\right)\mathbf{a_1}+\frac{1}{8}\mathbf{a_2}+y_2\,\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_2\right)a\,\hat{\mathbf{x}}+\frac{1}{8}a\,\hat{\mathbf{y}}+y_2\,a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{14}}$	=	$\left(\frac{3}{4}+y_2\right)\mathbf{a_1}+\frac{3}{8}\mathbf{a_2}-y_2\,\mathbf{a_3}$	=	$\left(\frac{3}{4}+y_2\right)a\,\hat{\mathbf{x}}+\frac{3}{8}a\,\hat{\mathbf{y}}-y_2\,a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{15}}$	=	$\left(\frac{1}{4}-y_2\right)\mathbf{a_1}+\frac{7}{8}\mathbf{a_2}+\left(\frac{1}{2}+y_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_2\right)a\,\hat{\mathbf{x}}+\frac{7}{8}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+y_2\right)a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{16}}$	=	$\left(\frac{3}{4}-y_2\right)\mathbf{a_1}+\frac{5}{8}\mathbf{a_2}+\left(\frac{1}{2}-y_2\right)\mathbf{a_3}$	=	$\left(\frac{3}{4}-y_2\right)a\,\hat{\mathbf{x}}+\frac{5}{8}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-y_2\right)a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{17}}$	=	$y_2\,\mathbf{a_1}+\left(\frac{1}{4}+y_2\right)\mathbf{a_2}+\frac{1}{8}\mathbf{a_3}$	=	$y_2\,a\,\hat{\mathbf{x}}+\left(\frac{1}{4}+y_2\right)a\,\hat{\mathbf{y}}+\frac{1}{8}a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{18}}$	=	$-y_2\,\mathbf{a_1}+\left(\frac{3}{4}+y_2\right)\mathbf{a_2}+\frac{3}{8}\mathbf{a_3}$	=	$-y_2\,a\,\hat{\mathbf{x}}+\left(\frac{3}{4}+y_2\right)a\,\hat{\mathbf{y}}+\frac{3}{8}a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2}+y_2\right)\mathbf{a_1}+\left(\frac{1}{4}-y_2\right)\mathbf{a_2}+\frac{7}{8}\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-y_2\right)a\,\hat{\mathbf{y}}+\frac{7}{8}a\,\hat{\mathbf{z}}$	(12*d*)	Mn II
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2}-y_2\right)\mathbf{a_1}+\left(\frac{3}{4}-y_2\right)\mathbf{a_2}+\frac{5}{8}\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_2\right)a\,\hat{\mathbf{x}}+\left(\frac{3}{4}-y_2\right)a\,\hat{\mathbf{y}}+\frac{5}{8}a\,\hat{\mathbf{z}}$	(12*d*)	Mn II

References:

- C. Brink Shoemaker, D. P. Shoemaker, T. E. Hopkins, and S. Yindepit, *Refinement of the structure of β-manganese and of a related phase in the Mn-Ni-Si system*, Acta Crystallogr. Sect. B Struct. Sci. **34**, 3573–3576 (1978), doi:10.1107/S0567740878011620.

Geometry files:

- CIF: pp. S760
- POSCAR: pp. S760

Sulvanite (Cu_3S_4V, $H2_4$) Structure: A3B4C_cP8_215_d_e_a

Prototype	:	Cu_3S_4V
AFLOW prototype label	:	A3B4C_cP8_215_d_e_a
***Strukturbericht* designation**	:	$H2_4$
Pearson symbol	:	cP8
Space group number	:	215
Space group symbol	:	$P\bar{4}3m$
AFLOW prototype command	:	`aflow --proto=A3B4C_cP8_215_d_e_a --params=`a, x_3

Other compounds with this structure:

- Cu_3S_4Nb, Cu_3S_4Ta, Cu_3Se_4Nb, Cu_3Te_4Ta, Cu_3Te_4V

- This structure is very similar to lazarevićite ($AsCu_3S_4$), except that in this case the copper atoms are on the cubic edges [the (3d) sites] rather than the cubic faces [the (3c) sites].

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	V

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(3d)$	Cu
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3d)$	Cu
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3d)$	Cu
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(4e)$	S
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(4e)$	S
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(4e)$	S
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(4e)$	S

References:

- F. J. Trojer, *Refinement of the Structure of Sulvanite*, Am. Mineral. **51**, 890–894 (1966).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S760
- POSCAR: pp. S761

Fe_4C Structure: AB4_cP5_215_a_e

Prototype	:	Fe_4C
AFLOW prototype label	:	AB4_cP5_215_a_e
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP5
Space group number	:	215
Space group symbol	:	$P\bar{4}3m$
AFLOW prototype command	:	`aflow --proto=AB4_cP5_215_a_e` `--params=`a, x_2

- When $x_2 = 1/4$, the iron atoms are at the positions of the face-centered cubic lattice. In Fe_4C, x_2 is about 0.265.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	C
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(4e)$	Fe
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(4e)$	Fe
$\mathbf{B_4}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(4e)$	Fe
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(4e)$	Fe

References:

- Z. G. Pinsker and S. V. Kaverin, *Electron-Diffraction Determination of the Structure of Iron Carbide Fe_4C*, Soviet Physics-Crystallography, translated from Kristallografiya **1**, 48–53 (1956).

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1895.

Geometry files:

- CIF: pp. S761
- POSCAR: pp. S761

Cubic Lazarevićite ($AsCu_3S_4$) Structure: AB3C4_cP8_215_a_c_e

Prototype	:	$AsCu_3S_4$
AFLOW prototype label	:	AB3C4_cP8_215_a_c_e
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP8
Space group number	:	215
Space group symbol	:	$P\bar{4}3m$
AFLOW prototype command	:	`aflow --proto=AB3C4_cP8_215_a_c_e` `--params=`a, x_3

- This structure is very similar to sulvanite ($H2_4$), except that in this case the copper atoms are on the cubic faces [the (3c) sites] rather than the cubic edges [the (3d) sites]. The actual composition of the sample under study is $Cu_3(As_{0.65}Cu_{0.20}Fe_{0.13})S_4$. We will ignore the alloying on the arsenic site here. The original reference for this structure, (Sclar, 1960), is apparently an abstract [see (Fleischer, 1961)] which does not appear in the online edition of the Geological Society of America Bulletin. We use the data for this structure printed in (Villars, 1991) Vol. I, pp. 1111-1112. Note that (Villars, 2005) gives the reference a different set of authors.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	As

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(3c)	Cu
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(3c)	Cu
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	(3c)	Cu
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(4e)	S
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(4e)	S
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(4e)	S
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(4e)	S

References:

- M. Fleischer, *New Mineral Names*, Am. Mineral. **46**, 464–468 (1961).
- C. B. Sclar and M. Drovenik, *Lazarevićite, A New Cubic Copper-Arsenic Sulfied from Bor, Jugoslavia*, Bull. Geo. Soc. Am. **71**, 1970 (1960).
- P. Villars and K. Cenzual, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag Berlin Heidelberg, 2005). Accessed through the Springer Materials site.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1111-1112.

Geometry files:

- CIF: pp. S761
- POSCAR: pp. S762

$AuBe_5$ ($C15_b$) Structure: AB5_cF24_216_a_ce

Prototype	:	$AuBe_5$
AFLOW prototype label	:	AB5_cF24_216_a_ce
***Strukturbericht* designation**	:	$C15_b$
Pearson symbol	:	cF24
Space group number	:	216
Space group symbol	:	$F\bar{4}3m$
AFLOW prototype command	:	`aflow --proto=AB5_cF24_216_a_ce --params=`a, x_3

Other compounds with this structure:

- $MgSnCu_4$, $AuNi_4Y$, Pt_5U, many more

- The lattice constant for this structure is taken from (Batchelder, 1958), which does not give the internal coordinate for the (16c) site. However, (Baenziger, 1950) assumes that uranium compounds of this type have an internal parameter $x_3 \approx 5/8$. (Pearson, 1958) uses this to infer a value of $x_3 \approx 5/8$ here as well.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{y}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{y}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Au
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(4c)$	Be I
$\mathbf{B_3}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(16e)$	Be II
$\mathbf{B_4}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - 3\,x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(16e)$	Be II
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} - 3\,x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(16e)$	Be II
$\mathbf{B_6}$	=	$-3\,x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(16e)$	Be II

References:

- N. C. Baenziger, R. E. Rundle, A. I. Snow, and A. S. Wilson, *Compounds of uranium with the transition metals of the first long period*, Acta Cryst. **3**, 34–40 (1950), doi:10.1107/S0365110X50000082.
- F. W. von Batchelder and R. F. Raeuchle, *The tetragonal MBe_{12} structure of silver, palladium, platinum and gold*, Acta Cryst. **11**, 122 (1958), doi:10.1107/S0365110X58000323.

Found in:

- W. B. Pearson, *A Handbook of Lattice Spacings and Structures of Metals and Alloys* (Pergamon Press, Oxford, 1958), pp. 406-407.

Geometry files:

- CIF: pp. S762
- POSCAR: pp. S762

Half-Heusler ($C1_b$) Structure: ABC_cF12_216_b_c_a

Prototype	:	AgAsMg
AFLOW prototype label	:	ABC_cF12_216_b_c_a
***Strukturbericht* designation**	:	$C1_b$
Pearson symbol	:	cF12
Space group number	:	216
Space group symbol	:	$F\bar{4}3m$
AFLOW prototype command	:	`aflow --proto=ABC_cF12_216_b_c_a --params=`a

Other compounds with this structure:

- MnNiSb, AuMgSn, CdLiP, BiMgNi, RhSnTi, numerous

- All of the atoms are located on the sites of a body-centered cubic lattice. This is sometimes called the "half-Heusler" structure because it is identical to the $L2_1$ (Heusler) structure with half of the copper atoms missing. The Mg and Ag atoms form a rock salt (B1) structure, while the As and either the Mg or Ag atoms form a zincblende (B3) structure. If the atoms on the (4a) and (4c) sites are identical, this reduces to the fluorite (C1) structure.

Face-centered Cubic primitive vectors:

$$\mathbf{a_1} = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a_2} = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a_3} = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	(4*a*)	Mg
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_1} + \frac{1}{2}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(4*b*)	Ag
$\mathbf{B_3}$	=	$\frac{1}{4}\mathbf{a_1} + \frac{1}{4}\mathbf{a_2} + \frac{1}{4}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(4*c*)	As

References:

- H. Nowotny and W. Sibert, *Ternäre Valenzverbindungen in den Systemen Kupfer(Silber)-Arsen(Antimon,Wismut)-Magnesium*, Z. Metallkd. **33**, 391–394 (1941).

Found in:

- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 386.

Geometry files:

- CIF: pp. S763
- POSCAR: pp. S763

Zincblende (ZnS, B3) Structure: AB_cF8_216_c_a

Prototype	:	ZnS
AFLOW prototype label	:	AB_cF8_216_c_a
***Strukturbericht* designation**	:	B3
Pearson symbol	:	cF8
Space group number	:	216
Space group symbol	:	F$\bar{4}$3m
AFLOW prototype command	:	`aflow --proto=AB_cF8_216_c_a --params=`a

- This is the cubic analog of the wurtzite lattice, i.e. the stacking of the ZnS dimers along the <111> direction is ABCABC ... This is also a two-component analog of the diamond structure, without the inversion symmetry in the middle of the bond.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	($4a$)	Zn
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	($4c$)	S

References:

- B. J. Skinner, *Unit-Cell Edges of Natural and Synthetic Sphalerites*, Am. Mineral. **46**, 1399–1411 (1961).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S763
- POSCAR: pp. S764

SiF_4 Structure: A4B_cI10_217_c_a

Prototype	:	SiF_4
AFLOW prototype label	:	A4B_cI10_217_c_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI10
Space group number	:	217
Space group symbol	:	$I\bar{4}3m$
AFLOW prototype command	:	`aflow --proto=A4B_cI10_217_c_a --params=`a, x_2

- We determined the lattice constant for this structure from the internal coordinates and the Si-F bond length given in the reference.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Si
$\mathbf{B_2}$	=	$2x_2\,\mathbf{a_1} + 2x_2\,\mathbf{a_2} + 2x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(8c)$	F
$\mathbf{B_3}$	=	$-2x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(8c)$	F
$\mathbf{B_4}$	=	$-2x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(8c)$	F
$\mathbf{B_5}$	=	$-2x_2\,\mathbf{a_1}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(8c)$	F

References:

- M. Atoji and W. N. Lipscomb, *The structure of* SiF_4, Acta Cryst. **7**, 597 (1954), doi:10.1107/S0365110X5400196X.

Geometry files:

- CIF: pp. S764
- POSCAR: pp. S765

α-Mn (A12) Structure: A_cI58_217_ac2g

Prototype	:	α-Mn
AFLOW prototype label	:	A_cI58_217_ac2g
***Strukturbericht* designation**	:	A12
Pearson symbol	:	cI58
Space group number	:	217
Space group symbol	:	I$\bar{4}$3m
AFLOW prototype command	:	`aflow --proto=A_cI58_217_ac2g` `--params=`$a, x_2, x_3, z_3, x_4, z_4$

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Mn I
$\mathbf{B_2}$	=	$2x_2\,\mathbf{a_1} + 2x_2\,\mathbf{a_2} + 2x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(8c)$	Mn II
$\mathbf{B_3}$	=	$-2x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(8c)$	Mn II

$\mathbf{B_4}$	=	$-2x_2\,\mathbf{a_2}$	=	$-x_2\ a\,\hat{\mathbf{x}} + x_2\ a\,\hat{\mathbf{y}} - x_2\ a\,\hat{\mathbf{z}}$	(8*c*)	Mn II
$\mathbf{B_5}$	=	$-2x_2\,\mathbf{a_1}$	=	$x_2\ a\,\hat{\mathbf{x}} - x_2\ a\,\hat{\mathbf{y}} - x_2\ a\,\hat{\mathbf{z}}$	(8*c*)	Mn II
$\mathbf{B_6}$	=	$(x_3+z_3)\ \mathbf{a_1} + (x_3+z_3)\ \mathbf{a_2} + 2x_3\,\mathbf{a_3}$	=	$x_3\ a\,\hat{\mathbf{x}} + x_3\ a\,\hat{\mathbf{y}} + z_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_7}$	=	$(z_3-x_3)\ \mathbf{a_1} + (z_3-x_3)\ \mathbf{a_2} - 2x_3\,\mathbf{a_3}$	=	$-x_3\ a\,\hat{\mathbf{x}} - x_3\ a\,\hat{\mathbf{y}} + z_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_8}$	=	$(x_3-z_3)\ \mathbf{a_1} - (x_3+z_3)\ \mathbf{a_2}$	=	$-x_3\ a\,\hat{\mathbf{x}} + x_3\ a\,\hat{\mathbf{y}} - z_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_9}$	=	$-(x_3+z_3)\ \mathbf{a_1} + (x_3-z_3)\ \mathbf{a_2}$	=	$x_3\ a\,\hat{\mathbf{x}} - x_3\ a\,\hat{\mathbf{y}} - z_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{10}}$	=	$2x_3\,\mathbf{a_1} + (x_3+z_3)\ \mathbf{a_2} + (x_3+z_3)\ \mathbf{a_3}$	=	$z_3\ a\,\hat{\mathbf{x}} + x_3\ a\,\hat{\mathbf{y}} + x_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{11}}$	=	$-2x_3\,\mathbf{a_1} + (z_3-x_3)\ \mathbf{a_2} + (z_3-x_3)\ \mathbf{a_3}$	=	$z_3\ a\,\hat{\mathbf{x}} - x_3\ a\,\hat{\mathbf{y}} - x_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{12}}$	=	$(x_3-z_3)\ \mathbf{a_2} - (x_3+z_3)\ \mathbf{a_3}$	=	$-z_3\ a\,\hat{\mathbf{x}} - x_3\ a\,\hat{\mathbf{y}} + x_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{13}}$	=	$-(x_3+z_3)\ \mathbf{a_2} + (x_3-z_3)\ \mathbf{a_3}$	=	$-z_3\ a\,\hat{\mathbf{x}} + x_3\ a\,\hat{\mathbf{y}} - x_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{14}}$	=	$(x_3+z_3)\ \mathbf{a_1} + 2x_3\,\mathbf{a_2} + (x_3+z_3)\ \mathbf{a_3}$	=	$x_3\ a\,\hat{\mathbf{x}} + z_3\ a\,\hat{\mathbf{y}} + x_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{15}}$	=	$(z_3-x_3)\ \mathbf{a_1} - 2x_3\,\mathbf{a_2} + (z_3-x_3)\ \mathbf{a_3}$	=	$-x_3\ a\,\hat{\mathbf{x}} + z_3\ a\,\hat{\mathbf{y}} - x_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{16}}$	=	$-(x_3+z_3)\ \mathbf{a_1} + (x_3-z_3)\ \mathbf{a_3}$	=	$x_3\ a\,\hat{\mathbf{x}} - z_3\ a\,\hat{\mathbf{y}} - x_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{17}}$	=	$(x_3-z_3)\ \mathbf{a_1} - (x_3+z_3)\ \mathbf{a_3}$	=	$-x_3\ a\,\hat{\mathbf{x}} - z_3\ a\,\hat{\mathbf{y}} + x_3\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn III
$\mathbf{B_{18}}$	=	$(x_4+z_4)\ \mathbf{a_1} + (x_4+z_4)\ \mathbf{a_2} + 2x_4\,\mathbf{a_3}$	=	$x_4\ a\,\hat{\mathbf{x}} + x_4\ a\,\hat{\mathbf{y}} + z_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{19}}$	=	$(z_4-x_4)\ \mathbf{a_1} + (z_4-x_4)\ \mathbf{a_2} - 2x_4\,\mathbf{a_3}$	=	$-x_4\ a\,\hat{\mathbf{x}} - x_4\ a\,\hat{\mathbf{y}} + z_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{20}}$	=	$(x_4-z_4)\ \mathbf{a_1} - (x_4+z_4)\ \mathbf{a_2}$	=	$-x_4\ a\,\hat{\mathbf{x}} + x_4\ a\,\hat{\mathbf{y}} - z_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{21}}$	=	$-(x_4+z_4)\ \mathbf{a_1} + (x_4-z_4)\ \mathbf{a_2}$	=	$x_4\ a\,\hat{\mathbf{x}} - x_4\ a\,\hat{\mathbf{y}} - z_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{22}}$	=	$2x_4\,\mathbf{a_1} + (x_4+z_4)\ \mathbf{a_2} + (x_4+z_4)\ \mathbf{a_3}$	=	$z_4\ a\,\hat{\mathbf{x}} + x_4\ a\,\hat{\mathbf{y}} + x_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{23}}$	=	$-2x_4\,\mathbf{a_1} + (z_4-x_4)\ \mathbf{a_2} + (z_4-x_4)\ \mathbf{a_3}$	=	$z_4\ a\,\hat{\mathbf{x}} - x_4\ a\,\hat{\mathbf{y}} - x_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{24}}$	=	$(x_4-z_4)\ \mathbf{a_2} - (x_4+z_4)\ \mathbf{a_3}$	=	$-z_4\ a\,\hat{\mathbf{x}} - x_4\ a\,\hat{\mathbf{y}} + x_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{25}}$	=	$-(x_4+z_4)\ \mathbf{a_2} + (x_4-z_4)\ \mathbf{a_3}$	=	$-z_4\ a\,\hat{\mathbf{x}} + x_4\ a\,\hat{\mathbf{y}} - x_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{26}}$	=	$(x_4+z_4)\ \mathbf{a_1} + 2x_4\,\mathbf{a_2} + (x_4+z_4)\ \mathbf{a_3}$	=	$x_4\ a\,\hat{\mathbf{x}} + z_4\ a\,\hat{\mathbf{y}} + x_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{27}}$	=	$(z_4-x_4)\ \mathbf{a_1} - 2x_4\,\mathbf{a_2} + (z_4-x_4)\ \mathbf{a_3}$	=	$-x_4\ a\,\hat{\mathbf{x}} + z_4\ a\,\hat{\mathbf{y}} - x_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{28}}$	=	$-(x_4+z_4)\ \mathbf{a_1} + (x_4-z_4)\ \mathbf{a_3}$	=	$x_4\ a\,\hat{\mathbf{x}} - z_4\ a\,\hat{\mathbf{y}} - x_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV
$\mathbf{B_{29}}$	=	$(x_4-z_4)\ \mathbf{a_1} - (x_4+z_4)\ \mathbf{a_3}$	=	$-x_4\ a\,\hat{\mathbf{x}} - z_4\ a\,\hat{\mathbf{y}} + x_4\ a\,\hat{\mathbf{z}}$	(24*g*)	Mn IV

References:

- J. A. Oberteuffer and J. A. Ibers, *A refinement of the atomic and thermal parameters of α-manganese from a single crystal*, Acta Crystallogr. Sect. B Struct. Sci. **26**, 1499–1504 (1970), doi:10.1107/S0567740870004399.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 191-196.

Geometry files:

- CIF: pp. S765
- POSCAR: pp. S765

γ-Brass (Cu_5Zn_8) Structure: A5B8_cI52_217_ce_cg

Prototype	:	Cu_5Zn_8
AFLOW prototype label	:	A5B8_cI52_217_ce_cg
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI52
Space group number	:	217
Space group symbol	:	$I\bar{4}3m$
AFLOW prototype command	:	`aflow --proto=A5B8_cI52_217_ce_cg` `--params=`$a, x_1, x_2, x_3, x_4, z_4$

Other compounds with this structure:

- Cu_xZn_{1-x}, Cu_xCd_{1-x}, Fe_xZn_{1-x}

- γ-Brass comes in a variety of compositions. We use the data from (Gourdon, 2007) for $Cu_{5.00}Zn_{8.00}$. At this composition the authors state that the sites are fully occupied as given below.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}a\,\hat{\mathbf{x}} - \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} - \tfrac{1}{2}a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$2x_1\,\mathbf{a_1} + 2x_1\,\mathbf{a_2} + 2x_1\,\mathbf{a_3}$	=	$x_1\ a\,\hat{\mathbf{x}} + x_1\ a\,\hat{\mathbf{y}} + x_1\ a\,\hat{\mathbf{z}}$	(8c)	Cu I
$\mathbf{B_2}$	=	$-2x_1\,\mathbf{a_3}$	=	$-x_1\ a\,\hat{\mathbf{x}} - x_1\ a\,\hat{\mathbf{y}} + x_1\ a\,\hat{\mathbf{z}}$	(8c)	Cu I
$\mathbf{B_3}$	=	$-2x_1\,\mathbf{a_2}$	=	$-x_1\ a\,\hat{\mathbf{x}} + x_1\ a\,\hat{\mathbf{y}} - x_1\ a\,\hat{\mathbf{z}}$	(8c)	Cu I
$\mathbf{B_4}$	=	$-2x_1\,\mathbf{a_1}$	=	$x_1\ a\,\hat{\mathbf{x}} - x_1\ a\,\hat{\mathbf{y}} - x_1\ a\,\hat{\mathbf{z}}$	(8c)	Cu I
$\mathbf{B_5}$	=	$2x_2\,\mathbf{a_1} + 2x_2\,\mathbf{a_2} + 2x_2\,\mathbf{a_3}$	=	$x_2\ a\,\hat{\mathbf{x}} + x_2\ a\,\hat{\mathbf{y}} + x_2\ a\,\hat{\mathbf{z}}$	(8c)	Zn I
$\mathbf{B_6}$	=	$-2x_2\,\mathbf{a_3}$	=	$-x_2\ a\,\hat{\mathbf{x}} - x_2\ a\,\hat{\mathbf{y}} + x_2\ a\,\hat{\mathbf{z}}$	(8c)	Zn I
$\mathbf{B_7}$	=	$-2x_2\,\mathbf{a_2}$	=	$-x_2\ a\,\hat{\mathbf{x}} + x_2\ a\,\hat{\mathbf{y}} - x_2\ a\,\hat{\mathbf{z}}$	(8c)	Zn I
$\mathbf{B_8}$	=	$-2x_2\,\mathbf{a_1}$	=	$x_2\ a\,\hat{\mathbf{x}} - x_2\ a\,\hat{\mathbf{y}} - x_2\ a\,\hat{\mathbf{z}}$	(8c)	Zn I
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\ a\,\hat{\mathbf{x}}$	(12e)	Cu II
$\mathbf{B_{10}}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_3}$	=	$x_3\ a\,\hat{\mathbf{y}}$	(12e)	Cu II
$\mathbf{B_{11}}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2}$	=	$x_3\ a\,\hat{\mathbf{z}}$	(12e)	Cu II
$\mathbf{B_{12}}$	=	$-x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\ a\,\hat{\mathbf{x}}$	(12e)	Cu II
$\mathbf{B_{13}}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_3}$	=	$-x_3\ a\,\hat{\mathbf{y}}$	(12e)	Cu II
$\mathbf{B_{14}}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2}$	=	$-x_3\ a\,\hat{\mathbf{z}}$	(12e)	Cu II
$\mathbf{B_{15}}$	=	$(x_4 + z_4)\,\mathbf{a_1} + (x_4 + z_4)\,\mathbf{a_2} + 2x_4\,\mathbf{a_3}$	=	$x_4\ a\,\hat{\mathbf{x}} + x_4\ a\,\hat{\mathbf{y}} + z_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{16}}$	=	$(z_4 - x_4)\,\mathbf{a_1} + (z_4 - x_4)\,\mathbf{a_2} - 2x_4\,\mathbf{a_3}$	=	$-x_4\ a\,\hat{\mathbf{x}} - x_4\ a\,\hat{\mathbf{y}} + z_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{17}}$	=	$(x_4 - z_4)\,\mathbf{a_1} - (x_4 + z_4)\,\mathbf{a_2}$	=	$-x_4\ a\,\hat{\mathbf{x}} + x_4\ a\,\hat{\mathbf{y}} - z_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{18}}$	=	$-(x_4 + z_4)\,\mathbf{a_1} + (x_4 - z_4)\,\mathbf{a_2}$	=	$x_4\ a\,\hat{\mathbf{x}} - x_4\ a\,\hat{\mathbf{y}} - z_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{19}}$	=	$2x_4\,\mathbf{a_1} + (x_4 + z_4)\,\mathbf{a_2} + (x_4 + z_4)\,\mathbf{a_3}$	=	$z_4\ a\,\hat{\mathbf{x}} + x_4\ a\,\hat{\mathbf{y}} + x_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{20}}$	=	$-2x_4\,\mathbf{a_1} + (z_4 - x_4)\,\mathbf{a_2} + (z_4 - x_4)\,\mathbf{a_3}$	=	$z_4\ a\,\hat{\mathbf{x}} - x_4\ a\,\hat{\mathbf{y}} - x_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{21}}$	=	$(x_4 - z_4)\,\mathbf{a_2} - (x_4 + z_4)\,\mathbf{a_3}$	=	$-z_4\ a\,\hat{\mathbf{x}} - x_4\ a\,\hat{\mathbf{y}} + x_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{22}}$	=	$-(x_4 + z_4)\,\mathbf{a_2} + (x_4 - z_4)\,\mathbf{a_3}$	=	$-z_4\ a\,\hat{\mathbf{x}} + x_4\ a\,\hat{\mathbf{y}} - x_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{23}}$	=	$(x_4 + z_4)\,\mathbf{a_1} + 2x_4\,\mathbf{a_2} + (x_4 + z_4)\,\mathbf{a_3}$	=	$x_4\ a\,\hat{\mathbf{x}} + z_4\ a\,\hat{\mathbf{y}} + x_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{24}}$	=	$(z_4 - x_4)\,\mathbf{a_1} - 2x_4\,\mathbf{a_2} + (z_4 - x_4)\,\mathbf{a_3}$	=	$-x_4\ a\,\hat{\mathbf{x}} + z_4\ a\,\hat{\mathbf{y}} - x_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{25}}$	=	$-(x_4 + z_4)\,\mathbf{a_1} + (x_4 - z_4)\,\mathbf{a_3}$	=	$x_4\ a\,\hat{\mathbf{x}} - z_4\ a\,\hat{\mathbf{y}} - x_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II
$\mathbf{B_{26}}$	=	$(x_4 - z_4)\,\mathbf{a_1} - (x_4 + z_4)\,\mathbf{a_3}$	=	$-x_4\ a\,\hat{\mathbf{x}} - z_4\ a\,\hat{\mathbf{y}} + x_4\ a\,\hat{\mathbf{z}}$	(24g)	Zn II

References:

- O. Gourdon, D. Gout, D. J. Williams, T. Proffen, S. Hobbs, and G. J. Miller, *Atomic Distributions in the γ-Brass Structure of the Cu-Zn System: A Structural and Theoretical Study*, Inorg. Chem. **46**, 251–260 (2007), doi:10.1021/ic0616380.

Geometry files:

- CIF: pp. S766
- POSCAR: pp. S766

High-Pressure cI16 Li Structure: A_cI16_220_c

Prototype	:	Li
AFLOW prototype label	:	A_cI16_220_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI16
Space group number	:	220
Space group symbol	:	I$\bar{4}$3d
AFLOW prototype command	:	`aflow --proto=A_cI16_220_c --params=`a, x_1

Other compounds with this structure:

- Na (under pressure)

- This is a high-pressure phase of lithium. We use the data from (Hanfland, 2000) at 38.9 GPa. When $x_1 = 0$ this becomes a body-centered cubic (A2) system. We have used the fact that all vectors of the form $(\pm a/2\hat{\mathbf{x}} \pm a/2\hat{\mathbf{y}} \pm a/2\hat{\mathbf{z}})$ are primitive vectors of the body-centered cubic lattice to simplify the positions of some atoms in both lattice and Cartesian coordinates.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$2x_1\,\mathbf{a_1} + 2x_1\,\mathbf{a_2} + 2x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	(16c)	Li
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	(16c)	Li
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} - x_1\,a\,\hat{\mathbf{z}}$	(16c)	Li
$\mathbf{B_4}$	=	$\left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$+x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}}\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{z}}$	(16c)	Li
$\mathbf{B_5}$	=	$\left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_1} + \left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_2} + \left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{z}}$	(16c)	Li
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} - 2x_1\,\mathbf{a_3}$	=	$\left(\frac{3}{4} - x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_1\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{z}}$	(16c)	Li
$\mathbf{B_7}$	=	$-2x_1\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{3}{4} - x_1\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_1\right)\,a\,\hat{\mathbf{z}}$	(16c)	Li
$\mathbf{B_8}$	=	$-2x_1\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - x_1\right)\,a\,\hat{\mathbf{z}}$	(16c)	Li

References:

- M. Hanfland, K. Syassen, N. E. Christensen, and D. L. Novikov, *New high-pressure phases of lithium*, Nature **408**, 174–178 (2000), doi:10.1038/35041515.

Geometry files:

- CIF: pp. S766
- POSCAR: pp. S767

Pu_2C_3 ($D5_c$) Structure: A3B2_cI40_220_d_c

Prototype	:	Pu_2C_3
AFLOW prototype label	:	A3B2_cI40_220_d_c
***Strukturbericht* designation**	:	$D5_c$
Pearson symbol	:	cI40
Space group number	:	220
Space group symbol	:	$I\bar{4}3d$
AFLOW prototype command	:	`aflow --proto=A3B2_cI40_220_d_c --params=`a, x_1, x_2

Other compounds with this structure:

- Am_2C_3, C_3Ce_2, C_3Hf_2, Ru_2Y_3, C_3U_2, Er_3Ru_2, C_3Y_2, many others.

- We use the data for ^{240}Pu.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$2x_1\,\mathbf{a_1} + 2x_1\,\mathbf{a_2} + 2x_1\,\mathbf{a_3}$	=	$x_1\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	(16*c*)	Pu
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_3}$	=	$-x_1\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{y}} + x_1\,a\,\hat{\mathbf{z}}$	(16*c*)	Pu
$\mathbf{B_3}$	=	$\left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{x}} + x_1\,a\,\hat{\mathbf{y}} - x_1\,a\,\hat{\mathbf{z}}$	(16*c*)	Pu
$\mathbf{B_4}$	=	$\left(\frac{1}{2} - 2x_1\right)\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$+x_1\,a\,\hat{\mathbf{x}} - x_1\,a\,\hat{\mathbf{y}}\left(\frac{1}{2} - x_1\right)\,a\,\hat{\mathbf{z}}$	(16*c*)	Pu
$\mathbf{B_5}$	=	$\left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_1} + \left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_2} + \left(\frac{1}{2} + 2x_1\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{z}}$	(16*c*)	Pu
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} - 2x_1\,\mathbf{a_3}$	=	$\left(\frac{3}{4} - x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_1\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{z}}$	(16*c*)	Pu
$\mathbf{B_7}$	=	$-2x_1\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{3}{4} - x_1\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_1\right)\,a\,\hat{\mathbf{z}}$	(16*c*)	Pu
$\mathbf{B_8}$	=	$-2x_1\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_1\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_1\right)\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - x_1\right)\,a\,\hat{\mathbf{z}}$	(16*c*)	Pu
$\mathbf{B_9}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(\frac{1}{4} + x_2\right)\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{10}}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{1}{4} - x_2\right)\,\mathbf{a_2} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{11}}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{4} + x_2\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	(24*d*)	C
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - x_2\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{4} - x_2\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{13}}$	=	$\left(\frac{1}{4} + x_2\right)\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{14}}$	=	$\left(\frac{1}{4} - x_2\right)\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{15}}$	=	$\left(\frac{3}{4} + x_2\right)\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{16}}$	=	$\left(\frac{3}{4} - x_2\right)\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{17}}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\,\mathbf{a_2} + \left(\frac{3}{4} + x_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{18}}$	=	$\frac{1}{4}\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{3}{4} - x_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2} + x_2\right)\,\mathbf{a_1} + \left(\frac{3}{4} + x_2\right)\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{z}}$	(24*d*)	C
$\mathbf{B_{20}}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{3}{4} - x_2\right)\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{z}}$	(24*d*)	C

References:

- J. L. Green, G. P. Arnold, J. A. Leary, and N. G. Nereson, *Crystallographic and magnetic ordering studies of plutonium carbides using neutron diffraction*, J. Nucl. Mater. **34**, 281–289 (1970), doi:10.1016/0022-3115(70)90194-7.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1993.

Geometry files:

- CIF: pp. S767
- POSCAR: pp. S767

CsCl (B2) Structure: AB_cP2_221_b_a

Prototype	:	CsCl
AFLOW prototype label	:	AB_cP2_221_b_a
***Strukturbericht* designation**	:	B2
Pearson symbol	:	cP2
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB_cP2_221_b_a --params=`a

Other compounds with this structure:

- CsBr, CsI, RbCl, AlCo, AgZn, BeCu, MgCe, RuAl, SrTl

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cs
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(1b)$	Cl

References:

- V. Ganesan and K. S. Girirajan, *Lattice parameter and thermal expansion of CsCl and CsBr by x-ray powder diffraction. I. Thermal expansion of CsCl from room temperature to 90° K*, Pramana – Journal of Physics **27**, 469–474 (1986).

Geometry files:
- CIF: pp. S768
- POSCAR: pp. S768

NbO Structure: AB_cP6_221_c_d

Prototype	:	NbO
AFLOW prototype label	:	AB_cP6_221_c_d
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP6
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB_cP6_221_c_d --params=`a

- This is the NaCl (B1) structure with 25% ordered vacancies on both the Na and Cl sites.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B}_1$	=	$\frac{1}{2}\,\mathbf{a}_2 + \frac{1}{2}\,\mathbf{a}_3$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	Nb
$\mathbf{B}_2$	=	$\frac{1}{2}\,\mathbf{a}_1 + \frac{1}{2}\,\mathbf{a}_3$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	Nb
$\mathbf{B}_3$	=	$\frac{1}{2}\,\mathbf{a}_1 + \frac{1}{2}\,\mathbf{a}_2$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3c)$	Nb
$\mathbf{B}_4$	=	$\frac{1}{2}\,\mathbf{a}_1$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(3d)$	O
$\mathbf{B}_5$	=	$\frac{1}{2}\,\mathbf{a}_2$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3d)$	O
$\mathbf{B}_6$	=	$\frac{1}{2}\,\mathbf{a}_3$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3d)$	O

References:

- A. L. Bowman, T. C. Wallace, J. L. Yarnell, and R. G. Wenzel, *The crystal structure of niobium monoxide*, Acta Cryst. **21**, 843 (1966), doi:10.1107/S0365110X66004043.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4535.

Geometry files:

- CIF: pp. S768
- POSCAR: pp. S769

Cubic Perovskite ($CaTiO_3$, $E2_1$) Structure: AB3C_cP5_221_a_c_b

Prototype	:	$CaTiO_3$
AFLOW prototype label	:	AB3C_cP5_221_a_c_b
***Strukturbericht* designation**	:	$E2_1$
Pearson symbol	:	cP5
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB3C_cP5_221_a_c_b --params=`a

Other compounds with this structure:

- $BaTiO_3$, $PbTiO_3$, $PbZrO_3$

- Cubic perovskite is actually the high-temperature phase of the compounds listed below. The ground states are usually distorted perovskite structures. Many of these substances are ferroelectric. By removing one atom type we get various structures, all with space group $Pm\bar{3}m$: Removing the calcium atoms leads to the α-ReO_3 ($D0_9$) structure; removing the titanium atoms leads to the Cu_3Au ($L1_2$) structure; removing the oxygen atoms leads to the CsCl (B2) structure; removing the calcium or titanium and the oxygen atoms leads to the simple cubic (A_h) structure.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Ca
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(1b)$	Ti
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	O
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	O
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3c)$	O

References:

- T. Barth, *Die Kristallstruktur von Perowskit und verwandten Verbindungen*, Norsk. Geol. Tidssk. **8**, 14–19 (1925).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S769
- POSCAR: pp. S769

Model of Austenite Structure (cP32): AB27CD3_cP32_221_a_dij_b_c

Prototype	:	$CrFe_{27}MoNi_3$
AFLOW prototype label	:	AB27CD3_cP32_221_a_dij_b_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP32
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB27CD3_cP32_221_a_dij_b_c` `--params=`a, y_5, y_6

- Austenitic steels are alloys of iron and other metals with an averaged face-centered cubic structure. This model represents one approximation for an austenite steel. It is not meant to represent a real steel, and the selection of atom types for each Wyckoff position is arbitrary. Note that when $y_5 = y_6 = 1/4$ all the atoms are on sites of an fcc lattice.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cr

$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(1b)$	Mo
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	Ni
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	Ni
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3c)$	Ni
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(3d)$	Fe I
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3d)$	Fe I
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3d)$	Fe I
$\mathbf{B_9}$	=	$y_5\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{y}} + y_5\,a\,\hat{\mathbf{z}}$	$(12i)$	Fe II
$\mathbf{B_{10}}$	=	$-y_5\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{y}} + y_5\,a\,\hat{\mathbf{z}}$	$(12i)$	Fe II
$\mathbf{B_{11}}$	=	$y_5\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{y}} - y_5\,a\,\hat{\mathbf{z}}$	$(12i)$	Fe II
$\mathbf{B_{12}}$	=	$-y_5\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{y}} - y_5\,a\,\hat{\mathbf{z}}$	$(12i)$	Fe II
$\mathbf{B_{13}}$	=	$y_5\,\mathbf{a_1} + y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{z}}$	$(12i)$	Fe II
$\mathbf{B_{14}}$	=	$-y_5\,\mathbf{a_1} + y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{z}}$	$(12i)$	Fe II
$\mathbf{B_{15}}$	=	$y_5\,\mathbf{a_1} - y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{z}}$	$(12i)$	Fe II
$\mathbf{B_{16}}$	=	$-y_5\,\mathbf{a_1} - y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{z}}$	$(12i)$	Fe II
$\mathbf{B_{17}}$	=	$y_5\,\mathbf{a_1} + y_5\,\mathbf{a_2}$	=	$y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}}$	$(12i)$	Fe II
$\mathbf{B_{18}}$	=	$-y_5\,\mathbf{a_1} + y_5\,\mathbf{a_2}$	=	$-y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}}$	$(12i)$	Fe II
$\mathbf{B_{19}}$	=	$y_5\,\mathbf{a_1} - y_5\,\mathbf{a_2}$	=	$y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}}$	$(12i)$	Fe II
$\mathbf{B_{20}}$	=	$-y_5\,\mathbf{a_1} - y_5\,\mathbf{a_2}$	=	$-y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}}$	$(12i)$	Fe II
$\mathbf{B_{21}}$	=	$\frac{1}{2}\,\mathbf{a_1} + y_6\,\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_6\,a\,\hat{\mathbf{y}} + y_6\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{22}}$	=	$\frac{1}{2}\,\mathbf{a_1} - y_6\,\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_6\,a\,\hat{\mathbf{y}} + y_6\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{23}}$	=	$\frac{1}{2}\,\mathbf{a_1} + y_6\,\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_6\,a\,\hat{\mathbf{y}} - y_6\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{24}}$	=	$\frac{1}{2}\,\mathbf{a_1} - y_6\,\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_6\,a\,\hat{\mathbf{y}} - y_6\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{25}}$	=	$y_6\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + y_6\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{26}}$	=	$-y_6\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + y_6\,\mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + y_6\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{27}}$	=	$y_6\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} - y_6\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{28}}$	=	$-y_6\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - y_6\,\mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} - y_6\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{29}}$	=	$y_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{x}} + y_6\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{30}}$	=	$-y_6\,\mathbf{a_1} + y_6\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{x}} + y_6\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{31}}$	=	$y_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$y_6\,a\,\hat{\mathbf{x}} - y_6\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III
$\mathbf{B_{32}}$	=	$-y_6\,\mathbf{a_1} - y_6\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-y_6\,a\,\hat{\mathbf{x}} - y_6\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12j)$	Fe III

References:

- M. J. Mehl, Hypothetical cP32 Austenite Structure.

Geometry files:

- CIF: pp. S769
- POSCAR: pp. S770

Cu_3Au ($L1_2$) Structure: AB3_cP4_221_a_c

Prototype	:	Cu_3Au
AFLOW prototype label	:	AB3_cP4_221_a_c
***Strukturbericht* designation**	:	$L1_2$
Pearson symbol	:	cP4
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB3_cP4_221_a_c --params=`a

Other compounds with this structure:

- Ni_3Al, Al_3Li (metastable), $TiPt_3$

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Au
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	Cu
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	Cu
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3c)$	Cu

References:

- E. A. Owen and Y. H. Liu, *The Thermal Expansion of the Gold-Copper Alloy* $AuCu_3$, Phil. Mag. **38**, 354–360 (1947), doi:10.1080/14786444708521607.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1273.

Geometry files:

- CIF: pp. S770
- POSCAR: pp. S771

α-Po (A_h) Structure: A_cP1_221_a

Prototype	:	α-Po
AFLOW prototype label	:	A_cP1_221_a
***Strukturbericht* designation**	:	A_h
Pearson symbol	:	cP1
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A_cP1_221_a --params=`a

- This is a simple cubic lattice. Polonium is the only element known with this ground state. Originally, Po was assigned Strukturbericht designation: A19, which is now considered to be incorrect (Donohue, 1982, pp. 390).

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Po

References:

- W. H. Beamer and C. R. Maxwell, *The Crystal Structure of Polonium*, J. Chem. Phys. **14**, 569 (1946), doi:10.1063/1.1724201.

Found in:

- J. Donohue, *The Structure of the Elements* (Robert E. Krieger Publishing Company, Malabar, Florida, 1982), pp. 390-391.

Geometry files:

- CIF: pp. S771
- POSCAR: pp. S771

$BaHg_{11}$ ($D2_e$) Structure: AB11_cP36_221_c_agij

Prototype	:	$BaHg_{11}$
AFLOW prototype label	:	AB11_cP36_221_c_agij
***Strukturbericht* designation**	:	$D2_e$
Pearson symbol	:	cP36
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB11_cP36_221_c_agij` `--params=`a, x_3, y_4, y_5

Other compounds with this structure:

- "A number of Hg and Cd phases with Group I or IIA metals or rare earths." (Pearson 1972) pp. 751-752.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Hg I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	Ba
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3c)$	Ba
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3c)$	Ba
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(8g)$	Hg II
$\mathbf{B_6}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(8g)$	Hg II
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(8g)$	Hg II
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(8g)$	Hg II
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(8g)$	Hg II
$\mathbf{B_{10}}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(8g)$	Hg II
$\mathbf{B_{11}}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(8g)$	Hg II
$\mathbf{B_{12}}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(8g)$	Hg II
$\mathbf{B_{13}}$	=	$y_4\,\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{y}} + y_4\,a\,\hat{\mathbf{z}}$	$(12i)$	Hg III
$\mathbf{B_{14}}$	=	$y_4\,\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{y}} - y_4\,a\,\hat{\mathbf{z}}$	$(12i)$	Hg III
$\mathbf{B_{15}}$	=	$-y_4\,\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{y}} + y_4\,a\,\hat{\mathbf{z}}$	$(12i)$	Hg III
$\mathbf{B_{16}}$	=	$-y_4\,\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{y}} - y_4\,a\,\hat{\mathbf{z}}$	$(12i)$	Hg III
$\mathbf{B_{17}}$	=	$y_4\,\mathbf{a_1} + y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{z}}$	$(12i)$	Hg III
$\mathbf{B_{18}}$	=	$y_4\,\mathbf{a_1} - y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{z}}$	$(12i)$	Hg III
$\mathbf{B_{19}}$	=	$-y_4\,\mathbf{a_1} + y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{z}}$	$(12i)$	Hg III
$\mathbf{B_{20}}$	=	$-y_4\,\mathbf{a_1} - y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{z}}$	$(12i)$	Hg III
$\mathbf{B_{21}}$	=	$y_4\,\mathbf{a_1} + y_4\,\mathbf{a_2}$	=	$y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}}$	$(12i)$	Hg III
$\mathbf{B_{22}}$	=	$y_4\,\mathbf{a_1} - y_4\,\mathbf{a_2}$	=	$y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}}$	$(12i)$	Hg III
$\mathbf{B_{23}}$	=	$-y_4\,\mathbf{a_1} + y_4\,\mathbf{a_2}$	=	$-y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}}$	$(12i)$	Hg III
$\mathbf{B_{24}}$	=	$-y_4\,\mathbf{a_1} - y_4\,\mathbf{a_2}$	=	$-y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}}$	$(12i)$	Hg III
$\mathbf{B_{25}}$	=	$\frac{1}{2}\,\mathbf{a_1} + y_5\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}} + y_5\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{26}}$	=	$\frac{1}{2}\,\mathbf{a_1} + y_5\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}} - y_5\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{27}}$	=	$\frac{1}{2}\,\mathbf{a_1} - y_5\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}} + y_5\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{28}}$	=	$\frac{1}{2}\,\mathbf{a_1} - y_5\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}} - y_5\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{29}}$	=	$y_5\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + y_5\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{30}}$	=	$y_5\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} - y_5\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{31}}$	=	$-y_5\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + y_5\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{32}}$	=	$-y_5\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} - y_5\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{33}}$	=	$y_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{34}}$	=	$y_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{35}}$	=	$-y_5\,\mathbf{a_1} + y_5\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV
$\mathbf{B_{36}}$	=	$-y_5\,\mathbf{a_1} - y_5\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(12j)$	Hg IV

References:

- G. Peyronel, *Struttura della fase* $BaHg_{11}$, Gazz. Chim. Ital. **82**, 679–690 (1952).

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S771
- POSCAR: pp. S772

Model of Ferrite Structure (cP16): AB11CD3_cP16_221_a_dg_b_c

Prototype	:	$CrFe_{11}MoNi_3$
AFLOW prototype label	:	AB11CD3_cP16_221_a_dg_b_c
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP16
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB11CD3_cP16_221_a_dg_b_c --params=`a, x_5

- Ferritic steels are alloys of iron and other metals with an averaged body-centered cubic structure. This model represents one approximation for a ferritic steel. It is not meant to represent a real steel, and the selection of atom types for each Wyckoff position is arbitrary. Note that when $x_5 = 1/4$ all the atoms are on sites of a bcc lattice.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Cr
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(1b)$	Mo

$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(3c)	Ni
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(3c)	Ni
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	(3c)	Ni
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	(3d)	Fe I
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	(3d)	Fe I
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	(3d)	Fe I
$\mathbf{B_9}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} + x_5\,a\,\hat{\mathbf{z}}$	(8g)	Fe II
$\mathbf{B_{10}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} + x_5\,a\,\hat{\mathbf{z}}$	(8g)	Fe II
$\mathbf{B_{11}}$	=	$-x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} - x_5\,a\,\hat{\mathbf{z}}$	(8g)	Fe II
$\mathbf{B_{12}}$	=	$x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} - x_5\,a\,\hat{\mathbf{z}}$	(8g)	Fe II
$\mathbf{B_{13}}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} - x_5\,a\,\hat{\mathbf{z}}$	(8g)	Fe II
$\mathbf{B_{14}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} - x_5\,a\,\hat{\mathbf{z}}$	(8g)	Fe II
$\mathbf{B_{15}}$	=	$x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}} - x_5\,a\,\hat{\mathbf{y}} + x_5\,a\,\hat{\mathbf{z}}$	(8g)	Fe II
$\mathbf{B_{16}}$	=	$-x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}} + x_5\,a\,\hat{\mathbf{y}} + x_5\,a\,\hat{\mathbf{z}}$	(8g)	Fe II

References:

- M. J. Mehl, Hypothetical cP16 Ferrite Structure.

Geometry files:

- CIF: pp. S772
- POSCAR: pp. S773

α-ReO_3 ($D0_9$) Structure: A3B_cP4_221_d_a

Prototype	:	α-ReO_3
AFLOW prototype label	:	A3B_cP4_221_d_a
***Strukturbericht* designation**	:	$D0_9$
Pearson symbol	:	cP4
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A3B_cP4_221_d_a --params=`a

Other compounds with this structure:

- Cu_3N, WO_3, UO_3

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Re
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(3d)$	O
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(3d)$	O
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(3d)$	O

References:

- K. Meisel, *Rheniumtrioxyd. III. Mitteilung. Über die Kristallstruktur des Rheniumtrioxyds*, Z. Anorg. Allg. Chem. **207**, 121–128 (1932), doi:10.1002/zaac.19322070113.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S773
- POSCAR: pp. S773

CaB_6 ($D2_1$) Structure: A6B_cP7_221_f_a

Prototype	:	CaB_6
AFLOW prototype label	:	A6B_cP7_221_f_a
***Strukturbericht* designation**	:	$D2_1$
Pearson symbol	:	cP7
Space group number	:	221
Space group symbol	:	$Pm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A6B_cP7_221_f_a` `--params=`a, x_2

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(1a)$	Ca
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(6f)$	B
$\mathbf{B_3}$	=	$-x_2\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(6f)$	B
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(6f)$	B
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(6f)$	B
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(6f)$	B
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(6f)$	B

References:

- Z. Yahia, S. Turrell, G. Turrell, and J. P. Mercurio, *Infrared and Raman spectra of hexaborides: force-field calculations, and isotopic effects*, J. Mol. Struct. **224**, 303–312 (1990), doi:10.1016/0022-2860(90)87025-S.

Geometry files:

- CIF: pp. S773
- POSCAR: pp. S774

Cr_3Si (A15) Structure: A3B_cP8_223_c_a

Prototype	:	Cr_3Si
AFLOW prototype label	:	A3B_cP8_223_c_a
***Strukturbericht* designation**	:	A15
Pearson symbol	:	cP8
Space group number	:	223
Space group symbol	:	$Pm\bar{3}n$
AFLOW prototype command	:	`aflow --proto=A3B_cP8_223_c_a --params=`a

Other compounds with this structure:

- β-W, Nb_3Al, CdV_3, Cr_3O, Ti_3Sb, Ti_3Au, many more

- The "A" Strukturbericht designation comes from the fact that this is also the structure of β-W.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Si
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(2a)$	Si
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(6c)$	Cr

$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(6*c*)	Cr
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	(6*c*)	Cr
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}}$	(6*c*)	Cr
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(6*c*)	Cr
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	(6*c*)	Cr

References:

- W. Jauch, A. J. Schultz, and G. Heger, *Single-crystal time-of-flight neutron diffraction of Cr_3Si and MnF_2 comparison with monochromatic-beam techniques*, J. Appl. Crystallogr. **20**, 117–119 (1987), doi:10.1107/S002188988708703X.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 2742.

Geometry files:

- CIF: pp. S774
- POSCAR: pp. S775

Si_{46} Clathrate Structure: A_cP46_223_dik

Prototype	:	Si
AFLOW prototype label	:	A_cP46_223_dik
***Strukturbericht* designation**	:	None
Pearson symbol	:	cP46
Space group number	:	223
Space group symbol	:	$Pm\bar{3}n$
AFLOW prototype command	:	`aflow --proto=A_cP46_223_dik` `--params=`a, x_2, y_3, z_3

Other compounds with this structure:

- β-W, Nb_3Al, CdV_3, Cr_3O, Ti_3Sb, Ti_3Au, many more

- Silicon clathrates are open structures of pentagonal dodecahedra connected so that all of the silicon atoms have sp^3 bonding. In nature these structures are stabilized by alkali impurity atoms. This structure and the Si_{34} structure are proposed "pure" silicon clathrate structures. For more information about these structures and their possible stability, see (Adams, 1994). Note that this is a theoretical description of a possible silicon clathrate crystal.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(6d)$	Si I
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(6d)$	Si I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(6d)$	Si I
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(6d)$	Si I
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(6d)$	Si I
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(6d)$	Si I
$\mathbf{B_7}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_8}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_9}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{10}}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1} + \left(\frac{1}{2}+x_2\right)\mathbf{a_2} + \left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1} + \left(\frac{1}{2}-x_2\right)\mathbf{a_2} + \left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{13}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1} + \left(\frac{1}{2}-x_2\right)\mathbf{a_2} + \left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1} + \left(\frac{1}{2}+x_2\right)\mathbf{a_2} + \left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{15}}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{16}}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{17}}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{18}}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1} + \left(\frac{1}{2}-x_2\right)\mathbf{a_2} + \left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{20}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1} + \left(\frac{1}{2}+x_2\right)\mathbf{a_2} + \left(\frac{1}{2}+x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{z}}$	$(16i)$	Si II
$\mathbf{B_{21}}$	=	$\left(\frac{1}{2}-x_2\right)\mathbf{a_1} + \left(\frac{1}{2}+x_2\right)\mathbf{a_2} + \left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	$(16i)$	Si II

$\mathbf{B_{22}}$	=	$\left(\frac{1}{2}+x_2\right)\mathbf{a_1}+\left(\frac{1}{2}-x_2\right)\mathbf{a_2}+\left(\frac{1}{2}-x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+x_2\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-x_2\right)a\,\hat{\mathbf{z}}$	(16*i*)	Si II
$\mathbf{B_{23}}$	=	$y_3\,\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{y}}+z_3\,a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{24}}$	=	$-y_3\,\mathbf{a_2}+z_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{y}}+z_3\,a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{25}}$	=	$y_3\,\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{y}}-z_3\,a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{26}}$	=	$-y_3\,\mathbf{a_2}-z_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{y}}-z_3\,a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{27}}$	=	$z_3\,\mathbf{a_1}+y_3\,\mathbf{a_3}$	=	$z_3\,a\,\hat{\mathbf{x}}+y_3\,a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{28}}$	=	$-z_3\,\mathbf{a_1}+y_3\,\mathbf{a_3}$	=	$-z_3\,a\,\hat{\mathbf{x}}+y_3\,a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{29}}$	=	$z_3\,\mathbf{a_1}-y_3\,\mathbf{a_3}$	=	$z_3\,a\,\hat{\mathbf{x}}-y_3\,a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{30}}$	=	$-z_3\,\mathbf{a_1}-y_3\,\mathbf{a_3}$	=	$-z_3\,a\,\hat{\mathbf{x}}-y_3\,a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{31}}$	=	$y_3\,\mathbf{a_1}+z_3\,\mathbf{a_2}$	=	$y_3\,a\,\hat{\mathbf{x}}+z_3\,a\,\hat{\mathbf{y}}$	(24*k*)	Si III
$\mathbf{B_{32}}$	=	$-y_3\,\mathbf{a_1}+z_3\,\mathbf{a_2}$	=	$-y_3\,a\,\hat{\mathbf{x}}+z_3\,a\,\hat{\mathbf{y}}$	(24*k*)	Si III
$\mathbf{B_{33}}$	=	$y_3\,\mathbf{a_1}-z_3\,\mathbf{a_2}$	=	$y_3\,a\,\hat{\mathbf{x}}-z_3\,a\,\hat{\mathbf{y}}$	(24*k*)	Si III
$\mathbf{B_{34}}$	=	$-y_3\,\mathbf{a_1}-z_3\,\mathbf{a_2}$	=	$-y_3\,a\,\hat{\mathbf{x}}-z_3\,a\,\hat{\mathbf{y}}$	(24*k*)	Si III
$\mathbf{B_{35}}$	=	$\left(\frac{1}{2}+y_3\right)\mathbf{a_1}+\frac{1}{2}\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{x}}+\frac{1}{2}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{36}}$	=	$\left(\frac{1}{2}-y_3\right)\mathbf{a_1}+\frac{1}{2}\mathbf{a_2}+\left(\frac{1}{2}-z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{x}}+\frac{1}{2}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-z_3\right)a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{37}}$	=	$\left(\frac{1}{2}+y_3\right)\mathbf{a_1}+\frac{1}{2}\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{x}}+\frac{1}{2}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{38}}$	=	$\left(\frac{1}{2}-y_3\right)\mathbf{a_1}+\frac{1}{2}\mathbf{a_2}+\left(\frac{1}{2}+z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{x}}+\frac{1}{2}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+z_3\right)a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{39}}$	=	$\frac{1}{2}\mathbf{a_1}+\left(\frac{1}{2}+z_3\right)\mathbf{a_2}+\left(\frac{1}{2}-y_3\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+z_3\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{40}}$	=	$\frac{1}{2}\mathbf{a_1}+\left(\frac{1}{2}+z_3\right)\mathbf{a_2}+\left(\frac{1}{2}+y_3\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+z_3\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{41}}$	=	$\frac{1}{2}\mathbf{a_1}+\left(\frac{1}{2}-z_3\right)\mathbf{a_2}+\left(\frac{1}{2}-y_3\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-z_3\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{42}}$	=	$\frac{1}{2}\mathbf{a_1}+\left(\frac{1}{2}-z_3\right)\mathbf{a_2}+\left(\frac{1}{2}+y_3\right)\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-z_3\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{43}}$	=	$\left(\frac{1}{2}+z_3\right)\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}+\frac{1}{2}\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{y}}+\frac{1}{2}a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{44}}$	=	$\left(\frac{1}{2}+z_3\right)\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}+\frac{1}{2}\mathbf{a_3}$	=	$\left(\frac{1}{2}+z_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{y}}+\frac{1}{2}a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{45}}$	=	$\left(\frac{1}{2}-z_3\right)\mathbf{a_1}+\left(\frac{1}{2}-y_3\right)\mathbf{a_2}+\frac{1}{2}\mathbf{a_3}$	=	$\left(\frac{1}{2}-z_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{y}}+\frac{1}{2}a\,\hat{\mathbf{z}}$	(24*k*)	Si III
$\mathbf{B_{46}}$	=	$\left(\frac{1}{2}-z_3\right)\mathbf{a_1}+\left(\frac{1}{2}+y_3\right)\mathbf{a_2}+\frac{1}{2}\mathbf{a_3}$	=	$\left(\frac{1}{2}-z_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{y}}+\frac{1}{2}a\,\hat{\mathbf{z}}$	(24*k*)	Si III

References:

- G. B. Adams, M. O'Keeffe, A. A. Demkov, O. F. Sankey, and Y.-M. Huang, *Wide-band-gap Si in open fourfold-coordinated clathrate structures*, Phys. Rev. B **49**, 8048–8053 (1994), doi:10.1103/PhysRevB.49.8048.

Geometry files:

- CIF: pp. S775
- POSCAR: pp. S775

Cuprite (Cu_2O, C3) Structure: A2B_cP6_224_b_a

Prototype	:	Cu_2O
AFLOW prototype label	:	A2B_cP6_224_b_a
***Strukturbericht* designation**	:	C3
Pearson symbol	:	cP6
Space group number	:	224
Space group symbol	:	$Pn\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A2B_cP6_224_b_a --params=`a

- (Restori, 1986) gives the equilibrium lattice constant of Cu_2O as $a = 4.627$Å, but gives nearest-neighbor distances which yield a lattice constant of 4.267Å. Since this value agrees with other sources, including those in (Downs, 2003), we use it.

Simple Cubic primitive vectors:

$$\mathbf{a}_1 = a\,\hat{\mathbf{x}}$$
$$\mathbf{a}_2 = a\,\hat{\mathbf{y}}$$
$$\mathbf{a}_3 = a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(2a)$	O
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(2a)$	O
$\mathbf{B_3}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4b)$	Cu
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(4b)$	Cu
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(4b)$	Cu
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(4b)$	Cu

References:

- R. Restori and D. Schwarzenbach, *Charge Density in Cuprite, Cu_2O*, Acta Crystallogr. Sect. B Struct. Sci. **42**, 201–208 (1986), doi:10.1107/S0108768186098336.
- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Found in:

- A. Kirfel and K. Eichhorn, *Accurate structure analysis with synchrotron radiation. The electron density in Al_2O_3 and Cu_2O*, Acta Crystallogr. Sect. A **46**, 271–284 (1990), doi:10.1107/S0108767389012596.

Geometry files:

- CIF: pp. S775
- POSCAR: pp. S776

Ca_7Ge Structure: A7B_cF32_225_bd_a

Prototype	:	Ca_7Ge
AFLOW prototype label	:	A7B_cF32_225_bd_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	cF32
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A7B_cF32_225_bd_a --params=`a

Other compounds with this structure:

- $LiPt_7$, $MoZn_7$

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Ge
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(4b)$	Ca I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Ca II
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Ca II
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Ca II
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Ca II
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	$(24d)$	Ca II
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(24d)$	Ca II

References:

- O. Helleis, H. Kandler, E. Leicht, W. Quiring, and E. Wölfel, *Die Kristallstrukturen der intermetallischen Phasen $Ca_{33}Ge$, Ca_7Ge, Ca_3Pb und Ca_5Pb_3*, Z. Anorg. Allg. Chem. **320**, 86–100 (1963), doi:10.1002/zaac.19633200113.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S776
- POSCAR: pp. S777

BiF_3 ($D0_3$) Structure: AB3_cF16_225_a_bc

Prototype	:	BiF_3
AFLOW prototype label	:	AB3_cF16_225_a_bc
***Strukturbericht* designation**	:	$D0_3$
Pearson symbol	:	cF16
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB3_cF16_225_a_bc --params=`a

Other compounds with this structure:

- $AlFe_3$, $BiFe_3$

- (Villars, 1991) corrects the original source, changing the positions of one third of the fluorine atoms so that the space group becomes $Fm\bar{3}m$, as is accepted for $D0_3$. This structure is crystallographically equivalent to the Heusler ($L2_1$) structure.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{y}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{y}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	(4*a*)	Bi
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_1} + \frac{1}{2}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(4*b*)	F I
$\mathbf{B_3}$	=	$\frac{1}{4}\mathbf{a_1} + \frac{1}{4}\mathbf{a_2} + \frac{1}{4}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	F II
$\mathbf{B_4}$	=	$\frac{3}{4}\mathbf{a_1} + \frac{3}{4}\mathbf{a_2} + \frac{3}{4}\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	F II

References:

- O. Hassel and S. Nilssen, *Der Kristallbau des BiF_3*, Z. Anorganische Chemie **181**, 172–176 (1929), doi:10.1002/zaac.19291810117.
- F. Hund and R. Fricke, *Der Kristallbau von α-BiF_3*, Z. Anorganische Chemie **258**, 198–204 (1949), doi:10.1002/zaac.19492580310.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 1774.

Geometry files:

- CIF: pp. S777
- POSCAR: pp. S779

Model of Ferrite Structure (cF128): A9B16C7_cF128_225_acd_2f_be

Prototype	:	$Cr_9Fe_{16}Ni_7$
AFLOW prototype label	:	A9B16C7_cF128_225_acd_2f_be
***Strukturbericht* designation**	:	None
Pearson symbol	:	cF128
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A9B16C7_cF128_225_acd_2f_be --params=`a, x_5, x_6, x_7

- Ferrite is steel with a bcc structure. This structure represents one possible ordering which might be found in an Fe-Ni-Cr steel. Note that it is not meant to represent a real steel. If we use the special values $x_5 = 1/4$, $x_6 = 1/8$, and $x_7 = 3/8$, and replace the Ni atoms by Cr, then this structure reverts to CsCl (B2) with $a_{B2} = 1/4a$. If we replace both the Ni and Cr atoms by Fe, then the structure becomes bcc, again with $a_{bcc} = 1/4a$.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Cr I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(4b)$	Ni I
$\mathbf{B_3}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	Cr II
$\mathbf{B_4}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	Cr II
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Cr III
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Cr III
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Cr III
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(24d)$	Cr III
$\mathbf{B_9}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	$(24d)$	Cr III
$\mathbf{B_{10}}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(24d)$	Cr III
$\mathbf{B_{11}}$	=	$-x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{x}}$	$(24e)$	Ni II
$\mathbf{B_{12}}$	=	$x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{y}}$	$(24e)$	Ni II
$\mathbf{B_{13}}$	=	$x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$x_5\,a\,\hat{\mathbf{z}}$	$(24e)$	Ni II
$\mathbf{B_{14}}$	=	$x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{x}}$	$(24e)$	Ni II
$\mathbf{B_{15}}$	=	$-x_5\,\mathbf{a_1} + x_5\,\mathbf{a_2} - x_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{y}}$	$(24e)$	Ni II
$\mathbf{B_{16}}$	=	$-x_5\,\mathbf{a_1} - x_5\,\mathbf{a_2} + x_5\,\mathbf{a_3}$	=	$-x_5\,a\,\hat{\mathbf{z}}$	$(24e)$	Ni II
$\mathbf{B_{17}}$	=	$x_6\,\mathbf{a_1} + x_6\,\mathbf{a_2} + x_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} + x_6\,a\,\hat{\mathbf{y}} + x_6\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe I
$\mathbf{B_{18}}$	=	$x_6\,\mathbf{a_1} + x_6\,\mathbf{a_2} - 3\,x_6\,\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} - x_6\,a\,\hat{\mathbf{y}} + x_6\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe I
$\mathbf{B_{19}}$	=	$x_6\,\mathbf{a_1} - 3\,x_6\,\mathbf{a_2} + x_6\,\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} + x_6\,a\,\hat{\mathbf{y}} - x_6\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe I
$\mathbf{B_{20}}$	=	$-3\,x_6\,\mathbf{a_1} + x_6\,\mathbf{a_2} + x_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} - x_6\,a\,\hat{\mathbf{y}} - x_6\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe I
$\mathbf{B_{21}}$	=	$-x_6\,\mathbf{a_1} - x_6\,\mathbf{a_2} + 3\,x_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} + x_6\,a\,\hat{\mathbf{y}} - x_6\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe I
$\mathbf{B_{22}}$	=	$-x_6\,\mathbf{a_1} - x_6\,\mathbf{a_2} - x_6\,\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} - x_6\,a\,\hat{\mathbf{y}} - x_6\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe I
$\mathbf{B_{23}}$	=	$-x_6\,\mathbf{a_1} + 3\,x_6\,\mathbf{a_2} - x_6\,\mathbf{a_3}$	=	$x_6\,a\,\hat{\mathbf{x}} - x_6\,a\,\hat{\mathbf{y}} + x_6\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe I
$\mathbf{B_{24}}$	=	$3\,x_6\,\mathbf{a_1} - x_6\,\mathbf{a_2} - x_6\,\mathbf{a_3}$	=	$-x_6\,a\,\hat{\mathbf{x}} + x_6\,a\,\hat{\mathbf{y}} + x_6\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe I
$\mathbf{B_{25}}$	=	$x_7\,\mathbf{a_1} + x_7\,\mathbf{a_2} + x_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}} + x_7\,a\,\hat{\mathbf{y}} + x_7\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe II
$\mathbf{B_{26}}$	=	$x_7\,\mathbf{a_1} + x_7\,\mathbf{a_2} - 3\,x_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}} - x_7\,a\,\hat{\mathbf{y}} + x_7\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe II
$\mathbf{B_{27}}$	=	$x_7\,\mathbf{a_1} - 3\,x_7\,\mathbf{a_2} + x_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}} + x_7\,a\,\hat{\mathbf{y}} - x_7\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe II
$\mathbf{B_{28}}$	=	$-3\,x_7\,\mathbf{a_1} + x_7\,\mathbf{a_2} + x_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}} - x_7\,a\,\hat{\mathbf{y}} - x_7\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe II
$\mathbf{B_{29}}$	=	$-x_7\,\mathbf{a_1} - x_7\,\mathbf{a_2} + 3\,x_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}} + x_7\,a\,\hat{\mathbf{y}} - x_7\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe II
$\mathbf{B_{30}}$	=	$-x_7\,\mathbf{a_1} - x_7\,\mathbf{a_2} - x_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}} - x_7\,a\,\hat{\mathbf{y}} - x_7\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe II
$\mathbf{B_{31}}$	=	$-x_7\,\mathbf{a_1} + 3\,x_7\,\mathbf{a_2} - x_7\,\mathbf{a_3}$	=	$x_7\,a\,\hat{\mathbf{x}} - x_7\,a\,\hat{\mathbf{y}} + x_7\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe II
$\mathbf{B_{32}}$	=	$3\,x_7\,\mathbf{a_1} - x_7\,\mathbf{a_2} - x_7\,\mathbf{a_3}$	=	$-x_7\,a\,\hat{\mathbf{x}} + x_7\,a\,\hat{\mathbf{y}} + x_7\,a\,\hat{\mathbf{z}}$	$(32f)$	Fe II

References:

- M. J. Mehl, Hypothetical cF128 Ferrite Structure

Geometry files:
- CIF: pp. S779
- POSCAR: pp. S780

UB_{12} Structure: A12B_cF52_225_i_a

Prototype	:	UB_{12}
AFLOW prototype label	:	A12B_cF52_225_i_a
***Strukturbericht* designation**	:	$D2_f$
Pearson symbol	:	cF52
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A12B_cF52_225_i_a --params=`a, y_2

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	U
$\mathbf{B_2}$	=	$\left(\frac{1}{2} + 2\,y_2\right)\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{z}}$	$(48i)$	B
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} + 2\,y_2\right)\mathbf{a_2} + \left(\frac{1}{2} - 2\,y_2\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{z}}$	$(48i)$	B
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \left(\frac{1}{2} - 2\,y_2\right)\mathbf{a_2} + \left(\frac{1}{2} + 2\,y_2\right)\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{z}}$	$(48i)$	B
$\mathbf{B_5}$	=	$\left(\frac{1}{2} - 2\,y_2\right)\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - y_2\right)a\,\hat{\mathbf{z}}$	$(48i)$	B

$\mathbf{B_6}$	=	$+\frac{1}{2}\,\mathbf{a_1}+\left(\frac{1}{2}+2\,y_2\right)\,\mathbf{a_2}+\frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_2\right)\,a\,\hat{\mathbf{x}}+\frac{1}{2}\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+y_2\right)\,a\,\hat{\mathbf{z}}$	(48*i*)	B
$\mathbf{B_7}$	=	$\left(\frac{1}{2}-2\,y_2\right)\,\mathbf{a_1}+\frac{1}{2}\,\mathbf{a_2}+\left(\frac{1}{2}+2\,y_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_2\right)\,a\,\hat{\mathbf{x}}+\frac{1}{2}\,a\,\hat{\mathbf{y}}\left(\frac{1}{2}-y_2\right)\,a\,\hat{\mathbf{z}}$	(48*i*)	B
$\mathbf{B_8}$	=	$\left(\frac{1}{2}+2\,y_2\right)\,\mathbf{a_1}+\frac{1}{2}\,\mathbf{a_2}+\left(\frac{1}{2}-2\,y_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_2\right)\,a\,\hat{\mathbf{x}}+\frac{1}{2}\,a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+y_2\right)\,a\,\hat{\mathbf{z}}$	(48*i*)	B
$\mathbf{B_9}$	=	$\frac{1}{2}\,\mathbf{a_1}+\left(\frac{1}{2}-2\,y_2\right)\,\mathbf{a_2}+\frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_2\right)\,a\,\hat{\mathbf{x}}+\frac{1}{2}\,a\,\hat{\mathbf{y}}\left(\frac{1}{2}-y_2\right)\,a\,\hat{\mathbf{z}}$	(48*i*)	B
$\mathbf{B_{10}}$	=	$\frac{1}{2}\,\mathbf{a_1}+\frac{1}{2}\,\mathbf{a_2}+\left(\frac{1}{2}+2\,y_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_2\right)\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)\,a\,\hat{\mathbf{y}}+\frac{1}{2}\,a\,\hat{\mathbf{z}}$	(48*i*)	B
$\mathbf{B_{11}}$	=	$\left(\frac{1}{2}+2\,y_2\right)\,\mathbf{a_1}+\left(\frac{1}{2}-2\,y_2\right)\,\mathbf{a_2}+\frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_2\right)\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_2\right)\,a\,\hat{\mathbf{y}}+\frac{1}{2}\,a\,\hat{\mathbf{z}}$	(48*i*)	B
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2}-2\,y_2\right)\,\mathbf{a_1}+\left(\frac{1}{2}+2\,y_2\right)\,\mathbf{a_2}+\frac{1}{2}\,\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_2\right)\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)\,a\,\hat{\mathbf{y}}+\frac{1}{2}\,a\,\hat{\mathbf{z}}$	(48*i*)	B
$\mathbf{B_{13}}$	=	$\frac{1}{2}\,\mathbf{a_1}+\frac{1}{2}\,\mathbf{a_2}+\left(\frac{1}{2}-2\,y_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_2\right)\,a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_2\right)\,a\,\hat{\mathbf{y}}+\frac{1}{2}\,a\,\hat{\mathbf{z}}$	(48*i*)	B

References:

- P. Blum and F. Bertaut, *Contribution à l'Étude des Borures à Teneur Élevée en Bore*, Acta Cryst. **7**, 81–86 (1954), doi:10.1107/S0365110X54000151.

Found in:

- W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley- Interscience, New York, London, Sydney, Toronto, 1972), pp. 757-759.

Geometry files:

- CIF: pp. S780
- POSCAR: pp. S781

Fluorite (CaF_2, C1) Structure: AB2_cF12_225_a_c

Prototype	:	CaF_2
AFLOW prototype label	:	AB2_cF12_225_a_c
***Strukturbericht* designation**	:	C1
Pearson symbol	:	cF12
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB2_cF12_225_a_c --params=`a

Other compounds with this structure:

- AmO_2, $AuAl_2$, $AuIn_2$, BaF_2, Be_2B, CO_2, CdF_2, CeO_2, $CoSi_2$, EuF_2, HgF_2, Ir_2P, Li_2O, Na_2O, $NiSi_2$, $PtAl_2$, Rb_2O, $SrCl_2$, $SrCl_2$, SrF_2, ThO_2, ZrO_2

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Ca
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	F
$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	F

References:

- S. Speziale and T. S. Duffy, *Single-crystal elastic constants of fluorite (CaF_2) to 9.3 GPa*, Phys. Chem. Miner. **29**, 465–472 (2002), doi:10.1007/s00269-002-0250-x.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S782
- POSCAR: pp. S783

$Cr_{23}C_6$ ($D8_4$) Structure: A6B23_cF116_225_e_acfh

Prototype	:	$Cr_{23}C_6$
AFLOW prototype label	:	A6B23_cF116_225_e_acfh
***Strukturbericht* designation**	:	$D8_4$
Pearson symbol	:	cF116
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A6B23_cF116_225_e_acfh` `--params=`a, x_3, x_4, y_5

Other compounds with this structure:

- The general structure of this compound is $M_{23}X_6$ where M=Fe, Cr, Ni, Mn, V, W, ..., or combinations thereof, and X = C or B.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Cr I
$\mathbf{B_2}$	=	$\frac{1}{4}\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	Cr II
$\mathbf{B_3}$	=	$\frac{3}{4}\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(8c)$	Cr II
$\mathbf{B_4}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}}$	$(24e)$	C
$\mathbf{B_5}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{y}}$	$(24e)$	C
$\mathbf{B_6}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{z}}$	$(24e)$	C
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}}$	$(24e)$	C
$\mathbf{B_8}$	=	$-x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{y}}$	$(24e)$	C
$\mathbf{B_9}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{z}}$	$(24e)$	C
$\mathbf{B_{10}}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	$(32f)$	Cr III
$\mathbf{B_{11}}$	=	$x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} - 3\,x_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	$(32f)$	Cr III
$\mathbf{B_{12}}$	=	$x_4\,\mathbf{a_1} - 3\,x_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	$(32f)$	Cr III
$\mathbf{B_{13}}$	=	$-3\,x_4\,\mathbf{a_1} + x_4\,\mathbf{a_2} + x_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	$(32f)$	Cr III
$\mathbf{B_{14}}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} + 3\,x_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	$(32f)$	Cr III
$\mathbf{B_{15}}$	=	$-x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	$(32f)$	Cr III
$\mathbf{B_{16}}$	=	$-x_4\,\mathbf{a_1} + 3\,x_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	$(32f)$	Cr III
$\mathbf{B_{17}}$	=	$3\,x_4\,\mathbf{a_1} - x_4\,\mathbf{a_2} - x_4\,\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	$(32f)$	Cr III
$\mathbf{B_{18}}$	=	$2\,y_5\,\mathbf{a_1}$	=	$y_5\,a\,\hat{\mathbf{y}} + y_5\,a\,\hat{\mathbf{z}}$	$(48h)$	Cr IV
$\mathbf{B_{19}}$	=	$2\,y_5\,\mathbf{a_2} - 2\,y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{y}} + y_5\,a\,\hat{\mathbf{z}}$	$(48h)$	Cr IV
$\mathbf{B_{20}}$	=	$-2\,y_5\,\mathbf{a_2} + 2\,y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{y}} - y_5\,a\,\hat{\mathbf{z}}$	$(48h)$	Cr IV
$\mathbf{B_{21}}$	=	$-2\,y_5\,\mathbf{a_1}$	=	$-y_5\,a\,\hat{\mathbf{y}} - y_5\,a\,\hat{\mathbf{z}}$	$(48h)$	Cr IV
$\mathbf{B_{22}}$	=	$2\,y_5\,\mathbf{a_2}$	=	$y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{z}}$	$(48h)$	Cr IV
$\mathbf{B_{23}}$	=	$-2\,y_5\,\mathbf{a_1} + 2\,y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{z}}$	$(48h)$	Cr IV
$\mathbf{B_{24}}$	=	$2\,y_5\,\mathbf{a_1} - 2\,y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{z}}$	$(48h)$	Cr IV
$\mathbf{B_{25}}$	=	$-2\,y_5\,\mathbf{a_2}$	=	$-y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{z}}$	$(48h)$	Cr IV
$\mathbf{B_{26}}$	=	$2\,y_5\,\mathbf{a_3}$	=	$y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}}$	$(48h)$	Cr IV
$\mathbf{B_{27}}$	=	$2\,y_5\,\mathbf{a_1} - 2\,y_5\,\mathbf{a_2}$	=	$-y_5\,a\,\hat{\mathbf{x}} + y_5\,a\,\hat{\mathbf{y}}$	$(48h)$	Cr IV
$\mathbf{B_{28}}$	=	$-2\,y_5\,\mathbf{a_1} + 2\,y_5\,\mathbf{a_2}$	=	$y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}}$	$(48h)$	Cr IV
$\mathbf{B_{29}}$	=	$-2\,y_5\,\mathbf{a_3}$	=	$-y_5\,a\,\hat{\mathbf{x}} - y_5\,a\,\hat{\mathbf{y}}$	$(48h)$	Cr IV

References:

- A. L. Bowman, G. P. Arnold, E. K. Storms, and N. G. Nereson, *The crystal structure of $Cr_{23}C_6$*, Acta Crystallogr. Sect. B Struct. Sci. **28**, 3102–3103 (1972), doi:10.1107/S0567740872007526.

Geometry files:

- CIF: pp. S783
- POSCAR: pp. S784

Heusler ($L2_1$) Structure: AB2C_cF16_225_a_c_b

Prototype	:	$AlCu_2Mn$
AFLOW prototype label	:	AB2C_cF16_225_a_c_b
***Strukturbericht* designation**	:	$L2_1$
Pearson symbol	:	cF16
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB2C_cF16_225_a_c_b --params=`a

Other compounds with this structure:

- $AlNi_2Ti$, $AlNi_2Hf$

- All of the atoms are located on the sites of a body-centered cubic lattice. If we replace the Mn atom by another copper atom, the structure reduces to the crystallographically equivalent $D0_3$ lattice. Also see the $C1_b$ "half-Heusler" structure.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{y}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Al

$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_1} + \frac{1}{2}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(4*b*)	Mn
$\mathbf{B_3}$	=	$\frac{1}{4}\mathbf{a_1} + \frac{1}{4}\mathbf{a_2} + \frac{1}{4}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	Cu
$\mathbf{B_4}$	=	$\frac{3}{4}\mathbf{a_1} + \frac{3}{4}\mathbf{a_2} + \frac{3}{4}\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	Cu

References:

- A. J. Bradley and J. W. Rodgers, *The Crystal Structure of Heusler Alloys*, Proc. R. Soc. A Math. Phys. Eng. Sci. **144**, 340–359 (1934), doi:10.1098/rspa.1934.0053.

Geometry files:

- CIF: pp. S784
- POSCAR: pp. S785

Face-Centered Cubic (Cu, A1) Structure: A_cF4_225_a

Prototype	:	Cu
AFLOW prototype label	:	A_cF4_225_a
***Strukturbericht* designation**	:	A1
Pearson symbol	:	cF4
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A_cF4_225_a --params=`a

Other elements with this structure:

- Al, Cu, Ni, Sr, Rh, Pd, Ag, Ce, Tb, Ir, Pt, Au, Pb, Th

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Cu

References:

- M. E. Straumanis and L. S. Yu, *Lattice parameters, densities, expansion coefficients and perfection of structure of Cu and of Cu-In α phase*, Acta Crystallogr. Sect. A **25**, 676–682 (1969), doi:10.1107/S0567739469001549.

Geometry files:

- CIF: pp. S786
- POSCAR: pp. S787

Model of Austenite Structure (cF108): AB18C8_cF108_225_a_eh_f

Prototype	:	$CrFe_{18}Ni_8$
AFLOW prototype label	:	AB18C8_cF108_225_a_eh_f
***Strukturbericht* designation**	:	None
Pearson symbol	:	cF108
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB18C8_cF108_225_a_eh_f` `--params=`a, x_2, x_3, y_4

- Austenitic steels are alloys of iron and other metals with an averaged face-centered cubic structure. If we set $x_2 = 1/3$, $x_3 = 2/3$, and $y_4 = 2/3$, the atoms are on the sites of an fcc lattice with lattice constant $a_{fcc} = 1/3a$.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{y}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	(4*a*)	Cr
$\mathbf{B_2}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}$	(24*e*)	Fe I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{y}}$	(24*e*)	Fe I
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{z}}$	(24*e*)	Fe I
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}$	(24*e*)	Fe I
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{y}}$	(24*e*)	Fe I
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{z}}$	(24*e*)	Fe I
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(32*f*)	Ni
$\mathbf{B_9}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} - 3\,x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(32*f*)	Ni
$\mathbf{B_{10}}$	=	$x_3\,\mathbf{a_1} - 3\,x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(32*f*)	Ni
$\mathbf{B_{11}}$	=	$-3\,x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(32*f*)	Ni
$\mathbf{B_{12}}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} + 3\,x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(32*f*)	Ni
$\mathbf{B_{13}}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(32*f*)	Ni
$\mathbf{B_{14}}$	=	$-x_3\,\mathbf{a_1} + 3\,x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(32*f*)	Ni
$\mathbf{B_{15}}$	=	$3\,x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(32*f*)	Ni
$\mathbf{B_{16}}$	=	$2\,y_4\,\mathbf{a_1}$	=	$y_4\,a\,\hat{\mathbf{y}} + y_4\,a\,\hat{\mathbf{z}}$	(48*h*)	Fe II
$\mathbf{B_{17}}$	=	$2\,y_4\,\mathbf{a_2} - 2\,y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{y}} + y_4\,a\,\hat{\mathbf{z}}$	(48*h*)	Fe II
$\mathbf{B_{18}}$	=	$-2\,y_4\,\mathbf{a_2} + 2\,y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{y}} - y_4\,a\,\hat{\mathbf{z}}$	(48*h*)	Fe II
$\mathbf{B_{19}}$	=	$-2\,y_4\,\mathbf{a_1}$	=	$-y_4\,a\,\hat{\mathbf{y}} - y_4\,a\,\hat{\mathbf{z}}$	(48*h*)	Fe II
$\mathbf{B_{20}}$	=	$2\,y_4\,\mathbf{a_2}$	=	$y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{z}}$	(48*h*)	Fe II
$\mathbf{B_{21}}$	=	$-2\,y_4\,\mathbf{a_1} + 2\,y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{z}}$	(48*h*)	Fe II
$\mathbf{B_{22}}$	=	$2\,y_4\,\mathbf{a_1} - 2\,y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{z}}$	(48*h*)	Fe II
$\mathbf{B_{23}}$	=	$-2\,y_4\,\mathbf{a_2}$	=	$-y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{z}}$	(48*h*)	Fe II
$\mathbf{B_{24}}$	=	$2\,y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}}$	(48*h*)	Fe II
$\mathbf{B_{25}}$	=	$2\,y_4\,\mathbf{a_1} - 2\,y_4\,\mathbf{a_2}$	=	$-y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}}$	(48*h*)	Fe II
$\mathbf{B_{26}}$	=	$-2\,y_4\,\mathbf{a_1} + 2\,y_4\,\mathbf{a_2}$	=	$y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}}$	(48*h*)	Fe II
$\mathbf{B_{27}}$	=	$-2\,y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}}$	(48*h*)	Fe II

References:

- M. J. Mehl, Hypothetical cF108 Austenite Structure.

Geometry files:

- CIF: pp. S787
- POSCAR: pp. S788

Rock Salt (NaCl, B1) Structure: AB_cF8_225_a_b

Prototype	:	NaCl
AFLOW prototype label	:	AB_cF8_225_a_b
***Strukturbericht* designation**	:	B1
Pearson symbol	:	cF8
Space group number	:	225
Space group symbol	:	$Fm\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB_cF8_225_a_b --params=`a

Other compounds with this structure:

- AgCl, BaS, CaO, CeSe, DyAs, GdN, KBr, LaP, LiCl, LiF, MgO, NaBr, NaF, NiO, PrBi, PuC, RbF, ScN, SrO, TbTe, UC, YN, YbO, ZrO

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{y}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(4a)$	Cl
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{y}} + \frac{1}{2}a\,\hat{\mathbf{z}}$	$(4b)$	Na

References:

- D. Walker, P. K. Verma, L. M. D. Cranswick, R. L. Jones, S. M. Clark, and S. Buhre, *Halite-sylvite thermoelasticity*, Am. Mineral. **89**, 204–210 (2004).

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S788
- POSCAR: pp. S789

Ideal β-Cristobalite (SiO_2, C9) Structure: A2B_cF24_227_c_a

Prototype	:	SiO_2
AFLOW prototype label	:	A2B_cF24_227_c_a
***Strukturbericht* designation**	:	C9
Pearson symbol	:	cF24
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A2B_cF24_227_c_a --params=`a

Other compounds with this structure:

- BeF_2

- This is an idealized version of the high-temperature phase of α-cristobalite. (Peacor, 1973) concludes that the oxygen atoms partially occupy the (96g) positions in the space group $Fd\bar{3}m$. We average those positions to put the oxygen on the (16c) sites.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{8}\mathbf{a_1} + \frac{1}{8}\mathbf{a_2} + \frac{1}{8}\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(8*a*)	Si
$\mathbf{B_2}$	=	$\frac{7}{8}\mathbf{a_1} + \frac{7}{8}\mathbf{a_2} + \frac{7}{8}\mathbf{a_3}$	=	$\frac{7}{8}\,a\,\hat{\mathbf{x}} + \frac{7}{8}\,a\,\hat{\mathbf{y}} + \frac{7}{8}\,a\,\hat{\mathbf{z}}$	(8*a*)	Si
$\mathbf{B_3}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	(16*c*)	O
$\mathbf{B_4}$	=	$\frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	(16*c*)	O
$\mathbf{B_5}$	=	$\frac{1}{2}\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*c*)	O
$\mathbf{B_6}$	=	$\frac{1}{2}\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*c*)	O

References:

- D. R. Peacor, *High-temperature single-crystal study of the cristobalite inversion*, Zeitschrift für Kristallographie **138**, 274–298 (1973), doi:10.1524/zkri.1973.138.1-4.274.

Found in:

- R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

Geometry files:

- CIF: pp. S789
- POSCAR: pp. S791

$NiTi_2$ Structure: AB2_cF96_227_e_cf

Prototype	:	$NiTi_2$
AFLOW prototype label	:	AB2_cF96_227_e_cf
***Strukturbericht* designation**	:	None
Pearson symbol	:	cF96
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB2_cF96_227_e_cf` `--params=`a, x_2, x_3

Other compounds with this structure:

- $CoTi_2$, $CoZr_2$, Cr_2Nb, $FeTi_2$, $FeZr_2$, Hf_2Ir, Hf_2Pt, $IrZr_2$, $NiSc_2$, $PdSc_2$, many others.

- We have used the fact that all vectors of the form $(0, \pm a/2, \pm a/2)$, $(\pm a/2, 0, \pm a/2)$, and $(\pm a/2, \pm a/2, 0)$ are primitive vectors of the face-centered cubic lattice to simplify the positions of some atoms in both lattice and Cartesian coordinates

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{y}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	(16*c*)	Ti I
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	(16*c*)	Ti I
$\mathbf{B_3}$	=	$\frac{1}{2}\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*c*)	Ti I
$\mathbf{B_4}$	=	$\frac{1}{2}\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*c*)	Ti I
$\mathbf{B_5}$	=	$x_2\mathbf{a_1} + x_2\mathbf{a_2} + x_2\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(32*e*)	Ni
$\mathbf{B_6}$	=	$x_2\mathbf{a_1} + x_2\mathbf{a_2} + \left(\frac{1}{2} - 3\,x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(32*e*)	Ni
$\mathbf{B_7}$	=	$x_2\mathbf{a_1} + \left(\frac{1}{2} - 3\,x_2\right)\mathbf{a_2} + x_2\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Ni
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - 3\,x_2\right)\mathbf{a_1} + x_2\mathbf{a_2} + x_2\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Ni
$\mathbf{B_9}$	=	$-x_2\mathbf{a_1} - x_2\mathbf{a_2} + \left(\frac{1}{2} + 3\,x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(32*e*)	Ni
$\mathbf{B_{10}}$	=	$-x_2\mathbf{a_1} - x_2\mathbf{a_2} - x_2\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(32*e*)	Ni
$\mathbf{B_{11}}$	=	$-x_2\mathbf{a_1} + \left(\frac{1}{2} + 3\,x_2\right)\mathbf{a_2} - x_2\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Ni
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + 3\,x_2\right)\mathbf{a_1} - x_2\mathbf{a_2} - x_2\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Ni
$\mathbf{B_{13}}$	=	$\left(\frac{1}{4} - x_3\right)\mathbf{a_1} + x_3\mathbf{a_2} + x_3\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{14}}$	=	$x_3\mathbf{a_1} + \left(\frac{1}{4} - x_3\right)\mathbf{a_2} + \left(\frac{1}{4} - x_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{15}}$	=	$x_3\mathbf{a_1} + \left(\frac{1}{4} - x_3\right)\mathbf{a_2} + x_3\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{16}}$	=	$\left(\frac{1}{4} - x_3\right)\mathbf{a_1} + x_3\mathbf{a_2} + \left(\frac{1}{4} - x_3\right)\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{17}}$	=	$x_3\mathbf{a_1} + x_3\mathbf{a_2} + \left(\frac{1}{4} - x_3\right)\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{18}}$	=	$\left(\frac{1}{4} - x_3\right)\mathbf{a_1} + \left(\frac{1}{4} - x_3\right)\mathbf{a_2} + x_3\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{19}}$	=	$\left(x_3 + \frac{3}{4}\right)\mathbf{a_1} - x_3\mathbf{a_2} + \left(x_3 + \frac{3}{4}\right)\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} + \left(x_3 + \frac{3}{4}\right)\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{20}}$	=	$-x_3\mathbf{a_1} + \left(x_3 + \frac{3}{4}\right)\mathbf{a_2} - x_3\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{21}}$	=	$-x_3\mathbf{a_1} + \left(x_3 + \frac{3}{4}\right)\mathbf{a_2} + \left(x_3 + \frac{3}{4}\right)\mathbf{a_3}$	=	$\left(x_3 + \frac{3}{4}\right)\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{22}}$	=	$\left(x_3 + \frac{3}{4}\right)\mathbf{a_1} - x_3\mathbf{a_2} - x_3\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{23}}$	=	$-x_3\mathbf{a_1} - x_3\mathbf{a_2} + \left(x_3 + \frac{3}{4}\right)\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II
$\mathbf{B_{24}}$	=	$+\left(x_3 + \frac{3}{4}\right)\mathbf{a_1} + \left(x_3 + \frac{3}{4}\right)\mathbf{a_2} - x_3\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} + \left(x_3 + \frac{3}{4}\right)\,a\,\hat{\mathbf{z}}$	(48*f*)	Ti II

References:

- G. A. Yurko, J. W. Barton, and J. G. Parr, *The crystal structure of Ti_2Ni*, Acta Cryst. **12**, 909–911 (1959), doi:10.1107/S0365110X59002559.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4715.

Geometry files:

- CIF: pp. S791
- POSCAR: pp. S792

NaTl (B32) Structure: AB_cF16_227_a_b

Prototype	:	NaTl
AFLOW prototype label	:	AB_cF16_227_a_b
***Strukturbericht* designation**	:	B32
Pearson symbol	:	cF16
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB_cF16_227_a_b --params=`a

- This is an example of a Zintl Phase.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{8}\mathbf{a_1} + \frac{1}{8}\mathbf{a_2} + \frac{1}{8}\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	Na
$\mathbf{B_2}$	=	$\frac{7}{8}\mathbf{a_1} + \frac{7}{8}\mathbf{a_2} + \frac{7}{8}\mathbf{a_3}$	=	$\frac{7}{8}\,a\,\hat{\mathbf{x}} + \frac{7}{8}\,a\,\hat{\mathbf{y}} + \frac{7}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	Na
$\mathbf{B_3}$	=	$\frac{3}{8}\mathbf{a_1} + \frac{3}{8}\mathbf{a_2} + \frac{3}{8}\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	$(8b)$	Tl
$\mathbf{B_4}$	=	$\frac{5}{8}\mathbf{a_1} + \frac{5}{8}\mathbf{a_2} + \frac{5}{8}\mathbf{a_3}$	=	$\frac{5}{8}\,a\,\hat{\mathbf{x}} + \frac{5}{8}\,a\,\hat{\mathbf{y}} + \frac{5}{8}\,a\,\hat{\mathbf{z}}$	$(8b)$	Tl

References:

- K. Kuriyama, S. Saito, and K. Iwamura, *Ultrasonic study on the elastic moduli of the NaTl (B32) structure*, J. Phys. Chem. Solids **40**, 457–461 (1979), doi:10.1016/0022-3697(79)90062-3.

Found in:

- P. Villars, *Material Phases Data System* ((MPDS), CH-6354 Vitznau, Switzerland, 2014). Accessed through the Springer Materials site.

Geometry files:

- CIF: pp. S792
- POSCAR: pp. S793

Si_{34} Clathrate Structure: A_cF136_227_aeg

Prototype	:	Si
AFLOW prototype label	:	A_cF136_227_aeg
***Strukturbericht* designation**	:	None
Pearson symbol	:	cF136
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A_cF136_227_aeg` `--params=`a, x_2, x_3, z_3

- Silicon clathrates are open structures of pentagonal dodecahedra connected so that all of the silicon atoms have sp^3 bonding. In nature these structures are stabilized by alkali impurity atoms. This structure and the Si_{46} structure are proposed "pure" silicon clathrate structures. For more information about these structures and their possible stability, see (Adams, 1994). See (Gryko, 2000) for a possible experimental realization of this structure ($Si_{34}Na_x$, were x is very small). We have used the fact that all vectors of the form $(0, \pm a/2, \pm a/2)$, $(\pm a/2, 0, \pm a/2)$, and $(\pm a/2, \pm a/2, 0)$ are primitive vectors of the face-centered cubic lattice to simplify the positions of some atoms in both lattice and Cartesian coordinates.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{1}{8}\,\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	Si I
$\mathbf{B_2}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{7}{8}\,\mathbf{a_3}$	=	$\frac{7}{8}\,a\,\hat{\mathbf{x}} + \frac{7}{8}\,a\,\hat{\mathbf{y}} + \frac{7}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	Si I
$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(32e)$	Si II
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \left(\frac{1}{2} - 3\,x_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(32e)$	Si II
$\mathbf{B_5}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{2} - 3\,x_2\right)\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{z}}$	$(32e)$	Si II
$\mathbf{B_6}$	=	$\left(\frac{1}{2} - 3\,x_2\right)\,\mathbf{a_1} + x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{z}}$	$(32e)$	Si II
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{1}{2} + 3\,x_2\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(32e)$	Si II
$\mathbf{B_8}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(32e)$	Si II
$\mathbf{B_9}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{1}{2} + 3\,x_2\right)\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{z}}$	$(32e)$	Si II
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} + 3\,x_2\right)\,\mathbf{a_1} - x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{z}}$	$(32e)$	Si II
$\mathbf{B_{11}}$	=	$z_3\,\mathbf{a_1} + z_3\,\mathbf{a_2} + (2x_3 - z_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + z_3\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{12}}$	=	$z_3\,\mathbf{a_1} + z_3\,\mathbf{a_2} + \left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}} + z_3\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{13}}$	=	$(2x_3 - z_3)\,\mathbf{a_1} + \left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_3\right)\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_1} + (2x_3 - z_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - z_3\right)\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{15}}$	=	$(2x_3 - z_3)\,\mathbf{a_1} + z_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$z_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_1} + z_3\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$z_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{17}}$	=	$z_3\,\mathbf{a_1} + (2x_3 - z_3)\,\mathbf{a_2} + \left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - z_3\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{18}}$	=	$z_3\,\mathbf{a_1} + \left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_2} + (2x_3 - z_3)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - z_3\right)\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{19}}$	=	$z_3\,\mathbf{a_1} + (2x_3 - z_3)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + z_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{20}}$	=	$z_3\,\mathbf{a_1} + \left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_2} + z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{x}} + z_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{21}}$	=	$\left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_1} + z_3\,\mathbf{a_2} + (2x_3 - z_3)\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - z_3\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{22}}$	=	$(2x_3 - z_3)\,\mathbf{a_1} + z_3\,\mathbf{a_2} + \left(\frac{1}{2} - 2x_3 - z_3\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - z_3\right)\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III
$\mathbf{B_{23}}$	=	$-z_3\,\mathbf{a_1} - z_3\,\mathbf{a_2} + \left(\frac{1}{2} + 2x_3 + z_3\right)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{y}} - z_3\,a\,\hat{\mathbf{z}}$	$(96g)$	Si III

$\mathbf{B_{24}}$	=	$-z_3\,\mathbf{a_1} - z_3\,\mathbf{a_2} + (z_3 - 2x_3)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - z_3\,a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{25}}$	=	$(z_3 - 2x_3)\,\mathbf{a_1} + \left(\frac{1}{2} + 2x_3 + z_3\right)\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right)a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{26}}$	=	$\left(\frac{1}{2} + 2x_3 + z_3\right)\mathbf{a_1} + (z_3 - 2x_3)\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + z_3\right)a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{27}}$	=	$(z_3 - 2x_3)\,\mathbf{a_1} - z_3\,\mathbf{a_2} + \left(\frac{1}{2} + 2x_3 + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + z_3\right)a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{28}}$	=	$\left(\frac{1}{2} + 2x_3 + z_3\right)\mathbf{a_1} - z_3\,\mathbf{a_2} + (z_3 - 2x_3)\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + z_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{29}}$	=	$-z_3\,\mathbf{a_1} + (z_3 - 2x_3)\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - z_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{30}}$	=	$-z_3\,\mathbf{a_1} + \left(\frac{1}{2} + 2x_3 + z_3\right)\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{x}} - z_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{31}}$	=	$-z_3\,\mathbf{a_1} + (z_3 - 2x_3)\,\mathbf{a_2} + \left(\frac{1}{2} + 2x_3 + z_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + z_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{32}}$	=	$-z_3\,\mathbf{a_1} + \left(\frac{1}{2} + 2x_3 + z_3\right)\mathbf{a_2} + (z_3 - 2x_3)\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + z_3\right)a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{33}}$	=	$\left(\frac{1}{2} + 2x_3 + z_3\right)\mathbf{a_1} - z_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-z_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{z}}$	(96g)	Si III
$\mathbf{B_{34}}$	=	$(z_3 - 2x_3)\,\mathbf{a_1} - z_3\,\mathbf{a_2} - z_3\,\mathbf{a_3}$	=	$-z_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(96g)	Si III

References:

- G. B. Adams, M. O'Keeffe, A. A. Demkov, O. F. Sankey, and Y.-M. Huang, *Wide-band-gap Si in open fourfold-coordinated clathrate structures*, Phys. Rev. B **49**, 8048–8053 (1994), doi:10.1103/PhysRevB.49.8048.
- J. Gryko, P. F. McMillan, R. F. Marzke, G. K. Ramachandran, D. Patton, S. K. Deb, and O. F. Sankey, *Low-density framework form of crystalline silicon with a wide optical band gap*, Phys. Rev. B **62**, R7707–7710 (2000), doi:10.1103/PhysRevB.62.R7707.

Geometry files:

- CIF: pp. S793
- POSCAR: pp. S795

Cu_2Mg Cubic Laves Structure (C15): A2B_cF24_227_d_a

Prototype	:	Cu_2Mg
AFLOW prototype label	:	A2B_cF24_227_d_a
***Strukturbericht* designation**	:	C15
Pearson symbol	:	cF24
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A2B_cF24_227_d_a --params=`a

Other compounds with this structure:

- $CsBi_2$, $RbBi_2$

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{1}{8}\,\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	Mg
$\mathbf{B_2}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{7}{8}\,\mathbf{a_3}$	=	$\frac{7}{8}\,a\,\hat{\mathbf{x}} + \frac{7}{8}\,a\,\hat{\mathbf{y}} + \frac{7}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	Mg
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(16d)$	Cu

$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(16*d*)	Cu
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*d*)	Cu
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*d*)	Cu

References:

- J. B. Friauf, *The Crystal Structures of Two Intermetallic Compounds*, J. Am. Chem. Soc. **49**, 3107–3114 (1927), doi:10.1021/ja01411a017.

Found in:

- R. W. G. Wyckoff, *Crystal Structures Vol. 1* (Wiley, 1963), 2nd edn, pp. 365-367.

Geometry files:

- CIF: pp. S795
- POSCAR: pp. S796

Diamond (A4) Structure: A_cF8_227_a

Prototype	:	C
AFLOW prototype label	:	A_cF8_227_a
***Strukturbericht* designation**	:	A4
Pearson symbol	:	cF8
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A_cF8_227_a --params=`a

Other elements with this structure:

- Si, Ge, Sn

- This is the first crystal structure to be determined by X-ray diffraction.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{8}\,\mathbf{a_1} + \frac{1}{8}\,\mathbf{a_2} + \frac{1}{8}\,\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	C
$\mathbf{B_2}$	=	$\frac{7}{8}\,\mathbf{a_1} + \frac{7}{8}\,\mathbf{a_2} + \frac{7}{8}\,\mathbf{a_3}$	=	$\frac{7}{8}\,a\,\hat{\mathbf{x}} + \frac{7}{8}\,a\,\hat{\mathbf{y}} + \frac{7}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	C

References:

- W. H. Bragg and W. L. Bragg, *The Structure of Diamond*, Proc. R. Soc. A Math. Phys. Eng. Sci. **89**, 277–291 (1913), doi:10.1098/rspa.1913.0084.

Geometry files:

- CIF: pp. S796
- POSCAR: pp. S797

Spinel (Al_2MgO_4, $H1_1$) Structure: A2BC4_cF56_227_d_a_e

Prototype	:	Al_2MgO_4
AFLOW prototype label	:	A2BC4_cF56_227_d_a_e
***Strukturbericht* designation**	:	$H1_1$
Pearson symbol	:	cF56
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A2BC4_cF56_227_d_a_e` `--params=`a, x_3

Other compounds with this structure:

- Al_2Se_4Zn, Al_2CrS_4, $CaIn_2S_4$, Al_2CdS_4, Cr_2Se_4Zr, Mn_2Te_4Zn, many others.

- An *inverse spinel* has four Al atoms on the (8a) sites and (Al,Mg) alloyed on the (16d) sites.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{8}\mathbf{a_1} + \frac{1}{8}\mathbf{a_2} + \frac{1}{8}\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	Mg
$\mathbf{B_2}$	=	$\frac{7}{8}\mathbf{a_1} + \frac{7}{8}\mathbf{a_2} + \frac{7}{8}\mathbf{a_3}$	=	$\frac{7}{8}\,a\,\hat{\mathbf{x}} + \frac{7}{8}\,a\,\hat{\mathbf{y}} + \frac{7}{8}\,a\,\hat{\mathbf{z}}$	$(8a)$	Mg
$\mathbf{B_3}$	=	$\frac{1}{2}\mathbf{a_1} + \frac{1}{2}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(16d)$	Al
$\mathbf{B_4}$	=	$\frac{1}{2}\mathbf{a_1} + \frac{1}{2}\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(16d)$	Al
$\mathbf{B_5}$	=	$\frac{1}{2}\mathbf{a_1} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(16d)$	Al
$\mathbf{B_6}$	=	$\frac{1}{2}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(16d)$	Al
$\mathbf{B_7}$	=	$x_3\,\mathbf{a_1} + x_3\,\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(32e)$	O
$\mathbf{B_8}$	=	$x_3\,\mathbf{a_1} + (1 + x_3)\,\mathbf{a_2} + \left(\frac{1}{2} - 3x_3\right)\mathbf{a_3}$	=	$\left(\frac{3}{4} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{z}}$	$(32e)$	O
$\mathbf{B_9}$	=	$(1 + x_3)\,\mathbf{a_1} + \left(\frac{1}{2} - 3x_3\right)\mathbf{a_2} + x_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} - x_3\right)a\,\hat{\mathbf{z}}$	$(32e)$	O
$\mathbf{B_{10}}$	=	$\left(\frac{1}{2} - 3x_3\right)\mathbf{a_1} + x_3\,\mathbf{a_2} + (1 + x_3)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{3}{4} - x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_3\right)a\,\hat{\mathbf{z}}$	$(32e)$	O
$\mathbf{B_{11}}$	=	$-x_3\,\mathbf{a_1} - x_3\,\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(32e)$	O
$\mathbf{B_{12}}$	=	$-x_3\,\mathbf{a_1} + (1 - x_3)\,\mathbf{a_2} + \left(\frac{1}{2} + 3x_3\right)\mathbf{a_3}$	=	$\left(\frac{3}{4} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{z}}$	$(32e)$	O
$\mathbf{B_{13}}$	=	$(1 - x_3)\,\mathbf{a_1} + \left(\frac{1}{2} + 3x_3\right)\mathbf{a_2} - x_3\,\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + x_3\right)a\,\hat{\mathbf{z}}$	$(32e)$	O
$\mathbf{B_{14}}$	=	$\left(\frac{1}{2} + 3x_3\right)\mathbf{a_1} - x_3\,\mathbf{a_2} + (1 - x_3)\,\mathbf{a_3}$	=	$\left(\frac{1}{2} - x_3\right)a\,\hat{\mathbf{x}} + \left(\frac{3}{4} + x_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_3\right)a\,\hat{\mathbf{z}}$	$(32e)$	O

References:

- R. J. Hill, J. R. Craig, and G. V. Gibbs, *Systematics of the Spinel Structure Type*, Phys. Chem. Miner. **4**, 317–339 (1979).

Geometry files:

- CIF: pp. S797
- POSCAR: pp. S799

CTi_2 Structure: AB2_cF48_227_c_e

Prototype	:	CTi_2
AFLOW prototype label	:	AB2_cF48_227_c_e
***Strukturbericht* designation**	:	None
Pearson symbol	:	cF48
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB2_cF48_227_c_e` `--params=`a, x_2

Other compounds with this structure:

- $Ca_{33}Ge$

- Some sources consider the real prototype of this system to be $Ca_{33}Ge$, with the (32e) sites occupied by calcium atoms and the (16c) sites randomly occupied by calcium and germanium atoms.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \frac{1}{2}a\,\hat{\mathbf{y}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \frac{1}{2}a\,\hat{\mathbf{x}} + \frac{1}{2}a\,\hat{\mathbf{y}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	(16*c*)	C
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	(16*c*)	C
$\mathbf{B_3}$	=	$\frac{1}{2}\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*c*)	C
$\mathbf{B_4}$	=	$\frac{1}{2}\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*c*)	C
$\mathbf{B_5}$	=	$x_2\mathbf{a_1} + x_2\mathbf{a_2} + x_2\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(32*e*)	Ti
$\mathbf{B_6}$	=	$x_2\mathbf{a_1} + x_2\mathbf{a_2} + \left(\frac{1}{2} - 3\,x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	(32*e*)	Ti
$\mathbf{B_7}$	=	$x_2\mathbf{a_1} + \left(\frac{1}{2} - 3\,x_2\right)\mathbf{a_2} + x_2\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Ti
$\mathbf{B_8}$	=	$\left(\frac{1}{2} - 3\,x_2\right)\mathbf{a_1} + x_2\mathbf{a_2} + x_2\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Ti
$\mathbf{B_9}$	=	$-x_2\mathbf{a_1} - x_2\mathbf{a_2} + \left(\frac{1}{2} + 3\,x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(32*e*)	Ti
$\mathbf{B_{10}}$	=	$-x_2\mathbf{a_1} - x_2\mathbf{a_2} - x_2\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	(32*e*)	Ti
$\mathbf{B_{11}}$	=	$-x_2\mathbf{a_1} + \left(\frac{1}{2} + 3\,x_2\right)\mathbf{a_2} - x_2\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Ti
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} + 3\,x_2\right)\mathbf{a_1} - x_2\mathbf{a_2} - x_2\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_2\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Ti

References:

- H. Goretzki, *Neutron Diffraction Studies on Titanium-Carbon and Zirconium-Carbon Alloys*, Phys. Stat. Solidi B **20**, K141–K143 (1967), doi:10.1002/pssb.19670200260.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 2022.

Geometry files:

- CIF: pp. S799
- POSCAR: pp. S800

Fe_3W_3C Structure: AB3C3_cF112_227_c_de_f

Prototype	:	Fe_3W_3C
AFLOW prototype label	:	AB3C3_cF112_227_c_de_f
***Strukturbericht* designation**	:	$E9_3$
Pearson symbol	:	cF112
Space group number	:	227
Space group symbol	:	$Fd\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB3C3_cF112_227_c_de_f` `--params=`a, x_3, x_4

- Experimentally, the (48f) site is a random mixture of composition $W_{2/3}Fe_{1/3}$. We use W for this site in the pictures above.

Face-centered Cubic primitive vectors:

$$\mathbf{a}_1 = \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}}$$

Basis vectors:

Lattice Coordinates	Cartesian Coordinates	Wyckoff Position	Atom Type

$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	(16*c*)	C
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}}$	(16*c*)	C
$\mathbf{B_3}$	=	$\frac{1}{2}\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*c*)	C
$\mathbf{B_4}$	=	$\frac{1}{2}\mathbf{a_1}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*c*)	C
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(16*d*)	Fe I
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	(16*d*)	Fe I
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*d*)	Fe I
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(16*d*)	Fe I
$\mathbf{B_9}$	=	$x_3\mathbf{a_1} + x_3\mathbf{a_2} + x_3\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(32*e*)	Fe II
$\mathbf{B_{10}}$	=	$x_3\mathbf{a_1} + x_3\mathbf{a_2} + \left(\frac{1}{2} - 3\,x_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	(32*e*)	Fe II
$\mathbf{B_{11}}$	=	$x_3\mathbf{a_1} + \left(\frac{1}{2} - 3\,x_3\right)\mathbf{a_2} + x_3\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Fe II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - 3\,x_3\right)\mathbf{a_1} + x_3\mathbf{a_2} + x_3\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_3\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Fe II
$\mathbf{B_{13}}$	=	$-x_3\mathbf{a_1} - x_3\mathbf{a_2} + \left(\frac{1}{2} + 3\,x_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(32*e*)	Fe II
$\mathbf{B_{14}}$	=	$-x_3\mathbf{a_1} - x_3\mathbf{a_2} - x_3\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	(32*e*)	Fe II
$\mathbf{B_{15}}$	=	$-x_3\mathbf{a_1} + \left(\frac{1}{2} + 3\,x_3\right)\mathbf{a_2} - x_3\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Fe II
$\mathbf{B_{16}}$	=	$\left(\frac{1}{2} + 3\,x_3\right)\mathbf{a_1} - x_3\mathbf{a_2} - x_3\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_3\right)\,a\,\hat{\mathbf{z}}$	(32*e*)	Fe II
$\mathbf{B_{17}}$	=	$\left(\frac{1}{4} - x_4\right)\mathbf{a_1} + x_4\mathbf{a_2} + x_4\mathbf{a_3}$	=	$x_4\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{18}}$	=	$x_4\mathbf{a_1} + \left(\frac{1}{4} - x_4\right)\mathbf{a_2} + \left(\frac{1}{4} - x_4\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_4\right)\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{19}}$	=	$x_4\mathbf{a_1} + \left(\frac{1}{4} - x_4\right)\mathbf{a_2} + x_4\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + x_4\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{20}}$	=	$\left(\frac{1}{4} - x_4\right)\mathbf{a_1} + x_4\mathbf{a_2} + \left(\frac{1}{4} - x_4\right)\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_4\right)\,a\,\hat{\mathbf{y}} + \frac{1}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{21}}$	=	$x_4\mathbf{a_1} + x_4\mathbf{a_2} + \left(\frac{1}{4} - x_4\right)\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + x_4\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{22}}$	=	$\left(\frac{1}{4} - x_4\right)\mathbf{a_1} + \left(\frac{1}{4} - x_4\right)\mathbf{a_2} + x_4\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + \frac{1}{8}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_4\right)\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{23}}$	=	$\left(x_4 + \frac{3}{4}\right)\mathbf{a_1} - x_4\mathbf{a_2} + \left(x_4 + \frac{3}{4}\right)\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} + \left(x_4 + \frac{3}{4}\right)\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{24}}$	=	$-x_4\mathbf{a_1} + \left(x_4 + \frac{3}{4}\right)\mathbf{a_2} - x_4\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} - x_4\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{25}}$	=	$-x_4\mathbf{a_1} + \left(x_4 + \frac{3}{4}\right)\mathbf{a_2} + \left(x_4 + \frac{3}{4}\right)\mathbf{a_3}$	=	$\left(x_4 + \frac{3}{4}\right)\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{26}}$	=	$\left(x_4 + \frac{3}{4}\right)\mathbf{a_1} - x_4\mathbf{a_2} - x_4\mathbf{a_3}$	=	$-x_4\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} + \frac{3}{8}\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{27}}$	=	$-x_4\mathbf{a_1} - x_4\mathbf{a_2} + \left(x_4 + \frac{3}{4}\right)\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} - x_4\,a\,\hat{\mathbf{z}}$	(48*f*)	W
$\mathbf{B_{28}}$	=	$+\left(x_4 + \frac{3}{4}\right)\mathbf{a_1} + \left(x_4 + \frac{3}{4}\right)\mathbf{a_2} - x_4\mathbf{a_3}$	=	$\frac{3}{8}\,a\,\hat{\mathbf{x}} + \frac{3}{8}\,a\,\hat{\mathbf{y}} + \left(x_4 + \frac{3}{4}\right)\,a\,\hat{\mathbf{z}}$	(48*f*)	W

References:

- Q.-B. Yang and S. Andersson, *Application of coincidence site lattices for crystal structure description. Part I:* $\Sigma = 3$, Acta Crystallogr. Sect. B Struct. Sci. **43**, 1–14 (1987), doi:10.1107/S0108768187098380.

Geometry files:

- CIF: pp. S800
- POSCAR: pp. S801

Body-Centered Cubic (W, A2) Structure: A_cI2_229_a

Prototype	:	W
AFLOW prototype label	:	A_cI2_229_a
***Strukturbericht* designation**	:	A2
Pearson symbol	:	cI2
Space group number	:	229
Space group symbol	:	$Im\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A_cI2_229_a --params=`a

Other elements with this structure:

- Li (at room temp.), Na, K, V, Cr, Fe, Rb, Nb, Mo, Cs, Ba, Eu, Ta

- Although more accurate measurements of the lattice constant of tungsten are available, (Davey, 1925) is chosen because of the unique experimental technique.

Body-centered Cubic primitive vectors:

$$\begin{aligned}
\mathbf{a}_1 &= -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}} \\
\mathbf{a}_2 &= \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}} \\
\mathbf{a}_3 &= \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}
\end{aligned}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	W

References:

- W. P. Davey, *The Lattice Parameter and Density of Pure Tungsten*, Phys. Rev. **26**, 736–738 (1925), doi:10.1103/PhysRev.26.736.

Geometry files:

- CIF: pp. S802
- POSCAR: pp. S802

High-Pressure H_3S Structure: A3B_cI8_229_b_a

Prototype	:	H_3S
AFLOW prototype label	:	A3B_cI8_229_b_a
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI8
Space group number	:	229
Space group symbol	:	$Im\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A3B_cI8_229_b_a --params=`a

Other compounds with this structure:

- La_2O_3, Nd_2O_3 (In both cases the oxygen atoms only partially occupy the (6b) Wyckoff positions.)

- (Duan, 2014) predicted that this structure of H_3S would be a conventional superconductor at temperatures above 191 K and a pressure of 200 GPa. (Drozdov, 2015) found a superconductor in the hydrogen-sulfur system at 203 K and pressure near 200 GPa. (Bernstein, 2015) showed that this structure is the ground state of the H-S system near 200 GPa. Both La_2O_3 and Nd_2O_3 can form in this structure under ambient conditions, but in both cases the oxygen atoms occupy only 50% of the (6b) Wyckoff positions. We have used the fact that all vectors of the form $(\pm a/2\hat{\mathbf{x}} \pm a/2\hat{\mathbf{y}} \pm a/2\hat{\mathbf{z}})$ are primitive vectors of the body-centered cubic lattice to simplify the positions of some atoms in both lattice and Cartesian coordinates.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	S
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(6b)$	H
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(6b)$	H
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(6b)$	H

References:

- A. P. Drozdov, M. I. Eremets, I. A. Troyan, V. Ksenofontov, and S. I. Shylin, *Conventional superconductivity at 203 kelvin at high pressures in the sulfur hydride system*, Nature **525**, 73–76 (2015), doi:10.1038/nature14964.
- D. Duan, Y. Liu, F. Tian, D. Li, X. Huang, Z. Zhao, H. Yu, B. Liu, W. Tian, and T. Cui, *Pressure-induced metallization of dense $(H_2S)_2H_2$ with high-T_c superconductivity*, Sci. Rep. **4**, 6968 (2014), doi:10.1038/srep06968.
- N. Bernstein, C. Stephen Hellberg, M. D. Johannes, I. I. Mazin, and M. J. Mehl, *What superconducts in sulfur hydrides under pressure and why*, Phys. Rev. B **91**, 060511(R) (2015), doi:10.1103/PhysRevB.91.060511.

Geometry files:

- CIF: pp. S802
- POSCAR: pp. S803

Pt_3O_4 Structure: A4B3_cI14_229_c_b

Prototype	:	Pt_3O_4
AFLOW prototype label	:	A4B3_cI14_229_c_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI14
Space group number	:	229
Space group symbol	:	$Im\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A4B3_cI14_229_c_b --params=`a

- This is a simple defect superstructure of the CsCl (B2) structure. One atom has been removed from a 2×2×2 supercell of CsCl.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}a\,\hat{\mathbf{x}} - \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} - \tfrac{1}{2}a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$\frac{1}{2}\mathbf{a_2} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{x}}$	$(6b)$	Pt
$\mathbf{B_2}$	=	$\frac{1}{2}\mathbf{a_1} + \frac{1}{2}\mathbf{a_3}$	=	$\frac{1}{2}a\,\hat{\mathbf{y}}$	$(6b)$	Pt
$\mathbf{B_3}$	=	$\frac{1}{2}\mathbf{a_1} + \frac{1}{2}\mathbf{a_2}$	=	$\frac{1}{2}a\,\hat{\mathbf{z}}$	$(6b)$	Pt

$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	O
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	O
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	O
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	O

References:

- O. Muller and R. Roy, *Formation and stability of the platinum and rhodium oxides at high oxygen pressures and the structures of Pt_3O_4, β-PtO_2 and RhO_2*, J. Less-Common Met. **16**, 129–146 (1968), doi:10.1016/0022-5088(68)90070-2.
- E. E. Galloni and A. E. Roffo Jr., *The Crystalline Structure of Pt_3O_4*, J. Chem. Phys. **9**, 875–877 (1941), doi:10.1063/1.1750860.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 4751.

Geometry files:

- CIF: pp. S803
- POSCAR: pp. S804

Sb_2Tl_7 ($L2_2$) Structure: A2B7_cI54_229_e_afh

Prototype	:	Sb_2Tl_7
AFLOW prototype label	:	A2B7_cI54_229_e_afh
***Strukturbericht* designation**	:	$L2_2$
Pearson symbol	:	cI54
Space group number	:	229
Space group symbol	:	$Im\bar{3}m$
AFLOW prototype command	:	`aflow --proto=A2B7_cI54_229_e_afh` `--params=`a, x_2, x_3, y_4

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Tl I
$\mathbf{B_2}$	=	$x_2\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}}$	$(12e)$	Sb

$\mathbf{B_3}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{y}}$	$(12e)$	Sb
$\mathbf{B_4}$	=	$x_2\,\mathbf{a_1} + x_2\,\mathbf{a_2}$	=	$x_2\,a\,\hat{\mathbf{z}}$	$(12e)$	Sb
$\mathbf{B_5}$	=	$-x_2\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}}$	$(12e)$	Sb
$\mathbf{B_6}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{y}}$	$(12e)$	Sb
$\mathbf{B_7}$	=	$-x_2\,\mathbf{a_1} - x_2\,\mathbf{a_2}$	=	$-x_2\,a\,\hat{\mathbf{z}}$	$(12e)$	Sb
$\mathbf{B_8}$	=	$2x_3\,\mathbf{a_1} + 2x_3\,\mathbf{a_2} + 2x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(16f)$	Tl II
$\mathbf{B_9}$	=	$-2x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(16f)$	Tl II
$\mathbf{B_{10}}$	=	$-2x_3\,\mathbf{a_2}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(16f)$	Tl II
$\mathbf{B_{11}}$	=	$-2x_3\,\mathbf{a_1}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(16f)$	Tl II
$\mathbf{B_{12}}$	=	$2x_3\,\mathbf{a_3}$	=	$x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(16f)$	Tl II
$\mathbf{B_{13}}$	=	$-2x_3\,\mathbf{a_1} - 2x_3\,\mathbf{a_2} - 2x_3\,\mathbf{a_3}$	=	$-x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} - x_3\,a\,\hat{\mathbf{z}}$	$(16f)$	Tl II
$\mathbf{B_{14}}$	=	$2x_3\,\mathbf{a_2}$	=	$x_3\,a\,\hat{\mathbf{x}} - x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(16f)$	Tl II
$\mathbf{B_{15}}$	=	$2x_3\,\mathbf{a_1}$	=	$-x_3\,a\,\hat{\mathbf{x}} + x_3\,a\,\hat{\mathbf{y}} + x_3\,a\,\hat{\mathbf{z}}$	$(16f)$	Tl II
$\mathbf{B_{16}}$	=	$2y_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{y}} + y_4\,a\,\hat{\mathbf{z}}$	$(24h)$	Tl III
$\mathbf{B_{17}}$	=	$y_4\,\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{y}} + y_4\,a\,\hat{\mathbf{z}}$	$(24h)$	Tl III
$\mathbf{B_{18}}$	=	$-y_4\,\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{y}} - y_4\,a\,\hat{\mathbf{z}}$	$(24h)$	Tl III
$\mathbf{B_{19}}$	=	$-2y_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{y}} - y_4\,a\,\hat{\mathbf{z}}$	$(24h)$	Tl III
$\mathbf{B_{20}}$	=	$y_4\,\mathbf{a_1} + 2y_4\,\mathbf{a_2} + y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{z}}$	$(24h)$	Tl III
$\mathbf{B_{21}}$	=	$-y_4\,\mathbf{a_1} + y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{z}}$	$(24h)$	Tl III
$\mathbf{B_{22}}$	=	$y_4\,\mathbf{a_1} - y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{z}}$	$(24h)$	Tl III
$\mathbf{B_{23}}$	=	$-y_4\,\mathbf{a_1} - 2y_4\,\mathbf{a_2} - y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{z}}$	$(24h)$	Tl III
$\mathbf{B_{24}}$	=	$y_4\,\mathbf{a_1} + y_4\,\mathbf{a_2} + 2y_4\,\mathbf{a_3}$	=	$y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}}$	$(24h)$	Tl III
$\mathbf{B_{25}}$	=	$y_4\,\mathbf{a_1} - y_4\,\mathbf{a_2}$	=	$-y_4\,a\,\hat{\mathbf{x}} + y_4\,a\,\hat{\mathbf{y}}$	$(24h)$	Tl III
$\mathbf{B_{26}}$	=	$-y_4\,\mathbf{a_1} + y_4\,\mathbf{a_2}$	=	$y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}}$	$(24h)$	Tl III
$\mathbf{B_{27}}$	=	$-y_4\,\mathbf{a_1} - y_4\,\mathbf{a_2} - 2y_4\,\mathbf{a_3}$	=	$-y_4\,a\,\hat{\mathbf{x}} - y_4\,a\,\hat{\mathbf{y}}$	$(24h)$	Tl III

References:

- R. Stokhuyzen, C. Chieh, and W. B. Pearson, *Crystal Structure of Sb_2Tl_7*, Can. J. Chem. **55**, 1120–1122 (1977), doi:10.1139/v77-157.

Found in:

- P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn, pp. 5199.

Geometry files:

- CIF: pp. S804
- POSCAR: pp. S805

Model of Austenite Structure (cI32): AB12C3_cI32_229_a_h_b

Prototype	:	$CrFe_{12}Ni_3$
AFLOW prototype label	:	AB12C3_cI32_229_a_h_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI32
Space group number	:	229
Space group symbol	:	$Im\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB12C3_cI32_229_a_h_b --params=`a, y_3

- Austenitic steels are alloys of iron and other metals with an averaged face-centered cubic structure. This model is not meant to represent a real steel, and the selection of atom types for each Wyckoff position is arbitrary. If we set the $y_3 = 1/4$ then the atoms are on the sites of an fcc lattice.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Cr
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(6b)$	Ni

$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	(6*b*)	Ni
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	(6*b*)	Ni
$\mathbf{B_5}$	=	$2y_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{y}} + y_3\,a\,\hat{\mathbf{z}}$	(24*h*)	Fe
$\mathbf{B_6}$	=	$y_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{y}} + y_3\,a\,\hat{\mathbf{z}}$	(24*h*)	Fe
$\mathbf{B_7}$	=	$-y_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{y}} - y_3\,a\,\hat{\mathbf{z}}$	(24*h*)	Fe
$\mathbf{B_8}$	=	$-2y_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{y}} - y_3\,a\,\hat{\mathbf{z}}$	(24*h*)	Fe
$\mathbf{B_9}$	=	$y_3\,\mathbf{a_1} + 2y_3\,\mathbf{a_2} + y_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{z}}$	(24*h*)	Fe
$\mathbf{B_{10}}$	=	$-y_3\,\mathbf{a_1} + y_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{z}}$	(24*h*)	Fe
$\mathbf{B_{11}}$	=	$y_3\,\mathbf{a_1} - y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{z}}$	(24*h*)	Fe
$\mathbf{B_{12}}$	=	$-y_3\,\mathbf{a_1} - 2y_3\,\mathbf{a_2} - y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{z}}$	(24*h*)	Fe
$\mathbf{B_{13}}$	=	$y_3\,\mathbf{a_1} + y_3\,\mathbf{a_2} + 2y_3\,\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}}$	(24*h*)	Fe
$\mathbf{B_{14}}$	=	$y_3\,\mathbf{a_1} - y_3\,\mathbf{a_2}$	=	$-y_3\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}}$	(24*h*)	Fe
$\mathbf{B_{15}}$	=	$-y_3\,\mathbf{a_1} + y_3\,\mathbf{a_2}$	=	$y_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}}$	(24*h*)	Fe
$\mathbf{B_{16}}$	=	$-y_3\,\mathbf{a_1} - y_3\,\mathbf{a_2} - 2y_3\,\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}} - y_3\,a\,\hat{\mathbf{y}}$	(24*h*)	Fe

References:

- M. J. Mehl, Hypothetical cI32 Austenite Structure.

Geometry files:

- CIF: pp. S805
- POSCAR: pp. S806

Model of Ferrite Structure (cI16): AB4C3_cI16_229_a_c_b

Prototype	:	$CrFe_4Ni_3$
AFLOW prototype label	:	AB4C3_cI16_229_a_c_b
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI16
Space group number	:	229
Space group symbol	:	$Im\bar{3}m$
AFLOW prototype command	:	`aflow --proto=AB4C3_cI16_229_a_c_b --params=`a

- Ferrite is steel with a bcc structure. This structure represents one possible ordering which might be found in an Fe-Ni-Cr steel. Note that it is not meant to represent a real steel. If we replace the Cr atoms by Ni, this becomes the CsCl (B2) structure. If we replace both the Cr and Ni atoms by Fe, we get the bcc (A2) structure. In either case, $a_{bcc/B2} = 1/2a$.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} - \tfrac{1}{2}\,a\,\hat{\mathbf{y}} + \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}\,a\,\hat{\mathbf{x}} + \tfrac{1}{2}\,a\,\hat{\mathbf{y}} - \tfrac{1}{2}\,a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(2a)$	Cr
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(6b)$	Ni
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(6b)$	Ni

$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	(6*b*)	Ni
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	Fe
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	Fe
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	Fe
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	(8*c*)	Fe

References:

- M. J. Mehl, Hypothetical cI16 Ferrite Structure.

Geometry files:

- CIF: pp. S806
- POSCAR: pp. S807

Ga_4Ni_3 Structure: A4B3_cI112_230_af_g

Prototype	:	Ga_4Ni_3
AFLOW prototype label	:	A4B3_cI112_230_af_g
***Strukturbericht* designation**	:	None
Pearson symbol	:	cI112
Space group number	:	230
Space group symbol	:	$Ia\bar{3}d$
AFLOW prototype command	:	`aflow --proto=A4B3_cI112_230_af_g` `--params=`a, x_2, y_3

- This is a simple defect superstructure of the CsCl (B2) structure. If a GaNi B2 structure is expanded into a 128 atom supercell, we can describe it using space group $Ia\bar{3}d$ (#230), with Ga atoms on the (16a) and (48f) Wyckoff sites and Ni atoms on the (16b) and (48g) sites. Removing the Ni atoms from the (16b) sites yields this structure.

Body-centered Cubic primitive vectors:

$$\mathbf{a}_1 = -\tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_2 = \tfrac{1}{2}a\,\hat{\mathbf{x}} - \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a}_3 = \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} - \tfrac{1}{2}a\,\hat{\mathbf{z}}$$

Basis vectors:

		Lattice Coordinates		Cartesian Coordinates	Wyckoff Position	Atom Type
$\mathbf{B_1}$	=	$0\,\mathbf{a_1} + 0\,\mathbf{a_2} + 0\,\mathbf{a_3}$	=	$0\hat{\mathbf{x}} + 0\hat{\mathbf{y}} + 0\hat{\mathbf{z}}$	$(16a)$	Ga I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{y}}$	$(16a)$	Ga I
$\mathbf{B_3}$	=	$\frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}$	$(16a)$	Ga I
$\mathbf{B_4}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(16a)$	Ga I
$\mathbf{B_5}$	=	$\frac{1}{2}\,\mathbf{a_1}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(16a)$	Ga I
$\mathbf{B_6}$	=	$\frac{1}{2}\,\mathbf{a_1} + \frac{1}{2}\,\mathbf{a_2} + \frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(16a)$	Ga I
$\mathbf{B_7}$	=	$\frac{1}{2}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(16a)$	Ga I
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a_2}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(16a)$	Ga I
$\mathbf{B_9}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(\frac{1}{4} + x_2\right)\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$x_2\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{10}}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{1}{4} - x_2\right)\mathbf{a_2} + \left(\frac{1}{2} - x_2\right)\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{11}}$	=	$x_2\,\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{4} + x_2\right)\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + x_2\,a\,\hat{\mathbf{y}}$	$(48f)$	Ga II
$\mathbf{B_{12}}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{4} - x_2\right)\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{13}}$	=	$\left(\frac{1}{4} + x_2\right)\mathbf{a_1} + x_2\,\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + x_2\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{14}}$	=	$\left(\frac{1}{4} - x_2\right)\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}\frac{1}{4}\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{15}}$	=	$\left(\frac{1}{4} + x_2\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + x_2\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{3}{4} + x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{16}}$	=	$\left(\frac{1}{4} - x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(\frac{1}{2} - x_2\right)\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)a\,\hat{\mathbf{y}}$	$(48f)$	Ga II
$\mathbf{B_{17}}$	=	$\frac{3}{4}\,\mathbf{a_1} + x_2\,\mathbf{a_2} + \left(\frac{1}{4} + x_2\right)\mathbf{a_3}$	=	$\left(\frac{3}{4} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{18}}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(\frac{1}{2} - x_2\right)\mathbf{a_2} + \left(\frac{1}{4} - x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{19}}$	=	$\left(\frac{1}{2} - x_2\right)\mathbf{a_1} + \left(\frac{1}{4} - x_2\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{20}}$	=	$x_2\,\mathbf{a_1} + \left(\frac{1}{4} + x_2\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}\frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{3}{4} + x_2\right)a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{21}}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{3}{4} - x_2\right)\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$-x_2\,a\,\hat{\mathbf{x}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{22}}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(x_2 + \frac{3}{4}\right)\mathbf{a_2} + \left(\frac{1}{2} + x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{23}}$	=	$-x_2\,\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{3}{4} - x_2\right)\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} - x_2\,a\,\hat{\mathbf{y}}$	$(48f)$	Ga II
$\mathbf{B_{24}}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} + \left(x_2 + \frac{3}{4}\right)\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{y}}$	$(48f)$	Ga II
$\mathbf{B_{25}}$	=	$\left(\frac{3}{4} - x_2\right)\mathbf{a_1} - x_2\,\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{y}} - x_2\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{26}}$	=	$\left(x_2 + \frac{3}{4}\right)\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{2} + x_2\right)a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{27}}$	=	$\left(\frac{3}{4} - x_2\right)\mathbf{a_1} + \frac{1}{4}\,\mathbf{a_2} - x_2\,\mathbf{a_3}$	=	$\frac{3}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} - x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{28}}$	=	$\left(x_2 + \frac{3}{4}\right)\mathbf{a_1} + \frac{3}{4}\,\mathbf{a_2} + \left(\frac{1}{2} + x_2\right)\mathbf{a_3}$	=	$\frac{1}{4}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{4} + x_2\right)a\,\hat{\mathbf{y}} + \frac{1}{2}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{29}}$	=	$\frac{1}{4}\,\mathbf{a_1} - x_2\,\mathbf{a_2} + \left(\frac{3}{4} - x_2\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} - x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{3}{4}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{30}}$	=	$\frac{3}{4}\,\mathbf{a_1} + \left(\frac{1}{2} + x_2\right)\mathbf{a_2} + \left(x_2 + \frac{3}{4}\right)\mathbf{a_3}$	=	$\left(\frac{1}{4} + x_2\right)a\,\hat{\mathbf{x}} + \frac{1}{2}\,a\,\hat{\mathbf{y}} + \frac{1}{4}\,a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{31}}$	=	$\left(\frac{1}{2} + x_2\right)\mathbf{a_1} + \left(x_2 + \frac{3}{4}\right)\mathbf{a_2} + \frac{3}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}} + \frac{1}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} + x_2\right)a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{32}}$	=	$-x_2\,\mathbf{a_1} + \left(\frac{3}{4} - x_2\right)\mathbf{a_2} + \frac{1}{4}\,\mathbf{a_3}$	=	$\frac{1}{2}\,a\,\hat{\mathbf{x}}\frac{3}{4}\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - x_2\right)a\,\hat{\mathbf{z}}$	$(48f)$	Ga II
$\mathbf{B_{33}}$	=	$\frac{1}{4}\,\mathbf{a_1} + \left(\frac{3}{8} - y_3\right)\mathbf{a_2} + \left(\frac{1}{8} + y_3\right)\mathbf{a_3}$	=	$\frac{1}{8}\,a\,\hat{\mathbf{x}} + y_3\,a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - y_3\right)a\,\hat{\mathbf{z}}$	$(48g)$	Ni
$\mathbf{B_{34}}$	=	$\left(\frac{3}{4} - 2y_3\right)\mathbf{a_1} + \left(\frac{1}{8} - y_3\right)\mathbf{a_2} + \left(\frac{3}{8} - y_3\right)\mathbf{a_3}$	=	$\frac{7}{8}\,a\,\hat{\mathbf{x}} + \left(\frac{1}{2} - y_3\right)a\,\hat{\mathbf{y}} + \left(\frac{1}{4} - y_3\right)a\,\hat{\mathbf{z}}$	$(48g)$	Ni

$\mathbf{B_{35}}$	=	$\left(2y_3+\frac{3}{4}\right)\mathbf{a_1}+\left(\frac{1}{8}+y_3\right)\mathbf{a_2}+\left(\frac{3}{8}+y_3\right)\mathbf{a_3}$	=	$\frac{7}{8}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{36}}$	=	$\frac{1}{4}\mathbf{a_1}+\left(\frac{3}{8}+y_3\right)\mathbf{a_2}+\left(\frac{1}{8}-y_3\right)\mathbf{a_3}$	=	$\frac{1}{8}a\,\hat{\mathbf{x}}-y_3\,a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{37}}$	=	$\left(\frac{1}{8}+y_3\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{3}{8}-y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{x}}+\frac{1}{8}a\,\hat{\mathbf{y}}+y_3\,a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{38}}$	=	$\left(\frac{3}{8}-y_3\right)\mathbf{a_1}+\left(\frac{3}{4}-2y_3\right)\mathbf{a_2}+\left(\frac{1}{8}-y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{x}}+\frac{7}{8}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{39}}$	=	$\left(\frac{3}{8}+y_3\right)\mathbf{a_1}+\left(2y_3+\frac{3}{4}\right)\mathbf{a_2}+\left(\frac{1}{8}+y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{x}}+\frac{7}{8}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{40}}$	=	$\left(\frac{1}{8}-y_3\right)\mathbf{a_1}+\frac{1}{4}\mathbf{a_2}+\left(\frac{3}{8}+y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{x}}+\frac{1}{8}a\,\hat{\mathbf{y}}-y_3\,a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{41}}$	=	$\left(\frac{3}{8}-y_3\right)\mathbf{a_1}+\left(\frac{1}{8}+y_3\right)\mathbf{a_2}+\frac{1}{4}\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{y}}+\frac{1}{8}a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{42}}$	=	$\left(\frac{1}{8}-y_3\right)\mathbf{a_1}+\left(\frac{3}{8}-y_3\right)\mathbf{a_2}+\left(\frac{3}{4}-2y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{y}}+\frac{7}{8}a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{43}}$	=	$\left(\frac{1}{8}+y_3\right)\mathbf{a_1}+\left(\frac{3}{8}+y_3\right)\mathbf{a_2}+\left(2y_3+\frac{3}{4}\right)\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{y}}+\frac{7}{8}a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{44}}$	=	$\left(\frac{3}{8}+y_3\right)\mathbf{a_1}+\left(\frac{1}{8}-y_3\right)\mathbf{a_2}+\frac{1}{4}\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{y}}+\frac{1}{8}a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{45}}$	=	$\frac{3}{4}\mathbf{a_1}+\left(\frac{5}{8}+y_3\right)\mathbf{a_2}+\left(\frac{7}{8}-y_3\right)\mathbf{a_3}$	=	$\frac{3}{8}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{46}}$	=	$\left(\frac{1}{4}+2y_3\right)\mathbf{a_1}+\left(\frac{7}{8}+y_3\right)\mathbf{a_2}+\left(\frac{5}{8}+y_3\right)\mathbf{a_3}$	=	$\frac{5}{8}a\,\hat{\mathbf{x}}+y_3\,a\,\hat{\mathbf{y}}+\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{47}}$	=	$\left(\frac{1}{4}-2y_3\right)\mathbf{a_1}+\left(\frac{7}{8}-y_3\right)\mathbf{a_2}+\left(\frac{5}{8}-y_3\right)\mathbf{a_3}$	=	$\frac{5}{8}a\,\hat{\mathbf{x}}-y_3\,a\,\hat{\mathbf{y}}+\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{48}}$	=	$\frac{3}{4}\mathbf{a_1}+\left(\frac{5}{8}-y_3\right)\mathbf{a_2}+\left(y_3+\frac{7}{8}\right)\mathbf{a_3}$	=	$\frac{3}{8}a\,\hat{\mathbf{x}}+\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{y}}+\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{49}}$	=	$\left(\frac{7}{8}-y_3\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{5}{8}+y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{x}}+\frac{3}{8}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{50}}$	=	$\left(y_3+\frac{5}{8}\right)\mathbf{a_1}+\left(\frac{1}{4}+2y_3\right)\mathbf{a_2}+\left(\frac{7}{8}+y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{x}}+\frac{5}{8}a\,\hat{\mathbf{y}}+y_3\,a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{51}}$	=	$\left(\frac{5}{8}-y_3\right)\mathbf{a_1}+\left(\frac{1}{4}-2y_3\right)\mathbf{a_2}+\left(\frac{7}{8}-y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{x}}+\frac{5}{8}a\,\hat{\mathbf{y}}-y_3\,a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{52}}$	=	$\left(y_3+\frac{7}{8}\right)\mathbf{a_1}+\frac{3}{4}\mathbf{a_2}+\left(\frac{5}{8}-y_3\right)\mathbf{a_3}$	=	$\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{x}}+\frac{3}{8}a\,\hat{\mathbf{y}}+\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{53}}$	=	$\left(\frac{5}{8}+y_3\right)\mathbf{a_1}+\left(\frac{7}{8}-y_3\right)\mathbf{a_2}+\frac{3}{4}\mathbf{a_3}$	=	$\left(\frac{1}{2}-y_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{y}}+\frac{3}{8}a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{54}}$	=	$\left(\frac{7}{8}+y_3\right)\mathbf{a_1}+\left(y_3+\frac{5}{8}\right)\mathbf{a_2}+\left(\frac{1}{4}+2y_3\right)\mathbf{a_3}$	=	$y_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{4}+y_3\right)a\,\hat{\mathbf{y}}+\frac{5}{8}a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{55}}$	=	$\left(\frac{7}{8}-y_3\right)\mathbf{a_1}+\left(\frac{5}{8}-y_3\right)\mathbf{a_2}+\left(\frac{1}{4}-2y_3\right)\mathbf{a_3}$	=	$-y_3\,a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{y}}+\frac{5}{8}a\,\hat{\mathbf{z}}$	(48*g*)	Ni
$\mathbf{B_{56}}$	=	$\left(\frac{5}{8}-y_3\right)\mathbf{a_1}+\left(y_3+\frac{7}{8}\right)\mathbf{a_2}+\frac{3}{4}\mathbf{a_3}$	=	$\left(\frac{1}{2}+y_3\right)a\,\hat{\mathbf{x}}+\left(\frac{1}{4}-y_3\right)a\,\hat{\mathbf{y}}+\frac{3}{8}a\,\hat{\mathbf{z}}$	(48*g*)	Ni

References:

- M. Ellner, K. J. Best, H. Jacobi, and K. Schubert, *Struktur von Ni_3Ga_4*, J. Less-Common Met. **19**, 294–296 (1969), doi:10.1016/0022-5088(69)90109-X.

Found in:

- P. Villars and K. Cenzual, *Landolt-Börnstein - Group III Condensed Matter* (Springer-Verlag Berlin Heidelberg, 2004). Accessed through the Springer Materials site.

Geometry files:
- CIF: pp. S807
- POSCAR: pp. S807

CIF and POSCAR Files

FeS_2 (P1): AB2_aP12_1_4a_8a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'pyrite'
_chemical_formula_sum 'Fe S2'

loop_
_publ_author_name
 'Peter Bayliss'
_journal_name_full
;
American Mineralogist
;
_journal_volume 62
_journal_year 1977
_journal_page_first 1168
_journal_page_last 1172
_publ_Section_title
;
 Crystal structure refinement a weakly anisotropic pyrite
;

_aflow_proto 'AB2_aP12_1_4a_8a'
_aflow_params 'a,b/a,c/a,\alpha,\beta,\gamma,x1,y1,z1,x2,y2,z2,x3,y3,z3,
      ↪ x4,y4,z4,x5,y5,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,y10,
      ↪ z10,x11,y11,z11,x12,y12,z12'
_aflow_params_values '5.417,1.0,1.0,90.0,90.0,90.0,0.001,0.002,0.003,
      ↪ 0.4966,0.0001,0.5036,0.5001,0.502,0.0011,-0.0006,0.5013,0.5038,
      ↪ 0.3857,0.3832,0.384,0.1149,0.6114,0.8846,0.8854,0.1157,0.6143,
      ↪ 0.6153,0.8865,0.1141,0.6151,0.6132,0.6137,0.8854,0.3818,0.1149,
      ↪ 0.1147,0.8856,0.3841,0.3857,0.1161,0.8842'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'aP12'

_symmetry_space_group_name_Hall "P 1"
_symmetry_space_group_name_H-M "P 1"
_symmetry_Int_Tables_number 1

_cell_length_a      5.41700
_cell_length_b      5.41700
_cell_length_c      5.41700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Fe1 Fe   1 a 0.00100  0.00200 0.00300 1.00000
Fe2 Fe   1 a 0.49660  0.00010 0.50360 1.00000
Fe3 Fe   1 a 0.50010  0.50200 0.00110 1.00000
Fe4 Fe   1 a -0.00060 0.50130 0.50380 1.00000
S1  S    1 a 0.38570  0.38320 0.38400 1.00000
S2  S    1 a 0.11490  0.61140 0.88460 1.00000
S3  S    1 a 0.88540  0.11570 0.61430 1.00000
S4  S    1 a 0.61530  0.88650 0.11410 1.00000
S5  S    1 a 0.61510  0.61320 0.61370 1.00000
S6  S    1 a 0.88540  0.38180 0.11490 1.00000
S7  S    1 a 0.11470  0.88560 0.38410 1.00000
S8  S    1 a 0.38570  0.11610 0.88420 1.00000
```

FeS_2 (P1): AB2_aP12_1_4a_8a - POSCAR

```
AB2_aP12_1_4a_8a & a,b/a,c/a,\alpha,\beta,\gamma,x1,y1,z1,x2,y2,z2,x3,y3
      ↪ ,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,
      ↪ y10,z10,x11,y11,z11,x12,y12,z12 --params=5.417,1.0,1.0,90.0,
      ↪ 90.0,90.0,0.001,0.002,0.003,0.4966,0.0001,0.5036,0.5001,0.502,
      ↪ 0.0011,-0.0006,0.5013,0.5038,0.3857,0.3832,0.384,0.1149,0.6114,
      ↪ 0.8846,0.8854,0.1157,0.6143,0.6153,0.8865,0.1141,0.6151,0.6132,
      ↪ 0.6137,0.8854,0.3818,0.1149,0.1147,0.8856,0.3841,0.3857,0.1161,
      ↪ 0.8842 & P1        C_1^1 #1 (a^12) & aP12 & & FeS2 & anisotropic
      ↪  Pyrite & Bayliss, Am. Mineral. 62, 1168-72 (1977)
   1.0000000000000000
   5.41700000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.41700000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.41700000000000
 (1a)
   12
Direct
  -0.00060000000000    0.50130000000000    0.50380000000000    Fe    (1a)
   0.00100000000000    0.00200000000000    0.00300000000000    Fe    (1a)
   0.49660000000000    0.00010000000000    0.50360000000000    Fe    (1a)
   0.50010000000000    0.50200000000000    0.00110000000000    Fe    (1a)
   0.11470000000000    0.88560000000000    0.38410000000000    S     (1a)
   0.11490000000000    0.61140000000000    0.88460000000000    S     (1a)
   0.38570000000000    0.11610000000000    0.88420000000000    S     (1a)
   0.38570000000000    0.38320000000000    0.38400000000000    S     (1a)
   0.61510000000000    0.61320000000000    0.61370000000000    S     (1a)
   0.61530000000000    0.88650000000000    0.11410000000000    S     (1a)
   0.88540000000000    0.11570000000000    0.61430000000000    S     (1a)
   0.88540000000000    0.38180000000000    0.11490000000000    S     (1a)
```

$AsKSe_2$ (P1): ABC2_aP16_1_4a_4a_8a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'As K Se2'

loop_
_publ_author_name
 'W. S. Sheldrick'
 'H. J. Ha\"usler'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 561
_journal_year 1988
_journal_page_first 139
_journal_page_last 148
_publ_Section_title
;
 Zur Kenntnis von Alkalimetaselenoarseniten Darstellung und
      ↪ Kristallstrukturen von MAsSe$_2$, M = K, Rb, Cs
;

# Found in  Pearson's Handbook, Vol I., P. 1165

_aflow_proto 'ABC2_aP16_1_4a_4a_8a'
_aflow_params 'a,b/a,c/a,\alpha,\beta,\gamma,x1,y1,z1,x2,y2,z2,x3,y3,z3,
      ↪ x4,y4,z4,x5,y5,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,y10,
      ↪ z10,x11,y11,z11,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15
      ↪ ,x16,y16,z16'
_aflow_params_values '6.554,1.00061031431,1.92662496186,100.43475,
      ↪ 100.46074,107.53,0.3267,0.582,0.177,0.565,-0.0132,0.4424,0.5217
      ↪ ,0.3883,0.6767,-0.0744,0.6254,-0.0574,0.0338,0.0476,0.2599,
      ↪ 0.0831,0.6072,0.4974,-0.0131,0.0949,0.7583,0.5449,0.1443,-
      ↪ 0.0022,-0.0211,0.5213,0.2073,0.2907,0.5956,-0.0183,-0.0616,
      ↪ 0.0602,0.4998,0.5068,-0.0175,0.2448,0.4596,0.0397,0.708,0.5326,
      ↪ 0.352,0.4818,0.0,0.0,0.0,-0.078,0.569,0.7448'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'aP16'

_symmetry_space_group_name_Hall "P 1"
_symmetry_space_group_name_H-M "P 1"
_symmetry_Int_Tables_number 1

_cell_length_a      6.55400
_cell_length_b      6.55800
_cell_length_c      12.62710
_cell_angle_alpha  100.43475
_cell_angle_beta   100.46074
_cell_angle_gamma  107.53000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
As1 As   1 a 0.32670  0.58200  0.17700  1.00000
As2 As   1 a 0.56500  -0.01320 0.44240  1.00000
As3 As   1 a 0.52170  0.38830  0.67670  1.00000
As4 As   1 a -0.07440 0.62540  -0.05740 1.00000
K1  K    1 a 0.03380  0.04760  0.25990  1.00000
K2  K    1 a 0.08310  0.60720  0.49740  1.00000
K3  K    1 a -0.01310 0.09490  0.75830  1.00000
K4  K    1 a 0.54490  0.14430  -0.00220 1.00000
Se1 Se   1 a -0.02110 0.52130  0.20730  1.00000
Se2 Se   1 a 0.29070  0.59560  -0.01830 1.00000
Se3 Se   1 a -0.06160 0.06020  0.49980  1.00000
Se4 Se   1 a 0.50680  -0.01750 0.24480  1.00000
Se5 Se   1 a 0.45960  0.03970  0.70800  1.00000
Se6 Se   1 a 0.53260  0.35200  0.48180  1.00000
Se7 Se   1 a 0.00000  0.00000  0.00000  1.00000
Se8 Se   1 a -0.07800 0.56900  0.74480  1.00000
```

$AsKSe_2$ (P1): ABC2_aP16_1_4a_4a_8a - POSCAR

```
ABC2_aP16_1_4a_4a_8a & a,b/a,c/a,\alpha,\beta,\gamma,x1,y1,z1,x2,y2,z2,
      ↪ x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,
      ↪ x10,y10,z10,x11,y11,z11,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15
      ↪ ,y15,z15,x16,y16,z16 --params=6.554,1.00061031431,1.92662496186
      ↪ ,100.43475,100.46074,107.53,0.3267,0.582,0.177,0.565,-0.0132,
      ↪ 0.4424,0.5217,0.3883,0.6767,-0.0744,0.6254,-0.0574,0.0338,
      ↪ 0.0476,0.2599,0.0831,0.6072,0.4974,-0.0131,0.0949,0.7583,0.5449
      ↪ ,0.1443,-0.0022,-0.0211,0.5213,0.2073,0.2907,0.5956,-0.0183,-
      ↪ 0.0616,0.0602,0.4998,0.5068,-0.0175,0.2448,0.4596,0.0397,0.708,
      ↪ 0.5326,0.352,0.4818,0.0,0.0,0.0,-0.078,0.569,0.7448 & P1
      ↪          C_1^1 #1 (a^16) & aP16 & & AsKSe2 & & Sheldrick and
      ↪ Hausler, ZAAC 561, 139-48 (1988)
```

```
   1.0000000000000000
   6.55400000000000    0.00000000000000    0.00000000000000
  -1.97530319852949    6.25344235392629    0.00000000000000
  -2.29259825357476   -3.12251953546006   12.01821614917856
    As    K    Se
     4    4     8
Direct
   0.32670000000000    0.58200000000000    0.17700000000000    As    (1a)
   0.52170000000000    0.38830000000000    0.67670000000000    As    (1a)
   0.56500000000000    0.98680000000000    0.44240000000000    As    (1a)
   0.92560000000000    0.62540000000000    0.94260000000000    As    (1a)
   0.03380000000000    0.04760000000000    0.25990000000000     K    (1a)
   0.08310000000000    0.60720000000000    0.49740000000000     K    (1a)
   0.54490000000000    0.14430000000000    0.99780000000000     K    (1a)
   0.98690000000000    0.09490000000000    0.75830000000000     K    (1a)
   0.00000000000000    0.00000000000000    0.00000000000000    Se    (1a)
   0.29070000000000    0.59560000000000    0.98170000000000    Se    (1a)
   0.45960000000000    0.03970000000000    0.70800000000000    Se    (1a)
   0.50680000000000    0.98250000000000    0.24480000000000    Se    (1a)
   0.53260000000000    0.35200000000000    0.48180000000000    Se    (1a)
   0.92200000000000    0.56900000000000    0.74480000000000    Se    (1a)
   0.93840000000000    0.06020000000000    0.50000000000000    Se    (1a)
   0.97890000000000    0.52130000000000    0.20730000000000    Se    (1a)
```

P_2I_4: A2B_aP6_2_2i_i - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'P2 I4'

loop_
_publ_author_name
 'Yuen Chu Leung'
 'J\"{u}rg Waser'
_journal_name_full
;
Journal of Physical Chemistry
;
_journal_volume 60
_journal_year 1956
_journal_page_first 539
_journal_page_last 543
_publ_Section_title
;
 The Crystal Structure of Phosphorus Diiodide, P$_2$I$_4$
;

# Found in  Wyckoff, Vol. I, pp. 375

_aflow_proto 'A2B_aP6_2_2i_i'
_aflow_params 'a,b/a,c/a,\alpha,\beta,\gamma,x1,y1,z1,x2,y2,z2,x3,y3,z3'
_aflow_params_values '4.56,1.54824561404,1.62280701754,80.2,106.96667,
    ↪ 98.2,0.557,0.73,0.165,0.82,0.803,0.695,0.397,0.639,0.463'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'aP6'

_symmetry_space_group_name_Hall "-P 1"
_symmetry_space_group_name_H-M "P -1"
_symmetry_Int_Tables_number 2

_cell_length_a      4.56000
_cell_length_b      7.06000
_cell_length_c      7.40000
_cell_angle_alpha  80.20000
_cell_angle_beta   106.96667
_cell_angle_gamma  98.20000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
I1  I    2 i  0.55700  0.73000  0.16500  1.00000
I2  I    2 i  0.82000  0.80300  0.69500  1.00000
P1  P    2 i  0.39700  0.63900  0.46300  1.00000
```

P_2I_4: A2B_aP6_2_2i_i - POSCAR

```
A2B_aP6_2_2i_i & a,b/a,c/a,\alpha,\beta,\gamma,x1,y1,z1,x2,y2,z2,x3,y3,
    ↪ z3 --params=4.56,1.54824561404,1.62280701754,80.2,106.96667,
    ↪ 98.2,0.557,0.73,0.165,0.82,0.803,0.695,0.397,0.639,0.463 & P(-1
    ↪ )      C_i^1 #2 (i^3) & aP6 & & P2I4 & & Y. C. Leung and J.
    ↪ Waser, J. Phys. Chem. 60, 539-43 (1956)
   1.0000000000000000
   4.56000000000000    0.00000000000000    0.00000000000000
  -1.00696027196000    6.98782019021000    0.00000000000000
  -2.15943321793000    0.96138157983000    7.01231727999000
     I     P
     4     2
Direct
   0.55700000000000    0.73000000000000    0.16500000000000     I    (2i)
   0.44300000000000    0.27000000000000    0.83500000000000     I    (2i)
   0.82000000000000    0.80300000000000    0.69500000000000     I    (2i)
   0.18000000000000    0.19700000000000    0.30500000000000     I    (2i)
   0.39700000000000    0.63900000000000    0.46300000000000     P    (2i)
   0.60300000000000    0.36100000000000    0.53700000000000     P    (2i)
```

Cf: A_aP4_2_aci - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'High Pressure Californium'
_chemical_formula_sum 'Cf'

loop_
_publ_author_name
 'R. B. Roof'
_journal_name_full
;
Journal of the Less-Common Metals
;
_journal_volume 120
_journal_year 1986
_journal_page_first 345
_journal_page_last 349
_publ_Section_title
;
 Concerning the Structure of a High Pressure Phase in Californium Metal
;

# Found in  Pearson's Handbook, Vol. 2, p. 2332

_aflow_proto 'A_aP4_2_aci'
_aflow_params 'a,b/a,c/a,\alpha,\beta,\gamma,x3,y3,z3'
_aflow_params_values '3.307,2.24130631993,0.844572119746,89.06,85.15,
    ↪ 85.7,0.572,0.259,0.433'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'aP4'

_symmetry_space_group_name_Hall "-P 1"
_symmetry_space_group_name_H-M "P -1"
_symmetry_Int_Tables_number 2

_cell_length_a      3.30700
_cell_length_b      7.41200
_cell_length_c      2.79300
_cell_angle_alpha  89.06000
_cell_angle_beta   85.15000
_cell_angle_gamma  85.70000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cf1  Cf    1 a  0.00000  0.00000  0.00000  1.00000
Cf2  Cf    1 c  0.00000  0.50000  0.00000  1.00000
Cf3  Cf    2 i  0.57200  0.25900  0.43300  1.00000
```

Cf: A_aP4_2_aci - POSCAR

```
A_aP4_2_aci & a,b/a,c/a,\alpha,\beta,\gamma,x3,y3,z3 --params=3.307,
    ↪ 2.24130631993,0.844572119746,89.06,85.15,85.7,0.572,0.259,0.433
    ↪ & P(-1)      C_i^1 #2 (aci) & aP4 & & Cf & 30-40 GPa & R. B.
    ↪ Roof, Journal of the Less-Common Metals 120, 345-9 (1986)
   1.0000000000000000
   3.30700000000000    0.00000000000000    0.00000000000000
   0.55574232324000    7.39113620969000    0.00000000000000
   0.23614093129000    0.02819398361000    2.78285672643000
   Cf
    4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cf    (1a)
   0.00000000000000    0.50000000000000    0.00000000000000    Cf    (1c)
   0.42800000000000    0.74100000000000    0.56700000000000    Cf    (2i)
   0.57200000000000    0.25900000000000    0.43300000000000    Cf    (2i)
```

SiO_2 (P2): A2B_mP12_3_bc3e_2e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'M. B. Boisen, Jr.'
 'G. V. Gibbs'
 'M. S. T. Bukowinski'
```

```
_journal_name_full
;
Physics and Chemistry of Minerals
;
_journal_volume 21
_journal_year 1994
_journal_page_first 269
_journal_page_last 284
_publ_Section_title
;
 Framework silica structures generated using simulated annealing with a
      ↪ potential energy function based on an H$_6$Si$_2$O$_7$
      ↪ molecule
;

_aflow_proto 'A2B_mP12_3_bc3e_2e'
_aflow_params 'a,b/a,c/a,\beta,y1,y2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6
      ↪ ,x7,y7,z7'
_aflow_params_values '4.1605,0.992524936907,1.78370388174,101.3752,
      ↪ 0.15907,0.73859,0.02399,0.752,0.18927,0.38562,0.71473,0.64074,
      ↪ 0.48963,0.20196,0.18802,0.18244,0.0,0.69651,0.38098,0.58564,
      ↪ 0.17797'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mP12'

_symmetry_space_group_name_Hall "P 2y"
_symmetry_space_group_name_H-M "P 1 2 1"
_symmetry_Int_Tables_number 3

_cell_length_a      4.16050
_cell_length_b      4.12940
_cell_length_c      7.42110
_cell_angle_alpha  90.00000
_cell_angle_beta   101.37520
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O    1 b 0.00000 0.15907 0.50000 1.00000
O2  O    1 c 0.50000 0.73859 0.00000 1.00000
O3  O    2 e 0.02399 0.75200 0.18927 1.00000
O4  O    2 e 0.38562 0.71473 0.64074 1.00000
O5  O    2 e 0.48963 0.20196 0.18802 1.00000
Si1 Si   2 e 0.18244 0.00000 0.69651 1.00000
Si2 Si   2 e 0.38098 0.58564 0.17797 1.00000
```

SiO_2 (P2): A2B_mP12_3_bc3e_2e - POSCAR

```
A2B_mP12_3_bc3e_2e & a,b/a,c/a,\beta,y1,y2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6
      ↪ ,y6,z6,x7,y7,z7 --params=4.1605,0.992524936907,1.78370388174,
      ↪ 101.3752,0.15907,0.73859,0.02399,0.752,0.18927,0.38562,0.71473,
      ↪ 0.64074,0.48963,0.20196,0.18802,0.18244,0.0,0.69651,0.38098,
      ↪ 0.58564,0.17797 & P2          C_2^1 #3 (bce^5) & mP12 & & SiO2 &
      ↪ derived from potential minimization & Boisen et all, Phys.
      ↪ Chem. Min. 21, 269-84 (1994)
   1.0000000000000000
   4.16050000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.12940000000000    0.00000000000000
  -1.46368596000000    0.00000000000000    7.27532464000000
     O    Si
     8     4
Direct
   0.00000000000000    0.15907000000000    0.50000000000000     O      (1b)
   0.50000000000000    0.73859000000000    0.00000000000000     O      (1c)
   0.02399000000000    0.75200000000000    0.18927000000000     O      (2e)
  -0.02399000000000    0.75200000000000   -0.18927000000000     O      (2e)
   0.38562000000000    0.71473000000000    0.64074000000000     O      (2e)
  -0.38562000000000    0.71473000000000   -0.64074000000000     O      (2e)
   0.48963000000000    0.20196000000000    0.18802000000000     O      (2e)
  -0.48963000000000    0.20196000000000   -0.18802000000000     O      (2e)
   0.18244000000000    0.00000000000000    0.69651000000000    Si      (2e)
  -0.18244000000000    0.00000000000000   -0.69651000000000    Si      (2e)
   0.38098000000000    0.58564000000000    0.17797000000000    Si      (2e)
  -0.38098000000000    0.58564000000000   -0.17797000000000    Si      (2e)
```

High-Pressure Te: A_mP4_4_2a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'High Pressure (4-7GPa) Tellurium'
_chemical_formula_sum 'Te'

loop_
_publ_author_name
 'Katsutoshi Aoki'
 'Osamu Shimomura'
 'Shigeru Minomura'
_journal_name_full
;
Journal of the Physical Society of Japan
;
_journal_volume 48
_journal_year 1980
_journal_page_first 551
_journal_page_last 556
_publ_Section_title
;
 Crystal Structure of the High-Pressure Phase of Tellurium
;

_aflow_proto 'A_mP4_4_2a'
_aflow_params 'a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2'
_aflow_params_values '3.104,2.42042525773,1.53350515464,92.71,0.25,0.23,
      ↪ 0.48,0.48,0.0,0.02'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mP4'

_symmetry_space_group_name_Hall "P 2yb"
_symmetry_space_group_name_H-M "P 1 21 1"
_symmetry_Int_Tables_number 4

_cell_length_a      3.10400
_cell_length_b      7.51300
_cell_length_c      4.76000
_cell_angle_alpha  90.00000
_cell_angle_beta   92.71000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Te1 Te   2 a 0.25000 0.23000 0.48000 1.00000
Te2 Te   2 a 0.48000 0.00000 0.02000 1.00000
```

High-Pressure Te: A_mP4_4_2a - POSCAR

```
A_mP4_4_2a & a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2 --params=3.104,
      ↪ 2.42042525773,1.53350515464,92.71,0.25,0.23,0.48,0.48,0.0,0.02
      ↪ & P2_1        C_2^2 #4 (a^2) & mP4 & & Te (4-7 GPa) & & K. Aoki,
      ↪ O. Shimomura, and S. Minomura, J. Phys. Soc. Jpn. 48 (2) 551-6
      ↪ (1980)
   1.0000000000000000
   3.10400000000000    0.00000000000000    0.00000000000000
   0.00000000000000    7.51300000000000    0.00000000000000
  -0.22505656000000    0.00000000000000    4.75467660000000
   Te
    4
Direct
   0.25000000000000    0.23000000000000    0.48000000000000    Te     (2a)
   0.75000000000000    0.73000000000000    0.52000000000000    Te     (2a)
   0.48000000000000    0.00000000000000    0.02000000000000    Te     (2a)
   0.52000000000000    0.50000000000000   -0.02000000000000    Te     (2a)
```

Po (A19): A_mC12_5_3c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Po'

loop_
_publ_author_name
 'M. A. Rollier'
 'S. B. Hendricks'
 'Louis R. Maxwell'
_journal_name_full
;
Journal of Chemical Physics
;
_journal_volume 4
_journal_year 1936
_journal_page_first 648
_journal_page_last 652
_publ_Section_title
;
 The Crystal Structure of Polonium by Electron Diffraction
;

# Found in AMS Database

_aflow_proto 'A_mC12_5_3c'
_aflow_params 'a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3'
_aflow_params_values '7.42,0.578167115903,1.90026954178,92.0,0.05,0.27,
      ↪ 0.245,0.63,0.3,0.4,0.245,0.43,0.07'
_aflow_Strukturbericht 'A19'
_aflow_Pearson 'mC12'

_symmetry_space_group_name_Hall "C 2y"
_symmetry_space_group_name_H-M "C 1 2 1"
```

```
_symmetry_Int_Tables_number 5

_cell_length_a      7.42000
_cell_length_b      4.29000
_cell_length_c      14.10000
_cell_angle_alpha  90.00000
_cell_angle_beta   92.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z
3 x+1/2,y+1/2,z
4 -x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Po1 Po    4 c 0.05000 0.27000 0.24500 1.00000
Po2 Po    4 c 0.63000 0.30000 0.40000 1.00000
Po3 Po    4 c 0.24500 0.43000 0.07000 1.00000
```

Po (A19): A_mC12_5_3c - POSCAR

```
A_mC12_5_3c & a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3 --params=7.42,
    ↪ 0.578167115903,1.90026954178,92.0,0.05,0.27,0.245,0.63,0.3,0.4,
    ↪ 0.245,0.43,0.07 & C2          C_2^3 #5 (c^3) & mC12 & A19 & Po &
    ↪ & M. A. Rollier, S. B. Hendricks, and L. R. Maxwell, JCP 4,
    ↪ 648-52 (1936)
   1.0000000000000000
   3.71000000000000   -2.14500000000000    0.00000000000000
   3.71000000000000    2.14500000000000    0.00000000000000
  -0.49208290350527    0.00000000000000   14.09141066096925
   Po
    6
Direct
   0.68000000000000    0.22000000000000    0.75500000000000    Po    (4c)
   0.78000000000000    0.32000000000000    0.24500000000000    Po    (4c)
   0.07000000000000    0.67000000000000    0.60000000000000    Po    (4c)
   0.33000000000000   -0.07000000000000    0.40000000000000    Po    (4c)
   0.32500000000000    0.18500000000000   -0.07000000000000    Po    (4c)
   0.81500000000000    0.67500000000000    0.07000000000000    Po    (4c)
```

Monoclinic PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_mC10_8_ab_a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Pb (Zr_0.50 Ti_0.48) O_3'
_chemical_formula_sum 'Pb Zr O3'

loop_
_publ_author_name
 'B. Noheda'
 'J. A. Gonzalo'
 'L. E. Cross'
 'R. Guo'
 'S.-E. Park'
 'D. E. Cox'
 'G. Shirane'
_journal_name_full
;
Physical Review B
;
_journal_volume 61
_journal_year 2000
_journal_page_first 8687
_journal_page_last 8695
_publ_Section_title
;
 Tetragonal-to-monoclinic phase transition in a ferroelectric perovskite
    ↪ : The structure of PbZr$_{0.52}$Ti$_{0.48}$O$_3$
;

_aflow_proto 'A3BC_mC10_8_ab_a_a'
_aflow_params 'a,b/a,c/a,\beta,x1,z1,x2,z2,x3,z3,x4,y4,z4'
_aflow_params_values '5.72204,0.9978207073,0.722908263486,90.498,0.5515
    ↪ ,-0.0994,0.0,0.0,0.523,0.4492,0.288,0.2434,0.3729'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mC10'

_symmetry_space_group_name_Hall "C -2y"
_symmetry_space_group_name_H-M "C 1 m 1"
_symmetry_Int_Tables_number 8

_cell_length_a      5.72204
_cell_length_b      5.70957
_cell_length_c      4.13651
_cell_angle_alpha  90.00000
_cell_angle_beta   90.49800
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,z
3 x+1/2,y+1/2,z
4 x+1/2,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O     2 a 0.55150 0.00000 -0.09940 1.00000
Pb1 Pb    2 a 0.00000 0.00000 0.00000  1.00000
Zr1 Zr    2 a 0.52300 0.00000 0.44920  1.00000
O2  O     4 b 0.28800 0.24340 0.37290  1.00000
```

Monoclinic PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_mC10_8_ab_a_a - POSCAR

```
A3BC_mC10_8_ab_a_a & a,b/a,c/a,\beta,x1,z1,x2,z2,x3,z3,x4,y4,z4 --params
    ↪ =5.72204,0.9978207073,0.722908263486,90.498,0.5515,-0.0994,0.0,
    ↪ 0.0,0.523,0.4492,0.288,0.2434,0.3729 & Cm          C_s^4 #8 (a^3b
    ↪ ) & mC10 & & Pb(Zr_0.52Ti_0.48)O_3 & Monoclinic PZT & B. Noheda
    ↪ et al., PRB 61, 8687 (2000)
   1.0000000000000000
   2.86102000000000   -2.85478500000000    0.00000000000000
   2.86102000000000    2.85478500000000    0.00000000000000
  -0.03595301539232    0.00000000000000    4.13635375189117
    O    Pb    Zr
    3     1     1
Direct
   0.55150000000000    0.55150000000000   -0.09940000000000    O    (2a)
   0.04460000000000    0.53140000000000    0.37290000000000    O    (4b)
   0.53140000000000    0.04460000000000    0.37290000000000    O    (4b)
   0.00000000000000    0.00000000000000    0.00000000000000    Pb   (2a)
   0.52300000000000    0.52300000000000    0.44920000000000    Zr   (2a)
```

Monoclinic (Cc) Low Tridymite (SiO_2): A2B_mC144_9_24a_12a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Low Tridymite'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'Wayne A. Dollase'
 'Werner H. Baur'
_journal_name_full
;
American Mineralogist
;
_journal_volume 61
_journal_year 1976
_journal_page_first 971
_journal_page_last 978
_publ_Section_title
;
 The superstructure of meteoritic low tridymite solved by computer
    ↪ simulation
;

_aflow_proto 'A2B_mC144_9_24a_12a'
_aflow_params 'a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5
    ↪ ,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,y10,z10,x11,y11,z11
    ↪ ,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15,x16,y16,z16,
    ↪ x17,y17,z17,x18,y18,z18,x19,y19,z19,x20,y20,z20,x21,y21,z21,x22
    ↪ ,y22,z22,x23,y23,z23,x24,y24,z24,x25,y25,z25,x26,y26,z26,x27,
    ↪ y27,z27,x28,y28,z28,x29,y29,z29,x30,y30,z30,x31,y31,z31,x32,y32
    ↪ ,z32,x33,y33,z33,x34,y34,z34,x35,y35,z35,x36,y36,z36'
_aflow_params_values '18.524,0.270092852516,1.28535953358,105.82,0.5749,
    ↪ 0.351,0.8182,0.0707,0.34,0.8476,0.7315,0.138,0.4851,0.2509,
    ↪ 0.144,0.5152,0.4155,0.352,0.6741,-0.0873,0.352,0.6434,0.8773,
    ↪ 0.164,-0.0787,0.416,0.168,-0.0639,0.7741,0.145,0.7538,0.2336,
    ↪ 0.143,0.7402,0.6195,0.341,0.5847,0.0811,0.343,0.5661,-0.0034,
    ↪ 0.011,0.6062,0.3533,0.489,0.5665,0.6498,0.005,0.6711,0.1524,
    ↪ 0.496,0.7805,0.8636,0.499,0.7328,0.3361,0.003,0.8333,0.0052,
    ↪ 0.493,0.7398,0.1369,0.011,-0.0732,0.4927,0.492,0.8868,0.5,0.468
    ↪ ,0.5,0.2252,0.491,0.5898,0.2744,0.021,-0.0845,0.0507,0.041,
    ↪ 0.5642,0.2036,0.447,0.7347,-0.0802,0.049,0.6225,0.5751,0.043,
    ↪ 0.7955,0.4247,0.048,0.6971,0.2643,0.444,0.5386,0.8023,0.449,
    ↪ 0.7661,0.6453,0.041,0.6027,0.8531,0.463,-0.0984,0.4493,0.466,-
    ↪ 0.0642,0.2244,0.059,-0.0395,0.0697,0.049,0.8702'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mC144'

_symmetry_space_group_name_Hall "C -2yc"
_symmetry_space_group_name_H-M "C 1 c 1"
_symmetry_Int_Tables_number 9

_cell_length_a      18.52400
_cell_length_b      5.00320
_cell_length_c      23.81000
_cell_angle_alpha  90.00000
_cell_angle_beta   105.82000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
```

```
1 x,y,z
2 x,-y,z+1/2
3 x+1/2,y+1/2,z
4 x+1/2,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1   O   4 a 0.57490  0.35100 0.81820  1.00000
O2   O   4 a 0.07070  0.34000 0.84760  1.00000
O3   O   4 a 0.73150  0.13800 0.48510  1.00000
O4   O   4 a 0.25090  0.14400 0.51520  1.00000
O5   O   4 a 0.41550  0.35200 0.67410  1.00000
O6   O   4 a -0.08730 0.35200 0.64340  1.00000
O7   O   4 a 0.87730  0.16400 -0.07870 1.00000
O8   O   4 a 0.41600  0.16800 -0.06390 1.00000
O9   O   4 a 0.77410  0.14500 0.75380  1.00000
O10  O   4 a 0.23360  0.14300 0.74020  1.00000
O11  O   4 a 0.61950  0.34100 0.58470  1.00000
O12  O   4 a 0.08110  0.34300 0.56610  1.00000
O13  O   4 a -0.00340 0.01100 0.60620  1.00000
O14  O   4 a 0.35330  0.48900 0.56650  1.00000
O15  O   4 a 0.64980  0.00500 0.67110  1.00000
O16  O   4 a 0.15240  0.49600 0.78050  1.00000
O17  O   4 a 0.86360  0.49900 0.73280  1.00000
O18  O   4 a 0.33610  0.00300 0.83330  1.00000
O19  O   4 a 0.00520  0.49300 0.73980  1.00000
O20  O   4 a 0.13690  0.01100 -0.07320 1.00000
O21  O   4 a 0.49270  0.49200 0.88680  1.00000
O22  O   4 a 0.50000  0.46800 0.50000  1.00000
O23  O   4 a 0.22520  0.49100 0.58980  1.00000
O24  O   4 a 0.27440  0.02100 -0.08450 1.00000
Si1  Si  4 a 0.05070  0.04100 0.56420  1.00000
Si2  Si  4 a 0.20360  0.44700 0.73470  1.00000
Si3  Si  4 a -0.08020 0.04900 0.62250  1.00000
Si4  Si  4 a 0.57510  0.04300 0.79550  1.00000
Si5  Si  4 a 0.42470  0.04800 0.69710  1.00000
Si6  Si  4 a 0.26430  0.44400 0.53860  1.00000
Si7  Si  4 a 0.80230  0.44900 0.76610  1.00000
Si8  Si  4 a 0.64530  0.04100 0.60270  1.00000
Si9  Si  4 a 0.85310  0.46300 -0.09840 1.00000
Si10 Si  4 a 0.44930  0.46600 -0.06420 1.00000
Si11 Si  4 a 0.22440  0.05900 -0.03950 1.00000
Si12 Si  4 a 0.06970  0.04900 0.87020  1.00000
```

Monoclinic (Cc) Low Tridymite (SiO_2): A2B_mC144_9_24a_12a - POSCAR

```
A2B_mC144_9_24a_12a & a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,
    ↪ z4,x5,y5,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,y10,z10,x11
    ↪ ,y11,z11,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15,x16,
    ↪ y16,z16,x17,y17,z17,x18,y18,z18,x19,y19,z19,x20,y20,z20,x21,y21
    ↪ ,z21,x22,y22,z22,x23,y23,z23,x24,y24,z24,x25,y25,z25,x26,y26,
    ↪ z26,x27,y27,z27,x28,y28,z28,x29,y29,z29,x30,y30,z30,x31,y31,z31
    ↪ ,x32,y32,z32,x33,y33,z33,x34,y34,z34,x35,y35,z35,x36,y36,z36 --
    ↪ params=18.524,0.270092852516,1.28535953358,105.82,0.5749,0.351,
    ↪ 0.8182,0.0707,0.34,0.8476,0.7315,0.138,0.4851,0.2509,0.144,
    ↪ 0.5152,0.4155,0.352,0.6741,-0.0873,0.352,0.6434,0.8773,0.164,-
    ↪ 0.0787,0.416,0.168,-0.0639,0.7741,0.145,0.7538,0.2336,0.143,
    ↪ 0.7402,0.6195,0.341,0.5847,0.0811,0.343,0.5661,-0.0034,0.011,
    ↪ 0.6062,0.3533,0.489,0.5665,0.6498,0.005,0.6711,0.1524,0.496,
    ↪ 0.7805,0.8636,0.499,0.7328,0.3361,0.003,0.8333,0.0052,0.493,
    ↪ 0.7398,0.1369,0.011,-0.0732,0.4927,0.492,0.8868,0.5,0.468,0.5,
    ↪ 0.2252,0.491,0.5898,0.2744,0.021,-0.0845,0.0507,0.041,0.5642,
    ↪ 0.2036,0.447,0.7347,-0.0802,0.049,0.6225,0.5751,0.043,0.7955,
    ↪ 0.4247,0.048,0.6971,0.2643,0.444,0.5386,0.8023,0.449,0.7661,
    ↪ 0.6453,0.041,0.6027,0.8531,0.463,-0.0984,0.4493,0.466,-0.0642,
    ↪ 0.2244,0.059,-0.0395,0.0697,0.049,0.8702 & Cc        C_s^4 #9 (
    ↪ a^36) & mC144 & & SiO2 & low Tridymite & Dollase and Baur, Am.
    ↪ Mineral. 61, 971-8 (1976)
   1.0000000000000000
   9.26200000000000   -2.50160000000000    0.00000000000000
   9.26200000000000    2.50160000000000    0.00000000000000
  -6.49098953000000    0.00000000000000   22.90814604000000
    O    Si
   48    24
Direct
   0.22390000000000   0.92590000000000   0.81820000000000   O   (4a)
   0.92590000000000   0.22390000000000   0.31820000000000   O   (4a)
   0.41070000000000   0.73070000000000   0.34760000000000   O   (4a)
   0.73070000000000   0.41070000000000   0.84760000000000   O   (4a)
   0.59350000000000   0.86950000000000   0.48510000000000   O   (4a)
   0.86950000000000   0.59350000000000   0.98510000000000   O   (4a)
   0.10690000000000   0.39490000000000   0.51520000000000   O   (4a)
   0.39490000000000   0.10690000000000   0.01520000000000   O   (4a)
   0.06350000000000   0.76750000000000   0.67410000000000   O   (4a)
   0.76750000000000   0.06350000000000   0.17410000000000   O   (4a)
   0.26470000000000   0.56070000000000   0.14340000000000   O   (4a)
   0.56070000000000   0.26470000000000   0.64340000000000   O   (4a)
   0.04130000000000   0.71330000000000   0.42130000000000   O   (4a)
   0.71330000000000   0.04130000000000   0.92130000000000   O   (4a)
   0.24800000000000   0.58400000000000   0.93610000000000   O   (4a)
   0.58400000000000   0.24800000000000   0.43610000000000   O   (4a)
   0.62910000000000   0.91910000000000   0.75380000000000   O   (4a)
   0.91910000000000   0.62910000000000   0.25380000000000   O   (4a)
   0.09060000000000   0.37660000000000   0.74020000000000   O   (4a)
   0.37660000000000   0.09060000000000   0.24020000000000   O   (4a)
   0.27850000000000   0.96050000000000   0.58470000000000   O   (4a)
   0.96050000000000   0.27850000000000   0.08470000000000   O   (4a)
   0.42410000000000   0.73810000000000   0.06610000000000   O   (4a)
   0.73810000000000   0.42410000000000   0.56610000000000   O   (4a)
   0.00760000000000  -0.01440000000000   0.10620000000000   O   (4a)
  -0.01440000000000   0.00760000000000   0.60620000000000   O   (4a)
   0.84230000000000   0.86430000000000   0.06650000000000   O   (4a)
   0.86430000000000   0.84230000000000   0.56650000000000   O   (4a)
   0.64480000000000   0.65480000000000   0.67110000000000   O   (4a)
   0.65480000000000   0.64480000000000   0.17110000000000   O   (4a)
   0.64840000000000   0.65640000000000   0.28050000000000   O   (4a)
   0.65640000000000   0.64840000000000   0.78050000000000   O   (4a)
   0.36260000000000   0.36460000000000   0.23280000000000   O   (4a)
   0.36460000000000   0.36260000000000   0.73280000000000   O   (4a)
   0.33310000000000   0.33910000000000   0.83330000000000   O   (4a)
   0.33910000000000   0.33310000000000   0.33330000000000   O   (4a)
   0.49820000000000   0.51220000000000   0.23980000000000   O   (4a)
   0.51220000000000   0.49820000000000   0.73980000000000   O   (4a)
   0.12590000000000   0.14790000000000   0.92680000000000   O   (4a)
   0.14790000000000   0.12590000000000   0.42680000000000   O   (4a)
   0.00070000000000   0.98470000000000   0.88680000000000   O   (4a)
   0.98470000000000   0.00070000000000   0.38680000000000   O   (4a)
   0.03200000000000   0.96800000000000   0.50000000000000   O   (4a)
   0.96800000000000   0.03200000000000   0.00000000000000   O   (4a)
   0.71620000000000   0.73420000000000   0.08980000000000   O   (4a)
   0.73420000000000   0.71620000000000   0.58980000000000   O   (4a)
   0.25340000000000   0.29540000000000   0.91550000000000   O   (4a)
   0.29540000000000   0.25340000000000   0.41550000000000   O   (4a)
   0.00970000000000   0.09170000000000   0.56420000000000   Si  (4a)
   0.09170000000000   0.00970000000000   0.06420000000000   Si  (4a)
  -0.01670000000000   0.91530000000000   0.93580000000000   Si  (4a)
   0.91530000000000  -0.01670000000000   0.43580000000000   Si  (4a)
   0.16540000000000   0.28340000000000   0.96050000000000   Si  (4a)
   0.28340000000000   0.16540000000000   0.46050000000000   Si  (4a)
   0.02070000000000   0.11870000000000   0.87020000000000   Si  (4a)
   0.11870000000000   0.02070000000000   0.37020000000000   Si  (4a)
   0.65060000000000   0.75660000000000   0.23470000000000   Si  (4a)
   0.75660000000000   0.65060000000000   0.73470000000000   Si  (4a)
   0.87080000000000   0.96880000000000   0.62250000000000   Si  (4a)
   0.96880000000000   0.87080000000000   0.12250000000000   Si  (4a)
   0.53210000000000   0.61810000000000   0.79550000000000   Si  (4a)
   0.61810000000000   0.53210000000000   0.29550000000000   Si  (4a)
   0.37670000000000   0.47270000000000   0.69710000000000   Si  (4a)
   0.47270000000000   0.37670000000000   0.19710000000000   Si  (4a)
   0.70830000000000   0.82030000000000   0.03860000000000   Si  (4a)
   0.82030000000000   0.70830000000000   0.53860000000000   Si  (4a)
   0.25130000000000   0.35330000000000   0.26610000000000   Si  (4a)
   0.35330000000000   0.25130000000000   0.76610000000000   Si  (4a)
   0.60430000000000   0.68630000000000   0.60270000000000   Si  (4a)
   0.68630000000000   0.60430000000000   0.10270000000000   Si  (4a)
   0.31610000000000   0.39010000000000   0.40160000000000   Si  (4a)
   0.39010000000000   0.31610000000000   0.90160000000000   Si  (4a)
```

NiTi: AB_mP4_11_e_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ni Ti'

loop_
_publ_author_name
 'H. Sitepu'
 'W. W. Schmal'
 'J. K. Stalick'
_journal_name_full
;
Applied Physics A
;
_journal_volume 74
_journal_year 2002
_journal_page_first S1719
_journal_page_last S1721
_publ_Section_title
;
 Correction of intensities for preferred orientation in
    ↪ neutron-diffraction data of NiTi shape-memory alloy using the
    ↪ generalized spherical-harmonic description
;

# Found in AMS Database

_aflow_proto 'AB_mP4_11_e_e'
_aflow_params 'a,b/a,c/a,\beta,x1,z1,x2,z2'
_aflow_params_values '2.8837,1.42393452856,1.61854561848,82.062,0.0387,
    ↪ 0.8252,0.5887,0.7184'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mP4'

_symmetry_space_group_name_Hall "-P 2yb"
_symmetry_space_group_name_H-M "P 1 21/m 1"
_symmetry_Int_Tables_number 11

_cell_length_a      2.88370
_cell_length_b      4.10620
_cell_length_c      4.66740
_cell_angle_alpha  90.00000
_cell_angle_beta   82.06200
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y+1/2,-z
```

```
3 -x,-y,-z
4 x,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ni1 Ni    2 e 0.03870 0.25000 0.82520 1.00000
Ti1 Ti    2 e 0.58870 0.25000 0.71840 1.00000
```

NiTi: AB_mP4_11_e_e - POSCAR

```
AB_mP4_11_e_e & a,b/a,c/a,\beta,x1,z1,x2,z2 --params=2.8837,
    ↪ 1.42393452856,1.61854561848,82.062,0.0387,0.8252,0.5887,0.7184
    ↪ & P2_1/m     C_{2h}^2 #11 (e^2) & mP4 & & NiTi & & H. Sitepu,
    ↪ W. W. Schmahl, and J. K. Stalick, App. Phys. A 74, S1719 (2002)
   1.0000000000000000
   2.88370000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.10620000000000    0.00000000000000
   0.64457469000000    0.00000000000000    4.62267739000000
   Ni    Ti
    2     2
Direct
   0.03870000000000    0.25000000000000    0.82520000000000    Ni    (2e)
   0.96130000000000    0.75000000000000    0.17480000000000    Ni    (2e)
   0.41130000000000    0.75000000000000    0.28160000000000    Ti    (2e)
   0.58870000000000    0.25000000000000    0.71840000000000    Ti    (2e)
```

$KClO_3$ ($G0_6$): ABC3_mP10_11_e_e_ef - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Potassium chlorate'
_chemical_formula_sum 'K Cl O3'

loop_
_publ_author_name
 'Jacob Danielsen'
 'Alan Hazell'
 'Finn Krebs Larsen'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 37
_journal_year 1981
_journal_page_first 913
_journal_page_last 915
_publ_Section_title
;
 The Structure of Potassium Chlorate at 77 and 298 K
;

_aflow_proto 'ABC3_mP10_11_e_e_ef'
_aflow_params 'a,b/a,c/a,\beta,x1,z1,x2,z2,x3,z3,x4,y4,z4'
_aflow_params_values '4.63,1.20259179266,1.52203023758,110.21,0.121,
    ↪ 0.1745,0.3531,0.7086,0.4009,0.1165,0.8544,0.5361,0.6943'
_aflow_Strukturbericht 'G0_6'
_aflow_Pearson 'mP10'

_symmetry_space_group_name_Hall "-P 2yb"
_symmetry_space_group_name_H-M "P 1 21/m 1"
_symmetry_Int_Tables_number 11

_cell_length_a      4.63000
_cell_length_b      5.56800
_cell_length_c      7.04700
_cell_angle_alpha  90.00000
_cell_angle_beta   110.2100
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y+1/2,-z
3 -x,-y,-z
4 x,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cl1 Cl    2 e 0.12100 0.25000 0.17450 1.00000
K1  K     2 e 0.35310 0.25000 0.70860 1.00000
O1  O     2 e 0.40090 0.25000 0.11650 1.00000
O2  O     4 f 0.85440 0.53610 0.69430 1.00000
```

$KClO_3$ ($G0_6$): ABC3_mP10_11_e_e_ef - POSCAR

```
ABC3_mP10_11_e_e_ef & a,b/a,c/a,\beta,x1,z1,x2,z2,x3,z3,x4,y4,z4 --
    ↪ params=4.63,1.20259179266,1.52203023758,110.21,0.121,0.1745,
    ↪ 0.3531,0.7086,0.4009,0.1165,0.8544,0.5361,0.6943 & P2_1/m
    ↪ C_{2h}^2 #11 (e^3f) & mP10 & G0_6 & KClO3 & & J. Daniesen, A.
    ↪ Hazell, and F. K. Larsen, Acta Cryst. B 37, 913-5 (1981)
   1.0000000000000000
   4.63000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.56800000000000    0.00000000000000
  -2.43447066000000    0.00000000000000    6.61313554000000
   Cl    K    O
    2    2    6
Direct
   0.12100000000000    0.25000000000000    0.17450000000000    Cl    (2e)
   0.87900000000000    0.75000000000000    0.82550000000000    Cl    (2e)
   0.35550000000000    0.25000000000000    0.70860000000000    K     (2e)
   0.64450000000000    0.75000000000000    0.29140000000000    K     (2e)
   0.40090000000000    0.25000000000000    0.11650000000000    O     (2e)
   0.59910000000000    0.75000000000000    0.88350000000000    O     (2e)
   0.14560000000000    0.03610000000000    0.30570000000000    O     (4f)
   0.14560000000000    0.46390000000000    0.30570000000000    O     (4f)
   0.85440000000000    0.53610000000000    0.69430000000000    O     (4f)
   0.85440000000000    0.96390000000000    0.69430000000000    O     (4f)
```

α-Pu: A_mP16_11_8e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha Pu'
_chemical_formula_sum 'Pu'

loop_
_publ_author_name
 'W. H. Zachariasen'
 'F. H. Ellinger'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 16
_journal_year 1963
_journal_page_first 777
_journal_page_last 783
_publ_Section_title
;
 The Crystal Structure of Alpha Plutonium Metal
;

# Found in  Donohue, pp. 159-162

_aflow_proto 'A_mP16_11_8e'
_aflow_params 'a,b/a,c/a,\beta,x1,z1,x2,z2,x3,z3,x4,z4,x5,z5,x6,z6,x7,z7
    ↪ ,x8,z8'
_aflow_params_values '6.183,0.779880316998,1.77308749798,101.79,0.345,
    ↪ 0.162,0.767,0.168,0.128,0.34,0.657,0.457,0.025,0.618,0.473,
    ↪ 0.653,0.328,-0.074,0.869,0.894'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mP16'

_symmetry_space_group_name_Hall "-P 2yb"
_symmetry_space_group_name_H-M "P 1 21/m 1"
_symmetry_Int_Tables_number 11

_cell_length_a      6.18300
_cell_length_b      4.82200
_cell_length_c      10.96300
_cell_angle_alpha  90.00000
_cell_angle_beta   101.79000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y+1/2,-z
3 -x,-y,-z
4 x,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pu1 Pu    2 e 0.34500 0.25000 0.16200  1.00000
Pu2 Pu    2 e 0.76700 0.25000 0.16800  1.00000
Pu3 Pu    2 e 0.12800 0.25000 0.34000  1.00000
Pu4 Pu    2 e 0.65700 0.25000 0.45700  1.00000
Pu5 Pu    2 e 0.02500 0.25000 0.61800  1.00000
Pu6 Pu    2 e 0.47300 0.25000 0.65300  1.00000
Pu7 Pu    2 e 0.32800 0.25000 -0.07400 1.00000
Pu8 Pu    2 e 0.86900 0.25000 0.89400  1.00000
```

α-Pu: A_mP16_11_8e - POSCAR

```
A_mP16_11_8e & a,b/a,c/a,\beta,x1,z1,x2,z2,x3,z3,x4,z4,x5,z5,x6,z6,x7,z7
    ↪ ,x8,z8 --params=6.183,0.779880316998,1.77308749798,101.79,0.345
    ↪ ,0.162,0.767,0.168,0.128,0.34,0.657,0.457,0.025,0.618,0.473,
    ↪ 0.653,0.328,-0.074,0.869,0.894 & P2_1/m     C_{2h}^2 #11 (e^8) &
```

```
      ↪ mP16 & & Pu & alpha & Zachariasen and Ellinger, Acta Cryst. 16
      ↪ , 777-83 (1963)
   1.0000000000000000
   6.18300000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.82200000000000    0.00000000000000
  -2.24001721000000    0.00000000000000   10.73171430000000
   Pu
   16
Direct
   0.34500000000000    0.25000000000000    0.16200000000000    Pu     (2e)
   0.65500000000000    0.75000000000000    0.83800000000000    Pu     (2e)
   0.23300000000000    0.75000000000000    0.83200000000000    Pu     (2e)
   0.76700000000000    0.25000000000000    0.16800000000000    Pu     (2e)
   0.12800000000000    0.25000000000000    0.34000000000000    Pu     (2e)
   0.87200000000000    0.75000000000000    0.66000000000000    Pu     (2e)
   0.34300000000000    0.75000000000000    0.54300000000000    Pu     (2e)
   0.65700000000000    0.25000000000000    0.45700000000000    Pu     (2e)
   0.02500000000000    0.25000000000000    0.61800000000000    Pu     (2e)
  -0.02500000000000    0.75000000000000    0.38200000000000    Pu     (2e)
   0.47300000000000    0.25000000000000    0.65300000000000    Pu     (2e)
   0.52700000000000    0.75000000000000    0.34700000000000    Pu     (2e)
   0.32800000000000    0.25000000000000   -0.07400000000000    Pu     (2e)
   0.67200000000000    0.75000000000000    0.07400000000000    Pu     (2e)
   0.13100000000000    0.75000000000000    0.10600000000000    Pu     (2e)
   0.86900000000000    0.25000000000000    0.89400000000000    Pu     (2e)
```

Calaverite ($AuTe_2$, C34): AB2_mC6_12_a_i - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Calaverite'
_chemical_formula_sum 'Au Te2'

loop_
_publ_author_name
 'K. Reithmayer'
 'W. Steurer'
 'H. Schulz'
 'J. L. de Boer'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 49
_journal_year 1993
_journal_page_first 6
_journal_page_last 11
_publ_Section_title
;
 High-pressure single-crystal structure study on calaverite, AuTe$_2$
;

_aflow_proto 'AB2_mC6_12_a_i'
_aflow_params 'a,b/a,c/a,\beta,x2,z2'
_aflow_params_values '7.189,0.613019891501,0.705105021561,90.04,0.6879,
      ↪ 0.2889'
_aflow_Strukturbericht 'C34'
_aflow_Pearson 'mC6'

_symmetry_space_group_name_Hall "-C 2y"
_symmetry_space_group_name_H-M "C 1 2/m 1"
_symmetry_Int_Tables_number 12

_cell_length_a      7.18900
_cell_length_b      4.40700
_cell_length_c      5.06900
_cell_angle_alpha  90.00000
_cell_angle_beta   90.04000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z
3 -x,-y,-z
4 x,-y,z
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z
7 -x+1/2,-y+1/2,-z
8 x+1/2,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Au1 Au   2 a 0.00000 0.00000 0.00000 1.00000
Te1 Te   4 i 0.68790 0.00000 0.28890 1.00000
```

Calaverite ($AuTe_2$, C34): AB2_mC6_12_a_i - POSCAR

```
AB2_mC6_12_a_i & a,b/a,c/a,\beta,x2,z2 --params=7.189,0.613019891501,
      ↪ 0.705105021561,90.04,0.6879,0.2889 & C2/m        C^3_{2h} #12 (
      ↪ ai) & mC6 & C34 & AuTe_2 & & K. Reithmayer et al., Acta Cryst.
      ↪ B 49, 6-11 (1993)
   1.0000000000000000
   3.59450000000000   -2.20350000000000    0.00000000000000
   3.59450000000000    2.20350000000000    0.00000000000000
   0.00353882930000    0.00000000000000    5.06899876470000
   Au    Te
    1     2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Au     (2a)
   0.68790000000000    0.68790000000000    0.28890000000000    Te     (4i)
   0.31210000000000    0.31210000000000    0.71110000000000    Te     (4i)
```

β-Pu: A_mC34_12_ah3i2j - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Plutonium'
_chemical_formula_sum 'Pu'

loop_
_publ_author_name
 'W. H. Zachariasen'
 'F. H. Ellinger'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 16
_journal_year 1963
_journal_page_first 369
_journal_page_last 375
_publ_Section_title
;
 The Crystal Structure of Beta Plutonium Metal
;

# Found in  Donohue, pp. 162-165

_aflow_proto 'A_mC34_12_ah3i2j'
_aflow_params 'a,b/a,c/a,\beta,y2,x3,z3,x4,z4,x5,z5,x6,y6,z6,x7,y7,z7'
_aflow_params_values '11.93871,0.876392843113,0.658278825769,129.00411,
      ↪ 0.22,0.854,0.241,0.663,0.745,0.566,0.238,0.355,0.232,-0.037,
      ↪ 0.333,0.35,0.586'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mC34'

_symmetry_space_group_name_Hall "-C 2y"
_symmetry_space_group_name_H-M "C 1 2/m 1"
_symmetry_Int_Tables_number 12

_cell_length_a      11.93871
_cell_length_b      10.46300
_cell_length_c      7.85900
_cell_angle_alpha  90.00000
_cell_angle_beta   129.00411
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z
3 -x,-y,-z
4 x,-y,z
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z
7 -x+1/2,-y+1/2,-z
8 x+1/2,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pu1 Pu   2 a 0.00000 0.00000 0.00000  1.00000
Pu2 Pu   4 h 0.00000 0.22000 0.50000  1.00000
Pu3 Pu   4 i 0.85400 0.00000 0.24100  1.00000
Pu4 Pu   4 i 0.66300 0.00000 0.74500  1.00000
Pu5 Pu   4 i 0.56600 0.00000 0.23800  1.00000
Pu6 Pu   8 j 0.35500 0.23200 -0.03700 1.00000
Pu7 Pu   8 j 0.33300 0.35000 0.58600  1.00000
```

β-Pu: A_mC34_12_ah3i2j - POSCAR

```
A_mC34_12_ah3i2j & a,b/a,c/a,\beta,y2,x3,z3,x4,z4,x5,z5,x6,y6,z6,x7,y7,
      ↪ z7 --params=11.93871,0.876392843113,0.658278825769,129.00411,
      ↪ 0.22,0.854,0.241,0.663,0.745,0.566,0.238,0.355,0.232,-0.037,
      ↪ 0.333,0.35,0.586 & C2/m        C_{2h}^3 #12 (ahi^3j^2) & mC34 & &
      ↪ Pu & beta & W. H. Zachariasen and F. H. Ellinger, Acta Cryst.
      ↪ 16, 369-75 (1963)
   1.0000000000000000
   5.96935749915200   -5.23150000000000    0.00000000000000
   5.96935749915200    5.23150000000000    0.00000000000000
  -4.94626686488100    0.00000000000000    6.10723547125700
   Pu
   17
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Pu     (2a)
   0.22000000000000    0.78000000000000    0.50000000000000    Pu     (4h)
   0.78000000000000    0.22000000000000    0.50000000000000    Pu     (4h)
   0.14600000000000    0.14600000000000    0.75900000000000    Pu     (4i)
```

```
    0.85400000000000    0.85400000000000    0.24100000000000    Pu    (4i)
    0.33700000000000    0.33700000000000    0.25500000000000    Pu    (4i)
    0.66300000000000    0.66300000000000    0.74500000000000    Pu    (4i)
    0.43400000000000    0.43400000000000    0.76200000000000    Pu    (4i)
    0.56600000000000    0.56600000000000    0.23800000000000    Pu    (4i)
    0.12300000000000    0.58700000000000   -0.03700000000000    Pu    (8j)
    0.41300000000000    0.87700000000000    0.03700000000000    Pu    (8j)
    0.58700000000000    0.12300000000000   -0.03700000000000    Pu    (8j)
    0.87700000000000    0.41300000000000    0.03700000000000    Pu    (8j)
    0.01700000000000    0.31700000000000    0.41400000000000    Pu    (8j)
   -0.01700000000000    0.68300000000000    0.58600000000000    Pu    (8j)
    0.31700000000000    0.01700000000000    0.41400000000000    Pu    (8j)
    0.68300000000000   -0.01700000000000    0.58600000000000    Pu    (8j)
```

$AlCl_3$ ($D0_{15}$): AB3_mC16_12_g_ij - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Aluminum trichloride'
_chemical_formula_sum 'Al Cl3'

loop_
_publ_author_name
 'S. I. Troyanov'
_journal_name_full
;
(Russian) Journal of Inorganic Chemistry (translated from Zhurnal
      ↪ Neorganicheskoi Khimii)
;
_journal_volume 37
_journal_year 1992
_journal_page_first 121
_journal_page_last 124
_publ_Section_title
;
 The crystal structure of titanium(II) tetrachloroaluminate Ti(AlCl$_4$)
      ↪ $_2$ and refinement of the crystal structure of AlCl$_3$
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
      ↪ sd_1250120

_aflow_proto 'AB3_mC16_12_g_ij'
_aflow_params 'a,b/a,c/a,\beta,y1,x2,z2,x3,y3,z3'
_aflow_params_values '5.914,1.73047007102,1.03956712885,108.25,0.1662,
      ↪ 0.2147,0.2263,0.2518,0.32131,0.2248'
_aflow_Strukturbericht 'D0_15'
_aflow_Pearson 'mC16'

_symmetry_space_group_name_Hall "-C 2y"
_symmetry_space_group_name_H-M "C 1 2/m 1"
_symmetry_Int_Tables_number 12

_cell_length_a      5.91400
_cell_length_b      10.23400
_cell_length_c      6.14800
_cell_angle_alpha  90.00000
_cell_angle_beta   108.25000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z
3 -x,-y,-z
4 x,-y,z
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z
7 -x+1/2,-y+1/2,-z
8 x+1/2,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1 Al    4 g 0.00000 0.16620 0.00000 1.00000
Cl1 Cl    4 i 0.21470 0.00000 0.22630 1.00000
Cl2 Cl    8 j 0.25180 0.32131 0.22480 1.00000
```

$AlCl_3$ ($D0_{15}$): AB3_mC16_12_g_ij - POSCAR

```
AB3_mC16_12_g_ij & a,b/a,c/a,\beta,y1,x2,z2,x3,y3,z3 --params=5.914,
      ↪ 1.73047007102,1.03956712885,108.25,0.1662,0.2147,0.2263,0.2518,
      ↪ 0.32131,0.2248 & C2/m        C_{2h}^3 #12 (gij) & mC16 & D0_{15}
      ↪ & AlCl_3 & & S. I. Troyanov, Russian Journal of Inorganic
      ↪ Chemistry 37, 121-124 (1992)
   1.0000000000000000
   2.95700000000000   -5.11700000000000    0.00000000000000
   2.95700000000000    5.11700000000000    0.00000000000000
  -1.92533108226200    0.00000000000000    5.83875022788900
   Al    Cl
    2     6
Direct
   0.16620000000000    0.83380000000000    0.00000000000000    Al    (4g)
   0.83380000000000    0.16620000000000    0.00000000000000    Al    (4g)
   0.21470000000000    0.21470000000000    0.22630000000000    Cl    (4i)
   0.78530000000000    0.78530000000000    0.77370000000000    Cl    (4i)
   0.06951000000000    0.42689000000000    0.77520000000000    Cl    (8j)
  -0.06951000000000    0.57311000000000    0.22480000000000    Cl    (8j)
   0.42689000000000    0.06951000000000    0.77520000000000    Cl    (8j)
   0.57311000000000   -0.06951000000000    0.22480000000000    Cl    (8j)
```

Au_5Mn_2: A5B2_mC14_12_a2i_i - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Au5 Mn2'

loop_
_publ_author_name
 'S. G. Humble'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 17
_journal_year 1964
_journal_page_first 1485
_journal_page_last 1486
_publ_Section_title
;
 Establishment of an ordered phase of composition Au$_5$Mn$_2$ in the
      ↪ gold-manganese system
;

# Found in  Pearson, 346-348

_aflow_proto 'A5B2_mC14_12_a2i_i'
_aflow_params 'a,b/a,c/a,\beta,x2,z2,x3,z3,x4,z4'
_aflow_params_values '9.188,0.430343926861,0.705158902917,97.56,0.14286,
      ↪ 0.42857,0.28571,0.85714,0.42857,0.28571'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mC14'

_symmetry_space_group_name_Hall "-C 2y"
_symmetry_space_group_name_H-M "C 1 2/m 1"
_symmetry_Int_Tables_number 12

_cell_length_a      9.18800
_cell_length_b      3.95400
_cell_length_c      6.47900
_cell_angle_alpha  90.00000
_cell_angle_beta   97.56000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z
3 -x,-y,-z
4 x,-y,z
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z
7 -x+1/2,-y+1/2,-z
8 x+1/2,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Au1 Au    2 a 0.00000 0.00000 0.00000 1.00000
Au2 Au    4 i 0.14286 0.00000 0.42857 1.00000
Au3 Au    4 i 0.28571 0.00000 0.85714 1.00000
Mn1 Mn    4 i 0.42857 0.00000 0.28571 1.00000
```

Au_5Mn_2: A5B2_mC14_12_a2i_i - POSCAR

```
A5B2_mC14_12_a2i_i & a,b/a,c/a,\beta,x2,z2,x3,z3,x4,z4 --params=9.188,
      ↪ 0.430343926861,0.705158902917,97.56,0.14286,0.42857,0.28571,
      ↪ 0.85714,0.42857,0.28571 & C2/m        C_{2h}^3 #12 (ai^3) &
      ↪ mC14 & & Au_5Mn_2 & & S. G. Humble, Acta Cryst. 17, 1485-1486 (
      ↪ 1964)
   1.0000000000000000
   4.59400000000000   -1.97700000000000    0.00000000000000
   4.59400000000000    1.97700000000000    0.00000000000000
  -0.85240548255900    0.00000000000000    6.42268214169900
   Au    Mn
    5     2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Au    (2a)
   0.14285714285700    0.14285714285700    0.42857142857100    Au    (4i)
   0.85714285714300    0.85714285714300    0.57142857142900    Au    (4i)
   0.28571428571400    0.28571428571400    0.85714285714300    Au    (4i)
   0.71428571428600    0.71428571428600    0.14285714285700    Au    (4i)
   0.42857142857100    0.42857142857100    0.28571428571400    Mn    (4i)
   0.57142857142900    0.57142857142900    0.71428571428600    Mn    (4i)
```

α-O: A_mC4_12_i - CIF

```
# CIF file
```

```
data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha oxygen'
_chemical_formula_sum 'O'

loop_
_publ_author_name
 'R. J. Meier'
 'R. B. Helmholdt'
_journal_name_full
;
Physical Review B
;
_journal_volume 29
_journal_year 1984
_journal_page_first 1387
_journal_page_last 1393
_publ_Section_title
;
 Neutron-diffraction study of $\alpha$- and $\beta$-oxygen
;

_aflow_proto 'A_mC4_12_i'
_aflow_params 'a,b/a,c/a,\beta,x1,z1'
_aflow_params_values '5.403,0.635387747548,0.940033314825,132.32,0.106,
    ↪ 0.173'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mC4'

_symmetry_space_group_name_Hall "-C 2y"
_symmetry_space_group_name_H-M "C 1 2/m 1"
_symmetry_Int_Tables_number 12

_cell_length_a      5.40300
_cell_length_b      3.43300
_cell_length_c      5.07900
_cell_angle_alpha  90.00000
_cell_angle_beta   132.32000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z
3 -x,-y,-z
4 x,-y,z
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z
7 -x+1/2,-y+1/2,-z
8 x+1/2,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1 O    4 i 0.10600 0.00000 0.17300 1.00000
```

α-O: A_mC4_12_i - POSCAR

```
A_mC4_12_i & a,b/a,c/a,\beta,x1,z1 --params=5.403,0.635387747548,
    ↪ 0.940033314825,132.32,0.106,0.173 & C2/m      C__{2h}^3 #12 (i)
    ↪  & mC4 & & O & alpha & R. J. Meier and R. B. Helmholdt, Phys.
    ↪ Rev. B 29, 1387-93 (1984)
   1.0000000000000000
   2.70150000000000  -1.71650000000000   0.00000000000000
   2.70150000000000   1.71650000000000   0.00000000000000
  -3.41954164384100   0.00000000000000   3.75539291500000
     O
     2
Direct
   0.10600000000000   0.10600000000000   0.17300000000000   O   (4i)
   0.89400000000000   0.89400000000000   0.82700000000000   O   (4i)
```

Sylvanite ($AgAuTe_4$, $E1_b$): ABC4_mP12_13_e_a_2g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Sylvanite'
_chemical_formula_sum 'Ag Au Te4'

loop_
_publ_author_name
 'F. Pertlik'
_journal_name_full
;
Tschermaks mineralogische und petrographische Mitteilungen
;
_journal_volume 33
_journal_year 1984
_journal_page_first 203
_journal_page_last 212
_publ_Section_title
;
 Kristallchemie nat\"{u}rlicher Telluride I: Verfeinerung der
    ↪ Kristallstruktur des Sylvanits, AuAgTe$_4$
;

# Found in http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_1702950

_aflow_proto 'ABC4_mP12_13_e_a_2g'
_aflow_params 'a,b/a,c/a,\beta,y2,x3,y3,z3,x4,y4,z4'
_aflow_params_values '8.95,0.500335195531,1.63360893855,145.35,0.5182,
    ↪ 0.2986,0.0278,0.0003,0.2821,0.4045,0.2366'
_aflow_Strukturbericht 'E1_b'
_aflow_Pearson 'mP12'

_symmetry_space_group_name_Hall "-P 2yc"
_symmetry_space_group_name_H-M "P 1 2/c 1"
_symmetry_Int_Tables_number 13

_cell_length_a      8.95000
_cell_length_b      4.47800
_cell_length_c      14.62080
_cell_angle_alpha  90.00000
_cell_angle_beta   145.35000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z+1/2
3 -x,-y,-z
4 x,-y,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Au1 Au   2 a 0.00000 0.00000 0.00000 1.00000
Ag1 Ag   2 e 0.00000 0.51820 0.25000 1.00000
Te1 Te   4 g 0.29860 0.02780 0.00030 1.00000
Te2 Te   4 g 0.28210 0.40450 0.23660 1.00000
```

Sylvanite ($AgAuTe_4$, $E1_b$): ABC4_mP12_13_e_a_2g - POSCAR

```
ABC4_mP12_13_e_a_2g & a,b/a,c/a,\beta,y2,x3,y3,z3,x4,y4,z4 --params=8.95
    ↪ ,0.500335195531,1.63360893855,145.35,0.5182,0.2986,0.0278,
    ↪ 0.0003,0.2821,0.4045,0.2366 & P2/c      C_{2h}^4 #13 (aeg^2) &
    ↪  mP12 & E1_b & AgAuTe4 & & F. Pertlik, TMPM 33, 203-212 (1984)
   1.0000000000000000
   8.95000000000000   0.00000000000000   0.00000000000000
   0.00000000000000   4.47800000000000   0.00000000000000
 -12.02700437000000   0.00000000000000   8.31237426000000
   Ag   Au   Te
    2    2    8
Direct
   0.00000000000000   0.48180000000000   0.75000000000000   Ag   (2e)
   0.00000000000000   0.51820000000000   0.25000000000000   Ag   (2e)
   0.00000000000000   0.00000000000000   0.00000000000000   Au   (2a)
   0.00000000000000   0.00000000000000   0.50000000000000   Au   (2a)
   0.29920000000000   0.02780000000000   0.00030000000000   Te   (4g)
   0.29920000000000   0.97220000000000   0.50030000000000   Te   (4g)
   0.70080000000000   0.02780000000000   0.49970000000000   Te   (4g)
   0.70080000000000   0.97220000000000   0.99970000000000   Te   (4g)
   0.28210000000000   0.40450000000000   0.23660000000000   Te   (4g)
   0.28210000000000   0.59550000000000   0.73660000000000   Te   (4g)
   0.71790000000000   0.40450000000000   0.26340000000000   Te   (4g)
   0.71790000000000   0.59550000000000   0.76340000000000   Te   (4g)
```

Monoclinic (Hittorf's) Phosphorus: A_mP84_13_21g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Hittorf'
_chemical_formula_sum 'P'

loop_
_publ_author_name
 'H. Thurn'
 'H. Krebs'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 25
_journal_year 1969
_journal_page_first 125
_journal_page_last 135
_publ_Section_title
;
 "{U}ber Struktur und Eigenschaften der Halbmetalle. XXII. Die
    ↪ Kristallstruktur des Hittorfschen Phosphors
;

# Found in Donohue, pp. 292-295

_aflow_proto 'A_mP84_13_21g'
```

```
_aflow_params 'a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5
    ↪ ,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,y10,z10,x11,y11,z11
    ↪ ,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15,x16,y16,z16,
    ↪ x17,y17,z17,x18,y18,z18,x19,y19,z19,x20,y20,z20,x21,y21,z21'
_aflow_params_values '9.21,0.99348534202,2.45385450597,106.1,0.30089,
    ↪ 0.20127,0.18147,0.17387,0.03262,0.11695,0.05014,-0.05231,
    ↪ 0.18035,-0.07589,0.78099,0.11634,0.79463,0.67872,0.1738,0.68463
    ↪ ,0.51532,0.10402,0.56601,0.44932,0.17224,0.42424,0.27741,
    ↪ 0.11672,0.0412,0.39067,0.07245,-0.00092,0.15881,0.04497,0.78847
    ↪ ,0.13878,0.07346,0.7486,-0.09081,0.04464,0.53574,0.87264,
    ↪ 0.06842,0.50833,0.63715,0.03304,0.30515,0.63715,0.06617,0.25041
    ↪ ,0.40555,0.0442,0.146,0.38905,0.17219,0.86038,0.10055,0.17357,
    ↪ 0.59606,0.82384,0.1694,0.41856,0.64581,0.16732,-0.05418,0.32296
    ↪ ,0.2006'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mP84'

_symmetry_space_group_name_Hall "-P 2yc"
_symmetry_space_group_name_H-M "P 1 2/c 1"
_symmetry_Int_Tables_number 13

_cell_length_a      9.21000
_cell_length_b      9.15000
_cell_length_c      22.60000
_cell_angle_alpha   90.00000
_cell_angle_beta    106.10000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z+1/2
3 -x,-y,-z
4 x,-y,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
P1  P  4 g 0.30089  0.20127  0.18147 1.00000
P2  P  4 g 0.17387  0.03262  0.11695 1.00000
P3  P  4 g 0.05014  -0.05231 0.18035 1.00000
P4  P  4 g -0.07589 0.78099  0.11634 1.00000
P5  P  4 g 0.79463  0.67872  0.17380 1.00000
P6  P  4 g 0.68463  0.51532  0.10402 1.00000
P7  P  4 g 0.56601  0.44932  0.17224 1.00000
P8  P  4 g 0.42424  0.27741  0.11672 1.00000
P9  P  4 g 0.04120  0.39067  0.07245 1.00000
P10 P  4 g -0.00092 0.15881  0.04497 1.00000
P11 P  4 g 0.78847  0.13878  0.07346 1.00000
P12 P  4 g 0.74860  -0.09081 0.04464 1.00000
P13 P  4 g 0.53574  0.87264  0.06842 1.00000
P14 P  4 g 0.50833  0.63715  0.03304 1.00000
P15 P  4 g 0.30515  0.63715  0.06617 1.00000
P16 P  4 g 0.25041  0.40555  0.04420 1.00000
P17 P  4 g 0.14600  0.38905  0.17219 1.00000
P18 P  4 g 0.86038  0.10055  0.17357 1.00000
P19 P  4 g 0.59606  0.82384  0.16940 1.00000
P20 P  4 g 0.41856  0.64581  0.16732 1.00000
P21 P  4 g -0.05418 0.32296  0.20060 1.00000
```

Monoclinic (Hittorf's) Phosphorus: A_mP84_13_21g - POSCAR

```
A_mP84_13_21g & a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,
    ↪ y5,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,y10,z10,x11,y11,
    ↪ z11,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15,x16,y16,z16
    ↪ ,x17,y17,z17,x18,y18,z18,x19,y19,z19,x20,y20,z20,x21,y21,z21 --
    ↪ params=9.21,0.99348534202,2.45385450597,106.1,0.30089,0.20127,
    ↪ 0.18147,0.17387,0.03262,0.11695,0.05014,-0.05231,0.18035,-
    ↪ 0.07589,0.78099,0.11634,0.79463,0.67872,0.1738,0.68463,0.51532,
    ↪ 0.10402,0.56601,0.44932,0.17224,0.42424,0.27741,0.11672,0.0412,
    ↪ 0.39067,0.07245,-0.00092,0.15881,0.04497,0.78847,0.13878,
    ↪ 0.07346,0.7486,-0.09081,0.04464,0.53574,0.87264,0.06842,0.50833
    ↪ ,0.63715,0.03304,0.30515,0.63715,0.06617,0.25041,0.40555,0.0442
    ↪ ,0.146,0.38905,0.17219,0.86038,0.10055,0.17357,0.59606,0.82384,
    ↪ 0.1694,0.41856,0.64581,0.16732,-0.05418,0.32296,0.2006 & P2/c
    ↪ C_{2h}^4 #13 (g^21) & mP84 & & P & Hittorf & Thurn and
    ↪ Krebs, Acta Cryst. B 125 (1969)
   1.0000000000000000
   9.21000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    9.15000000000000    0.00000000000000
  -6.26731116000000    0.00000000000000   21.71360888000000
    P
   84
Direct
   0.30089000000000    0.20127000000000    0.18147000000000    P    (4g)
   0.30089000000000    0.79873000000000    0.68147000000000    P    (4g)
   0.69911000000000    0.20127000000000    0.31853000000000    P    (4g)
   0.69911000000000    0.79873000000000    0.81853000000000    P    (4g)
  -0.00092000000000    0.15881000000000    0.04497000000000    P    (4g)
  -0.00092000000000    0.84119000000000    0.54497000000000    P    (4g)
   1.00092000000000    0.15881000000000    0.45503000000000    P    (4g)
   1.00092000000000    0.84119000000000    0.95503000000000    P    (4g)
   0.21153000000000    0.13878000000000    0.42654000000000    P    (4g)
   0.21153000000000    0.86122000000000    0.92654000000000    P    (4g)
   0.78847000000000    0.13878000000000    0.07346000000000    P    (4g)
   0.78847000000000    0.86122000000000    0.57346000000000    P    (4g)
   0.25140000000000   -0.09081000000000    0.45536000000000    P    (4g)
   0.25140000000000    1.09081000000000    0.95536000000000    P    (4g)
   0.74860000000000   -0.09081000000000    0.04464000000000    P    (4g)
   0.74860000000000    1.09081000000000    0.54464000000000    P    (4g)
   0.46426000000000    0.12736000000000    0.93158000000000    P    (4g)
   0.46426000000000    0.87264000000000    0.43158000000000    P    (4g)
   0.53574000000000    0.12736000000000    0.56842000000000    P    (4g)
   0.53574000000000    0.87264000000000    0.06842000000000    P    (4g)
   0.49167000000000    0.36285000000000    0.96696000000000    P    (4g)
   0.49167000000000    0.63715000000000    0.46696000000000    P    (4g)
   0.50833000000000    0.36285000000000    0.53304000000000    P    (4g)
   0.50833000000000    0.63715000000000    0.03304000000000    P    (4g)
   0.30515000000000    0.36285000000000    0.56617000000000    P    (4g)
   0.30515000000000    0.63715000000000    0.06617000000000    P    (4g)
   0.69485000000000    0.36285000000000    0.93383000000000    P    (4g)
   0.69485000000000    0.63715000000000    0.43383000000000    P    (4g)
   0.25041000000000    0.40555000000000    0.04420000000000    P    (4g)
   0.25041000000000    0.59445000000000    0.54420000000000    P    (4g)
   0.74959000000000    0.40555000000000    0.45580000000000    P    (4g)
   0.74959000000000    0.59445000000000    0.95580000000000    P    (4g)
   0.14600000000000    0.38905000000000    0.17219000000000    P    (4g)
   0.14600000000000    0.61095000000000    0.67219000000000    P    (4g)
   0.85400000000000    0.38905000000000    0.32781000000000    P    (4g)
   0.85400000000000    0.61095000000000    0.82781000000000    P    (4g)
   0.13962000000000    0.10055000000000    0.32643000000000    P    (4g)
   0.13962000000000    0.89945000000000    0.82643000000000    P    (4g)
   0.86038000000000    0.10055000000000    0.17357000000000    P    (4g)
   0.86038000000000    0.89945000000000    0.67357000000000    P    (4g)
   0.40394000000000    0.17616000000000    0.83060000000000    P    (4g)
   0.40394000000000    0.82384000000000    0.33060000000000    P    (4g)
   0.59606000000000    0.17616000000000    0.66940000000000    P    (4g)
   0.59606000000000    0.82384000000000    0.16940000000000    P    (4g)
   0.17387000000000    0.03262000000000    0.11695000000000    P    (4g)
   0.17387000000000    0.96738000000000    0.61695000000000    P    (4g)
   0.82613000000000    0.03262000000000    0.38305000000000    P    (4g)
   0.82613000000000    0.96738000000000    0.88305000000000    P    (4g)
   0.41856000000000    0.35419000000000    0.66732000000000    P    (4g)
   0.41856000000000    0.64581000000000    0.16732000000000    P    (4g)
   0.58144000000000    0.35419000000000    0.83268000000000    P    (4g)
   0.58144000000000    0.64581000000000    0.33268000000000    P    (4g)
  -0.05418000000000    0.32296000000000    0.20060000000000    P    (4g)
  -0.05418000000000    0.67704000000000    0.70060000000000    P    (4g)
   1.05418000000000    0.32296000000000    0.29940000000000    P    (4g)
   1.05418000000000    0.67704000000000    0.79940000000000    P    (4g)
   0.05014000000000   -0.05231000000000    0.18035000000000    P    (4g)
   0.05014000000000    1.05231000000000    0.68035000000000    P    (4g)
   0.94986000000000   -0.05231000000000    0.31965000000000    P    (4g)
   0.94986000000000    1.05231000000000    0.81965000000000    P    (4g)
  -0.07589000000000    0.21901000000000    0.61634000000000    P    (4g)
  -0.07589000000000    0.78099000000000    0.11634000000000    P    (4g)
   1.07589000000000    0.21901000000000    0.88366000000000    P    (4g)
   1.07589000000000    0.78099000000000    0.38366000000000    P    (4g)
   0.20537000000000    0.32128000000000    0.82620000000000    P    (4g)
   0.20537000000000    0.67872000000000    0.32620000000000    P    (4g)
   0.79463000000000    0.32128000000000    0.67380000000000    P    (4g)
   0.79463000000000    0.67872000000000    0.17380000000000    P    (4g)
   0.31537000000000    0.48468000000000    0.89598000000000    P    (4g)
   0.31537000000000    0.51532000000000    0.39598000000000    P    (4g)
   0.68463000000000    0.48468000000000    0.60402000000000    P    (4g)
   0.68463000000000    0.51532000000000    0.10402000000000    P    (4g)
   0.43399000000000    0.44932000000000    0.32776000000000    P    (4g)
   0.43399000000000    0.55068000000000    0.82776000000000    P    (4g)
   0.56601000000000    0.44932000000000    0.17224000000000    P    (4g)
   0.56601000000000    0.55068000000000    0.67224000000000    P    (4g)
   0.42424000000000    0.27741000000000    0.11672000000000    P    (4g)
   0.42424000000000    0.72259000000000    0.61672000000000    P    (4g)
   0.57576000000000    0.27741000000000    0.38328000000000    P    (4g)
   0.57576000000000    0.72259000000000    0.88328000000000    P    (4g)
   0.04120000000000    0.39067000000000    0.07245000000000    P    (4g)
   0.04120000000000    0.60933000000000    0.57245000000000    P    (4g)
   0.95880000000000    0.39067000000000    0.42755000000000    P    (4g)
   0.95880000000000    0.60933000000000    0.92755000000000    P    (4g)
```

Baddeleyite (ZrO_2, C43): A2B_mP12_14_2e_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Baddeleyite'
_chemical_formula_sum 'Zr O2'

loop_
_publ_author_name
 'C. J. Howard'
 'R. J. Hill'
 'B. E. Reichert'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 44
_journal_year 1988
_journal_page_first 116
_journal_page_last 120
_publ_Section_title
;
 Structures of ZrO$_2$ polymorphs at room temperature by high-resolution
    ↪ neutron powder diffraction
;

_aflow_proto 'A2B_mP12_14_2e_e'
_aflow_params 'a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3'
_aflow_params_values '5.1505,1.01186292593,1.03238520532,99.23,0.07,
    ↪ 0.3317,0.3447,0.4496,0.7569,0.4792,0.2754,0.0395,0.2083'
_aflow_Strukturbericht 'C43'
```

```
_aflow_Pearson 'mP12'

_symmetry_space_group_name_Hall "-P 2ybc"
_symmetry_space_group_name_H-M "P 1 21/c 1"
_symmetry_Int_Tables_number 14

_cell_length_a      5.15050
_cell_length_b      5.21160
_cell_length_c      5.31730
_cell_angle_alpha  90.00000
_cell_angle_beta   99.23000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y+1/2,-z+1/2
3 -x,-y,-z
4 x,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O    4 e 0.07000 0.33170 0.34470 1.00000
O2  O    4 e 0.44960 0.75690 0.47920 1.00000
Zr1 Zr   4 e 0.27540 0.03950 0.20830 1.00000
```

Baddeleyite (ZrO_2, C43): A2B_mP12_14_2e_e - POSCAR

```
A2B_mP12_14_2e_e & a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3 --params=
    ↪ 5.1505,1.01186292593,1.03238520532,99.23,0.07,0.3317,0.3447,
    ↪ 0.4496,0.7569,0.4792,0.2754,0.0395,0.2083 & P2_1/c  C_{2h}^5
    ↪ #14 (e^3) & mP12 & C43 & ZrO2 & Baddeleyite & Howard, Hill,
    ↪ and Reichert, Acta Cryst. B 44, 116-20 (1988)
  1.0000000000000000
  5.15050000000000   0.00000000000000   0.00000000000000
  0.00000000000000   5.21160000000000   0.00000000000000
 -0.85288444000000   0.00000000000000   5.24845381000000
   O   Zr
   8   4
Direct
  0.07000000000000   0.16830000000000   0.84470000000000   O   (4e)
  0.07000000000000   0.33170000000000   0.34470000000000   O   (4e)
  0.93000000000000   0.66830000000000   0.65530000000000   O   (4e)
  0.93000000000000   0.83170000000000   0.15530000000000   O   (4e)
  0.44960000000000   0.74310000000000   0.97920000000000   O   (4e)
  0.44960000000000   0.75690000000000   0.47920000000000   O   (4e)
  0.55040000000000   0.24310000000000   0.52080000000000   O   (4e)
  0.55040000000000   0.25690000000000   0.02080000000000   O   (4e)
  0.27540000000000   0.03950000000000   0.20830000000000   Zr  (4e)
  0.27540000000000   0.46050000000000   0.70830000000000   Zr  (4e)
  0.72460000000000   0.53950000000000   0.29170000000000   Zr  (4e)
  0.72460000000000   0.96050000000000   0.79170000000000   Zr  (4e)
```

β-Se (A_l): A_mP32_14_8e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Selenium'
_chemical_formula_sum 'Se'

loop_
_publ_author_name
 'R. E. Marsh'
 'L. Pauling'
 'J. D. McCullough'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 6
_journal_year 1953
_journal_page_first 71
_journal_page_last 75
_publ_Section_title
;
 The Crystal Structure of $\beta$ Selenium
;

# Found in  Donohue, pp. 379-384

_aflow_proto 'A_mP32_14_8e'
_aflow_params 'a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5
    ↪ ,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8'
_aflow_params_values '9.31,0.866809881847,1.38023630505,93.13333,0.437,
    ↪ 0.185,0.084,0.246,0.273,-0.023,0.24,0.102,0.828,0.05,-0.08,
    ↪ 0.852,0.157,0.669,-0.09,0.142,0.66,0.09,0.368,0.746,0.16,0.334,
    ↪ 0.021,0.21'

_aflow_Strukturbericht 'A_l'
_aflow_Pearson 'mP32'

_symmetry_space_group_name_Hall "-P 2ybc"
_symmetry_space_group_name_H-M "P 1 21/c 1"
_symmetry_Int_Tables_number 14

_cell_length_a      9.31000
_cell_length_b      8.07000
_cell_length_c      12.85000
_cell_angle_alpha  90.00000
_cell_angle_beta   93.13333
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y+1/2,-z+1/2
3 -x,-y,-z
4 x,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Se1 Se   4 e 0.43700 0.18500  0.08400 1.00000
Se2 Se   4 e 0.24600 0.27300 -0.02300 1.00000
Se3 Se   4 e 0.24000 0.10200  0.82800 1.00000
Se4 Se   4 e 0.05000 -0.08000  0.85200 1.00000
Se5 Se   4 e 0.15700 0.66900 -0.09000 1.00000
Se6 Se   4 e 0.14200 0.66000  0.09000 1.00000
Se7 Se   4 e 0.36800 0.74600  0.16000 1.00000
Se8 Se   4 e 0.33400 0.02100 0.21000 1.00000
```

β-Se (A_l): A_mP32_14_8e - POSCAR

```
A_mP32_14_8e & a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5
    ↪ ,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8 --params=9.31,0.866809881847,
    ↪ 1.38023630505,93.13333,0.437,0.185,0.084,0.246,0.273,-0.023,
    ↪ 0.24,0.102,0.828,0.05,-0.08,0.852,0.157,0.669,-0.09,0.142,0.66,
    ↪ 0.09,0.368,0.746,0.16,0.334,0.021,0.21 & P2_1/c  C_{2h}^5 #
    ↪ 14 (e^8) & mP32 & A_l & Se & beta & Marsh, Pauling, and
    ↪ McCullough, Acta Cryst. 6, 71-75 (1953)
  1.0000000000000000
  9.31000000000000   0.00000000000000   0.00000000000000
  0.00000000000000   8.07000000000000   0.00000000000000
 -0.70237752000000   0.00000000000000  12.83078976000000
  Se
  32
Direct
  0.43700000000000   0.18500000000000   0.08400000000000   Se   (4e)
  0.43700000000000   0.31500000000000   0.58400000000000   Se   (4e)
  0.56300000000000   0.68500000000000   0.41600000000000   Se   (4e)
  0.56300000000000   0.81500000000000  -0.08400000000000   Se   (4e)
  0.24600000000000   0.22700000000000   0.47700000000000   Se   (4e)
  0.24600000000000   0.27300000000000  -0.02300000000000   Se   (4e)
  0.75400000000000   0.72700000000000   0.02300000000000   Se   (4e)
  0.75400000000000   0.77300000000000   0.52300000000000   Se   (4e)
  0.24000000000000   0.10200000000000   0.82800000000000   Se   (4e)
  0.24000000000000   0.39800000000000   0.32800000000000   Se   (4e)
  0.76000000000000   0.60200000000000   0.67200000000000   Se   (4e)
  0.76000000000000   0.89800000000000   0.17200000000000   Se   (4e)
 -0.05000000000000   0.08000000000000   0.14800000000000   Se   (4e)
  0.05000000000000  -0.08000000000000   0.85200000000000   Se   (4e)
 -0.05000000000000   0.42000000000000   0.64800000000000   Se   (4e)
  0.05000000000000   0.58000000000000   0.35200000000000   Se   (4e)
  0.15700000000000   0.66900000000000  -0.09000000000000   Se   (4e)
  0.15700000000000   0.83100000000000   0.41000000000000   Se   (4e)
  0.84300000000000   0.16900000000000   0.59000000000000   Se   (4e)
  0.84300000000000   0.33100000000000   0.09000000000000   Se   (4e)
  0.14200000000000   0.66000000000000   0.09000000000000   Se   (4e)
  0.14200000000000   0.84000000000000   0.59000000000000   Se   (4e)
  0.85800000000000   0.16000000000000   0.41000000000000   Se   (4e)
  0.85800000000000   0.34000000000000  -0.09000000000000   Se   (4e)
  0.36800000000000   0.74600000000000   0.16000000000000   Se   (4e)
  0.36800000000000   0.75400000000000   0.66000000000000   Se   (4e)
  0.63200000000000   0.24600000000000   0.34000000000000   Se   (4e)
  0.63200000000000   0.25400000000000   0.84000000000000   Se   (4e)
  0.33400000000000   0.02100000000000   0.21000000000000   Se   (4e)
  0.33400000000000   0.47900000000000   0.71000000000000   Se   (4e)
  0.66600000000000  -0.02100000000000   0.79000000000000   Se   (4e)
  0.66600000000000   0.52100000000000   0.29000000000000   Se   (4e)
```

Se (A_k): A_mP64_14_16e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'red selenium'
_chemical_formula_sum 'Se'

loop_
_publ_author_name
 'Olav Foss'
 'Vitalijus Janickis'
_journal_name_full
;
Journal of the Chemical Society, Chemical Communications
;
_journal_volume
_journal_year 1977
_journal_page_first 834
_journal_page_last 835
```

```
_publ_Section_title
;
 X-Ray crystal structure of a new red, monoclinic form of
      ↪ cyclo-octaselenium, Se$_{8}$
;

# Found in  Pearson's Hanbook, Vol. IV, p. 5716

_aflow_proto 'A_mP64_14_16e'
_aflow_params 'a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5
      ↪ ,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,y10,z10,x11,y11,z11
      ↪ ,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15,x16,y16,z16'
_aflow_params_values '15.018,0.979691037422,0.585231056066,93.61,0.18313
      ↪ ,0.14063,0.03451,0.22856,0.28408,0.12262,0.35548,0.31907,-
      ↪ 0.00548,0.47826,0.28776,0.16131,0.52853,0.14438,0.09345,0.47966
      ↪ ,0.04033,0.27102,0.36296,-0.02818,0.15123,0.22521,0.04261,
      ↪ 0.2343,0.09552,0.48601,0.14213,0.01298,0.58883,0.27815,-0.01931
      ↪ ,0.71476,0.12135,0.08347,0.82945,0.18553,0.19177,0.81338,
      ↪ 0.00963,0.3102,0.73961,0.14402,0.30834,0.59137,0.04778,0.24353,
      ↪ 0.50553,0.23353'
_aflow_Strukturbericht 'A_k'
_aflow_Pearson 'mP64'

_symmetry_space_group_name_Hall "-P 2ybc"
_symmetry_space_group_name_H-M "P 1 21/c 1"
_symmetry_Int_Tables_number 14

_cell_length_a      15.01800
_cell_length_b      14.71300
_cell_length_c      8.78900
_cell_angle_alpha   90.00000
_cell_angle_beta    93.61000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y+1/2,-z+1/2
3 -x,-y,-z
4 x,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Se1  Se  4 e 0.18313  0.14063  0.03451  1.00000
Se2  Se  4 e 0.22856  0.28408  0.12262  1.00000
Se3  Se  4 e 0.35548  0.31907  -0.00548  1.00000
Se4  Se  4 e 0.47826  0.28776  0.16131  1.00000
Se5  Se  4 e 0.52853  0.14438  0.09345  1.00000
Se6  Se  4 e 0.47966  0.04033  0.27102  1.00000
Se7  Se  4 e 0.36296  -0.02818  0.15123  1.00000
Se8  Se  4 e 0.22521  0.04261  0.23430  1.00000
Se9  Se  4 e 0.09552  0.48601  0.14213  1.00000
Se10 Se  4 e 0.01298  0.58883  0.27815  1.00000
Se11 Se  4 e -0.01931 0.71476  0.12135  1.00000
Se12 Se  4 e 0.08347  0.82945  0.18553  1.00000
Se13 Se  4 e 0.19177  0.81338  0.00963  1.00000
Se14 Se  4 e 0.31020  0.73961  0.14402  1.00000
Se15 Se  4 e 0.30834  0.59137  0.04778  1.00000
Se16 Se  4 e 0.24353  0.50553  0.23353  1.00000
```

Se (A_k): A_mP64_14_16e - POSCAR

```
A_mP64_14_16e & a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,
      ↪ y5,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8,x9,y9,z9,x10,y10,z10,x11,y11,
      ↪ z11,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15,x16,y16,z16
      ↪  --params=15.018,0.979691037422,0.585231056066,93.61,0.18313,
      ↪ 0.14063,0.03451,0.22856,0.28408,0.12262,0.35548,0.31907,-
      ↪ 0.00548,0.47826,0.28776,0.16131,0.52853,0.14438,0.09345,0.47966
      ↪ ,0.04033,0.27102,0.36296,-0.02818,0.15123,0.22521,0.04261,
      ↪ 0.2343,0.09552,0.48601,0.14213,0.01298,0.58883,0.27815,-0.01931
      ↪ ,0.71476,0.12135,0.08347,0.82945,0.18553,0.19177,0.81338,
      ↪ 0.00963,0.3102,0.73961,0.14402,0.30834,0.59137,0.04778,0.24353,
      ↪ 0.50553,0.23353 & P2_1/c      C_{2h}^5 #14 (e^16) & mP64 & A_k &
      ↪  Se & Red (gamma) & Foss and Janickis J. Chem. Soc., Chem.
      ↪ Comm. 834-835 (1977)
   1.0000000000000000
  15.01800000000000    0.00000000000000    0.00000000000000
   0.00000000000000   14.71300000000000    0.00000000000000
  -0.55339681000000    0.00000000000000    8.77156046000000
   Se
   64
Direct
   0.18313000000000    0.14063000000000    0.03451000000000    Se    (4e)
   0.18313000000000    0.35937000000000    0.53451000000000    Se    (4e)
   0.81687000000000    0.64063000000000    0.46549000000000    Se    (4e)
   0.81687000000000    0.85937000000000   -0.03451000000000    Se    (4e)
  -0.01298000000000    0.08883000000000    0.22185000000000    Se    (4e)
   0.01298000000000   -0.08883000000000    0.77815000000000    Se    (4e)
  -0.01298000000000    0.41117000000000    0.72185000000000    Se    (4e)
   0.01298000000000    0.58883000000000    0.27815000000000    Se    (4e)
   0.01931000000000    0.21476000000000    0.37865000000000    Se    (4e)
   0.01931000000000    0.28524000000000    0.87865000000000    Se    (4e)
  -0.01931000000000    0.71476000000000    0.12135000000000    Se    (4e)
  -0.01931000000000    0.78524000000000    0.62135000000000    Se    (4e)
  -0.08347000000000    0.17055000000000    0.81447000000000    Se    (4e)
  -0.08347000000000    0.32945000000000    0.31447000000000    Se    (4e)
   0.08347000000000    0.67055000000000    0.68553000000000    Se    (4e)
   0.08347000000000    0.82945000000000    0.18553000000000    Se    (4e)
   0.19177000000000    0.68662000000000    0.50963000000000    Se    (4e)
   0.19177000000000    0.81338000000000    0.00963000000000    Se    (4e)
   0.80823000000000    0.18662000000000   -0.00963000000000    Se    (4e)
   0.80823000000000    0.31338000000000    0.49037000000000    Se    (4e)
   0.31020000000000    0.73961000000000    0.14402000000000    Se    (4e)
   0.31020000000000    0.76039000000000    0.64402000000000    Se    (4e)
   0.68980000000000    0.23961000000000    0.35598000000000    Se    (4e)
   0.68980000000000    0.26039000000000    0.85598000000000    Se    (4e)
   0.30834000000000   -0.09137000000000    0.54778000000000    Se    (4e)
   0.30834000000000    0.59137000000000    0.04778000000000    Se    (4e)
   0.69166000000000    0.09137000000000    0.45222000000000    Se    (4e)
   0.69166000000000    0.40863000000000   -0.04778000000000    Se    (4e)
   0.24353000000000   -0.00553000000000    0.73353000000000    Se    (4e)
   0.24353000000000    0.50553000000000    0.23353000000000    Se    (4e)
   0.75647000000000    0.00553000000000    0.26647000000000    Se    (4e)
   0.75647000000000    0.49447000000000    0.76647000000000    Se    (4e)
   0.22856000000000    0.21592000000000    0.62262000000000    Se    (4e)
   0.22856000000000    0.28408000000000    0.12262000000000    Se    (4e)
   0.77144000000000    0.71592000000000    0.87738000000000    Se    (4e)
   0.77144000000000    0.78408000000000    0.37738000000000    Se    (4e)
   0.35548000000000    0.18093000000000    0.49452000000000    Se    (4e)
   0.35548000000000    0.31907000000000   -0.00548000000000    Se    (4e)
   0.64452000000000    0.68093000000000    0.00548000000000    Se    (4e)
   0.64452000000000    0.81907000000000    0.50548000000000    Se    (4e)
   0.47826000000000    0.21224000000000    0.66131000000000    Se    (4e)
   0.47826000000000    0.28776000000000    0.16131000000000    Se    (4e)
   0.52174000000000    0.71224000000000    0.83869000000000    Se    (4e)
   0.52174000000000    0.78776000000000    0.33869000000000    Se    (4e)
   0.47147000000000    0.64438000000000    0.40655000000000    Se    (4e)
   0.47147000000000    0.85562000000000   -0.09345000000000    Se    (4e)
   0.52853000000000    0.14438000000000    0.09345000000000    Se    (4e)
   0.52853000000000    0.35562000000000    0.59345000000000    Se    (4e)
   0.47966000000000    0.04033000000000    0.27102000000000    Se    (4e)
   0.47966000000000    0.45967000000000    0.77102000000000    Se    (4e)
   0.52034000000000   -0.04033000000000    0.72898000000000    Se    (4e)
   0.52034000000000    0.54033000000000    0.22898000000000    Se    (4e)
   0.36296000000000   -0.02818000000000    0.15123000000000    Se    (4e)
   0.36296000000000    0.52818000000000    0.65123000000000    Se    (4e)
   0.63704000000000    0.02818000000000    0.84877000000000    Se    (4e)
   0.63704000000000    0.47182000000000    0.34877000000000    Se    (4e)
   0.22521000000000    0.04261000000000    0.23430000000000    Se    (4e)
   0.22521000000000    0.45739000000000    0.73430000000000    Se    (4e)
   0.77479000000000   -0.04261000000000    0.76570000000000    Se    (4e)
   0.77479000000000    0.54261000000000    0.26570000000000    Se    (4e)
  -0.09552000000000   -0.01399000000000    0.35787000000000    Se    (4e)
   0.09552000000000    0.01399000000000    0.64213000000000    Se    (4e)
   0.09552000000000    0.48601000000000    0.14213000000000    Se    (4e)
  -0.09552000000000    0.51399000000000    0.85787000000000    Se    (4e)
```

B_2Pd_5: A2B5_mC28_15_f_e2f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'B2 Pd5'

loop_
_publ_author_name
 'Erik Stenberg'
_journal_name_full
;
Acta Chemica Scandinavica
;
_journal_volume 15
_journal_year 1961
_journal_page_first 861
_journal_page_last 870
_publ_Section_title
;
 The Crystal Structures of Pd$_5$B$_2$, (Mn$_5$C$_2$), and Pd$_3$B
;

_aflow_proto 'A2B5_mC28_15_f_e2f'
_aflow_params 'a,b/a,c/a,\beta,y1,x2,y2,z2,x3,y3,z3,x4,y4,z4'
_aflow_params_values '12.786,0.387533239481,0.427968090099,97.03333,
      ↪ 0.5727,0.106,0.311,0.077,0.0958,0.0952,0.4213,0.7127,0.0726,
      ↪ 0.3138'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mC28'

_symmetry_space_group_name_Hall "-C 2yc"
_symmetry_space_group_name_H-M "C 1 2/c 1"
_symmetry_Int_Tables_number 15

_cell_length_a      12.78600
_cell_length_b      4.95500
_cell_length_c      5.47200
_cell_angle_alpha   90.00000
_cell_angle_beta    97.03333
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z+1/2
3 -x,-y,-z
4 x,-y,z+1/2
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z+1/2
7 -x+1/2,-y+1/2,-z
```

```
8 x+1/2,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pd1 Pd   4 e 0.00000 0.57270 0.25000 1.00000
B1  B    8 f 0.10600 0.31100 0.07700 1.00000
Pd2 Pd   8 f 0.09580 0.09520 0.42130 1.00000
Pd3 Pd   8 f 0.71270 0.07260 0.31380 1.00000
```

B_2Pd_5: A2B5_mC28_15_f_e2f - POSCAR

```
A2B5_mC28_15_f_e2f & a,b/a,c/a,\beta,y1,x2,y2,z2,x3,y3,z3,x4,y4,z4 --
    ↪ params=12.786,0.387533239481,0.427968090099,97.03333,0.5727,
    ↪ 0.106,0.311,0.077,0.0958,0.0952,0.4213,0.7127,0.0726,0.3138 &
    ↪ C2/c  C_{2h}^6 #15 (ef^3) & mC28 & & B2Pd5 & & Stenberg,
    ↪ Acta Chem. Scand. 15, 861-70 (1961)
  1.0000000000000000
  6.39300000000000  -2.47750000000000  0.00000000000000
  6.39300000000000   2.47750000000000  0.00000000000000
 -0.67002869000000   0.00000000000000  5.43082365000000
   B   Pd
   4   10
Direct
  0.20500000000000  0.58300000000000  0.92300000000000   B   (8f)
  0.41700000000000  0.79500000000000  0.57700000000000   B   (8f)
  0.58300000000000  0.20500000000000  0.42300000000000   B   (8f)
  0.79500000000000  0.41700000000000  0.07700000000000   B   (8f)
  0.42730000000000  0.57270000000000  0.25000000000000  Pd   (4e)
  0.57270000000000  0.42730000000000  0.75000000000000  Pd   (4e)
  0.00060000000000  0.19100000000000  0.42130000000000  Pd   (8f)
 -0.00060000000000  0.80900000000000  0.57870000000000  Pd   (8f)
  0.19100000000000  0.00060000000000  0.92130000000000  Pd   (8f)
  0.80900000000000 -0.00060000000000  0.07870000000000  Pd   (8f)
  0.21470000000000  0.35990000000000  0.18620000000000  Pd   (8f)
  0.35990000000000  0.21470000000000  0.68620000000000  Pd   (8f)
  0.64010000000000  0.78530000000000  0.31380000000000  Pd   (8f)
  0.78530000000000  0.64010000000000  0.81380000000000  Pd   (8f)
```

Tenorite (CuO, B26): AB_mC8_15_c_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Tenorite'
_chemical_formula_sum 'Cu O'

loop_
_publ_author_name
 'S. \AAsbrink'
 'L.-J. Norrby'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 26
_journal_year 1970
_journal_page_first 8
_journal_page_last 15
_publ_Section_title
;
 A refinement of the crystal structure of copper(II) oxide with a
    ↪ discussion of some exceptional e.s.d.'s
;

_aflow_proto 'AB_mC8_15_c_e'
_aflow_params 'a,b/a,c/a,\beta,y2'
_aflow_params_values '4.6837,0.730747058949,1.0950317057,120.34,0.4184'
_aflow_Strukturbericht 'B26'
_aflow_Pearson 'mC8'

_symmetry_space_group_name_Hall "-C 2yc"
_symmetry_space_group_name_H-M "C 1 2/c 1"
_symmetry_Int_Tables_number 15

_cell_length_a    4.68370
_cell_length_b    3.42260
_cell_length_c    5.12880
_cell_angle_alpha 90.00000
_cell_angle_beta  120.34000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z+1/2
3 -x,-y,-z
4 x,-y,z+1/2
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z+1/2
7 -x+1/2,-y+1/2,-z
8 x+1/2,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu   4 c 0.25000 0.25000 0.00000 1.00000
O1  O    4 e 0.00000 0.41840 0.25000 1.00000
```

Tenorite (CuO, B26): AB_mC8_15_c_e - POSCAR

```
AB_mC8_15_c_e & a,b/a,c/a,\beta,y2 --params=4.6837,0.730747058949,
    ↪ 1.0950317057,120.34,0.4184 & C2/c  C_{2h}^6 #15 (ce) &
    ↪ mC8 & B26 & CuO & Tenorite & \AAsbrink and Norrby, Acta Cryst.
    ↪ B 26, 8-15 (1970)
  1.0000000000000000
  2.34185000000000  -1.71130000000000  0.00000000000000
  2.34185000000000   1.71130000000000  0.00000000000000
 -2.59071210000000   0.00000000000000  4.42637552000000
   Cu   O
    2   2
Direct
 -0.00000000000000   0.50000000000000  0.00000000000000   Cu   (4c)
  0.50000000000000  -0.00000000000000  0.50000000000000   Cu   (4c)
  0.41840000000000   0.58160000000000  0.75000000000000   O    (4e)
  0.58160000000000   0.41840000000000  0.25000000000000   O    (4e)
```

Coesite (SiO_2): A2B_mC48_15_ae3f_2f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Coesite'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'Louise Levien'
 'Charles T. Prewitt'
_journal_name_full
;
American Mineralogist
;
_journal_volume 66
_journal_year 1981
_journal_page_first 324
_journal_page_last 333
_publ_Section_title
;
 High-pressure crystal structure and compressibility of coesite
;

_aflow_proto 'A2B_mC48_15_ae3f_2f'
_aflow_params 'a,b/a,c/a,\beta,y2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6,x7
    ↪ ,y7,z7'
_aflow_params_values '7.1356,1.73344918437,1.00532541062,120.34,0.1163,
    ↪ 0.266,0.1234,0.9401,0.3114,0.1038,0.3282,0.0172,0.2117,0.4782,
    ↪ 0.14033,0.10833,0.07227,0.50682,0.15799,0.54077'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mC48'

_symmetry_space_group_name_Hall "-C 2yc"
_symmetry_space_group_name_H-M "C 1 2/c 1"
_symmetry_Int_Tables_number 15

_cell_length_a    7.13560
_cell_length_b    12.36920
_cell_length_c    7.17360
_cell_angle_alpha 90.00000
_cell_angle_beta  120.34000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z+1/2
3 -x,-y,-z
4 x,-y,z+1/2
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z+1/2
7 -x+1/2,-y+1/2,-z
8 x+1/2,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O    4 a 0.00000 0.00000 0.00000 1.00000
O2  O    4 e 0.00000 0.11630 0.25000 1.00000
O3  O    8 f 0.26600 0.12340 0.94010 1.00000
O4  O    8 f 0.31140 0.10380 0.32820 1.00000
O5  O    8 f 0.01720 0.21170 0.47820 1.00000
Si1 Si   8 f 0.14033 0.10833 0.07227 1.00000
Si2 Si   8 f 0.50682 0.15799 0.54077 1.00000
```

Coesite (SiO_2): A2B_mC48_15_ae3f_2f - POSCAR

```
A2B_mC48_15_ae3f_2f & a,b/a,c/a,\beta,y2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,
    ↪ y6,z6,x7,y7,z7 --params=7.1356,1.73344918437,1.00532541062,
    ↪ 120.34,0.1163,0.266,0.1234,0.9401,0.3114,0.1038,0.3282,0.0172,
    ↪ 0.2117,0.4782,0.14033,0.10833,0.07227,0.50682,0.15799,0.54077 &
    ↪ C2/c C_{2h}^6 #15 (aef^5) & mC48 & & SiO2 & Coesite (1
    ↪ atm) & Levien and Prewitt, Am. Mineral. 66, 324-33 (1981)
   1.0000000000000000
   3.56780000000000  -6.18460000000000   0.00000000000000
   3.56780000000000   6.18460000000000   0.00000000000000
  -3.62360247000000   0.00000000000000   6.19112608000000
   O   Si
   16   8
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   O   (4a)
   0.00000000000000   0.00000000000000   0.50000000000000   O   (4a)
   0.11630000000000   0.88370000000000   0.75000000000000   O   (4e)
   0.88370000000000   0.11630000000000   0.25000000000000   O   (4e)
   0.14260000000000   0.38940000000000   0.94010000000000   O   (8f)
   0.38940000000000   0.14260000000000   0.44010000000000   O   (8f)
   0.61060000000000   0.85740000000000   0.55990000000000   O   (8f)
   0.85740000000000   0.61060000000000   0.05990000000000   O   (8f)
   0.20760000000000   0.41520000000000   0.32820000000000   O   (8f)
   0.41520000000000   0.20760000000000   0.82820000000000   O   (8f)
   0.58480000000000   0.79240000000000   0.17180000000000   O   (8f)
   0.79240000000000   0.58480000000000   0.67180000000000   O   (8f)
   0.19450000000000   0.77110000000000   0.52180000000000   O   (8f)
   0.22890000000000   0.80550000000000   0.97820000000000   O   (8f)
   0.77110000000000   0.19450000000000   0.02180000000000   O   (8f)
   0.80550000000000   0.22890000000000   0.47820000000000   O   (8f)
   0.03200000000000   0.24866000000000   0.07227000000000  Si   (8f)
  -0.03200000000000   0.75134000000000   0.92773000000000  Si   (8f)
   0.24866000000000   0.03200000000000   0.57227000000000  Si   (8f)
   0.75134000000000  -0.03200000000000   0.42773000000000  Si   (8f)
   0.33519000000000   0.65117000000000  -0.04077000000000  Si   (8f)
   0.34883000000000   0.66481000000000   0.54077000000000  Si   (8f)
   0.65117000000000   0.33519000000000   0.45923000000000  Si   (8f)
   0.66481000000000   0.34883000000000   0.04077000000000  Si   (8f)
```

Esseneite: ABC6D2_mC40_15_e_e_3f_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Esseneite'
_chemical_formula_sum 'Ca Fe O6 Si2'

loop_
_publ_author_name
 'Michael A. Cosca'
 'Donald R. Peacor'
_journal_name_full
;
American Mineralogist
;
_journal_volume 72
_journal_year 1987
_journal_page_first 148
_journal_page_last 156
_publ_Section_title
;
 Chemistry and structure of esseneite (CaFe$^{3+}$AlSiO$_6$), a new
    ↪ pyroxene produced by pyrometamorphism
;

# Found in AMS Database

_aflow_proto 'ABC6D2_mC40_15_e_e_3f_f'
_aflow_params 'a,b/a,c/a,\beta,y1,y2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6
    ↪ '
_aflow_params_values '9.79,0.901123595506,0.548518896834,105.81,0.3082,-
    ↪ 0.0942,0.3888,0.4123,0.8659,0.1365,0.2411,0.6799,0.1468,0.4802,
    ↪ 0.0124,0.2117,0.4057,0.7764'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'mC40'

_symmetry_space_group_name_Hall "-C 2yc"
_symmetry_space_group_name_H-M "C 1 2/c 1"
_symmetry_Int_Tables_number 15

_cell_length_a    9.79000
_cell_length_b    8.82200
_cell_length_c    5.37000
_cell_angle_alpha 90.00000
_cell_angle_beta  105.81000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,y,-z+1/2
3 -x,-y,-z
4 x,-y,z+1/2
5 x+1/2,y+1/2,z
6 -x+1/2,y+1/2,-z+1/2
7 -x+1/2,-y+1/2,-z
8 x+1/2,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ca1 Ca   4 e 0.00000 0.30820  0.25000 1.00000
Fe1 Fe   4 e 0.00000 -0.09420 0.25000 1.00000
O1  O    8 f 0.38880 0.41230  0.86590 1.00000
O2  O    8 f 0.13650 0.24110  0.67990 1.00000
O3  O    8 f 0.14680 0.48020  0.01240 1.00000
Si1 Si   8 f 0.21170 0.40570  0.77640 1.00000
```

Esseneite: ABC6D2_mC40_15_e_e_3f_f - POSCAR

```
ABC6D2_mC40_15_e_e_3f_f & a,b/a,c/a,\beta,y1,y2,x3,y3,z3,x4,y4,z4,x5,y5,
    ↪ z5,x6,y6,z6 --params=9.79,0.901123595506,0.548518896834,105.81,
    ↪ 0.3082,-0.0942,0.3888,0.4123,0.8659,0.1365,0.2411,0.6799,0.1468
    ↪ ,0.4802,0.0124,0.2117,0.4057,0.7764 & C2/c C_{2h}^6 #15 (e
    ↪ ^2f^4) & mC40 & & CaFeO6Si2 & Esseneite & Cosca and Peacor, Am.
    ↪ Mineral. 72, 148-156 (1987)
   1.0000000000000000
   4.89500000000000  -4.41100000000000   0.00000000000000
   4.89500000000000   4.41100000000000   0.00000000000000
  -1.46304674000000   0.00000000000000   5.16685535000000
   Ca   Fe   O   Si
   2    2   12   4
Direct
   0.30820000000000   0.69180000000000   0.75000000000000  Ca   (4e)
   0.69180000000000   0.30820000000000   0.25000000000000  Ca   (4e)
  -0.09420000000000   0.09420000000000   0.75000000000000  Fe   (4e)
   0.09420000000000   0.90580000000000   0.25000000000000  Fe   (4e)
   0.02350000000000   0.19890000000000   0.13410000000000   O   (8f)
  -0.02350000000000   0.80110000000000   0.86590000000000   O   (8f)
   0.19890000000000   0.02350000000000   0.63410000000000   O   (8f)
   0.80110000000000   0.97650000000000   0.36590000000000   O   (8f)
   0.10460000000000   0.62240000000000   0.32010000000000   O   (8f)
   0.37760000000000   0.89540000000000   0.17990000000000   O   (8f)
   0.62240000000000   0.10460000000000   0.82010000000000   O   (8f)
   0.89540000000000   0.37760000000000   0.67990000000000   O   (8f)
   0.33340000000000   0.37300000000000   0.98760000000000   O   (8f)
   0.37300000000000   0.33340000000000   0.48760000000000   O   (8f)
   0.62700000000000   0.66660000000000   0.51240000000000   O   (8f)
   0.66660000000000   0.62700000000000   0.01240000000000   O   (8f)
   0.19400000000000   0.38260000000000   0.22360000000000  Si   (8f)
   0.38260000000000   0.19400000000000   0.72360000000000  Si   (8f)
   0.61740000000000   0.80600000000000   0.27640000000000  Si   (8f)
   0.80600000000000   0.61740000000000   0.77640000000000  Si   (8f)
```

$AlPS_4$: ABC4_oP12_16_ag_cd_2u - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Al P S4'

loop_
_publ_author_name
 'A. Weiss'
 'H. Sch{\"a}fer'
_journal_name_full
;
Naturwissenschaften
;
_journal_volume 47
_journal_year 1960
_journal_page_first 495
_journal_page_last 495
_publ_Section_title
;
 Zur Kenntnis von Aluminiumthiophosphat AlPS$_4$
;

_aflow_proto 'ABC4_oP12_16_ag_cd_2u'
_aflow_params 'a,b/a,c/a,x5,y5,z5,x6,y6,z6'
_aflow_params_values '5.61,1.01069518717,1.61319073084,0.2,0.26,0.125,
    ↪ 0.74,0.8,0.63'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP12'

_symmetry_space_group_name_Hall "P 2 2"
_symmetry_space_group_name_H-M "P 2 2 2"
_symmetry_Int_Tables_number 16

_cell_length_a    5.61000
_cell_length_b    5.67000
_cell_length_c    9.05000
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
```

```
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1  Al    1  a  0.00000  0.00000  0.00000  1.00000
P1   P     1  c  0.00000  0.50000  0.00000  1.00000
P2   P     1  d  0.00000  0.00000  0.50000  1.00000
Al2  Al    1  g  0.00000  0.50000  0.50000  1.00000
S1   S     4  u  0.20000  0.26000  0.12500  1.00000
S2   S     4  u  0.74000  0.80000  0.63000  1.00000
```

$AlPS_4$: ABC4_oP12_16_ag_cd_2u - POSCAR

```
ABC4_oP12_16_ag_cd_2u & a,b/a,c/a,x5,y5,z5,x6,y6,z6 --params=5.61,
      ↪ 1.01069518717,1.61319073084,0.2,0.26,0.125,0.74,0.8,0.63 & P222
      ↪          D_2^1 #16 (acdgu^2) & oP12 & & AlPS4 & & A. Weiss and H.
      ↪ Sch{"\a}fer, Naturwissenschaften 47, 495 (1960)
   1.0000000000000000
   5.61000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.67000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    9.05000000000000
   Al     P     S
    2     2     8
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Al    (1a)
   0.00000000000000    0.50000000000000    0.50000000000000    Al    (1g)
   0.00000000000000    0.50000000000000    0.00000000000000     P    (1c)
   0.00000000000000    0.00000000000000    0.50000000000000     P    (1d)
   0.20000000000000    0.26000000000000    0.12500000000000     S    (4u)
   0.20000000000000    0.74000000000000    0.87500000000000     S    (4u)
   0.80000000000000    0.26000000000000    0.87500000000000     S    (4u)
   0.80000000000000    0.74000000000000    0.12500000000000     S    (4u)
   0.26000000000000    0.20000000000000    0.63000000000000     S    (4u)
   0.26000000000000    0.80000000000000    0.37000000000000     S    (4u)
   0.74000000000000    0.20000000000000    0.37000000000000     S    (4u)
   0.74000000000000    0.80000000000000    0.63000000000000     S    (4u)
```

BaS_3: AB3_oP16_18_ab_3c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ba S3'

loop_
_publ_author_name
 'W. S. Miller'
 'A. J. King'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 94
_journal_year 1936
_journal_page_first 439
_journal_page_last 446
_publ_Section_title
;
 The Structure of Polysuflides: 1 Barium Trisulfide
;

# Found in  Pearson's Handbook II, p. 1701

_aflow_proto 'AB3_oP16_18_ab_3c'
_aflow_params 'a,b/a,c/a,z1,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5'
_aflow_params_values '8.32,1.15865384615,0.579326923077,0.0,0.0,0.25,
      ↪ 0.25,0.0,0.25,0.5,0.5,0.124,0.309,0.382'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP16'

_symmetry_space_group_name_Hall "P 2 2ab"
_symmetry_space_group_name_H-M "P 21 21 2"
_symmetry_Int_Tables_number 18

_cell_length_a      8.32000
_cell_length_b      9.64000
_cell_length_c      4.82000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x+1/2,y+1/2,-z
4 -x,-y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ba1  Ba    2  a  0.00000  0.00000  0.00000  1.00000
Ba2  Ba    2  b  0.00000  0.50000  0.00000  1.00000
S1   S     4  c  0.25000  0.25000  0.00000  1.00000
S2   S     4  c  0.25000  0.50000  0.50000  1.00000
S3   S     4  c  0.12400  0.30900  0.38200  1.00000
```

BaS_3: AB3_oP16_18_ab_3c - POSCAR

```
AB3_oP16_18_ab_3c & a,b/a,c/a,z1,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5 --params=
      ↪ 8.32,1.15865384615,0.579326923077,0.0,0.0,0.25,0.25,0.0,0.25,
      ↪ 0.5,0.5,0.124,0.309,0.382 & P2_12_12  D_2^3 #18 (abc^3) & oP16
      ↪ & & BaS3 & & W. S. Miller and A.J. King, Zeitschrift f\"{u}r
      ↪ Kristallographie - Crystalline Materials 94, 439-446 (1936)
   1.0000000000000000
   8.32000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    9.64000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.82000000000000
   Ba     S
    4    12
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Ba    (2a)
   0.50000000000000    0.50000000000000    0.00000000000000    Ba    (2a)
   0.00000000000000    0.50000000000000    0.00000000000000    Ba    (2b)
   0.50000000000000    0.00000000000000    0.00000000000000    Ba    (2b)
   0.25000000000000    0.25000000000000    0.00000000000000     S    (4c)
   0.25000000000000    0.75000000000000    0.00000000000000     S    (4c)
   0.75000000000000    0.25000000000000    0.00000000000000     S    (4c)
   0.75000000000000    0.75000000000000    0.00000000000000     S    (4c)
   0.25000000000000    0.00000000000000    0.50000000000000     S    (4c)
   0.25000000000000    0.50000000000000    0.50000000000000     S    (4c)
   0.75000000000000    0.00000000000000    0.50000000000000     S    (4c)
   0.75000000000000    0.50000000000000    0.50000000000000     S    (4c)
   0.12400000000000    0.30900000000000    0.38200000000000     S    (4c)
   0.37600000000000    0.80900000000000    0.61800000000000     S    (4c)
   0.62400000000000    0.19100000000000    0.61800000000000     S    (4c)
   0.87600000000000    0.69100000000000    0.38200000000000     S    (4c)
```

Naumannite (Ag_2Se): A2B_oP12_19_2a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ag2 Se'

loop_
_publ_author_name
 'G. A. Wiegers'
_journal_name_full
;
American Mineralogist
;
_journal_volume 56
_journal_year 1971
_journal_page_first 1882
_journal_page_last 1888
_publ_Section_title
;
 The Crystal Structure of the Low-Temperature Form of Silver Selenide
;

# Found in  Pearson's Handbook, Vol I., page 626

_aflow_proto 'A2B_oP12_19_2a_a'
_aflow_params 'a,b/a,c/a,x1,y1,z1,x2,y2,z2,x3,y3,z3'
_aflow_params_values '7.764,0.909582689335,0.558088614116,0.185,0.07,
      ↪ 0.465,0.055,0.765,-0.008,0.884,-0.011,0.391'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP12'

_symmetry_space_group_name_Hall "P 2ac 2ab"
_symmetry_space_group_name_H-M "P 21 21 21"
_symmetry_Int_Tables_number 19

_cell_length_a      7.76400
_cell_length_b      7.06200
_cell_length_c      4.33300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ag1  Ag    4  a  0.18500  0.07000  0.46500  1.00000
Ag2  Ag    4  a  0.05500  0.76500  -0.00800  1.00000
Se1  Se    4  a  0.88400  -0.01100  0.39100  1.00000
```

Naumannite (Ag_2Se): A2B_oP12_19_2a_a - POSCAR

```
A2B_oP12_19_2a_a & a,b/a,c/a,x1,y1,z1,x2,y2,z2,x3,y3,z3 --params=7.764,
      ↪ 0.909582689335,0.558088614116,0.185,0.07,0.465,0.055,0.765,-
      ↪ 0.008,0.884,-0.011,0.391 & P212121      D_2^4 #19 (a^3) & oP12 &
      ↪ & Ag_2Se & Naumannite (below 406K) & G A Wiegers, Am. Mineral.
      ↪ 56, 1882-1888 (1971)
   1.0000000000000000
   7.76400000000000    0.00000000000000    0.00000000000000
   0.00000000000000    7.06200000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.33300000000000
   Ag    Se
    8     4
Direct
   0.18500000000000    0.07000000000000    0.46500000000000    Ag    (4a)
   0.31500000000000   -0.07000000000000   -0.03500000000000    Ag    (4a)
   0.68500000000000    0.43000000000000    0.53500000000000    Ag    (4a)
   0.81500000000000    0.57000000000000    0.03500000000000    Ag    (4a)
  -0.05500000000000    0.26500000000000    0.50800000000000    Ag    (4a)
   0.05500000000000    0.76500000000000   -0.00800000000000    Ag    (4a)
   0.44500000000000    0.23500000000000    0.49200000000000    Ag    (4a)
   0.55500000000000    0.73500000000000    0.00800000000000    Ag    (4a)
   0.11600000000000    0.48900000000000    0.10900000000000    Se    (4a)
   0.38400000000000    0.51100000000000    0.60900000000000    Se    (4a)
   0.61600000000000    0.01100000000000    0.89100000000000    Se    (4a)
   0.88400000000000   -0.01100000000000    0.39100000000000    Se    (4a)
```

Orthorhombic Tridymite (SiO_2): A2B_oC24_20_abc_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'High (Orthorhombic) Tridymite'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'W. A. Dollase'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 23
_journal_year 1967
_journal_page_first 617
_journal_page_last 623
_publ_Section_title
;
 The crystal structure at 220$^\circ$C of orthorhombic high tridymite
      ↪ from the Steinbach meteorite
;

_aflow_proto 'A2B_oC24_20_abc_c'
_aflow_params 'a,b/a,c/a,x1,y2,x3,y3,z3,x4,y4,z4'
_aflow_params_values '8.74,0.576659038902,0.942791762014,0.3336,0.4403,
      ↪ 0.2453,0.1971,0.2713,0.33154,0.03589,0.81143'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oC24'

_symmetry_space_group_name_Hall "C 2c 2"
_symmetry_space_group_name_H-M "C 2 2 21"
_symmetry_Int_Tables_number 20

_cell_length_a      8.74000
_cell_length_b      5.04000
_cell_length_c      8.24000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z+1/2
4 -x,-y,z+1/2
5 x+1/2,y+1/2,z
6 x+1/2,-y+1/2,-z
7 -x+1/2,y+1/2,-z+1/2
8 -x+1/2,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O    4 a 0.33360 0.00000 0.00000 1.00000
O2  O    4 b 0.00000 0.44030 0.25000 1.00000
O3  O    8 c 0.24530 0.19710 0.27130 1.00000
Si1 Si   8 c 0.33154 0.03589 0.81143 1.00000
```

Orthorhombic Tridymite (SiO_2): A2B_oC24_20_abc_c - POSCAR

```
A2B_oC24_20_abc_c & a,b/a,c/a,x1,y2,x3,y3,z3,x4,y4,z4 --params=8.74,
      ↪ 0.576659038902,0.942791762014,0.3336,0.4403,0.2453,0.1971,
      ↪ 0.2713,0.33154,0.03589,0.81143 & C222_1      D_2^5 #20 (abc^2)
      ↪ & oC24 & & SiO2 & ortho-tridymate & Dollase, Acta Cryst. 23,
      ↪ 617-623 (1967)
   1.0000000000000000
   4.37000000000000   -2.52000000000000    0.00000000000000
   4.37000000000000    2.52000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    8.24000000000000
   O    Si
    8    4
Direct
   0.33360000000000    0.33360000000000    0.00000000000000    O    (4a)
   0.66640000000000    0.66640000000000    0.50000000000000    O    (4a)
   0.44030000000000    0.55970000000000    0.75000000000000    O    (4b)
   0.55970000000000    0.44030000000000    0.25000000000000    O    (4b)
   0.04820000000000    0.44240000000000    0.27130000000000    O    (8c)
  -0.04820000000000    0.55760000000000    0.77130000000000    O    (8c)
   0.44240000000000    0.04820000000000    0.72870000000000    O    (8c)
   0.55760000000000   -0.04820000000000    0.22870000000000    O    (8c)
   0.29565000000000    0.36743000000000    0.81143000000000    Si   (8c)
   0.36743000000000    0.29565000000000    0.18857000000000    Si   (8c)
   0.63257000000000    0.70435000000000    0.68857000000000    Si   (8c)
   0.70435000000000    0.63257000000000    0.31143000000000    Si   (8c)
```

High-Pressure CdTe: AB_oP2_25_b_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'High Pressure Cadmuum Telluride'
_chemical_formula_sum 'Cd Te'

loop_
_publ_author_name
 'Jing Zhu Hu'
_journal_name_full
;
Solid State Communications
;
_journal_volume 63
_journal_year 1987
_journal_page_first 471
_journal_page_last 474
_publ_Section_title
;
 A New High Pressure Phase of CdTe
;

# Found in  Pearson's Handbook, II, p. 2816

_aflow_proto 'AB_oP2_25_b_a'
_aflow_params 'a,b/a,c/a,z1,z2'
_aflow_params_values '2.8102,1.87104120703,1.0769696107,0.0,0.25'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP2'

_symmetry_space_group_name_Hall "P 2 -2"
_symmetry_space_group_name_H-M "P m m 2"
_symmetry_Int_Tables_number 25

_cell_length_a      2.81020
_cell_length_b      5.25800
_cell_length_c      3.02650
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 -x,y,z
4 x,-y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Te1 Te   1 a 0.00000 0.00000 0.00000 1.00000
Cd1 Cd   1 b 0.00000 0.50000 0.25000 1.00000
```

High-Pressure CdTe: AB_oP2_25_b_a - POSCAR

```
AB_oP2_25_b_a & a,b/a,c/a,z1,z2 --params=2.8102,1.87104120703,
      ↪ 1.0769696107,0.0,0.25 & Pmm2      C_{2v}^1 #25 (ab) & oP2 & &
      ↪ CdTe & P>12GPa & Jing Zhu Hu, Solid State Comm. 63, 471-474 (
      ↪ 1987)
   1.0000000000000000
   2.81020000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.25800000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.02650000000000
   Cd    Te
    1     1
Direct
   0.00000000000000    0.50000000000000    0.25000000000000    Cd    (1b)
   0.00000000000000    0.00000000000000    0.00000000000000    Te    (1a)
```

Krennerite ($AuTe_2$, C46): AB2_oP24_28_acd_2c3d - CIF

```
# CIF file

data_findsym-output
```

```
_audit_creation_method FINDSYM

_chemical_name_mineral 'Krennerite'
_chemical_formula_sum 'Au Te2'

loop_
_publ_author_name
 'George Tunell'
 'K. J. Murata'
_journal_name_full
;
The American Mineralogist
;
_journal_volume 35
_journal_year 1950
_journal_page_first 959
_journal_page_last 984
_publ_Section_title
;
 The Atomic Arrangement and Chemical Composition of Krennerite
;

_aflow_proto 'AB2_oP24_28_acd_2c3d'
_aflow_params 'a,b/a,c/a,z1,y2,z2,y3,z3,y4,z4,x5,y5,z5,x6,y6,z6,x7,y7,z7
    ↪ ,x8,y8,z8'
_aflow_params_values '16.54,0.533252720677,0.269649334946,0.0,0.319,
    ↪ 0.014,0.018,0.042,0.617,0.042,0.624,0.334,0.5,0.503,0.301,0.042
    ↪ ,0.632,0.636,0.5,0.619,0.036,0.5'
_aflow_Strukturbericht 'C46'
_aflow_Pearson 'oP24'

_symmetry_space_group_name_Hall "P 2 -2a"
_symmetry_space_group_name_H-M "P m a 2"
_symmetry_Int_Tables_number 28

_cell_length_a      16.54000
_cell_length_b      8.82000
_cell_length_c      4.46000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 -x+1/2,y,z
4 x+1/2,-y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Au1 Au   2 a 0.00000 0.00000  0.00000 1.00000
Au2 Au   2 c 0.25000 0.31900  0.01400 1.00000
Te1 Te   2 c 0.25000 0.01800  0.04200 1.00000
Te2 Te   2 c 0.25000 0.61700  0.04200 1.00000
Au3 Au   4 d 0.62400 0.33400  0.50000 1.00000
Te3 Te   4 d 0.50300 0.301000  0.04200 1.00000
Te4 Te   4 d 0.63200 0.63600  0.50000 1.00000
Te5 Te   4 d 0.61900 0.03600 0.50000 1.00000
```

Krennerite ($AuTe_2$, C46): AB2_oP24_28_acd_2c3d - POSCAR

```
AB2_oP24_28_acd_2c3d & a,b/a,c/a,z1,y2,z2,y3,z3,y4,z4,x5,y5,z5,x6,y6,z6,
    ↪ x7,y7,z7,x8,y8,z8 --params=16.54,0.533252720677,0.269649334946,
    ↪ 0.0,0.319,0.014,0.018,0.042,0.617,0.042,0.624,0.334,0.5,0.503,
    ↪ 0.301,0.042,0.632,0.636,0.5,0.619,0.036,0.5 & Pma2        C_{2v
    ↪ }^4 #28 (ac^3d^4) & oP24 & C46 & AuTe2 & Krennerite & G. Tunell
    ↪  and K. J. Murata, Am. Mineral. 35, 959-984 (1950)
   1.0000000000000000
  16.54000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    8.82000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.46000000000000
   Au   Te
    8   16
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Au    (2a)
   0.50000000000000    0.00000000000000    0.00000000000000    Au    (2a)
   0.25000000000000    0.31900000000000    0.01400000000000    Au    (2c)
   0.75000000000000    0.68100000000000    0.01400000000000    Au    (2c)
   0.12400000000000    0.66600000000000    0.50000000000000    Au    (4d)
   0.37600000000000    0.66600000000000    0.50000000000000    Au    (4d)
   0.62400000000000    0.33400000000000    0.50000000000000    Au    (4d)
   0.87600000000000    0.33400000000000    0.50000000000000    Au    (4d)
   0.25000000000000    0.01800000000000    0.04200000000000    Te    (2c)
   0.75000000000000    0.98200000000000    0.04200000000000    Te    (2c)
   0.25000000000000    0.61700000000000    0.04200000000000    Te    (2c)
   0.75000000000000    0.38300000000000    0.04200000000000    Te    (2c)
   0.00300000000000    0.69900000000000    0.04200000000000    Te    (4d)
   0.49700000000000    0.69900000000000    0.04200000000000    Te    (4d)
   0.50300000000000    0.30100000000000    0.04200000000000    Te    (4d)
   0.99700000000000    0.30100000000000    0.04200000000000    Te    (4d)
   0.13200000000000    0.36400000000000    0.50000000000000    Te    (4d)
   0.36800000000000    0.36400000000000    0.50000000000000    Te    (4d)
   0.63200000000000    0.63600000000000    0.50000000000000    Te    (4d)
   0.86800000000000    0.63600000000000    0.50000000000000    Te    (4d)
   0.11900000000000    0.96400000000000    0.50000000000000    Te    (4d)
   0.38100000000000    0.96400000000000    0.50000000000000    Te    (4d)
   0.61900000000000    0.03600000000000    0.50000000000000    Te    (4d)
   0.88100000000000    0.03600000000000    0.50000000000000    Te    (4d)
```

Enargite ($AsCu_3S_4$, $H2_5$): AB3C4_oP16_31_a_ab_2ab - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Enargite'
_chemical_formula_sum 'As Cu3 S4'

loop_
_publ_author_name
 'G. Adiwidjaja'
 'J. L{\"o}hn'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 26
_journal_year 1970
_journal_page_first 1878
_journal_page_last 1879
_publ_Section_title
;
 Strukturverfeinerung von Enargit, Cu$_3$AsS$_4$
;

_aflow_proto 'AB3C4_oP16_31_a_ab_2ab'
_aflow_params 'a,b/a,c/a,y1,z1,y2,z2,y3,z3,y4,z4,x5,y5,z5,x6,y6,z6'
_aflow_params_values '7.43,0.869448183042,0.831763122476,0.8268,0.0,
    ↪ 0.1514,0.4983,0.8226,0.6454,0.1436,0.1166,0.2466,0.3255,-0.0134
    ↪ ,0.2598,0.3364,0.6184'
_aflow_Strukturbericht 'H2_5'
_aflow_Pearson 'oP16'

_symmetry_space_group_name_Hall "P 2ac -2"
_symmetry_space_group_name_H-M "P m n 21"
_symmetry_Int_Tables_number 31

_cell_length_a      7.43000
_cell_length_b      6.46000
_cell_length_c      6.18000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x+1/2,-y,z+1/2
3 -x,y,z
4 x+1/2,-y,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
As1 As   2 a 0.00000 0.82680 0.00000  1.00000
Cu1 Cu   2 a 0.00000 0.15140 0.49830  1.00000
S1  S    2 a 0.00000 0.82260 0.64540  1.00000
S2  S    2 a 0.00000 0.14360 0.11660  1.00000
Cu2 Cu   4 b 0.24660 0.32550 -0.01340 1.00000
S3  S    4 b 0.25980 0.33640 0.61840  1.00000
```

Enargite ($AsCu_3S_4$, $H2_5$): AB3C4_oP16_31_a_ab_2ab - POSCAR

```
AB3C4_oP16_31_a_ab_2ab & a,b/a,c/a,y1,z1,y2,z2,y3,z3,y4,z4,x5,y5,z5,x6,
    ↪ y6,z6 --params=7.43,0.869448183042,0.831763122476,0.8268,0.0,
    ↪ 0.1514,0.4983,0.8226,0.6454,0.1436,0.1166,0.2466,0.3255,-0.0134
    ↪ ,0.2598,0.3364,0.6184 & Pmn2_1        C_{2v}^7 #31 (a^4b^2) & oP16
    ↪  & H2_5 & AsCu3S4 & Enargite & G. Adiwidjaja and J. L"{o}hn,
    ↪ Acta Cryst. B 26, 1878-1879 (1970)
   1.0000000000000000
   7.43000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    6.46000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.18000000000000
   As   Cu   S
    2    6   8
Direct
   0.00000000000000    0.82680000000000    0.00000000000000    As    (2a)
   0.50000000000000    0.17320000000000    0.50000000000000    As    (2a)
   0.00000000000000    0.15140000000000    0.49830000000000    Cu    (2a)
   0.50000000000000    0.84860000000000    0.99830000000000    Cu    (2a)
   0.24660000000000    0.32550000000000    0.98660000000000    Cu    (4b)
   0.25340000000000    0.67450000000000    0.48660000000000    Cu    (4b)
   0.74660000000000    0.67450000000000    0.48660000000000    Cu    (4b)
   0.75340000000000    0.32550000000000    0.98660000000000    Cu    (4b)
   0.00000000000000    0.82260000000000    0.64540000000000    S    (2a)
   0.50000000000000    0.17740000000000    0.14540000000000    S    (2a)
   0.00000000000000    0.14360000000000    0.11660000000000    S    (2a)
   0.50000000000000    0.85640000000000    0.61660000000000    S    (2a)
   0.24020000000000    0.66360000000000    0.11840000000000    S    (4b)
   0.25980000000000    0.33640000000000    0.61840000000000    S    (4b)
   0.74020000000000    0.33640000000000    0.61840000000000    S    (4b)
   0.75980000000000    0.66360000000000    0.11840000000000    S    (4b)
```

Modderite (CoAs): AB_oP8_33_a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Modderite'
_chemical_formula_sum 'Co As'

loop_
_publ_author_name
 'P. S. Lyman'
 'C. T. Prewitt'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 40
_journal_year 1984
_journal_page_first 14
_journal_page_last 20
_publ_Section_title
;
 Room- and high-pressure crystal chemistry of CoAs and FeAs
;

_aflow_proto 'AB_oP8_33_a_a'
_aflow_params 'a,b/a,c/a,x1,y1,z1,x2,y2,z2'
_aflow_params_values '5.2857,1.11007056776,0.659950432298,0.1996,0.5867,
    ↪ 0.2506,0.002,0.2003,0.25'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP8'

_symmetry_space_group_name_Hall "P 2c -2n"
_symmetry_space_group_name_H-M "P n a 21"
_symmetry_Int_Tables_number 33

_cell_length_a    5.28570
_cell_length_b    5.86750
_cell_length_c    3.48830
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z+1/2
3 -x+1/2,y+1/2,z+1/2
4 x+1/2,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
As1 As   4 a 0.19960 0.58670 0.25060 1.00000
Co1 Co   4 a 0.00200 0.20030 0.25000 1.00000
```

Modderite (CoAs): AB_oP8_33_a_a - POSCAR

```
AB_oP8_33_a_a & a,b/a,c/a,x1,y1,z1,x2,y2,z2 --params=5.2857,
    ↪ 1.11007056776,0.659950432298,0.1996,0.5867,0.2506,0.002,0.2003,
    ↪ 0.25 & Pna2_1     C_{2v}^9 #33 (a^2) & oP8 & & CoAs & Modderite
    ↪ & P. S. Lyman and C. T. Prewitt, Acta Cryst. B 40, 14-20 (1984
    ↪ )
   1.0000000000000000
   5.28570000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.86750000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.48830000000000
   As    Co
    4     4
Direct
   0.19960000000000    0.58670000000000    0.25060000000000    As    (4a)
   0.30040000000000    0.08670000000000    0.75060000000000    As    (4a)
   0.69960000000000   -0.08670000000000    0.25060000000000    As    (4a)
   0.80040000000000    0.41330000000000    0.75060000000000    As    (4a)
   0.00200000000000    0.20030000000000    0.25000000000000    Co    (4a)
  -0.00200000000000    0.79970000000000    0.75000000000000    Co    (4a)
   0.49800000000000    0.70030000000000    0.75000000000000    Co    (4a)
   0.50200000000000    0.29970000000000    0.25000000000000    Co    (4a)
```

AsK_3S_4: AB3C4_oP32_33_a_3a_4a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'As K3 S4'

loop_
_publ_author_name
 'M. Palazzi'
 'S. Jaulmes'
 'P. Laruelle'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 30
_journal_year 1974
_journal_page_first 2378
_journal_page_last 2381
_publ_Section_title
;
 Structure cristalline de K$_3$AsS$_4$
;

# Found in Pearson's Handbook, Vol. I, p. 1164

_aflow_proto 'AB3C4_oP32_33_a_3a_4a'
_aflow_params 'a,b/a,c/a,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6
    ↪ ,y6,z6,x7,y7,z7,x8,y8,z8'
_aflow_params_values '9.11,1.01866081229,1.1613611416,0.2187,0.4807,
    ↪ 0.2031,0.4418,0.2052,0.0015,0.4488,0.1967,0.4146,0.1422,0.9176,
    ↪ 0.2246,0.191,0.2506,0.2228,0.3424,0.5361,0.0415,0.0069,0.5876,
    ↪ 0.2212,0.3355,0.546,0.3761'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP32'

_symmetry_space_group_name_Hall "P 2c -2n"
_symmetry_space_group_name_H-M "P n a 21"
_symmetry_Int_Tables_number 33

_cell_length_a    9.11000
_cell_length_b    9.28000
_cell_length_c    10.58000
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z+1/2
3 -x+1/2,y+1/2,z+1/2
4 x+1/2,-y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
As1 As   4 a 0.21870 0.48070 0.20310 1.00000
K1  K    4 a 0.44180 0.20520 0.00150 1.00000
K2  K    4 a 0.44880 0.19670 0.41460 1.00000
K3  K    4 a 0.14220 0.91760 0.22460 1.00000
S1  S    4 a 0.19100 0.25060 0.22280 1.00000
S2  S    4 a 0.34240 0.53610 0.04150 1.00000
S3  S    4 a 0.00690 0.58760 0.22120 1.00000
S4  S    4 a 0.33550 0.54600 0.37610 1.00000
```

AsK_3S_4: AB3C4_oP32_33_a_3a_4a - POSCAR

```
AB3C4_oP32_33_a_3a_4a & a,b/a,c/a,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5
    ↪ ,y5,z5,x6,y6,z6,x7,y7,z7,x8,y8,z8 --params=9.11,1.01866081229,
    ↪ 1.1613611416,0.2187,0.4807,0.2031,0.4418,0.2052,0.0015,0.4488,
    ↪ 0.1967,0.4146,0.1422,0.9176,0.2246,0.191,0.2506,0.2228,0.3424,
    ↪ 0.5361,0.0415,0.0069,0.5876,0.2212,0.3355,0.546,0.3761 & Pna2_1
    ↪     C_{2v}^9 #33 (a^8) & oP32 & & AsK3S4 & & M. Palazzi, S.
    ↪ Jaulmes and P. Laruelle, Acta Cryst. B 30, 2378-2381 (1974)
   1.0000000000000000
   9.11000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    9.28000000000000    0.00000000000000
   0.00000000000000    0.00000000000000   10.58000000000000
   As    K    S
    4   12   16
Direct
   0.21870000000000    0.48070000000000    0.20310000000000    As    (4a)
   0.28130000000000   -0.01930000000000    0.70310000000000    As    (4a)
   0.71870000000000    0.01930000000000    0.20310000000000    As    (4a)
   0.78130000000000    0.51930000000000    0.70310000000000    As    (4a)
   0.05820000000000    0.70520000000000    0.50150000000000    K    (4a)
   0.44180000000000    0.20520000000000    0.00150000000000    K    (4a)
  -0.44180000000000    0.79480000000000    0.50150000000000    K    (4a)
   0.94180000000000    0.29480000000000    0.00150000000000    K    (4a)
   0.05120000000000    0.69670000000000    0.91460000000000    K    (4a)
   0.44880000000000    0.19670000000000    0.41460000000000    K    (4a)
  -0.44880000000000    0.80330000000000    0.91460000000000    K    (4a)
   0.94880000000000    0.30330000000000    0.41460000000000    K    (4a)
  -0.14220000000000    0.08240000000000    0.72460000000000    K    (4a)
   0.14220000000000    0.91760000000000    0.22460000000000    K    (4a)
   0.35780000000000    0.41760000000000    0.72460000000000    K    (4a)
   0.64220000000000   -0.41760000000000    0.22460000000000    K    (4a)
   0.19100000000000    0.25060000000000    0.22280000000000    S    (4a)
  -0.19100000000000    0.74940000000000    0.72280000000000    S    (4a)
   0.30900000000000    0.75060000000000    0.72280000000000    S    (4a)
   0.69100000000000    0.24940000000000    0.22280000000000    S    (4a)
   0.15760000000000    0.03610000000000    0.54150000000000    S    (4a)
  -0.34240000000000    0.46390000000000    0.54150000000000    S    (4a)
   0.34240000000000    0.53610000000000    0.04150000000000    S    (4a)
   0.84240000000000   -0.03610000000000    0.04150000000000    S    (4a)
  -0.00690000000000    0.41240000000000    0.72120000000000    S    (4a)
   0.00690000000000    0.58760000000000    0.22120000000000    S    (4a)
   0.49310000000000    0.08760000000000    0.72120000000000    S    (4a)
   0.50690000000000   -0.08760000000000    0.22120000000000    S    (4a)
   0.16450000000000    0.04600000000000    0.87610000000000    S    (4a)
```

```
  -0.33550000000000   0.45400000000000   0.87610000000000   S   (4a)
   0.33550000000000   0.54600000000000   0.37610000000000   S   (4a)
   0.83550000000000  -0.04600000000000   0.37610000000000   S   (4a)
```

$HgBr_2$ (C24): A2B_oC12_36_2a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Hg Br2'

loop_
_publ_author_name
 'H. Braekken'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 81
_journal_year 1932
_journal_page_first 152
_journal_page_last 154
_publ_Section_title
;
 Zur Kristallstruktur des Quecksilberbromids HgBr$_2$
;

# Found in  AMS Database

_aflow_proto 'A2B_oC12_36_2a_a'
_aflow_params 'a,b/a,c/a,y1,z1,y2,z2,y3,z3'
_aflow_params_values '4.624,1.46820934256,2.69139273356,0.333,0.0,0.061,
    ↪ 0.134,0.395,0.366'
_aflow_Strukturbericht 'C24'
_aflow_Pearson 'oC12'

_symmetry_space_group_name_Hall "C 2c -2"
_symmetry_space_group_name_H-M "C m c 21"
_symmetry_Int_Tables_number 36

_cell_length_a     4.62400
_cell_length_b     6.78900
_cell_length_c     12.44500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z+1/2
3 -x,y,z
4 x,-y,z+1/2
5 x+1/2,y+1/2,z
6 -x+1/2,-y+1/2,z+1/2
7 -x+1/2,y+1/2,z
8 x+1/2,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Br1 Br   4 a 0.00000 0.33300 0.00000 1.00000
Br2 Br   4 a 0.00000 0.06100 0.13400 1.00000
Hg1 Hg   4 a 0.00000 0.39500 0.36600 1.00000
```

$HgBr_2$ (C24): A2B_oC12_36_2a_a - POSCAR

```
A2B_oC12_36_2a_a & a,b/a,c/a,y1,z1,y2,z2,y3,z3 --params=4.624,
    ↪ 1.46820934256,2.69139273356,0.333,0.0,0.061,0.134,0.395,0.366 &
    ↪  Cmc2_1     C_{2v}^{12} #36 (a^3) & oC12 & C24 & HgBr2 & & H.
    ↪ Braekken, Zeitschrift f\"{u}r Kristallographie - Crystalline
    ↪ Materials 81, 152-154 (1932)
  1.0000000000000000
  2.31200000000000  -3.39450000000000   0.00000000000000
  2.31200000000000   3.39450000000000   0.00000000000000
  0.00000000000000   0.00000000000000  12.44500000000000
  Br   Hg
   4    2
Direct
  0.33300000000000   0.66700000000000   0.50000000000000   Br   (4a)
  0.66700000000000   0.33300000000000   0.00000000000000   Br   (4a)
 -0.06100000000000   0.06100000000000   0.13400000000000   Br   (4a)
  0.06100000000000  -0.06100000000000   0.63400000000000   Br   (4a)
  0.39500000000000   0.60500000000000   0.86600000000000   Hg   (4a)
  0.60500000000000   0.39500000000000   0.36600000000000   Hg   (4a)
```

C_2CeNi: A2BC_oC8_38_e_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'C2 Ce Ni'

loop_
_publ_author_name
 'O. Yi. Bodak'
 'Je. P. Marusin'
_journal_name_full
;
Dopovidi Akademii Nauk Ukrains'koj RSR Seriya A, Fiziko-Tekhnichni ta
    ↪ Matematichni Nauki
;
_journal_volume 12
_journal_year 1979
_journal_page_first 1048
_journal_page_last 1050
_publ_Section_title
;
 The Crystal Structure of RNiC$_2$ Compounds (R=Ce,La,Pr)
;

# Found in  Pearson's Handbook II, 1858-1859

_aflow_proto 'A2BC_oC8_38_e_a_b'
_aflow_params 'a,b/a,c/a,z1,z2,y3,z3'
_aflow_params_values '3.875,1.17470967742,1.59019354839,0.0,0.6144,0.155
    ↪ ,0.2914'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oC8'

_symmetry_space_group_name_Hall "A 2 -2"
_symmetry_space_group_name_H-M "A m m 2"
_symmetry_Int_Tables_number 38

_cell_length_a     3.87500
_cell_length_b     4.55200
_cell_length_c     6.16200
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 x,-y,z
4 -x,y,z
5 x,y+1/2,z+1/2
6 -x,-y+1/2,z+1/2
7 x,-y+1/2,z+1/2
8 -x,y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ce1 Ce   2 a 0.00000 0.00000 0.00000 1.00000
Ni1 Ni   2 b 0.50000 0.00000 0.61440 1.00000
C1  C    4 e 0.50000 0.15500 0.29140 1.00000
```

C_2CeNi: A2BC_oC8_38_e_a_b - POSCAR

```
A2BC_oC8_38_e_a_b & a,b/a,c/a,z1,z2,y3,z3 --params=3.875,1.17470967742,
    ↪ 1.59019354839,0.0,0.6144,0.155,0.2914 & Amm2      C_{2v}^{14} #
    ↪ 38 (abe) & oC8 & & C2CeNi & & O. I. Bodak and E. P. Marusin,
    ↪ Dopovidia Akademii Nauk Ukrains'koi RSR, Seriya A:
    ↪ Fiziko_Matematichni Ta Tekhnichni Nauki 12, 1048-1050 (1979)
  1.0000000000000000
  3.87500000000000   0.00000000000000   0.00000000000000
  0.00000000000000   2.27600000000000  -3.08100000000000
  0.00000000000000   2.27600000000000   3.08100000000000
  C   Ce   Ni
  2    1    1
Direct
  0.50000000000000   0.55360000000000   0.13640000000000   C   (4e)
  0.50000000000000   0.86360000000000   0.44640000000000   C   (4e)
  0.00000000000000   0.00000000000000   0.00000000000000   Ce  (2a)
  0.50000000000000   0.38560000000000   0.61440000000000   Ni  (2b)
```

Au_2V: A2B_oC12_38_de_ab - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Au2 V'

loop_
_publ_author_name
 'E. Stolz'
 'K. Schubert'
_journal_name_full
;
Zeitschrift f\"{u}r Metallkunde
;
_journal_volume 53
_journal_year 1962
_journal_page_first 433
```

```
_journal_page_last 444
_publ_Section_title
;
 Strukturuntersuchungen in einigen zu T$^4$-B$^1$ homologen und
      ↪ quasihomologen Systemen
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
      ↪ sd_1250637

_aflow_proto 'A2B_oC12_38_de_ab'
_aflow_params 'a,b/a,c/a,z1,z2,y3,z3,y4,z4'
_aflow_params_values '4.684,1.81084543126,1.0269000854,0.06,0.5,0.17,
      ↪ 0.56,0.17,0.0'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oC12'

_symmetry_space_group_name_Hall "A 2 -2"
_symmetry_space_group_name_H-M "A m m 2"
_symmetry_Int_Tables_number 38

_cell_length_a      4.68400
_cell_length_b      8.48200
_cell_length_c      4.81000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 x,-y,z
4 -x,y,z
5 x,y+1/2,z+1/2
6 -x,-y+1/2,z+1/2
7 x,-y+1/2,z+1/2
8 -x,y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
V1  V    2 a 0.00000 0.00000 0.06000 1.00000
V2  V    2 b 0.50000 0.00000 0.50000 1.00000
Au1 Au   4 d 0.00000 0.17000 0.56000 1.00000
Au2 Au   4 e 0.50000 0.17000 0.00000 1.00000
```

Au_2V: A2B_oC12_38_de_ab - POSCAR

```
A2B_oC12_38_de_ab & a,b/a,c/a,z1,z2,y3,z3,y4,z4 --params=4.684,
      ↪ 1.81084543126,1.0269000854,0.06,0.5,0.17,0.56,0.17,0.0 & Amm2
      ↪        C_{2v}^{14} #38 (abde) & oC12 & & Au2V & & Stolz and
      ↪ Schubert, Z. Metallkd. 53, 433-444 (1962)
   1.0000000000000000
   4.68400000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.24100000000000   -2.40500000000000
   0.00000000000000    4.24100000000000    2.40500000000000
   Au    V
    4    2
Direct
   0.00000000000000   -0.39000000000000    0.73000000000000   Au    (4d)
   0.00000000000000   -0.73000000000000    0.39000000000000   Au    (4d)
   0.50000000000000    0.17500000000000    0.17500000000000   Au    (4e)
   0.50000000000000   -0.17500000000000   -0.17500000000000   Au    (4e)
   0.00000000000000   -0.06000000000000    0.06000000000000    V    (2a)
   0.50000000000000   -0.50000000000000    0.50000000000000    V    (2b)
```

$PtSn_4$: AB4_oC20_41_a_2b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Pt Sn4'

loop_
_publ_author_name
 'K. Schubert'
 'U. R\"{o}sler'
_journal_name_full
;
Zeitschrift f\"{u}r Metallkunde
;
_journal_volume 41
_journal_year 1950
_journal_page_first 298
_journal_page_last 300
_publ_Section_title
;
 Die Kristallstruktur von PtSn$_4$
;

# Found in  Pearson's Handbook IV, p. 5001

_aflow_proto 'AB4_oC20_41_a_2b'
_aflow_params 'a,b/a,c/a,z1,x2,y2,z2,x3,y3,z3'
_aflow_params_values '6.388,1.00485284909,1.7778647464,0.0,0.673,0.327,
      ↪ 0.376,0.827,0.673,0.125'
_aflow_Strukturbericht 'D1_c'
_aflow_Pearson 'oC20'

_symmetry_space_group_name_Hall "A 2 -2ac"
_symmetry_space_group_name_H-M "A b a 2"
_symmetry_Int_Tables_number 41

_cell_length_a      6.38800
_cell_length_b      6.41900
_cell_length_c      11.35700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 x+1/2,-y,z+1/2
4 -x+1/2,y,z+1/2
5 x,y+1/2,z+1/2
6 -x,-y+1/2,z+1/2
7 x+1/2,-y+1/2,z
8 -x+1/2,y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pt1 Pt   4 a 0.00000 0.00000 0.00000 1.00000
Sn1 Sn   8 b 0.67300 0.32700 0.37600 1.00000
Sn2 Sn   8 b 0.82700 0.67300 0.12500 1.00000
```

$PtSn_4$: AB4_oC20_41_a_2b - POSCAR

```
AB4_oC20_41_a_2b & a,b/a,c/a,z1,x2,y2,z2,x3,y3,z3 --params=6.388,
      ↪ 1.00485284909,1.7778647464,0.0,0.673,0.327,0.376,0.827,0.673,
      ↪ 0.125 & Aba2          C_{2v}^{17} #41 (ab^2) & oC20 & D1_c &
      ↪ PtSn4 & & K. Schubert and U. R"{o}sler, Z. Metallkd. 41,
      ↪ 298-300 (1950)
   1.0000000000000000
   6.38800000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.20950000000000   -5.67850000000000
   0.00000000000000    3.20950000000000    5.67850000000000
   Pt    Sn
    2     8
Direct
   0.00000000000000    0.00000000000000    0.00000000000000   Pt    (4a)
   0.50000000000000    0.50000000000000    0.50000000000000   Pt    (4a)
   0.17300000000000    0.20200000000000    0.45200000000000   Sn    (8b)
   0.32700000000000    0.70200000000000   -0.04800000000000   Sn    (8b)
   0.67300000000000    0.04800000000000    0.29800000000000   Sn    (8b)
   0.82700000000000    0.54800000000000    0.79800000000000   Sn    (8b)
   0.17300000000000    0.79700000000000    0.54900000000000   Sn    (8b)
   0.32700000000000    0.29700000000000    0.04900000000000   Sn    (8b)
   0.67300000000000   -0.04900000000000    0.70300000000000   Sn    (8b)
   0.82700000000000    0.45100000000000    0.20300000000000   Sn    (8b)
```

$PdSn_2$ (C_e): AB2_oC24_41_2a_2b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Pd Sn2'

loop_
_publ_author_name
 'K. Schubert'
 'H. Pfisterer'
_journal_name_full
;
Zeitschrift f\"{u}r Metallkunde
;
_journal_volume 41
_journal_year 1950
_journal_page_first 433
_journal_page_last 441
_publ_Section_title
;
 Zur Kristallchemie der B-Metall-reichsten Phasen in Legierungen von \"{
      ↪ U}"bergangsmetallen der Eisen- und Platintriaden mit Elementen
      ↪  der vierten Nebengruppe
;

# Found in  Pearson's Handbook IV, p. 4929-4930

_aflow_proto 'AB2_oC24_41_2a_2b'
_aflow_params 'a,b/a,c/a,z1,z2,x3,y3,z3,x4,y4,z4'
_aflow_params_values '6.478,1.0,1.87635072553,0.01,0.238,0.342,0.158,
      ↪ 0.125,0.25,0.25,-0.125'
_aflow_Strukturbericht 'C_e'
_aflow_Pearson 'oC24'

_symmetry_space_group_name_Hall "A 2 -2ac"
```

```
_symmetry_space_group_name_H-M "A b a 2"
_symmetry_Int_Tables_number 41

_cell_length_a      6.47800
_cell_length_b      6.47800
_cell_length_c      12.15500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 x+1/2,-y,z+1/2
4 -x+1/2,y,z+1/2
5 x,y+1/2,z+1/2
6 -x,-y+1/2,z+1/2
7 x+1/2,-y+1/2,z
8 -x+1/2,y+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pd1 Pd    4 a 0.00000  0.00000  0.01000  1.00000
Pd2 Pd    4 a 0.00000  0.00000  0.23800  1.00000
Sn1 Sn    8 b 0.34200  0.15800  0.12500  1.00000
Sn2 Sn    8 b 0.25000  0.25000 -0.12500  1.00000
```

$PdSn_2$ (C_e): AB2_oC24_41_2a_2b - POSCAR

```
AB2_oC24_41_2a_2b & a,b/a,c/a,z1,z2,x3,y3,z3,x4,y4,z4 --params=6.478,1.0
      ↪ ,1.87635072553,0.01,0.238,0.342,0.158,0.125,0.25,0.25,-0.125 &
      ↪ Aba2        C_{2v}^{17} #41 (a^2b^2) & oC24 & C_e & PdSn2 & & K.
      ↪ Schubert and H. Pfisterer, Z. Metallkd. 41, 433-441 (1950)
   1.0000000000000000
   6.47800000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.23900000000000   -6.07750000000000
   0.00000000000000    3.23900000000000    6.07750000000000
   Pd    Sn
    4     8
Direct
   0.00000000000000   -0.01000000000000    0.01000000000000    Pd    (4a)
   0.50000000000000    0.49000000000000    0.51000000000000    Pd    (4a)
   0.00000000000000    0.76200000000000    0.23800000000000    Pd    (4a)
   0.50000000000000    0.26200000000000    0.73800000000000    Pd    (4a)
   0.15800000000000    0.53300000000000    0.78300000000000    Sn    (8b)
   0.34200000000000    0.03300000000000    0.28300000000000    Sn    (8b)
   0.65800000000000    0.71700000000000   -0.03300000000000    Sn    (8b)
   0.84200000000000    0.21700000000000    0.46700000000000    Sn    (8b)
   0.25000000000000    0.37500000000000    0.12500000000000    Sn    (8b)
   0.25000000000000    0.87500000000000    0.62500000000000    Sn    (8b)
   0.75000000000000    0.37500000000000    0.12500000000000    Sn    (8b)
   0.75000000000000    0.87500000000000    0.62500000000000    Sn    (8b)
```

GeS_2 (C44): AB2_oF72_43_ab_3b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Germanium disuphide'
_chemical_formula_sum 'Ge S2'

loop_
_publ_author_name
 'W. H. Zachariasen'
_journal_name_full
;
Journal of Chemical Physics
;
_journal_volume 4
_journal_year 1936
_journal_page_first 618
_journal_page_last 619
_publ_Section_title
;
 The Crystal Structure of Germanium Disulphide
;

# Found in  AMS Database

_aflow_proto 'AB2_oF72_43_ab_3b'
_aflow_params 'a,b/a,c/a,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5'
_aflow_params_values '11.66,1.91595197256,0.58833619211,0.0,0.125,
      ↪ 0.13889,0.0,0.02222,0.08056,0.18333,0.15278,-0.01389,-0.18333,
      ↪ 0.0625,0.125,0.27778'
_aflow_Strukturbericht 'C44'
_aflow_Pearson 'oF72'

_symmetry_space_group_name_Hall "F 2 -2d"
_symmetry_space_group_name_H-M "F d d 2"
_symmetry_Int_Tables_number 43

_cell_length_a      11.66000
_cell_length_b      22.34000
_cell_length_c      6.86000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 -x+1/4,y+1/4,z+1/4
4 x+1/4,-y+1/4,z+1/4
5 x,y+1/2,z+1/2
6 -x,-y+1/2,z+1/2
7 -x+1/4,y+3/4,z+3/4
8 x+1/4,-y+3/4,z+3/4
9 x+1/2,y,z+1/2
10 -x+1/2,-y,z+1/2
11 -x+3/4,y+1/4,z+3/4
12 x+3/4,-y+1/4,z+3/4
13 x+1/2,y+1/2,z
14 -x+1/2,-y+1/2,z
15 -x+3/4,y+3/4,z+1/4
16 x+3/4,-y+3/4,z+1/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ge1 Ge    8 a 0.00000   0.00000  0.00000  1.00000
Ge2 Ge   16 b 0.12500   0.13889  0.00000  1.00000
S1  S    16 b 0.02222   0.08056  0.18333  1.00000
S2  S    16 b 0.15278  -0.01389  -0.18333  1.00000
S3  S    16 b 0.06250   0.12500  0.27778  1.00000
```

GeS_2 (C44): AB2_oF72_43_ab_3b - POSCAR

```
AB2_oF72_43_ab_3b & a,b/a,c/a,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5 --
      ↪ params=11.66,1.91595197256,0.58833619211,0.0,0.125,0.13889,0.0,
      ↪ 0.02222,0.08056,0.18333,0.15278,-0.01389,-0.18333,0.0625,0.125,
      ↪ 0.27778 & Fdd2        C_{2v}^{16} #43 (ab^4) & oF72 & C44 & GeS2
      ↪ & & W. H. Zachariassen, J. Chem. Phys. 4, 618-619 (1936)
   1.0000000000000000
   0.00000000000000   11.17000000000000    3.43000000000000
   5.83000000000000    0.00000000000000    3.43000000000000
   5.83000000000000   11.17000000000000    0.00000000000000
   Ge     S
    6    12
Direct
   0.01388888888889   -0.01388888888889    0.26388888888889    Ge    (16b)
  -0.01388888888889    0.01388888888889    0.73611111111111    Ge    (16b)
  -0.01388888888889    0.51388888888889    0.23611111111111    Ge    (16b)
   0.51388888888889   -0.01388888888889    0.26388888888889    Ge    (16b)
   0.00000000000000    0.00000000000000    0.00000000000000    Ge     (8a)
   0.25000000000000    0.25000000000000    0.25000000000000    Ge     (8a)
   0.12500000000000    0.24166666666667    0.71388888888889     S    (16b)
   0.24166666666667    0.12500000000000   -0.08055555555556     S    (16b)
   0.33055555555556    0.53611111111111    0.00833333333333     S    (16b)
   0.53611111111111    0.33055555555556    0.12500000000000     S    (16b)
  -0.01666666666667    0.65000000000000    0.04444444444444     S    (16b)
  -0.07222222222222    0.20555555555556    0.60000000000000     S    (16b)
   0.20555555555556   -0.07222222222222    0.26666666666667     S    (16b)
   0.65000000000000   -0.01666666666667    0.32222222222222     S    (16b)
   0.21527777777778    0.34027777777778    0.53472222222222     S    (16b)
   0.34027777777778    0.21527777777778   -0.09027777777778     S    (16b)
   0.34027777777778    0.71527777777778   -0.09027777777778     S    (16b)
   0.71527777777778    0.34027777777778    0.03472222222222     S    (16b)
```

High-pressure GaAs: AB_oI4_44_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ga As'

loop_
_publ_author_name
 'Samuel T. Weir'
 'Yogesh K. Vohra'
 'Craig A. Vanderborgh'
 'Arthur L. Ruoff'
_journal_name_full
;
Physical Review B
;
_journal_volume 39
_journal_year 1989
_journal_page_first 1280
_journal_page_last 1285
_publ_Section_title
;
 Structural phase transitions in GaAs to 108 GPa
;

# Found in  Pearson's Handbook I, p. 1135

_aflow_proto 'AB_oI4_44_a_b'
_aflow_params 'a,b/a,c/a,z1,z2'
```

```
_aflow_params_values '4.92,0.973577235772,0.535569105691,0.0,0.425'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oI4'

_symmetry_space_group_name_Hall "I 2 -2"
_symmetry_space_group_name_H-M "I m m 2"
_symmetry_Int_Tables_number 44

_cell_length_a      4.92000
_cell_length_b      4.79000
_cell_length_c      2.63500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 -x,y,z
4 x,-y,z
5 x+1/2,y+1/2,z+1/2
6 -x+1/2,-y+1/2,z+1/2
7 -x+1/2,y+1/2,z+1/2
8 x+1/2,-y+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
As1 As    2 a 0.00000 0.00000 0.00000   1.00000
Ga1 Ga    2 b 0.00000 0.50000 0.42500   1.00000
```

High-pressure GaAs: AB_oI4_44_a_b - POSCAR

```
AB_oI4_44_a_b & a,b/a,c/a,z1,z2 --params=4.92,0.973577235772,
    ↪ 0.535569105691,0.0,0.425 & Imm2      C_{2v}^{20} #44 (ab) & oI4
    ↪ & & GaAs & III, 28.1 GPa & S. Weir et al., PRB 39, 1280-1285 (
    ↪ 1989)
   1.0000000000000000
  -2.46000000000000    2.39500000000000    1.31750000000000
   2.46000000000000   -2.39500000000000    1.31750000000000
   2.46000000000000    2.39500000000000   -1.31750000000000
   As    Ga
    1     1
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    As    (2a)
   0.92500000000000    0.42500000000000    0.50000000000000    Ga    (2b)
```

1212C [$YBa_2Cu_3O_{7-x}$]: A2B3C7D_oP13_47_t_aq_eqrs_h - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ba2 Cu3 O7 Y'

loop_
_publ_author_name
 'W. I. F. David'
 'W. T. A. Harrison'
 'J. M. F. Gunn'
 'O. Moze, A. K. Soper'
 'P. Day'
 'J. D. Jorgensen'
 'D. G. Hinks'
 'M. A. Beno'
 'L. Soderholm'
 'D. W. Capone II'
 'I. K. Schuller'
 'C. U. Segre'
 'K. Zhang'
 'J. D. Grace'
_journal_name_full
;
Nature
;
_journal_volume 327
_journal_year 1987
_journal_page_first 310
_journal_page_last 312
_publ_Section_title
;
 Structure and crystal chemistry of the high-Tc superconductor
    ↪ YBa$_2$Cu$_3$O$_{7-x}$
;

_aflow_proto 'A2B3C7D_oP13_47_t_aq_eqrs_h'
_aflow_params 'a,b/a,c/a,z4,z5,z6,z7,z8'
_aflow_params_values '3.8187,1.01691675177,3.05567339671,0.3554,0.1579,
    ↪ 0.3771,0.3788,0.18445'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP13'

_symmetry_space_group_name_Hall "-P 2 2"
_symmetry_space_group_name_H-M "P m m m"
_symmetry_Int_Tables_number 47

_cell_length_a      3.81870
_cell_length_b      3.88330
_cell_length_c     11.66870
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -x,-y,-z
6 -x,y,z
7 x,-y,z
8 x,y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    1 a 0.00000 0.00000 0.00000 1.00000
O1  O     1 e 0.00000 0.50000 0.00000 1.00000
Y1  Y     1 h 0.50000 0.50000 0.50000 1.00000
Cu2 Cu    2 q 0.00000 0.00000 0.35540 1.00000
O2  O     2 q 0.00000 0.00000 0.15790 1.00000
O3  O     2 r 0.00000 0.50000 0.37710 1.00000
O4  O     2 s 0.50000 0.00000 0.37880 1.00000
Ba1 Ba    2 t 0.50000 0.50000 0.18445 1.00000
```

1212C [$YBa_2Cu_3O_{7-x}$]: A2B3C7D_oP13_47_t_aq_eqrs_h - POSCAR

```
A2B3C7D_oP13_47_t_aq_eqrs_h & a,b/a,c/a,z4,z5,z6,z7,z8 --params=3.8187,
    ↪ 1.01691675177,3.05567339671,0.3554,0.1579,0.3771,0.3788,0.18445
    ↪ & Pmmm      D_{2h}^{7} #47 (aehq^2rst) & oP13 & Ba2Cu3O(7-x
    ↪ ) & & David et al., Nature 327, 310-312 (1987)
   1.0000000000000000
   3.81870000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.88330000000000    0.00000000000000
   0.00000000000000    0.00000000000000   11.66870000000000
   Ba    Cu    O    Y
    2     3    7    1
Direct
   0.50000000000000    0.50000000000000    0.18445000000000    Ba    (2t)
   0.50000000000000    0.50000000000000    0.81555000000000    Ba    (2t)
   0.00000000000000    0.00000000000000    0.00000000000000    Cu    (1a)
   0.00000000000000    0.00000000000000    0.35540000000000    Cu    (2q)
   0.00000000000000    0.00000000000000    0.64460000000000    Cu    (2q)
   0.00000000000000    0.50000000000000    0.00000000000000    O     (1e)
   0.00000000000000    0.00000000000000    0.15790000000000    O     (2q)
   0.00000000000000    0.00000000000000    0.84210000000000    O     (2q)
   0.00000000000000    0.50000000000000    0.37710000000000    O     (2r)
   0.00000000000000    0.50000000000000    0.62290000000000    O     (2r)
   0.50000000000000    0.00000000000000    0.37880000000000    O     (2s)
   0.50000000000000    0.00000000000000    0.62120000000000    O     (2s)
   0.50000000000000    0.50000000000000    0.50000000000000    Y     (1h)
```

β'-AuCd (B19): AB_oP4_51_e_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta-prime cadmium gold'
_chemical_formula_sum 'Au Cd'

loop_
_publ_author_name
 'L.-C. Chang'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 4
_journal_year 1951
_journal_page_first 320
_journal_page_last 324
_publ_Section_title
;
 Atomic displacements and crystallographic mechanisms in diffusionless
    ↪ transformation of gold-cadium single crystals containing 47.5
    ↪ atomic per cent cadmium
;

# Found in  Pearson, Alloys, p. 313-314

_aflow_proto 'AB_oP4_51_e_f'
_aflow_params 'a,b/a,c/a,z1,z2'
_aflow_params_values '4.7549,0.661969757513,1.0209678437,0.8125,0.3125'
_aflow_Strukturbericht 'B19'
_aflow_Pearson 'oP4'

_symmetry_space_group_name_Hall "-P 2a 2a"
_symmetry_space_group_name_H-M "P m m a"
_symmetry_Int_Tables_number 51
```

```
_cell_length_a      4.75490
_cell_length_b      3.14760
_cell_length_c      4.85460
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z
3 -x,y,-z
4 -x+1/2,-y,z
5 -x,-y,-z
6 -x+1/2,y,z
7 x,-y,z
8 x+1/2,y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Au1 Au    2 e 0.25000 0.00000 0.81250 1.00000
Cd1 Cd    2 f 0.25000 0.50000 0.31250 1.00000
```

β'-AuCd (B19): AB_oP4_51_e_f - POSCAR

```
AB_oP4_51_e_f & a,b/a,c/a,z1,z2 --params=4.7549,0.661969757513,
    ↪ 1.0209678437,0.8125,0.3125 & Pmma      D_{2h}^5 #51 (ef) & oP4
    ↪ & B19 & AuCd (beta') && L.-C. Chang, Acta Cryst., 320-324 (
    ↪ 1951)
   1.0000000000000000
   4.75490000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.14760000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.85460000000000
   Au    Cd
    2     2
Direct
   0.25000000000000    0.00000000000000    0.81250000000000    Au    (2e)
   0.75000000000000    0.00000000000000    0.18750000000000    Au    (2e)
   0.25000000000000    0.50000000000000    0.31250000000000    Cd    (2f)
   0.75000000000000    0.50000000000000    0.68750000000000    Cd    (2f)
```

Sb_2O_3 ($D5_{11}$): A3B2_oP20_56_ce_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Antimony trioxide'
_chemical_formula_sum 'Sb2 O3'

loop_
_publ_author_name
 'C. Svensson'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 30
_journal_year 1974
_journal_page_first 458
_journal_page_last 461
_publ_Section_title
;
 The crystal structure of orthorhombic antimony trioxide, Sb$_2$O$_3$
;
# Found in AMS Database

_aflow_proto 'A3B2_oP20_56_ce_e'
_aflow_params 'a,b/a,c/a,z1,x2,y2,z2,x3,y3,z3'
_aflow_params_values '4.911,2.53797597231,1.10201588271,0.029,0.147,
    ↪ 0.058,0.861,0.044,0.128,0.179'
_aflow_Strukturbericht 'D5_11'
_aflow_Pearson 'oP20'

_symmetry_space_group_name_Hall "-P 2ab 2ac"
_symmetry_space_group_name_H-M "P c c n"
_symmetry_Int_Tables_number 56

_cell_length_a      4.91100
_cell_length_b      12.46400
_cell_length_c      5.41200
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z+1/2
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y+1/2,z
5 -x,-y,-z
6 -x+1/2,y,z+1/2
7 x,-y+1/2,z+1/2
8 x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O    4 c 0.25000 0.25000 0.02900 1.00000
O2  O    8 e 0.14700 0.05800 0.86100 1.00000
Sb1 Sb   8 e 0.04400 0.12800 0.17900 1.00000
```

Sb_2O_3 ($D5_{11}$): A3B2_oP20_56_ce_e - POSCAR

```
A3B2_oP20_56_ce_e & a,b/a,c/a,z1,x2,y2,z2,x3,y3,z3 --params=4.911,
    ↪ 2.53797597231,1.10201588271,0.029,0.147,0.058,0.861,0.044,0.128
    ↪ ,0.179 & Pccn      D_{2h}^{10} #56 (ce^2) & oP20 & D5_{11} &
    ↪ Sb2O3 && C. Svensson, Acta Cryst. B 30, 458-461 (1974)
   1.0000000000000000
   4.91100000000000    0.00000000000000    0.00000000000000
   0.00000000000000   12.46400000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.41200000000000
    O    Sb
   12     8
Direct
   0.25000000000000    0.25000000000000    0.02900000000000    O    (4c)
   0.25000000000000    0.25000000000000    0.52900000000000    O    (4c)
   0.75000000000000    0.75000000000000    0.47100000000000    O    (4c)
   0.75000000000000    0.75000000000000    0.97100000000000    O    (4c)
   0.14700000000000    0.05800000000000   -0.13900000000000    O    (8e)
   0.14700000000000    0.44200000000000    0.36100000000000    O    (8e)
   0.35300000000000    0.05800000000000    0.36100000000000    O    (8e)
   0.35300000000000    0.44200000000000   -0.13900000000000    O    (8e)
   0.64700000000000    0.55800000000000    0.13900000000000    O    (8e)
   0.64700000000000    0.94200000000000    0.63900000000000    O    (8e)
   0.85300000000000    0.55800000000000    0.63900000000000    O    (8e)
   0.85300000000000    0.94200000000000    0.13900000000000    O    (8e)
   0.04400000000000    0.12800000000000    0.17900000000000   Sb    (8e)
   0.04400000000000    0.37200000000000    0.67900000000000   Sb    (8e)
   0.45600000000000    0.12800000000000    0.67900000000000   Sb    (8e)
   0.45600000000000    0.37200000000000    0.17900000000000   Sb    (8e)
   0.54400000000000    0.62800000000000    0.82100000000000   Sb    (8e)
   0.54400000000000    0.87200000000000    0.32100000000000   Sb    (8e)
   0.95600000000000    0.62800000000000    0.32100000000000   Sb    (8e)
   0.95600000000000    0.87200000000000    0.82100000000000   Sb    (8e)
```

KCNS ($F5_9$): ABCD_oP16_57_d_c_d_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Potassium thiocyanate'
_chemical_formula_sum 'K C N S'

loop_
_publ_author_name
 'D. J. Cookson'
 'M. M. Elcombe'
 'T. R. Finlayson'
_journal_name_full
;
Journal of Physics: Condensed Matter
;
_journal_volume 4
_journal_year 1992
_journal_page_first 7851
_journal_page_last 7864
_publ_Section_title
;
 Phonon dispersion relations for potassium thiocyanate at and above room
    ↪ temperature
;

# Found in http://materials.springer.com/lb/docs/
    ↪ sm_lbs_978-3-540-31353-3_141

_aflow_proto 'ABCD_oP16_57_d_c_d_d'
_aflow_params 'a,b/a,c/a,x1,x2,y2,x3,y3,x4,y4'
_aflow_params_values '6.707,0.997614432682,1.13627553303,0.208,0.7704,
    ↪ 0.2871,0.889,0.4154,0.605,0.1087'
_aflow_Strukturbericht 'F5_9'
_aflow_Pearson 'oP16'

_symmetry_space_group_name_Hall "-P 2c 2b"
_symmetry_space_group_name_H-M "P b c m"
_symmetry_Int_Tables_number 57

_cell_length_a      6.70700
_cell_length_b      6.69100
_cell_length_c      7.62100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x,-y,z+1/2
```

```
5 -x,-y,-z
6 -x,y+1/2,z
7 x,-y+1/2,z+1/2
8 x,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
K1 K    4 c 0.20800 0.25000 0.00000 1.00000
C1 C    4 d 0.77040 0.28710 0.25000 1.00000
N1 N    4 d 0.88900 0.41540 0.25000 1.00000
S1 S    4 d 0.60500 0.10870 0.25000 1.00000
```

KCNS ($F5_9$): ABCD_oP16_57_d_c_d_d - POSCAR

```
ABCD_oP16_57_d_c_d_d & a,b/a,c/a,x1,x2,y2,x3,y3,x4,y4 --params=6.707,
    ↪ 0.997614432682,1.13627553303,0.208,0.7704,0.2871,0.889,0.4154,
    ↪ 0.605,0.1087 & Pbcm D_{2h}^{11} #57 (cd^3) & oP16 & F5_9 &
    ↪ KCNS & Potassium thiocyanate & D. J. Cookson, M. M. Elcombe
    ↪ and T. R. Finlayson, J. Phys: Condens. Matter 4, 7851-7864 (
    ↪ 1992)
   1.0000000000000000
   6.70700000000000   0.00000000000000   0.00000000000000
   0.00000000000000   6.69100000000000   0.00000000000000
   0.00000000000000   0.00000000000000   7.62100000000000
    C    K    N    S
    4    4    4    4
Direct
   0.22960000000000   0.71290000000000   0.75000000000000   C    (4d)
   0.22960000000000   0.78710000000000   0.25000000000000   C    (4d)
   0.77040000000000   0.21290000000000   0.75000000000000   C    (4d)
   0.77040000000000   0.28710000000000   0.25000000000000   C    (4d)
   0.20800000000000   0.25000000000000   0.00000000000000   K    (4c)
   0.20800000000000   0.25000000000000   0.50000000000000   K    (4c)
   0.79200000000000   0.75000000000000   0.00000000000000   K    (4c)
   0.79200000000000   0.75000000000000   0.50000000000000   K    (4c)
   0.11100000000000  -0.08460000000000   0.25000000000000   N    (4d)
   0.11100000000000   0.58460000000000   0.75000000000000   N    (4d)
   0.88900000000000   0.08460000000000   0.75000000000000   N    (4d)
   0.88900000000000   0.41540000000000   0.25000000000000   N    (4d)
   0.39500000000000   0.60870000000000   0.25000000000000   S    (4d)
   0.39500000000000   0.89130000000000   0.75000000000000   S    (4d)
   0.60500000000000   0.10870000000000   0.25000000000000   S    (4d)
   0.60500000000000   0.39130000000000   0.75000000000000   S    (4d)
```

TlF-II: AB_oP8_57_d_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'TlF-II'
_chemical_formula_sum 'Tl F'

loop_
_publ_author_name
 'P. Berastegui'
 'S. Hull'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 150
_journal_year 2000
_journal_page_first 266
_journal_page_last 275
_publ_Section_title
;
 The Crystal Structures of Thallium(I) Fluoride
;

_aflow_proto 'AB_oP8_57_d_d'
_aflow_params 'a,b/a,c/a,x1,y1,x2,y2'
_aflow_params_values '6.09556,0.900425883758,0.850291031505,0.8593,
    ↪ 0.0628,0.255,0.0096'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP8'

_symmetry_space_group_name_Hall "-P 2c 2b"
_symmetry_space_group_name_H-M "P b c m"
_symmetry_Int_Tables_number 57

_cell_length_a     6.09556
_cell_length_b     5.48860
_cell_length_c     5.18300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x,-y,z+1/2
5 -x,-y,-z
6 -x,y+1/2,z
7 x,-y+1/2,z+1/2
8 x,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
F1  F    4 d 0.85930 0.06280 0.25000 1.00000
Tl1 Tl   4 d 0.25500 0.00960 0.25000 1.00000
```

TlF-II: AB_oP8_57_d_d - POSCAR

```
AB_oP8_57_d_d & a,b/a,c/a,x1,y1,x2,y2 --params=6.09556,0.900425883758,
    ↪ 0.850291031505,0.8593,0.0628,0.255,0.0096 & Pbcm D_{2h}^{
    ↪ 11} #57 (d^2) & oP8 & & TlF & TlF-II & P. Berastegui and S.
    ↪ Hull, J. Solid State Chem. 150, 266-275 (2000)
   1.0000000000000000
   6.09556000000000   0.00000000000000   0.00000000000000
   0.00000000000000   5.48860000000000   0.00000000000000
   0.00000000000000   0.00000000000000   5.18300000000000
    F    Tl
    4    4
Direct
   0.14070000000000  -0.06280000000000   0.75000000000000   F    (4d)
   0.14070000000000   0.56280000000000   0.25000000000000   F    (4d)
   0.85930000000000   0.06280000000000   0.25000000000000   F    (4d)
   0.85930000000000   0.43720000000000   0.75000000000000   F    (4d)
   0.25500000000000   0.00960000000000   0.25000000000000   Tl   (4d)
   0.25500000000000   0.49040000000000   0.75000000000000   Tl   (4d)
   0.74500000000000  -0.00960000000000   0.75000000000000   Tl   (4d)
   0.74500000000000   0.50960000000000   0.25000000000000   Tl   (4d)
```

Hydrophilite ($CaCl_2$, C35): AB2_oP6_58_a_g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Hydrophilite'
_chemical_formula_sum 'Ca Cl2'

loop_
_publ_author_name
 'A. K. van Bever'
 'W. Nieuwenkamp'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 90
_journal_year 1935
_journal_page_first 374
_journal_page_last 376
_publ_Section_title
;
 Die Kristallstruktur von Calciumchlorid, CaCl$_2$
;

# Found in AMS Database

_aflow_proto 'AB2_oP6_58_a_g'
_aflow_params 'a,b/a,c/a,x2,y2'
_aflow_params_values '6.24,1.03044871795,0.673076923077,0.275,0.325'
_aflow_Strukturbericht 'C35'
_aflow_Pearson 'oP6'

_symmetry_space_group_name_Hall "-P 2 2n"
_symmetry_space_group_name_H-M "P n n m"
_symmetry_Int_Tables_number 58

_cell_length_a     6.24000
_cell_length_b     6.43000
_cell_length_c     4.20000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x+1/2,y+1/2,-z+1/2
4 -x,-y,z
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x+1/2,-y+1/2,z+1/2
8 x,y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ca1 Ca   2 a 0.00000 0.00000 0.00000 1.00000
```

```
Cl1  Cl    4 g 0.27500 0.32500 0.00000 1.00000
```

Hydrophilite ($CaCl_2$, C35): AB2_oP6_58_a_g - POSCAR

```
AB2_oP6_58_a_g & a,b/a,c/a,x2,y2 --params=6.24,1.03044871795,
      ↪ 0.673076923077,0.275,0.325 & Pnnm      D_{2h}^{12} #58 (ag) &
      ↪ oP6 & C35 & CaCl2 & Hydrophilite & A. van Bever and W.
      ↪ Nieuwenkamp, Zeitschrift f\"{u}r Kristallographie - Crystalline
      ↪  Materials 90, 374-376 (1935)
   1.0000000000000000
   6.24000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    6.43000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.20000000000000
   Ca    Cl
    2     4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Ca    (2a)
   0.50000000000000    0.50000000000000    0.50000000000000    Ca    (2a)
   0.22500000000000    0.82500000000000    0.50000000000000    Cl    (4g)
   0.27500000000000    0.32500000000000    0.00000000000000    Cl    (4g)
   0.72500000000000    0.67500000000000    0.00000000000000    Cl    (4g)
   0.77500000000000    0.17500000000000    0.50000000000000    Cl    (4g)
```

η-Fe_2C: AB2_oP6_58_a_g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'zeta iron carbide'
_chemical_formula_sum 'Fe2 C'

loop_
_publ_author_name
 'Y. Hirotsu'
 'S. Nagakura'
_journal_name_full
;
Acta Metallurgica
;
_journal_volume 20
_journal_year 1972
_journal_page_first 645
_journal_page_last 655
_publ_Section_title
;
 Crystal structure and morphology of the carbide precipitated from
      ↪ martensitic high carbon steel during the first stage of
      ↪ tempering
;

_aflow_proto 'AB2_oP6_58_a_g'
_aflow_params 'a,b/a,c/a,x2,y2'
_aflow_params_values '4.704,0.917942176871,0.601615646259,0.66667,0.25'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP6'

_symmetry_space_group_name_Hall "-P 2 2n"
_symmetry_space_group_name_H-M "P n n m"
_symmetry_Int_Tables_number 58

_cell_length_a     4.70400
_cell_length_b     4.31800
_cell_length_c     2.83000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x+1/2,y+1/2,-z+1/2
4 -x,-y,z
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x+1/2,-y+1/2,z+1/2
8 x,y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1   C     2 a 0.00000 0.00000 0.00000 1.00000
Fe1  Fe    4 g 0.66667 0.25000 0.00000 1.00000
```

η-Fe_2C: AB2_oP6_58_a_g - POSCAR

```
AB2_oP6_58_a_g & a,b/a,c/a,x2,y2 --params=4.704,0.917942176871,
      ↪ 0.601615646259,0.66667,0.25 & Pnnm      D_{2h}^{12} #58 (ag) &
      ↪ oP6 & & Fe2C & eta & Y. Hirotsu and S. Nagakura, Acta\
      ↪ Metallurgica 20, 645-655 (1972)
   1.0000000000000000
   4.70400000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.31800000000000    0.00000000000000
   0.00000000000000    0.00000000000000    2.83000000000000
    C     Fe
    2     4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    C     (2a)
   0.50000000000000    0.50000000000000    0.50000000000000    C     (2a)
   0.16666666700000    0.25000000000000    0.50000000000000    Fe    (4g)
  -0.16666666700000    0.75000000000000    0.50000000000000    Fe    (4g)
   0.33333333300000    0.75000000000000    0.00000000000000    Fe    (4g)
   0.66666666700000    0.25000000000000    0.00000000000000    Fe    (4g)
```

Marcasite (FeS_2, C18): AB2_oP6_58_a_g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Marcasite'
_chemical_formula_sum 'Fe S2'

loop_
_publ_author_name
 'Milan Rieder'
 'John C. Crelling'
 'Ond\v{r}ej \v{S}ustai'
 'Milan Dr\'{a}bek'
 'Zden\v{e}k Weiss'
 'Mariana Klementov\'{a},'
_journal_name_full
;
International Journal of Coal Geology
;
_journal_volume 71
_journal_year 2007
_journal_page_first 115
_journal_page_last 121
_publ_Section_title
;
 Arsenic in iron disulfides in a brown coal from the North Bohemian
      ↪ Basin, Czech Republic
;

# Found in AMS Database

_aflow_proto 'AB2_oP6_58_a_g'
_aflow_params 'a,b/a,c/a,x2,y2'
_aflow_params_values '4.4446,1.22049228277,0.761913333033,0.2004,0.3787'
_aflow_Strukturbericht 'C18'
_aflow_Pearson 'oP6'

_symmetry_space_group_name_Hall "-P 2 2n"
_symmetry_space_group_name_H-M "P n n m"
_symmetry_Int_Tables_number 58

_cell_length_a     4.44460
_cell_length_b     5.42460
_cell_length_c     3.38640
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x+1/2,y+1/2,-z+1/2
4 -x,-y,z
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x+1/2,-y+1/2,z+1/2
8 x,y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Fe1  Fe    2 a 0.00000 0.00000 0.00000 1.00000
S1   S     4 g 0.20040 0.37870 0.00000 1.00000
```

Marcasite (FeS_2, C18): AB2_oP6_58_a_g - POSCAR

```
AB2_oP6_58_a_g & a,b/a,c/a,x2,y2 --params=4.4446,1.22049228277,
      ↪ 0.761913333033,0.2004,0.3787 & Pnnm      D_{2h}^{12} #58 (ag) &
      ↪  oP6 & C18 & FeS2 & Marcasite & M. Rieder et al., Int. J. Coal
      ↪ Geol. 71, 115-121 (2007)
   1.0000000000000000
   4.44460000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.42460000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.38640000000000
   Fe    S
    2    4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Fe    (2a)
   0.50000000000000    0.50000000000000    0.50000000000000    Fe    (2a)
   0.20040000000000    0.37870000000000    0.00000000000000    S     (4g)
   0.29960000000000    0.87870000000000    0.50000000000000    S     (4g)
   0.70040000000000    0.12130000000000    0.50000000000000    S     (4g)
   0.79960000000000    0.62130000000000    0.00000000000000    S     (4g)
```

Vulcanite (CuTe): AB_oP4_59_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Vulcanite'
_chemical_formula_sum 'Cu Te'

loop_
_publ_author_name
 'Eugene N. Cameron'
 'Ian M. Threadgold'
_journal_name_full
;
American Mineralogist
;
_journal_volume 46
_journal_year 1961
_journal_page_first 258
_journal_page_last 268
_publ_Section_title
;
 Vulcanite, a new copper telluride from Colorado, with notes on certain
      ↪ associated minerals
;

# Found in AMS Database

_aflow_proto 'AB_oP4_59_a_b'
_aflow_params 'a,b/a,c/a,z1,z2'
_aflow_params_values '3.15,1.29841269841,2.20634920635,0.051,0.277'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP4'

_symmetry_space_group_name_Hall "-P 2ab 2a"
_symmetry_space_group_name_H-M "P m m n:2"
_symmetry_Int_Tables_number 59

_cell_length_a      3.15000
_cell_length_b      4.09000
_cell_length_c      6.95000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z
3 -x,y+1/2,-z
4 -x+1/2,-y+1/2,z
5 -x,-y,-z
6 -x+1/2,y,z
7 x,-y+1/2,z
8 x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    2 a 0.25000 0.25000 0.05100 1.00000
Te1 Te    2 b 0.25000 0.75000 0.27700 1.00000
```

Vulcanite (CuTe): AB_oP4_59_a_b - POSCAR

```
AB_oP4_59_a_b & a,b/a,c/a,z1,z2 --params=3.15,1.29841269841,
      ↪ 2.20634920635,0.051,0.277 & Pmmn      D_{2h}^{13} #59 (ab) &
      ↪ oP4 & & CuTe & Vulcanite & E.N. Cameron and I.M. Threadgold,
      ↪ Am. Mineral. 46, 258-268 (1961)
   1.0000000000000000
   3.15000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.09000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.95000000000000
   Cu    Te
    2     2
Direct
   0.25000000000000    0.25000000000000    0.05100000000000    Cu    (2a)
   0.75000000000000    0.75000000000000    0.94900000000000    Cu    (2a)
   0.25000000000000    0.75000000000000    0.27700000000000    Te    (2b)
   0.75000000000000    0.25000000000000    0.72300000000000    Te    (2b)
```

CNCl: ABC_oP6_59_a_a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Cyanogen Chloride'
_chemical_formula_sum 'C N Cl'

loop_
_publ_author_name
 'R. B. Heiart'
 'G. B. Carpenter'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 9
_journal_year 1956
_journal_page_first 889
_journal_page_last 895
_publ_Section_title
;
 The crystal structure of cyanogen chloride
;

# Found in Wyckoff, Vol. I, pp. 173-174

_aflow_proto 'ABC_oP6_59_a_a_a'
_aflow_params 'a,b/a,c/a,z1,z2,z3'
_aflow_params_values '5.68,0.700704225352,1.01056338028,0.1499,0.4237,
      ↪ 0.6255'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP6'

_symmetry_space_group_name_Hall "-P 2ab 2a"
_symmetry_space_group_name_H-M "P m m n:2"
_symmetry_Int_Tables_number 59

_cell_length_a      5.68000
_cell_length_b      3.98000
_cell_length_c      5.74000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z
3 -x,y+1/2,-z
4 -x+1/2,-y+1/2,z
5 -x,-y,-z
6 -x+1/2,y,z
7 x,-y+1/2,z
8 x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cl1 C     2 a 0.25000 0.25000 0.14990 1.00000
Cl1 Cl    2 a 0.25000 0.25000 0.42370 1.00000
N1  N     2 a 0.25000 0.25000 0.62550 1.00000
```

CNCl: ABC_oP6_59_a_a_a - POSCAR

```
ABC_oP6_59_a_a_a & a,b/a,c/a,z1,z2,z3 --params=5.68,0.700704225352,
      ↪ 1.01056338028,0.1499,0.4237,0.6255 & Pmmn      D_{2h}^{13} #59
      ↪ (a^3) & oP6 & & CNCl & & R. B. Heiart and G. B. Carpenter, Acta
      ↪ Cryst. 9, 889-895 (1956)
   1.0000000000000000
   5.68000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.98000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.74000000000000
    C    Cl    N
    2     2    2
Direct
   0.25000000000000    0.25000000000000    0.14990000000000    C    (2a)
   0.75000000000000    0.75000000000000    0.85010000000000    C    (2a)
   0.25000000000000    0.25000000000000    0.42370000000000    Cl   (2a)
   0.75000000000000    0.75000000000000    0.57630000000000    Cl   (2a)
   0.25000000000000    0.25000000000000    0.62550000000000    N    (2a)
   0.75000000000000    0.75000000000000    0.37450000000000    N    (2a)
```

β-$TiCu_3$ ($D0_a$): A3B_oP8_59_bf_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Cu3Ti'
_chemical_formula_sum 'Ti Cu3'

loop_
_publ_author_name
 'N. Karlsson'
_journal_name_full
;
Journal of the Institute of Metals
;
_journal_volume 79
_journal_year 1951
_journal_page_first 391
_journal_page_last 391
_publ_Section_title
;
 ~
;

# Found in Pearson Alloys, p. 329-331

_aflow_proto 'A3B_oP8_59_bf_a'
_aflow_params 'a,b/a,c/a,z1,z2,x3,z3'
```

```
_aflow_params_values '5.162,0.842115459124,0.877760557923,0.67125,0.329,
    ↪ 0.505,0.174'
_aflow_Strukturbericht 'D0_a'
_aflow_Pearson 'oP8'

_symmetry_space_group_name_Hall "-P 2ab 2a"
_symmetry_space_group_name_H-M "P m m n:2"
_symmetry_Int_Tables_number 59

_cell_length_a      5.16200
_cell_length_b      4.34700
_cell_length_c      4.53100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z
3 -x,y+1/2,-z
4 -x+1/2,-y+1/2,z
5 -x,-y,-z
6 -x+1/2,y,z
7 x,-y+1/2,z
8 x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1 Ti   2 a 0.25000 0.25000 0.67125 1.00000
Cu1 Cu   2 b 0.25000 0.75000 0.32900 1.00000
Cu2 Cu   4 f 0.50500 0.25000 0.17400 1.00000
```

β-$TiCu_3$ ($D0_d$): A3B_oP8_59_bf_a - POSCAR

```
A3B_oP8_59_bf_a & a,b/a,c/a,z1,z2,x3,z3 --params=5.162,0.842115459124,
    ↪ 0.877760557923,0.67125,0.329,0.505,0.174 & Pmmn D_{2h}^{
    ↪ 13} #59 (abf) & oP8 & D0_a & TiCu3 & beta & N. Karlsson, J.
    ↪ Inst. Met. 79, 391 (1951)
   1.0000000000000000
   5.16200000000000   0.00000000000000   0.00000000000000
   0.00000000000000   4.34700000000000   0.00000000000000
   0.00000000000000   0.00000000000000   4.53100000000000
   Cu   Ti
    6    2
Direct
   0.25000000000000   0.75000000000000   0.32900000000000   Cu   (2b)
   0.75000000000000   0.25000000000000   0.67100000000000   Cu   (2b)
  -0.00500000000000   0.25000000000000   0.17400000000000   Cu   (4f)
   0.49500000000000   0.75000000000000   0.82600000000000   Cu   (4f)
   0.50500000000000   0.25000000000000   0.17400000000000   Cu   (4f)
   1.00500000000000   0.75000000000000   0.82600000000000   Cu   (4f)
   0.25000000000000   0.25000000000000   0.67125138656800   Ti   (2a)
   0.75000000000000   0.75000000000000   0.32874861343200   Ti   (2a)
```

CdSb (B_e): AB_oP16_61_c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cd Sb'

loop_
_publ_author_name
 'Karl Erik Almin'
_journal_name_full
;
Acta Chemica Scandinavica
;
_journal_volume 2
_journal_year 1948
_journal_page_first 400
_journal_page_last 407
_publ_Section_title
;
 The Crystal Structure of CdSb and ZnSb
;

_aflow_proto 'AB_oP16_61_c_c'
_aflow_params 'a,b/a,c/a,x1,y1,z1,x2,y2,z2'
_aflow_params_values '6.471,1.27538247566,1.31757070005,0.136,0.072,
    ↪ 0.108,0.456,0.119,0.872'
_aflow_Strukturbericht 'B_e'
_aflow_Pearson 'oP16'

_symmetry_space_group_name_Hall "-P 2ac 2ab"
_symmetry_space_group_name_H-M "P b c a"
_symmetry_Int_Tables_number 61

_cell_length_a      6.47100
_cell_length_b      8.25300
_cell_length_c      8.52600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z
7 x,-y+1/2,z+1/2
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cd1 Cd   8 c 0.13600 0.07200 0.10800 1.00000
Sb1 Sb   8 c 0.45600 0.11900 0.87200 1.00000
```

CdSb (B_e): AB_oP16_61_c_c - POSCAR

```
AB_oP16_61_c_c & a,b/a,c/a,x1,y1,z1,x2,y2,z2 --params=6.471,
    ↪ 1.27538247566,1.31757070005,0.136,0.072,0.108,0.456,0.119,0.872
    ↪ & Pbca D_{2h}^{15} #61 (c^2) & oP16 & B_e & CdSb & & K.
    ↪ E. Almin, Acta Chem. Scand. 2, 400-407 (1948)
   1.0000000000000000
   6.47100000000000   0.00000000000000   0.00000000000000
   0.00000000000000   8.25300000000000   0.00000000000000
   0.00000000000000   0.00000000000000   8.52600000000000
   Cd   Sb
    8    8
Direct
   0.13600000000000   0.07200000000000   0.10800000000000   Cd   (8c)
   0.13600000000000   0.42800000000000   0.60800000000000   Cd   (8c)
   0.36400000000000   0.57200000000000   0.10800000000000   Cd   (8c)
   0.36400000000000   0.92800000000000   0.60800000000000   Cd   (8c)
   0.63600000000000   0.07200000000000   0.39200000000000   Cd   (8c)
   0.63600000000000   0.42800000000000   0.89200000000000   Cd   (8c)
   0.86400000000000   0.57200000000000   0.39200000000000   Cd   (8c)
   0.86400000000000   0.92800000000000   0.89200000000000   Cd   (8c)
   0.04400000000000   0.61900000000000   0.87200000000000   Sb   (8c)
   0.04400000000000   0.88100000000000   0.37200000000000   Sb   (8c)
   0.45600000000000   0.11900000000000   0.87200000000000   Sb   (8c)
   0.45600000000000   0.38100000000000   0.37200000000000   Sb   (8c)
   0.54400000000000   0.61900000000000   0.62800000000000   Sb   (8c)
   0.54400000000000   0.88100000000000   0.12800000000000   Sb   (8c)
   0.95600000000000   0.11900000000000   0.62800000000000   Sb   (8c)
   0.95600000000000   0.38100000000000   0.12800000000000   Sb   (8c)
```

Brookite (TiO_2, C21): A2B_oP24_61_2c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Brookite'
_chemical_formula_sum 'Ti O2'

loop_
_publ_author_name
 'E. P. Meagher'
 'G. A. Lager'
_journal_name_full
;
Canadian Mineralogist
;
_journal_volume 17
_journal_year 1979
_journal_page_first 77
_journal_page_last 85
_publ_Section_title
;
 Polyhedral thermal expansion in the TiO$_2$ polymorphs; refinement of
    ↪ the crystal structures of rutile and brookite at high
    ↪ temperature
;

_aflow_proto 'A2B_oP24_61_2c_c'
_aflow_params 'a,b/a,c/a,x1,y1,z1,x2,y2,z2,x3,y3,z3'
_aflow_params_values '9.174,0.375953782429,0.560061042075,0.0095,0.1491,
    ↪ 0.1835,0.2314,0.111,0.5366,0.1289,0.0972,0.8628'
_aflow_Strukturbericht 'C21'
_aflow_Pearson 'oP24'

_symmetry_space_group_name_Hall "-P 2ac 2ab"
_symmetry_space_group_name_H-M "P b c a"
_symmetry_Int_Tables_number 61

_cell_length_a      9.17400
_cell_length_b      3.44900
_cell_length_c      5.13800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
```

```
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z
7 x,-y+1/2,z+1/2
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1   O    8 c 0.00950 0.14910 0.18350 1.00000
O2   O    8 c 0.23140 0.11100 0.53660 1.00000
Ti1  Ti   8 c 0.12890 0.09720 0.86280 1.00000
```

Brookite (TiO_2, C21): A2B_oP24_61_2c_c - POSCAR

```
A2B_oP24_61_2c_c & a,b/a,c/a,x1,y1,z1,x2,y2,z2,x3,y3,z3 --params=9.174,
      ↪ 0.375953782429,0.560061042075,0.0095,0.1491,0.1835,0.2314,0.111
      ↪ ,0.5366,0.1289,0.0972,0.8628 & Pbca      D_{2h}^{15} #61 (c^3)
      ↪ & oP24 & C21 & TiO2 & Brookite & E. P. Meagher and G. A. Lager,
      ↪  Can. Mineral. 17, 77-85 (1979)
   1.0000000000000000
   9.17400000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.44900000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.13800000000000
    O    Ti
   16    8
Direct
   0.00950000000000    0.14910000000000    0.18350000000000    O    (8c)
   0.00950000000000    0.35090000000000    0.68350000000000    O    (8c)
   0.49050000000000    0.64910000000000    0.18350000000000    O    (8c)
   0.49050000000000    0.85090000000000    0.68350000000000    O    (8c)
   0.50950000000000    0.14910000000000    0.31650000000000    O    (8c)
   0.50950000000000    0.35090000000000    0.81650000000000    O    (8c)
   0.99050000000000    0.64910000000000    0.31650000000000    O    (8c)
   0.99050000000000    0.85090000000000    0.81650000000000    O    (8c)
   0.23140000000000    0.11100000000000    0.53660000000000    O    (8c)
   0.23140000000000    0.38900000000000    0.03660000000000    O    (8c)
   0.26860000000000    0.61100000000000    0.53660000000000    O    (8c)
   0.26860000000000    0.88900000000000    0.03660000000000    O    (8c)
   0.73140000000000    0.11100000000000    0.96340000000000    O    (8c)
   0.73140000000000    0.38900000000000    0.46340000000000    O    (8c)
   0.76860000000000    0.61100000000000    0.96340000000000    O    (8c)
   0.76860000000000    0.88900000000000    0.46340000000000    O    (8c)
   0.12890000000000    0.09720000000000    0.86280000000000    Ti   (8c)
   0.12890000000000    0.40280000000000    0.36280000000000    Ti   (8c)
   0.37110000000000    0.59720000000000    0.86280000000000    Ti   (8c)
   0.37110000000000    0.90280000000000    0.36280000000000    Ti   (8c)
   0.62890000000000    0.09720000000000    0.63720000000000    Ti   (8c)
   0.62890000000000    0.40280000000000    0.13720000000000    Ti   (8c)
   0.87110000000000    0.59720000000000    0.63720000000000    Ti   (8c)
   0.87110000000000    0.90280000000000    0.13720000000000    Ti   (8c)
```

Stibnite (Sb_2S_3, $D5_8$): A3B2_oP20_62_3c_2c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Stibnite'
_chemical_formula_sum 'Sb2 S3'

loop_
_publ_author_name
 'Atsushi Kyono'
 'Mitsuyoshi Kimata'
_journal_name_full
;
American Mineralogist
;
_journal_volume 89
_journal_year 2004
_journal_page_first 932
_journal_page_last 940
_publ_Section_title
;
 Structural variations induced by difference of the inert pair effect in
      ↪  the stibnite-bismuthinite solid solution series (Sb,Bi)
      ↪ $_2$S$_3$
;

# Found in  AMS Database

_aflow_proto 'A3B2_oP20_62_3c_2c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,z4,x5,z5'
_aflow_params_values '11.282,0.339443361106,0.994947704308,0.2922,
      ↪ 0.19181,0.4504,0.877,0.6246,0.5611,-0.02937,0.17398,0.64939,-
      ↪ 0.03603'
_aflow_Strukturbericht 'D5_8'
_aflow_Pearson 'oP20'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62
_cell_length_a      11.28200
_cell_length_b      3.82960
_cell_length_c      11.22500
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
S1   S    4 c 0.29220 0.25000 0.19181  1.00000
S2   S    4 c 0.45040 0.25000 0.87700  1.00000
S3   S    4 c 0.62460 0.25000 0.56110  1.00000
Sb1  Sb   4 c -0.02937 0.25000 0.17398  1.00000
Sb2  Sb   4 c 0.64939 0.25000 -0.03603 1.00000
```

Stibnite (Sb_2S_3, $D5_8$): A3B2_oP20_62_3c_2c - POSCAR

```
A3B2_oP20_62_3c_2c & a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,z4,x5,z5 --params=
      ↪ 11.282,0.339443361106,0.994947704308,0.2922,0.19181,0.4504,
      ↪ 0.877,0.6246,0.5611,-0.02937,0.17398,0.64939,-0.03603 & Pnma
      ↪       D^{16}_{2h} #62 (c^5) & oP20 & D5_8 & Sb2S3 & Stibnite &
      ↪ A. Kyono and M. Kimata, Am. Mineral. 89, 932-940 (2004)
   1.0000000000000000
  11.28200000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.82960000000000    0.00000000000000
   0.00000000000000    0.00000000000000   11.22500000000000
    S    Sb
   12    8
Direct
   0.20780000000000    0.75000000000000    0.69181000000000    S    (4c)
   0.29220000000000    0.25000000000000    0.19181000000000    S    (4c)
   0.70780000000000    0.75000000000000    0.80819000000000    S    (4c)
   0.79220000000000    0.25000000000000    0.30819000000000    S    (4c)
  -0.04960000000000    0.25000000000000    0.62300000000000    S    (4c)
   0.04960000000000    0.75000000000000    0.37700000000000    S    (4c)
   0.45040000000000    0.25000000000000    0.87700000000000    S    (4c)
   0.54960000000000    0.75000000000000    0.12300000000000    S    (4c)
   0.12460000000000    0.25000000000000   -0.06110000000000    S    (4c)
   0.37540000000000    0.75000000000000    0.43890000000000    S    (4c)
   0.62460000000000    0.25000000000000    0.56110000000000    S    (4c)
   0.87540000000000    0.75000000000000    0.06110000000000    S    (4c)
  -0.02937000000000    0.25000000000000    0.17398000000000   Sb    (4c)
   0.02937000000000    0.75000000000000    0.82602000000000   Sb    (4c)
   0.47063000000000    0.25000000000000    0.32602000000000   Sb    (4c)
   0.52937000000000    0.75000000000000    0.67398000000000   Sb    (4c)
   0.14939000000000    0.25000000000000    0.53603000000000   Sb    (4c)
   0.35061000000000    0.75000000000000    0.03603000000000   Sb    (4c)
   0.64939000000000    0.25000000000000   -0.03603000000000   Sb    (4c)
   0.85061000000000    0.75000000000000    0.46397000000000   Sb    (4c)
```

$CaTiO_3$ Pnma Perovskite: AB3C_oP20_62_c_cd_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Orthorhombic Perovskite'
_chemical_formula_sum 'Ca Ti O3'

loop_
_publ_author_name
 'Takamitsu Yamanaka'
 'Noriyuki Hirai'
 'Yutaka Komatsu'
_journal_name_full
;
American Mineralogist
;
_journal_volume 87
_journal_year 2002
_journal_page_first 1183
_journal_page_last 1189
_publ_Section_title
;
 Structure change of Ca$_{1-x}$Sr$_x$TiO$_3$ perovskite with composition
      ↪  and pressure
;

# Found in  AMS Database

_aflow_proto 'AB3C_oP20_62_c_cd_a'
_aflow_params 'a,b/a,c/a,x2,z2,x3,z3,x4,y4,z4'
_aflow_params_values '5.4224,1.41099881971,0.996661994689,0.4877,-0.0084
      ↪ ,0.0313,0.0586,0.288,0.537,0.213'
_aflow_Strukturbericht 'None'
```

```
_aflow_Pearson 'oP20'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      5.42240
_cell_length_b      7.65100
_cell_length_c      5.40430
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1 Ti   4 a 0.00000   0.00000 0.00000   1.00000
Ca1 Ca   4 c 0.48770   0.25000 -0.00840  1.00000
O1  O    4 c 0.03130   0.25000 0.05860   1.00000
O2  O    8 d 0.28800   0.53700 0.21300   1.00000
```

$CaTiO_3$ Pnma Perovskite: AB3C_oP20_62_c_cd_a - POSCAR

```
AB3C_oP20_62_c_cd_a & a,b/a,c/a,x2,z2,x3,z3,x4,y4,z4 --params=5.4224,
    ↪ 1.41099881971,0.996661994689,0.4877,-0.0084,0.0313,0.0586,0.288
    ↪ ,0.537,0.213 & Pnma D_{2h}^{16} #62 (ac^2d) & oP20 & &
    ↪ CaTiO3 & orthrhombic perovskite & T. Yamanaka, N. Hirai and Y.
    ↪ Komatsu, Am. Mineral. 87, 1183-1189 (2002)
  1.0000000000000000
  5.42240000000000   0.00000000000000   0.00000000000000
  0.00000000000000   7.65100000000000   0.00000000000000
  0.00000000000000   0.00000000000000   5.40430000000000
  Ca   O   Ti
   4   12   4
Direct
 -0.01230000000000   0.25000000000000   0.50840000000000   Ca   (4c)
  0.01230000000000   0.75000000000000   0.49160000000000   Ca   (4c)
  0.48770000000000   0.25000000000000  -0.00840000000000   Ca   (4c)
  0.51230000000000   0.75000000000000   0.00840000000000   Ca   (4c)
  0.03130000000000   0.25000000000000   0.05860000000000   O    (4c)
 -0.03130000000000   0.75000000000000  -0.05860000000000   O    (4c)
  0.46870000000000   0.75000000000000   0.55860000000000   O    (4c)
  0.53130000000000   0.25000000000000   0.44140000000000   O    (4c)
  0.21200000000000   0.03700000000000   0.71300000000000   O    (8d)
  0.21200000000000   0.46300000000000   0.71300000000000   O    (8d)
  0.28800000000000   0.53700000000000   0.21300000000000   O    (8d)
  0.28800000000000   0.96300000000000   0.21300000000000   O    (8d)
  0.71200000000000   0.03700000000000   0.78700000000000   O    (8d)
  0.71200000000000   0.46300000000000   0.78700000000000   O    (8d)
  0.78800000000000  -0.03700000000000   0.28700000000000   O    (8d)
  0.78800000000000   0.53700000000000   0.28700000000000   O    (8d)
  0.00000000000000   0.00000000000000   0.00000000000000   Ti   (4a)
  0.00000000000000   0.50000000000000   0.00000000000000   Ti   (4a)
  0.50000000000000   0.00000000000000   0.50000000000000   Ti   (4a)
  0.50000000000000   0.50000000000000   0.50000000000000   Ti   (4a)
```

MgB_4: A4B_oP20_62_2cd_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Magnesium tetraboride'
_chemical_formula_sum 'Mg B4'

loop_
_publ_author_name
 'Roger Naslain'
 'Alain Guette'
 'Michel Barret'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 8
_journal_year 1973
_journal_page_first 68
_journal_page_last 85
_publ_Section_title
;
 Sur le diborure et le t\'{e}traborure de magn\'{e}sium. Consid\'{e}
    ↪ rations cristallochimiques sur les t\'{e}traborures
;

# Found in http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_1906993

_aflow_proto 'A4B_oP20_62_2cd_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,y4,z4'
_aflow_params_values '5.464,0.810395314788,1.36749633968,0.22451,0.65626
    ↪ ,0.55801,0.6466,0.05131,0.36362,0.13079,0.0579,0.06543'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oP20'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      5.46400
_cell_length_b      4.42800
_cell_length_c      7.47200
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1  B    4 c 0.22451 0.25000 0.65626 1.00000
B2  B    4 c 0.55801 0.25000 0.64660 1.00000
Mg1 Mg   4 c 0.05131 0.25000 0.36362 1.00000
B3  B    8 d 0.13079 0.05790 0.06543 1.00000
```

MgB_4: A4B_oP20_62_2cd_c - POSCAR

```
A4B_oP20_62_2cd_c & a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,y4,z4 --params=5.464,
    ↪ 0.810395314788,1.36749633968,0.22451,0.65626,0.55801,0.6466,
    ↪ 0.05131,0.36362,0.13079,0.0579,0.06543 & Pnma D^{16}_{2h}
    ↪ #62 (c^3d) & oP20 & & MgB4 & & R. Naslain, A. Guette and M.
    ↪ Barrat, J. Solid State Chem. 8, 68-85 (1973)
  1.0000000000000000
  5.46400000000000   0.00000000000000   0.00000000000000
  0.00000000000000   4.42800000000000   0.00000000000000
  0.00000000000000   0.00000000000000   7.47200000000000
   B   Mg
  16   4
Direct
  0.22451000000000   0.25000000000000   0.65626000000000   B   (4c)
  0.27549000000000   0.75000000000000   0.15626000000000   B   (4c)
  0.72451000000000   0.25000000000000   0.84374000000000   B   (4c)
  0.77549000000000   0.75000000000000   0.34374000000000   B   (4c)
  0.05801000000000   0.25000000000000   0.85340000000000   B   (4c)
 -0.05801000000000   0.75000000000000   0.14660000000000   B   (4c)
  0.44199000000000   0.75000000000000   0.35340000000000   B   (4c)
  0.55801000000000   0.25000000000000   0.64660000000000   B   (4c)
  0.13079000000000   0.05790000000000   0.06543000000000   B   (8d)
  0.13079000000000   0.44210000000000   0.06543000000000   B   (8d)
  0.36921000000000  -0.05790000000000   0.56543000000000   B   (8d)
  0.36921000000000   0.55790000000000   0.56543000000000   B   (8d)
  0.63079000000000   0.05790000000000   0.43457000000000   B   (8d)
  0.63079000000000   0.44210000000000   0.43457000000000   B   (8d)
  0.86921000000000  -0.05790000000000  -0.06543000000000   B   (8d)
  0.86921000000000   0.55790000000000  -0.06543000000000   B   (8d)
  0.05131000000000   0.25000000000000   0.36362000000000   Mg  (4c)
 -0.05131000000000   0.75000000000000   0.63638000000000   Mg  (4c)
  0.44869000000000   0.75000000000000   0.86362000000000   Mg  (4c)
  0.55131000000000   0.25000000000000   0.13638000000000   Mg  (4c)
```

Chalcostibite ($CuSbS_2$, $F5_6$): AB2C_oP16_62_c_2c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Chalcostibite'
_chemical_formula_sum 'Cu Sb S2'

loop_
_publ_author_name
 'Atsushi Kyono'
 'Mitsuyoshi Kimata'
_journal_name_full
;
American Mineralogist
;
_journal_volume 90
_journal_year 2005
_journal_page_first 162
_journal_page_last 165
_publ_Section_title
;
```

```
 Crystal structures of chalcostibite (CuSbS$_2$) and emplectite (
      ↪ CuBiS$_2$): Structural relationship of stereochemical activity
      ↪  between chalcostibite and emplectite
;

_aflow_proto 'AB2C_oP16_62_c_2c_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,z4'
_aflow_params_values '6.018,0.630741110003,2.4086075108,0.2522,0.8276,
      ↪ 0.6221,0.095,0.8706,0.8244,0.226,0.06333'
_aflow_Strukturbericht 'F5_6'
_aflow_Pearson 'oP16'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      6.01800
_cell_length_b      3.79580
_cell_length_c      14.49500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    4 c 0.25220 0.25000 0.82760 1.00000
S1  S     4 c 0.62210 0.25000 0.09500 1.00000
S2  S     4 c 0.87060 0.25000 0.82440 1.00000
Sb1 Sb    4 c 0.22600 0.25000 0.06333 1.00000
```

Chalcostibite ($CuSbS_2$, $F5_6$): AB2C_oP16_62_c_2c_c - POSCAR

```
AB2C_oP16_62_c_2c_c & a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,z4 --params=6.018,
      ↪ 0.630741110003,2.4086075108,0.2522,0.8276,0.6221,0.095,0.8706,
      ↪ 0.8244,0.226,0.06333 & Pnma      D_{2h}^{16} #62 (c^4) & oP16 &
      ↪  F5_6 & CuSbS2 & Chalcostibite & A. Kyono and M. Kimata, Am.
      ↪ Mineral. 90, 162-165 (2005)
   1.0000000000000000
   6.01800000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.79580000000000    0.00000000000000
   0.00000000000000    0.00000000000000   14.49500000000000
   Cu    S    Sb
    4    8    4
Direct
   0.24780000000000    0.75000000000000    0.32760000000000    Cu    (4c)
   0.25220000000000    0.25000000000000    0.82760000000000    Cu    (4c)
   0.74780000000000    0.75000000000000    0.17240000000000    Cu    (4c)
   0.75220000000000    0.25000000000000    0.67240000000000    Cu    (4c)
   0.12210000000000    0.25000000000000    0.40500000000000    S     (4c)
   0.37790000000000    0.75000000000000   -0.09500000000000    S     (4c)
   0.62210000000000    0.25000000000000    0.09500000000000    S     (4c)
   0.87790000000000    0.75000000000000    0.59500000000000    S     (4c)
   0.12940000000000    0.75000000000000    0.17560000000000    S     (4c)
   0.37060000000000    0.25000000000000    0.67560000000000    S     (4c)
   0.62940000000000    0.75000000000000    0.32440000000000    S     (4c)
   0.87060000000000    0.25000000000000    0.82440000000000    S     (4c)
   0.22600000000000    0.25000000000000    0.06333000000000    Sb    (4c)
   0.27400000000000    0.75000000000000    0.56333000000000    Sb    (4c)
   0.72600000000000    0.25000000000000    0.43667000000000    Sb    (4c)
   0.77400000000000    0.75000000000000   -0.06333000000000    Sb    (4c)
```

Co_2Si (C37): A2B_oP12_62_2c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Co2 Si'

loop_
_publ_author_name
 'S. Geller'
 'V. M. Wolontis'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 8
_journal_year 1955
_journal_page_first 83
_journal_page_last 87
_publ_Section_title
;
 The Crystal Structure of Co$_2$Si
;

_aflow_proto 'A2B_oP12_62_2c_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2,x3,z3'
_aflow_params_values '4.918,0.7600650671,1.44550630338,0.038,0.282,0.674
      ↪ ,0.562,0.202,0.611'
_aflow_Strukturbericht 'C37'
_aflow_Pearson 'oP12'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      4.91800
_cell_length_b      3.73800
_cell_length_c      7.10900
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Co1 Co    4 c 0.03800 0.25000 0.28200 1.00000
Co2 Co    4 c 0.67400 0.25000 0.56200 1.00000
Si1 Si    4 c 0.20200 0.25000 0.61100 1.00000
```

Co_2Si (C37): A2B_oP12_62_2c_c - POSCAR

```
A2B_oP12_62_2c_c & a,b/a,c/a,x1,z1,x2,z2,x3,z3 --params=4.918,
      ↪ 0.7600650671,1.44550630338,0.038,0.282,0.674,0.562,0.202,0.611
      ↪ & Pnma      D_{2h}^{16} #62 (c^3) & oP12 & C37 & Co2Si & & S.
      ↪ Geller and V. M. Wolontis, Acta Cryst. 8, 83-87 (1955)
   1.0000000000000000
   4.91800000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.73800000000000    0.00000000000000
   0.00000000000000    0.00000000000000    7.10900000000000
   Co    Si
    8    4
Direct
   0.03800000000000    0.25000000000000    0.28200000000000    Co    (4c)
  -0.03800000000000    0.75000000000000    0.71800000000000    Co    (4c)
   0.46200000000000    0.75000000000000    0.78200000000000    Co    (4c)
   0.53800000000000    0.25000000000000    0.21800000000000    Co    (4c)
   0.17400000000000    0.25000000000000   -0.06200000000000    Co    (4c)
   0.32600000000000    0.75000000000000    0.43800000000000    Co    (4c)
   0.67400000000000    0.25000000000000    0.56200000000000    Co    (4c)
   0.82600000000000    0.75000000000000    0.06200000000000    Co    (4c)
   0.20200000000000    0.25000000000000    0.61100000000000    Si    (4c)
   0.29800000000000    0.75000000000000    0.11100000000000    Si    (4c)
   0.70200000000000    0.25000000000000    0.88900000000000    Si    (4c)
   0.79800000000000    0.75000000000000    0.38900000000000    Si    (4c)
```

$HgCl_2$ (C25): A2B_oP12_62_2c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Hg Cl2'

loop_
_publ_author_name
 'H. Braekken'
 'W. Scholten'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 89
_journal_year 1934
_journal_page_first 448
_journal_page_last 455
_publ_Section_title
;
 Die Kristallstruktur des Quecksilberchloride HgCl$_2$
;

_aflow_proto 'A2B_oP12_62_2c_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2,x3,z3'
_aflow_params_values '12.735,0.468237141735,0.339615233608,0.733,0.125,
      ↪ 0.508,0.722,0.874,0.447'
_aflow_Strukturbericht 'C25'
_aflow_Pearson 'oP12'
```

```
_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      12.73500
_cell_length_b      5.96300
_cell_length_c      4.32500
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cl1 Cl    4 c 0.73300 0.25000 0.12500 1.00000
Cl2 Cl    4 c 0.50800 0.25000 0.72200 1.00000
Hg1 Hg    4 c 0.87400 0.25000 0.44700 1.00000
```

$HgCl_2$ (C25): A2B_oP12_62_2c_c - POSCAR

```
A2B_oP12_62_2c_c & a,b/a,c/a,x1,z1,x2,z2,x3,z3 --params=12.735,
    ↪ 0.468237141735,0.339615233608,0.733,0.125,0.508,0.722,0.874,
    ↪ 0.447 & Pnma      D_{2h}^{16} #62 (c^3) & oP12 & C25 & HgCl2 &
    ↪ & H. Brakken and W. Scholten, Zeitschrift f\"{u}r
    ↪ Kristallographie - Crystalline Materials 89, 448-455 (1934)
    ↪ rotated to Pnma setting
   1.0000000000000000
  12.73500000000000   0.00000000000000   0.00000000000000
   0.00000000000000   5.96300000000000   0.00000000000000
   0.00000000000000   0.00000000000000   4.32500000000000
   Cl   Hg
    8    4
Direct
   0.23300000000000   0.25000000000000   0.37500000000000   Cl   (4c)
   0.26700000000000   0.75000000000000  -0.12500000000000   Cl   (4c)
   0.73300000000000   0.25000000000000   0.12500000000000   Cl   (4c)
   0.76700000000000   0.75000000000000   0.62500000000000   Cl   (4c)
   0.00800000000000   0.25000000000000   0.77800000000000   Cl   (4c)
   0.49200000000000   0.75000000000000   0.27800000000000   Cl   (4c)
   0.50800000000000   0.25000000000000   0.72200000000000   Cl   (4c)
   0.99200000000000   0.75000000000000   0.22200000000000   Cl   (4c)
   0.12600000000000   0.75000000000000   0.55300000000000   Hg   (4c)
   0.37400000000000   0.25000000000000   0.05300000000000   Hg   (4c)
   0.62600000000000   0.75000000000000   0.94700000000000   Hg   (4c)
   0.87400000000000   0.25000000000000   0.44700000000000   Hg   (4c)
```

Cotunnite ($PbCl_2$, C23): A2B_oP12_62_2c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Cotunnite'
_chemical_formula_sum 'Pb Cl2'

loop_
_publ_author_name
 'Ronald L. Sass'
 'E. B. Brackett'
 'T. E. Brackett'
_journal_name_full
;
Journal of Physical Chemistry
;
_journal_volume 67
_journal_year 1963
_journal_page_first 2863
_journal_page_last 2864
_publ_Section_title
;
 The Crystal Structure of Lead Chloride
;

_aflow_proto 'A2B_oP12_62_2c_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2,x3,z3'
_aflow_params_values '7.6204,0.595008136056,1.1869718125,0.125,0.4217,
    ↪ 0.0202,0.837,0.2377,0.0959'
_aflow_Strukturbericht 'C23'
_aflow_Pearson 'oP12'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      7.62040
_cell_length_b      4.53420
_cell_length_c      9.04520
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cl1 Cl    4 c 0.12500 0.25000 0.42170 1.00000
Cl2 Cl    4 c 0.02020 0.25000 0.83700 1.00000
Pb1 Pb    4 c 0.23770 0.25000 0.09590 1.00000
```

Cotunnite ($PbCl_2$, C23): A2B_oP12_62_2c_c - POSCAR

```
A2B_oP12_62_2c_c & a,b/a,c/a,x1,z1,x2,z2,x3,z3 --params=7.6204,
    ↪ 0.595008136056,1.1869718125,0.125,0.4217,0.0202,0.837,0.2377,
    ↪ 0.0959 & Pnma      D_{2h}^{16} #62 (c^3) & oP12 & C23 & PbCl2
    ↪ & Cotunnite & R. L. Sass, E. B. Brackett, and T. E. Brackett,
    ↪ J. Phys. Chem. 67, 2863-2864 (1963)
   1.0000000000000000
   7.62040000000000   0.00000000000000   0.00000000000000
   0.00000000000000   4.53420000000000   0.00000000000000
   0.00000000000000   0.00000000000000   9.04520000000000
   Cl   Pb
    8    4
Direct
   0.12500000000000   0.25000000000000   0.42170000000000   Cl   (4c)
   0.37500000000000   0.75000000000000  -0.07830000000000   Cl   (4c)
   0.62500000000000   0.25000000000000   0.07830000000000   Cl   (4c)
   0.87500000000000   0.75000000000000   0.57830000000000   Cl   (4c)
   0.02020000000000   0.25000000000000   0.83700000000000   Cl   (4c)
  -0.02020000000000   0.75000000000000   0.16300000000000   Cl   (4c)
   0.47980000000000   0.75000000000000   0.33700000000000   Cl   (4c)
   0.52020000000000   0.25000000000000   0.66300000000000   Cl   (4c)
   0.23770000000000   0.25000000000000   0.09590000000000   Pb   (4c)
   0.26230000000000   0.75000000000000   0.59590000000000   Pb   (4c)
   0.73770000000000   0.25000000000000   0.40410000000000   Pb   (4c)
   0.76230000000000   0.75000000000000  -0.09590000000000   Pb   (4c)
```

GeS (B16): AB_oP8_62_c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ge S'

loop_
_publ_author_name
 'W. H. Zachariasen'
_journal_name_full
;
Physical Review
;
_journal_volume 40
_journal_year 1932
_journal_page_first 917
_journal_page_last 922
_publ_Section_title
;
 The Crystal Lattice of Germano Sulphide, GeS
;

# Found in AMS Database

_aflow_proto 'AB_oP8_62_c_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2'
_aflow_params_values '10.42,0.349328214971,0.411708253359,0.375,0.333,
    ↪ 0.139,0.389'
_aflow_Strukturbericht 'B16'
_aflow_Pearson 'oP8'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      10.42000
_cell_length_b      3.64000
_cell_length_c      4.29000
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
```

```
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ge1 Ge    4 c 0.37500 0.25000 0.33300 1.00000
S1  S     4 c 0.13900 0.25000 0.38900 1.00000
```

GeS (B16): AB_oP8_62_c_c - POSCAR

```
AB_oP8_62_c_c & a,b/a,c/a,x1,z1,x2,z2 --params=10.42,0.349328214971,
    ↪ 0.411708253359,0.375,0.333,0.139,0.389 & Pnma      D^{16}_{2h}
    ↪ #62 (c^2) & oP8 & B16 & GeS & & W. H. Zachariasen, Phys. Rev.
    ↪ 40, 917-922 (1932)
   1.0000000000000000
  10.42000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.64000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.29000000000000
   Ge     S
    4     4
Direct
   0.12500000000000    0.75000000000000    0.83300000000000   Ge    (4c)
   0.37500000000000    0.25000000000000    0.33300000000000   Ge    (4c)
   0.62500000000000    0.75000000000000    0.66700000000000   Ge    (4c)
   0.87500000000000    0.25000000000000    0.16700000000000   Ge    (4c)
   0.13900000000000    0.25000000000000    0.38900000000000    S    (4c)
   0.36100000000000    0.75000000000000   -0.11100000000000    S    (4c)
   0.63900000000000    0.25000000000000    1.11100000000000    S    (4c)
   0.86100000000000    0.75000000000000    0.61100000000000    S    (4c)
```

MnP (B31): AB_oP8_62_c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Mn P'

loop_
_publ_author_name
 'Helmer Fjellv{\aa}g'
 'Arne Kjekshus'
_journal_name_full
;
Acta Chemica Scandinvaca A
;
_journal_volume 38
_journal_year 1984
_journal_page_first 563
_journal_page_last 573
_publ_Section_title
;
 Magnetic and Structural Properties of Transition Metal Substituted MnP.
    ↪ I. Mn$_{1-t}$Co$_t$P ($0.00<=t<=0.30$).
;

_aflow_proto 'AB_oP8_62_c_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2'
_aflow_params_values '5.24160,0.606723137973,1.12622100122,0.0056,0.1952
    ↪ ,0.1879,0.5696'
_aflow_Strukturbericht 'B31'
_aflow_Pearson 'oP8'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      5.24160
_cell_length_b      3.18020
_cell_length_c      5.90320
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mn1 Mn    4 c 0.00560 0.25000 0.19520 1.00000
P1  P     4 c 0.18790 0.25000 0.56960 1.00000
```

MnP (B31): AB_oP8_62_c_c - POSCAR

```
AB_oP8_62_c_c & a,b/a,c/a,x1,z1,x2,z2 --params=5.24160,0.606723137973,
    ↪ 1.12622100122,0.0056,0.1952,0.1879,0.5696 & Pnma      D_{2h}^16
    ↪ #62 (c^2) & oP8 & B31 & MnP & & Helmer Fjellv{\aa}g and Arne
    ↪ Kjekshus, Acta Chemica Scandinvaca A 38, 563-573 (1984)
   1.0000000000000000
   5.24160000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.18020000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.90320000000000
   Mn     P
    4     4
Direct
   0.00560000000000    0.25000000000000    0.19520000000000   Mn    (4c)
  -0.00560000000000    0.75000000000000   -0.19520000000000   Mn    (4c)
   0.49440000000000    0.75000000000000    0.69520000000000   Mn    (4c)
   0.50560000000000    0.25000000000000    0.30480000000000   Mn    (4c)
   0.18790000000000    0.25000000000000    0.56960000000000    P    (4c)
  -0.18790000000000    0.75000000000000   -0.56960000000000    P    (4c)
   0.31210000000000    0.75000000000000    0.06960000000000    P    (4c)
   0.68790000000000    0.25000000000000   -0.06960000000000    P    (4c)
```

Cementite (Fe_3C, $D0_{11}$): AB3_oP16_62_c_cd - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Cementite'
_chemical_formula_sum 'Fe3 C'

loop_
_publ_author_name
 'F. H. Herbstein'
 'J. Smuts'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 17
_journal_year 1964
_journal_page_first 1331
_journal_page_last 1332
_publ_Section_title
;
 Comparison of X-ray and neutron-diffraction refinements of the
    ↪ structure of cementite Fe$_3$C
;

# Found in AMS Database

_aflow_proto 'AB3_oP16_62_c_cd'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2,x3,y3,z3'
_aflow_params_values '5.09,1.3257367387,0.888605108055,0.39,0.05,0.036,
    ↪ 0.852,0.186,0.063,0.328'
_aflow_Strukturbericht 'D0_11'
_aflow_Pearson 'oP16'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      5.09000
_cell_length_b      6.74800
_cell_length_c      4.52300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C     4 c 0.39000 0.25000 0.05000 1.00000
Fe1 Fe    4 c 0.03600 0.25000 0.85200 1.00000
Fe2 Fe    8 d 0.18600 0.06300 0.32800 1.00000
```

Cementite (Fe_3C, $D0_{11}$): AB3_oP16_62_c_cd - POSCAR

```
AB3_oP16_62_c_cd & a,b/a,c/a,x1,z1,x2,z2,x3,y3,z3 --params=5.09,
      ↪ 1.3257367387,0.888605108055,0.39,0.05,0.036,0.852,0.186,0.063,
      ↪ 0.328 & Pnma      D^{16}_{2h} #62 (c^2d) & oP16 & D0_11 & Fe3C
      ↪ & Cementite & F. H. Herbstein and J. Smuts, Acta Cryst. 17,
      ↪ 1331-1332 (1964)
   1.0000000000000000
   5.09000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    6.74800000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.52300000000000
    C    Fe
    4    12
Direct
   0.11000000000000    0.75000000000000   -0.45000000000000    C    (4c)
   0.39000000000000    0.25000000000000    0.05000000000000    C    (4c)
   0.61000000000000    0.75000000000000    0.95000000000000    C    (4c)
   0.89000000000000    0.25000000000000    0.45000000000000    C    (4c)
   0.03600000000000    0.25000000000000    0.85200000000000   Fe    (4c)
  -0.03600000000000    0.75000000000000    0.14800000000000   Fe    (4c)
   0.46400000000000    0.75000000000000    0.35200000000000   Fe    (4c)
   0.53600000000000    0.25000000000000    0.64800000000000   Fe    (4c)
   0.18600000000000    0.06300000000000    0.32800000000000   Fe    (8d)
   0.18600000000000    0.43700000000000    0.32800000000000   Fe    (8d)
   0.31400000000000   -0.06300000000000    0.82800000000000   Fe    (8d)
   0.31400000000000    0.56300000000000    0.82800000000000   Fe    (8d)
   0.68600000000000    0.06300000000000    0.17200000000000   Fe    (8d)
   0.68600000000000    0.43700000000000    0.17200000000000   Fe    (8d)
   0.81400000000000    0.56300000000000    0.67200000000000   Fe    (8d)
   0.81400000000000    0.93700000000000    0.67200000000000   Fe    (8d)
```

C_3Cr_7 ($D10_1$): A3B7_oP40_62_cd_3c2d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'C3 Cr7'

loop_
_publ_author_name
 'M. A. Rouault'
 'P. Herpin'
 'M. R. Fruchart'
_journal_name_full
;
Annales de Chimie (Paris)
;
_journal_volume 5
_journal_year 1970
_journal_page_first 461
_journal_page_last 470
_publ_Section_title
;
 Etude Cristallographique des Carbures Cr$_7$C$_3$ et Mn$_7$C$_3$
;

# Found in  Pearson's Handbook Vol. II, p. 1873

_aflow_proto 'A3B7_oP40_62_cd_3c2d'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,z4,x5,y5,z5,x6,y6,z6,x7,y7
      ↪ ,z7'
_aflow_params_values '4.526,1.54882898807,2.68272205038,0.4594,0.5629,
      ↪ 0.0579,0.6261,0.2501,0.2063,0.2619,0.4165,0.0288,0.0291,0.3428,
      ↪ 0.0565,0.0642,0.8119,0.2509,0.0657,0.0218'
_aflow_Strukturbericht 'D10_1'
_aflow_Pearson 'oP40'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a    4.52600
_cell_length_b    7.01000
_cell_length_c    12.14200
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x,y+1/2,-z
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x+1/2,y+1/2,z+1/2
7 x,-y+1/2,z
8 x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    4 c 0.45940 0.25000 0.56290 1.00000
Cr1 Cr   4 c 0.05790 0.25000 0.62610 1.00000
Cr2 Cr   4 c 0.25010 0.25000 0.20630 1.00000
Cr3 Cr   4 c 0.26190 0.25000 0.41650 1.00000
C2  C    8 d 0.02880 0.02910 0.34280 1.00000
Cr4 Cr   8 d 0.05650 0.06420 0.81190 1.00000
Cr5 Cr   8 d 0.25090 0.06570 0.02180 1.00000
```

C_3Cr_7 ($D10_1$): A3B7_oP40_62_cd_3c2d - POSCAR

```
A3B7_oP40_62_cd_3c2d & a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,z4,x5,y5,z5,x6,y6,
      ↪ z6,x7,y7,z7 --params=4.526,1.54882898807,2.68272205038,0.4594,
      ↪ 0.5629,0.0579,0.6261,0.2501,0.2063,0.2619,0.4165,0.0288,0.0291,
      ↪ 0.3428,0.0565,0.0642,0.8119,0.2509,0.0657,0.0218 & Pnma      D
      ↪ ^{16}_{2h} #62 (c^4d^3) & oP40 & D10_1 & C3Cr7 & & M. A.
      ↪ Rouault, P. Herpin and M. R. Fruchart, Ann. Chim. (Paris) 5,
      ↪ 461-470 (1970)
   1.0000000000000000
   4.52600000000000    0.00000000000000    0.00000000000000
   0.00000000000000    7.01000000000000    0.00000000000000
   0.00000000000000    0.00000000000000   12.14200000000000
    C    Cr
   12    28
Direct
   0.04060000000000    0.75000000000000    0.06290000000000    C    (4c)
   0.45940000000000    0.25000000000000    0.56290000000000    C    (4c)
   0.54060000000000    0.75000000000000    0.43710000000000    C    (4c)
   0.95940000000000    0.25000000000000   -0.06290000000000    C    (4c)
   0.02880000000000    0.02910000000000    0.34280000000000    C    (8d)
   0.02880000000000    0.47090000000000    0.34280000000000    C    (8d)
   0.47120000000000   -0.02910000000000    0.84280000000000    C    (8d)
   0.47120000000000    0.52910000000000    0.84280000000000    C    (8d)
   0.52880000000000    0.02910000000000    0.15720000000000    C    (8d)
   0.52880000000000    0.47090000000000    0.15720000000000    C    (8d)
   0.97120000000000    0.52910000000000    0.65720000000000    C    (8d)
   0.97120000000000    0.97090000000000    0.65720000000000    C    (8d)
   0.05790000000000    0.25000000000000    0.62610000000000   Cr    (4c)
   0.44210000000000    0.75000000000000    0.12610000000000   Cr    (4c)
   0.55790000000000    0.25000000000000   -0.12610000000000   Cr    (4c)
   0.94210000000000    0.75000000000000    0.37390000000000   Cr    (4c)
   0.24990000000000    0.75000000000000   -0.29370000000000   Cr    (4c)
   0.25010000000000    0.25000000000000    0.20630000000000   Cr    (4c)
   0.74990000000000    0.75000000000000    0.79370000000000   Cr    (4c)
   0.75010000000000    0.25000000000000    0.29370000000000   Cr    (4c)
   0.23810000000000    0.75000000000000   -0.08350000000000   Cr    (4c)
   0.26190000000000    0.25000000000000    0.41650000000000   Cr    (4c)
  -0.26190000000000    0.75000000000000    0.58350000000000   Cr    (4c)
   0.76190000000000    0.25000000000000    1.08350000000000   Cr    (4c)
   0.05650000000000    0.06420000000000    0.81190000000000   Cr    (8d)
   0.05650000000000    0.43580000000000    0.81190000000000   Cr    (8d)
   0.44350000000000   -0.06420000000000    1.31190000000000   Cr    (8d)
   0.44350000000000    0.56420000000000    1.31190000000000   Cr    (8d)
   0.55650000000000    0.06420000000000   -0.31190000000000   Cr    (8d)
   0.55650000000000    0.43580000000000   -0.31190000000000   Cr    (8d)
   0.94350000000000    0.56420000000000    0.18810000000000   Cr    (8d)
   0.94350000000000    0.93580000000000    0.18810000000000   Cr    (8d)
   0.24910000000000   -0.06570000000000    0.52180000000000   Cr    (8d)
   0.24910000000000    0.56570000000000    0.52180000000000   Cr    (8d)
   0.25090000000000    0.06570000000000    0.02180000000000   Cr    (8d)
   0.25090000000000    0.43430000000000    0.02180000000000   Cr    (8d)
   0.74910000000000    0.56570000000000    0.97820000000000   Cr    (8d)
   0.74910000000000    0.93430000000000    0.97820000000000   Cr    (8d)
   0.75090000000000    0.06570000000000    0.47820000000000   Cr    (8d)
   0.75090000000000    0.43430000000000    0.47820000000000   Cr    (8d)
```

α-Np (A_c): A_oP8_62_2c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha Np'
_chemical_formula_sum 'Np'

loop_
_publ_author_name
 'W. H. Zachariasen'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 5
_journal_year 1952
_journal_page_first 660
_journal_page_last 664
_publ_Section_title
;
 Crystal chemical studies of the 5f-series of elements. XVII. The
      ↪ crystal structure of neptunium metal
;

# Found in  Donohue, pp. 151-153

_aflow_proto 'A_oP8_62_2c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2'
_aflow_params_values '6.663,0.708839861924,0.73345339937,0.464,0.292,
      ↪ 0.181,0.658'
_aflow_Strukturbericht 'A_c'
_aflow_Pearson 'oP8'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a    6.66300
_cell_length_b    4.72300
_cell_length_c    4.88700
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
```

```
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y+1/2,-z+1/2
3  -x,y+1/2,-z
4  -x+1/2,-y,z+1/2
5  -x,-y,-z
6  -x+1/2,y+1/2,z+1/2
7  x,-y+1/2,z
8  x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Np1  Np     4  c  0.46400  0.25000  0.29200  1.00000
Np2  Np     4  c  0.18100  0.25000  0.65800  1.00000
```

α-Np (A_c): A_oP8_62_2c - POSCAR

```
A_oP8_62_2c & a,b/a,c/a,x1,z1,x2,z2 --params=6.663,0.708839861924,
      ↪ 0.73345339937,0.464,0.292,0.181,0.658 & Pnma        D^{16}_{2h} #
      ↪ 62 (c^2) & oP8 & A_c & Np & alpha & W. H. Zachariasen, Acta
      ↪ Cryst. 5, 660-664 (1952)
   1.0000000000000000
   6.66300000000000     0.00000000000000     0.00000000000000
   0.00000000000000     4.72300000000000     0.00000000000000
   0.00000000000000     0.00000000000000     4.88700000000000
   Np
    8
Direct
   0.46400000000000     0.25000000000000     0.29200000000000     Np     (4c)
   0.03600000000000     0.75000000000000     0.79200000000000     Np     (4c)
   0.53600000000000     0.75000000000000     0.70800000000000     Np     (4c)
   0.96400000000000     0.25000000000000     0.20800000000000     Np     (4c)
   0.18100000000000     0.25000000000000     0.65800000000000     Np     (4c)
   0.31900000000000     0.75000000000000     0.15800000000000     Np     (4c)
   0.81900000000000     0.75000000000000     0.34200000000000     Np     (4c)
   0.68100000000000     0.25000000000000     0.84200000000000     Np     (4c)
```

FeB (B27): AB_oP8_62_c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Iron Boride'
_chemical_formula_sum 'Fe B'

loop_
_publ_author_name
 'Sterling B. Hendricks'
 'Peter R. Kosting'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 74
_journal_year 1930
_journal_page_first 511
_journal_page_last 533
_publ_Section_title
;
 The Crystal Structure of Fe$_2$P, Fe$_2$N, Fe$_3$N and FeB
;

# Found in  AMS Database

_aflow_proto 'AB_oP8_62_c_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2'
_aflow_params_values '5.495,0.536123748863,0.737579617834,0.125,0.69,-
      ↪ 0.18,0.125'
_aflow_Strukturbericht 'B27'
_aflow_Pearson 'oP8'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      5.49500
_cell_length_b      2.94600
_cell_length_c      4.05300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y+1/2,-z+1/2
3  -x,y+1/2,-z
4  -x+1/2,-y,z+1/2
5  -x,-y,-z
6  -x+1/2,y+1/2,z+1/2
7  x,-y+1/2,z
8  x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1   B     4  c  0.12500  0.25000  0.69000  1.00000
Fe1  Fe    4  c  -0.18000  0.25000  0.12500  1.00000
```

FeB (B27): AB_oP8_62_c_c - POSCAR

```
AB_oP8_62_c_c & a,b/a,c/a,x1,z1,x2,z2 --params=5.495,0.536123748863,
      ↪ 0.737579617834,0.125,0.69,-0.18,0.125 & Pnma        D^{16}_{2h} #
      ↪ 62 (c^2) & oP8 & B27 & FeB & S. B. Hendricks and P. R.
      ↪ Kosting, Zeitschrift f\"{u}r Kristallographie - Crystalline
      ↪ Materials 74, 511-533 (1930)
   1.0000000000000000
   5.49500000000000     0.00000000000000     0.00000000000000
   0.00000000000000     2.94600000000000     0.00000000000000
   0.00000000000000     0.00000000000000     4.05300000000000
    B    Fe
    4    4
Direct
   0.12500000000000     0.25000000000000     0.69000000000000     B     (4c)
   0.37500000000000     0.75000000000000     0.19000000000000     B     (4c)
   0.62500000000000     0.25000000000000     0.81000000000000     B     (4c)
   0.87500000000000     0.75000000000000     0.31000000000000     B     (4c)
  -0.18000000000000     0.25000000000000     0.12500000000000    Fe     (4c)
   0.18000000000000     0.75000000000000     0.87500000000000    Fe     (4c)
   0.32000000000000     0.25000000000000     0.37500000000000    Fe     (4c)
   0.68000000000000     0.75000000000000     0.62500000000000    Fe     (4c)
```

SnS (B29): AB_oP8_62_c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Sn S'

loop_
_publ_author_name
 'Sylvie Del Bucchia'
 'Jean-Claude Jumas'
 'Maurice Maurin'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 37
_journal_year 1981
_journal_page_first 1903
_journal_page_last 1905
_publ_Section_title
;
 Contribution \`{a} l'\'{e}tude de compos\'{e}s sulfur\'{e}s d'\'{e}tain
      ↪ (II): affinement de la structure de SnS
;

_aflow_proto 'AB_oP8_62_c_c'
_aflow_params 'a,b/a,c/a,x1,z1,x2,z2'
_aflow_params_values '11.18,0.356171735242,0.387209302326,0.3507,0.0201,
      ↪ 0.61937,0.3806'
_aflow_Strukturbericht 'B29'
_aflow_Pearson 'oP8'

_symmetry_space_group_name_Hall "-P 2ac 2n"
_symmetry_space_group_name_H-M "P n m a"
_symmetry_Int_Tables_number 62

_cell_length_a      11.18000
_cell_length_b      3.98200
_cell_length_c      4.32900
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y+1/2,-z+1/2
3  -x,y+1/2,-z
4  -x+1/2,-y,z+1/2
5  -x,-y,-z
6  -x+1/2,y+1/2,z+1/2
7  x,-y+1/2,z
8  x+1/2,y,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
```

```
S1   S     4 c 0.35070  0.25000  0.02010  1.00000
Sn1  Sn    4 c 0.61937  0.25000  0.38060  1.00000
```

SnS (B29): AB_oP8_62_c_c - POSCAR

```
AB_oP8_62_c_c & a,b/a,c/a,x1,z1,x2,z2 --params=11.18,0.356171735242,
    ↪ 0.387209302326,0.3507,0.0201,0.61937,0.3806 & Pnma      D^{16}_
    ↪ {2h} #62 (c^2) & oP8 & B29 & SnS & & S. Del Bucchia et al.,
    ↪ Acta Cryst. B 73, 1903-1905 (1981)
   1.0000000000000000
  11.18000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.98200000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.32900000000000
    S    Sn
    4     4
Direct
   0.14930000000000    0.75000000000000    0.52010000000000     S     (4c)
   0.35070000000000    0.25000000000000    0.02010000000000     S     (4c)
   0.64930000000000    0.75000000000000    0.97990000000000     S     (4c)
   0.85070000000000    0.25000000000000    0.47990000000000     S     (4c)
   0.11937000000000    0.25000000000000    0.11940000000000    Sn     (4c)
   0.38063000000000    0.75000000000000    0.61940000000000    Sn     (4c)
   0.61937000000000    0.25000000000000    0.38060000000000    Sn     (4c)
   0.88063000000000    0.75000000000000    0.88060000000000    Sn     (4c)
```

$SrCuO_2$: AB2C_oC16_63_c_2c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Sr Cu O2'

loop_
_publ_author_name
 'Yoshitaka Matsushita'
 'Yasunao Oyama'
 'Masashi Hasegawa'
 'Humihiko Takei'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 114
_journal_year 1994
_journal_page_first 289
_journal_page_last 293
_publ_Section_title
;
 Growth and Structural Refinement of Orthorhombic SrCuO$_2$ Crystals
;

_aflow_proto 'AB2C_oC16_63_c_2c_c'
_aflow_params 'a,b/a,c/a,y1,y2,y3,y4'
_aflow_params_values '3.577,4.56863293263,1.09538719597,0.06109,-0.0558,
    ↪ 0.1792,0.33096'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oC16'

_symmetry_space_group_name_Hall "-C 2c 2"
_symmetry_space_group_name_H-M "C m c m"
_symmetry_Int_Tables_number 63

_cell_length_a      3.57700
_cell_length_b      16.34200
_cell_length_c      3.91820
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z+1/2
4 -x,-y,z+1/2
5 -x,-y,-z
6 -x,y,z
7 x,-y,z+1/2
8 x,y,-z+1/2
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x+1/2,y+1/2,-z+1/2
12 -x+1/2,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x+1/2,-y+1/2,z+1/2
16 x+1/2,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    4 c 0.00000  0.06109   0.25000  1.00000
O1  O     4 c 0.00000 -0.05580  0.25000  1.00000
O2  O     4 c 0.00000  0.17920   0.25000  1.00000
Sr1 Sr    4 c 0.00000  0.33096   0.25000  1.00000
```

$SrCuO_2$: AB2C_oC16_63_c_2c_c - POSCAR

```
AB2C_oC16_63_c_2c_c & a,b/a,c/a,y1,y2,y3,y4 --params=3.577,4.56863293263
    ↪ ,1.09538719597,0.06109,-0.0558,0.1792,0.33096 & Cmcm      D_{2h
    ↪ }^{17} #63 (c^4) & oC16 & & SrCuO2 & & Y. Matsushita, Y. Oyama,
    ↪ M. Hasegawa and H. Takei, J. Solid State Chem. 114 289-293 (
    ↪ 1994)
   1.0000000000000000
   1.78850000000000   -8.17100000000000    0.00000000000000
   1.78850000000000    8.17100000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.91820000000000
   Cu    O    Sr
    2    4     2
Direct
  -0.06109000000000    0.06109000000000    0.25000000000000    Cu     (4c)
   0.06109000000000   -0.06109000000000    0.75000000000000    Cu     (4c)
   0.05580000000000   -0.05580000000000    0.25000000000000     O     (4c)
  -0.05580000000000    0.05580000000000    0.75000000000000     O     (4c)
   0.17920000000000    0.82080000000000    0.75000000000000     O     (4c)
   0.82080000000000    0.17920000000000    0.25000000000000     O     (4c)
   0.33096000000000    0.66904000000000    0.75000000000000    Sr     (4c)
   0.66904000000000    0.33096000000000    0.25000000000000    Sr     (4c)
```

$ZrSi_2$ (C49): A2B_oC12_63_2c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Zirconium Disilicide'
_chemical_formula_sum 'Zr Si2'

loop_
_publ_author_name
 'P. G. Cotter'
 'J. A. Kohn'
 'R. A. Potter'
_journal_name_full
;
Journal of the American Ceramic Society
;
_journal_volume 39
_journal_year 1956
_journal_page_first 11
_journal_page_last 12
_publ_Section_title
;
 Physical and X-Ray Study of the Disilicides of Titanium, Zirconium, and
    ↪ Hafnium
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_0530831

_aflow_proto 'A2B_oC12_63_2c_c'
_aflow_params 'a,b/a,c/a,y1,y2,y3'
_aflow_params_values '3.73,3.94638069705,0.983914209115,0.061,0.75,0.396
    ↪ '
_aflow_Strukturbericht 'C49'
_aflow_Pearson 'oC12'

_symmetry_space_group_name_Hall "-C 2c 2"
_symmetry_space_group_name_H-M "C m c m"
_symmetry_Int_Tables_number 63

_cell_length_a      3.73000
_cell_length_b      14.72000
_cell_length_c      3.67000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z+1/2
4 -x,-y,z+1/2
5 -x,-y,-z
6 -x,y,z
7 x,-y,z+1/2
8 x,y,-z+1/2
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x+1/2,y+1/2,-z+1/2
12 -x+1/2,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x+1/2,-y+1/2,z+1/2
16 x+1/2,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si    4 c 0.00000  0.06100  0.25000  1.00000
Si2 Si    4 c 0.00000  0.75000   0.25000  1.00000
Zr1 Zr    4 c 0.00000  0.39600   0.25000  1.00000
```

$ZrSi_2$ (C49): A2B_oC12_63_2c_c - POSCAR

```
A2B_oC12_63_2c_c & a,b/a,c/a,y1,y2,y3 --params=3.73,3.94638069705,
    ↪ 0.983914209115,0.061,0.75,0.396 & Cmcm      D_{2h}^{17} #63 (c^
    ↪ 3) & oC12 & C49 & ZrSi2 & & P. G. Cotter, J. A. Kohn and R. A.
    ↪ Potter, J. Am. Ceram. Soc. 39, 11-12 (1956)
   1.0000000000000000
   1.86500000000000  -7.36000000000000   0.00000000000000
   1.86500000000000   7.36000000000000   0.00000000000000
   0.00000000000000   0.00000000000000   3.67000000000000
   Si   Zr
    4    2
Direct
  -0.06100000000000   0.06100000000000   0.25000000000000   Si   (4c)
   0.06100000000000  -0.06100000000000   0.75000000000000   Si   (4c)
   0.25000000000000   0.75000000000000   0.25000000000000   Si   (4c)
   0.75000000000000   0.25000000000000   0.75000000000000   Si   (4c)
   0.39600000000000   0.60400000000000   0.75000000000000   Zr   (4c)
   0.60400000000000   0.39600000000000   0.25000000000000   Zr   (4c)
```

CrB (B33): AB_oC8_63_c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr B'

loop_
_publ_author_name
 'Shigeru Okada'
 'Tetsuzo Atoda'
 'Iwami Higashi'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 68
_journal_year 1987
_journal_page_first 61
_journal_page_last 67
_publ_Section_title
;
 Structural investigation of Cr$_2$B$_3$, Cr$_3$B$_4$, and CrB by
    ↪ single-crystal diffractometry
;

# Found in http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_0455627

_aflow_proto 'AB_oC8_63_c_c'
_aflow_params 'a,b/a,c/a,y1,y2'
_aflow_params_values '2.9782,2.64253575985,0.985360284736,0.436,0.14525'
_aflow_Strukturbericht 'B33'
_aflow_Pearson 'oC8'

_symmetry_space_group_name_Hall "-C 2c 2"
_symmetry_space_group_name_H-M "C m c m"
_symmetry_Int_Tables_number 63

_cell_length_a      2.97820
_cell_length_b      7.87000
_cell_length_c      2.93460
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z+1/2
4 -x,-y,z+1/2
5 -x,-y,-z
6 -x,y,z
7 x,-y,z+1/2
8 x,y,-z+1/2
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x+1/2,y+1/2,-z+1/2
12 -x+1/2,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x+1/2,-y+1/2,z+1/2
16 x+1/2,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1  B    4 c 0.00000 0.43600 0.25000 1.00000
Cr1 Cr   4 c 0.00000 0.14525 0.25000 1.00000
```

CrB (B33): AB_oC8_63_c_c - POSCAR

```
AB_oC8_63_c_c & a,b/a,c/a,y1,y2 --params=2.9782,2.64253575985,
    ↪ 0.985360284736,0.436,0.14525 & Cmcm      D_{2h}^{17} #63 (c^2)
    ↪ & oC8 & B33 & CrB & & S. Okada, T. Atoda, and I. Higashi, J.
    ↪ Solid State Chem. 68, 61-67 (1987)
   1.0000000000000000
   1.48910000000000  -3.93500000000000   0.00000000000000
   1.48910000000000   3.93500000000000   0.00000000000000
   0.00000000000000   0.00000000000000   2.93460000000000
    B   Cr
    2    2
Direct
   0.43600000000000   0.56400000000000   0.75000000000000   B   (4c)
   0.56400000000000   0.43600000000000   0.25000000000000   B   (4c)
   0.14525000000000   0.85475000000000   0.75000000000000   Cr  (4c)
   0.85475000000000   0.14525000000000   0.25000000000000   Cr  (4c)
```

α-U (A20): A_oC4_63_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha U'
_chemical_formula_sum 'U'

loop_
_publ_author_name
 'C. S. Barrett'
 'M. H. Mueller'
 'R. L. Hitterman'
_journal_name_full
;
Physical Review
;
_journal_volume 129
_journal_year 1963
_journal_page_first 625
_journal_page_last 629
_publ_Section_title
;
 Crystal Structure Variations in Alpha Uranium at Low Temperatures
;

_aflow_proto 'A_oC4_63_c'
_aflow_params 'a,b/a,c/a,y1'
_aflow_params_values '2.8444,2.06331739558,1.73379271551,0.10228'
_aflow_Strukturbericht 'A20'
_aflow_Pearson 'oC4'

_symmetry_space_group_name_Hall "-C 2c 2"
_symmetry_space_group_name_H-M "C m c m"
_symmetry_Int_Tables_number 63

_cell_length_a      2.84440
_cell_length_b      5.86890
_cell_length_c      4.93160
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z+1/2
4 -x,-y,z+1/2
5 -x,-y,-z
6 -x,y,z
7 x,-y,z+1/2
8 x,y,-z+1/2
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x+1/2,y+1/2,-z+1/2
12 -x+1/2,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x+1/2,-y+1/2,z+1/2
16 x+1/2,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
U1 U    4 c 0.00000 0.10228 0.25000 1.00000
```

α-U (A20): A_oC4_63_c - POSCAR

```
A_oC4_63_c & a,b/a,c/a,y1 --params=2.8444,2.06331739558,1.73379271551,
    ↪ 0.10228 & Cmcm      D_{2h}^{17} #63 (c) & oC4 & A20 & U & alpha
    ↪ & C. S. Barrett, M. H. Mueller and R. L. Hitterman, Phys. Rev.
    ↪ 129, 625-629 (1963)
   1.0000000000000000
   1.42220000000000  -2.93445000000000   0.00000000000000
   1.42220000000000   2.93445000000000   0.00000000000000
   0.00000000000000   0.00000000000000   4.93160000000000
    U
    2
Direct
```

```
    0.10228000000000    0.89772000000000    0.75000000000000    U    (4c)
    0.89772000000000    0.10228000000000    0.25000000000000    U    (4c)
```

α-Ga (A11): A_oC8_64_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha'
_chemical_formula_sum 'Ga'

loop_
_publ_author_name
 'Brahama D. Sharma'
 'Jerry Donohue'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie
;
_journal_volume 117
_journal_year 1962
_journal_page_first 293
_journal_page_last 300
_publ_Section_title
;
 A refinement of the crystal structure of gallium
;

# Found in AMS Database

_aflow_proto 'A_oC8_64_f'
_aflow_params 'a,b/a,c/a,y1,z1'
_aflow_params_values '4.523,1.69378730931,1.0002210922,0.1549,0.081'
_aflow_Strukturbericht 'A11'
_aflow_Pearson 'oC8'

_symmetry_space_group_name_Hall "-C 2bc 2"
_symmetry_space_group_name_H-M "C m c a"
_symmetry_Int_Tables_number 64

_cell_length_a      4.52300
_cell_length_b      7.66100
_cell_length_c      4.52400
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x+1/2,y,-z+1/2
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x,y,z
7 x+1/2,-y,z+1/2
8 x+1/2,y,-z+1/2
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x,y+1/2,-z+1/2
12 -x,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x,-y+1/2,z+1/2
16 x,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ga1 Ga    8 f 0.00000 0.15490 0.08100 1.00000
```

α-Ga (A11): A_oC8_64_f - POSCAR

```
A_oC8_64_f & a,b/a,c/a,y1,z1 --params=4.523,1.69378730931,1.0002210922,
    ↪ 0.1549,0.081 & Cmca      D_{2h}^{18} #64 (f) & oC8 & A11 & Ga &
    ↪ alpha & B. D. Sharma and J. Donohue, Zeitschrift f\"{u}r
    ↪ Kristallographie 117, 293-300 (1962)
   1.0000000000000000
   2.26150000000000   -3.83050000000000    0.00000000000000
   2.26150000000000    3.83050000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.52400000000000
   Ga
    4
Direct
   0.15490000000000    0.84510000000000    0.91900000000000    Ga    (8f)
   0.34510000000000    0.65490000000000    0.41900000000000    Ga    (8f)
   0.65490000000000    0.34510000000000    0.58100000000000    Ga    (8f)
   0.84510000000000    0.15490000000000    0.08100000000000    Ga    (8f)
```

MgB_2C_2: A2B2C_oC80_64_efg_efg_df - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Mg B2 C2'

loop_
_publ_author_name
 'Michael W\"{o}rle'
 'Reinhard Nesper'
_journal_name_full
;
Journal of Alloys and Compounds
;
_journal_volume 216
_journal_year 1994
_journal_page_first 75
_journal_page_last 83
_publ_Section_title
;
 MgB$_2$C$_2$, a new graphite-related refractory compound
;

_aflow_proto 'A2B2C_oC80_64_efg_efg_df'
_aflow_params 'a,b/a,c/a,x1,y2,y3,y4,z4,y5,z5,y6,z6,x7,y7,z7,x8,y8,z8'
_aflow_params_values '10.922,0.866233290606,0.682933528658,0.84657,
    ↪ 0.0946,0.9271,0.5886,0.276,-0.0792,0.2314,0.27981,-0.0113,
    ↪ 0.1278,0.3415,0.2438,0.1245,0.175,0.2231'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oC80'

_symmetry_space_group_name_Hall "-C 2bc 2"
_symmetry_space_group_name_H-M "C m c a"
_symmetry_Int_Tables_number 64

_cell_length_a      10.92200
_cell_length_b      9.46100
_cell_length_c      7.45900
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x+1/2,y,-z+1/2
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x,y,z
7 x+1/2,-y,z+1/2
8 x+1/2,y,-z+1/2
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x,y+1/2,-z+1/2
12 -x,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x,-y+1/2,z+1/2
16 x,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mg1 Mg    8 d 0.84657 0.00000 0.00000 1.00000
B1  B     8 e 0.25000 0.09460 0.25000 1.00000
C1  C     8 e 0.25000 0.92710 0.25000 1.00000
B2  B     8 f 0.00000 0.58860 0.27600 1.00000
C2  C     8 f 0.00000 -0.07920 0.23140 1.00000
Mg2 Mg    8 f 0.00000 0.27981 -0.0113 1.00000
B3  B    16 g 0.12780 0.34150 0.24380 1.00000
C3  C    16 g 0.12450 0.17500 0.22310 1.00000
```

MgB_2C_2: A2B2C_oC80_64_efg_efg_df - POSCAR

```
A2B2C_oC80_64_efg_efg_df & a,b/a,c/a,x1,y2,y3,y4,z4,y5,z5,y6,z6,x7,y7,z7
    ↪ ,x8,y8,z8 --params=10.922,0.866233290606,0.682933528658,0.84657
    ↪ ,0.0946,0.9271,0.5886,0.276,-0.0792,0.2314,0.27981,-0.0113,
    ↪ 0.1278,0.3415,0.2438,0.1245,0.175,0.2231 & Cmca      D_{2h}^{18
    ↪ } #64 (de^2f^3g^2) & oC80 & & MgB2C2 & & M. Worle and R Nespar,
    ↪ J. Alloys and Compd. 216, 75-83 (1994)
   1.0000000000000000
   5.46100000000000   -4.73050000000000    0.00000000000000
   5.46100000000000    4.73050000000000    0.00000000000000
   0.00000000000000    0.00000000000000    7.45900000000000
    B    C    Mg
   16   16    8
Direct
   0.21370000000000   -0.46930000000000   -0.24380000000000    B    (16g)
  -0.21370000000000    0.46930000000000    0.24380000000000    B    (16g)
   0.28630000000000   -0.03070000000000    0.74380000000000    B    (16g)
  -0.28630000000000    0.03070000000000    0.74380000000000    B    (16g)
   0.46930000000000   -0.21370000000000   -0.24380000000000    B    (16g)
  -0.46930000000000    0.21370000000000    0.24380000000000    B    (16g)
   0.96930000000000   -0.71370000000000   -0.25620000000000    B    (16g)
  -0.96930000000000    0.71370000000000    0.25620000000000    B    (16g)
   0.15540000000000    0.34460000000000    0.25000000000000    B     (8e)
  -0.34460000000000    0.84460000000000    0.25000000000000    B     (8e)
   0.34460000000000    1.15540000000000    0.75000000000000    B     (8e)
   0.84460000000000    0.65540000000000    0.75000000000000    B     (8e)
```

```
  0.08860000000000  -0.08860000000000   0.77600000000000   B    (8f)
  0.58860000000000  -0.58860000000000  -0.27600000000000   B    (8f)
 -0.58860000000000   0.58860000000000   0.27600000000000   B    (8f)
 -1.08860000000000   1.08860000000000   0.22400000000000   B    (8f)
  0.05050000000000  -0.29950000000000  -0.22310000000000   C   (16g)
 -0.05050000000000   0.29950000000000   0.22310000000000   C   (16g)
  0.29950000000000  -0.05050000000000  -0.22310000000000   C   (16g)
 -0.29950000000000   0.05050000000000   0.22310000000000   C   (16g)
  0.44950000000000  -0.20050000000000  -0.72310000000000   C   (16g)
 -0.44950000000000   0.20050000000000   0.72310000000000   C   (16g)
  0.79950000000000  -0.55050000000000  -0.27690000000000   C   (16g)
 -0.79950000000000   0.55050000000000   0.27690000000000   C   (16g)
 -0.67710000000000   1.17710000000000   0.25000000000000   C    (8e)
  1.17710000000000   0.32290000000000   0.75000000000000   C    (8e)
 -1.17710000000000   1.67710000000000   0.25000000000000   C    (8e)
  1.67710000000000  -0.17710000000000   0.75000000000000   C    (8e)
  0.07920000000000  -0.07920000000000   0.23140000000000   C    (8f)
 -0.07920000000000   0.07920000000000  -0.23140000000000   C    (8f)
 -0.42080000000000   0.42080000000000   0.26860000000000   C    (8f)
 -0.57920000000000   0.57920000000000   0.73140000000000   C    (8f)
  0.15343000000000   0.15343000000000   0.00000000000000  Mg    (8d)
 -0.15343000000000  -0.15343000000000   0.00000000000000  Mg    (8d)
 -0.34657000000000   0.65343000000000   0.50000000000000  Mg    (8d)
 -0.65343000000000   0.34657000000000   0.50000000000000  Mg    (8d)
 -0.22019000000000   0.22019000000000   0.48870000000000  Mg    (8f)
  0.27981000000000  -0.27981000000000   0.01130000000000  Mg    (8f)
 -0.27981000000000   0.27981000000000  -0.01130000000000  Mg    (8f)
 -0.77981000000000   0.77981000000000   0.51130000000000  Mg    (8f)
```

Black Phosphorus (A17): A_oC8_64_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'black P'
_chemical_formula_sum 'P'

loop_
_publ_author_name
 'Allan Brown'
 'Stig Rundqvist'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 19
_journal_year 1965
_journal_page_first 684
_journal_page_last 685
_publ_Section_title
;
 Refinement of the crystal structure of black phosphorus
;

_aflow_proto 'A_oC8_64_f'
_aflow_params 'a,b/a,c/a,y1,z1'
_aflow_params_values '3.3136,3.16211974891,1.32070859488,0.10168,0.08056
    ↪ '
_aflow_Strukturbericht 'A17'
_aflow_Pearson 'oC8'

_symmetry_space_group_name_Hall "-C 2bc 2"
_symmetry_space_group_name_H-M "C m c a"
_symmetry_Int_Tables_number 64

_cell_length_a    3.31360
_cell_length_b    10.47800
_cell_length_c    4.37630
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x+1/2,y,-z+1/2
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x,y,z
7 x+1/2,-y,z+1/2
8 x+1/2,y,-z+1/2
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x,y+1/2,-z+1/2
12 -x,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x,-y+1/2,z+1/2
16 x,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
P1 P   8 f 0.00000 0.10168 0.08056 1.00000
```

Black Phosphorus (A17): A_oC8_64_f - POSCAR

```
A_oC8_64_f & a,b/a,c/a,y1,z1 --params=3.3136,3.16211974891,1.32070859488
    ↪ ,0.10168,0.08056 & Cmca      D_{2h}^{18} #64 (f) & oC8 & A17 &
    ↪ P & Black Phosphorous & A. Brown and S. Rundqvist, Acta Cryst.
    ↪ 19, 684-685 (1965)
   1.0000000000000000
   1.65680000000000  -5.23900000000000   0.00000000000000
   1.65680000000000   5.23900000000000   0.00000000000000
   0.00000000000000   0.00000000000000   4.37630000000000
    P
    4
Direct
   0.10168000000000   0.89832000000000   0.91944000000000   P    (8f)
   0.39832000000000   0.60168000000000   0.41944000000000   P    (8f)
   0.60168000000000   0.39832000000000   0.58056000000000   P    (8f)
   0.89832000000000   0.10168000000000   0.08056000000000   P    (8f)
```

Molecular Iodine (I) (A14): A_oC8_64_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'I'

loop_
_publ_author_name
 'C. Petrillo'
 'O. Moze'
 'R. M. Ibberson'
_journal_name_full
;
Physica B
;
_journal_volume 180-181
_journal_year 1992
_journal_page_first 639
_journal_page_last 641
_publ_Section_title
;
 High resolution neutron powder diffraction investigation of the low
    ↪ temperature crystal structure of molecular iodine (I$_2$)
;

# Found in  http://www.webelements.com/iodine/crystal_structure.html

_aflow_proto 'A_oC8_64_f'
_aflow_params 'a,b/a,c/a,y1,z1'
_aflow_params_values '7.11906,0.654575182679,1.37596817557,0.15485,
    ↪ 0.1175'
_aflow_Strukturbericht 'A14'
_aflow_Pearson 'oC8'

_symmetry_space_group_name_Hall "-C 2bc 2"
_symmetry_space_group_name_H-M "C m c a"
_symmetry_Int_Tables_number 64

_cell_length_a    7.11906
_cell_length_b    4.65996
_cell_length_c    9.79560
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x+1/2,y,-z+1/2
4 -x+1/2,-y,z+1/2
5 -x,-y,-z
6 -x,y,z
7 x+1/2,-y,z+1/2
8 x+1/2,y,-z+1/2
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x,y+1/2,-z+1/2
12 -x,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x,-y+1/2,z+1/2
16 x,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
I1 I   8 f 0.00000 0.15485 0.11750 1.00000
```

Molecular Iodine (I) (A14): A_oC8_64_f - POSCAR

```
A_oC8_64_f & a,b/a,c/a,y1,z1 --params=7.11906,0.654575182679,
    ↪ 1.37596817557,0.15485,0.1175 & Cmca      D_{2h}^{18} #64 (f) &
    ↪ oC8 & A14 & I & Iodine & C. Petrillo, O. Moze and R. M.
    ↪ Ibberson, Physica B 180 & 181 639-641 (1992)
   1.0000000000000000
```

```
   3.55953000000000   -2.32998000000000    0.00000000000000
   3.55953000000000    2.32998000000000    0.00000000000000
   0.00000000000000    0.00000000000000    9.79560000000000
    I
    4
Direct
   0.15485000000000    0.84515000000000    0.88250000000000    I    (8f)
   0.34515000000000    0.65485000000000    0.38250000000000    I    (8f)
   0.65485000000000    0.34515000000000    0.61750000000000    I    (8f)
   0.84515000000000    0.15485000000000    0.11750000000000    I    (8f)
```

α-IrV: AB_oC8_65_j_g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha iridium vanadium'
_chemical_formula_sum 'Ir V'

loop_
_publ_author_name
 'B. C. Giessen'
 'N. J. Grant'
_journal_name_full
;
Acta Crytallographica
;
_journal_volume 18
_journal_year 1965
_journal_page_first 1080
_journal_page_last 1081
_publ_Section_title
;
 New intermediate phases in transition metal systems, III
;

# Found in  Pearson's Handbook, Vol. IV, pp. 4139

_aflow_proto 'AB_oC8_65_j_g'
_aflow_params 'a,b/a,c/a,x1,y2'
_aflow_params_values '5.971,1.1314687657,0.468263272484,0.28,0.22'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oC8'

_symmetry_space_group_name_Hall "-C 2 2 "
_symmetry_space_group_name_H-M "C m m m"
_symmetry_Int_Tables_number 65

_cell_length_a     5.97100
_cell_length_b     6.75600
_cell_length_c     2.79600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -x,-y,-z
6 -x,y,z
7 x,-y,z
8 x,y,-z
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x+1/2,y+1/2,-z
12 -x+1/2,-y+1/2,z
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x+1/2,-y+1/2,z
16 x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
V1  V    4 g 0.28000 0.00000 0.00000 1.00000
Ir1 Ir   4 j 0.00000 0.22000 0.50000 1.00000
```

α-IrV: AB_oC8_65_j_g - POSCAR

```
AB_oC8_65_j_g & a,b/a,c/a,x1,y2 --params=5.971,1.1314687657,
      ↪ 0.468263272484,0.28,0.22 & Cmmm      D_{2h}^{19} #65 (gj) & oC8
      ↪ & & IrV & alpha & B. C. Giessen and N. J. Grant, Acta Cryst.
      ↪ 18, 1080-1081 (1965)
   1.0000000000000000
   2.98550000000000   -3.37800000000000    0.00000000000000
   2.98550000000000    3.37800000000000    0.00000000000000
   0.00000000000000    0.00000000000000    2.79600000000000
   Ir    V
    2    2
Direct
   0.22000000000000    0.78000000000000    0.50000000000000    Ir    (4j)
   0.78000000000000    0.22000000000000    0.50000000000000    Ir    (4j)
   0.28000000000000    0.28000000000000    0.00000000000000    V     (4g)
   0.72000000000000    0.72000000000000    0.00000000000000    V     (4g)
```

Ga_3Pt_5: A3B5_oC16_65_ah_bej - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ga3 Pt5'

loop_
_publ_author_name
 'K. Schubert'
 'S. Bhan'
 'W. Burkhardt'
 'R. Gohle'
 'H. G. Meissner'
 'M. P\"{o}tzschke'
 'E. Stolz'
_journal_name_full
;
Naturwissenschaften
;
_journal_volume 47
_journal_year 1960
_journal_page_first 303
_journal_page_last 303
_publ_Section_title
;
 Einige strukturelle Ergebnisse an metallischen Phasen (5)
;

# Found in  Pearson's Handbook III, p. 3540

_aflow_proto 'A3B5_oC16_65_ah_bej'
_aflow_params 'a,b/a,c/a,x4,y5'
_aflow_params_values '8.031,0.926410160628,0.491595069107,0.25,0.225'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oC16'

_symmetry_space_group_name_Hall "-C 2 2 "
_symmetry_space_group_name_H-M "C m m m"
_symmetry_Int_Tables_number 65

_cell_length_a     8.03100
_cell_length_b     7.44000
_cell_length_c     3.94800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -x,-y,-z
6 -x,y,z
7 x,-y,z
8 x,y,-z
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x+1/2,y+1/2,-z
12 -x+1/2,-y+1/2,z
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x+1/2,-y+1/2,z
16 x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ga1 Ga   2 a 0.00000 0.00000 0.00000 1.00000
Pt1 Pt   2 b 0.50000 0.00000 0.00000 1.00000
Pt2 Pt   4 e 0.25000 0.25000 0.00000 1.00000
Ga2 Ga   4 h 0.25000 0.00000 0.50000 1.00000
Pt3 Pt   4 j 0.00000 0.22500 0.50000 1.00000
```

Ga_3Pt_5: A3B5_oC16_65_ah_bej - POSCAR

```
A3B5_oC16_65_ah_bej & a,b/a,c/a,x4,y5 --params=8.031,0.926410160628,
      ↪ 0.491595069107,0.25,0.225 & Cmmm      D_{2h}^{19} #65 (abehj) &
      ↪ oC16 & & Ga3Pt5 & & K. Schubert, S. Bhan et al.,
      ↪ Naturwissenschaften 47, 303 (1960)
   1.0000000000000000
   4.01550000000000   -3.72000000000000    0.00000000000000
   4.01550000000000    3.72000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.94800000000000
   Ga    Pt
    3    5
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Ga    (2a)
   0.25000000000000    0.25000000000000    0.50000000000000    Ga    (4h)
   0.75000000000000    0.75000000000000    0.50000000000000    Ga    (4h)
   0.50000000000000    0.50000000000000    0.00000000000000    Pt    (2b)
```

```
    0.00000000000000    0.50000000000000    0.00000000000000    Pt    (4e)
    0.50000000000000    0.00000000000000    0.00000000000000    Pt    (4e)
    0.22500000000000    0.77500000000000    0.50000000000000    Pt    (4j)
    0.77500000000000    0.22500000000000    0.50000000000000    Pt    (4j)
```

Predicted $CdPt_3$ ("$L1_3$"): AB3_oC8_65_a_bf - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cd Pt3'

loop_
_publ_author_name
 'Gus L. W. Hart'
_journal_name_full
;
Physical Review B
;
_journal_volume 80
_journal_year 2009
_journal_page_first 014106
_journal_page_last 014106
_publ_Section_title
;
 Verifying predictions of the L1$_3$ crystal structure in Cd-Pt and
      ↪ Pd-Pt by exhaustive enumeration
;

_aflow_proto 'AB3_oC8_65_a_bf'
_aflow_params 'a,b/a,c/a'
_aflow_params_values '5.82068,1.35259626023,0.493507631411'
_aflow_Strukturbericht 'L1_3'
_aflow_Pearson 'oC8'

_symmetry_space_group_name_Hall "-C 2 2 "
_symmetry_space_group_name_H-M "C m m m"
_symmetry_Int_Tables_number 65

_cell_length_a      5.82068
_cell_length_b      7.87303
_cell_length_c      2.87255
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -x,-y,-z
6 -x,y,z
7 x,-y,z
8 x,y,-z
9 x+1/2,y+1/2,z
10 x+1/2,-y+1/2,-z
11 -x+1/2,y+1/2,-z
12 -x+1/2,-y+1/2,z
13 -x+1/2,-y+1/2,-z
14 -x+1/2,y+1/2,z
15 x+1/2,-y+1/2,z
16 x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cd1 Cd    2 a 0.00000 0.00000 0.00000 1.00000
Pt1 Pt    2 b 0.50000 0.00000 0.00000 1.00000
Pt2 Pt    4 f 0.25000 0.25000 0.50000 1.00000
```

Predicted $CdPt_3$ ("$L1_3$"): AB3_oC8_65_a_bf - POSCAR

```
AB3_oC8_65_a_bf & a,b/a,c/a --params=5.82068,1.35259626023,
      ↪ 0.493507631411 & Cmmm      D_{2h}^{19} #65 (abf) & oC8 & L1_3 &
      ↪  CdPt3 & Predicted & G.L.W. Hart, PRB 80, 014106 (2009)
   1.0000000000000000
   2.91034000000000   -3.93651500000000    0.00000000000000
   2.91034000000000    3.93651500000000    0.00000000000000
   0.00000000000000    0.00000000000000    2.87255000000000
   Cd    Pt
    1     3
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cd    (2a)
   0.50000000000000    0.50000000000000    0.00000000000000    Pt    (2b)
   0.00000000000000    0.50000000000000    0.50000000000000    Pt    (4f)
   0.50000000000000    0.00000000000000    0.50000000000000    Pt    (4f)
```

TlF (B24): AB_oF8_69_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Tl F'

loop_
_publ_author_name
 'J. A. A. Ketelaar'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 92
_journal_year 1935
_journal_page_first 30
_journal_page_last 38
_publ_Section_title
;
 Die Kristallstruktur des Thallofluorids
;

# Found in P. Berastegui and S. Hull, J. Solid State Chem. 150, 266-75 (
      ↪ 2000)

_aflow_proto 'AB_oF8_69_a_b'
_aflow_params 'a,b/a,c/a'
_aflow_params_values '6.08,0.903782894737,0.851973684211'
_aflow_Strukturbericht 'B24'
_aflow_Pearson 'oF8'

_symmetry_space_group_name_Hall "-F 2 2"
_symmetry_space_group_name_H-M "F m m m"
_symmetry_Int_Tables_number 69

_cell_length_a      6.08000
_cell_length_b      5.49500
_cell_length_c      5.18000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -x,-y,-z
6 -x,y,z
7 x,-y,z
8 x,y,-z
9 x,y+1/2,z+1/2
10 x,-y+1/2,-z+1/2
11 -x,y+1/2,-z+1/2
12 -x,-y+1/2,z+1/2
13 -x,-y+1/2,-z+1/2
14 -x,y+1/2,z+1/2
15 x,-y+1/2,z+1/2
16 x,y+1/2,-z+1/2
17 x+1/2,y,z+1/2
18 x+1/2,-y,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
21 -x+1/2,-y,-z+1/2
22 -x+1/2,y,z+1/2
23 x+1/2,-y,z+1/2
24 x+1/2,y,-z+1/2
25 x+1/2,y+1/2,z
26 x+1/2,-y+1/2,-z
27 -x+1/2,y+1/2,-z
28 -x+1/2,-y+1/2,z
29 -x+1/2,-y+1/2,-z
30 -x+1/2,y+1/2,z
31 x+1/2,-y+1/2,z
32 x+1/2,y+1/2,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
F1  F     4 a 0.00000 0.00000 0.00000 1.00000
Tl1 Tl    4 b 0.00000 0.00000 0.50000 1.00000
```

TlF (B24): AB_oF8_69_a_b - POSCAR

```
AB_oF8_69_a_b & a,b/a,c/a --params=6.08,0.903782894737,0.851973684211 &
      ↪ Fmmm      D_{2h}^{23} #69 (ab) & oF8 & B24 & TlF & & J. A. A.
      ↪ Ketellar, Zeitschrift f\"{u}r Kristallographie - Crystalline
      ↪ Materials 92, 30-38 (1935)
   1.0000000000000000
   0.00000000000000    2.74750000000000    2.59000000000000
   3.04000000000000    0.00000000000000    2.59000000000000
   3.04000000000000    2.74750000000000    0.00000000000000
    F    Tl
    1     1
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    F     (4a)
   0.50000000000000    0.50000000000000    0.50000000000000    Tl    (4b)
```

γ-Pu: A_oF8_70_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'gamma plutonium'
_chemical_formula_sum 'Pu'

loop_
_publ_author_name
 'W. H. Zachariasen'
 'F. H. Ellinger'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 8
_journal_year 1955
_journal_page_first 431
_journal_page_last 433
_publ_Section_title
;
 Crystal chemical studies of the 5f-series of elements. XXIV. The
      ↪ crystal structure and thermal expansion of $\gamma$-plutonium
;

_aflow_proto 'A_oF8_70_a'
_aflow_params 'a,b/a,c/a'
_aflow_params_values '3.1587,1.82613100326,3.21714629436'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oF8'

_symmetry_space_group_name_Hall "-F 2uv 2vw"
_symmetry_space_group_name_H-M "F d d d:2"
_symmetry_Int_Tables_number 70

_cell_length_a      3.15870
_cell_length_b      5.76820
_cell_length_c      10.16200
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+3/4,-z+3/4
3 -x+3/4,y,-z+3/4
4 -x+3/4,-y+3/4,z
5 -x,-y,-z
6 -x,y+1/4,z+1/4
7 x+1/4,-y,z+1/4
8 x+1/4,y+1/4,-z
9 x,y+1/2,z+1/2
10 x,-y+1/4,-z+1/4
11 -x+3/4,y+1/2,-z+1/4
12 -x+3/4,-y+1/4,z+1/2
13 -x,-y+1/2,-z+1/2
14 -x,y+3/4,z+3/4
15 x+1/4,-y+1/2,z+3/4
16 x+1/4,y+3/4,-z+1/2
17 x+1/2,y,z+1/2
18 x+1/2,-y+3/4,-z+1/4
19 -x+1/4,y,-z+1/4
20 -x+1/4,-y+3/4,z+1/2
21 -x+1/2,-y,-z+1/2
22 -x+1/2,y+1/4,z+3/4
23 x+3/4,-y,z+3/4
24 x+3/4,y+1/4,-z+1/2
25 x+1/2,y+1/2,z
26 x+1/2,-y+1/4,-z+3/4
27 -x+1/4,y+1/2,-z+3/4
28 -x+1/4,-y+1/4,z
29 -x+1/2,-y+1/2,-z
30 -x+1/2,y+3/4,z+1/4
31 x+3/4,-y+1/2,z+1/4
32 x+3/4,y+3/4,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pu1 Pu    8 a 0.12500 0.12500 0.12500 1.00000
```

γ-Pu: A_oF8_70_a - POSCAR

```
A_oF8_70_a & a,b/a,c/a --params=3.1587,1.82613100326,3.21714629436 &
      ↪ Fddd        D_{2h}^{24} #70 (a) & oF8 & & Pu & gamma & W. H.
      ↪ Zachariasen and F. H. Ellinger, Acta Cryst. B 8, 431-433 (1955)
   1.0000000000000000
   0.00000000000000    2.88410000000000    5.08100000000000
   1.57935000000000    0.00000000000000    5.08100000000000
   1.57935000000000    2.88410000000000    0.00000000000000
   Pu
    2
Direct
   0.12500000000000    0.12500000000000    0.12500000000000    Pu    (8a)
   0.87500000000000    0.87500000000000    0.87500000000000    Pu    (8a)
```

$TiSi_2$ (C54): A2B_oF24_70_e_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Titanium Disilicide'
_chemical_formula_sum 'Ti Si2'

loop_
_publ_author_name
 'W. Jeitschko'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 33
_journal_year 1977
_journal_page_first 2347
_journal_page_last 2348
_publ_Section_title
;
 Refinement of the crystal structure of TiSi$_2$ and some comments on
      ↪ bonding in TiSi$_2$ and related compounds
;

_aflow_proto 'A2B_oF24_70_e_a'
_aflow_params 'a,b/a,c/a,x2'
_aflow_params_values '8.2671,0.580614725841,1.0342804611,0.4615'
_aflow_Strukturbericht 'C54'
_aflow_Pearson 'oF24'

_symmetry_space_group_name_Hall "-F 2uv 2vw"
_symmetry_space_group_name_H-M "F d d d:2"
_symmetry_Int_Tables_number 70

_cell_length_a      8.26710
_cell_length_b      4.80000
_cell_length_c      8.55050
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+3/4,-z+3/4
3 -x+3/4,y,-z+3/4
4 -x+3/4,-y+3/4,z
5 -x,-y,-z
6 -x,y+1/4,z+1/4
7 x+1/4,-y,z+1/4
8 x+1/4,y+1/4,-z
9 x,y+1/2,z+1/2
10 x,-y+1/4,-z+1/4
11 -x+3/4,y+1/2,-z+1/4
12 -x+3/4,-y+1/4,z+1/2
13 -x,-y+1/2,-z+1/2
14 -x,y+3/4,z+3/4
15 x+1/4,-y+1/2,z+3/4
16 x+1/4,y+3/4,-z+1/2
17 x+1/2,y,z+1/2
18 x+1/2,-y+3/4,-z+1/4
19 -x+1/4,y,-z+1/4
20 -x+1/4,-y+3/4,z+1/2
21 -x+1/2,-y,-z+1/2
22 -x+1/2,y+1/4,z+3/4
23 x+3/4,-y,z+3/4
24 x+3/4,y+1/4,-z+1/2
25 x+1/2,y+1/2,z
26 x+1/2,-y+1/4,-z+3/4
27 -x+1/4,y+1/2,-z+3/4
28 -x+1/4,-y+1/4,z
29 -x+1/2,-y+1/2,-z
30 -x+1/2,y+3/4,z+1/4
31 x+3/4,-y+1/2,z+1/4
32 x+3/4,y+3/4,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1 Ti    8 a 0.12500 0.12500 0.12500 1.00000
Si1 Si   16 e 0.46150 0.12500 0.12500 1.00000
```

$TiSi_2$ (C54): A2B_oF24_70_e_a - POSCAR

```
A2B_oF24_70_e_a & a,b/a,c/a,x2 --params=8.2671,0.580614725841,
      ↪ 1.0342804611,0.4615 & Fddd        D_{2h}^{24} #70 (ae) & oF24 &
      ↪ C54 & TiSi2 & & W. Jeitschko, Acta Cryst. B 33, 2347-2348 (1977
      ↪ )
   1.0000000000000000
   0.00000000000000    2.40000000000000    4.27525000000000
   4.13355000000000    0.00000000000000    4.27525000000000
   4.13355000000000    2.40000000000000    0.00000000000000
   Si    Ti
```

```
    4     2
Direct
   0.21150000000000   0.53850000000000   0.53850000000000   Si   (16e)
   0.46150000000000   0.78850000000000   0.78850000000000   Si   (16e)
   0.53850000000000   0.21150000000000   0.21150000000000   Si   (16e)
   0.78850000000000   0.46150000000000   0.46150000000000   Si   (16e)
   0.12500000000000   0.12500000000000   0.12500000000000   Ti    (8a)
   0.87500000000000   0.87500000000000   0.87500000000000   Ti    (8a)
```

α-S (A16): A_oF128_70_4h - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha'
_chemical_formula_sum 'S'

loop_
_publ_author_name
 'Steven J. Rettig'
 'James Trotter'
_journal_name_full
;
Acta Crystallographic C
;
_journal_volume 43
_journal_year 1987
_journal_page_first 2260
_journal_page_last 2262
_publ_Section_title
;
 Refinement of the structure of orthorhombic sulfur, $\alpha$-S$_8$
;

_aflow_proto 'A_oF128_70_4h'
_aflow_params 'a,b/a,c/a,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4'
_aflow_params_values '10.4646,1.22947843205,2.33988876785,0.14415,
    ↪ 0.04732,0.0486,0.29277,0.2269,0.25406,0.21598,0.28022,0.32618,
    ↪ 0.21405,0.15761,0.37947'
_aflow_Strukturbericht 'A16'
_aflow_Pearson 'oF128'

_symmetry_space_group_name_Hall "-F 2uv 2vw"
_symmetry_space_group_name_H-M "F d d d:2"
_symmetry_Int_Tables_number 70

_cell_length_a      10.46460
_cell_length_b      12.86600
_cell_length_c      24.48600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+3/4,-z+3/4
3 -x+3/4,y,-z+3/4
4 -x+3/4,-y+3/4,z
5 -x,-y,-z
6 -x,y+1/4,z+1/4
7 x+1/4,-y,z+1/4
8 x+1/4,y+1/4,-z
9 x,y+1/2,z+1/2
10 x,-y+1/4,-z+1/4
11 -x+3/4,y+1/2,-z+1/4
12 -x+3/4,-y+1/4,z+1/2
13 -x,-y+1/2,-z+1/2
14 -x,y+3/4,z+3/4
15 x+1/4,-y+1/2,z+3/4
16 x+1/4,y+3/4,-z+1/2
17 x+1/2,y,z+1/2
18 x+1/2,-y+3/4,-z+1/4
19 -x+1/4,y,-z+1/4
20 -x+1/4,-y+3/4,z+1/2
21 -x+1/2,-y,-z+1/2
22 -x+1/2,y+1/4,z+3/4
23 x+3/4,-y,z+3/4
24 x+3/4,y+1/4,-z+1/2
25 x+1/2,y+1/2,z
26 x+1/2,-y+1/4,-z+3/4
27 -x+1/4,y+1/2,-z+3/4
28 -x+1/4,-y+1/4,z
29 -x+1/2,-y+1/2,-z
30 -x+1/2,y+3/4,z+1/4
31 x+3/4,-y+1/2,z+1/4
32 x+3/4,y+3/4,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
S1 S  32 h 0.14415 0.04732 0.04860 1.00000
S2 S  32 h 0.29277 0.22690 0.25406 1.00000
S3 S  32 h 0.21598 0.28022 0.32618 1.00000
S4 S  32 h 0.21405 0.15761 0.37947 1.00000
```

α-S (A16): A_oF128_70_4h - POSCAR

```
A_oF128_70_4h & a,b/a,c/a,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4 --params=
    ↪ 10.4646,1.22947843205,2.33988876785,0.14415,0.04732,0.0486,
    ↪ 0.29277,0.2269,0.25406,0.21598,0.28022,0.32618,0.21405,0.15761,
    ↪ 0.37947 & Fddd      D_{2h}^{24} #70 (h^4) & oF128 & A16 & S & (
    ↪ alpha sulfur) & S. Rettig and J. Trotter, Acta Cryst. C 43,
    ↪ 2260-2262 (1987)
   1.0000000000000000
   0.00000000000000   6.43300000000000   12.24300000000000
   5.23230000000000   0.00000000000000   12.24300000000000
   5.23230000000000   6.43300000000000    0.00000000000000
    S
   32
Direct
   0.04823000000000   0.85457000000000   0.85713000000000   S   (32h)
   0.74007000000000   0.85713000000000   0.85457000000000   S   (32h)
   0.85713000000000   0.74007000000000   0.04823000000000   S   (32h)
   0.85457000000000   0.04823000000000   0.74007000000000   S   (32h)
  -0.04823000000000   0.14543000000000   0.14287000000000   S   (32h)
   0.25993000000000   0.14287000000000   0.14543000000000   S   (32h)
   0.14287000000000   0.25993000000000  -0.04823000000000   S   (32h)
   0.14543000000000  -0.04823000000000   0.25993000000000   S   (32h)
   0.27373000000000   0.73439000000000   0.68007000000000   S   (32h)
   0.81181000000000   0.68007000000000   0.73439000000000   S   (32h)
   0.68007000000000   0.81181000000000   0.27373000000000   S   (32h)
   0.73439000000000   0.27373000000000   0.81181000000000   S   (32h)
   0.72627000000000   0.26561000000000   0.31993000000000   S   (32h)
   0.18819000000000   0.31993000000000   0.26561000000000   S   (32h)
   0.31993000000000   0.18819000000000   0.72627000000000   S   (32h)
   0.26561000000000   0.72627000000000   0.18819000000000   S   (32h)
   0.32238000000000   0.82998000000000   0.73806000000000   S   (32h)
   0.60958000000000   0.73806000000000   0.82998000000000   S   (32h)
   0.73806000000000   0.60958000000000   0.32238000000000   S   (32h)
   0.82998000000000   0.32238000000000   0.60958000000000   S   (32h)
   0.67762000000000   0.17002000000000   0.26194000000000   S   (32h)
   0.39042000000000   0.26194000000000   0.17002000000000   S   (32h)
   0.26194000000000   0.39042000000000   0.67762000000000   S   (32h)
   0.17002000000000   0.67762000000000   0.39042000000000   S   (32h)
   0.25113000000000   0.00781000000000   0.56409000000000   S   (32h)
   0.67697000000000   0.56409000000000   0.00781000000000   S   (32h)
   0.56409000000000   0.67697000000000   0.25113000000000   S   (32h)
   0.00781000000000   0.25113000000000   0.67697000000000   S   (32h)
   0.74887000000000  -0.00781000000000   0.43591000000000   S   (32h)
   0.32303000000000   0.43591000000000  -0.00781000000000   S   (32h)
   0.43591000000000   0.32303000000000   0.74887000000000   S   (32h)
  -0.00781000000000   0.74887000000000   0.32303000000000   S   (32h)
```

$ReSi_2$: AB2_oI6_71_a_i - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Re Si2'

loop_
_publ_author_name
 'T. Siegrist'
 'F. Hulliger'
 'G. Travaglini'
_journal_name_full
;
Journal of the Less Common Metals
;
_journal_volume 92
_journal_year 1983
_journal_page_first 119
_journal_page_last 129
_publ_Section_title
;
 The crystal structure and some properties of ReSi$_2$
;

_aflow_proto 'AB2_oI6_71_a_i'
_aflow_params 'a,b/a,c/a,z2'
_aflow_params_values '3.144,0.994910941476,2.44179389313,0.339'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oI6'

_symmetry_space_group_name_Hall "-I 2 2 "
_symmetry_space_group_name_H-M "I m m m"
_symmetry_Int_Tables_number 71

_cell_length_a      3.14400
_cell_length_b      3.12800
_cell_length_c      7.67700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -x,-y,-z
6 -x,y,z
7 x,-y,z
8 x,y,-z
9 x+1/2,y+1/2,z+1/2
```

```
10 x+1/2,-y+1/2,-z+1/2
11 -x+1/2,y+1/2,-z+1/2
12 -x+1/2,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z+1/2
14 -x+1/2,y+1/2,z+1/2
15 x+1/2,-y+1/2,z+1/2
16 x+1/2,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Re1 Re   2 a 0.00000 0.00000 0.00000 1.00000
Si1 Si   4 i 0.00000 0.00000 0.33900 1.00000
```

$ReSi_2$: AB2_oI6_71_a_i - POSCAR

```
AB2_oI6_71_a_i & a,b/a,c/a,z2 --params=3.144,0.994910941476,
    ↪ 2.44179389313,0.339 & Immm      D_{2h}^{25} #71 (ai) & oI6 & &
    ↪ ReSi2 & & T. Siegrist, F. Hulliger and G. Travaglini, J.
    ↪ Less-Common Metals 92, 119-129 (1983)
  1.0000000000000000
 -1.56400000000000   1.57200000000000   3.83850000000000
  1.56400000000000  -1.57200000000000   3.83850000000000
  1.56400000000000   1.57200000000000  -3.83850000000000
  Re   Si
   1    2
Direct
  0.00000000000000   0.00000000000000   0.00000000000000   Re   (2a)
  0.33900000000000   0.33900000000000   0.00000000000000   Si   (4i)
  0.66100000000000   0.66100000000000   0.00000000000000   Si   (4i)
```

$MoPt_2$: AB2_oI6_71_a_g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Mo Pt2'

loop_
_publ_author_name
 'K. Schubert'
 'W. Burkhardt'
 'P. Esslinger'
 'E. G\"{u}nzel'
 'H. G. Meissner'
 'W. Sch\"{u}tt'
 'J. Wegst'
 'M. Wilkens'
_journal_name_full
;
Naturwissenschaften
;
_journal_volume 43
_journal_year 1956
_journal_page_first 248
_journal_page_last 249
_publ_Section_title
;
 Einige strukturelle Ergebnisse an metallischen Phasen
;

# Found in http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_1250591

_aflow_proto 'AB2_oI6_71_a_g'
_aflow_params 'a,b/a,c/a,y2'
_aflow_params_values '2.75984,2.9999963766,1.4241115427,0.35333'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'oI6'

_symmetry_space_group_name_Hall "-I 2 2 "
_symmetry_space_group_name_H-M "I m m m"
_symmetry_Int_Tables_number 71

_cell_length_a     2.75984
_cell_length_b     8.27951
_cell_length_c     3.93032
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -x,-y,-z
6 -x,y,z
7 x,-y,z
8 x,y,-z
9 x+1/2,y+1/2,z+1/2
10 x+1/2,-y+1/2,-z+1/2
11 -x+1/2,y+1/2,-z+1/2
12 -x+1/2,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z+1/2
14 -x+1/2,y+1/2,z+1/2
15 x+1/2,-y+1/2,z+1/2
16 x+1/2,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mo1 Mo   2 a 0.00000 0.00000 0.00000 1.00000
Pt1 Pt   4 g 0.00000 0.35333 0.00000 1.00000
```

$MoPt_2$: AB2_oI6_71_a_g - POSCAR

```
AB2_oI6_71_a_g & a,b/a,c/a,y2 --params=2.75984,2.9999963766,1.4241115427
    ↪ ,0.35333 & Immm      D_{2h}^{25} #71 (ag) & oI6 & & MoPt_2 & &
    ↪ K. Schubert et al., Naturwissenschaften 43, 248-249 (1956)
  1.0000000000000000
 -1.37991888000000   4.13975665000000   1.96516050000000
  1.37991888000000  -4.13975665000000   1.96516050000000
  1.37991888000000   4.13975665000000  -1.96516050000000
  Mo   Pt
   1    2
Direct
  0.00000000000000   0.00000000000000   0.00000000000000   Mo   (2a)
  0.35333333000000   0.00000000000000   0.35333333000000   Pt   (4g)
  0.64666667000000   0.00000000000000   0.64666667000000   Pt   (4g)
```

SiS_2: A2B_oI12_72_j_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Silicon Disuphide'
_chemical_formula_sum 'Si S2'

loop_
_publ_author_name
 'Johannes Peters'
 'Bernt Krebs'
_journal_name_full
;
Acta Crystallographic B
;
_journal_volume 38
_journal_year 1982
_journal_page_first 1270
_journal_page_last 1272
_publ_Section_title
;
 Silicon disulphide and silicon diselenide: a reinvestigation
;

_aflow_proto 'A2B_oI12_72_j_a'
_aflow_params 'a,b/a,c/a,x2,y2'
_aflow_params_values '9.583,0.585829072316,0.578837524783,0.1182,0.2088'
_aflow_Strukturbericht 'C42'
_aflow_Pearson 'oI12'

_symmetry_space_group_name_Hall "-I 2 2c"
_symmetry_space_group_name_H-M "I b a m"
_symmetry_Int_Tables_number 72

_cell_length_a     9.58300
_cell_length_b     5.61400
_cell_length_c     5.54700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x,y,-z+1/2
4 -x,-y,z
5 -x,-y,-z
6 -x,y,z+1/2
7 x,-y,z+1/2
8 x,y,-z
9 x+1/2,y+1/2,z+1/2
10 x+1/2,-y+1/2,-z
11 -x+1/2,y+1/2,-z
12 -x+1/2,-y+1/2,z+1/2
13 -x+1/2,-y+1/2,-z+1/2
14 -x+1/2,y+1/2,z
15 x+1/2,-y+1/2,z
16 x+1/2,y+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
```

```
_atom_site_occupancy
Si1  Si    4  a  0.00000  0.00000  0.25000  1.00000
S1   S     8  j  0.11820  0.20880  0.00000  1.00000
```

SiS_2: A2B_oI12_72_j_a - POSCAR

```
A2B_oI12_72_j_a & a,b/a,c/a,x2,y2 --params=9.583,0.585829072316,
    ↪ 0.578837524783,0.1182,0.2088 & Ibam      D_{2h}^{26} #72 (aj) &
    ↪ oI12 & C42 & SiS2 & & J. Peters and B. Krebs, Acta Cryst. B 38,
    ↪  1270-1272 (1982)
   1.0000000000000000
  -4.79150000000000    2.80700000000000    2.77350000000000
   4.79150000000000   -2.80700000000000    2.77350000000000
   4.79150000000000    2.80700000000000   -2.77350000000000
    S    Si
    4     2
Direct
   0.20880000000000    0.11820000000000    0.32700000000000     S     (8j)
   0.29120000000000    0.61820000000000   -0.09060000000000     S     (8j)
   0.70880000000000    0.38180000000000    0.09060000000000     S     (8j)
   0.79120000000000    0.88180000000000    0.67300000000000     S     (8j)
   0.25000000000000    0.25000000000000    0.00000000000000    Si     (4a)
   0.75000000000000    0.75000000000000    0.00000000000000    Si     (4a)
```

BPO_4 ($H0_7$): AB4C_tI12_82_c_g_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'B P O4'

loop_
_publ_author_name
 'M. Schmidt'
 'B. Ewald'
 'Yu. Prots'
 'R. Cardoso-Gil'
 'M. Armbr\"{u}ster'
 'I. Loa'
 'L. Zhang'
 'Ya-Xi Huang'
 'U. Schwarz'
 'R. Kniep'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 630
_journal_year 2004
_journal_page_first 655
_journal_page_last 662
_publ_Section_title
;
 Growth and Characterization of BPO$_4$ Single Crystals
;

_aflow_proto 'AB4C_tI12_82_c_g_a'
_aflow_params 'a,c/a,x3,y3,z3'
_aflow_params_values '4.3404,1.53216293429,0.256,0.2566,0.3722'
_aflow_Strukturbericht 'H0_7'
_aflow_Pearson 'tI12'

_symmetry_space_group_name_Hall "I -4"
_symmetry_space_group_name_H-M "I -4"
_symmetry_Int_Tables_number 82

_cell_length_a      4.34040
_cell_length_b      4.34040
_cell_length_c      6.65020
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 y,-x,-z
4 -y,x,-z
5 x+1/2,y+1/2,z+1/2
6 -x+1/2,-y+1/2,z+1/2
7 y+1/2,-x+1/2,-z+1/2
8 -y+1/2,x+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
P1  P    2  a  0.00000  0.00000  0.00000  1.00000
B1  B    2  c  0.00000  0.50000  0.25000  1.00000
O1  O    8  g  0.25600  0.25660  0.37220  1.00000
```

BPO_4 ($H0_7$): AB4C_tI12_82_c_g_a - POSCAR

```
AB4C_tI12_82_c_g_a & a,c/a,x3,y3,z3 --params=4.3404,1.53216293429,0.256,
    ↪ 0.2566,0.3722 & I(-4)      S_4^2 #82 (acg) & tI12 & H0_7 & BPO4
    ↪ & & M. Schmidt et al., Z. Anorg. Allg. Chem. 630, 655-662 (2004
    ↪ )
   1.0000000000000000
  -2.17020000000000    2.17020000000000    3.32510000000000
   2.17020000000000   -2.17020000000000    3.32510000000000
   2.17020000000000    2.17020000000000   -3.32510000000000
    B    O    P
    1    4    1
Direct
   0.75000000000000    0.25000000000000    0.50000000000000     B     (2c)
   0.11560000000000    0.11620000000000    0.48740000000000     O     (8g)
   0.37180000000000    0.88440000000000    0.00060000000000     O     (8g)
   0.62880000000000    0.62820000000000    0.51260000000000     O     (8g)
   0.88380000000000    0.37120000000000   -0.00060000000000     O     (8g)
   0.00000000000000    0.00000000000000    0.00000000000000     P     (2a)
```

$CdAl_2S_4$ (E3): A2BC4_tI14_82_bc_a_g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cd Al2 S4'

loop_
_publ_author_name
 'Harry Hahn'
 'G\"{u}nter Frank'
 'Wilhelm Klingler'
 'Anne-Dorothee St\"{o}rger'
 'Georg St\"{o}rger'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 279
_journal_year 1955
_journal_page_first 241
_journal_page_last 270
_publ_Section_title
;
 Untersuchungen \"{u}ber tern\"{a}re Chalkogenide. VI. \"{U}ber tern\"{a
    ↪ }re Chalogenide des Aluminiums, Galliums und Indiums mit Zink,
    ↪  Cadmium und Quecksilber
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_0301428

_aflow_proto 'A2BC4_tI14_82_bc_a_g'
_aflow_params 'a,c/a,x4,y4,z4'
_aflow_params_values '5.55,1.85585585586,0.26,0.25,0.13'
_aflow_Strukturbericht 'E3'
_aflow_Pearson 'tI14'

_symmetry_space_group_name_Hall "I -4"
_symmetry_space_group_name_H-M "I -4"
_symmetry_Int_Tables_number 82

_cell_length_a      5.55000
_cell_length_b      5.55000
_cell_length_c      10.30000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 y,-x,-z
4 -y,x,-z
5 x+1/2,y+1/2,z+1/2
6 -x+1/2,-y+1/2,z+1/2
7 y+1/2,-x+1/2,-z+1/2
8 -y+1/2,x+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cd1  Cd    2  a  0.00000  0.00000  0.00000  1.00000
Al1  Al    2  b  0.00000  0.00000  0.50000  1.00000
Al2  Al    2  c  0.00000  0.50000  0.25000  1.00000
S1   S     8  g  0.26000  0.25000  0.13000  1.00000
```

$CdAl_2S_4$ (E3): A2BC4_tI14_82_bc_a_g - POSCAR

```
A2BC4_tI14_82_bc_a_g & a,c/a,x4,y4,z4 --params=5.55,1.85585585586,0.26,
    ↪ 0.25,0.13 & I(-4)      S_4^2 #82 (abcg) & tI14 & E3 & CdAl2S4 &
    ↪ & H. Hahn et al., Z. anorg. allg. Chemie 279, 241-270 (1955)
   1.0000000000000000
  -2.77500000000000    2.77500000000000    5.15000000000000
   2.77500000000000   -2.77500000000000    5.15000000000000
   2.77500000000000    2.77500000000000   -5.15000000000000
```

```
   Al    Cd    S
    2     1    4
Direct
   0.50000000000000   0.50000000000000   0.00000000000000   Al    (2b)
   0.75000000000000   0.25000000000000   0.50000000000000   Al    (2c)
   0.00000000000000   0.00000000000000   0.00000000000000   Cd    (2a)
   0.13000000000000   0.62000000000000   0.01000000000000   S     (8g)
   0.38000000000000   0.39000000000000   0.51000000000000   S     (8g)
   0.61000000000000   0.12000000000000  -0.01000000000000   S     (8g)
   0.88000000000000   0.87000000000000   0.49000000000000   S     (8g)
```

PdS (B34): AB_tP16_84_cej_k - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Pd S'

loop_
_publ_author_name
 'Nathaniel E. Brese'
 'Philip J. Squattrito'
 'James A. Ibers'
_journal_name_full
;
Acta Crystallographica C
;
_journal_volume 41
_journal_year 1985
_journal_page_first 1829
_journal_page_last 1830
_publ_Section_title
;
 Reinvestigation of the structure of PdS
;

_aflow_proto 'AB_tP16_84_cej_k'
_aflow_params 'a,c/a,x3,y3,x4,y4,z4'
_aflow_params_values '6.429,1.02830922383,0.46779,0.25713,0.19361,
    ↪ 0.30754,0.22904'
_aflow_Strukturbericht 'B34'
_aflow_Pearson 'tP16'

_symmetry_space_group_name_Hall "-P 4c"
_symmetry_space_group_name_H-M "P 42/m"
_symmetry_Int_Tables_number 84

_cell_length_a    6.42900
_cell_length_b    6.42900
_cell_length_c    6.61100
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 -y,x,z+1/2
4 y,-x,z+1/2
5 -x,-y,-z
6 x,y,-z
7 y,-x,-z+1/2
8 -y,x,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pd1 Pd   2 c 0.00000 0.50000 0.00000 1.00000
Pd2 Pd   2 e 0.00000 0.00000 0.25000 1.00000
Pd3 Pd   4 j 0.46779 0.25713 0.00000 1.00000
S1  S    8 k 0.19361 0.30754 0.22904 1.00000
```

PdS (B34): AB_tP16_84_cej_k - POSCAR

```
AB_tP16_84_cej_k & a,c/a,x3,y3,x4,y4,z4 --params=6.429,1.02830922383,
    ↪ 0.46779,0.25713,0.19361,0.30754,0.22904 & P4_2/m    C_{4h}^2 #
    ↪ 84 (cejk) & tP16 & B34 & PdS & & N. E. Brese, P. J. Squarttrito
    ↪  and J. A. Ibers, Acta Cryst. C 41, 1829-1830 (1985)
   1.0000000000000000
   6.42900000000000   0.00000000000000   0.00000000000000
   0.00000000000000   6.42900000000000   0.00000000000000
   0.00000000000000   0.00000000000000   6.61100000000000
   Pd    S
    8    8
Direct
   0.00000000000000   0.50000000000000   0.00000000000000   Pd    (2c)
   0.50000000000000   0.00000000000000   0.50000000000000   Pd    (2c)
   0.00000000000000   0.00000000000000   0.25000000000000   Pd    (2e)
   0.00000000000000   0.00000000000000   0.75000000000000   Pd    (2e)
   0.25713200000000   0.53220800000000   0.50000000000000   Pd    (4j)
   0.46779200000000   0.25713200000000   0.00000000000000   Pd    (4j)
   0.53220800000000   0.74286800000000   0.00000000000000   Pd    (4j)
   0.74286800000000   0.46779200000000   0.50000000000000   Pd    (4j)
   0.19361000000000   0.30754000000000   0.22904000000000   S     (8k)
   0.19361000000000   0.30754000000000   0.77096000000000   S     (8k)
   0.30754000000000   0.80639000000000   0.27096000000000   S     (8k)
   0.30754000000000   0.80639000000000   0.72904000000000   S     (8k)
   0.69246000000000   0.19361000000000   0.27096000000000   S     (8k)
   0.69246000000000   0.19361000000000   0.72904000000000   S     (8k)
   0.80639000000000   0.69246000000000   0.22904000000000   S     (8k)
   0.80639000000000   0.69246000000000   0.77096000000000   S     (8k)
```

Ti_5Te_4: A4B5_tI18_87_h_ah - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Titanium telluride'
_chemical_formula_sum 'Ti5 Te4'

loop_
_publ_author_name
 'F. Gr\onvold'
 'A. Kjekshus'
 'F. Raaum'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 14
_journal_year 1961
_journal_page_first 930
_journal_page_last 934
_publ_Section_title
;
 The crystal structure of Ti$_5$Te$_4$
;

# Found in  Pearson's Handbook, Vol. IV, pp. 5321

_aflow_proto 'A4B5_tI18_87_h_ah'
_aflow_params 'a,c/a,x2,y2,x3,y3'
_aflow_params_values '10.164,0.37111373475,0.2797,-0.0589,0.3752,0.6856'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI18'

_symmetry_space_group_name_Hall "-I 4"
_symmetry_space_group_name_H-M "I 4/m"
_symmetry_Int_Tables_number 87

_cell_length_a    10.16400
_cell_length_b    10.16400
_cell_length_c    3.77200
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 -y,x,z
4 y,-x,z
5 -x,-y,-z
6 x,y,-z
7 y,-x,-z
8 -y,x,-z
9 x+1/2,y+1/2,z+1/2
10 -x+1/2,-y+1/2,z+1/2
11 -y+1/2,x+1/2,z+1/2
12 y+1/2,-x+1/2,z+1/2
13 -x+1/2,-y+1/2,-z+1/2
14 x+1/2,y+1/2,-z+1/2
15 y+1/2,-x+1/2,-z+1/2
16 -y+1/2,x+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1 Ti   2 a 0.00000 0.00000  0.00000 1.00000
Te1 Te   8 h 0.27970 -0.05890 0.00000 1.00000
Ti2 Ti   8 h 0.37520 0.68560  0.00000 1.00000
```

Ti_5Te_4: A4B5_tI18_87_h_ah - POSCAR

```
A4B5_tI18_87_h_ah & a,c/a,x2,y2,x3,y3 --params=10.164,0.37111373475,
    ↪ 0.2797,-0.0589,0.3752,0.6856 & I4/m    C_{2h}^5 #87 (ah^2) &
    ↪ tI18 & & Ti5Te4 & & F. Gronvold, A. Kjekshus and F. Raaum, Acta
    ↪  Cryst. 14, 930-934 (1961)
   1.0000000000000000
  -5.08200000000000   5.08200000000000   1.88600000000000
   5.08200000000000  -5.08200000000000   1.88600000000000
   5.08200000000000   5.08200000000000  -1.88600000000000
   Te    Ti
    4     5
Direct
  -0.05890000000000   0.27970000000000   0.22080000000000   Te    (8h)
   0.05890000000000   0.72030000000000   0.77920000000000   Te    (8h)
   0.27970000000000   0.05890000000000   0.33860000000000   Te    (8h)
   0.72030000000000  -0.05890000000000   0.66140000000000   Te    (8h)
```

```
    0.00000000000000    0.00000000000000    0.00000000000000    Ti    (2a)
    0.31440000000000    0.62480000000000   -0.06080000000000    Ti    (8h)
    0.37520000000000    0.31440000000000    0.68960000000000    Ti    (8h)
    0.62480000000000    0.68560000000000    0.31040000000000    Ti    (8h)
    0.68560000000000    0.37520000000000    0.06080000000000    Ti    (8h)
```

Ni_4Mo ($D1_a$): AB4_tI10_87_a_h - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ni4 Mo'

loop_
_publ_author_name
 'David Harker'
_journal_name_full
;
Journal of Chemical Physics
;
_journal_volume 12
_journal_year 1944
_journal_page_first 315
_journal_page_last 315
_publ_Section_title
;
 The Crystal Structure of Ni$_4$Mo
;

_aflow_proto 'AB4_tI10_87_a_h'
_aflow_params 'a,c/a,x2,y2'
_aflow_params_values '5.72,0.623076923077,0.4,0.8'
_aflow_Strukturbericht 'D1_a'
_aflow_Pearson 'tI10'

_symmetry_space_group_name_Hall "-I 4"
_symmetry_space_group_name_H-M "I 4/m"
_symmetry_Int_Tables_number 87

_cell_length_a      5.72000
_cell_length_b      5.72000
_cell_length_c      3.56400
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 -y,x,z
4 y,-x,z
5 -x,-y,-z
6 x,y,-z
7 y,-x,-z
8 -y,x,-z
9 x+1/2,y+1/2,z+1/2
10 -x+1/2,-y+1/2,z+1/2
11 -y+1/2,x+1/2,z+1/2
12 y+1/2,-x+1/2,z+1/2
13 -x+1/2,-y+1/2,-z+1/2
14 x+1/2,y+1/2,-z+1/2
15 y+1/2,-x+1/2,-z+1/2
16 -y+1/2,x+1/2,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mo1 Mo    2 a 0.00000 0.00000 0.00000 1.00000
Ni1 Ni    8 h 0.40000 0.80000 0.00000 1.00000
```

Ni_4Mo ($D1_a$): AB4_tI10_87_a_h - POSCAR

```
AB4_tI10_87_a_h & a,c/a,x2,y2 --params=5.72,0.623076923077,0.4,0.8 & I4/
    ↪ m      C_{2h}^5 #87 (ah) & tI10 & D1_a & Ni4Mo & & D. Harker,
    ↪ J. Chem. Phys. 12, 315 (1944)
   1.0000000000000000
  -2.86000000000000    2.86000000000000    1.78200000000000
   2.86000000000000   -2.86000000000000    1.78200000000000
   2.86000000000000    2.86000000000000   -1.78200000000000
   Mo    Ni
    1     4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Mo    (2a)
   0.20000000000000    0.60000000000000    0.80000000000000    Ni    (8h)
   0.40000000000000    0.20000000000000    0.60000000000000    Ni    (8h)
   0.60000000000000    0.80000000000000    0.40000000000000    Ni    (8h)
   0.80000000000000    0.40000000000000    0.20000000000000    Ni    (8h)
```

α-Cristobalite (SiO_2, low): A2B_tP12_92_b_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'low (alpha) Cristobalite'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'J. J. Pluth'
 'J. V. Smith'
 'J. Faber, Jr.'
_journal_name_full
;
Journal of Applied Physics
;
_journal_volume 57
_journal_year 1985
_journal_page_first 1045
_journal_page_last 1049
_publ_Section_title
;
 Crystal structure of low cristobalite at 10, 293, and 473 K: Variation
    ↪ of framework geometry with temperature
;

# Found in  Pearson's Handbook, Vol. IV, pp. 4759

_aflow_proto 'A2B_tP12_92_b_a'
_aflow_params 'a,c/a,x1,x2,y2,z2'
_aflow_params_values '4.957,1.39001412144,0.3047,0.2381,0.1109,0.1826'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP12'

_symmetry_space_group_name_Hall "P 4abw 2nw"
_symmetry_space_group_name_H-M "P 41 21 2"
_symmetry_Int_Tables_number 92

_cell_length_a      4.95700
_cell_length_b      4.95700
_cell_length_c      6.89030
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+3/4
3 -x+1/2,y+1/2,-z+1/4
4 -x,-y,z+1/2
5 -y,-x,-z+1/2
6 -y+1/2,x+1/2,z+1/4
7 y+1/2,-x+1/2,z+3/4
8 y,x,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si    4 a 0.30470 0.30470 0.00000 1.00000
O1  O     8 b 0.23810 0.11090 0.18260 1.00000
```

α-Cristobalite (SiO_2, low): A2B_tP12_92_b_a - POSCAR

```
A2B_tP12_92_b_a & a,c/a,x1,x2,y2,z2 --params=4.957,1.39001412144,0.3047,
    ↪ 0.2381,0.1109,0.1826 & P4_12_12  D_4^4 #92 (ab) & tP12 & & SiO2
    ↪  & alpha (low) Cristobalite & J.J. Pluth, J.V. Smith, and J.
    ↪ Faber, Jr., J. App. Phys. 57, 1045-1049 (1985)
   1.0000000000000000
   4.95700000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.95700000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.89030000000000
    O    Si
    8     4
Direct
   0.11090000000000    0.23810000000000    0.81740000000000    O    (8b)
   0.23810000000000    0.11090000000000    0.18260000000000    O    (8b)
   0.26190000000000    0.61090000000000    0.06740000000000    O    (8b)
   0.38910000000000    0.73810000000000    0.43260000000000    O    (8b)
   0.61090000000000    0.26190000000000    0.93260000000000    O    (8b)
   0.73810000000000    0.38910000000000    0.56740000000000    O    (8b)
   0.76190000000000    0.88910000000000    0.68260000000000    O    (8b)
   0.88910000000000    0.76190000000000    0.31740000000000    O    (8b)
   0.19530000000000    0.80470000000000    0.25000000000000    Si   (4a)
   0.30470000000000    0.30470000000000    0.00000000000000    Si   (4a)
   0.69530000000000    0.69530000000000    0.50000000000000    Si   (4a)
   0.80470000000000    0.19530000000000    0.75000000000000    Si   (4a)
```

Keatite (SiO_2): A2B_tP36_96_3b_ab - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Keatite'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
```

```
 'Joseph Shropshire'
 'Paul P. Keat'
 'Philip A. Vaughan'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie
;
_journal_volume 112
_journal_year 1959
_journal_page_first 409
_journal_page_last 413
_publ_Section_title
;
 The crystal structure of keatite, a new form of silica
;

# Found in  demuth99:keatite

_aflow_proto 'A2B_tP36_96_3b_ab'
_aflow_params 'a,c/a,x1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5'
_aflow_params_values '7.464,1.15487674169,0.41,0.445,0.132,0.4,0.117,
    ↪ 0.123,0.296,0.344,0.297,0.143,0.326,0.12,0.248'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP36'

_symmetry_space_group_name_Hall "P 4nw 2abw"
_symmetry_space_group_name_H-M "P 43 21 2"
_symmetry_Int_Tables_number 96

_cell_length_a      7.46400
_cell_length_b      7.46400
_cell_length_c      8.62000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/4
3 -x+1/2,y+1/2,-z+3/4
4 -x,-y,z+1/2
5 -y,-x,-z+1/2
6 -y+1/2,x+1/2,z+3/4
7 y+1/2,-x+1/2,z+1/4
8 y,x,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   4 a 0.41000 0.41000 0.00000 1.00000
O1  O    8 b 0.44500 0.13200 0.40000 1.00000
O2  O    8 b 0.11700 0.12300 0.29600 1.00000
O3  O    8 b 0.34400 0.29700 0.14300 1.00000
Si2 Si   8 b 0.32600 0.12000 0.24800 1.00000
```

Keatite (SiO_2): A2B_tP36_96_3b_ab - POSCAR

```
A2B_tP36_96_3b_ab & a,c/a,x1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5 --
    ↪ params=7.464,1.15487674169,0.41,0.445,0.132,0.4,0.117,0.123,
    ↪ 0.296,0.344,0.297,0.143,0.326,0.12,0.248 & P4_32_12  D_4^8 #96
    ↪ (ab^4) & tP36 & & SiO2 & Keatite & Shropshire, et. al.
    ↪ Zeitschrift f\"{u}r Kristallographie 112, 409-413 (1959)
  1.0000000000000000
  7.46400000000000   0.00000000000000   0.00000000000000
  0.00000000000000   7.46400000000000   0.00000000000000
  0.00000000000000   0.00000000000000   8.62000000000000
   O   Si
  24   12
Direct
  0.05500000000000   0.63200000000000   0.35000000000000   O   (8b)
  0.13200000000000   0.44500000000000   0.60000000000000   O   (8b)
  0.36800000000000   0.94500000000000   0.15000000000000   O   (8b)
  0.44500000000000   0.13200000000000   0.40000000000000   O   (8b)
  0.55500000000000   0.86800000000000   0.90000000000000   O   (8b)
  0.63200000000000   0.05500000000000   0.65000000000000   O   (8b)
  0.86800000000000   0.55500000000000   0.10000000000000   O   (8b)
  0.94500000000000   0.36800000000000   0.85000000000000   O   (8b)
  0.11700000000000   0.12300000000000   0.29600000000000   O   (8b)
  0.12300000000000   0.11700000000000   0.70400000000000   O   (8b)
  0.37700000000000   0.61700000000000   0.04600000000000   O   (8b)
  0.38300000000000   0.62300000000000   0.45400000000000   O   (8b)
  0.61700000000000   0.37700000000000  -0.04600000000000   O   (8b)
  0.62300000000000   0.38300000000000   0.54600000000000   O   (8b)
  0.87700000000000   0.88300000000000   0.20400000000000   O   (8b)
  0.88300000000000   0.87700000000000   0.79600000000000   O   (8b)
  0.15600000000000   0.79700000000000   0.60700000000000   O   (8b)
  0.20300000000000   0.84400000000000   0.89300000000000   O   (8b)
  0.29700000000000   0.34400000000000   0.85700000000000   O   (8b)
  0.34400000000000   0.29700000000000   0.14300000000000   O   (8b)
  0.65600000000000   0.70300000000000   0.64300000000000   O   (8b)
  0.70300000000000   0.65600000000000   0.35700000000000   O   (8b)
  0.79700000000000   0.15600000000000   0.39300000000000   O   (8b)
  0.84400000000000   0.20300000000000   0.10700000000000   O   (8b)
  0.09000000000000   0.91000000000000   0.75000000000000  Si   (4a)
  0.41000000000000   0.41000000000000   0.00000000000000  Si   (4a)
  0.59000000000000   0.59000000000000   0.50000000000000  Si   (4a)
  0.91000000000000   0.09000000000000   0.25000000000000  Si   (4a)
  0.12000000000000   0.32600000000000   0.75200000000000  Si   (8b)
  0.17400000000000   0.62000000000000   0.50200000000000  Si   (8b)
  0.32600000000000   0.12000000000000   0.24800000000000  Si   (8b)
  0.38000000000000   0.82600000000000   0.99800000000000  Si   (8b)
  0.62000000000000   0.17400000000000   0.49800000000000  Si   (8b)
  0.67400000000000   0.88000000000000   0.74800000000000  Si   (8b)
  0.82600000000000   0.38000000000000   0.00200000000000  Si   (8b)
  0.88000000000000   0.67400000000000   0.25200000000000  Si   (8b)
```

"ST12" of Si: A_tP12_96_ab - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Si'

loop_
_publ_author_name
 'J. Crain'
 'S. J. Clark'
 'G. J. Ackland'
 'M. C. Payne'
 'V. Milman'
 'P. D. Hatton'
 'B. J. Reid'
_journal_name_full
;
Physical Review B
;
_journal_volume 49
_journal_year 1994
_journal_page_first 5329
_journal_page_last 5340
_publ_Section_title
;
 Theoretical study of high-density phases of covalent semiconductors. I.
    ↪ {\em Ab initio treatment}
;

_aflow_proto 'A_tP12_96_ab'
_aflow_params 'a,c/a,x1,x2,y2,z2'
_aflow_params_values '5.51889,1.25999974633,0.0849,0.1752,0.3792,0.2742'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP12'

_symmetry_space_group_name_Hall "P 4nw 2abw"
_symmetry_space_group_name_H-M "P 43 21 2"
_symmetry_Int_Tables_number 96

_cell_length_a      5.51889
_cell_length_b      5.51889
_cell_length_c      6.95380
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/4
3 -x+1/2,y+1/2,-z+3/4
4 -x,-y,z+1/2
5 -y,-x,-z+1/2
6 -y+1/2,x+1/2,z+3/4
7 y+1/2,-x+1/2,z+1/4
8 y,x,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   4 a 0.08490 0.08490 0.00000 1.00000
Si2 Si   8 b 0.17520 0.37920 0.27420 1.00000
```

"ST12" of Si: A_tP12_96_ab - POSCAR

```
A_tP12_96_ab & a,c/a,x1,x2,y2,z2 --params=5.51889,1.25999974633,0.0849,
    ↪ 0.1752,0.3792,0.2742 & P4_32_12  D_4^8 #96 (ab) & tP12 & & Si &
    ↪ ST12 & J. Crain et al., Phys. Rev. B 49, 5329-5340 (1994)
  1.0000000000000000
  5.51889083000000   0.00000000000000   0.00000000000000
  0.00000000000000   5.51889083000000   0.00000000000000
  0.00000000000000   0.00000000000000   6.95380245000000
  Si
  12
Direct
  0.08490000000000   0.08490000000000   0.00000000000000  Si   (4a)
 -0.08490000000000  -0.08490000000000   0.50000000000000  Si   (4a)
  0.41510000000000   0.58490000000000   0.75000000000000  Si   (4a)
  0.58490000000000   0.41510000000000   0.25000000000000  Si   (4a)
  0.12080000000000   0.67520000000000   0.02420000000000  Si   (8b)
  0.17520000000000   0.37920000000000   0.27420000000000  Si   (8b)
  0.32480000000000   0.87920000000000   0.47580000000000  Si   (8b)
  0.37920000000000   0.17520000000000   0.72580000000000  Si   (8b)
  0.62080000000000   0.82480000000000   0.22580000000000  Si   (8b)
  0.67520000000000   0.12080000000000  -0.02420000000000  Si   (8b)
```

```
    0.82480000000000    0.62080000000000    0.77420000000000    Si    (8b)
    0.87920000000000    0.32480000000000    0.52420000000000    Si    (8b)
```

Tetragonal PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_tP5_99_bc_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Pb(Zr_(1-x)Ti_x)O3'
_chemical_formula_sum 'Pb Zr O3'

loop_
_publ_author_name
 'B. Noheda'
 'J. A. Gonzalo'
 'L. E. Cross'
 'R. Guo'
 'S.-E. Park'
 'D. E. Cox'
 'G. Shirane'
_journal_name_full
;
Physical Review B
;
_journal_volume 61
_journal_year 2000
_journal_page_first 8687
_journal_page_last 8695
_publ_Section_title
;
 Tetragonal-to-monoclinic phase transition in a ferroelectric perovskite
      ↪ : The structure of PbZr$_{0.52}$Ti$_{0.48}$O$_3$
;

_aflow_proto 'A3BC_tP5_99_bc_a_b'
_aflow_params 'a,c/a,z1,z2,z3,z4'
_aflow_params_values '4.046,1.02308452793,0.0,0.8973,0.4517,0.3785'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP5'

_symmetry_space_group_name_Hall "P 4 -2"
_symmetry_space_group_name_H-M "P 4 m m"
_symmetry_Int_Tables_number 99

_cell_length_a      4.04600
_cell_length_b      4.04600
_cell_length_c      4.13940
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -x,-y,z
3 -y,x,z
4 y,-x,z
5 -x,y,z
6 x,-y,z
7 y,x,z
8 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pb1 Pb    1 a 0.00000 0.00000 0.00000 1.00000
O1  O     1 b 0.50000 0.50000 0.89730 1.00000
Zr1 Zr    1 b 0.50000 0.50000 0.45170 1.00000
O2  O     2 c 0.50000 0.00000 0.37850 1.00000
```

Tetragonal PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_tP5_99_bc_a_b - POSCAR

```
A3BC_tP5_99_bc_a_b & a,c/a,z1,z2,z3,z4 --params=4.046,1.02308452793,0.0,
      ↪ 0.8973,0.4517,0.3785 & P4mm        C_{4v}^1 #99 (ab^2c) & tP5 & &
      ↪  Pb(Zr0.52Ti0.48)O3 & Tetragonal PZT & B. Noheda et al., PRB 61
      ↪ , 8687-8695 (2000)
   1.0000000000000000
   4.04600000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.04600000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.13940000000000
    O   Pb   Zr
    3    1    1
Direct
   0.50000000000000    0.50000000000000   -0.10270000000000    O    (1b)
   0.00000000000000    0.50000000000000    0.37850000000000    O    (2c)
   0.50000000000000    0.00000000000000    0.37850000000000    O    (2c)
   0.00000000000000    0.00000000000000    0.00000000000000   Pb    (1a)
   0.50000000000000    0.50000000000000    0.45170000000000   Zr    (1b)
```

BaS_3 ($D0_{17}$): AB3_tP8_113_a_ce - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Barium trisulfide'
_chemical_formula_sum 'Ba S3'

loop_
_publ_author_name
 'S. Yamaoka'
 'J. T. Lemley'
 'J. M. Jenks'
 'H. Steinfink'
_journal_name_full
;
Inorganic Chemistry
;
_journal_volume 14
_journal_year 1975
_journal_page_first 129
_journal_page_last 131
_publ_Section_title
;
 Structural chemistry of the polysulfides dibarium trisulfide and
      ↪ monobarium trisulfide
;

# Found in  Pearson's Handbook Vol II, pp. 1071-1072

_aflow_proto 'AB3_tP8_113_a_ce'
_aflow_params 'a,c/a,z2,x3,z3'
_aflow_params_values '6.871,0.606622034638,0.206,0.1797,0.476'
_aflow_Strukturbericht 'D0_17'
_aflow_Pearson 'tP8'

_symmetry_space_group_name_Hall "P -4 2ab"
_symmetry_space_group_name_H-M "P -4 21 m"
_symmetry_Int_Tables_number 113

_cell_length_a      6.87100
_cell_length_b      6.87100
_cell_length_c      4.16810
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x+1/2,y+1/2,-z
4 -x,-y,z
5 y+1/2,x+1/2,z
6 y,-x,-z
7 -y,x,-z
8 -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ba1 Ba    2 a 0.00000 0.00000 0.00000 1.00000
S1  S     2 c 0.00000 0.50000 0.20600 1.00000
S2  S     4 e 0.17970 0.67970 0.47600 1.00000
```

BaS_3 ($D0_{17}$): AB3_tP8_113_a_ce - POSCAR

```
AB3_tP8_113_a_ce & a,c/a,z2,x3,z3 --params=6.871,0.606622034638,0.206,
      ↪ 0.1797,0.476 & P(-4)2_1m D_{2d}^3 #113 (ace) & tP8 & D0_{17} &
      ↪ BaS_3 & & S. Yamaoka, J. T. Lemley and H. Steinfink, Inorg.
      ↪ Chem. 14, 129-131 (1975)
   1.0000000000000000
   6.87100000000000    0.00000000000000    0.00000000000000
   0.00000000000000    6.87100000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.16810000000000
   Ba    S
    2    6
Direct
   0.00000000000000    0.00000000000000    0.00000000000000   Ba    (2a)
   0.50000000000000    0.50000000000000    0.00000000000000   Ba    (2a)
   0.00000000000000    0.50000000000000    0.20600000000000    S    (2c)
   0.50000000000000    0.00000000000000    0.79400000000000    S    (2c)
   0.17970000000000    0.67970000000000    0.47600000000000    S    (4e)
   0.32030000000000    0.17970000000000    0.52400000000000    S    (4e)
   0.67970000000000    0.82030000000000    0.52400000000000    S    (4e)
   0.82030000000000    0.32030000000000    0.47600000000000    S    (4e)
```

Stannite (Cu_2FeS_4Sn, $H2_6$): A2BC4D_tI16_121_d_a_i_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Stannite'
_chemical_formula_sum 'Cu2 Fe S4 Sn'

loop_
_publ_author_name
 'L. O. Brockway'
_journal_name_full
;
```

```
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 89
_journal_year 1934
_journal_page_first 434
_journal_page_last 441
_publ_Section_title
;
 The Crystal Structure of Stannite, Cu$_2$FeSnS$_4$
;

_aflow_proto 'A2BC4D_tI16_121_d_a_i_b'
_aflow_params 'a,c/a,x4,z4'
_aflow_params_values '5.46,1.96428571429,0.245,0.132'
_aflow_Strukturbericht 'H2_6'
_aflow_Pearson 'tI16'

_symmetry_space_group_name_Hall "I -4 2"
_symmetry_space_group_name_H-M "I -4 2 m"
_symmetry_Int_Tables_number 121

_cell_length_a      5.46000
_cell_length_b      5.46000
_cell_length_c      10.72500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,x,z
6 y,-x,-z
7 -y,x,-z
8 -y,-x,z
9 x+1/2,y+1/2,z+1/2
10 x+1/2,-y+1/2,-z+1/2
11 -x+1/2,y+1/2,-z+1/2
12 -x+1/2,-y+1/2,z+1/2
13 y+1/2,x+1/2,z+1/2
14 y+1/2,-x+1/2,-z+1/2
15 -y+1/2,x+1/2,-z+1/2
16 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Fe1 Fe    2 a 0.00000 0.00000 0.00000 1.00000
Sn1 Sn    2 b 0.00000 0.00000 0.50000 1.00000
Cu1 Cu    4 d 0.00000 0.50000 0.25000 1.00000
S1  S     8 i 0.24500 0.24500 0.13200 1.00000
```

Stannite (Cu_2FeS_4Sn, $H2_6$): A2BC4D_tI16_121_d_a_i_b - POSCAR

```
A2BC4D_tI16_121_d_a_i_b & a,c/a,x4,z4 --params=5.46,1.96428571429,0.245,
    ↪ 0.132 & I(-4)2m    D_{2d}^{11} #121 (abdi) & tI16 & H2_6 &
    ↪ Cu2FeS4Sn & Stannite & L. O. Brockway, Zeitschrift f\"{u}r
    ↪ Kristallographie - Crystalline Materials 89, 434-441 (1934)
   1.0000000000000000
  -2.73000000000000    2.73000000000000    5.36250000001170
   2.73000000000000   -2.73000000000000    5.36250000001170
   2.73000000000000    2.73000000000000   -5.36250000001170
   Cu    Fe    S    Sn
    2     1    4     1
Direct
   0.25000000000000    0.75000000000000    0.50000000000000    Cu    (4d)
   0.75000000000000    0.25000000000000    0.50000000000000    Cu    (4d)
   0.00000000000000    0.00000000000000    0.00000000000000    Fe    (2a)
   0.37700000000000    0.37700000000000    0.49000000000000    S     (8i)
   0.62300000000000    0.11300000000000    0.00000000000000    S     (8i)
   0.88700000000000    0.88700000000000    0.51000000000000    S     (8i)
   0.11300000000000    0.62300000000000    0.00000000000000    S     (8i)
   0.50000000000000    0.50000000000000    0.00000000000000    Sn    (2b)
```

Chalcopyrite ($CuFeS_2$, $E1_1$): ABC2_tI16_122_a_b_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Chalcopyrite'
_chemical_formula_sum 'Cu Fe S2'

loop_
_publ_author_name
 'S. R. Hall'
 'J. M. Stewart'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 29
_journal_year 1973
_journal_page_first 579
_journal_page_last 585
_publ_Section_title
;
 The Crystal Structure Refinement of Chalcopyrite, CuFeS$_2$
;

_aflow_proto 'ABC2_tI16_122_a_b_d'
_aflow_params 'a,c/a,x3'
_aflow_params_values '5.289,1.97069389299,0.2574'
_aflow_Strukturbericht 'E1_1'
_aflow_Pearson 'tI16'

_symmetry_space_group_name_Hall "I -4 2bw"
_symmetry_space_group_name_H-M "I -4 2 d"
_symmetry_Int_Tables_number 122

_cell_length_a      5.28900
_cell_length_b      5.28900
_cell_length_c      10.42300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/2,-z+1/4
3 -x,y+1/2,-z+1/4
4 -x,-y,z
5 y,x+1/2,z+1/4
6 y,-x,-z
7 -y,x,-z
8 -y,-x+1/2,z+1/4
9 x+1/2,y+1/2,z+1/2
10 x+1/2,-y,-z+3/4
11 -x+1/2,y,-z+3/4
12 -x+1/2,-y+1/2,z+1/2
13 y+1/2,x,z+3/4
14 y+1/2,-x+1/2,-z+1/2
15 -y+1/2,x+1/2,-z+1/2
16 -y+1/2,-x,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    4 a 0.00000 0.00000 0.00000 1.00000
Fe1 Fe    4 b 0.00000 0.00000 0.50000 1.00000
S1  S     8 d 0.25740 0.25000 0.12500 1.00000
```

Chalcopyrite ($CuFeS_2$, $E1_1$): ABC2_tI16_122_a_b_d - POSCAR

```
ABC2_tI16_122_a_b_d & a,c/a,x3 --params=5.289,1.97069389299,0.2574 & I(-
    ↪ 4)2d    D_{2d}^{12} #122 (abd) & tI16 & E1_1 & CuFeS2 &
    ↪ Chalcopyrite & S. R. Hall and J. M. Stewart, Acta Cryst. B 29,
    ↪ 579-585 (1973)
   1.0000000000000000
  -2.64450000000000    2.64450000000000    5.21150000001205
   2.64450000000000   -2.64450000000000    5.21150000001205
   2.64450000000000    2.64450000000000   -5.21150000001205
   Cu    Fe    S
    2     2    4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cu    (4a)
   0.75000000000000    0.25000000000000    0.50000000000000    Cu    (4a)
   0.25000000000000    0.75000000000000    0.50000000000000    Fe    (4b)
   0.50000000000000    0.50000000000000    0.00000000000000    Fe    (4b)
   0.37500000000000    0.38240000000000    0.50740000000000    S     (8d)
   0.61760000000000    0.12500000000000   -0.00740000000000    S     (8d)
   0.87500000000000   -0.13240000000000    0.49260000000000    S     (8d)
   0.13240000000000    0.62500000000000    0.00740000000000    S     (8d)
```

$HoCoGa_5$: AB5C_tP7_123_b_ci_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ho Co Ga5'

loop_
_publ_author_name
 'Yu.N Grin'
 'Ya.P. Yarmolyuk'
 'E. I. Gladyshevskii'
_journal_name_full
;
Kristallografiya
;
_journal_volume 24
_journal_year 1979
_journal_page_first 242
_journal_page_last 246
_publ_Section_title
;
```

```
 Kristallicheskie struktury soedinenij R$_2$COGa$_8$ (R=Sm, Gd, Tb, Dy,
      ↪ Ho, Er, Tm, Lu, Y) i RCoGa$_5$ (R=Gd, Tb, Dy, Ho, Er, Tm, Lu,
      ↪ Y)
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
      ↪ sd_1406905

_aflow_proto 'AB5C_tP7_123_b_ci_a'
_aflow_params 'a,c/a,z4'
_aflow_params_values '4.207,1.61516520086,0.312'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP7'

_symmetry_space_group_name_Hall "-P 4 2"
_symmetry_space_group_name_H-M "P 4/m m m"
_symmetry_Int_Tables_number 123

_cell_length_a      4.20700
_cell_length_b      4.20700
_cell_length_c      6.79500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ho1 Ho   1 a 0.00000 0.00000 0.00000 1.00000
Co1 Co   1 b 0.00000 0.00000 0.50000 1.00000
Ga1 Ga   1 c 0.50000 0.50000 0.00000 1.00000
Ga2 Ga   4 i 0.00000 0.50000 0.31200 1.00000
```

$HoCoGa_5$: AB5C_tP7_123_b_ci_a - POSCAR

```
AB5C_tP7_123_b_ci_a & a,c/a,z4 --params=4.207,1.61516520086,0.312 & P4/
      ↪ mmm    D_{4h}^1 #123 (abci) & tP7 & & HoCoGa5 & & Y. Grin, Y.
      ↪ P. Yarmolyuk and E. I. Gladyshevskii, Kristallografiya 24,
      ↪ 242-246 (1979)
   1.0000000000000000
   4.20700000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.20700000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.79500000000000
   Co   Ga   Ho
    1    5    1
Direct
   0.00000000000000    0.00000000000000    0.50000000000000    Co    (1b)
   0.50000000000000    0.50000000000000    0.00000000000000    Ga    (1c)
   0.00000000000000    0.50000000000000    0.31200000000000    Ga    (4i)
   0.00000000000000    0.50000000000000    0.68800000000000    Ga    (4i)
   0.50000000000000    0.00000000000000    0.31200000000000    Ga    (4i)
   0.50000000000000    0.00000000000000    0.68800000000000    Ga    (4i)
   0.00000000000000    0.00000000000000    0.00000000000000    Ho    (1a)
```

$CuTi_3$ ($L6_0$): AB3_tP4_123_a_ce - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cu Ti3'

loop_
_publ_author_name
 'N. Karlsson'
_journal_name_full
;
Journal of the Institute of Metals (London)
;
_journal_volume 79
_journal_year 1951
_journal_page_first 391
_journal_page_last 405
_publ_Section_title
;
 An X-ray study of the phases in the copper-titanium system
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
      ↪ sd_1250535

_aflow_proto 'AB3_tP4_123_a_ce'
_aflow_params 'a,c/a'
_aflow_params_values '4.158,0.864357864358'
_aflow_Strukturbericht 'L6_0'
_aflow_Pearson 'tP4'

_symmetry_space_group_name_Hall "-P 4 2"
_symmetry_space_group_name_H-M "P 4/m m m"
_symmetry_Int_Tables_number 123

_cell_length_a      4.15800
_cell_length_b      4.15800
_cell_length_c      3.59400
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu   1 a 0.00000 0.00000 0.00000 1.00000
Ti1 Ti   1 c 0.50000 0.50000 0.00000 1.00000
Ti2 Ti   2 e 0.00000 0.50000 0.50000 1.00000
```

$CuTi_3$ ($L6_0$): AB3_tP4_123_a_ce - POSCAR

```
AB3_tP4_123_a_ce & a,c/a --params=4.158,0.864357864358 & P4/mmm    D_{4h
      ↪ }^1 #123 (ace) & tP4 & L6_0 & CuTi3 & & N. Karlsson, Journal of
      ↪ the J. Inst. Met. 79, 391-405 (1951)
   1.0000000000000000
   4.15800000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.15800000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.59400000000000
   Cu   Ti
    1    3
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cu    (1a)
   0.50000000000000    0.50000000000000    0.00000000000000    Ti    (1c)
   0.00000000000000    0.50000000000000    0.50000000000000    Ti    (2e)
   0.50000000000000    0.00000000000000    0.50000000000000    Ti    (2e)
```

CuAu ($L1_0$): AB_tP2_123_a_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Tetraauricupride'
_chemical_formula_sum 'Cu Au'

loop_
_publ_author_name
 'Peter Bayliss'
_journal_name_full
;
Canadian Mineralogist
;
_journal_volume 28
_journal_year 1990
_journal_page_first 751
_journal_page_last 755
_publ_Section_title
;
 Revised Unit-Cell Dimensions, Space Group, and Chemical Formula of Some
      ↪ Metallic Materials
;

# Found in  AMS database

_aflow_proto 'AB_tP2_123_a_d'
_aflow_params 'a,c/a'
_aflow_params_values '2.8,1.31071428571'
_aflow_Strukturbericht 'L1_0'
_aflow_Pearson 'tP2'
```

```
_symmetry_space_group_name_Hall "-P 4 2"
_symmetry_space_group_name_H-M "P 4/m m m"
_symmetry_Int_Tables_number 123

_cell_length_a      2.80000
_cell_length_b      2.80000
_cell_length_c      3.67000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Au1 Au    1 a 0.00000 0.00000 0.00000 1.00000
Cu1 Cu    1 d 0.50000 0.50000 0.50000 1.00000
```

CuAu ($L1_0$): AB_tP2_123_a_d - POSCAR

```
AB_tP2_123_a_d & a,c/a --params=2.8,1.31071428571 & P4/mmm     D_{4h}^1 #
    ↪ 123 (ad) & tP2 & L1_0 & CuAu & tetraauricupride & P. Bayliss,
    ↪ Can. Mineral. 28, 751-755 (1990)
   1.0000000000000000
   2.80000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    2.80000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.67000000000000
   Au    Cu
    1     1
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Au     (1a)
   0.50000000000000    0.50000000000000    0.50000000000000    Cu     (1d)
```

$CaCuO_2$: ABC2_tP4_123_d_a_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ca Cu O2'

loop_
_publ_author_name
 'T. Siegrist'
 'S. M. Zahurak'
 'D. W. Murphy'
 'R. S. Roth'
_journal_name_full
;
Nature
;
_journal_volume 334
_journal_year 1988
_journal_page_first 231
_journal_page_last 232
_publ_Section_title
;
 The parent structure of the layered high-temperature superconductors
;

_aflow_proto 'ABC2_tP4_123_d_a_f'
_aflow_params 'a,c/a'
_aflow_params_values '3.8611,0.828649866618'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP4'

_symmetry_space_group_name_Hall "-P 4 2"
_symmetry_space_group_name_H-M "P 4/m m m"
_symmetry_Int_Tables_number 123

_cell_length_a      3.86110
_cell_length_b      3.86110
_cell_length_c      3.19950
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    1 a 0.00000 0.00000 0.00000 1.00000
Ca1 Ca    1 d 0.50000 0.50000 0.50000 1.00000
O1  O     2 f 0.00000 0.50000 0.00000 1.00000
```

$CaCuO_2$: ABC2_tP4_123_d_a_f - POSCAR

```
ABC2_tP4_123_d_a_f & a,c/a --params=3.8611,0.828649866618 & P4/mmm     D_
    ↪ {4h}^1 #123 (adf) & tP4 & & CaCuO2 & & T. Siegrist, S. M.
    ↪ Zahurak, D. W. Murphy and R. S. Roth, Nature 334, 231-232 (1988
    ↪ )
   1.0000000000000000
   3.86110000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.86110000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.19950000000000
   Ca    Cu    O
    1     1     2
Direct
   0.50000000000000    0.50000000000000    0.50000000000000    Ca     (1d)
   0.00000000000000    0.00000000000000    0.00000000000000    Cu     (1a)
   0.00000000000000    0.50000000000000    0.00000000000000    O      (2f)
   0.50000000000000    0.00000000000000    0.00000000000000    O      (2f)
```

Si_2U_3 ($D5_a$): A2B3_tP10_127_g_ah - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Si2 U3'

loop_
_publ_author_name
 'K. Remschnig'
 'T. Le Bihan'
 'H. No\"{e}l'
 'P. Rogl'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 97
_journal_year 1992
_journal_page_first 391
_journal_page_last 399
_publ_Section_title
;
 Structural chemistry and magnetic behavior of binary uranium silicides
;

# Found in  http://materials.springer.com/lb/docs/
    ↪ sm_lbs_978-3-642-22847-6_359

_aflow_proto 'A2B3_tP10_127_g_ah'
_aflow_params 'a,c/a,x2,x3'
_aflow_params_values '7.3364,0.530232811733,0.3841,0.1821'
_aflow_Strukturbericht 'D5_a'
_aflow_Pearson 'tP10'

_symmetry_space_group_name_Hall "-P 4 2ab"
_symmetry_space_group_name_H-M "P 4/m b m"
_symmetry_Int_Tables_number 127

_cell_length_a      7.33640
_cell_length_b      7.33640
_cell_length_c      3.89000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
```

```
3 -x+1/2,y+1/2,-z
4 -x,-y,z
5 -y+1/2,-x+1/2,-z
6 -y,x,z
7 y,-x,z
8 y+1/2,x+1/2,-z
9 -x,-y,-z
10 -x+1/2,y+1/2,z
11 x+1/2,-y+1/2,z
12 x,y,-z
13 y+1/2,x+1/2,z
14 y,-x,-z
15 -y,x,-z
16 -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
U1  U    2 a 0.00000 0.00000 0.00000 1.00000
Si1 Si   4 g 0.38410 0.88410 0.00000 1.00000
U2  U    4 h 0.18210 0.68210 0.50000 1.00000
```

Si_2U_3 ($D5_a$): A2B3_tP10_127_g_ah - POSCAR

```
A2B3_tP10_127_g_ah & a,c/a,x2,x3 --params=7.3364,0.530232811733,0.3841,
    ↪ 0.1821 & P4/mbm    D_{4h}^5 #127 (agh) & tP10 & D5_a & Si2U3 &
    ↪ & K. Remshnig, T. Le Bihan, H. Noel and P. Rogl, J. Solid State
    ↪  Chem. 97, 391-399 (1992)
   1.0000000000000000
   7.33640000000000    0.00000000000000    0.00000000000000
   0.00000000000000    7.33640000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.89000000000000
   Si    U
    4    6
Direct
   0.11590000000000    0.38410000000000    0.00000000000000    Si    (4g)
   0.38410000000000    0.88410000000000    0.00000000000000    Si    (4g)
   0.61590000000000    0.11590000000000    0.00000000000000    Si    (4g)
   0.88410000000000    0.61590000000000    0.00000000000000    Si    (4g)
   0.00000000000000    0.00000000000000    0.00000000000000    U     (2a)
   0.50000000000000    0.50000000000000    0.00000000000000    U     (2a)
   0.18210000000000    0.68210000000000    0.50000000000000    U     (4h)
   0.31790000000000    0.18210000000000    0.50000000000000    U     (4h)
   0.68210000000000    0.81790000000000    0.50000000000000    U     (4h)
   0.81790000000000    0.31790000000000    0.50000000000000    U     (4h)
```

AsCuSiZr: ABCD_tP8_129_c_b_a_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Parent of FeAs superconductors'
_chemical_formula_sum 'As Cu Si Zr'

loop_
_publ_author_name
 'V. Johnson'
 'W. Jeitschko'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 11
_journal_year 1974
_journal_page_first 161
_journal_page_last 166
_publ_Section_title
;
 ZrCuSiAs: A ``filled'' PbFCl type
;

# Found in  Pearson, Vol. I, pp. 1116

_aflow_proto 'ABCD_tP8_129_c_b_a_c'
_aflow_params 'a,c/a,z3,z4'
_aflow_params_values '3.6736,2.60540069686,0.6793,0.2246'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP8'

_symmetry_space_group_name_Hall "-P 4a 2a"
_symmetry_space_group_name_H-M "P 4/n m m:2"
_symmetry_Int_Tables_number 129

_cell_length_a      3.67360
_cell_length_b      3.67360
_cell_length_c      9.57120
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z
3 -x,y+1/2,-z
4 -x+1/2,-y+1/2,z
5 -y,-x,-z
6 -y+1/2,x,z
7 y,-x+1/2,z
8 y+1/2,x+1/2,-z
9 -x,-y,-z
10 -x+1/2,y,z
11 x,-y+1/2,z
12 x+1/2,y+1/2,-z
13 y,x,z
14 y+1/2,-x,-z
15 -y,x+1/2,-z
16 -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   2 a 0.75000 0.25000 0.00000 1.00000
Cu1 Cu   2 b 0.75000 0.25000 0.50000 1.00000
As1 As   2 c 0.25000 0.25000 0.67930 1.00000
Zr1 Zr   2 c 0.25000 0.25000 0.22460 1.00000
```

AsCuSiZr: ABCD_tP8_129_c_b_a_c - POSCAR

```
ABCD_tP8_129_c_b_a_c & a,c/a,z3,z4 --params=3.6736,2.60540069686,0.6793,
    ↪ 0.2246 & P4/mmm    D_{4h}^7 #129 (abc^2) & tP8 && AsCuSiZr &&
    ↪  V. Johnson and W. Jeitschko, J. Solid State Chem. 11, 161-166
    ↪ (1974)
   1.0000000000000000
   3.67360000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.67360000000000    0.00000000000000
   0.00000000000000    0.00000000000000    9.57120000000000
   As    Cu    Si    Zr
    2     2     2     2
Direct
   0.25000000000000    0.25000000000000    0.67930000000000    As    (2c)
   0.75000000000000    0.75000000000000    0.32070000000000    As    (2c)
   0.25000000000000    0.75000000000000    0.50000000000000    Cu    (2b)
   0.75000000000000    0.25000000000000    0.50000000000000    Cu    (2b)
   0.25000000000000    0.75000000000000    0.00000000000000    Si    (2a)
   0.75000000000000    0.25000000000000    0.00000000000000    Si    (2a)
   0.25000000000000    0.25000000000000    0.22460000000000    Zr    (2c)
   0.75000000000000    0.75000000000000    0.77540000000000    Zr    (2c)
```

β-Np (A_d): A_tP4_129_ac - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Np'
_chemical_formula_sum 'Np'

loop_
_publ_author_name
 'W. H. Zachariasen'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 5
_journal_year 1952
_journal_page_first 664
_journal_page_last 667
_publ_Section_title
;
 Crystal chemical studies of the 5f-series of elements. XVIII. Crystal
    ↪ structure studies of neptunium metal at elevated temperatures
;

# Found in  Donohue, pp. 154-156

_aflow_proto 'A_tP4_129_ac'
_aflow_params 'a,c/a,z2'
_aflow_params_values '4.897,0.69185215438,0.375'
_aflow_Strukturbericht 'A_d'
_aflow_Pearson 'tP4'

_symmetry_space_group_name_Hall "-P 4a 2a"
_symmetry_space_group_name_H-M "P 4/n m m:2"
_symmetry_Int_Tables_number 129

_cell_length_a      4.89700
_cell_length_b      4.89700
_cell_length_c      3.38800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z
3 -x,y+1/2,-z
4 -x+1/2,-y+1/2,z
5 -y,-x,-z
6 -y+1/2,x,z
7 y,-x+1/2,z
```

```
8  y+1/2,x+1/2,-z
9  -x,-y,-z
10  -x+1/2,y,z
11  x,-y+1/2,z
12  x+1/2,y+1/2,-z
13  y,x,z
14  y+1/2,-x,-z
15  -y,x+1/2,-z
16  -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Np1  Np    2  a  0.75000  0.25000  0.00000  1.00000
Np2  Np    2  c  0.25000  0.25000  0.37500  1.00000
```

β-Np (A_d): A_tP4_129_ac - POSCAR

```
A_tP4_129_ac & a,c/a,z2 --params=4.897,0.69185215438,0.375 & P4/nmm
      ↪ D_{4h}^7 #129 (ac) & tP4 & A_d & Np & beta & W. H. Zachariasen,
      ↪  Acta Cryst. 5, 664-667 (1952)
   1.0000000000000000
   4.89700000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.89700000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.38800000000000
   Np
    4
Direct
   0.25000000000000    0.75000000000000    0.00000000000000    Np    (2a)
   0.75000000000000    0.25000000000000    0.00000000000000    Np    (2a)
   0.25000000000000    0.25000000000000    0.37500000000000    Np    (2c)
   0.75000000000000    0.75000000000000    0.62500000000000    Np    (2c)
```

Matlockite ($E0_1$, PbFCl): ABC_tP6_129_c_a_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Matlockite'
_chemical_formula_sum 'Pb F Cl'

loop_
_publ_author_name
 'N. Pasero'
 'N. Perchiazzi'
_journal_name_full
;
Mineralogical Magazine
;
_journal_volume 60
_journal_year 1996
_journal_page_first 833
_journal_page_last 836
_publ_Section_title
;
 Crystal structure refinement of matlockite
;

# Found in  AMS Database

_aflow_proto 'ABC_tP6_129_c_a_c'
_aflow_params 'a,c/a,z2,z3'
_aflow_params_values '4.11,1.76301703163,0.6497,0.2058'
_aflow_Strukturbericht 'E0_1'
_aflow_Pearson 'tP6'

_symmetry_space_group_name_Hall "-P 4a 2a"
_symmetry_space_group_name_H-M "P 4/n m m:2"
_symmetry_Int_Tables_number 129

_cell_length_a      4.11000
_cell_length_b      4.11000
_cell_length_c      7.24600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y,-z
3  -x,y+1/2,-z
4  -x+1/2,-y+1/2,z
5  -y,-x,-z
6  -y+1/2,x,z
7  y,-x+1/2,z
8  y+1/2,x+1/2,-z
9  -x,-y,-z
10  -x+1/2,y,z
11  x,-y+1/2,z
12  x+1/2,y+1/2,-z
13  y,x,z
14  y+1/2,-x,-z
15  -y,x+1/2,-z
16  -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
F1   F     2  a  0.75000  0.25000  0.00000  1.00000
Cl1  Cl    2  c  0.25000  0.25000  0.64970  1.00000
Pb1  Pb    2  c  0.25000  0.25000  0.20580  1.00000
```

Matlockite ($E0_1$, PbFCl): ABC_tP6_129_c_a_c - POSCAR

```
ABC_tP6_129_c_a_c & a,c/a,z2,z3 --params=4.11,1.76301703163,0.6497,
      ↪ 0.2058 & P4/nmm     D_{4h}^7 #129 (ac^2) & tP6 & E0_1 & PbFCl &
      ↪ Matlockite & M. Pasero and N. Perchiazzi, Mineral. Mag. 60,
      ↪ 833-836 (1996)
   1.0000000000000000
   4.11000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.11000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    7.24600000000000
   Cl    F    Pb
    2    2    2
Direct
   0.25000000000000    0.25000000000000    0.64970000000000    Cl    (2c)
   0.75000000000000    0.75000000000000    0.35030000000000    Cl    (2c)
   0.25000000000000    0.75000000000000    0.00000000000000     F    (2a)
   0.75000000000000    0.25000000000000    0.00000000000000     F    (2a)
   0.25000000000000    0.25000000000000    0.20580000000000    Pb    (2c)
   0.75000000000000    0.75000000000000    0.79420000000000    Pb    (2c)
```

Cu_2Sb (C38): A2B_tP6_129_ac_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cu2 Sb'

loop_
_publ_author_name
 'W. B. Pearson'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie
;
_journal_volume 171
_journal_year 1985
_journal_page_first 23
_journal_page_last 39
_publ_Section_title
;
 The Cu$_2$Sb and related structures
;

_aflow_proto 'A2B_tP6_129_ac_c'
_aflow_params 'a,c/a,z2,z3'
_aflow_params_values '4.0006,1.52584612308,0.27,0.7'
_aflow_Strukturbericht 'C38'
_aflow_Pearson 'tP6'

_symmetry_space_group_name_Hall "-P 4a 2a"
_symmetry_space_group_name_H-M "P 4/n m m:2"
_symmetry_Int_Tables_number 129

_cell_length_a      4.00060
_cell_length_b      4.00060
_cell_length_c      6.10430
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y,-z
3  -x,y+1/2,-z
4  -x+1/2,-y+1/2,z
5  -y,-x,-z
6  -y+1/2,x,z
7  y,-x+1/2,z
8  y+1/2,x+1/2,-z
9  -x,-y,-z
10  -x+1/2,y,z
11  x,-y+1/2,z
12  x+1/2,y+1/2,-z
13  y,x,z
14  y+1/2,-x,-z
15  -y,x+1/2,-z
16  -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
```

```
Cu1 Cu    2 a 0.75000 0.25000 0.00000 1.00000
Cu2 Cu    2 c 0.25000 0.25000 0.27000 1.00000
Sb1 Sb    2 c 0.25000 0.25000 0.70000 1.00000
```

Cu_2Sb (C38): A2B_tP6_129_ac_c - POSCAR

```
A2B_tP6_129_ac_c & a,c/a,z2,z3 --params=4.0006,1.52584612308,0.27,0.7 &
    ↪ P4/nmm    D_{4h}^7 #129 (ac^2) & tP6 & C38 & Cu2Sb & & W. B.
    ↪ Pearson, Zeitschrift f\"{u}r Kristallographie 171, 23-39 (1985)
   1.0000000000000000
   4.00060000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.00060000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.10430000000000
   Cu    Sb
    4     2
Direct
   0.25000000000000    0.75000000000000    0.00000000000000    Cu    (2a)
   0.75000000000000    0.25000000000000    0.00000000000000    Cu    (2a)
   0.25000000000000    0.25000000000000    0.27000000000000    Cu    (2c)
   0.75000000000000    0.75000000000000    0.73000000000000    Cu    (2c)
   0.25000000000000    0.25000000000000    0.70000000000000    Sb    (2c)
   0.75000000000000    0.75000000000000    0.30000000000000    Sb    (2c)
```

PbO (B10): AB_tP4_129_a_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'lead oxide'
_chemical_formula_sum 'Pb O'

loop_
_publ_author_name
 'P. Boher'
 'P. Garnier'
 'J. R. Gavarri'
 'A. W. Hewat'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 57
_journal_year 1985
_journal_page_first 343
_journal_page_last 350
_publ_Section_title
;
 Monoxyde quadratique PbO$\alpha$(I): Description de la transition
    ↪ structurale ferroe'lastique
;

# Found in  Pearson's Handbook, Vol. IV, p. 4745

_aflow_proto 'AB_tP4_129_a_c'
_aflow_params 'a,c/a,z2'
_aflow_params_values '3.9645,1.26008323874,0.2368'
_aflow_Strukturbericht 'B10'
_aflow_Pearson 'tP4'

_symmetry_space_group_name_Hall "-P 4a 2a"
_symmetry_space_group_name_H-M "P 4/n m m:2"
_symmetry_Int_Tables_number 129

_cell_length_a      3.96450
_cell_length_b      3.96450
_cell_length_c      4.99560
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z
3 -x,y+1/2,-z
4 -x+1/2,-y+1/2,z
5 -y,-x,-z
6 -y+1/2,x,z
7 y,-x+1/2,z
8 y+1/2,x+1/2,-z
9 -x,-y,-z
10 -x+1/2,y,z
11 x,-y+1/2,z
12 x+1/2,y+1/2,-z
13 y,x,z
14 y+1/2,-x,-z
15 -y,x+1/2,-z
16 -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O     2 a 0.75000 0.25000 0.00000 1.00000
Pb1 Pb    2 c 0.25000 0.25000 0.23680 1.00000
```

PbO (B10): AB_tP4_129_a_c - POSCAR

```
AB_tP4_129_a_c & a,c/a,z2 --params=3.9645,1.26008323874,0.2368 & P4/nmm
    ↪    D_{4h}^7 #129 (ac) & tP4 & B10 & PbO & & P. Boher, P.Garnier
    ↪ , J. R. Gavarri and A. W. Hewat, J. Solid State Chem. 57,
    ↪ 343-350 (1985)
   1.0000000000000000
   3.96450000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.96450000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.99560000000000
    O    Pb
    2     2
Direct
   0.25000000000000    0.75000000000000    0.00000000000000    O     (2a)
   0.75000000000000    0.25000000000000    0.00000000000000    O     (2a)
   0.25000000000000    0.25000000000000    0.23680000000000    Pb    (2c)
   0.75000000000000    0.75000000000000    0.76320000000000    Pb    (2c)
```

γ-CuTi (B11): AB_tP4_129_c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'gamma CuTi'
_chemical_formula_sum 'Cu Ti'

loop_
_publ_author_name
 'V. N. Eremenko'
 'Yu. I. Buyanov'
 'S. B. Prima'
_journal_name_full
;
Soviet Powder Metallurgy and Metal Ceramics
;
_journal_volume 5
_journal_year 1966
_journal_page_first 494
_journal_page_last 502
_publ_Section_title
;
 Phase diagram of the system titanium-copper
;

# Found in  Pearson's Handbook, Vol. III, pp. 3021

_aflow_proto 'AB_tP4_129_c_c'
_aflow_params 'a,c/a,z1,z2'
_aflow_params_values '3.107,1.90505310589,0.1,0.65'
_aflow_Strukturbericht 'B11'
_aflow_Pearson 'tP4'

_symmetry_space_group_name_Hall "-P 4a 2a"
_symmetry_space_group_name_H-M "P 4/n m m:2"
_symmetry_Int_Tables_number 129

_cell_length_a      3.10700
_cell_length_b      3.10700
_cell_length_c      5.91900
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y,-z
3 -x,y+1/2,-z
4 -x+1/2,-y+1/2,z
5 -y,-x,-z
6 -y+1/2,x,z
7 y,-x+1/2,z
8 y+1/2,x+1/2,-z
9 -x,-y,-z
10 -x+1/2,y,z
11 x,-y+1/2,z
12 x+1/2,y+1/2,-z
13 y,x,z
14 y+1/2,-x,-z
15 -y,x+1/2,-z
16 -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    2 c 0.25000 0.25000 0.10000 1.00000
Ti1 Ti    2 c 0.25000 0.25000 0.65000 1.00000
```

γ-CuTi (B11): AB_tP4_129_c_c - POSCAR

```
AB_tP4_129_c_c & a,c/a,z1,z2 --params=3.107,1.90505310589,0.1,0.65 & P4/
    ↪ nmm    D_{4h}^7 #129 (c^2) & tP4 & B11 & CuTi (gamma) & & V. N.
    ↪  Eremenko and Yu. I. Buyanov and S. B. Prima, Soviet Powder
    ↪ Metallurgy and Metal Ceramics 5, 494-502 (1966)
   1.0000000000000000
   3.10700000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.10700000000000    0.00000000000000
```

```
   0.00000000000000    0.00000000000000    5.91900000000000
   Cu    Ti
    2     2
Direct
   0.25000000000000    0.25000000000000    0.10000000000000    Cu    (2c)
   0.75000000000000    0.75000000000000    0.90000000000000    Cu    (2c)
   0.25000000000000    0.25000000000000    0.65000000000000    Ti    (2c)
   0.75000000000000    0.75000000000000    0.35000000000000    Ti    (2c)
```

PtS (B17): AB_tP4_131_c_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Pt S'

loop_
_publ_author_name
 'Fredrik Gronvold'
 'Haakon Haraldsen'
 'Arne Kjekshus'
_journal_name_full
;
Acta Chemica Scandinavica
;
_journal_volume 14
_journal_year 1960
_journal_page_first 1879
_journal_page_last 1893
_publ_Section_title
;
 On the Sulfides, Selenides and Tellurides of Platinum
;

_aflow_proto 'AB_tP4_131_c_e'
_aflow_params 'a,c/a'
_aflow_params_values '4.9073,1.24500234345'
_aflow_Strukturbericht 'B17'
_aflow_Pearson 'tP4'

_symmetry_space_group_name_Hall "-P 4c 2"
_symmetry_space_group_name_H-M "P 42/m m c"
_symmetry_Int_Tables_number 131

_cell_length_a    4.90730
_cell_length_b    4.90730
_cell_length_c    6.10960
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z+1/2
6 -y,x,z+1/2
7 y,-x,z+1/2
8 y,x,-z+1/2
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z+1/2
14 y,-x,-z+1/2
15 -y,x,-z+1/2
16 -y,-x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pt1 Pt   2 c 0.00000 0.50000 0.00000 1.00000
S1  S    2 e 0.00000 0.00000 0.25000 1.00000
```

PtS (B17): AB_tP4_131_c_e - POSCAR

```
AB_tP4_131_c_e & a,c/a --params=4.9073,1.24500234345 & P4_2/mmc  D_{4h}^
    ↪ 9 #131 (ce) & tP4 & B17 & PtS & & F. Gronvold and h. Haakon
    ↪ Haraldsen and A. Kjeksus, Acta Chem. Scand. 14, 1879-1893 (1960
    ↪ )
   1.0000000000000000
   4.90730000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.90730000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.10960000000000
   Pt    S
    2    2
Direct
   0.00000000000000    0.50000000000000    0.00000000000000    Pt    (2c)
   0.50000000000000    0.00000000000000    0.50000000000000    Pt    (2c)
   0.00000000000000    0.00000000000000    0.25000000000000    S     (2e)
   0.00000000000000    0.00000000000000    0.75000000000000    S     (2e)
```

T-50 B (A_g): A_tP50_134_b2m2n - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'T-50 Boron'
_chemical_formula_sum 'B'

loop_
_publ_author_name
 'J. L. Hoard'
 'R. E. Hughes'
 'D. E. Sands'
_journal_name_full
;
Journal of the American Chemical Society
;
_journal_volume 80
_journal_year 1958
_journal_page_first 4507
_journal_page_last 4515
_publ_Section_title
;
 The Structure of Tetragonal Boron
;

# Found in  Donohue, Chapter 5, pp. 48-56

_aflow_proto 'A_tP50_134_b2m2n'
_aflow_params 'a,c/a,x2,z2,x3,z3,x4,y4,z4,x5,y5,z5'
_aflow_params_values '8.74,0.575514874142,0.0048,0.1685,0.1305,0.628,
    ↪ 0.1695,0.5228,0.1635,0.0753,0.3383,0.1485'
_aflow_Strukturbericht 'A_g'
_aflow_Pearson 'tP50'

_symmetry_space_group_name_Hall "-P 4ac 2bc"
_symmetry_space_group_name_H-M "P 42/n n m:2"
_symmetry_Int_Tables_number 134

_cell_length_a    8.74000
_cell_length_b    8.74000
_cell_length_c    5.03000
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/2,-z+1/2
3 -x+1/2,y,-z+1/2
4 -x+1/2,-y+1/2,z
5 -y+1/2,-x+1/2,-z
6 -y+1/2,x,z+1/2
7 y,-x+1/2,z+1/2
8 y,x,-z
9 -x,-y,-z
10 -x,y+1/2,z+1/2
11 x+1/2,-y,z+1/2
12 x+1/2,y+1/2,-z
13 y+1/2,x+1/2,z
14 y+1/2,-x,-z+1/2
15 -y,x+1/2,-z+1/2
16 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1 B   2 b 0.75000  0.25000  0.25000 1.00000
B2 B   8 m 0.00480 -0.00480  0.16850 1.00000
B3 B   8 m 0.13050  0.86950  0.62800 1.00000
B4 B  16 n 0.16950  0.52280  0.16350 1.00000
B5 B  16 n 0.07530  0.33830  0.14850 1.00000
```

T-50 B (A_g): A_tP50_134_b2m2n - POSCAR

```
A_tP50_134_b2m2n & a,c/a,x2,z2,x3,z3,x4,y4,z4,x5,y5,z5 --params=8.74,
    ↪ 0.575514874142,0.0048,0.1685,0.1305,0.628,0.1695,0.5228,0.1635,
    ↪ 0.0753,0.3383,0.1485 & P4_2/nnm  D_{4h}^{12} #134 (bm^2n^2) &
    ↪ tP50 & A_g & B & T50 & J. L. Hoard, R. E. Hughes and D.E. Sands
    ↪ , J. Am. Chem. Soc. 80, 4507-4515 (1958)
   1.0000000000000000
   8.74000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    8.74000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.03000000000000
    B
   50
Direct
   0.75000000000000    0.25000000000000    0.25000000000000    B   (2b)   1
   0.25000000000000    0.75000000000000    0.75000000000000    B   (2b)   1
   0.00480000000000   -0.00480000000000    0.16850000000000    B   (8m)   2
   0.49520000000000    0.50480000000000    0.16850000000000    B   (8m)   2
   0.50480000000000    0.00480000000000    0.66850000000000    B   (8m)   2
  -0.00480000000000    0.49520000000000    0.66850000000000    B   (8m)   2
   0.49520000000000   -0.00480000000000    0.33150000000000    B   (8m)   2
   0.00480000000000    0.50480000000000    0.33150000000000    B   (8m)   2
  -0.00480000000000    0.00480000000000    0.83150000000000    B   (8m)   2
   0.50480000000000    0.49520000000000    0.83150000000000    B   (8m)   2
```

```
    0.130500000000000    0.869500000000000    0.628000000000000   B   (8m)   3
    0.369500000000000    0.630500000000000    0.628000000000000   B   (8m)   3
    0.630500000000000    0.130500000000000    0.128000000000000   B   (8m)   3
    0.869500000000000    0.369500000000000    0.128000000000000   B   (8m)   3
    0.369500000000000    0.869500000000000    0.872000000000000   B   (8m)   3
    0.130500000000000    0.630500000000000    0.872000000000000   B   (8m)   3
    0.869500000000000    0.130500000000000    0.372000000000000   B   (8m)   3
    0.630500000000000    0.369500000000000    0.372000000000000   B   (8m)   3
    0.169500000000000    0.522800000000000    0.163500000000000   B  (16n)  4
    0.330500000000000   -0.022800000000000    0.163500000000000   B  (16n)  4
   -0.022800000000000    0.169500000000000    0.663500000000000   B  (16n)  4
    0.522800000000000    0.330500000000000    0.663500000000000   B  (16n)  4
    0.330500000000000    0.522800000000000    0.336500000000000   B  (16n)  4
    0.169500000000000   -0.022800000000000    0.336500000000000   B  (16n)  4
    0.522800000000000    0.169500000000000    0.836500000000000   B  (16n)  4
   -0.022800000000000    0.330500000000000    0.836500000000000   B  (16n)  4
    0.830500000000000    0.477200000000000    0.836500000000000   B  (16n)  4
    0.669500000000000    0.022800000000000    0.836500000000000   B  (16n)  4
    0.022800000000000    0.830500000000000    0.336500000000000   B  (16n)  4
    0.477200000000000    0.669500000000000    0.336500000000000   B  (16n)  4
    0.669500000000000    0.477200000000000    0.663500000000000   B  (16n)  4
    0.830500000000000    0.022800000000000    0.663500000000000   B  (16n)  4
    0.477200000000000    0.830500000000000    0.163500000000000   B  (16n)  4
    0.022800000000000    0.669500000000000    0.163500000000000   B  (16n)  4
    0.075300000000000    0.338300000000000    0.148500000000000   B  (16n)  5
    0.424700000000000    0.161700000000000    0.148500000000000   B  (16n)  5
    0.161700000000000    0.075300000000000    0.648500000000000   B  (16n)  5
    0.338300000000000    0.424700000000000    0.648500000000000   B  (16n)  5
    0.424700000000000    0.338300000000000    0.351500000000000   B  (16n)  5
    0.075300000000000    0.161700000000000    0.351500000000000   B  (16n)  5
    0.338300000000000    0.075300000000000    0.851500000000000   B  (16n)  5
    0.161700000000000    0.424700000000000    0.851500000000000   B  (16n)  5
   -0.075300000000000    0.661700000000000    0.851500000000000   B  (16n)  5
    0.575300000000000    0.838300000000000    0.851500000000000   B  (16n)  5
    0.838300000000000   -0.075300000000000    0.351500000000000   B  (16n)  5
    0.661700000000000    0.575300000000000    0.351500000000000   B  (16n)  5
    0.575300000000000    0.661700000000000    0.648500000000000   B  (16n)  5
   -0.075300000000000    0.838300000000000    0.648500000000000   B  (16n)  5
    0.661700000000000   -0.075300000000000    0.148500000000000   B  (16n)  5
    0.838300000000000    0.575300000000000    0.148500000000000   B  (16n)  5
```

β-U (A_b): A_tP30_136_bf2ij - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Uranium'
_chemical_formula_sum 'U'

loop_
_publ_author_name
 'Charles W. Tucker, Jr.'
 'Peter Senio'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 6
_journal_year 1953
_journal_page_first 753
_journal_page_last 760
_publ_Section_title
;
 An improved determination of the crystal structure of $\beta$-uranium
;

# Found in  Donohue, pp. 134-147

_aflow_proto 'A_tP30_136_bf2ij'
_aflow_params 'a,c/a,x2,x3,y3,x4,y4,x5,z5'
_aflow_params_values '10.59,0.532011331445,0.1033,0.3667,0.0383,0.5608,
    ↪ 0.2354,0.3183,0.27'
_aflow_Strukturbericht 'A_b'
_aflow_Pearson 'tP30'

_symmetry_space_group_name_Hall "-P 4n 2n"
_symmetry_space_group_name_H-M "P 42/m n m"
_symmetry_Int_Tables_number 136

_cell_length_a     10.59000
_cell_length_b     10.59000
_cell_length_c      5.63400
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x+1/2,y+1/2,-z+1/2
4 -x,-y,z
5 -y,-x,-z
6 -y+1/2,x+1/2,z+1/2
7 y+1/2,-x+1/2,z+1/2
8 y,x,-z
9 -x,-y,-z
10 -x+1/2,y+1/2,z+1/2
11 x+1/2,-y+1/2,z+1/2
12 x,y,-z
13 y,x,z
14 y+1/2,-x+1/2,-z+1/2
15 -y+1/2,x+1/2,-z+1/2
16 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
U1 U   2 b 0.00000 0.00000 0.50000 1.00000
U2 U   4 f 0.10330 0.10330 0.00000 1.00000
U3 U   8 i 0.36670 0.03830 0.00000 1.00000
U4 U   8 i 0.56080 0.23540 0.00000 1.00000
U5 U   8 j 0.31830 0.31830 0.27000 1.00000
```

β-U (A_b): A_tP30_136_bf2ij - POSCAR

```
A_tP30_136_bf2ij & a,c/a,x2,x3,y3,x4,y4,x5,z5 --params=10.59,
    ↪ 0.532011331445,0.1033,0.3667,0.0383,0.5608,0.2354,0.3183,0.27 &
    ↪ P4_2/mnm D_{4h}^{14} #136 (bfi^2j) & tP30 & A_b & U & beta &
    ↪ C. W. Tucker, Jr. and P. Senio, Acta Cryst 6, 753-760 (1953)
   1.0000000000000000
  10.59000000000000    0.00000000000000    0.00000000000000
   0.00000000000000   10.59000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.63400000000000
    U
   30
Direct
   0.00000000000000    0.00000000000000    0.50000000000000    U    (2b)
   0.50000000000000    0.50000000000000    0.00000000000000    U    (2b)
   0.10330000000000    0.10330000000000    0.00000000000000    U    (4f)
   0.39670000000000    0.60330000000000    0.50000000000000    U    (4f)
   0.60330000000000    0.39670000000000    0.50000000000000    U    (4f)
   0.89670000000000    0.89670000000000    0.00000000000000    U    (4f)
   0.03830000000000    0.36670000000000    0.00000000000000    U    (8i)
   0.13330000000000    0.53830000000000    0.50000000000000    U    (8i)
   0.36670000000000    0.03830000000000    0.00000000000000    U    (8i)
   0.46170000000000    0.86670000000000    0.50000000000000    U    (8i)
   0.53830000000000    0.13330000000000    0.50000000000000    U    (8i)
   0.63330000000000    0.96170000000000    0.00000000000000    U    (8i)
   0.86670000000000    0.46170000000000    0.50000000000000    U    (8i)
   0.96170000000000    0.63330000000000    0.00000000000000    U    (8i)
   0.06080000000000    0.26460000000000    0.50000000000000    U    (8i)
  -0.06080000000000    0.73540000000000    0.50000000000000    U    (8i)
   0.23540000000000    0.56080000000000    0.00000000000000    U    (8i)
   0.26460000000000    0.06080000000000    0.50000000000000    U    (8i)
   0.43920000000000    0.76460000000000    0.00000000000000    U    (8i)
   0.56080000000000    0.23540000000000    0.00000000000000    U    (8i)
   0.73540000000000   -0.06080000000000    0.50000000000000    U    (8i)
   0.76460000000000    0.43920000000000    0.00000000000000    U    (8i)
   0.18170000000000    0.81830000000000    0.23000000000000    U    (8j)
   0.18170000000000    0.81830000000000    0.77000000000000    U    (8j)
   0.31830000000000    0.31830000000000    0.27000000000000    U    (8j)
   0.31830000000000    0.31830000000000    0.73000000000000    U    (8j)
   0.68170000000000    0.68170000000000    0.27000000000000    U    (8j)
   0.68170000000000    0.68170000000000    0.73000000000000    U    (8j)
   0.81830000000000    0.18170000000000    0.23000000000000    U    (8j)
   0.81830000000000    0.18170000000000    0.77000000000000    U    (8j)
```

β-BeO: AB_tP8_136_g_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta beryllia'
_chemical_formula_sum 'Be O'

loop_
_publ_author_name
 'Deane K. Smith'
 'Carl F. Cline'
 'Stanley B. Austerman'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 18
_journal_year 1965
_journal_page_first 393
_journal_page_last 397
_publ_Section_title
;
 The Crystal Structure of $\beta$-Beryllia
;

_aflow_proto 'AB_tP8_136_g_f'
_aflow_params 'a,c/a,x1,x2'
_aflow_params_values '4.75,0.576842105263,0.31,0.336'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP8'

_symmetry_space_group_name_Hall "-P 4n 2n"
_symmetry_space_group_name_H-M "P 42/m n m"
_symmetry_Int_Tables_number 136

_cell_length_a     4.75000
_cell_length_b     4.75000
_cell_length_c     2.74000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
```

```
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y+1/2,-z+1/2
3  -x+1/2,y+1/2,-z+1/2
4  -x,-y,z
5  -y,-x,-z
6  -y+1/2,x+1/2,z+1/2
7  y+1/2,-x+1/2,z+1/2
8  y,x,-z
9  -x,-y,-z
10  -x+1/2,y+1/2,z+1/2
11  x+1/2,-y+1/2,z+1/2
12  x,y,-z
13  y,x,z
14  y+1/2,-x+1/2,-z+1/2
15  -y+1/2,x+1/2,-z+1/2
16  -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1   O     4  f  0.31000  0.31000  0.00000  1.00000
Be1  Be    4  g  0.33600  0.66400  0.00000  1.00000
```

β-BeO: AB_tP8_136_g_f - POSCAR

```
AB_tP8_136_g_f & a,c/a,x1,x2 --params=4.75,0.576842105263,0.31,0.336 &
      ↪ P4_2/mnm  D_{4h}^{14} #136 (fg) & tP8 & & BeO & beta & D. K.
      ↪ Smith, C. F. Cline, and S. B. Austerman, Acta Cryst. 18,
      ↪ 393-397 (1965)
   1.0000000000000000
   4.75000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.75000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    2.74000000000000
   Be    O
    4    4
Direct
   0.16400000000000    0.16400000000000    0.50000000000000    Be    (4g)
   0.33600000000000    0.66400000000000    0.00000000000000    Be    (4g)
   0.66400000000000    0.33600000000000    0.00000000000000    Be    (4g)
   0.83600000000000    0.83600000000000    0.50000000000000    Be    (4g)
   0.19000000000000    0.81000000000000    0.50000000000000    O     (4f)
   0.31000000000000    0.31000000000000    0.00000000000000    O     (4f)
   0.69000000000000    0.69000000000000    0.00000000000000    O     (4f)
   0.81000000000000    0.19000000000000    0.50000000000000    O     (4f)
```

Rutile (TiO_2, C4): A2B_tP6_136_f_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method  FINDSYM

_chemical_name_mineral  'Rutile'
_chemical_formula_sum  'Ti O2'

loop_
_publ_author_name
 'R. Jeffrey Swope'
 'Joseph R. Smyth'
 'Allen C. Larson'
_journal_name_full
;
American Mineralogist
;
_journal_volume  80
_journal_year  1995
_journal_page_first  448
_journal_page_last  453
_publ_Section_title
;
 H in rutile-type compounds: I. Single-crystal neutron and X-ray
      ↪ diffraction study of H in rutile
;

# Found in  AMS Database

_aflow_proto  'A2B_tP6_136_f_a'
_aflow_params  'a,c/a,x2'
_aflow_params_values  '4.5922,0.644005052045,0.30496'
_aflow_Strukturbericht  'C4'
_aflow_Pearson  'tP6'

_symmetry_space_group_name_Hall  "-P 4n 2n"
_symmetry_space_group_name_H-M  "P 42/m n m"
_symmetry_Int_Tables_number  136

_cell_length_a      4.59220
_cell_length_b      4.59220
_cell_length_c      2.95740
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y+1/2,-z+1/2
3  -x+1/2,y+1/2,-z+1/2
4  -x,-y,z
5  -y,-x,-z
6  -y+1/2,x+1/2,z+1/2
7  y+1/2,-x+1/2,z+1/2
8  y,x,-z
9  -x,-y,-z
10  -x+1/2,y+1/2,z+1/2
11  x+1/2,-y+1/2,z+1/2
12  x,y,-z
13  y,x,z
14  y+1/2,-x+1/2,-z+1/2
15  -y+1/2,x+1/2,-z+1/2
16  -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1  Ti    2  a  0.00000  0.00000  0.00000  1.00000
O1   O     4  f  0.30496  0.30496  0.00000  1.00000
```

Rutile (TiO_2, C4): A2B_tP6_136_f_a - POSCAR

```
A2B_tP6_136_f_a & a,c/a,x2 --params=4.5922,0.644005052045,0.30496 & P4_2
      ↪ /mnm  D_{4h}^{14} #136 (af) & tP6 & C4 & TiO2 & Rutile & R. J.
      ↪ Swope, J. R. Smithe, and A. C. Larson, Am. Mineral. 80,
      ↪ 448-453 (1995)
   1.0000000000000000
   4.59220000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.59220000000000    0.00000000000000
   0.00000000000000    0.00000000000000    2.95740000000000
    O    Ti
    4    2
Direct
   0.19504000000000    0.80496000000000    0.50000000000000    O     (4f)
   0.30496000000000    0.30496000000000    0.00000000000000    O     (4f)
   0.69504000000000    0.69504000000000    0.00000000000000    O     (4f)
   0.80496000000000    0.19504000000000    0.50000000000000    O     (4f)
   0.00000000000000    0.00000000000000    0.00000000000000    Ti    (2a)
   0.50000000000000    0.50000000000000    0.50000000000000    Ti    (2a)
```

σ-CrFe ($D8_b$): sigma_tP30_136_bf2ij - CIF

```
# CIF file

data_findsym-output
_audit_creation_method  FINDSYM

_chemical_name_mineral  'sigma phase CrFe, different elements used to
      ↪ distinguish Wyckoff positions'
_chemical_formula_sum  'Pd Rh2 Ni4 Cr4 Fe4'

loop_
_publ_author_name
 'H. L. Yakel'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume  39
_journal_year  1983
_journal_page_first  20
_journal_page_last  28
_publ_Section_title
;
 Atom distributions in sigma phases. I. Fe and Cr atom distributions in
      ↪ a binary sigma phase equilibrated at 1063, 1013 and 923 K
;

# Found in  Pearson Vol II. pp. 2639

_aflow_proto  'sigma_tP30_136_bf2ij'
_aflow_params  'a,c/a,x2,x3,y3,x4,y4,x5,z5'
_aflow_params_values  '8.7966,0.518177477662,0.39864,0.13122,0.46349,
      ↪ 0.06609,0.73933,0.18267,0.25202'
_aflow_Strukturbericht  'D8_b'
_aflow_Pearson  'tP30'

_symmetry_space_group_name_Hall  "-P 4n 2n"
_symmetry_space_group_name_H-M  "P 42/m n m"
_symmetry_Int_Tables_number  136

_cell_length_a      8.79660
_cell_length_b      8.79660
_cell_length_c      4.55820
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y+1/2,-z+1/2
3  -x+1/2,y+1/2,-z+1/2
```

```
4 -x,-y,z
5 -y,-x,-z
6 -y+1/2,x+1/2,z+1/2
7 y+1/2,-x+1/2,z+1/2
8 y,x,-z
9 -x,-y,-z
10 -x+1/2,y+1/2,z+1/2
11 x+1/2,-y+1/2,z+1/2
12 x,y,-z
13 y,x,z
14 y+1/2,-x+1/2,-z+1/2
15 -y+1/2,x+1/2,-z+1/2
16 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pd1 Pd    2 b 0.00000   0.00000 0.50000 1.00000
Rh1 Rh    4 f 0.39864   0.39864 0.00000 1.00000
Ni1 Ni    8 i 0.13122   0.46349 0.00000 1.00000
Cr1 Cr    8 i 0.06609   0.73933 0.00000 1.00000
Fe1 Fe    8 j 0.18267   0.18267 0.25202 1.00000
```

σ-CrFe ($D8_b$): sigma_tP30_136_bf2ij - POSCAR

```
sigma_tP30_136_bf2ij & a,c/a,x2,x3,y3,x4,y4,x5,z5 --params=8.7966,
      ↪ 0.518177477662,0.39864,0.13122,0.46349,0.06609,0.73933,0.18267,
      ↪ 0.25202 & P4_2/mnm  D_{4h}^{14} #136 (bfi^2j) & tP30 & D8_b &
      ↪ CrFe & sigma (disordered) & H. L. Yakel, Acta Cryst B 39, 20-28
      ↪ (1983)
   1.0000000000000000
   8.79660000000000    0.00000000000000    0.00000000000000
   0.00000000000000    8.79660000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.55820000000000
    M
   30
Direct
   0.00000000000000    0.00000000000000    0.50000000000000    M    (2b)
   0.50000000000000    0.50000000000000    0.00000000000000    M    (2b)
   0.10136000000000    0.89864000000000    0.50000000000000    M    (4f)
   0.39864000000000    0.39864000000000    0.00000000000000    M    (4f)
   0.60136000000000    0.60136000000000    0.00000000000000    M    (4f)
   0.89864000000000    0.10136000000000    0.50000000000000    M    (4f)
   0.03651000000000    0.63122000000000    0.50000000000000    M    (8i)
   0.13122000000000    0.46349000000000    0.00000000000000    M    (8i)
   0.36878000000000    0.96349000000000    0.50000000000000    M    (8i)
   0.46349000000000    0.13122000000000    0.00000000000000    M    (8i)
   0.53651000000000    0.86878000000000    0.00000000000000    M    (8i)
   0.63122000000000    0.03651000000000    0.50000000000000    M    (8i)
   0.86878000000000    0.53651000000000    0.00000000000000    M    (8i)
   0.96349000000000    0.36878000000000    0.50000000000000    M    (8i)
   0.06609000000000    0.73933000000000    0.00000000000000    M    (8i)
   0.23933000000000    0.43391000000000    0.50000000000000    M    (8i)
   0.26067000000000    0.93391000000000    0.00000000000000    M    (8i)
   0.43391000000000    0.23933000000000    0.50000000000000    M    (8i)
   0.56609000000000    0.76067000000000    0.50000000000000    M    (8i)
   0.73933000000000    0.06609000000000    0.00000000000000    M    (8i)
   0.76067000000000    0.56609000000000    0.50000000000000    M    (8i)
   0.93391000000000    0.26067000000000    0.00000000000000    M    (8i)
   0.18267000000000    0.18267000000000    0.25202000000000    M    (8j)
   0.18267000000000    0.18267000000000    0.74798000000000    M    (8j)
   0.31733000000000    0.68267000000000    0.24798000000000    M    (8j)
   0.31733000000000    0.68267000000000    0.75202000000000    M    (8j)
   0.68267000000000    0.31733000000000    0.24798000000000    M    (8j)
   0.68267000000000    0.31733000000000    0.75202000000000    M    (8j)
   0.81733000000000    0.81733000000000    0.25202000000000    M    (8j)
   0.81733000000000    0.81733000000000    0.74798000000000    M    (8j)
```

γ-N: A_tP4_136_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'gamma nitrogen'
_chemical_formula_sum 'N'

loop_
_publ_author_name
 'R. L. Mills'
 'A. F. Schuch'
_journal_name_full
;
Physical Review Letters
;
_journal_volume 23
_journal_year 1969
_journal_page_first 1154
_journal_page_last 1156
_publ_Section_title
;
 Crystal Structure of Gamma Nitrogen
;

# Found in  Donohue, pp. 207-208

_aflow_proto 'A_tP4_136_f'
_aflow_params 'a,c/a,x1'
_aflow_params_values '3.957,1.29112964367,0.098'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tP4'

_symmetry_space_group_name_Hall "-P 4n 2n"
_symmetry_space_group_name_H-M "P 42/m n m"
_symmetry_Int_Tables_number 136

_cell_length_a     3.95700
_cell_length_b     3.95700
_cell_length_c     5.10900
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z+1/2
3 -x+1/2,y+1/2,-z+1/2
4 -x,-y,z
5 -y,-x,-z
6 -y+1/2,x+1/2,z+1/2
7 y+1/2,-x+1/2,z+1/2
8 y,x,-z
9 -x,-y,-z
10 -x+1/2,y+1/2,z+1/2
11 x+1/2,-y+1/2,z+1/2
12 x,y,-z
13 y,x,z
14 y+1/2,-x+1/2,-z+1/2
15 -y+1/2,x+1/2,-z+1/2
16 -y,-x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
N1 N    4 f 0.09800 0.09800 0.00000 1.00000
```

γ-N: A_tP4_136_f - POSCAR

```
A_tP4_136_f & a,c/a,x1 --params=3.957,1.29112964367,0.098 & P4_2/mnm  D_
      ↪ {4h}^{14} #136 (f) & tP4 & & N & gamma & R. L. Mills and A. F.
      ↪ Schuch, Phys. Rev. Lett. 23, 1154-1156 (1969)
   1.0000000000000000
   3.95700000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.95700000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.10900000000000
    N
    4
Direct
   0.09800000000000    0.09800000000000    0.00000000000000    N    (4f)
  -0.09800000000000   -0.09800000000000    0.00000000000000    N    (4f)
   0.40200000000000    0.59800000000000    0.50000000000000    N    (4f)
   0.59800000000000    0.40200000000000    0.50000000000000    N    (4f)
```

Cl (A18): A_tP16_138_j - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cl'

loop_
_publ_author_name
 'W. H. Keesom'
 'K. W. Taconis'
_journal_name_full
;
Physica
;
_journal_volume 3
_journal_year 1936
_journal_page_first 237
_journal_page_last 242
_publ_Section_title
;
 On the crystal structure of chlorine
;

# Found in  Donohue, pp. 396, Strukturbericht IV, pp. 1-4

_aflow_proto 'A_tP16_138_j'
_aflow_params 'a,c/a,x1,y1,z1'
_aflow_params_values '8.56,0.714953271028,0.375,-0.083,0.857'
_aflow_Strukturbericht 'A18'
_aflow_Pearson 'tP16'

_symmetry_space_group_name_Hall "-P 4ac 2ac"
_symmetry_space_group_name_H-M "P 42/n c m:2"
_symmetry_Int_Tables_number 138

_cell_length_a     8.56000
_cell_length_b     8.56000
_cell_length_c     6.12000
```

```
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x+1/2,-y,-z+1/2
3  -x,y+1/2,-z+1/2
4  -x+1/2,-y+1/2,z
5  -y,-x,-z
6  -y+1/2,x,z+1/2
7  y,-x+1/2,z+1/2
8  y+1/2,x+1/2,-z
9  -x,-y,-z
10  -x+1/2,y,z+1/2
11  x,-y+1/2,z+1/2
12  x+1/2,y+1/2,-z
13  y,x,z
14  y+1/2,-x,-z+1/2
15  -y,x+1/2,-z+1/2
16  -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cl1  Cl   16  j  0.37500  -0.08300  0.85700  1.00000
```

Cl (A18): A_tP16_138_j - POSCAR

```
A_tP16_138_j & a,c/a,x1,y1,z1 --params=8.56,0.714953271028,0.375,-0.083,
    ↪ 0.857 & P4_2/ncm  D_{4h}^{16} #138 (j) & tP16 & A18 & Cl & & W.
    ↪  H. Keesom and K. W. Taconis, Physica 3, 237-242 (1936)
   1.0000000000000000
   8.56000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    8.56000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.12000000000000
   Cl
   16
Direct
    0.3750000000000    -0.0830000000000    0.8570000000000    Cl    (16j)
    0.1250000000000     0.5830000000000    0.8570000000000    Cl    (16j)
    0.5830000000000     0.3750000000000    0.3570000000000    Cl    (16j)
   -0.0830000000000     0.1250000000000    0.3570000000000    Cl    (16j)
    0.6250000000000     0.4170000000000    0.6430000000000    Cl    (16j)
    0.8750000000000     0.0830000000000    0.6430000000000    Cl    (16j)
    0.4170000000000     0.8750000000000    0.1430000000000    Cl    (16j)
    0.0830000000000     0.6250000000000    0.1430000000000    Cl    (16j)
    0.6250000000000     0.0830000000000    0.1430000000000    Cl    (16j)
    0.8750000000000     0.4170000000000    0.1430000000000    Cl    (16j)
    0.4170000000000     0.6250000000000    0.6430000000000    Cl    (16j)
    0.0830000000000     0.8750000000000    0.6430000000000    Cl    (16j)
    0.3750000000000     0.5830000000000    0.3570000000000    Cl    (16j)
    0.1250000000000    -0.0830000000000    0.3570000000000    Cl    (16j)
    0.5830000000000     0.1250000000000    0.8570000000000    Cl    (16j)
   -0.0830000000000     0.3750000000000    0.8570000000000    Cl    (16j)
```

Al_3Zr ($D0_{23}$): A3B_tI16_139_cde_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Al3 Zr'

loop_
_publ_author_name
 'Y. Ma'
 'C. R{\o}mming'
 'B. Lebech'
 'J. Gj{\o}nnes'
 'J. Taft{\o}'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 48
_journal_year 1992
_journal_page_first 11
_journal_page_last 16
_publ_Section_title
;
 Structure Refinement of Al3Zr using Single-Crystal X-ray Diffraction,
    ↪ Powder Neutron Diffraction and CBED
;

# Found in  ghosh05:AlTM

_aflow_proto 'A3B_tI16_139_cde_e'
_aflow_params 'a,c/a,z3,z4'
_aflow_params_values '3.9993,4.3215062636,0.37498,0.11886'
_aflow_Strukturbericht 'D0_23'
_aflow_Pearson 'tI16'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a      3.99930
_cell_length_b      3.99930
_cell_length_c      17.28300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x,-y,-z
3  -x,y,-z
4  -x,-y,z
5  -y,-x,-z
6  -y,x,z
7  y,-x,z
8  y,x,-z
9  -x,-y,-z
10  -x,y,z
11  x,-y,z
12  x,y,-z
13  y,x,z
14  y,-x,-z
15  -y,x,-z
16  -y,-x,z
17  x+1/2,y+1/2,z+1/2
18  x+1/2,-y+1/2,-z+1/2
19  -x+1/2,y+1/2,-z+1/2
20  -x+1/2,-y+1/2,z+1/2
21  -y+1/2,-x+1/2,-z+1/2
22  -y+1/2,x+1/2,z+1/2
23  y+1/2,-x+1/2,z+1/2
24  y+1/2,x+1/2,-z+1/2
25  -x+1/2,-y+1/2,-z+1/2
26  -x+1/2,y+1/2,z+1/2
27  x+1/2,-y+1/2,z+1/2
28  x+1/2,y+1/2,-z+1/2
29  y+1/2,x+1/2,z+1/2
30  y+1/2,-x+1/2,-z+1/2
31  -y+1/2,x+1/2,-z+1/2
32  -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1  Al    4  c  0.00000  0.50000  0.00000  1.00000
Al2  Al    4  d  0.00000  0.50000  0.25000  1.00000
Al3  Al    4  e  0.00000  0.00000  0.37498  1.00000
Zr1  Zr    4  e  0.00000  0.00000  0.11886  1.00000
```

Al_3Zr ($D0_{23}$): A3B_tI16_139_cde_e - POSCAR

```
A3B_tI16_139_cde_e & a,c/a,z3,z4 --params=3.9993,4.3215062636,0.37498,
    ↪ 0.11886 & I4/mmm  D_{4h}^{17} #139 (cde^2) & tI16 & D0_{23} &
    ↪  Al3Zr & & Y. Ma, C. R{\o}mming, B. Lebech, J. Gj{\o}nnes and
    ↪ J. Taft{\o}, Acta Cryst. B 48, 11-16 (1992)
   1.0000000000000000
  -1.99965000000000    1.99965000000000    8.64150000000000
   1.99965000000000   -1.99965000000000    8.64150000000000
   1.99965000000000    1.99965000000000   -8.64150000000000
   Al    Zr
    6     2
Direct
   0.00000000000000    0.50000000000000    0.50000000000000    Al    (4c)
   0.50000000000000    0.00000000000000    0.50000000000000    Al    (4c)
   0.25000000000000    0.75000000000000    0.50000000000000    Al    (4d)
   0.75000000000000    0.25000000000000    0.50000000000000    Al    (4d)
   0.37498000000000    0.37498000000000    0.00000000000000    Al    (4e)
   0.62502000000000    0.62502000000000    0.00000000000000    Al    (4e)
   0.11886000000000    0.11886000000000    0.00000000000000    Zr    (4e)
   0.88114000000000    0.88114000000000    0.00000000000000    Zr    (4e)
```

Hypothetical BCT5 Si: A_tI4_139_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'BCT5'
_chemical_formula_sum 'Si'

loop_
_publ_author_name
 'L. L. Boyer'
 'Efthimios Kaxiras'
 'J. L. Feldman'
 'J. Q. Broughton'
 'M. J. Mehl'
_journal_name_full
;
Physical Review Letters
;
_journal_volume 67
_journal_year 1991
_journal_page_first 715
```

```
_journal_page_last 718
_publ_Section_title
;
 New low-energy crystal structure for silicon
;

_aflow_proto 'A_tI4_139_e'
_aflow_params 'a,c/a,z1'
_aflow_params_values '3.34916,1.94217355994,0.819'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI4'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a      3.34916
_cell_length_b      3.34916
_cell_length_c      6.50465
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si    4 e 0.00000 0.00000 0.81900 1.00000
```

Hypothetical BCT5 Si: A_tI4_139_e - POSCAR

```
A_tI4_139_e & a,c/a,z1 --params=3.34916,1.94217355994,0.819 & I4/mmm
      ↪ D_{4h}^{17} #139 (e) & tI4 & & Si & BCT5 & L. L. Boyer, E.
      ↪ Kaxiras, J. L. Feldman, J. Q. Broughton and M. J. Mehl, PRL 67,
      ↪ 715-718 (1991)
   1.0000000000000000
  -1.67458127566500   1.67458127566500   3.25232312221200
   1.67458127566500  -1.67458127566500   3.25232312221200
   1.67458127566500   1.67458127566500  -3.25232312221200
   Si
    2
Direct
   0.18100000000000   0.18100000000000   0.00000000000000   Si   (4e)
   0.81900000000000   0.81900000000000   0.00000000000000   Si   (4e)
```

0201 [(La,Ba)$_2$CuO$_4$]: AB2C4_tI14_139_a_e_ce - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral '(La,Ba)CuO4'
_chemical_formula_sum 'La2 Cu O4'

loop_
_publ_author_name
 'J. D. Jorgensen'
 'H.-B. Sch\"{u}ttler'
 'D. G. Hinks'
 'D. W. Capone, II'
 'K. Zhang'
 'M. B. Brodsky'
_journal_name_full
;
Physical Review Letters
;
_journal_volume 58
_journal_year 1987
_journal_page_first 1024
_journal_page_last 1029
_publ_Section_title
;
 Lattice instability and high-$T_c$ superconductivity in La$_{2-x}
      ↪ $Ba$_x$CuO$_4$
;

# Found in  shaked94:hightcstruct

_aflow_proto 'AB2C4_tI14_139_a_e_ce'
_aflow_params 'a,c/a,z3,z4'
_aflow_params_values '3.7817,3.50337149959,0.36075,0.1824'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI14'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a      3.78170
_cell_length_b      3.78170
_cell_length_c      13.24870
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    2 a 0.00000 0.00000 0.00000 1.00000
O1  O     4 c 0.00000 0.50000 0.00000 1.00000
La1 La    4 e 0.00000 0.00000 0.36075 1.00000
O2  O     4 e 0.00000 0.00000 0.18240 1.00000
```

0201 [(La,Ba)$_2$CuO$_4$]: AB2C4_tI14_139_a_e_ce - POSCAR

```
AB2C4_tI14_139_a_e_ce & a,c/a,z3,z4 --params=3.7817,3.50337149959,
      ↪ 0.36075,0.1824 & I4/mmm    D_{4h}^{17} #139 (ace^2) & tI14 & &
      ↪ (La,Ba)2CuO4 & 0201 Superconductor & J. D. Jorgensen et al.,
      ↪ PRL 58, 1024-1028 (1987)
   1.0000000000000000
  -1.890850000000   1.890850000000   6.624350000000
   1.890850000000  -1.890850000000   6.624350000000
   1.890850000000   1.890850000000  -6.624350000000
   Cu   La   O
    1    2    4
Direct
   0.000000000000   0.000000000000   0.000000000000   Cu   (2a)
   0.360750000000   0.360750000000   0.000000000000   La   (4e)
   0.639250000000   0.639250000000   0.000000000000   La   (4e)
   0.500000000000   0.000000000000   0.500000000000   O    (4c)
   0.000000000000   0.500000000000   0.500000000000   O    (4c)
   0.182400000000   0.182400000000   0.000000000000   O    (4e)
   0.817600000000   0.817600000000   0.000000000000   O    (4e)
```

$Mn_{12}Th$ ($D2_b$): A12B_tI26_139_fij_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Mn12 Th'

loop_
_publ_author_name
 'John V. Florio'
 'R. E. Rundle'
 'A. I. Snow'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 5
_journal_year 1952
_journal_page_first 449
_journal_page_last 457
_publ_Section_title
;
 Compounds of thorium with transition metals. I. The thorium-manganese
      ↪ system
;

# Found in  Pearson's Handbook, Vol. IV, pp. 4396

_aflow_proto 'A12B_tI26_139_fij_a'
_aflow_params 'a,c/a,x3,x4'
_aflow_params_values '8.47,0.584415584416,0.361,0.278'
_aflow_Strukturbericht 'D2_b'
_aflow_Pearson 'tI26'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a      8.47000
_cell_length_b      8.47000
_cell_length_c      4.95000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Th1 Th    2 a 0.00000 0.00000 0.00000 1.00000
Mn1 Mn    8 f 0.25000 0.25000 0.25000 1.00000
Mn2 Mn    8 i 0.36100 0.00000 0.00000 1.00000
Mn3 Mn    8 j 0.27800 0.50000 0.00000 1.00000
```

$Mn_{12}Th$ ($D2_b$): A12B_tI26_139_fij_a - POSCAR

```
A12B_tI26_139_fij_a & a,c/a,x3,x4 --params=8.47,0.584415584416,0.361,
      ↪ 0.278 & I4/mmm     D_{4h}^{17} #139 (afij) & tI26 & D2_b &
      ↪ Mn12Th & & J. V. Florio, R. E. Rundle and A. I. Snow, Acta
      ↪ Cryst. 5, 449-457 (1952)
   1.0000000000000000
  -4.23500000000000    4.23500000000000    2.47500000000000
   4.23500000000000   -4.23500000000000    2.47500000000000
   4.23500000000000    4.23500000000000   -2.47500000000000
   Mn    Th
   12    1
Direct
   0.00000000000000    0.00000000000000    0.50000000000000    Mn    (8f)
   0.00000000000000    0.50000000000000    0.00000000000000    Mn    (8f)
   0.50000000000000    0.00000000000000    0.00000000000000    Mn    (8f)
   0.50000000000000    0.50000000000000    0.50000000000000    Mn    (8f)
   0.00000000000000    0.36100000000000    0.36100000000000    Mn    (8i)
   0.00000000000000    0.63900000000000    0.63900000000000    Mn    (8i)
   0.36100000000000    0.00000000000000    0.36100000000000    Mn    (8i)
   0.63900000000000    0.00000000000000    0.63900000000000    Mn    (8i)
   0.27800000000000    0.50000000000000    0.77800000000000    Mn    (8j)
   0.50000000000000    0.27800000000000    0.77800000000000    Mn    (8j)
   0.50000000000000    0.72200000000000    0.22200000000000    Mn    (8j)
   0.72200000000000    0.50000000000000    0.22200000000000    Mn    (8j)
   0.00000000000000    0.00000000000000    0.00000000000000    Th    (2a)
```

In (A6): A_tI2_139_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Indium'
_chemical_formula_sum 'In'

loop_
_publ_author_name
 'V. T. Deshpande'
 'R. R. Pawar'
_journal_name_full
;
Acta Crystallographica A
;
_journal_volume 25
_journal_year 1969
_journal_page_first 415
_journal_page_last 416
_publ_Section_title
;
 Anisotropic Thermal Expansion of Indium
;

# Found in  Donohue, pp. 244-246

_aflow_proto 'A_tI2_139_a'
_aflow_params 'a,c/a'
_aflow_params_values '4.6002,1.07523585931'
_aflow_Strukturbericht 'A6'
_aflow_Pearson 'tI2'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a      4.60020
_cell_length_b      4.60020
_cell_length_c      4.94630
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
```

```
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
In1 In    2 a 0.00000 0.00000 0.00000 1.00000
```

In (A6): A_tI2_139_a - POSCAR

```
A_tI2_139_a & a,c/a --params=4.6002,1.07523585931 & I4/mmm    D_{4h}^{17
    ↪ } #139 (a) & tI2 & A6 & In & & V. T. Deshpande and R. R. Pawar,
    ↪  Acta Cryst. B 25, 415-416 (1969)
   1.0000000000000000
 -2.300100000000   2.300100000000   2.473150000000
  2.300100000000  -2.300100000000   2.473150000000
  2.300100000000   2.300100000000  -2.473150000000
   In
    1
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   In    (2a)
```

Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Theoretical Carbon Structure'
_chemical_formula_sum 'C'

loop_
_publ_author_name
 'Peter A. Schultz'
 'Kevin Leung'
 'E. B. Stechel'
_journal_name_full
;
Physical Review B
;
_journal_volume 59
_journal_year 1999
_journal_page_first 733
_journal_page_last 741
_publ_Section_title
;
 Small rings and amorphous tetrahedral carbon
;

_aflow_proto 'A_tI8_139_h'
_aflow_params 'a,c/a,x1'
_aflow_params_values '4.33184,0.574102459925,0.17916'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI8'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a    4.33184
_cell_length_b    4.33184
_cell_length_c    2.48692
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1 C    8 h 0.17916 0.17916 0.00000 1.00000
```

Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h - POSCAR

```
A_tI8_139_h & a,c/a,x1 --params=4.33184,0.574102459925,0.17916 & I4/mmm
    ↪     D_{4h}^{17} #139 (h) & tI8 & & C & hypothetical 4-member
    ↪ ring structure & P. A. Schultz, K. Leung and E. B. Stechel, PRB
    ↪  59, 733-741 (1999)
   1.0000000000000000
 -2.16592000000000   2.16592000000000   1.24346000000000
  2.16592000000000  -2.16592000000000   1.24346000000000
  2.16592000000000   2.16592000000000  -1.24346000000000
   C
   4
Direct
   0.17916000000000   0.17916000000000   0.35832000000000   C    (8h)
   0.17916000000000   0.82084000000000   0.00000000000000   C    (8h)
   0.82084000000000   0.17916000000000   0.00000000000000   C    (8h)
   0.82084000000000   0.82084000000000   0.64168000000000   C    (8h)
```

Al_3Ti ($D0_{22}$): A3B_tI8_139_bd_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Al3 Ti'

loop_
_publ_author_name
 'P. Norby'
 'A. N{\o}rlund Christensen'
_journal_name_full
;
Acta Chemica Scandinavica
;
_journal_volume A40
_journal_year 1986
_journal_page_first 157
_journal_page_last 159
_publ_Section_title
;
 Preparation and Structure of Al$_3$Ti
;

# Found in  Pearson's Handbook, Vol. I, p. 1023

_aflow_proto 'A3B_tI8_139_bd_a'
_aflow_params 'a,c/a'
_aflow_params_values '3.8537,2.22744375535'
_aflow_Strukturbericht 'D0_22'
_aflow_Pearson 'tI8'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a    3.85370
_cell_length_b    3.85370
_cell_length_c    8.58390
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
```

```
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1 Ti   2 a 0.00000 0.00000 0.00000 1.00000
Al1 Al   2 b 0.00000 0.00000 0.50000 1.00000
Al2 Al   4 d 0.00000 0.50000 0.25000 1.00000
```

Al_3Ti ($D0_{22}$): A3B_tI8_139_bd_a - POSCAR

```
A3B_tI8_139_bd_a & a,c/a --params=3.8537,2.22744375535 & I4/mmm  D_{4h
    ↪ }^{17} #139 (abd) & tI8 & D0_{22} & Al3Ti & & P. Norby and A.
    ↪ Norlund Christensen, Acta Chem. Scand. A 40, 157-159 (1986)
  1.0000000000000000
 -1.92685000000000   1.92685000000000   4.29195000000000
  1.92685000000000  -1.92685000000000   4.29195000000000
  1.92685000000000   1.92685000000000  -4.29195000000000
  Al   Ti
   3    1
Direct
  0.50000000000000   0.50000000000000   0.00000000000000   Al   (2b)
  0.25000000000000   0.75000000000000   0.50000000000000   Al   (4d)
  0.75000000000000   0.25000000000000   0.50000000000000   Al   (4d)
  0.00000000000000   0.00000000000000   0.00000000000000   Ti   (2a)
```

$MoSi_2$ ($C11_b$): AB2_tI6_139_a_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Mo Si2'

loop_
_publ_author_name
 'Y. Harada'
 'M. Morinaga'
 'D. Saso'
 'M. Takata'
 'M. Sakata'
_journal_name_full
;
Intermetallics
;
_journal_volume 6
_journal_year 1998
_journal_page_first 523
_journal_page_last 527
_publ_Section_title
;
 Refinement of crystal structure in MoSi$_2$
;

_aflow_proto 'AB2_tI6_139_a_e'
_aflow_params 'a,c/a,z2'
_aflow_params_values '3.2064,2.44754241517,0.3353'
_aflow_Strukturbericht 'C11_b'
_aflow_Pearson 'tI6'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a    3.20640
_cell_length_b    3.20640
_cell_length_c    7.84780
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mo1 Mo   2 a 0.00000 0.00000 0.00000 1.00000
Si1 Si   4 e 0.00000 0.00000 0.33530 1.00000
```

$MoSi_2$ ($C11_b$): AB2_tI6_139_a_e - POSCAR

```
AB2_tI6_139_a_e & a,c/a,z2 --params=3.2064,2.44754241517,0.3353 & I4/mmm
    ↪      D_{4h}^{17} #139 (ae) & tI6 & C11_b & MoSi_2 & & Y. Harada,
    ↪  M. Morinaga, D. Saso, M. Takata and M. Sakata, Intermetallics
    ↪ 6, 523-527 (1998)
  1.0000000000000000
 -1.60320000000000   1.60320000000000   3.92390000000054
  1.60320000000000  -1.60320000000000   3.92390000000054
  1.60320000000000   1.60320000000000  -3.92390000000054
  Mo   Si
   1    2
Direct
  0.00000000000000   0.00000000000000   0.00000000000000   Mo   (2a)
  0.33530000000000   0.33530000000000   0.00000000000000   Si   (4e)
  0.66470000000000   0.66470000000000   0.00000000000000   Si   (4e)
```

V_4Zn_5: A4B5_tI18_139_i_ah - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'V4 Zn5'

loop_
_publ_author_name
 'K. Schubert'
 'H. G. Meissner'
 'A. Raman'
 'W. Rossteutscher'
_journal_name_full
;
Naturwissenschaften
;
_journal_volume 51
_journal_year 1964
_journal_page_first 287
_journal_page_last 287
_publ_Section_title
;
 Einige Strukturdaten metallischer Phasen (9)
;

# Found in  Pearson's Handbook, Vol. IV, pp. 5154

_aflow_proto 'A4B5_tI18_139_i_ah'
_aflow_params 'a,c/a,x2,x3'
_aflow_params_values '8.91,0.361391694725,0.328,0.348'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI18'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a    8.91000
_cell_length_b    8.91000
_cell_length_c    3.22000
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
```

```
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Zn1 Zn    2 a 0.00000 0.00000 0.00000 1.00000
Zn2 Zn    8 h 0.32800 0.32800 0.00000 1.00000
V1  V     8 i 0.34800 0.00000 0.00000 1.00000
```

V_4Zn_5: A4B5_tI18_139_i_ah - POSCAR

```
A4B5_tI18_139_i_ah & a,c/a,x2,x3 --params=8.91,0.361391694725,0.328,
    ↪ 0.348 & I4/mmm     D_{4h}^{17} #139 (ahi) & tI18 & & V4Zn5 & &
    ↪ K. Schubert, H. G. Meissner, A. Raman and W. Rossteutscher,
    ↪ Naturwissenschaften 51, 287 (1964)
   1.0000000000000000
  -4.45500000000000    4.45500000000000    1.61000000000000
   4.45500000000000   -4.45500000000000    1.61000000000000
   4.45500000000000    4.45500000000000   -1.61000000000000
    V    Zn
    4     5
Direct
   0.00000000000000    0.34800000000000    0.34800000000000     V     (8i)
   0.00000000000000    0.65200000000000    0.65200000000000     V     (8i)
   0.34800000000000    0.00000000000000    0.34800000000000     V     (8i)
   0.65200000000000    0.00000000000000    0.65200000000000     V     (8i)
   0.00000000000000    0.00000000000000    0.00000000000000    Zn     (2a)
   0.32800000000000    0.32800000000000    0.65600000000000    Zn     (8h)
   0.32800000000000    0.67200000000000    0.00000000000000    Zn     (8h)
   0.67200000000000    0.32800000000000    0.00000000000000    Zn     (8h)
   0.67200000000000    0.67200000000000    0.34400000000000    Zn     (8h)
```

Al_4Ba ($D1_3$): A4B_tI10_139_de_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Al4 Ba'

loop_
_publ_author_name
 'K. R. Andress'
 'E. Alberti'
_journal_name_full
;
Zeitschrift f\"{u}r Metallkunde
;
_journal_volume 27
_journal_year 1935
_journal_page_first 126
_journal_page_last 128
_publ_Section_title
;
 R\"{o}ntgenographische Untersuchung der Legierungsreihe
    ↪ Aluminium-Barium
;

_aflow_proto 'A4B_tI10_139_de_a'
_aflow_params 'a,c/a,z3'
_aflow_params_values '4.53,2.45033112583,0.38'
_aflow_Strukturbericht 'D1_3'
_aflow_Pearson 'tI10'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a      4.53000
_cell_length_b      4.53000
_cell_length_c      11.10000
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ba1 Ba    2 a 0.00000 0.00000 0.00000 1.00000
Al1 Al    4 d 0.00000 0.50000 0.25000 1.00000
Al2 Al    4 e 0.00000 0.00000 0.38000 1.00000
```

Al_4Ba ($D1_3$): A4B_tI10_139_de_a - POSCAR

```
A4B_tI10_139_de_a & a,c/a,z3 --params=4.53,2.45033112583,0.38 & I4/mmm
    ↪     D_{4h}^{17} #139 (ade) & tI10 & D1_3 & Al4Ba & & K.R.
    ↪ Andress and E. Alberto, Z. Metallkd. 27(26), 126-128 (1935)
   1.0000000000000000
  -2.26500000000000    2.26500000000000    5.55000000000000
   2.26500000000000   -2.26500000000000    5.55000000000000
   2.26500000000000    2.26500000000000   -5.55000000000000
    Al    Ba
    4     1
Direct
   0.25000000000000    0.75000000000000    0.50000000000000    Al     (4d)
   0.75000000000000    0.25000000000000    0.50000000000000    Al     (4d)
   0.38000000000000    0.38000000000000    0.00000000000000    Al     (4e)
   0.62000000000000    0.62000000000000    0.00000000000000    Al     (4e)
   0.00000000000000    0.00000000000000    0.00000000000000    Ba     (2a)
```

Pt_8Ti: A8B_tI18_139_hi_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Pt8 Ti'

loop_
_publ_author_name
 'P. Pietrokowsky'
_journal_name_full
;
Nature
;
_journal_volume 206
_journal_year 1965
_journal_page_first 291
_journal_page_last 291
_publ_Section_title
;
 Novel Ordered Phase, Pt$_8$Ti
;

# Found in  Pearson's Handbook, Vol. IV, pp. 5011

_aflow_proto 'A8B_tI18_139_hi_a'
_aflow_params 'a,c/a,x2,x3'
_aflow_params_values '8.312,0.468840230991,0.333,0.327'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI18'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a      8.31200
_cell_length_b      8.31200
_cell_length_c      3.89700
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000
```

```
loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1 Ti   2 a 0.00000 0.00000 0.00000 1.00000
Pt1 Pt   8 h 0.33300 0.33300 0.00000 1.00000
Pt2 Pt   8 i 0.32700 0.00000 0.00000 1.00000
```

Pt_8Ti: A8B_tI18_139_hi_a - POSCAR

```
A8B_tI18_139_hi_a & a,c/a,x2,x3 --params=8.312,0.468840230991,0.333,
    ↪ 0.327 & I4/mmm D_{4h}^{17} #139 (ahi) & tI18 & & Pt8Ti & &
    ↪ P. Pietrokowsky, Nature 206, 291 (1965)
   1.0000000000000000
  -4.15600000000000   4.15600000000000   1.94850000000000
   4.15600000000000  -4.15600000000000   1.94850000000000
   4.15600000000000   4.15600000000000  -1.94850000000000
   Pt   Zn
    8    1
Direct
   0.33300000000000   0.33300000000000   0.66600000000000   Pt   (8h)
   0.33300000000000   0.66700000000000   0.00000000000000   Pt   (8h)
   0.66700000000000   0.33300000000000   0.00000000000000   Pt   (8h)
   0.66700000000000   0.66700000000000   0.33400000000000   Pt   (8h)
   0.00000000000000   0.32700000000000   0.32700000000000   Pt   (8i)
   0.00000000000000   0.67300000000000   0.67300000000000   Pt   (8i)
   0.32700000000000   0.00000000000000   0.32700000000000   Pt   (8i)
   0.67300000000000   0.00000000000000   0.67300000000000   Pt   (8i)
   0.00000000000000   0.00000000000000   0.00000000000000   Ti   (2a)
```

ThH_2 (L'2): A2B_tI6_139_d_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Th H2'

loop_
_publ_author_name
 'R. E. Rundle'
 'C. G. Shull'
 'E. O. Wollan'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 5
_journal_year 1952
_journal_page_first 22
_journal_page_last 26
_publ_Section_title
;
 The crystal structure of thorium and zirconium dihydrides by X-ray and
    ↪ neutron diffraction
;

_aflow_proto 'A2B_tI6_139_d_a'
_aflow_params 'a,c/a'
_aflow_params_values '4.1,1.22682926829'
_aflow_Strukturbericht 'L\'2'
_aflow_Pearson 'tI6'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a     4.10000
_cell_length_b     4.10000
_cell_length_c     5.03000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Th1 Th   2 a 0.00000 0.00000 0.00000 1.00000
H1  H    4 d 0.00000 0.50000 0.25000 1.00000
```

ThH_2 (L'2): A2B_tI6_139_d_a - POSCAR

```
A2B_tI6_139_d_a & a,c/a --params=4.1,1.22682926829 & I4/mmm D_{4h}^{
    ↪ 17} #139 (ad) & tI6 & L'2 & ThH2 & & R. E. Rundle, C. G. Shull
    ↪ and E. O. Wollan, Acta Cryst. 5, 22-26 (1952)
   1.0000000000000000
  -2.05000000000000   2.05000000000000   2.51500000000000
   2.05000000000000  -2.05000000000000   2.51500000000000
   2.05000000000000   2.05000000000000  -2.51500000000000
   H   Th
   2    1
Direct
   0.25000000000000   0.75000000000000   0.50000000000000   H   (4d)
   0.75000000000000   0.25000000000000   0.50000000000000   H   (4d)
   0.00000000000000   0.00000000000000   0.00000000000000   Th  (2a)
```

α-Pa (A_a): A_tI2_139_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Protactinium'
_chemical_formula_sum 'Pa'

loop_
_publ_author_name
 'W. H. Zachariasen'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 12
_journal_year 1959
_journal_page_first 698
_journal_page_last 700
_publ_Section_title
;
 On the crystal structure of protactinium metal
;

# Found in  Donohue, pp. 125-127
```

```
_aflow_proto 'A_tI2_139_a'
_aflow_params 'a,c/a'
_aflow_params_values '3.932,0.823499491353'
_aflow_Strukturbericht 'A_a'
_aflow_Pearson 'tI2'

_symmetry_space_group_name_Hall "-I 4 2"
_symmetry_space_group_name_H-M "I 4/m m m"
_symmetry_Int_Tables_number 139

_cell_length_a      3.93200
_cell_length_b      3.93200
_cell_length_c      3.23800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 -y,-x,-z
6 -y,x,z
7 y,-x,z
8 y,x,-z
9 -x,-y,-z
10 -x,y,z
11 x,-y,z
12 x,y,-z
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y+1/2,-z+1/2
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z+1/2
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z+1/2
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y+1/2,z+1/2
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z+1/2
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pa1 Pa    2 a 0.00000 0.00000 0.00000 1.00000
```

α-Pa (A_a): A_tI2_139_a - POSCAR

```
A_tI2_139_a & a,c/a --params=3.932,0.823499491353 & I4/mmm      D_{4h}^{
    ↪ 17} #139 (a) & tI2 & A_a & Pa & alpha & W. H. Zachariasen, Acta
    ↪  Cryst. 12, 698-700 (1959)
   1.0000000000000000
 -1.966000000000   1.966000000000   1.619000000000
  1.966000000000  -1.966000000000   1.619000000000
  1.966000000000   1.966000000000  -1.619000000000
   Pa
    1
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Pa    (2a)
```

Khatyrkite (Al_2Cu, C16): A2B_tI12_140_h_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Khatyrkite'
_chemical_formula_sum 'Al2 Cu'

loop_
_publ_author_name
 'James B. Friauf'
_journal_name_full
;
Journal of the American Chemical Society
;
_journal_volume 49
_journal_year 1927
_journal_page_first 3107
_journal_page_last 3114
_publ_Section_title
;
 The Crystal Structures of Two Intermetallic Compounds
;

_aflow_proto 'A2B_tI12_140_h_a'
_aflow_params 'a,c/a,x2'
_aflow_params_values '6.04,0.804635761589,0.158'
_aflow_Strukturbericht 'C16'
_aflow_Pearson 'tI12'

_symmetry_space_group_name_Hall "-I 4 2c"
_symmetry_space_group_name_H-M "I 4/m c m"
_symmetry_Int_Tables_number 140

_cell_length_a      6.04000
_cell_length_b      6.04000
_cell_length_c      4.86000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x,y,-z+1/2
4 -x,-y,z
5 -y,-x,-z+1/2
6 -y,x,z
7 y,-x,z
8 y,x,-z+1/2
9 -x,-y,-z
10 -x,y,z+1/2
11 x,-y,z+1/2
12 x,y,-z
13 y,x,z+1/2
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z+1/2
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z
19 -x+1/2,y+1/2,-z
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z
27 x+1/2,-y+1/2,z
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu    4 a 0.00000 0.00000 0.25000 1.00000
Al1 Al    8 h 0.15800 0.65800 0.00000 1.00000
```

Khatyrkite (Al_2Cu, C16): A2B_tI12_140_h_a - POSCAR

```
A2B_tI12_140_h_a & a,c/a,x2 --params=6.04,0.804635761589,0.158 & I4/mcm
    ↪      D_{4h}^{18} #140 (ah) & tI12 & C16 & Al_2Cu & Khatyrkite &
    ↪ J. A. Friauf, J. Am. Chem. Soc. 49, 3107-3114 (1927)
   1.0000000000000000
  -3.02000000000000    3.02000000000000    2.42999999999878
   3.02000000000000   -3.02000000000000    2.42999999999878
   3.02000000000000    3.02000000000000   -2.42999999999878
   Al    Cu
    4     2
Direct
   0.65800000000000   0.15800000000000   0.81600000000000   Al    (8h)
   0.15800000000000   0.34200000000000   0.50000000000000   Al    (8h)
   0.84200000000000   0.65800000000000   0.50000000000000   Al    (8h)
   0.34200000000000   0.84200000000000   0.18400000000000   Al    (8h)
   0.75000000000000   0.75000000000000   0.00000000000000   Cu    (4a)
   0.25000000000000   0.25000000000000   0.00000000000000   Cu    (4a)
```

SiU_3 ($D0_c$): AB3_tI16_140_b_ah - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Uranium Silicide'
_chemical_formula_sum 'Si U3'

loop_
_publ_author_name
 'W. H. Zachariasen'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 2
_journal_year 1949
_journal_page_first 94
_journal_page_last 99
_publ_Section_title
```

```
;
 Crystal chemical studies of the 5f-series of elements. VIII. Crystal
      ↪ structure studies of uranium silicides and of CeSi$_2$,
      ↪ NpSi$_2$, and PuSi$_2$
;

_aflow_proto 'AB3_tI16_140_b_ah'
_aflow_params 'a,c/a,x3'
_aflow_params_values '6.017,1.44241316271,0.231'
_aflow_Strukturbericht 'D0_c'
_aflow_Pearson 'tI16'

_symmetry_space_group_name_Hall "-I 4 2c"
_symmetry_space_group_name_H-M "I 4/m c m"
_symmetry_Int_Tables_number 140

_cell_length_a     6.01700
_cell_length_b     6.01700
_cell_length_c     8.67900
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x,y,-z+1/2
4 -x,-y,z
5 -y,-x,-z+1/2
6 -y,x,z
7 y,-x,z
8 y,x,-z+1/2
9 -x,-y,-z
10 -x,y,z+1/2
11 x,-y,z+1/2
12 x,y,-z
13 y,x,z+1/2
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z+1/2
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z
19 -x+1/2,y+1/2,-z
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z
27 x+1/2,-y+1/2,z
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
U1  U   4 a 0.00000 0.00000 0.25000 1.00000
Si1 Si  4 b 0.00000 0.50000 0.25000 1.00000
U2  U   8 h 0.23100 0.73100 0.00000 1.00000
```

SiU_3 ($D0_c$): AB3_tI16_140_b_ah - POSCAR

```
AB3_tI16_140_b_ah & a,c/a,x3 --params=6.017,1.44241316271,0.231 & I4/mcm
      ↪ D_{4h}^{18} #140 (abh) & tI16 & D0_c & SiU3 & & W. H.
      ↪ Zachariasen, Acta Cryst. 2, 94-99 (1949)
   1.0000000000000000
  -3.00850000000000   3.00850000000000   4.33950000000000
   3.00850000000000  -3.00850000000000   4.33950000000000
   3.00850000000000   3.00850000000000  -4.33950000000000
   Si   U
    2   6
Direct
   0.25000000000000   0.75000000000000   0.50000000000000   Si   (4b)
   0.75000000000000   0.25000000000000   0.50000000000000   Si   (4b)
   0.25000000000000   0.25000000000000   0.00000000000000   U    (4a)
   0.75000000000000   0.75000000000000   0.00000000000000   U    (4a)
   0.23100000000000   0.26900000000000   0.50000000000000   U    (8h)
   0.26900000000000   0.76900000000000   0.03800000000000   U    (8h)
   0.73100000000000   0.23100000000000  -0.03800000000000   U    (8h)
   0.76900000000000   0.73100000000000   0.50000000000000   U    (8h)
```

SeTl (B37): AB_tI16_140_ab_h - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'I4/mcm'
_chemical_formula_sum 'Se Tl'

loop_
_publ_author_name
 'R.R. Yadav'
 'R. P. Ram'
 'S Bhan'
_journal_name_full
;
Zeitschrift f\"{u}r Metallkunde
;
_journal_volume 67
_journal_year 1976
_journal_page_first 173
_journal_page_last 177
_publ_Section_title
;
 On the Thallium-Selenium-Tellurium System
;

# Found in http://materials.springer.com/isp/crystallographic/docs/
      ↪ sd_0261726

_aflow_proto 'AB_tI16_140_ab_h'
_aflow_params 'a,c/a,x3'
_aflow_params_values '8.03,0.87297633873,0.179'
_aflow_Strukturbericht 'B37'
_aflow_Pearson 'tI16'

_symmetry_space_group_name_Hall "-I 4 2c"
_symmetry_space_group_name_H-M "I 4/m c m"
_symmetry_Int_Tables_number 140

_cell_length_a     8.03000
_cell_length_b     8.03000
_cell_length_c     7.01000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x,y,-z+1/2
4 -x,-y,z
5 -y,-x,-z+1/2
6 -y,x,z
7 y,-x,z
8 y,x,-z+1/2
9 -x,-y,-z
10 -x,y,z+1/2
11 x,-y,z+1/2
12 x,y,-z
13 y,x,z+1/2
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z+1/2
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z
19 -x+1/2,y+1/2,-z
20 -x+1/2,-y+1/2,z+1/2
21 -y+1/2,-x+1/2,-z
22 -y+1/2,x+1/2,z+1/2
23 y+1/2,-x+1/2,z+1/2
24 y+1/2,x+1/2,-z
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z
27 x+1/2,-y+1/2,z
28 x+1/2,y+1/2,-z+1/2
29 y+1/2,x+1/2,z
30 y+1/2,-x+1/2,-z+1/2
31 -y+1/2,x+1/2,-z+1/2
32 -y+1/2,-x+1/2,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Se1 Se  4 a 0.00000 0.00000 0.25000 1.00000
Se2 Se  4 b 0.00000 0.50000 0.25000 1.00000
Tl1 Tl  8 h 0.17900 0.67900 0.00000 1.00000
```

SeTl (B37): AB_tI16_140_ab_h - POSCAR

```
AB_tI16_140_ab_h & a,c/a,x3 --params=8.03,0.87297633873,0.179 & I4/mcm
      ↪ D_{4h}^{18} #140 (abh) & tI16 & B37 & SeTl & & R.R. Yadav,
      ↪ R.P. Ram and S Bhan, Z. Metallkd. 67, 173-177 (1976)
   1.0000000000000000
  -4.01500000000000   4.01500000000000   3.50500000000095
   4.01500000000000  -4.01500000000000   3.50500000000095
   4.01500000000000   4.01500000000000  -3.50500000000095
   Se   Tl
    4    4
Direct
   0.75000000000000   0.75000000000000   0.00000000000000   Se   (4a)
   0.25000000000000   0.25000000000000   0.00000000000000   Se   (4a)
   0.25000000000000   0.75000000000000   0.50000000000000   Se   (4b)
   0.75000000000000   0.25000000000000   0.50000000000000   Se   (4b)
   0.67900000000000   0.17900000000000   0.85800000000000   Tl   (8h)
   0.17900000000000   0.32100000000000   0.50000000000000   Tl   (8h)
   0.82100000000000   0.67900000000000   0.50000000000000   Tl   (8h)
   0.32100000000000   0.82100000000000   0.14200000000000   Tl   (8h)
```

Zircon ($ZrSiO_4$): A4BC_tI24_141_h_b_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Zircon'
_chemical_formula_sum 'Zr Si O4'

loop_
_publ_author_name
 'Robert M. Hazen'
 'Larry W. Finger'
_journal_name_full
;
American Mineralogist
;
_journal_volume 64
_journal_year 1979
_journal_page_first 196
_journal_page_last 201
_publ_Section_title
;
 Crystal structure and compressibility of zircon at high pressure
;

# Found in AMS Database

_aflow_proto 'A4BC_tI24_141_h_b_a'
_aflow_params 'a,c/a,y3,z3'
_aflow_params_values '6.6042,0.905423821205,0.066,0.1951'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI24'

_symmetry_space_group_name_Hall "-I 4bd 2"
_symmetry_space_group_name_H-M "I 41/a m d:2"
_symmetry_Int_Tables_number 141

_cell_length_a      6.60420
_cell_length_b      6.60420
_cell_length_c      5.97960
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y+1/2,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+3/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+3/4
9 -x,-y,-z
10 -x,y,z
11 x,-y+1/2,z
12 x,y+1/2,-z
13 y+3/4,x+3/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+1/4,-x+3/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
21 -y+3/4,-x+3/4,-z+1/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+1/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y,-z+1/2
29 y+1/4,x+1/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+3/4,-x+1/4,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Zr1 Zr   4 a 0.00000 0.75000 0.12500 1.00000
Si1 Si   4 b 0.00000 0.25000 0.37500 1.00000
O1  O   16 h 0.00000 0.06600 0.19510 1.00000
```

Zircon ($ZrSiO_4$): A4BC_tI24_141_h_b_a - POSCAR

```
A4BC_tI24_141_h_b_a & a,c/a,y3,z3 --params=6.6042,0.905423821205,0.066,
    ↪ 0.1951 & I4_1/amd D_{4h}^{19} #141 (abh) & tI24 & & ZrSiO4 &
    ↪ Zircon & R. M. Hazen and L. W. Finger, Am. Mineral. 64, 196-201
    ↪ (1979)
  1.0000000000000000
 -3.30210000000000   3.30210000000000   2.98980000000000
  3.30210000000000  -3.30210000000000   2.98980000000000
  3.30210000000000   3.30210000000000  -2.98980000000000
   O   Si   Zr
   8    2    2
Direct
  0.19510000000000   0.26110000000000   0.56600000000000   O   (16h)
  0.19510000000000   0.62910000000000  -0.06600000000000   O   (16h)
  0.26110000000000   0.19510000000000   0.06600000000000   O   (16h)
  0.37090000000000   0.80490000000000   0.56600000000000   O   (16h)
  0.62910000000000   0.19510000000000   0.43400000000000   O   (16h)
  0.73890000000000   0.80490000000000  -0.06600000000000   O   (16h)
  0.80490000000000   0.37090000000000   0.06600000000000   O   (16h)
  0.80490000000000   0.73890000000000   0.43400000000000   O   (16h)
  0.37500000000000   0.62500000000000   0.75000000000000  Si   (4b)
  0.62500000000000   0.37500000000000   0.25000000000000  Si   (4b)
  0.12500000000000   0.87500000000000   0.25000000000000  Zr   (4a)
  0.87500000000000   0.12500000000000   0.75000000000000  Zr   (4a)
```

β-Sn (A5): A_tI4_141_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Sn'
_chemical_formula_sum 'Sn'

loop_
_publ_author_name
 'V. T. Deshpande'
 'D. B. Sirdeshmukh'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 14
_journal_year 1961
_journal_page_first 355
_journal_page_last 356
_publ_Section_title
;
 Thermal Expansion of Tetragonal Tin
;

# Found in https://www.webelements.com/tin/crystal_structure.html

_aflow_proto 'A_tI4_141_a'
_aflow_params 'a,c/a'
_aflow_params_values '5.8318,0.545611989437'
_aflow_Strukturbericht 'A5'
_aflow_Pearson 'tI4'

_symmetry_space_group_name_Hall "-I 4bd 2"
_symmetry_space_group_name_H-M "I 41/a m d:2"
_symmetry_Int_Tables_number 141

_cell_length_a      5.83180
_cell_length_b      5.83180
_cell_length_c      3.18190
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y+1/2,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+3/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+3/4
9 -x,-y,-z
10 -x,y,z
11 x,-y+1/2,z
12 x,y+1/2,-z
13 y+3/4,x+3/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+1/4,-x+3/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
21 -y+3/4,-x+3/4,-z+1/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+1/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y,-z+1/2
29 y+1/4,x+1/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+3/4,-x+1/4,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
```

```
_atom_site_fract_z
_atom_site_occupancy
Sn1 Sn    4 a 0.00000 0.75000 0.12500 1.00000
```

β-Sn (A5): A_tI4_141_a - POSCAR

```
A_tI4_141_a & a,c/a --params=5.8318,0.545611989437 & I4_1/amd  D_{4h}^{
    ↪ 19} #141 (a) & tI4 & A5 & Sn & beta & V. T. Deshpande and D. B.
    ↪ Sirdeshmukh, Acta Cryst. 14, 355-356 (1961)
   1.0000000000000000
  -2.91590000000000    2.91590000000000    1.59095000000000
   2.91590000000000   -2.91590000000000    1.59095000000000
   2.91590000000000    2.91590000000000   -1.59095000000000
   Sn
    2
Direct
   0.12500000000000    0.87500000000000    0.25000000000000    Sn    (4a)
   0.87500000000000    0.12500000000000    0.75000000000000    Sn    (4a)
```

Hausmannite (Mn_3O_4): A3B4_tI28_141_ad_h - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Hausmannite'
_chemical_formula_sum 'Mn3 O4'

loop_
_publ_author_name
 'D. Jarosch'
_journal_name_full
;
Mineralogy and Petrology
;
_journal_volume 37
_journal_year 1987
_journal_page_first 15
_journal_page_last 23
_publ_Section_title
;
 Crystal structure refinement and reflectance measurements of
    ↪ hausmannite, Mn$_3$O$_4$
;

# Found in  Pearson IV, pp. 4347

_aflow_proto 'A3B4_tI28_141_ad_h'
_aflow_params 'a,c/a,y3,z3'
_aflow_params_values '5.765,1.63781439722,0.0278,0.2589'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI28'

_symmetry_space_group_name_Hall "-I 4bd 2"
_symmetry_space_group_name_H-M "I 41/a m d:2"
_symmetry_Int_Tables_number 141

_cell_length_a    5.76500
_cell_length_b    5.76500
_cell_length_c    9.44200
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y+1/2,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+3/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+3/4
9 -x,-y,-z
10 -x,y,z
11 x,-y+1/2,z
12 x,y+1/2,-z
13 y+3/4,x+3/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+1/4,-x+3/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
21 -y+3/4,-x+3/4,-z+1/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+1/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y,-z+1/2
29 y+1/4,x+1/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+3/4,-x+1/4,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mn1 Mn    4 a 0.00000 0.75000 0.12500 1.00000
Mn2 Mn    8 d 0.00000 0.00000 0.50000 1.00000
O1  O    16 h 0.00000 0.02780 0.25890 1.00000
```

Hausmannite (Mn_3O_4): A3B4_tI28_141_ad_h - POSCAR

```
A3B4_tI28_141_ad_h & a,c/a,y3,z3 --params=5.765,1.63781439722,0.0278,
    ↪ 0.2589 & I4_1/amd          D_{4h}^{19} #141 (adh) & tI28 &
    ↪ Mn3O4 & Hausmannite & D. Jorosch, Mineral. Petrol. 37, 15-23 (
    ↪ 1987)
   1.0000000000000000
  -2.88250000000000    2.88250000000000    4.72100000000000
   2.88250000000000   -2.88250000000000    4.72100000000000
   2.88250000000000    2.88250000000000   -4.72100000000000
  Mn1  Mn2   O
   2    4    8
Direct
   0.12500000000000   -0.12500000000000    0.25000000000000    Mn    (4a)
  -0.12500000000000    0.12500000000000   -0.25000000000000    Mn    (4a)
   0.00000000000000    0.50000000000000    0.50000000000000    Mn    (8d)
   0.50000000000000    0.00000000000000   -0.00000000000000    Mn    (8d)
   0.50000000000000    0.50000000000000   -0.00000000000000    Mn    (8d)
   0.50000000000000    0.50000000000000    0.50000000000000    Mn    (8d)
   0.25890000000000   -0.26890000000000   -0.02780000000000    O    (16h)
  -0.25890000000000    0.26890000000000    0.02780000000000    O    (16h)
   0.25890000000000    0.28670000000000   -0.47220000000000    O    (16h)
  -0.25890000000000   -0.28670000000000    0.47220000000000    O    (16h)
   0.26890000000000   -0.25890000000000   -0.47220000000000    O    (16h)
  -0.26890000000000    0.25890000000000    0.47220000000000    O    (16h)
   0.28670000000000    0.25890000000000    0.02780000000000    O    (16h)
  -0.28670000000000   -0.25890000000000   -0.02780000000000    O    (16h)
```

Anatase (TiO_2, C5): A2B_tI12_141_e_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Anatase'
_chemical_formula_sum 'Ti O2'

loop_
_publ_author_name
 'C. J. Howard'
 'T. M. Sabine'
 'Fiona Dickson'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 47
_journal_year 1991
_journal_page_first 462
_journal_page_last 468
_publ_Section_title
;
 Structural and thermal parameters for rutile and anatase
;

_aflow_proto 'A2B_tI12_141_e_a'
_aflow_params 'a,c/a,z2'
_aflow_params_values '3.785,2.51360634082,0.20806'
_aflow_Strukturbericht 'C5'
_aflow_Pearson 'tI12'

_symmetry_space_group_name_Hall "-I 4bd 2"
_symmetry_space_group_name_H-M "I 41/a m d:2"
_symmetry_Int_Tables_number 141

_cell_length_a    3.78500
_cell_length_b    3.78500
_cell_length_c    9.51400
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y+1/2,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+3/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+3/4
9 -x,-y,-z
10 -x,y,z
11 x,-y+1/2,z
12 x,y+1/2,-z
13 y+3/4,x+3/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+1/4,-x+3/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
```

```
21 -y+3/4,-x+3/4,-z+1/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+1/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y,-z+1/2
29 y+1/4,x+1/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+3/4,-x+1/4,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1 Ti    4 a 0.00000 0.75000 0.12500 1.00000
O1  O     8 e 0.00000 0.25000 0.20806 1.00000
```

Anatase (TiO_2, C5): A2B_tI12_141_e_a - POSCAR

```
A2B_tI12_141_e_a & a,c/a,z2 --params=3.785,2.51360634082,0.20806 & I4_1/
    ↪ amd D_{4h}^{19} #141 (ae) & tI12 & C5 & TiO2 & Anatase &
    ↪ Howard et al., Acta Cryst. B 47, 462-468 (1991)
   1.0000000000000000
  -1.89250000000000   1.89250000000000   4.75700000000000
   1.89250000000000  -1.89250000000000   4.75700000000000
   1.89250000000000   1.89250000000000  -4.75700000000000
    O    Ti
    4    2
Direct
   0.20806000000000   0.45806000000000   0.75000000000000   O   (8e)
   0.45806000000000   0.20806000000000   0.25000000000000   O   (8e)
   0.54194000000000   0.79194000000000   0.75000000000000   O   (8e)
   0.79194000000000   0.54194000000000   0.25000000000000   O   (8e)
   0.12500000000000   0.87500000000000   0.25000000000000  Ti   (4a)
   0.87500000000000   0.12500000000000   0.75000000000000  Ti   (4a)
```

MoB (B_g): AB_tI16_141_e_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'delta Molybdenum Boride'
_chemical_formula_sum 'Mo B'

loop_
_publ_author_name
 'Roland Kiessling'
_journal_name_full
;
Acta Chemica Scandinavica
;
_journal_volume 1
_journal_year 1947
_journal_page_first 893
_journal_page_last 916
_publ_Section_title
;
 The Crystal Structure of Molybdenum and Tungsten Borides
;

_aflow_proto 'AB_tI16_141_e_e'
_aflow_params 'a,c/a,z1,z2'
_aflow_params_values '3.108,5.45045045045,0.227,0.071'
_aflow_Strukturbericht 'B_g'
_aflow_Pearson 'tI16'

_symmetry_space_group_name_Hall "-I 4bd 2"
_symmetry_space_group_name_H-M "I 41/a m d:2"
_symmetry_Int_Tables_number 141

_cell_length_a      3.10800
_cell_length_b      3.10800
_cell_length_c      16.94000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y+1/2,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+3/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+3/4
9 -x,-y,-z
10 -x,y,z
11 x,-y+1/2,z
12 x,y+1/2,-z
13 y+3/4,x+3/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+1/4,-x+3/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
21 -y+3/4,-x+3/4,-z+1/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+1/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y,-z+1/2
29 y+1/4,x+1/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+3/4,-x+1/4,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1  B     8 e 0.00000 0.25000 0.22700 1.00000
Mo1 Mo    8 e 0.00000 0.25000 0.07100 1.00000
```

MoB (B_g): AB_tI16_141_e_e - POSCAR

```
AB_tI16_141_e_e & a,c/a,z1,z2 --params=3.108,5.45045045045,0.227,0.071 &
    ↪ I4_1/amd D_{4h}^{19} #141 (e^2) & tI16 & B_g & MoB & & Roland
    ↪ Kiessling, Acta Chem. Scand. 1, 893-916 (1947)
   1.0000000000000000
  -1.55400000000000   1.55400000000000   8.47000000000000
   1.55400000000000  -1.55400000000000   8.47000000000000
   1.55400000000000   1.55400000000000  -8.47000000000000
    B    Mo
    4    4
Direct
   0.47700000000000   0.22700000000000   0.25000000000000   B   (8e)
   0.52300000000000   0.77300000000000   0.75000000000000   B   (8e)
   0.77300000000000   0.52300000000000   0.25000000000000   B   (8e)
   0.22700000000000   0.47700000000000   0.75000000000000   B   (8e)
   0.67900000000000  -0.07100000000000   0.75000000000000  Mo   (8e)
   0.92900000000000   0.67900000000000   0.25000000000000  Mo   (8e)
   0.07100000000000   0.32100000000000   0.75000000000000  Mo   (8e)
   0.32100000000000   0.07100000000000   0.25000000000000  Mo   (8e)
```

Ga_2Hf: A2B_tI24_141_2e_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ga2 Hf'

loop_
_publ_author_name
 'K. Schubert',
 'H. G. Meissner',
 'M. P{\"o}tzschke'
 'W. Rossteutscher'
 'E. Stolz'
_journal_name_full
;
Naturwissenschaften
;
_journal_volume 49
_journal_year 1962
_journal_page_first 57
_journal_page_last 57
_publ_Section_title
;
 Einige Strukturdaten metallischer Phasen (7)
;

# Found in  Pearson, Vol. III, pp. 3436

_aflow_proto 'A2B_tI24_141_2e_e'
_aflow_params 'a,c/a,z1,z2,z3'
_aflow_params_values '4.046,6.28917449333,0.125,0.289,-0.051'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI24'

_symmetry_space_group_name_Hall "-I 4bd 2"
_symmetry_space_group_name_H-M "I 41/a m d:2"
_symmetry_Int_Tables_number 141

_cell_length_a      4.04600
_cell_length_b      4.04600
_cell_length_c      25.44600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
```

```
3 -x,y+1/2,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+3/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+3/4
9 -x,-y,-z
10 -x,y,z
11 x,-y+1/2,z
12 x,y+1/2,-z
13 y+3/4,x+3/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+1/4,-x+3/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
21 -y+3/4,-x+3/4,-z+1/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+1/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y,-z+1/2
29 y+1/4,x+1/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+3/4,-x+1/4,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ga1 Ga    8 e 0.00000 0.25000 0.12500   1.00000
Ga2 Ga    8 e 0.00000 0.25000 0.28900   1.00000
Hf1 Hf    8 e 0.00000 0.25000 -0.05100   1.00000
```

Ga_2Hf: A2B_tI24_141_2e_e - POSCAR

```
A2B_tI24_141_2e_e & a,c/a,z1,z2,z3 --params=4.046,6.28917449333,0.125,
    ↪ 0.289,-0.051 & I4_1/amd  D_{4h}^{19} #141 (e^3) & tI24 & &
    ↪ Ga2Hf & & K. Schubert et al., Naturwissenschaften 49, 57 (1962)
   1.0000000000000000
  -2.02300000000000    2.02300000000000   12.72300000000000
   2.02300000000000   -2.02300000000000   12.72300000000000
   2.02300000000000    2.02300000000000  -12.72300000000000
   Ga    Hf
    8     4
Direct
   0.37500000000000   0.12500000000000   0.25000000000000   Ga    (8e)
   0.12500000000000   0.37500000000000   0.75000000000000   Ga    (8e)
   0.62500000000000   0.87500000000000   0.75000000000000   Ga    (8e)
   0.87500000000000   0.62500000000000   0.25000000000000   Ga    (8e)
   0.53900000000000   0.28900000000000   0.25000000000000   Ga    (8e)
   0.28900000000000   0.53900000000000   0.75000000000000   Ga    (8e)
   0.46100000000000   0.71100000000000   0.75000000000000   Ga    (8e)
   0.71100000000000   0.46100000000000   0.25000000000000   Ga    (8e)
   0.19900000000000  -0.05100000000000   0.25000000000000   Hf    (8e)
  -0.05100000000000   0.19900000000000   0.75000000000000   Hf    (8e)
   0.80100000000000   0.05100000000000   0.75000000000000   Hf    (8e)
   0.05100000000000   0.80100000000000   0.25000000000000   Hf    (8e)
```

NbP ("40"): AB_tI8_141_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha Niobium phosphide'
_chemical_formula_sum 'Nb P'

loop_
_publ_author_name
 'N. Sch\"{o}nberg'
_journal_name_full
;
Acta Chemica Scandinavica
;
_journal_volume 8
_journal_year 1954
_journal_page_first 226
_journal_page_last 239
_publ_Section_title
;
 An X-Ray Investigation of Transition Metal Phosphides
;

# Found in  Pearson's Handbook, Vol. IV, pp. 4511

_aflow_proto 'AB_tI8_141_a_b'
_aflow_params 'a,c/a'
_aflow_params_values '3.325,3.42255639098'
_aflow_Strukturbericht '"40"'
_aflow_Pearson 'tI8'

_symmetry_space_group_name_Hall "-I 4bd 2"
_symmetry_space_group_name_H-M "I 41/a m d:2"
_symmetry_Int_Tables_number 141

_cell_length_a     3.32500
_cell_length_b     3.32500
_cell_length_c     11.38000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y+1/2,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+3/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+3/4
9 -x,-y,-z
10 -x,y,z
11 x,-y+1/2,z
12 x,y+1/2,-z
13 y+3/4,x+3/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+1/4,-x+3/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
21 -y+3/4,-x+3/4,-z+1/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+1/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y,-z+1/2
29 y+1/4,x+1/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+3/4,-x+1/4,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Nb1 Nb    4 a 0.00000 0.75000 0.12500 1.00000
P1  P     4 b 0.00000 0.25000 0.37500 1.00000
```

NbP ("40"): AB_tI8_141_a_b - POSCAR

```
AB_tI8_141_a_b & a,c/a --params=3.325,3.42255639098 & I4_1/amd  D_{4h}^{
    ↪ 19} #141 (ab) & tI8 & "40" & NbP & alpha & N. Sch\"{o}nberg,
    ↪ Acta Chem. Scand. 8, 226-239 (1954)
   1.0000000000000000
  -1.66250000000000   1.66250000000000   5.69000000000425
   1.66250000000000  -1.66250000000000   5.69000000000425
   1.66250000000000   1.66250000000000  -5.69000000000425
   Nb    P
    2    2
Direct
   0.12500000000000   0.87500000000000   0.25000000000000   Nb    (4a)
   0.87500000000000   0.12500000000000   0.75000000000000   Nb    (4a)
   0.37500000000000   0.62500000000000   0.75000000000000    P    (4b)
   0.62500000000000   0.37500000000000   0.25000000000000    P    (4b)
```

β-In_2S_3: A2B3_tI80_141_ceh_3h - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta indium sulfide'
_chemical_formula_sum 'In2 S3'

loop_
_publ_author_name
 'Niyum S Rampersadh'
 'Andrew M Venter'
 'David G Billing'
_journal_name_full
;
Physica B
;
_journal_volume 350
_journal_year 2004
_journal_page_first e383
_journal_page_last e385
_publ_Section_title
;
 Rietveld refinement of In$_2$S$_3$ using neutron and X-ray powder
    ↪ diffraction data
;

_aflow_proto 'A2B3_tI80_141_ceh_3h'
_aflow_params 'a,c/a,z2,y3,z3,y4,z4,y5,z5,y6,z6'
```

```
_aflow_params_values '7.5937,4.26037373086,0.2044,0.5201,0.3324,0.516,
    ↪ 0.2547,0.494,0.0859,0.4667,0.4164'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI80'

_symmetry_space_group_name_Hall "-I 4bd 2"
_symmetry_space_group_name_H-M "I 41/a m d:2"
_symmetry_Int_Tables_number 141

_cell_length_a      7.59370
_cell_length_b      7.59370
_cell_length_c      32.35200
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y+1/2,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+3/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+3/4
9 -x,-y,-z
10 -x,y,z
11 x,-y+1/2,z
12 x,y+1/2,-z
13 y+3/4,x+3/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+1/4,-x+3/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x+1/2,-y+1/2,-z+1/2
19 -x+1/2,y,-z+1/2
20 -x+1/2,-y,z+1/2
21 -y+3/4,-x+3/4,-z+1/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+1/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y,-z+1/2
29 y+1/4,x+1/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+3/4,-x+1/4,z+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
In1 In   8 c 0.00000 0.00000 0.00000 1.00000
In2 In   8 e 0.00000 0.25000 0.20440 1.00000
In3 In  16 h 0.00000 0.52010 0.33240 1.00000
S1  S   16 h 0.00000 0.51600 0.25470 1.00000
S2  S   16 h 0.00000 0.49400 0.08590 1.00000
S3  S   16 h 0.00000 0.46670 0.41640 1.00000
```

β-In_2S_3: A2B3_tI80_141_ceh_3h - POSCAR

```
A2B3_tI80_141_ceh_3h & a,c/a,z2,y3,z3,y4,z4,y5,z5,y6,z6 --params=7.5937,
    ↪ 4.26037373086,0.2044,0.5201,0.3324,0.516,0.2547,0.494,0.0859,
    ↪ 0.4667,0.4164 & I4_1/amd D_{4h}^{19} #141 (ceh^4) & tI80 & &
    ↪ In2S3 & beta & Niyum S Rampersadh and Andrew M Venter and David
    ↪ G Billing, Physica B 350, e383-e385 (2004)
   1.0000000000000000
  -3.79685000000000   3.79685000000000  16.17600000000000
   3.79685000000000  -3.79685000000000  16.17600000000000
   3.79685000000000   3.79685000000000 -16.17600000000000
   In    S
   16   24
Direct
   0.14750000000000   0.66760000000000   0.47990000000000   In   (16h)
   0.31230000000000   0.33240000000000  -0.02010000000000   In   (16h)
   0.33240000000000   0.31230000000000   0.47990000000000   In   (16h)
   0.33240000000000   0.85250000000000   0.02010000000000   In   (16h)
   0.66760000000000   0.14750000000000  -0.02010000000000   In   (16h)
   0.66760000000000   0.68770000000000   0.52010000000000   In   (16h)
   0.68770000000000   0.66760000000000   0.02010000000000   In   (16h)
   0.85250000000000   0.33240000000000   0.52010000000000   In   (16h)
   0.00000000000000   0.00000000000000   0.00000000000000   In    (8c)
   0.00000000000000   0.00000000000000   0.50000000000000   In    (8c)
   0.00000000000000   0.50000000000000   0.00000000000000   In    (8c)
   0.50000000000000   0.00000000000000   0.50000000000000   In    (8c)
   0.20440000000000   0.45440000000000   0.75000000000000   In    (8e)
   0.45440000000000   0.20440000000000   0.25000000000000   In    (8e)
   0.54560000000000   0.79560000000000   0.75000000000000   In    (8e)
   0.79560000000000   0.54560000000000   0.25000000000000   In    (8e)
   0.22930000000000   0.74530000000000   0.48400000000000   S   (16h)
   0.23870000000000   0.25470000000000  -0.01600000000000   S   (16h)
   0.25470000000000   0.23870000000000   0.48400000000000   S   (16h)
   0.25470000000000   0.77070000000000   0.01600000000000   S   (16h)
   0.74530000000000   0.22930000000000  -0.01600000000000   S   (16h)
   0.74530000000000   0.76130000000000   0.51600000000000   S   (16h)
   0.76130000000000   0.74530000000000   0.01600000000000   S   (16h)
   0.77070000000000   0.25470000000000   0.51600000000000   S   (16h)
  -0.08590000000000  -0.09190000000000   0.49400000000000   S   (16h)
   0.08590000000000   0.09190000000000   0.50600000000000   S   (16h)
  -0.08590000000000   0.42010000000000   0.00600000000000   S   (16h)
   0.08590000000000   0.57990000000000  -0.00600000000000   S   (16h)
   0.09190000000000   0.08590000000000   0.00600000000000   S   (16h)
  -0.09190000000000  -0.08590000000000  -0.00600000000000   S   (16h)
   0.42010000000000  -0.08590000000000   0.50600000000000   S   (16h)
   0.57990000000000   0.08590000000000   0.49400000000000   S   (16h)
   0.11690000000000   0.58360000000000   0.53330000000000   S   (16h)
   0.41640000000000   0.44970000000000   0.53330000000000   S   (16h)
   0.41640000000000   0.88310000000000  -0.03330000000000   S   (16h)
   0.44970000000000   0.41640000000000   0.03330000000000   S   (16h)
   0.55030000000000   0.58360000000000  -0.03330000000000   S   (16h)
   0.58360000000000   0.11690000000000   0.03330000000000   S   (16h)
   0.58360000000000   0.55030000000000   0.46670000000000   S   (16h)
   0.88310000000000   0.41640000000000   0.46670000000000   S   (16h)
```

$PPrS_4$: ABC4_tI96_142_e_ab_2g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'P Pr S4'

loop_
_publ_author_name
 'C. Wibbelmann'
 'W. Brockner'
 'B. Eisenmann'
 'H. Sch\"{a}fer'
_journal_name_full
;
Zeitschrift f\"{u}r Naturforschung
;
_journal_volume 39a
_journal_year 1983
_journal_page_first 190
_journal_page_last 194
_publ_Section_title
;
 Kristallstruktur und Schwingungsspektrum des
    ↪ Praseodym-ortho-Thiophosphates PrPS$_4$
;

# Found in http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_1703369

_aflow_proto 'ABC4_tI96_142_e_ab_2g'
_aflow_params 'a,c/a,x3,x4,y4,z4,x5,y5,z5'
_aflow_params_values '10.914,1.77396005131,0.0375,0.2482,0.3197,-0.0867,
    ↪ 0.0923,0.1117,0.0025'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'tI96'

_symmetry_space_group_name_Hall "-I 4bd 2c"
_symmetry_space_group_name_H-M "I 41/a c d:2"
_symmetry_Int_Tables_number 142

_cell_length_a      10.91400
_cell_length_b      10.91400
_cell_length_c      19.36100
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x+1/2,y,-z
4 -x,-y+1/2,z
5 -y+1/4,-x+1/4,-z+1/4
6 -y+1/4,x+3/4,z+1/4
7 y+3/4,-x+3/4,z+1/4
8 y+3/4,x+1/4,-z+1/4
9 -x,-y,-z
10 -x,y,z+1/2
11 x,-y+1/2,z+1/2
12 x,y+1/2,-z
13 y+1/4,x+1/4,z+1/4
14 y+3/4,-x+1/4,-z+3/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+3/4,-x+1/4,z+1/4
17 x+1/2,y+1/2,z+1/2
18 x,-y,-z+1/2
19 -x,y+1/2,-z+1/2
20 -x+1/2,-y,z+1/2
21 -y+3/4,-x+3/4,-z+3/4
22 -y+3/4,x+1/4,z+3/4
23 y+1/4,-x+1/4,z+3/4
24 y+1/4,x+3/4,-z+3/4
25 -x+1/2,-y+1/2,-z+1/2
26 -x+1/2,y+1/2,z
27 x+1/2,-y,z
28 x+1/2,y,-z+1/2
29 y+3/4,x+3/4,z+3/4
30 y+1/4,-x+3/4,-z+1/4
31 -y+3/4,x+3/4,-z+1/4
32 -y+1/4,-x+3/4,z+3/4
```

```
loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pr1  Pr    8  a  0.00000  0.25000   0.37500  1.00000
Pr2  Pr    8  b  0.00000  0.25000   0.12500  1.00000
P1   P    16  e  0.03750  0.00000   0.25000  1.00000
S1   S    32  g  0.24820  0.31970  -0.08670  1.00000
S2   S    32  g  0.09230  0.11170   0.00250  1.00000
```

$PPrS_4$: ABC4_tI96_142_e_ab_2g - POSCAR

```
ABC4_tI96_142_e_ab_2g & a,c/a,x3,x4,y4,z4,x5,y5,z5 --params=10.914,
    ↪ 1.77396005131,0.0375,0.2482,0.3197,-0.0867,0.0923,0.1117,0.0025
    ↪ & I4_1/acd D_{4h}^{20} #142 (abeg^2) & tI96 && PPrS4 && C.
    ↪ Wibbelmann and W. Brockner, Z. Naturforsch. 39a, 190-194 (1984)
  1.0000000000000000
 -5.45700000000000   5.45700000000000   9.68050000000000
  5.45700000000000  -5.45700000000000   9.68050000000000
  5.45700000000000   5.45700000000000  -9.68050000000000
   P   Pr   S
   8    8  32
Direct
  0.21250000000000   0.25000000000000   0.46250000000000   P   (16e)
  0.25000000000000   0.28750000000000   0.03750000000000   P   (16e)
  0.25000000000000   0.78750000000000   0.53750000000000   P   (16e)
  0.28750000000000   0.75000000000000   0.03750000000000   P   (16e)
  0.71250000000000   0.25000000000000  -0.03750000000000   P   (16e)
  0.75000000000000   0.21250000000000   0.46250000000000   P   (16e)
  0.75000000000000   0.71250000000000  -0.03750000000000   P   (16e)
  0.78750000000000   0.75000000000000   0.53750000000000   P   (16e)
  0.12500000000000   0.87500000000000   0.25000000000000  Pr    (8a)
  0.37500000000000   0.62500000000000   0.75000000000000  Pr    (8a)
  0.62500000000000   0.37500000000000   0.25000000000000  Pr    (8a)
  0.87500000000000   0.12500000000000   0.75000000000000  Pr    (8a)
  0.12500000000000   0.37500000000000   0.75000000000000  Pr    (8b)
  0.37500000000000   0.12500000000000   0.25000000000000  Pr    (8b)
  0.62500000000000   0.87500000000000   0.75000000000000  Pr    (8b)
  0.87500000000000   0.62500000000000   0.25000000000000  Pr    (8b)
 -0.09360000000000   0.33490000000000   0.06790000000000   S   (32g)
  0.09360000000000   0.66510000000000  -0.06790000000000   S   (32g)
  0.16150000000000   0.09360000000000  -0.07150000000000   S   (32g)
  0.16510000000000   0.59360000000000   0.43210000000000   S   (32g)
  0.23300000000000   0.16150000000000   0.56790000000000   S   (32g)
  0.26700000000000   0.83490000000000  -0.07150000000000   S   (32g)
  0.33490000000000   0.76700000000000   0.42850000000000   S   (32g)
  0.33850000000000   0.26700000000000  -0.06790000000000   S   (32g)
  0.40640000000000   0.33850000000000   0.57150000000000   S   (32g)
  0.59360000000000   0.66150000000000   0.42850000000000   S   (32g)
  0.66150000000000   0.73300000000000   0.06790000000000   S   (32g)
  0.66510000000000   0.23300000000000   0.57150000000000   S   (32g)
  0.73300000000000   0.16510000000000   0.07150000000000   S   (32g)
  0.76700000000000   0.83850000000000   0.43210000000000   S   (32g)
  0.83490000000000   0.40640000000000   0.56790000000000   S   (32g)
  0.83850000000000  -0.09360000000000   0.07150000000000   S   (32g)
 -0.08980000000000   0.11420000000000   0.51940000000000   S   (32g)
  0.08980000000000   0.88580000000000   0.48060000000000   S   (32g)
  0.09480000000000   0.39080000000000  -0.01940000000000   S   (32g)
 -0.09480000000000   0.60920000000000   0.01940000000000   S   (32g)
  0.10920000000000   0.40520000000000   0.51940000000000   S   (32g)
  0.11420000000000   0.09480000000000   0.20400000000000   S   (32g)
  0.38580000000000   0.58980000000000  -0.01940000000000   S   (32g)
  0.39080000000000  -0.08980000000000   0.29600000000000   S   (32g)
  0.40520000000000   0.38580000000000   0.29600000000000   S   (32g)
  0.41020000000000   0.89080000000000   0.79600000000000   S   (32g)
  0.58980000000000   0.10920000000000   0.20400000000000   S   (32g)
  0.59480000000000   0.61420000000000   0.70400000000000   S   (32g)
  0.60920000000000   0.08980000000000   0.70400000000000   S   (32g)
  0.61420000000000   0.41020000000000   0.01940000000000   S   (32g)
  0.88580000000000  -0.09480000000000   0.79600000000000   S   (32g)
  0.89080000000000   0.59480000000000   0.48060000000000   S   (32g)
```

ζ-AgZn (B_b): A2B_hP9_147_g_ad - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'zeta silver zinc'
_chemical_formula_sum 'Ag2 Zn'

loop_
_publ_author_name
 'Gunnar Bergman'
 'Robert W. Jaross'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 8
_journal_year 1955
_journal_page_first 232
_journal_page_last 235
_publ_Section_title
;
 On the Crystal Structure of the $\zeta$ Phase in the Silver-Zinc System
    ↪ and the Mechanism of the $\beta-\zeta$ Transformation
;
_aflow_proto 'A2B_hP9_147_g_ad'
_aflow_params 'a,c/a,z2,x3,y3,z3'
_aflow_params_values '7.636,0.369264012572,0.25,0.33333,0.0,0.25'
_aflow_Strukturbericht 'B_b'
_aflow_Pearson 'hP9'

_symmetry_space_group_name_Hall "-P 3"
_symmetry_space_group_name_H-M "P -3"
_symmetry_Int_Tables_number 147

_cell_length_a      7.63600
_cell_length_b      7.63600
_cell_length_c      2.81970
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 -x,-y,-z
5 y,-x+y,-z
6 x-y,x,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Zn1  Zn    1  a  0.00000  0.00000  0.00000  1.00000
Zn2  Zn    2  d  0.33333  0.66667  0.25000  1.00000
Ag1  Ag    6  g  0.33333  0.00000  0.25000  1.00000
```

ζ-AgZn (B_b): A2B_hP9_147_g_ad - POSCAR

```
A2B_hP9_147_g_ad & a,c/a,z2,x3,y3,z3 --params=7.636,0.369264012572,0.25,
    ↪ 0.33333,0.0,0.25 & P(-3)      C_{3i}^1 #147 (adg) & hP9 && B_b &
    ↪ Ag2Zn & zeta & G. Bergman and R. W. Jaross, Acta Cryst. 8,
    ↪ 232-235 (1955)
  1.0000000000000000
  3.81800000000000  -6.61296998329800   0.00000000000000
  3.81800000000000   6.61296998329800   0.00000000000000
  0.00000000000000   0.00000000000000   2.81970000000000
  Ag   Zn
   6    3
Direct
  0.00000000000000   0.33333333333333   0.25000000000000   Ag   (6g)
  0.00000000000000   0.66666666666667   0.75000000000000   Ag   (6g)
  0.33333333333333   0.00000000000000   0.25000000000000   Ag   (6g)
  0.33333333333333   0.33333333333333   0.75000000000000   Ag   (6g)
  0.66666666666667   0.00000000000000   0.75000000000000   Ag   (6g)
  0.66666666666667   0.66666666666667   0.25000000000000   Ag   (6g)
  0.00000000000000   0.00000000000000   0.00000000000000   Zn   (1a)
  0.33333333333333   0.66666666666667   0.25000000000000   Zn   (2d)
  0.66666666666667   0.33333333333333   0.75000000000000   Zn   (2d)
```

Solid Cubane (C_8H_8): AB_hR16_148_cf_cf - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Cubane'
_chemical_formula_sum 'C8 H8'

loop_
_publ_author_name
 'Everly B. Fleischer'
_journal_name_full
;
Journal of the American Chemical Society
;
_journal_volume 86
_journal_year 1964
_journal_page_first 3889
_journal_page_last 3890
_publ_Section_title
;
 X-Ray Structure Determination of Cubane
;

_aflow_proto 'AB_hR16_148_cf_cf'
_aflow_params 'a,c/a,x1,x2,x3,y3,z3,x4,y4,z4'
_aflow_params_values '6.29713,1.8633345667,0.11546,0.21,0.10706,0.81289,
    ↪ 0.19519,0.1848,0.6754,0.3468'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR16'

_symmetry_space_group_name_Hall "-R 3"
_symmetry_space_group_name_H-M "R -3:H"
_symmetry_Int_Tables_number 148

_cell_length_a      6.29713
_cell_length_b      6.29713
_cell_length_c      11.73366
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
```

```
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  -y,x-y,z
3  -x+y,-x,z
4  -x,-y,-z
5  y,-x+y,-z
6  x-y,x,-z
7  x+1/3,y+2/3,z+2/3
8  -y+1/3,x-y+2/3,z+2/3
9  -x+y+1/3,-x+2/3,z+2/3
10  -x+1/3,-y+2/3,-z+2/3
11  y+1/3,-x+y+2/3,-z+2/3
12  x-y+1/3,x+2/3,-z+2/3
13  x+2/3,y+1/3,z+1/3
14  -y+2/3,x-y+1/3,z+1/3
15  -x+y+2/3,-x+1/3,z+1/3
16  -x+2/3,-y+1/3,-z+1/3
17  y+2/3,-x+y+1/3,-z+1/3
18  x-y+2/3,x+1/3,-z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    6  c  0.00000  0.00000  0.11546  1.00000
H1  H    6  c  0.00000  0.00000  0.21000  1.00000
C2  C   18  f  0.06868  0.84319  0.03838  1.00000
H2  H   18  f  0.11580  0.72220  0.06900  1.00000
```

Solid Cubane (C_8H_8): AB_hR16_148_cf_cf - POSCAR

```
AB_hR16_148_cf_cf & a,c/a,x1,x2,x3,y3,z3,x4,y4,z4 --params=6.29713,
    ↪ 1.8633345667,0.11546,0.21,0.10706,0.81289,0.19519,0.1848,0.6754
    ↪ ,0.3468 & R(-3)      C_{3i}^2 #148 (c^2f^2) & hR16 & & C8H8 &
    ↪ Cubane & E. B. Fleischer, JACS 86, 3889-3890 (1964)
   1.0000000000000000
   3.14856727069900   -1.81782616130000    3.91121876007700
   0.00000000000000    3.63565232259900    3.91121876007700
  -3.14856727069900   -1.81782616130000    3.91121876007700
    C     H
    8     8
Direct
   0.11546000000000    0.11546000000000    0.11546000000000    C    (2c)
   0.88454000000000    0.88454000000000    0.88454000000000    C    (2c)
   0.10706000000000    0.81289000000000    0.19519000000000    C    (6f)
   0.18711000000000    0.80481000000000    0.89294000000000    C    (6f)
   0.19519000000000    0.10706000000000    0.81289000000000    C    (6f)
   0.80481000000000    0.89294000000000    0.18711000000000    C    (6f)
   0.81289000000000    0.19519000000000    0.10706000000000    C    (6f)
   0.89294000000000    0.18711000000000    0.80481000000000    C    (6f)
   0.21000000000000    0.21000000000000    0.21000000000000    H    (2c)
   0.79000000000000    0.79000000000000    0.79000000000000    H    (2c)
   0.18480000000000    0.67540000000000    0.34680000000000    H    (6f)
   0.32460000000000    0.65320000000000    0.81520000000000    H    (6f)
   0.34680000000000    0.18480000000000    0.67540000000000    H    (6f)
   0.65320000000000    0.81520000000000    0.32460000000000    H    (6f)
   0.67540000000000    0.34680000000000    0.18480000000000    H    (6f)
   0.81520000000000    0.32460000000000    0.65320000000000    H    (6f)
```

BiI_3 ($D0_5$): AB3_hR8_148_c_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Bismuth triodide'
_chemical_formula_sum 'Bi I3'

loop_
_publ_author_name
 'H. Br\aekken'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 74
_journal_year 1930
_journal_page_first 67
_journal_page_last 72
_publ_Section_title
;
 IX. Die Kristallstruktur der Trijodide von Arsen, Antimon und Wismut
;

# Found in  Strukturbericht Vol. II, pp. 25-27

_aflow_proto 'AB3_hR8_148_c_f'
_aflow_params 'a,c/a,x1,x2,y2,z2'
_aflow_params_values '7.49626,2.75900649124,0.33333,0.088,0.755,0.421'
_aflow_Strukturbericht 'D0_5'
_aflow_Pearson 'hR8'

_symmetry_space_group_name_Hall "-R 3"
_symmetry_space_group_name_H-M "R -3:H"
_symmetry_Int_Tables_number 148

_cell_length_a      7.49626
_cell_length_b      7.49626
_cell_length_c      20.68223
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  -y,x-y,z
3  -x+y,-x,z
4  -x,-y,-z
5  y,-x+y,-z
6  x-y,x,-z
7  x+1/3,y+2/3,z+2/3
8  -y+1/3,x-y+2/3,z+2/3
9  -x+y+1/3,-x+2/3,z+2/3
10  -x+1/3,-y+2/3,-z+2/3
11  y+1/3,-x+y+2/3,-z+2/3
12  x-y+1/3,x+2/3,-z+2/3
13  x+2/3,y+1/3,z+1/3
14  -y+2/3,x-y+1/3,z+1/3
15  -x+y+2/3,-x+1/3,z+1/3
16  -x+2/3,-y+1/3,-z+1/3
17  y+2/3,-x+y+1/3,-z+1/3
18  x-y+2/3,x+1/3,-z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Bi1  Bi    6  c  0.00000  0.00000  0.33333  1.00000
I1   I    18  f  0.00000  0.66700  0.08800  1.00000
```

BiI_3 ($D0_5$): AB3_hR8_148_c_f - POSCAR

```
AB3_hR8_148_c_f & a,c/a,x1,x2,y2,z2 --params=7.49626,2.75900649124,
    ↪ 0.33333,0.088,0.755,0.421 & R(-3)      C_{3i}^2 #148 (cf) & hR8
    ↪ & D0_5 & BiI3 & & H. Braekken, Zeitschrift f\"{u}r
    ↪ Kristallographie - Crystalline Materials 74, 67-72 (1930)
   1.0000000000000000
   3.74813000000000   -2.16398386445771    6.89407666667425
   0.00000000000000    4.32796772891543    6.89407666667425
  -3.74813000000000   -2.16398386445771    6.89407666667425
    Bi    I
    2     6
Direct
   0.33333333333333    0.33333333333333    0.33333333333333    Bi    (2c)
   0.66666666666667    0.66666666666667    0.66666666666667    Bi    (2c)
  -0.08800000000000    0.24500000000000    0.57900000000000    I    (6f)
   0.08800000000000    0.75500000000000    0.42100000000000    I    (6f)
   0.24500000000000    0.57900000000000   -0.08800000000000    I    (6f)
   0.42100000000000    0.08800000000000    0.75500000000000    I    (6f)
   0.57900000000000   -0.08800000000000    0.24500000000000    I    (6f)
   0.75500000000000    0.42100000000000    0.08800000000000    I    (6f)
```

PdAl: AB_hR26_148_b2f_a2f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta-prime palladium aluminum'
_chemical_formula_sum 'Pd Al'

loop_
_publ_author_name
 'T. Matkovi\'{c}'
 'K. Schubert'
_journal_name_full
;
Journal of the Less-Common Metals
;
_journal_volume 55
_journal_year 1977
_journal_page_first 45
_journal_page_last 52
_publ_Section_title
;
 Kristallstruktur vo PdAl.r
;

# Found in  http://materials.springer.com/lb/docs/
    ↪ sm_lbs_978-3-540-70892-6_476

_aflow_proto 'AB_hR26_148_b2f_a2f'
_aflow_params 'a,c/a,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6'
_aflow_params_values '15.659,0.335334312536,0.054,0.346,0.098,0.754,
    ↪ 0.15699,0.6,0.555,0.84401,0.599,0.252,0.65501,0.098'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR26'

_symmetry_space_group_name_Hall "-R 3"
_symmetry_space_group_name_H-M "R -3:H"
_symmetry_Int_Tables_number 148
```

```
_cell_length_a      15.65900
_cell_length_b      15.65900
_cell_length_c      5.25100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 -x,-y,-z
5 y,-x+y,-z
6 x-y,x,-z
7 x+1/3,y+2/3,z+2/3
8 -y+1/3,x-y+2/3,z+2/3
9 -x+y+1/3,-x+2/3,z+2/3
10 -x+1/3,-y+2/3,-z+2/3
11 y+1/3,-x+y+2/3,-z+2/3
12 x-y+1/3,x+2/3,-z+2/3
13 x+2/3,y+1/3,z+1/3
14 -y+2/3,x-y+1/3,z+1/3
15 -x+y+2/3,-x+1/3,z+1/3
16 -x+2/3,-y+1/3,-z+1/3
17 y+2/3,-x+y+1/3,-z+1/3
18 x-y+2/3,x+1/3,-z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pd1  Pd    3  a  0.00000  0.00000   0.00000  1.00000
Al1  Al    3  b  0.00000  0.00000   0.50000  1.00000
Al2  Al   18  f  0.88800  0.06800   0.16600  1.00000
Al3  Al   18  f  0.58367  0.57033   0.17033  1.00000
Pd2  Pd   18  f  0.22233  0.73367   0.33267  1.00000
Pd3  Pd   18  f  0.25033 -0.09633  0.00167  1.00000
```

PdAl: AB_hR26_148_b2f_a2f - POSCAR

```
AB_hR26_148_b2f_a2f & a,c/a,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6 --params
    ↪ =15.659,0.335334312536,0.054,0.346,0.098,0.754,0.15699,0.6,
    ↪ 0.555,0.84401,0.599,0.252,0.65501,0.098 & R(-3)      C_{3i}^2 #
    ↪ 148 (abf^4) & hR26 & & PdAl & beta' & T. Matkovi\'{c} and K.
    ↪ Schubert, J. Less Common Metals 55, 45-52 (1977)
   1.0000000000000000
   7.82950000000000   -4.52036393262018    1.75033333333333
   0.00000000000000    9.04072786524035    1.75033333333333
  -7.82950000000000   -4.52036393262018    1.75033333333333
   Al    Pd
   13    13
Direct
   0.50000000000000    0.50000000000000    0.50000000000000    Al    (1b)
   0.05400000000000    0.34600000000000    0.09800000000000    Al    (6f)
  -0.05400000000000    0.65400000000000   -0.09800000000000    Al    (6f)
   0.09800000000000    0.05400000000000    0.34600000000000    Al    (6f)
  -0.09800000000000   -0.05400000000000    0.65400000000000    Al    (6f)
   0.34600000000000    0.09800000000000    0.05400000000000    Al    (6f)
   0.65400000000000   -0.09800000000000   -0.05400000000000    Al    (6f)
  -0.15700000000000    0.40000000000000    0.24600000000000    Al    (6f)
   0.15700000000000    0.60000000000000    0.75400000000000    Al    (6f)
   0.24600000000000   -0.15700000000000    0.40000000000000    Al    (6f)
   0.40000000000000    0.24600000000000   -0.15700000000000    Al    (6f)
   0.60000000000000    0.75400000000000    0.15700000000000    Al    (6f)
   0.75400000000000    0.15700000000000    0.60000000000000    Al    (6f)
   0.00000000000000    0.00000000000000    0.00000000000000    Pd    (1a)
   0.15600000000000    0.40100000000000    0.44500000000000    Pd    (6f)
   0.40100000000000    0.44500000000000    0.15600000000000    Pd    (6f)
   0.44500000000000    0.15600000000000    0.40100000000000    Pd    (6f)
   0.55500000000000    0.84400000000000    0.59900000000000    Pd    (6f)
   0.59900000000000    0.55500000000000    0.84400000000000    Pd    (6f)
   0.84400000000000    0.59900000000000    0.55500000000000    Pd    (6f)
   0.09800000000000    0.25200000000000    0.65500000000000    Pd    (6f)
  -0.09800000000000    0.74800000000000    0.34500000000000    Pd    (6f)
   0.25200000000000    0.65500000000000    0.09800000000000    Pd    (6f)
   0.34500000000000   -0.09800000000000    0.74800000000000    Pd    (6f)
   0.65500000000000    0.09800000000000    0.25200000000000    Pd    (6f)
   0.74800000000000    0.34500000000000   -0.09800000000000    Pd    (6f)
```

Ilmenite ($FeTiO_3$): AB3C_hR10_148_c_f_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Ilmenite'
_chemical_formula_sum 'Fe Ti O3'

loop_
_publ_author_name
 'Barry A. Wechsler'
 'Charles T. Prewitt'
_journal_name_full
;
American Mineralogist
;
_journal_volume 69
_journal_year 1984
_journal_page_first 176
_journal_page_last 185
_publ_Section_title
;
 Crystal Structure of Ilmenite (FeTiO$_3$) at high temperature and high
    ↪ pressure
;

# Found in  Wyckoff, Vol. II, pp. 420

_aflow_proto 'AB3C_hR10_148_c_f_c'
_aflow_params 'a,c/a,x1,x2,x3,y3,z3'
_aflow_params_values '5.0884,2.76815894977,0.35537,0.1464,0.22174,
    ↪ 0.56249,0.95095'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR10'

_symmetry_space_group_name_Hall "-R 3"
_symmetry_space_group_name_H-M "R -3:H"
_symmetry_Int_Tables_number 148

_cell_length_a      5.08840
_cell_length_b      5.08840
_cell_length_c      14.08550
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 -x,-y,-z
5 y,-x+y,-z
6 x-y,x,-z
7 x+1/3,y+2/3,z+2/3
8 -y+1/3,x-y+2/3,z+2/3
9 -x+y+1/3,-x+2/3,z+2/3
10 -x+1/3,-y+2/3,-z+2/3
11 y+1/3,-x+y+2/3,-z+2/3
12 x-y+1/3,x+2/3,-z+2/3
13 x+2/3,y+1/3,z+1/3
14 -y+2/3,x-y+1/3,z+1/3
15 -x+y+2/3,-x+1/3,z+1/3
16 -x+2/3,-y+1/3,-z+1/3
17 y+2/3,-x+y+1/3,-z+1/3
18 x-y+2/3,x+1/3,-z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Fe1  Fe    6  c  0.00000   0.00000  0.35537  1.00000
Ti1  Ti    6  c  0.00000   0.00000  0.14640  1.00000
O1   O    18  f -0.02332  0.29411  0.24506  1.00000
```

Ilmenite ($FeTiO_3$): AB3C_hR10_148_c_f_c - POSCAR

```
AB3C_hR10_148_c_f_c & a,c/a,x1,x2,x3,y3,z3 --params=5.0884,2.76815894977
    ↪ ,0.35537,0.1464,0.22174,0.56249,0.95095 & R(-3)      C_{3i}^2 #
    ↪ 148 (c^2f) & hR10 & & FeTiO3 & Ilmenite & B. A. Wechsler and C.
    ↪ T. Prewitt, Am. Mineral. 69, 176-185 (1984)
   1.0000000000000000
   2.54420000000000   -1.46889455487200    4.69516666666700
   0.00000000000000    2.93778910974400    4.69516666666700
  -2.54420000000000   -1.46889455487200    4.69516666666700
   Fe    O    Ti
    2    6    2
Direct
   0.35537000000000    0.35537000000000    0.35537000000000    Fe    (2c)
   0.64463000000000    0.64463000000000    0.64463000000000    Fe    (2c)
  -0.04905000000000    0.22174000000000    0.56249000000000    O    (6f)
   0.04905000000000    0.77826000000000    0.43751000000000    O    (6f)
   0.22174000000000    0.56249000000000   -0.04905000000000    O    (6f)
   0.43751000000000    0.04905000000000    0.77826000000000    O    (6f)
   0.56249000000000   -0.04905000000000    0.22174000000000    O    (6f)
   0.77826000000000    0.43751000000000    0.04905000000000    O    (6f)
   0.14640000000000    0.14640000000000    0.14640000000000    Ti    (2c)
   0.85360000000000    0.85360000000000    0.85360000000000    Ti    (2c)
```

Original Fe_2P (C22): A2B_hP9_150_ef_bd - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Fe2 P'

loop_
_publ_author_name
 'Sterling B. Hendricks'
 'Peter R. Kosting'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
```

```
;
_journal_volume 74
_journal_year 1930
_journal_page_first 511
_journal_page_last 533
_publ_Section_title
;
 The Crystal Structure of Fe$_2$P, Fe$_2$N, Fe$_3$N and FeB
;

# Found in  Strukturbericht, Vol. II, pp. 15

_aflow_proto 'A2B_hP9_150_ef_bd'
_aflow_params 'a,c/a,z2,x3,x4'
_aflow_params_values '5.85,0.589743589744,0.875,0.26,0.6'
_aflow_Strukturbericht 'C22'
_aflow_Pearson 'hP9'

_symmetry_space_group_name_Hall "P 3 2"
_symmetry_space_group_name_H-M "P 3 2 1"
_symmetry_Int_Tables_number 150

_cell_length_a     5.85000
_cell_length_b     5.85000
_cell_length_c     3.45000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x-y,-y,-z
5 y,x,-z
6 -x,-x+y,-z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
P1  P    1 b 0.00000 0.00000 0.50000 1.00000
P2  P    2 d 0.33333 0.66667 0.87500 1.00000
Fe1 Fe   3 e 0.26000 0.00000 0.00000 1.00000
Fe2 Fe   3 f 0.60000 0.00000 0.50000 1.00000
```

Original Fe_2P (C22): A2B_hP9_150_ef_bd - POSCAR

```
A2B_hP9_150_ef_bd & a,c/a,z2,x3,x4 --params=5.85,0.589743589744,0.875,
    ↪ 0.26,0.6 & P321      D_3^2 #150 (bdef) & hP9 & C22 & Fe2P &
    ↪ incorrect but historical structure & S. B. Hendricks and P. R.
    ↪ Kosting, Zeitschrift f\"{u}r Kristallographie - Crystalline
    ↪ Materials 74, 511-533 (1930)
   1.0000000000000000
   2.92500000000000  -5.06624861213897   0.00000000000000
   2.92500000000000   5.06624861213897   0.00000000000000
   0.00000000000000   0.00000000000000   3.45000000000000
   Fe    P
    6    3
Direct
   0.00000000000000   0.26000000000000   0.00000000000000   Fe   (3e)
   0.26000000000000   0.00000000000000   0.00000000000000   Fe   (3e)
   0.74000000000000   0.74000000000000   0.00000000000000   Fe   (3e)
   0.00000000000000   0.60000000000000   0.50000000000000   Fe   (3f)
   0.40000000000000   0.40000000000000   0.50000000000000   Fe   (3f)
   0.60000000000000   0.00000000000000   0.50000000000000   Fe   (3f)
   0.00000000000000   0.00000000000000   0.50000000000000   P    (1b)
   0.33333333333333   0.66666666666667  -0.12500000000000   P    (2d)
   0.66666666666667   0.33333333333333   0.12500000000000   P    (2d)
```

$CrCl_3$ ($D0_4$): A3B_hP24_151_3c_2a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Chromium trichloride'
_chemical_formula_sum 'Cr Cl3'

loop_
_publ_author_name
 'Nora Wooster'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 74
_journal_year 1930
_journal_page_first 363
_journal_page_last 374
_publ_Section_title
;
 The Structure of Chromium Trichloride CrCl$_3$
;

# Found in  AMS Database

_aflow_proto 'A3B_hP24_151_3c_2a'
_aflow_params 'a,c/a,x1,x2,x3,y3,z3,x4,y4,z4,x5,y5,z5'
_aflow_params_values '6.017,2.87518697025,0.8889,0.5556,0.8889,0.1111,
    ↪ 0.0731,0.5556,0.4444,0.0731,0.2222,0.77778,0.0731'
_aflow_Strukturbericht 'D0_4'
_aflow_Pearson 'hP24'

_symmetry_space_group_name_Hall "P 31 2c (0 0 1)"
_symmetry_space_group_name_H-M "P 31 1 2"
_symmetry_Int_Tables_number 151

_cell_length_a     6.01700
_cell_length_b     6.01700
_cell_length_c     17.30000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z+1/3
3 -x+y,-x,z+2/3
4 x,x-y,-z
5 -x+y,y,-z+1/3
6 -y,-x,-z+2/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1 Cr   3 a 0.88890 0.11110 0.33333 1.00000
Cr2 Cr   3 a 0.55560 0.44440 0.33333 1.00000
Cl1 Cl   6 c 0.88890 0.11110 0.07310 1.00000
Cl2 Cl   6 c 0.55560 0.44440 0.07310 1.00000
Cl3 Cl   6 c 0.22220 0.77778 0.07310 1.00000
```

$CrCl_3$ ($D0_4$): A3B_hP24_151_3c_2a - POSCAR

```
A3B_hP24_151_3c_2a & a,c/a,x1,x2,x3,y3,z3,x4,y4,z4,x5,y5,z5 --params=
    ↪ 6.017,2.87518697025,0.8889,0.5556,0.8889,0.1111,0.0731,0.5556,
    ↪ 0.4444,0.0731,0.2222,0.77778,0.0731 & P3_112      D_3^3 #151 (a^
    ↪ 2c^3) & hP24 & D0_4 & CrCl3 & & N. Wooster, Zeitschrift f\"{u}r
    ↪  Kristallographie - Crystalline Materials 74, 363-374 (1930)
   1.0000000000000000
   3.00850000000000  -5.21087485457097   0.00000000000000
   3.00850000000000   5.21087485457097   0.00000000000000
   0.00000000000000   0.00000000000000  17.30000000000000
   Cl    Cr
   18    6
Direct
   0.22220000000000   0.11110000000000   0.26023333333333   Cl   (6c)
   0.22220000000000   0.11110000000000   0.73976666666667   Cl   (6c)
   0.88890000000000   0.11110000000000   0.07310000000000   Cl   (6c)
   0.88890000000000   0.11110000000000   0.59356666666667   Cl   (6c)
   0.88890000000000   0.77780000000000  -0.07310000000000   Cl   (6c)
   0.88890000000000   0.77780000000000   0.40643333333333   Cl   (6c)
   0.55560000000000   0.11120000000000  -0.07310000000000   Cl   (6c)
   0.55560000000000   0.11120000000000   0.40643333333333   Cl   (6c)
   0.55560000000000   0.44440000000000   0.07310000000000   Cl   (6c)
   0.55560000000000   0.44440000000000   0.59356666666667   Cl   (6c)
   0.88880000000000   0.44440000000000   0.26023333333333   Cl   (6c)
   0.88880000000000   0.44440000000000   0.73976666666667   Cl   (6c)
   0.22220000000000   0.44442000000000  -0.07310000000000   Cl   (6c)
   0.22220000000000   0.77778000000000   0.07310000000000   Cl   (6c)
   0.22222000000000   0.44442000000000   0.40643333333333   Cl   (6c)
   0.22222000000000   0.77780000000000   0.59356666666667   Cl   (6c)
   0.55558000000000   0.77778000000000   0.26023333333333   Cl   (6c)
   0.55558000000000   0.77780000000000   0.73976666666667   Cl   (6c)
   0.22220000000000   0.11110000000000   0.00000000000000   Cr   (3a)
   0.88890000000000   0.11110000000000   0.33333333333333   Cr   (3a)
   0.88890000000000   0.77780000000000   0.66666666666667   Cr   (3a)
   0.55560000000000   0.11120000000000   0.66666666666667   Cr   (3a)
   0.55560000000000   0.44440000000000   0.33333333333333   Cr   (3a)
   0.88880000000000   0.44440000000000   0.00000000000000   Cr   (3a)
```

α-Quartz (low Quartz): A2B_hP9_152_c_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'quartz (alpha)'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'R. M. Hazen'
 'L. W. Finger'
 'R. J. Hemley'
 'H. K. Mao'
_journal_name_full
;
Solid State Communications
;
_journal_volume 72
_journal_year 1989
_journal_page_first 507
```

```
_journal_page_last 511
_publ_Section_title
;
 High-pressure crystal chemistry and amorphization of $\alpha$-quartz
;

# Found in  AMS Database

_aflow_proto 'A2B_hP9_152_c_a'
_aflow_params 'a,c/a,x1,x2,y2,z2'
_aflow_params_values '4.914,1.10012210012,0.4699,0.413,0.2668,0.214'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP9'

_symmetry_space_group_name_Hall "P 31 2"
_symmetry_space_group_name_H-M "P 31 2 1"
_symmetry_Int_Tables_number 152

_cell_length_a     4.91400
_cell_length_b     4.91400
_cell_length_c     5.40600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z+1/3
3 -x+y,-x,z+2/3
4 x-y,-y,-z+2/3
5 y,x,-z
6 -x,-x+y,-z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   3 a 0.46990 0.00000 0.33333 1.00000
O1  O    6 c 0.41300 0.26680 0.21400 1.00000
```

α-Quartz (low Quartz): A2B_hP9_152_c_a - POSCAR

```
A2B_hP9_152_c_a & a,c/a,x1,x2,y2,z2 --params=4.914,1.10012210012,0.4699,
    ↪ 0.413,0.2668,0.214 & P3_121     D_3^4 #152 (ac) & hP9 & & SiO2 &
    ↪  alpha quartz & R. M. Hazen, L. W. Finger, R. J. Hemley and H.
    ↪ K. Mao, Solid State Comm. 72, 507-511 (1989)
   1.0000000000000000
   2.45700000000000  -4.25564883419700   0.00000000000000
   2.45700000000000   4.25564883419700   0.00000000000000
   0.00000000000000   0.00000000000000   5.40600000000000
    O   Si
    6    3
Direct
   0.14620000000000   0.73320000000000   0.45266666666700   O    (6c)
   0.26680000000000   0.41300000000000   0.78600000000000   O    (6c)
   0.41300000000000   0.26680000000000   0.21400000000000   O    (6c)
   0.58700000000000   0.85380000000000   0.11933333333300   O    (6c)
   0.73320000000000   0.14620000000000   0.54733333333300   O    (6c)
   0.85380000000000   0.58700000000000   0.88066666666700   O    (6c)
   0.00000000000000   0.46990000000000   0.66666666666700   Si   (3a)
   0.46990000000000   0.00000000000000   0.33333333333300   Si   (3a)
   0.53010000000000   0.53010000000000   0.00000000000000   Si   (3a)
```

γ-Se (A8): A_hP3_152_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha Selenium'
_chemical_formula_sum 'Se'

loop_
_publ_author_name
 'Paul Cherin'
 'Phyllis Unger'
_journal_name_full
;
Inorganic Chemistry
;
_journal_volume 6
_journal_year 1967
_journal_page_first 1589
_journal_page_last 1591
_publ_Section_title
;
 The crystal structure of trigonal selenium
;

# Found in  Donohue, pp. 370-372

_aflow_proto 'A_hP3_152_a'
_aflow_params 'a,c/a,x1'
_aflow_params_values '4.3662,1.13453346159,0.2254'
_aflow_Strukturbericht 'A8'
_aflow_Pearson 'hP3'
_symmetry_space_group_name_Hall "P 31 2"
_symmetry_space_group_name_H-M "P 31 2 1"
_symmetry_Int_Tables_number 152

_cell_length_a     4.36620
_cell_length_b     4.36620
_cell_length_c     4.95360
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z+1/3
3 -x+y,-x,z+2/3
4 x-y,-y,-z+2/3
5 y,x,-z
6 -x,-x+y,-z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Se1 Se   3 a 0.22540 0.00000 0.33333 1.00000
```

γ-Se (A8): A_hP3_152_a - POSCAR

```
A_hP3_152_a & a,c/a,x1 --params=4.3662,1.13453346159,0.2254 & P3_121
    ↪ D_3^4 #152 (a) & hP3 & A8 & Se & gamma & P. Cherin and P. Unger
    ↪ , Inorg. Chem. 6, 1589-1591 (1967)
   1.0000000000000000
   2.18310000000000  -3.78124011800400   0.00000000000000
   2.18310000000000   3.78124011800400   0.00000000000000
   0.00000000000000   0.00000000000000   4.95360000000000
   Se
    3
Direct
   0.00000000000000   0.22540000000000   0.66666666666667   Se   (3a)
   0.22540000000000   0.00000000000000   0.33333333333333   Se   (3a)
   0.77460000000000   0.77460000000000   0.00000000000000   Se   (3a)
```

Cinnabar (B9): AB_hP6_154_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Cinnabar'
_chemical_formula_sum 'Hg S'

loop_
_publ_author_name
 'P. Auvray'
 'F. Genet'
_journal_name_full
;
Bulletin de la Societe Francaise de Mineralogie et de Cristallographie
;
_journal_volume 96
_journal_year 1973
_journal_page_first 218
_journal_page_last 219
_publ_Section_title
;
 Affinement de la structure cristalline du cinabre $\alpha$-HgS
;

# Found in  AMS Database

_aflow_proto 'AB_hP6_154_a_b'
_aflow_params 'a,c/a,x1,x2'
_aflow_params_values '4.145,2.29095295537,0.7198,0.4889'
_aflow_Strukturbericht 'B9'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "P 32 2"
_symmetry_space_group_name_H-M "P 32 2 1"
_symmetry_Int_Tables_number 154

_cell_length_a     4.14500
_cell_length_b     4.14500
_cell_length_c     9.49600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z+2/3
3 -x+y,-x,z+1/3
4 x-y,-y,-z+1/3
5 y,x,-z
6 -x,-x+y,-z+2/3

loop_
```

```
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Hg1 Hg    3 a 0.71980 0.00000 0.66667 1.00000
S1  S     3 b 0.48890 0.00000 0.16667 1.00000
```

Cinnabar (B9): AB_hP6_154_a_b - POSCAR

```
AB_hP6_154_a_b & a,c/a,x1,x2 --params=4.145,2.29095295537,0.7198,0.4889
    ↪ & P3_221     D_3^6 #154 (ab) & hP6 & B9 & HgS & Cinnabar & P.
    ↪ Auvray and F. Genet, Bull. Soc. fr. Min\'{e}ral. Crystallogr.
    ↪ 96, 218-219 (1973)
   1.0000000000000000
   2.07250000000000  -3.58967529868600   0.00000000000000
   2.07250000000000   3.58967529868600   0.00000000000000
   0.00000000000000   0.00000000000000   9.49600000000000
   Hg    S
    3    3
Direct
   0.00000000000000   0.71980000000000   0.33333333333333   Hg   (3a)
   0.28020000000000   0.28020000000000   0.00000000000000   Hg   (3a)
   0.71980000000000   0.00000000000000   0.66666666666667   Hg   (3a)
   0.00000000000000   0.48890000000000   0.83333333333333   S    (3b)
   0.48890000000000   0.00000000000000   0.16666666666667   S    (3b)
   0.51110000000000   0.51110000000000   0.50000000000000   S    (3b)
```

AlF_3 ($D0_{14}$) : AB3_hR8_155_c_de - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Al F3'

loop_
_publ_author_name
 'J. A. A. Ketelaar'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 85
_journal_year 1933
_journal_page_first 119
_journal_page_last 131
_publ_Section_title
;
 Die Kristallstruktur der Aluminiumhalogenide: I. Die Kristallstruktur
    ↪ von AlF$_3$
;

# Found in AMS Database

_aflow_proto 'AB3_hR8_155_c_de'
_aflow_params 'a,c/a,x1,y2,y3'
_aflow_params_values '4.91608,2.53341483458,0.237,0.43,0.07'
_aflow_Strukturbericht 'D0_14'
_aflow_Pearson 'hR8'

_symmetry_space_group_name_Hall "R 3 2"
_symmetry_space_group_name_H-M "R 32:H"
_symmetry_Int_Tables_number 155

_cell_length_a      4.91608
_cell_length_b      4.91608
_cell_length_c      12.45447
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 x+1/3,y+2/3,z+2/3
8 -y+1/3,x-y+2/3,z+2/3
9 -x+y+1/3,-x+2/3,z+2/3
10 y+1/3,x+2/3,-z+2/3
11 -x+1/3,-x+y+2/3,-z+2/3
12 x-y+1/3,-y+2/3,-z+2/3
13 x+2/3,y+1/3,z+1/3
14 -y+2/3,x-y+1/3,z+1/3
15 -x+y+2/3,-x+1/3,z+1/3
16 y+2/3,x+1/3,-z+1/3
17 -x+2/3,-x+y+1/3,-z+1/3
18 x-y+2/3,-y+1/3,-z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1 Al    6 c 0.00000 0.00000 0.23700 1.00000
F1  F     9 d 0.43000 0.00000 0.00000 1.00000
F2  F     9 e 0.57000 0.00000 0.50000 1.00000
```

AlF_3 ($D0_{14}$) : AB3_hR8_155_c_de - POSCAR

```
AB3_hR8_155_c_de & a,c/a,x1,y2,y3 --params=4.91608,2.53341483458,0.237,
    ↪ 0.43,0.07 & R32      D_3^7 #155 (cde) & hR8 & D0_{14} & AlF3 &
    ↪ & J. Ketelaar, Zeitschrift f\"{u}r Kristallographie -
    ↪ Crystalline Materials 85, 119-131 (1933)
   1.0000000000000000
   2.45804199855867  -1.41915120954725   4.15149134381397
   0.00000000000000   2.83830241909450   4.15149134381397
  -2.45804199855867  -1.41915120954725   4.15149134381397
   Al    F
    2    6
Direct
   0.23700000000000   0.23700000000000   0.23700000000000   Al   (2c)
   0.76300000000000   0.76300000000000   0.76300000000000   Al   (2c)
   0.00000000000000   0.43000000000000   0.57000000000000   F    (3d)
   0.43000000000000   0.57000000000000  -0.00000000000000   F    (3d)
   0.57000000000000   0.00000000000000   0.43000000000000   F    (3d)
   0.07000000000000  -0.07000000000000   0.50000000000000   F    (3e)
  -0.07000000000000   0.50000000000000   0.07000000000000   F    (3e)
   0.50000000000000   0.07000000000000  -0.07000000000000   F    (3e)
```

Hazelwoodite (Ni_3S_2, $D5_e$) : A3B2_hR5_155_e_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Hazelwoodite'
_chemical_formula_sum 'Ni3 S2'

loop_
_publ_author_name
 'John B. Parise'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 36
_journal_year 1980
_journal_page_first 1179
_journal_page_last 1180
_publ_Section_title
;
 Structure of Hazelwoodite (Ni$_3$S$_2$
;

_aflow_proto 'A3B2_hR5_155_e_c'
_aflow_params 'a,c/a,x1,y2'
_aflow_params_values '5.73296,1.24097324942,0.2521,0.2449'
_aflow_Strukturbericht 'D5_e'
_aflow_Pearson 'hR5'

_symmetry_space_group_name_Hall "R 3 2"
_symmetry_space_group_name_H-M "R 32:H"
_symmetry_Int_Tables_number 155

_cell_length_a      5.73296
_cell_length_b      5.73296
_cell_length_c      7.11445
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 x+1/3,y+2/3,z+2/3
8 -y+1/3,x-y+2/3,z+2/3
9 -x+y+1/3,-x+2/3,z+2/3
10 y+1/3,x+2/3,-z+2/3
11 -x+1/3,-x+y+2/3,-z+2/3
12 x-y+1/3,-y+2/3,-z+2/3
13 x+2/3,y+1/3,z+1/3
14 -y+2/3,x-y+1/3,z+1/3
15 -x+y+2/3,-x+1/3,z+1/3
16 y+2/3,x+1/3,-z+1/3
17 -x+2/3,-x+y+1/3,-z+1/3
18 x-y+2/3,-y+1/3,-z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
S1  S     6 c 0.00000 0.00000 0.25210 1.00000
Ni1 Ni    9 e 0.74490 0.00000 0.50000 1.00000
```

Hazelwoodite (Ni_3S_2, $D5_e$) : A3B2_hR5_155_e_c - POSCAR

```
A3B2_hR5_155_e_c & a,c/a,x1,y2 --params=5.73296,1.24097324942,0.2521,
    ↪ 0.2449 & R32        D_3^7 #155 (ce) & hR5 & D5_e & Ni3S2 &
    ↪ Hazelwoodite & J. B. Parise, Acta Cryst. B 36, 1179-1180 (1980)
   1.0000000000000000
   2.86648097666438   -1.65496356350412    2.37148427232714
   0.00000000000000    3.30992712700824    2.37148427232714
  -2.86648097666438   -1.65496356350412    2.37148427232714
   Ni    S
    3    2
Direct
   0.24490000000000    0.75510000000000    0.50000000000000    Ni    (3e)
   0.50000000000000    0.24490000000000    0.75510000000000    Ni    (3e)
   0.75510000000000    0.50000000000000    0.24490000000000    Ni    (3e)
   0.25210000000000    0.25210000000000    0.25210000000000     S    (2c)
   0.74790000000000    0.74790000000000    0.74790000000000     S    (2c)
```

Millerite (NiS, B13): AB_hR6_160_b_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Millerite'
_chemical_formula_sum 'Ni S'

loop_
_publ_author_name
 'V. Rajamani'
 'C. T. Prewitt'
_journal_name_full
;
Canadian Mineralogist
;
_journal_volume 12
_journal_year 1974
_journal_page_first 253
_journal_page_last 257
_publ_Section_title
;
 The Crystal Structure of Millerite
;

# Found in AMS Database

_aflow_proto 'AB_hR6_160_b_b'
_aflow_params 'a,c/a,x1,z1,x2,z2'
_aflow_params_values '9.619,0.327466472606,0.00019,0.26362,0.7288,
    ↪ 0.39161'
_aflow_Strukturbericht 'B13'
_aflow_Pearson 'hR6'

_symmetry_space_group_name_Hall "R 3 -2"
_symmetry_space_group_name_H-M "R 3 m:H"
_symmetry_Int_Tables_number 160

_cell_length_a      9.61900
_cell_length_b      9.61900
_cell_length_c      3.14990
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 -y,-x,z
5 x,x-y,z
6 -x+y,y,z
7 x+1/3,y+2/3,z+2/3
8 -y+1/3,x-y+2/3,z+2/3
9 -x+y+1/3,-x+2/3,z+2/3
10 -y+1/3,-x+2/3,z+2/3
11 x+1/3,x-y+2/3,z+2/3
12 -x+y+1/3,y+2/3,z+2/3
13 x+2/3,y+1/3,z+1/3
14 -y+2/3,x-y+1/3,z+1/3
15 -x+y+2/3,-x+1/3,z+1/3
16 -y+2/3,-x+1/3,z+1/3
17 x+2/3,x-y+1/3,z+1/3
18 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ni1 Ni    9 b -0.08781 0.08781 0.08800 1.00000
S1  S     9 b 0.44573  0.55427 0.28307 1.00000
```

Millerite (NiS, B13): AB_hR6_160_b_b - POSCAR

```
AB_hR6_160_b_b & a,c/a,x1,z1,x2,z2 --params=9.619,0.327466472606,0.00019
    ↪ ,0.26362,0.7288,0.39161 & R3m        C_{3v}^5 #160 (b^2) & hR6 &
    ↪ B13 & NiS (beta) & Millerite & V. Rajamni and C. T. Prewitt,
    ↪ Can. Min. 12, 253-257 (1974)
   1.0000000000000000
   4.80950000000000   -2.77676611966800    1.04996666666700
   0.00000000000000    5.55353223933500    1.04996666666700
  -4.80950000000000   -2.77676611966800    1.04996666666700
   Ni    Si
    3     3
Direct
   0.00019000000000    0.00019000000000    0.26362000000000    Ni    (3b)
   0.00019000000000    0.26362000000000    0.00019000000000    Ni    (3b)
   0.26362000000000    0.00019000000000    0.00019000000000    Ni    (3b)
   0.39160000000000    0.72880000000000    0.72880000000000     S    (3b)
   0.72880000000000    0.39160000000000    0.72880000000000     S    (3b)
   0.72880000000000    0.72880000000000    0.39160000000000     S    (3b)
```

Moissanite 9R: AB_hR6_160_3a_3a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Moissanite 9R'
_chemical_formula_sum 'C Si'

loop_
_publ_author_name
 'Michael J. Mehl'
_journal_name_full
;
None
;
_journal_volume 0
_journal_year 2001
_journal_page_first 0
_journal_page_last 0
_publ_Section_title
;
 Hypothetical SiO2 Structure with 9R stacking
;

_aflow_proto 'AB_hR6_160_3a_3a'
_aflow_params 'a,c/a,x1,x2,x3,x4,x5,x6'
_aflow_params_values '3.01791,7.34847294982,0.0,0.22222,0.77778,0.08333,
    ↪ 0.30556,0.86111'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR6'

_symmetry_space_group_name_Hall "R 3 -2"
_symmetry_space_group_name_H-M "R 3 m:H"
_symmetry_Int_Tables_number 160

_cell_length_a      3.01791
_cell_length_b      3.01791
_cell_length_c      22.17703
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 -y,-x,z
5 x,x-y,z
6 -x+y,y,z
7 x+1/3,y+2/3,z+2/3
8 -y+1/3,x-y+2/3,z+2/3
9 -x+y+1/3,-x+2/3,z+2/3
10 -y+1/3,-x+2/3,z+2/3
11 x+1/3,x-y+2/3,z+2/3
12 -x+y+1/3,y+2/3,z+2/3
13 x+2/3,y+1/3,z+1/3
14 -y+2/3,x-y+1/3,z+1/3
15 -x+y+2/3,-x+1/3,z+1/3
16 -y+2/3,-x+1/3,z+1/3
17 x+2/3,x-y+1/3,z+1/3
18 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    3 a 0.00000 0.00000 0.00000 1.00000
C2  C    3 a 0.00000 0.00000 0.22222 1.00000
C3  C    3 a 0.00000 0.00000 0.77778 1.00000
Si1 Si   3 a 0.00000 0.00000 0.08333 1.00000
Si2 Si   3 a 0.00000 0.00000 0.30556 1.00000
Si3 Si   3 a 0.00000 0.00000 0.86111 1.00000
```

Moissanite 9R: AB_hR6_160_3a_3a - POSCAR

```
AB_hR6_160_3a_3a & a,c/a,x1,x2,x3,x4,x5,x6 --params=3.01791,
    ↪ 7.34847294982,0.0,0.22222,0.77778,0.08333,0.30556,0.86111 & R3m
    ↪          C_{3v}^5 #160 (a^6) & hR6 & & CSi & 9R (Hypothetical
    ↪ ABCBCACAB stacking) &
   1.0000000000000000
   1.50895500000000   -0.87119557544503    7.39234333333042
   0.00000000000000    1.74239115089006    7.39234333333042
```

```
  -1.50895500000000   -0.87119557544503    7.39234333333042
     C     Si
     3     3
Direct
    0.00000000000000    0.00000000000000    0.00000000000000     C     (1a)
    0.22222222222222    0.22222222222222    0.22222222222222     C     (1a)
    0.77777777777778    0.77777777777778    0.77777777777778     C     (1a)
    0.08333333333333    0.08333333333333    0.08333333333333    Si     (1a)
    0.30555555555556    0.30555555555556    0.30555555555556    Si     (1a)
    0.86111111111111    0.86111111111111    0.86111111111111    Si     (1a)
```

Ferroelectric $LiNbO_3$: ABC3_hR10_161_a_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Li Nb O3'

loop_
_publ_author_name
 'H. Boysen'
 'F. Altorfer'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 50
_journal_year 1994
_journal_page_first 405
_journal_page_last 414
_publ_Section_title
;
 A neutron powder investigation of the high-temperature structure and
      ↪ phase transition in LiNbO$_3$
;

_aflow_proto 'ABC3_hR10_161_a_a_b'
_aflow_params 'a,c/a,x1,x2,x3,y3,z3'
_aflow_params_values '5.2542,2.64091583876,0.2875,0.0128,0.74643,0.14093
      ↪ ,0.36263'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR10'

_symmetry_space_group_name_Hall "R 3 -2c"
_symmetry_space_group_name_H-M "R 3 c:H"
_symmetry_Int_Tables_number 161

_cell_length_a      5.25420
_cell_length_b      5.25420
_cell_length_c      13.87590
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 -y,-x,z+1/2
5 x,x-y,z+1/2
6 -x+y,y,z+1/2
7 x+1/3,y+2/3,z+2/3
8 -y+1/3,x-y+2/3,z+2/3
9 -x+y+1/3,-x+2/3,z+2/3
10 -y+1/3,-x+2/3,z+1/6
11 x+1/3,x-y+2/3,z+1/6
12 -x+y+1/3,y+2/3,z+1/6
13 x+2/3,y+1/3,z+1/3
14 -y+2/3,x-y+1/3,z+1/3
15 -x+y+2/3,-x+1/3,z+1/3
16 -y+2/3,-x+1/3,z+5/6
17 x+2/3,x-y+1/3,z+5/6
18 -x+y+2/3,y+1/3,z+5/6

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Li1 Li    6 a 0.00000 0.00000 0.28750 1.00000
Nb1 Nb    6 a 0.00000 0.00000 0.01280 1.00000
O1  O    18 b 0.66310 0.72070 0.08333 1.00000
```

Ferroelectric $LiNbO_3$: ABC3_hR10_161_a_a_b - POSCAR

```
ABC3_hR10_161_a_a_b & a,c/a,x1,x2,x3,y3,z3 --params=5.2542,2.64091583876
      ↪ ,0.2875,0.0128,0.74643,0.14093,0.36263 & R3c        C_{3v}^6 #
      ↪ 161 (a^2b) & hR10 & & LiNbO3 & Ferroelectric & H. Boysen and F.
      ↪  Altorfer, Acta Cryst. B 50, 405-414 (1994)
   1.0000000000000000
   2.62710000000000   -1.51675689218800    4.62530000000000
   0.00000000000000    3.03351378437600    4.62530000000000
  -2.62710000000000   -1.51675689218800    4.62530000000000
    Li    Nb    O
     2     2    6
Direct
    0.28750000000000    0.28750000000000    0.28750000000000    Li    (2a)
    0.78750000000000    0.78750000000000    0.78750000000000    Li    (2a)
    0.01280000000000    0.01280000000000    0.01280000000000    Nb    (2a)
    0.51280000000000    0.51280000000000    0.51280000000000    Nb    (2a)
    0.14093333333333    0.36263333333333    0.74643333333333     O    (6b)
    0.24643333333333    0.86263333333333    0.64093333333333     O    (6b)
    0.36263333333333    0.74643333333333    0.14093333333333     O    (6b)
    0.64093333333333    0.24643333333333    0.86263333333333     O    (6b)
    0.74643333333333    0.14093333333333    0.36263333333333     O    (6b)
    0.86263333333333    0.64093333333333    0.24643333333333     O    (6b)
```

β-V_2N: AB2_hP9_162_ad_k - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Vanadium nitride'
_chemical_formula_sum 'V2 N'

loop_
_publ_author_name
 'A. N{\o}rlund Christensen'
 'B. Lebech'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 35
_journal_year 1979
_journal_page_first 2677
_journal_page_last 2678
_publ_Section_title
;
 The structure of $\beta$-Vanadium Nitride
;

# Found in  Pearson's Handbook IV, pp. 4503

_aflow_proto 'AB2_hP9_162_ad_k'
_aflow_params 'a,c/a,x3,z3'
_aflow_params_values '4.917,0.929021761237,0.325,0.272'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP9'

_symmetry_space_group_name_Hall "-P 3 2"
_symmetry_space_group_name_H-M "P -3 1 m"
_symmetry_Int_Tables_number 162

_cell_length_a      4.91700
_cell_length_b      4.91700
_cell_length_c      4.56800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x,x-y,-z
5 -x+y,y,-z
6 -y,-x,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -x,-x+y,z
11 x-y,-y,z
12 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
N1 N    1 a 0.00000 0.00000 0.00000 1.00000
N2 N    2 d 0.33333 0.66667 0.50000 1.00000
V1 V    6 k 0.32500 0.00000 0.27200 1.00000
```

β-V_2N: AB2_hP9_162_ad_k - POSCAR

```
AB2_hP9_162_ad_k & a,c/a,x3,z3 --params=4.917,0.929021761237,0.325,0.272
      ↪ & P(-3)1m    D_{3d}^1 #162 (adk) & hP9 & & V2N & beta & A. N.
      ↪ Christensen and B. Lebech, Acta Cryst. B 35, 2677-2678 (1979)
   1.0000000000000000
   2.45850000000000   -4.25824691040809    0.00000000000000
   2.45850000000000    4.25824691040809    0.00000000000000
   0.00000000000000    0.00000000000000    4.56800000000000
    N     V
    3     6
Direct
    0.00000000000000    0.00000000000000    0.00000000000000     N    (1a)
    0.33333333333333    0.66666666666667    0.50000000000000     N    (2d)
    0.66666666666667    0.33333333333333    0.50000000000000     N    (2d)
    0.00000000000000    0.32500000000000    0.27200000000000     V    (6k)
    0.00000000000000    0.67500000000000    0.72800000000000     V    (6k)
    0.32500000000000    0.00000000000000    0.27200000000000     V    (6k)
    0.32500000000000    0.32500000000000    0.72800000000000     V    (6k)
```

```
   0.67500000000000    0.00000000000000    0.72800000000000    V    (6k)
   0.67500000000000    0.67500000000000    0.27200000000000    V    (6k)
```

KAg(CN)$_2$ (F5$_{10}$): AB2CD2_hP36_163_h_i_bf_i - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Potassium Silver Cyanide'
_chemical_formula_sum 'Ag C2 K N2'

loop_
_publ_author_name
 'J. L. Hoard'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 84
_journal_year 1933
_journal_page_first 231
_journal_page_last 255
_publ_Section_title
;
 The Crystal Structure of Potassium Silver Cyanide
;

# Found in http://materials.springer.com/isp/crystallographic/docs/
      ↪ sd_1253381

_aflow_proto 'AB2CD2_hP36_163_h_i_bf_i'
_aflow_params 'a,c/a,z2,x3,x4,y4,z4,x5,y5,z5'
_aflow_params_values '7.384,2.37716684724,0.01,0.833,0.33333,0.03833,
      ↪ 0.141,0.03167,0.365,0.083'
_aflow_Strukturbericht 'F5_10'
_aflow_Pearson 'hP36'

_symmetry_space_group_name_Hall "-P 3 2c"
_symmetry_space_group_name_H-M "P -3 1 c"
_symmetry_Int_Tables_number 163

_cell_length_a      7.38400
_cell_length_b      7.38400
_cell_length_c      17.55300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x,x-y,-z+1/2
5 -x+y,y,-z+1/2
6 -y,-x,-z+1/2
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -x,-x+y,z+1/2
11 x-y,-y,z+1/2
12 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
K1  K    2 b 0.00000 0.00000 0.00000 1.00000
K2  K    4 f 0.33333 0.66667 0.01000 1.00000
Ag1 Ag   6 h 0.83300 0.16700 0.25000 1.00000
C1  C   12 i 0.33333 0.03833 0.14100 1.00000
N1  N   12 i 0.03167 0.36500 0.08300 1.00000
```

KAg(CN)$_2$ (F5$_{10}$): AB2CD2_hP36_163_h_i_bf_i - POSCAR

```
AB2CD2_hP36_163_h_i_bf_i & a,c/a,z2,x3,x4,y4,z4,x5,y5,z5 --params=7.384,
      ↪ 2.37716684724,0.01,0.833,0.33333,0.03833,0.141,0.03167,0.365,
      ↪ 0.083 & P(-3)1c  D_{3d}^2 #163 (bfhi^2) & hP36 & F5_10 & KAg(
      ↪ CN)2 & & J. L. Hoard, Zeitschrift f\"{u}r Kristallographie -
      ↪ Crystalline Materials 84, 231-255 (1933)
   1.0000000000000000
   3.69200000000000  -6.39473158154430   0.00000000000000
   3.69200000000000   6.39473158154430   0.00000000000000
   0.00000000000000   0.00000000000000  17.55300000000000
   Ag   C   K   N
    6  12   6  12
Direct
   0.16700000000000   0.33400000000000   0.75000000000000   Ag   (6h)
   0.16700000000000   0.83300000000000   0.75000000000000   Ag   (6h)
   0.33400000000000   0.16700000000000   0.25000000000000   Ag   (6h)
   0.66600000000000   0.83300000000000   0.75000000000000   Ag   (6h)
   0.83300000000000   0.16700000000000   0.25000000000000   Ag   (6h)
   0.83300000000000   0.66600000000000   0.25000000000000   Ag   (6h)
  -0.03833000000000   0.29500000000000   0.14100000000000   C   (12i)
   0.03833000000000   0.33333000000000   0.64100000000000   C   (12i)
  -0.03833000000000   0.66667000000000   0.35900000000000   C   (12i)
   0.03833000000000   0.70500000000000   0.85900000000000   C   (12i)
   0.29500000000000  -0.03833000000000   0.64100000000000   C   (12i)
   0.29500000000000   0.33333000000000   0.85900000000000   C   (12i)
   0.33333000000000   0.03833000000000   0.14100000000000   C   (12i)
   0.33333000000000   0.29500000000000   0.35900000000000   C   (12i)
   0.66667000000000  -0.03833000000000   0.85900000000000   C   (12i)
   0.66667000000000   0.70500000000000   0.64100000000000   C   (12i)
   0.70500000000000   0.03833000000000   0.35900000000000   C   (12i)
   0.70500000000000   0.66667000000000   0.14100000000000   C   (12i)
   0.00000000000000   0.00000000000000   0.00000000000000   K    (2b)
   0.00000000000000   0.00000000000000   0.50000000000000   K    (2b)
   0.33333333333333   0.66666666666667   0.01000000000000   K    (4f)
   0.33333333333333   0.66666666666667   0.49000000000000   K    (4f)
   0.66666666666667   0.33333333333333  -0.01000000000000   K    (4f)
   0.66666666666667   0.33333333333333   0.51000000000000   K    (4f)
  -0.03167000000000   0.33333000000000   0.58300000000000   N   (12i)
   0.03167000000000   0.36500000000000   0.08300000000000   N   (12i)
  -0.03167000000000   0.63500000000000  -0.08300000000000   N   (12i)
   0.03167000000000   0.66667000000000   0.41700000000000   N   (12i)
   0.33333000000000  -0.03167000000000   0.08300000000000   N   (12i)
   0.33333000000000   0.36500000000000   0.41700000000000   N   (12i)
   0.36500000000000   0.03167000000000   0.58300000000000   N   (12i)
   0.36500000000000   0.33333000000000  -0.08300000000000   N   (12i)
   0.63500000000000  -0.03167000000000   0.41700000000000   N   (12i)
   0.63500000000000   0.66667000000000   0.08300000000000   N   (12i)
   0.66667000000000   0.03167000000000  -0.08300000000000   N   (12i)
   0.66667000000000   0.63500000000000   0.58300000000000   N   (12i)
```

Al_3Ni_2 (D5$_{13}$): A3B2_hP5_164_ad_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Al3 Ni2'

loop_
_publ_author_name
 'A. J. Bradley'
 'A. Taylor'
_journal_name_full
;
Philosophical Magazine
;
_journal_volume 23
_journal_year 1937
_journal_page_first 1049
_journal_page_last 1067
_publ_Section_title
;
 The crystal structures of Ni$_2$Al$_3$ and NiAl$_3$
;

# Found in http://materials.springer.com/lb/docs/
      ↪ sm_lbs_978-3-540-44752-8_197

_aflow_proto 'A3B2_hP5_164_ad_d'
_aflow_params 'a,c/a,z2,z3'
_aflow_params_values '4.0282,1.21409066084,0.648,0.149'
_aflow_Strukturbericht 'D5_13'
_aflow_Pearson 'hP5'

_symmetry_space_group_name_Hall "-P 3 2"
_symmetry_space_group_name_H-M "P -3 m 1"
_symmetry_Int_Tables_number 164

_cell_length_a      4.02820
_cell_length_b      4.02820
_cell_length_c      4.89060
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x-y,-y,-z
5 y,x,-z
6 -x,-x+y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -x+y,y,z
11 -y,-x,z
12 x,x-y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1 Al   1 a 0.00000 0.00000 0.00000 1.00000
Al2 Al   2 d 0.33333 0.66667 0.64800 1.00000
Ni1 Ni   2 d 0.33333 0.66667 0.14900 1.00000
```

Al_3Ni_2 (D5$_{13}$): A3B2_hP5_164_ad_d - POSCAR

```
A3B2_hP5_164_ad_d & a,c/a,z2,z3 --params=4.0282,1.21409066084,0.648,
    ↪ 0.149 & P(-3)ml    D_{3d}^3 #164 (ad^2) & hP5 & D5_{13} & Al3Ni2
    ↪ & & A. J. Bradley and A. Taylor, Phil. Mag. 23, 1049-1067 (
    ↪ 1937)
   1.0000000000000000
   2.01410000000000   -3.48852353152400    0.00000000000000
   2.01410000000000    3.48852353152400    0.00000000000000
   0.00000000000000    0.00000000000000    4.89060000000000
   Al    Ni
    3     2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Al    (1a)
   0.33333333333333    0.66666666666667    0.64800000000000    Al    (2d)
   0.66666666666667    0.33333333333333    0.35200000000000    Al    (2d)
   0.33333333333333    0.66666666666667    0.14900000000000    Ni    (2d)
   0.66666666666667    0.33333333333333    0.85100000000000    Ni    (2d)
```

ω (C6) Phase: AB2_hP3_164_a_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'trigonal omega'
_chemical_formula_sum 'Cd I2'

loop_
_publ_author_name
 'Richard M. Bozorth'
_journal_name_full
;
Journal of the American Chemical Society
;
_journal_volume 44
_journal_year 1922
_journal_page_first 2232
_journal_page_last 2236
_publ_Section_title
;
 The Crystal Structure of Cadmium Iodide
;

# Found in  Strukturbericht Vol. I, pp. 161-3

_aflow_proto 'AB2_hP3_164_a_d'
_aflow_params 'a,c/a,z2'
_aflow_params_values '4.24,1.61320754717,0.252'
_aflow_Strukturbericht 'C6'
_aflow_Pearson 'hP3'

_symmetry_space_group_name_Hall "-P 3 2"
_symmetry_space_group_name_H-M "P -3 m 1"
_symmetry_Int_Tables_number 164

_cell_length_a      4.24000
_cell_length_b      4.24000
_cell_length_c      6.84000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x-y,-y,-z
5 y,x,-z
6 -x,-x+y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -x+y,y,z
11 -y,-x,z
12 x,x-y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cd1 Cd    1 a 0.00000 0.00000 0.00000 1.00000
I1  I     2 d 0.33333 0.66667 0.25200 1.00000
```

ω (C6) Phase: AB2_hP3_164_a_d - POSCAR

```
AB2_hP3_164_a_d & a,c/a,z2 --params=4.24,1.61320754717,0.252 & P(-3)ml
    ↪ D_{3d}^3 #164 (ad) & hP3 & C6 & CdI2 & trigonal omega & R. M.
    ↪ Bozorth, J. Am. Chem. Soc. 44, 2232-2236 (1922)
   1.0000000000000000
   2.12000000000000   -3.67194771204602    0.00000000000000
   2.12000000000000    3.67194771204602    0.00000000000000
   0.00000000000000    0.00000000000000    6.84000000000000
   Cd    I
    1    2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cd    (1a)
   0.33333333333333    0.66666666666667    0.25200000000000    I     (2d)
   0.66666666666667    0.33333333333333    0.74800000000000    I     (2d)
```

H_3Ho: A3B_hP24_165_adg_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'H3 Ho'

loop_
_publ_author_name
 'M. Mansmann'
 'W. E. Wallace'
_journal_name_full
;
Le Journal de Physique
;
_journal_volume 25
_journal_year 1964
_journal_page_first 454
_journal_page_last 459
_publ_Section_title
;
 The Structure of HoD$_3$
;

# Found in  Pearson's Handbook, Vol III, pp. 3829

_aflow_proto 'A3B_hP24_165_adg_f'
_aflow_params 'a,c/a,z2,x3,x4,y4,z4'
_aflow_params_values '6.308,1.03994927077,0.167,0.666,0.356,0.028,0.096'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP24'

_symmetry_space_group_name_Hall "-P 3 2c"
_symmetry_space_group_name_H-M "P -3 c 1"
_symmetry_Int_Tables_number 165

_cell_length_a      6.30800
_cell_length_b      6.30800
_cell_length_c      6.56000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x-y,-y,-z+1/2
5 y,x,-z+1/2
6 -x,-x+y,-z+1/2
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -x+y,y,z+1/2
11 -y,-x,z+1/2
12 x,x-y,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
H1  H     2 a 0.00000 0.00000 0.25000 1.00000
H2  H     4 d 0.33333 0.66667 0.16700 1.00000
Ho1 Ho    6 f 0.66600 0.00000 0.25000 1.00000
H3  H    12 g 0.35600 0.02800 0.09600 1.00000
```

H_3Ho: A3B_hP24_165_adg_f - POSCAR

```
A3B_hP24_165_adg_f & a,c/a,z2,x3,x4,y4,z4 --params=6.308,1.03994927077,
    ↪ 0.167,0.666,0.356,0.028,0.096 & P(-3)c1    D_{3d}^4 #165 (adfg)
    ↪ & hP24 & & H_3Ho & & M. Mansmann and W. E. Wallace, Le Journal
    ↪ de Physique 25, 454-459 (1964)
   1.0000000000000000
   3.15400000000000   -5.46288824707224    0.00000000000000
   3.15400000000000    5.46288824707224    0.00000000000000
   0.00000000000000    0.00000000000000    6.56000000000000
    H    Ho
   18    6
Direct
  -0.02800000000000    0.32800000000000    0.09600000000000    H    (12g)
   0.02800000000000    0.35600000000000    0.40400000000000    H    (12g)
  -0.02800000000000    0.64400000000000    0.59600000000000    H    (12g)
   0.02800000000000    0.67200000000000   -0.09600000000000    H    (12g)
   0.32800000000000   -0.02800000000000    0.40400000000000    H    (12g)
   0.32800000000000    0.35600000000000   -0.09600000000000    H    (12g)
   0.35600000000000    0.02800000000000    0.09600000000000    H    (12g)
   0.35600000000000    0.32800000000000    0.59600000000000    H    (12g)
   0.64400000000000   -0.02800000000000   -0.09600000000000    H    (12g)
   0.64400000000000    0.67200000000000    0.40400000000000    H    (12g)
   0.67200000000000    0.02800000000000    0.59600000000000    H    (12g)
   0.67200000000000    0.64400000000000    0.09600000000000    H    (12g)
   0.00000000000000    0.00000000000000    0.25000000000000    H     (2a)
   0.00000000000000    0.00000000000000    0.75000000000000    H     (2a)
   0.33333333333333    0.66666666666667    0.16700000000000    H     (4d)
   0.33333333333333    0.66666666666667    0.66700000000000    H     (4d)
```

```
    0.66666666666667    0.33333333333333    0.33300000000000    H    (4d)
    0.66666666666667    0.33333333333333    0.83300000000000    H    (4d)
    0.00000000000000    0.33400000000000    0.75000000000000    Ho   (6f)
    0.00000000000000    0.66600000000000    0.25000000000000    Ho   (6f)
    0.33400000000000    0.00000000000000    0.75000000000000    Ho   (6f)
    0.33400000000000    0.33400000000000    0.25000000000000    Ho   (6f)
    0.66600000000000    0.00000000000000    0.25000000000000    Ho   (6f)
    0.66600000000000    0.66600000000000    0.75000000000000    Ho   (6f)
```

CuPt ($L1_1$): AB_hR2_166_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cu Pt'

loop_
_publ_author_name
 'C. H. Johansson'
 'J. O. Linde'
_journal_name_full
;
Annalen der Physik
;
_journal_volume 387
_journal_year 1927
_journal_page_first 449
_journal_page_last 478
_publ_Section_title
;
 Gitterstruktur und elektrisches Leitverm\"{o}gen der
      ↪ Mischkristallreihen Au-Cu, Pd-Cu und Pt-Cu
;

# Found in  http://materials.springer.com/lb/docs/
      ↪ sm_lbs_978-3-540-46933-9_359

_aflow_proto 'AB_hR2_166_a_b'
_aflow_params 'a,c/a'
_aflow_params_values '3.13,4.78594249201'
_aflow_Strukturbericht 'L1_1'
_aflow_Pearson 'hR2'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      3.13000
_cell_length_b      3.13000
_cell_length_c      14.98000
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu   3 a 0.00000 0.00000 0.00000 1.00000
Pt1 Pt   3 b 0.00000 0.00000 0.50000 1.00000
```

CuPt ($L1_1$): AB_hR2_166_a_b - POSCAR

```
AB_hR2_166_a_b & a,c/a --params=3.13,4.78594249201 & R(-3)m    D_{3d}^5
      ↪ #166 (ab) & hR2 & L1_1 & CuPt & approximate & C. H. Johansson
      ↪ and J. O. Linde, Annalen der Physik 387, 449-478 (1927)
   1.0000000000000000
   1.56500000000000   -0.90355317128200    4.99333333333300
   0.00000000000000    1.80710634256400    4.99333333333300
  -1.56500000000000   -0.90355317128200    4.99333333333300
   Cu    Pt
    1     1
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cu    (1a)
   0.50000000000000    0.50000000000000    0.50000000000000    Pt    (1b)
```

α-As (A7): A_hR2_166_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha As'
_chemical_formula_sum 'As'

loop_
_publ_author_name
 'D. Schiferl'
 'C. S. Barrett'
_journal_name_full
;
Journal of Applied Crystallography
;
_journal_volume 2
_journal_year 1969
_journal_page_first 30
_journal_page_last 36
_publ_Section_title
;
 The crystal structure of arsenic at 4.2, 78 and 299 K
;

# Found in  AMS Database

_aflow_proto 'A_hR2_166_c'
_aflow_params 'a,c/a,x1'
_aflow_params_values '3.7595,2.7815666977,0.22754'
_aflow_Strukturbericht 'A7'
_aflow_Pearson 'hR2'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      3.75950
_cell_length_b      3.75950
_cell_length_c      10.45730
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3
```

```
loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
As1 As    6 c 0.00000  0.00000  0.22754  1.00000
```

α-As (A7): A_hR2_166_c - POSCAR

```
A_hR2_166_c & a,c/a,x1 --params=3.7595,2.7815666977,0.22754 & R(-3)m
    ↪ D_{3d}^5 #166 (c) & hR2 & A7 & As & alpha & D. Schiferl and C.
    ↪ S. Barrett, J. App. Cryst. 2, 30-36 (1969)
   1.0000000000000000
   1.87975000000000   -1.08527416850900    3.48576666666700
   0.00000000000000    2.17054833701800    3.48576666666700
  -1.87975000000000   -1.08527416850900    3.48576666666700
   As
    2
Direct
   0.22754000000000    0.22754000000000    0.22754000000000    As    (2c)
   0.77246000000000    0.77246000000000    0.77246000000000    As    (2c)
```

β-Po (A_i): A_hR1_166_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Polonium'
_chemical_formula_sum 'Po'

loop_
_publ_author_name
 'William H. Beamer'
 'Charles R. Maxwell'
_journal_name_full
;
Journal of Chemical Physics
;
_journal_volume 17
_journal_year 1949
_journal_page_first 1293
_journal_page_last 1298
_publ_Section_title
;
 Physical Properties of Polonium. II. X-Ray Studies and Crystal
    ↪ Structure
;

# Found in  Donohue, pp. 392

_aflow_proto 'A_hR1_166_a'
_aflow_params 'a,c/a'
_aflow_params_values '5.07846,0.968139947937'
_aflow_Strukturbericht 'A_i'
_aflow_Pearson 'hR1'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a    5.07846
_cell_length_b    5.07846
_cell_length_c    4.91666
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Po1 Po    3 a 0.00000  0.00000  0.00000  1.00000
```

β-Po (A_i): A_hR1_166_a - POSCAR

```
A_hR1_166_a & a,c/a --params=5.07846,0.968139947937 & R(-3)m    D_{3d}^5
    ↪ #166 (a) & hR1 & A_i & Po & beta & W. H. Beamer and C. R.
    ↪ Maxwell, J. Chem. Phys. 17, 1293-1298 (1949)
   1.0000000000000000
   2.53923164757300   -1.46602607526100    1.63888717934400
   0.00000000000000    2.93205215052200    1.63888717934400
  -2.53923164757300   -1.46602607526100    1.63888717934400
   Po
    1
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Po    (1a)
```

Fe_7W_6 ($D8_5$) μ-phase: A7B6_hR13_166_ah_3c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Frank-Kasper $\mu$ Phase'
_chemical_formula_sum 'Fe7 W6'

loop_
_publ_author_name
 'H. Arnfelt'
_journal_name_full
;
Jernkontorets Annaler
;
_journal_volume 119
_journal_year 1935
_journal_page_first 185
_journal_page_last 187
_publ_Section_title
;
 Crystal Structure of Fe$_7$W$_6$
;

# Found in  Pearson's Handbook, Vol. III, pp. 3415

_aflow_proto 'A7B6_hR13_166_ah_3c'
_aflow_params 'a,c/a,x2,x3,x4,x5,z5'
_aflow_params_values '4.757,5.4319949548,0.167,0.346,0.448,0.09,0.59001'
_aflow_Strukturbericht 'D8_5'
_aflow_Pearson 'hR13'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a    4.75700
_cell_length_b    4.75700
_cell_length_c    25.84000
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
```

```
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Fe1 Fe   3 a 0.00000 0.00000 0.00000 1.00000
W1  W    6 c 0.00000 0.00000 0.16700 1.00000
W2  W    6 c 0.00000 0.00000 0.34600 1.00000
W3  W    6 c 0.00000 0.00000 0.44800 1.00000
Fe2 Fe  18 h 0.83333 0.16667 0.25667 1.00000
```

Fe_7W_6 ($D8_5$) μ-phase: A7B6_hR13_166_ah_3c - POSCAR

```
A7B6_hR13_166_ah_3c & a,c/a,x2,x3,x4,x5,z5 --params=4.757,5.4319949548,
    ↪ 0.167,0.346,0.448,0.09,0.59001 & R(-3)m  D_{3d}^5 #166 (ac^3h
    ↪ ) & hR13 & D8_5 & Fe7W6 & & H. Arnfelt, Jernkontorets Annaler
    ↪ 119, 185-187 (1935), quoted in Pearson's Handbook III, pp. 3415
   1.0000000000000000
   2.37850000000000  -1.37322761526800   8.61333333333300
   0.00000000000000   2.74645523053500   8.61333333333300
  -2.37850000000000  -1.37322761526800   8.61333333333300
   Fe   W
    7   6
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Fe   (1a)
  -0.09000000000000  -0.09000000000000   0.41000000000000   Fe   (6h)
   0.09000000000000   0.09000000000000   0.59000000000000   Fe   (6h)
  -0.09000000000000   0.41000000000000  -0.09000000000000   Fe   (6h)
   0.09000000000000   0.59000000000000   0.09000000000000   Fe   (6h)
   0.41000000000000  -0.09000000000000  -0.09000000000000   Fe   (6h)
   0.59000000000000   0.09000000000000   0.09000000000000   Fe   (6h)
   0.16700000000000   0.16700000000000   0.16700000000000   W    (2c)
   0.83300000000000   0.83300000000000   0.83300000000000   W    (2c)
   0.34600000000000   0.34600000000000   0.34600000000000   W    (2c)
   0.65400000000000   0.65400000000000   0.65400000000000   W    (2c)
   0.44800000000000   0.44800000000000   0.44800000000000   W    (2c)
   0.55200000000000   0.55200000000000   0.55200000000000   W    (2c)
```

α-Sm (C19): A_hR3_166_ac - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha Samarium'
_chemical_formula_sum 'Sm'

loop_
_publ_author_name
 'A. H. Daane'
 'R. E. Rundle'
 'H. G. Smith'
 'F. H. Spedding'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 7
_journal_year 1954
_journal_page_first 532
_journal_page_last 535
_publ_Section_title
;
 The crystal structure of samarium
;

_aflow_proto 'A_hR3_166_ac'
_aflow_params 'a,c/a,x2'
_aflow_params_values '3.62036,7.25049442597,0.22222'
_aflow_Strukturbericht 'C19'
_aflow_Pearson 'hR3'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      3.62036
_cell_length_b      3.62036
_cell_length_c      26.24940
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Sm1 Sm   3 a 0.00000 0.00000 0.00000 1.00000
Sm2 Sm   6 c 0.00000 0.00000 0.22222 1.00000
```

α-Sm (C19): A_hR3_166_ac - POSCAR

```
A_hR3_166_ac & a,c/a,x2 --params=3.62036,7.25049442597,0.22222 & R(-3)m
    ↪  D^5_{3d} #166 (ac) & hR3 & C19 & Sm (alpha) &  & A. H. Daane
    ↪ , R. E. Rundle, H. G. Smith and F. H. Spedding, Acta Cryst. 7,
    ↪ 532-535 (1954)
   1.0000000000000000
   1.81017865060100  -1.04510713120600   8.74980115986700
   0.00000000000000   2.09021426241200   8.74980115986700
  -1.81017865060100  -1.04510713120600   8.74980115986700
   Sm
    3
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Sm   (1a)
   0.22222222222222   0.22222222222222   0.22222222222222   Sm   (2c)
   0.77777777777778   0.77777777777778   0.77777777777778   Sm   (2c)
```

Bi_2Te_3 (C33): A2B3_hR5_166_c_ac - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Bi2 Te3'

loop_
_publ_author_name
 'Paul W. Lange'
_journal_name_full
;
Naturwissenschaften
;
_journal_volume 27
_journal_year 1939
_journal_page_first 133
_journal_page_last 134
_publ_Section_title
;
 Ein Vergleich zwischen Bi$_2$Te$_3$ und Bi$_2$Te$_2$S
;

_aflow_proto 'A2B3_hR5_166_c_ac'
_aflow_params 'a,c/a,x2,x3'
_aflow_params_values '4.36914,6.96313919902,0.399,0.208'
_aflow_Strukturbericht 'C33'
_aflow_Pearson 'hR5'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      4.36914
_cell_length_b      4.36914
_cell_length_c      30.42293
_cell_angle_alpha  90.00000
```

```
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Te1 Te   3 a 0.00000 0.00000 0.00000 1.00000
Bi1 Bi   6 c 0.00000 0.00000 0.39900 1.00000
Te2 Te   6 c 0.00000 0.00000 0.20800 1.00000
```

Bi_2Te_3 (C33): A2B3_hR5_166_c_ac - POSCAR

```
A2B3_hR5_166_c_ac & a,c/a,x2,x3 --params=4.36914,6.96313919902,0.399,
    ↪ 0.208 & R(-3)m    D^5_{3d} #166 (ac^2) & hR5 & C33 & Bi2Te3 & &
    ↪ P. W. Lange, Naturwissenschaften 27, 133-134 (1939)
   1.0000000000000000
   2.18457000000000   -1.26126207756358   10.14097666666875
   0.00000000000000    2.52252415512716   10.14097666666875
  -2.18457000000000   -1.26126207756358   10.14097666666875
   Bi   Te
    2    3
Direct
   0.39900000000000   0.39900000000000   0.39900000000000   Bi   (2c)
   0.60100000000000   0.60100000000000   0.60100000000000   Bi   (2c)
   0.00000000000000   0.00000000000000   0.00000000000000   Te   (1a)
   0.20800000000000   0.20800000000000   0.20800000000000   Te   (2c)
   0.79200000000000   0.79200000000000   0.79200000000000   Te   (2c)
```

α-Hg (A10): A_hR1_166_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha'
_chemical_formula_sum 'Hg'

loop_
_publ_author_name
 'C. S. Barrett'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 10
_journal_year 1957
_journal_page_first 58
_journal_page_last 60
_publ_Section_title
;
 The structure of mercury at low temperatures
;

# Found in  Donohue, pp. 231-233

_aflow_proto 'A_hR1_166_a'
_aflow_params 'a,c/a'
_aflow_params_values '3.45741,1.92728082582'
_aflow_Strukturbericht 'A10'
_aflow_Pearson 'hR1'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a     3.45741
_cell_length_b     3.45741
_cell_length_c     6.66340
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Hg1 Hg   3 a 0.00000 0.00000 0.00000 1.00000
```

α-Hg (A10): A_hR1_166_a - POSCAR

```
A_hR1_166_a & a,c/a --params=3.45741,1.92728082582 & R(-3)m    D_{3d}^
    ↪ 5 #166 (a) & hR1 & A10 & Hg & alpha-Hg & C. S. Barrett, Acta
    ↪ Cryst. 10, 58-60 (1957)
   1.0000000000000000
   1.72870340938900   -0.99806737876000   2.22113343134200
   0.00000000000000    1.99613475751900   2.22113343134200
  -1.72870340938900   -0.99806737876000   2.22113343134200
   Po
    1
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Hg   (1a)
```

Mo_2B_5 ($D8_i$): A5B2_hR7_166_a2c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Molybdenum Boride'
_chemical_formula_sum 'Mo2 B5'

loop_
_publ_author_name
 'Roland Kiessling'
_journal_name_full
;
Acta Chemica Scandinavica
;
_journal_volume 1
_journal_year 1947
_journal_page_first 893
_journal_page_last 916
_publ_Section_title
;
 The Crystal Structures of Molybdenum and Tungsten Borides
;
```

```
_aflow_proto 'A5B2_hR7_166_a2c_c'
_aflow_params 'a,c/a,x2,x3,x4'
_aflow_params_values '3.011,6.9511790103,0.186,0.33333,0.075'
_aflow_Strukturbericht 'D8_i'
_aflow_Pearson 'hR7'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      3.01100
_cell_length_b      3.01100
_cell_length_c      20.93000
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1  B   3 a 0.00000 0.00000 0.00000 1.00000
B2  B   6 c 0.00000 0.00000 0.18600 1.00000
B3  B   6 c 0.00000 0.00000 0.33333 1.00000
Mo1 Mo  6 c 0.00000 0.00000 0.07500 1.00000
```

Mo_2B_5 ($D8_i$): A5B2_hR7_166_a2c_c - POSCAR

```
A5B2_hR7_166_a2c_c & a,c/a,x2,x3,x4 --params=3.011,6.9511790103,0.186,
    ↪ 0.33333,0.075 & R(-3)m D_{3d}^5 #166 (ac^3) & hR7 & D8_i &
    ↪ Mo2B5 & epsilon & R Kiessling, Acta Chem. Scand. 1, 893-916 (
    ↪ 1947)
   1.0000000000000000
   1.50550000000000  -0.86920083026498   6.97666666666667
   0.00000000000000   1.73840166052996   6.97666666666667
  -1.50550000000000  -0.86920083026498   6.97666666666667
    B   Mo
    5   2
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   B   (1a)
   0.18600000000000   0.18600000000000   0.18600000000000   B   (2c)
   0.81400000000000   0.81400000000000   0.81400000000000   B   (2c)
   0.33333333333333   0.33333333333333   0.33333333333333   B   (2c)
   0.66666666666667   0.66666666666667   0.66666666666667   B   (2c)
   0.07500000000000   0.07500000000000   0.07500000000000  Mo   (2c)
   0.92500000000000   0.92500000000000   0.92500000000000  Mo   (2c)
```

Rhombohedral Graphite: A_hR2_166_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'rhombohedral graphite'
_chemical_formula_sum 'C'

loop_
_publ_author_name
 'H. Lipson'
 'A. R. Stokes'
_journal_name_full
;
Proceedings of the Royal Society A: Mathematical, Physical and
    ↪ Engineering Sciences
;
_journal_volume 181
_journal_year 1942
_journal_page_first 101
_journal_page_last 105
_publ_Section_title
;
 The structure of graphite
;

# Found in  Donohue, pp. 258-260

_aflow_proto 'A_hR2_166_c'
_aflow_params 'a,c/a,x1'
_aflow_params_values '2.456,4.08957654723,0.16667'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR2'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      2.45600
_cell_length_b      2.45600
_cell_length_c      10.04400
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1 C   6 c 0.00000 0.00000 0.16667 1.00000
```

Rhombohedral Graphite: A_hR2_166_c - POSCAR

```
A_hR2_166_c & a,c/a,x1 --params=2.456,4.08957654723,0.16667 & R(-3)m
    ↪ D_{3d}^5 #166 (c) & hR2 & & C & rhombohedral graphite & H.
    ↪ Lipson and A. R. Stokes, Proc. R. Soc. A Math. Phys. Eng. Sci.
    ↪ 181, 101-105 (1942)
   1.0000000000000000
   1.22800000000000  -0.70898613056486   3.34800000000000
   0.00000000000000   1.41797226112972   3.34800000000000
  -1.22800000000000  -0.70898613056486   3.34800000000000
    C
    2
Direct
   0.16666666666667   0.16666666666667   0.16666666666667   C   (2c)
   0.83333333333333   0.83333333333333   0.83333333333333   C   (2c)
```

α-B (hR12): A_hR12_166_2h - CIF

```
# CIF file
```

```
data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha boron'
_chemical_formula_sum 'B'

loop_
_publ_author_name
 'B. F. Decker'
 'J. S. Kasper'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 12
_journal_year 1959
_journal_page_first 503
_journal_page_last 506
_publ_Section_title
;
 The crystal structure of a simple rhombohedral form of boron
;

# Found in  Donohue, pp. 57-60

_aflow_proto 'A_hR12_166_2h'
_aflow_params 'a,c/a,x1,z1,x2,z2'
_aflow_params_values '4.908,2.56022616137,0.0104,0.65729,0.2206,0.6323'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR12'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      4.90800
_cell_length_b      4.90800
_cell_length_c      12.56559
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1 B   18 h 0.78437 0.21563 0.22603 1.00000
B2 B   18 h 0.19610 0.80390 0.02450 1.00000
```

α-B (hR12): A_hR12_166_2h - POSCAR

```
A_hR12_166_2h & a,c/a,x1,z1,x2,z2 --params=4.908,2.56022616137,0.0104,
    ↪ 0.65729,0.2206,0.6323 & R(-3)m     D_{3d}^5 #166 (h^2) & hR12 &
    ↪ & B & alpha & B. F. Decker and J. S. Kasper, Acta Cryst. 12,
    ↪ 503-506 (1959)
   1.0000000000000000
   2.45399776558700   -1.41681627055200    4.18852905230400
   0.00000000000000    2.83363254110400    4.18852905230400
  -2.45399776558700   -1.41681627055200    4.18852905230400
    B
   12
Direct
  -0.01040000000000  -0.01040000000000   0.34270000000000   B   (6h)
   0.01040000000000   0.01040000000000   0.65730000000000   B   (6h)
  -0.01040000000000   0.34270000000000  -0.01040000000000   B   (6h)
   0.01040000000000   0.65730000000000   0.01040000000000   B   (6h)
   0.34270000000000  -0.01040000000000  -0.01040000000000   B   (6h)
   0.65730000000000   0.01040000000000   0.01040000000000   B   (6h)
   0.22060000000000   0.22060000000000   0.63230000000000   B   (6h)
   0.22060000000000   0.63230000000000   0.22060000000000   B   (6h)
   0.36770000000000   0.77940000000000   0.77940000000000   B   (6h)
   0.63230000000000   0.22060000000000   0.22060000000000   B   (6h)
   0.77940000000000   0.36770000000000   0.77940000000000   B   (6h)
   0.77940000000000   0.77940000000000   0.36770000000000   B   (6h)
```

Caswellsilverite ($CrNaS_2$, $F5_1$): ABC2_hR4_166_a_b_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Caswellsilverite'
_chemical_formula_sum 'Cr Na S2'

loop_
_publ_author_name
 'F. M. R. Engelsman'
 'G. A. Wiegers'
 'F. Jellinek'
 'B. Van Laar'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 6
_journal_year 1973
_journal_page_first 574
_journal_page_last 582
_publ_Section_title
;
 Crystal structures and magnetic structures of some metal(I) chromium(
    ↪ III) sulfides and selenides
;

# Found in  AMS Database

_aflow_proto 'ABC2_hR4_166_a_b_c'
_aflow_params 'a,c/a,x3'
_aflow_params_values '3.5561,5.44557239673,0.2667'
_aflow_Strukturbericht 'F5_1'
_aflow_Pearson 'hR4'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      3.55610
_cell_length_b      3.55610
_cell_length_c      19.36500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
```

```
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1  Cr    3  a  0.00000  0.00000  0.00000  1.00000
Na1  Na    3  b  0.00000  0.00000  0.50000  1.00000
S1   S     6  c  0.00000  0.00000  0.26670  1.00000
```

Caswellsilverite ($CrNaS_2$, $F5_1$): ABC2_hR4_166_a_b_c - POSCAR

```
ABC2_hR4_166_a_b_c & a,c/a,x3 --params=3.5561,5.44557239673,0.2667 & R(-
    ↪ 3)m    D_{3d}^5 #166 (abc) & hR4 & F5_1 & CrNaS2 &
    ↪ Caswellsilverite & F. M. R. Engelsman, G. A. Wiegers, F.
    ↪ Jellinek, and B. van Laar, J. Solid State Chem. 6, 574-582 (
    ↪ 1973)
   1.0000000000000000
   1.77805000000000   -1.02655764613300    6.45500000000000
   0.00000000000000    2.05311529226500    6.45500000000000
  -1.77805000000000   -1.02655764613300    6.45500000000000
   Cr    Na    S
    1     1     2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cr    (1a)
   0.50000000000000    0.50000000000000    0.50000000000000    Na    (1b)
   0.26670000000000    0.26670000000000    0.26670000000000     S    (2c)
   0.73330000000000    0.73330000000000    0.73330000000000     S    (2c)
```

β-O: A_hR2_166_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta oxygen'
_chemical_formula_sum 'O'

loop_
_publ_author_name
 'R. J. Meier'
 'R. B. Helmholdt'
_journal_name_full
;
Physical Review B
;
_journal_volume 29
_journal_year 1984
_journal_page_first 1387
_journal_page_last 1393
_publ_Section_title
;
 Neutron-diffraction study of $\alpha$- and $\beta$-oxygen
;

_aflow_proto 'A_hR2_166_c'
_aflow_params 'a,c/a,x1'
_aflow_params_values '3.289,3.42991790818,0.0543'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR2'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      3.28900
_cell_length_b      3.28900
_cell_length_c      11.28100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1 O    6 c 0.00000 0.00000 0.05430 1.00000
```

β-O: A_hR2_166_c - POSCAR

```
A_hR2_166_c & a,c/a,x1 --params=3.289,3.42991790818,0.0543 & R(-3)m
    ↪ D_{3d}^5 #166 (c) & hR2 & & O & beta & R. J. Meier and R. B.
    ↪ Helmholdt, PRB 29, 1387-1393 (1984)
   1.0000000000000000
   1.64450000000000   -0.94945251768200    3.76033333333300
   0.00000000000000    1.89890503536500    3.76033333333300
  -1.64450000000000   -0.94945251768200    3.76033333333300
    O
    2
Direct
   0.05430000000000    0.05430000000000    0.05430000000000    O    (2c)
  -0.05430000000000   -0.05430000000000   -0.05430000000000    O    (2c)
```

β-B (R-105): A_hR105_166_bc9h4i - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Boron'
_chemical_formula_sum 'B'

loop_
_publ_author_name
 'D. Geist'
 'R. Kloss'
 'H. Follner'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 26
_journal_year 1970
_journal_page_first 1800
_journal_page_last 1802
_publ_Section_title
;
 Verfeinerung des $\beta$-rhomboedrischen Bors
;

# Found in  Donohue, pp. 61-78

_aflow_proto 'A_hR105_166_bc9h4i'
_aflow_params 'a,c/a,x2,x3,z3,x4,z4,x5,z5,x6,z6,x7,z7,x8,z8,x9,z9,x10,
    ↪ z10,x11,z11,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15'
_aflow_params_values '10.96,2.17974452555,0.3848,0.3843,0.21309,0.4895,
    ↪ 0.21780,0.3873,0.56899,0.1991,0.50609,0.1983,0.68740,0.1032,
    ↪ 0.49209,0.9933,0.66980,0.1008,0.83740,0.0025,0.16801,0.3622,
    ↪ 0.58109,0.0976,0.3765,0.68261,0.2024,0.1673,0.55209,0.8921,
    ↪ 0.1777,0.3473,0.0033'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR105'

_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      10.96000
_cell_length_b      10.96000
_cell_length_c      23.89000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
```

```
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1  B   3 b 0.00000  0.00000  0.50000 1.00000
B2  B   6 c 0.00000  0.00000  0.38480 1.00000
B3  B  18 h 0.05707 -0.05707 0.32723 1.00000
B4  B  18 h 0.42390  0.57610  0.06560 1.00000
B5  B  18 h 0.27277  0.72723  0.11453 1.00000
B6  B  18 h 0.89767  0.10233  0.30143 1.00000
B7  B  18 h 0.17030  0.82970  0.02800 1.00000
B8  B  18 h 0.87037  0.12963  0.23283 1.00000
B9  B  18 h 0.77450  0.22550  0.21880 1.00000
B10 B  18 h 0.08780 -0.08780 0.01300 1.00000
B11 B  18 h -0.05517 0.05517  0.05767 1.00000
B12 B  36 i 0.34857 -0.08397 0.01363 1.00000
B13 B  36 i 0.28933  0.88477  0.08717 1.00000
B14 B  36 i -0.03653 0.31173  0.20383 1.00000
B15 B  36 i 0.00160  0.17280  0.17610 1.00000
```

β-B (R-105): A_hR105_166_bc9h4i - POSCAR

```
A_hR105_166_bc9h4i & a,c/a,x2,x3,z3,x4,z4,x5,z5,x6,z6,x7,z7,x8,z8,x9,z9,
    ↪ x10,z10,x11,z11,x12,y12,z12,x13,y13,z13,x14,y14,z14,x15,y15,z15
    ↪  --params=10.96,2.17974452555,0.3848,0.3843,0.21309,0.4895,
    ↪ 0.21780,0.3873,0.56899,0.1991,0.50609,0.1983,0.68740,0.1032,
    ↪ 0.49209,0.9933,0.66980,0.1008,0.83740,0.0025,0.16801,0.3622,
    ↪ 0.58109,0.0976,0.3765,0.68261,0.2024,0.1673,0.55209,0.8921,
    ↪ 0.1777,0.3473,0.0033 & R(-3)m        D_{3d}^5 #166 (bch^9i^4) &
    ↪ hR105 & & B & beta (R-105) & D. Geist, R. Kloss and H. Follner,
    ↪  Acta Cryst. B 26, 1800-1802 (1970)
  1.0000000000000000
  5.47929888352000  -3.16347468537100  7.96232451361300
  0.00000000000000   6.32694937074100  7.96232451361300
 -5.47929888352000  -3.16347468537100  7.96232451361300
   B
  105
Direct
  0.09760000000000  0.36220000000000  0.58110000000000  B  (12i)
 -0.09760000000000  0.41890000000000  0.63780000000000  B  (12i)
  0.09760000000000  0.58110000000000  0.36220000000000  B  (12i)
 -0.09760000000000  0.63780000000000  0.41890000000000  B  (12i)
  0.36220000000000  0.09760000000000  0.58110000000000  B  (12i)
  0.36220000000000  0.58110000000000  0.09760000000000  B  (12i)
  0.41890000000000 -0.09760000000000  0.63780000000000  B  (12i)
  0.41890000000000  0.63780000000000 -0.09760000000000  B  (12i)
  0.58110000000000  0.09760000000000  0.36220000000000  B  (12i)
  0.58110000000000  0.36220000000000  0.09760000000000  B  (12i)
  0.63780000000000 -0.09760000000000  0.41890000000000  B  (12i)
  0.63780000000000  0.41890000000000 -0.09760000000000  B  (12i)
  0.20240000000000  0.37650000000000  0.68260000000000  B  (12i)
  0.20240000000000  0.68260000000000  0.37650000000000  B  (12i)
  0.31740000000000  0.62350000000000  0.79760000000000  B  (12i)
  0.31740000000000  0.79760000000000  0.62350000000000  B  (12i)
  0.37650000000000  0.20240000000000  0.68260000000000  B  (12i)
  0.37650000000000  0.68260000000000  0.20240000000000  B  (12i)
  0.62350000000000  0.31740000000000  0.79760000000000  B  (12i)
  0.62350000000000  0.79760000000000  0.31740000000000  B  (12i)
  0.68260000000000  0.20240000000000  0.37650000000000  B  (12i)
  0.68260000000000  0.37650000000000  0.20240000000000  B  (12i)
  0.79760000000000  0.31740000000000  0.62350000000000  B  (12i)
  0.79760000000000  0.62350000000000  0.31740000000000  B  (12i)
  0.10790000000000  0.44790000000000  0.83270000000000  B  (12i)
  0.10790000000000  0.83270000000000  0.44790000000000  B  (12i)
  0.16730000000000  0.55210000000000  0.89210000000000  B  (12i)
  0.16730000000000  0.89210000000000  0.55210000000000  B  (12i)
  0.44790000000000  0.10790000000000  0.83270000000000  B  (12i)
  0.44790000000000  0.83270000000000  0.10790000000000  B  (12i)
  0.55210000000000  0.16730000000000  0.89210000000000  B  (12i)
  0.55210000000000  0.89210000000000  0.16730000000000  B  (12i)
  0.83270000000000  0.10790000000000  0.44790000000000  B  (12i)
  0.83270000000000  0.44790000000000  0.10790000000000  B  (12i)
  0.89210000000000  0.16730000000000  0.55210000000000  B  (12i)
  0.89210000000000  0.55210000000000  0.16730000000000  B  (12i)
  0.00330000000000  0.17770000000000  0.34730000000000  B  (12i)
  0.00330000000000  0.34730000000000  0.17770000000000  B  (12i)
 -0.00330000000000  0.65270000000000  0.82230000000000  B  (12i)
 -0.00330000000000  0.82230000000000  0.65270000000000  B  (12i)
  0.17770000000000  0.00330000000000  0.34730000000000  B  (12i)
  0.17770000000000  0.34730000000000  0.00330000000000  B  (12i)
  0.34730000000000  0.00330000000000  0.17770000000000  B  (12i)
  0.34730000000000  0.17770000000000  0.00330000000000  B  (12i)
  0.65270000000000 -0.00330000000000  0.82230000000000  B  (12i)
  0.65270000000000  0.82230000000000 -0.00330000000000  B  (12i)
  0.82230000000000 -0.00330000000000  0.65270000000000  B  (12i)
  0.82230000000000  0.65270000000000 -0.00330000000000  B  (12i)
  0.50000000000000  0.50000000000000  0.50000000000000  B  (1b)
  0.38480000000000  0.38480000000000  0.38480000000000  B  (2c)
  0.61520000000000  0.61520000000000  0.61520000000000  B  (2c)
  0.10080000000000  0.10080000000000  0.83740000000000  B  (6h)
  0.10080000000000  0.83740000000000  0.10080000000000  B  (6h)
  0.16260000000000  0.89920000000000  0.89920000000000  B  (6h)
  0.83740000000000  0.10080000000000  0.10080000000000  B  (6h)
  0.89920000000000  0.16260000000000  0.89920000000000  B  (6h)
  0.89920000000000  0.89920000000000  0.16260000000000  B  (6h)
  0.00250000000000  0.00250000000000  0.16800000000000  B  (6h)
 -0.00250000000000 -0.00250000000000  0.83200000000000  B  (6h)
  0.00250000000000  0.16800000000000  0.00250000000000  B  (6h)
 -0.00250000000000  0.83200000000000 -0.00250000000000  B  (6h)
  0.16800000000000  0.00250000000000  0.00250000000000  B  (6h)
  0.83200000000000 -0.00250000000000 -0.00250000000000  B  (6h)
  0.21310000000000  0.38430000000000  0.38430000000000  B  (6h)
  0.38430000000000  0.21310000000000  0.38430000000000  B  (6h)
  0.38430000000000  0.38430000000000  0.21310000000000  B  (6h)
  0.61570000000000  0.61570000000000  0.78690000000000  B  (6h)
  0.61570000000000  0.78690000000000  0.61570000000000  B  (6h)
  0.78690000000000  0.61570000000000  0.61570000000000  B  (6h)
  0.21780000000000  0.48950000000000  0.48950000000000  B  (6h)
  0.48950000000000  0.21780000000000  0.48950000000000  B  (6h)
  0.48950000000000  0.48950000000000  0.21780000000000  B  (6h)
  0.51050000000000  0.51050000000000  0.78220000000000  B  (6h)
  0.51050000000000  0.78220000000000  0.51050000000000  B  (6h)
  0.78220000000000  0.51050000000000  0.51050000000000  B  (6h)
  0.38730000000000  0.38730000000000  0.56900000000000  B  (6h)
  0.38730000000000  0.56900000000000  0.38730000000000  B  (6h)
  0.43100000000000  0.61270000000000  0.61270000000000  B  (6h)
  0.56900000000000  0.38730000000000  0.38730000000000  B  (6h)
  0.61270000000000  0.43100000000000  0.61270000000000  B  (6h)
  0.61270000000000  0.61270000000000  0.43100000000000  B  (6h)
  0.19910000000000  0.19910000000000  0.50610000000000  B  (6h)
  0.19910000000000  0.50610000000000  0.19910000000000  B  (6h)
  0.49390000000000  0.80090000000000  0.80090000000000  B  (6h)
  0.50610000000000  0.19910000000000  0.19910000000000  B  (6h)
  0.80090000000000  0.49390000000000  0.80090000000000  B  (6h)
  0.80090000000000  0.80090000000000  0.49390000000000  B  (6h)
  0.19830000000000  0.19830000000000  0.68740000000000  B  (6h)
  0.19830000000000  0.68740000000000  0.19830000000000  B  (6h)
  0.31260000000000  0.80170000000000  0.80170000000000  B  (6h)
  0.68740000000000  0.19830000000000  0.19830000000000  B  (6h)
  0.80170000000000  0.31260000000000  0.80170000000000  B  (6h)
  0.80170000000000  0.80170000000000  0.31260000000000  B  (6h)
  0.10320000000000  0.10320000000000  0.49210000000000  B  (6h)
  0.10320000000000  0.49210000000000  0.10320000000000  B  (6h)
  0.49210000000000  0.10320000000000  0.10320000000000  B  (6h)
  0.50790000000000  0.89680000000000  0.89680000000000  B  (6h)
  0.89680000000000  0.50790000000000  0.89680000000000  B  (6h)
  0.89680000000000  0.89680000000000  0.50790000000000  B  (6h)
  0.00670000000000  0.00670000000000  0.33020000000000  B  (6h)
 -0.00670000000000 -0.00670000000000  0.66980000000000  B  (6h)
  0.00670000000000  0.33020000000000  0.00670000000000  B  (6h)
 -0.00670000000000  0.66980000000000 -0.00670000000000  B  (6h)
  0.33020000000000  0.00670000000000  0.00670000000000  B  (6h)
  0.66980000000000 -0.00670000000000 -0.00670000000000  B  (6h)
```

CaC_6: A6B_hR7_166_g_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ca C6'

loop_
_publ_author_name
 'N. Emery'
 'C. H\'{e}rold'
 'M. d'Astuto'
 'V. Garcia'
 'Ch. Bellin'
 'J. F. Mar\^{e}ch\'{e}'
 'P. Lagrange,'
 'G. Loupias'
_journal_name_full
;
Physical Review Letters
;
_journal_volume 95
_journal_year 2005
_journal_page_first 087003
_journal_page_last 087003
_publ_Section_title
;
 Superconductivity of Bulk CaC6
;

_aflow_proto 'A6B_hR7_166_g_a'
_aflow_params 'a,c/a,x2'
_aflow_params_values '4.33304,3.13251204697,0.16667'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR7'
```

```
_symmetry_space_group_name_Hall "-R 3 2"
_symmetry_space_group_name_H-M "R -3 m:H"
_symmetry_Int_Tables_number 166

_cell_length_a      4.33304
_cell_length_b      4.33304
_cell_length_c      13.57330
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z
5 -x,-x+y,-z
6 x-y,-y,-z
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z
11 x,x-y,z
12 -x+y,y,z
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+2/3
17 -x+1/3,-x+y+2/3,-z+2/3
18 x-y+1/3,-y+2/3,-z+2/3
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+2/3
23 x+1/3,x-y+2/3,z+2/3
24 -x+y+1/3,y+2/3,z+2/3
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+1/3
29 -x+2/3,-x+y+1/3,-z+1/3
30 x-y+2/3,-y+1/3,-z+1/3
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+1/3
35 x+2/3,x-y+1/3,z+1/3
36 -x+y+2/3,y+1/3,z+1/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ca1 Ca   3 a 0.00000 0.00000 0.00000 1.00000
C1  C   18 g 0.66667 0.00000 0.50000 1.00000
```

CaC_6: A6B_hR7_166_g_a - POSCAR

```
A6B_hR7_166_g_a & a,c/a,x2 --params=4.33304,3.13251204697,0.16667 & R(-3
    ↪ )m    D_{3d}^5 #166 (ag) & hR7 & & CaC6 & & Emery et al. PRB 95
    ↪ , 087003 (2005)
   1.0000000000000000
   2.16651926089496   -1.25084047848222    4.52443282517947
   0.00000000000000    2.50168095696443    4.52443282517947
  -2.16651926089496   -1.25084047848222    4.52443282517947
    C    Ca
    6     1
Direct
   0.16666666666667    0.50000000000000    0.83333333333333    C    (6g)
   0.16666666666667    0.83333333333333    0.50000000000000    C    (6g)
   0.50000000000000    0.16666666666667    0.83333333333333    C    (6g)
   0.50000000000000    0.83333333333333    0.16666666666667    C    (6g)
   0.83333333333333    0.16666666666667    0.50000000000000    C    (6g)
   0.83333333333333    0.50000000000000    0.16666666666667    C    (6g)
   0.00000000000000    0.00000000000000    0.00000000000000   Ca    (1a)
```

Paraelectric $LiNbO_3$: ABC3_hR10_167_a_b_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Li Nb O3'

loop_
_publ_author_name
 'H. Boysen'
 'F. Altorfer'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 50
_journal_year 1994
_journal_page_first 405
_journal_page_last 414
_publ_Section_title
;
 A neutron powder investigation of the high-temperature structure and
    ↪ phase transition in LiNbO$_3$
;

_aflow_proto 'ABC3_hR10_167_a_b_e'
_aflow_params 'a,c/a,x3'
_aflow_params_values '5.285,2.62039735099,0.85756666666667'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hR10'

_symmetry_space_group_name_Hall "-R 3 2c"
_symmetry_space_group_name_H-M "R -3 c:H"
_symmetry_Int_Tables_number 167

_cell_length_a      5.28500
_cell_length_b      5.28500
_cell_length_c      13.84880
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z+1/2
5 -x,-x+y,-z+1/2
6 x-y,-y,-z+1/2
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z+1/2
11 x,x-y,z+1/2
12 -x+y,y,z+1/2
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+1/6
17 -x+1/3,-x+y+2/3,-z+1/6
18 x-y+1/3,-y+2/3,-z+1/6
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+1/6
23 x+1/3,x-y+2/3,z+1/6
24 -x+y+1/3,y+2/3,z+1/6
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+5/6
29 -x+2/3,-x+y+1/3,-z+5/6
30 x-y+2/3,-y+1/3,-z+5/6
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+5/6
35 x+2/3,x-y+1/3,z+5/6
36 -x+y+2/3,y+1/3,z+5/6

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Li1 Li   6 a 0.00000 0.00000 0.25000 1.00000
Nb1 Nb   6 b 0.00000 0.00000 0.00000 1.00000
O1  O   18 e 0.39243 0.00000 0.25000 1.00000
```

Paraelectric $LiNbO_3$: ABC3_hR10_167_a_b_e - POSCAR

```
ABC3_hR10_167_a_b_e & a,c/a,x3 --params=5.285,2.62039735099,
    ↪ 0.85756666666667 & R(-3)c    D_{3d}^6 #167 (abe) & hR10 & &
    ↪ LiNbO3 & Paraelectric & H. Boysen and F. Altorfer, Acta Cryst.
    ↪ B 50, 405-414 (1994)
   1.0000000000000000
   2.64250000000000   -1.52564808633359    4.61626666666072
   0.00000000000000    3.05129617266717    4.61626666666072
  -2.64250000000000   -1.52564808633359    4.61626666666072
    Li    Ni    O
     2     2    6
Direct
   0.25000000000000    0.25000000000000    0.25000000000000   Li    (2a)
   0.75000000000000    0.75000000000000    0.75000000000000   Li    (2a)
   0.00000000000000    0.00000000000000    0.00000000000000   Nb    (2b)
   0.50000000000000    0.50000000000000    0.50000000000000   Nb    (2b)
   0.14243333333333    0.35756666666667    0.75000000000000    O    (6e)
   0.25000000000000    0.85756666666667    0.64243333333333    O    (6e)
   0.35756666666667    0.75000000000000    0.14243333333333    O    (6e)
   0.64243333333333    0.25000000000000    0.85756666666667    O    (6e)
   0.75000000000000    0.14243333333333    0.35756666666667    O    (6e)
   0.85756666666667    0.64243333333333    0.25000000000000    O    (6e)
```

Calcite ($CaCO_3$, $G0_1$): ABC3_hR10_167_a_b_e - CIF

```
# CIF file
```

```
data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Calcite'
_chemical_formula_sum 'Ca C O3'

loop_
_publ_author_name
 'S. A. Markgraf'
 'R. J. Reeder'
_journal_name_full
;
American Mineralogist
;
_journal_volume 70
_journal_year 1985
_journal_page_first 590
_journal_page_last 600
_publ_Section_title
;
 High-temperature structure refinements of calcite and magnesite
;

# Found in AMS Database

_aflow_proto 'ABC3_hR10_167_a_b_e'
_aflow_params 'a,c/a,x3'
_aflow_params_values '4.988,3.42040898156,0.5067'
_aflow_Strukturbericht 'G0_1'
_aflow_Pearson 'hR10'

_symmetry_space_group_name_Hall "-R 3 2c"
_symmetry_space_group_name_H-M "R -3 c:H"
_symmetry_Int_Tables_number 167

_cell_length_a      4.98800
_cell_length_b      4.98800
_cell_length_c      17.06100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z+1/2
5 -x,-x+y,-z+1/2
6 x-y,-y,-z+1/2
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z+1/2
11 x,x-y,z+1/2
12 -x+y,y,z+1/2
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+1/6
17 -x+1/3,-x+y+2/3,-z+1/6
18 x-y+1/3,-y+2/3,-z+1/6
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+1/6
23 x+1/3,x-y+2/3,z+1/6
24 -x+y+1/3,y+2/3,z+1/6
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+5/6
29 -x+2/3,-x+y+1/3,-z+5/6
30 x-y+2/3,-y+1/3,-z+5/6
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+5/6
35 x+2/3,x-y+1/3,z+5/6
36 -x+y+2/3,y+1/3,z+5/6

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    6 a 0.00000 0.00000 0.25000 1.00000
Ca1 Ca   6 b 0.00000 0.00000 0.00000 1.00000
O1  O   18 e 0.74330 0.00000 0.25000 1.00000
```

Calcite ($CaCO_3$, $G0_1$): ABC3_hR10_167_a_b_e - POSCAR

```
ABC3_hR10_167_a_b_e & a,c/a,x3 --params=4.988,3.42040898156,0.5067 & R(-
    ↪ 3)c     D^{6}_{3d} #167 (abe) & hR10 & G0_1 & CaCO3 & Calcite &
    ↪ S. A. Markgraf and R. J. Reeder, Am. Mineral. 70, 590-600 (1985
    ↪ )
   1.0000000000000000
   2.49400000000000   -1.43991157135900    5.68700000000000
   0.00000000000000    2.87982314271800    5.68700000000000
  -2.49400000000000   -1.43991157135900    5.68700000000000
     C    Ca     O
     2     2     6
Direct
   0.25000000000000   0.25000000000000   0.25000000000000    C    (2a)
   0.75000000000000   0.75000000000000   0.75000000000000    C    (2a)
   0.00000000000000   0.00000000000000   0.00000000000000   Ca    (2b)
   0.50000000000000   0.50000000000000   0.50000000000000   Ca    (2b)
  -0.00670000000000   0.25000000000000   0.50670000000000    O    (6e)
   0.00670000000000   0.75000000000000   0.49330000000000    O    (6e)
   0.25000000000000   0.50670000000000  -0.00670000000000    O    (6e)
   0.49330000000000   0.00670000000000   0.75000000000000    O    (6e)
   0.50670000000000  -0.00670000000000   0.25000000000000    O    (6e)
   0.75000000000000   0.49330000000000   0.00670000000000    O    (6e)
```

Corundum (Al_2O_3, $D5_1$): A2B3_hR10_167_c_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Corundum'
_chemical_formula_sum 'Al2 O3'

loop_
_publ_author_name
 'Larry W. Finger'
 'Robert M. Hazen'
_journal_name_full
;
Journal of Applied Physics
;
_journal_volume 49
_journal_year 1978
_journal_page_first 5823
_journal_page_last 5826
_publ_Section_title
;
 Crystal structure and compression of ruby to 46 kbar
;

_aflow_proto 'A2B3_hR10_167_c_e'
_aflow_params 'a,c/a,x1,x2'
_aflow_params_values '4.7607,2.72957758313,0.35216,0.5561'
_aflow_Strukturbericht 'D5_1'
_aflow_Pearson 'hR10'

_symmetry_space_group_name_Hall "-R 3 2c"
_symmetry_space_group_name_H-M "R -3 c:H"
_symmetry_Int_Tables_number 167

_cell_length_a      4.76070
_cell_length_b      4.76070
_cell_length_c      12.99470
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 y,x,-z+1/2
5 -x,-x+y,-z+1/2
6 x-y,-y,-z+1/2
7 -x,-y,-z
8 y,-x+y,-z
9 x-y,x,-z
10 -y,-x,z+1/2
11 x,x-y,z+1/2
12 -x+y,y,z+1/2
13 x+1/3,y+2/3,z+2/3
14 -y+1/3,x-y+2/3,z+2/3
15 -x+y+1/3,-x+2/3,z+2/3
16 y+1/3,x+2/3,-z+1/6
17 -x+1/3,-x+y+2/3,-z+1/6
18 x-y+1/3,-y+2/3,-z+1/6
19 -x+1/3,-y+2/3,-z+2/3
20 y+1/3,-x+y+2/3,-z+2/3
21 x-y+1/3,x+2/3,-z+2/3
22 -y+1/3,-x+2/3,z+1/6
23 x+1/3,x-y+2/3,z+1/6
24 -x+y+1/3,y+2/3,z+1/6
25 x+2/3,y+1/3,z+1/3
26 -y+2/3,x-y+1/3,z+1/3
27 -x+y+2/3,-x+1/3,z+1/3
28 y+2/3,x+1/3,-z+5/6
29 -x+2/3,-x+y+1/3,-z+5/6
30 x-y+2/3,-y+1/3,-z+5/6
31 -x+2/3,-y+1/3,-z+1/3
32 y+2/3,-x+y+1/3,-z+1/3
33 x-y+2/3,x+1/3,-z+1/3
34 -y+2/3,-x+1/3,z+5/6
35 x+2/3,x-y+1/3,z+5/6
36 -x+y+2/3,y+1/3,z+5/6

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
```

```
_atom_site_fract_z
_atom_site_occupancy
Al1  Al   12  c  0.00000  0.00000  0.35216  1.00000
O1   O    18  e  0.30610  0.00000  0.25000  1.00000
```

Corundum (Al_2O_3, $D5_1$): A2B3_hR10_167_c_e - POSCAR

```
A2B3_hR10_167_c_e & a,c/a,x1,x2 --params=4.7607,2.72957758313,0.35216,
    ↪ 0.5561 & R(-3)c     D^{6}_{3d} #167 (ce) & hR10 & D5_1 & Al2O3 &
    ↪  Corundum & L. W. Finger and R. M. Hazen, J. Appl. Phys. 49,
    ↪ 5823-5826 (1976)
   1.0000000000000000
   2.38035000000000   -1.37429571326600    4.33156666666700
   0.00000000000000    2.74859142653100    4.33156666666700
  -2.38035000000000   -1.37429571326600    4.33156666666700
   Al    O
    4    6
Direct
   0.14784000000000    0.14784000000000    0.14784000000000    Al    (4c)
   0.35216000000000    0.35216000000000    0.35216000000000    Al    (4c)
   0.64784000000000    0.64784000000000    0.64784000000000    Al    (4c)
   0.85216000000000    0.85216000000000    0.85216000000000    Al    (4c)
  -0.05610000000000    0.25000000000000    0.55610000000000    O     (6e)
   0.05610000000000    0.75000000000000    0.44390000000000    O     (6e)
   0.25000000000000    0.55610000000000   -0.05610000000000    O     (6e)
   0.44390000000000    0.05610000000000    0.75000000000000    O     (6e)
   0.55610000000000   -0.05610000000000    0.25000000000000    O     (6e)
   0.75000000000000    0.44390000000000    0.05610000000000    O     (6e)
```

Mg_2Ni (C_a): A2B_hP18_180_fi_bd - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Mg2 Ni'

loop_
_publ_author_name
 'J. Schefer'
 'P. Fischer'
 'W. H\"{a}lg'
 'F. Stucki'
 'L. Schlapbach'
 'J. J. Didisheim'
 'K. Yvon'
 'A. F. Andresen'
_journal_name_full
;
Journal of the Less Common Metals
;
_journal_volume 74
_journal_year 1980
_journal_page_first 65
_journal_page_last 73
_publ_Section_title
;
 New structure results for hydrides and deuterides of the hydrogen
    ↪ storage material Mg$_2$Ni
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_0450086

_aflow_proto 'A2B_hP18_180_fi_bd'
_aflow_params 'a,c/a,z3,x4'
_aflow_params_values '5.198,2.54136206233,0.163,0.1141'
_aflow_Strukturbericht 'C_a'
_aflow_Pearson 'hP18'

_symmetry_space_group_name_Hall "P 62 2c (0 0 1)"
_symmetry_space_group_name_H-M "P 62 2 2"
_symmetry_Int_Tables_number 180

_cell_length_a      5.19800
_cell_length_b      5.19800
_cell_length_c      13.21000
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/3
3 -y,x-y,z+2/3
4 -x,-y,z
5 -x+y,-x,z+1/3
6 y,-x+y,z+2/3
7 x-y,-y,-z
8 x,x-y,-z+1/3
9 y,x,-z+2/3
10 -x+y,y,-z
11 -x,-x+y,-z+1/3
12 -y,-x,-z+2/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ni1  Ni    3  b  0.00000  0.00000  0.50000  1.00000
Ni2  Ni    3  d  0.50000  0.00000  0.50000  1.00000
Mg1  Mg    6  f  0.50000  0.00000  0.16300  1.00000
Mg2  Mg    6  i  0.11410  0.22820  0.00000  1.00000
```

Mg_2Ni (C_a): A2B_hP18_180_fi_bd - POSCAR

```
A2B_hP18_180_fi_bd & a,c/a,z3,x4 --params=5.198,2.54136206233,0.163,
    ↪ 0.1141 & P6_222     D_6^4 #180 (bdfi) & hP18 & C_a & Mg2Ni & &
    ↪ J. Schefer et al., J. Less-Common Met. 74, 65-73 (1980)
   1.0000000000000000
   2.59900000000000   -4.50160004887200    0.00000000000000
   2.59900000000000    4.50160004887200    0.00000000000000
   0.00000000000000    0.00000000000000   13.21000000000000
   Mg    Ni
   12    6
Direct
   0.00000000000000    0.50000000000000    0.50366666666667    Mg    (6f)
   0.00000000000000    0.50000000000000    0.82966666666667    Mg    (6f)
   0.50000000000000    0.00000000000000    0.16300000000000    Mg    (6f)
   0.50000000000000    0.00000000000000    0.83700000000000    Mg    (6f)
   0.50000000000000    0.50000000000000    0.17033333333333    Mg    (6f)
   0.50000000000000    0.50000000000000    0.49633333333333    Mg    (6f)
   0.11410000000000    0.22820000000000    0.00000000000000    Mg    (6i)
   0.11410000000000    0.88590000000000    0.33333333333333    Mg    (6i)
   0.22820000000000    0.11410000000000    0.66666666666667    Mg    (6i)
   0.77180000000000    0.88590000000000    0.66666666666667    Mg    (6i)
   0.88590000000000    0.11410000000000    0.33333333333333    Mg    (6i)
   0.88590000000000    0.77180000000000    0.00000000000000    Mg    (6i)
   0.00000000000000    0.00000000000000    0.16666666666667    Ni    (3b)
   0.00000000000000    0.00000000000000    0.50000000000000    Ni    (3b)
   0.00000000000000    0.00000000000000    0.83333333333333    Ni    (3b)
   0.00000000000000    0.50000000000000    0.16666666666667    Ni    (3d)
   0.50000000000000    0.00000000000000    0.50000000000000    Ni    (3d)
   0.50000000000000    0.50000000000000    0.83333333333333    Ni    (3d)
```

$CrSi_2$ (C40): AB2_hP9_180_d_j - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr Si2'

loop_
_publ_author_name
 'T. Dasgupta'
 'J. Etourneau'
 'B. Chevalier'
 'S. F. Matar'
 'A. M. Umarji'
_journal_name_full
;
Journal of Applied Physics
;
_journal_volume 103
_journal_year 2008
_journal_page_first 113516
_journal_page_last 113516
_publ_Section_title
;
 Structural, thermal, and electrical properties of CrSi$_2$
;

_aflow_proto 'AB2_hP9_180_d_j'
_aflow_params 'a,c/a,x2'
_aflow_params_values '4.42758,1.43826876081,0.16559'
_aflow_Strukturbericht 'C40'
_aflow_Pearson 'hP9'

_symmetry_space_group_name_Hall "P 62 2c (0 0 1)"
_symmetry_space_group_name_H-M "P 62 2 2"
_symmetry_Int_Tables_number 180

_cell_length_a      4.42758
_cell_length_b      4.42758
_cell_length_c      6.36805
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/3
3 -y,x-y,z+2/3
4 -x,-y,z
5 -x+y,-x,z+1/3
6 y,-x+y,z+2/3
7 x-y,-y,-z
8 x,x-y,-z+1/3
9 y,x,-z+2/3
10 -x+y,y,-z
11 -x,-x+y,-z+1/3
12 -y,-x,-z+2/3

loop_
_atom_site_label
_atom_site_type_symbol
```

```
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1  Cr    3  d  0.50000  0.00000  0.50000  1.00000
Si1  Si    6  j  0.16559  0.33118  0.50000  1.00000
```

$CrSi_2$ (C40): AB2_hP9_180_d_j - POSCAR

```
AB2_hP9_180_d_j & a,c/a,x2 --params=4.42758,1.43826876081,0.16559 &
      ↪ P6_222      D_6^4 #180 (dj) & hP9 & C40 & CrSi2 & & T. Dasgupta,
      ↪ J. Etourneau, B. Chevalier, S. F. Matar and A. M. Umarji, J.
      ↪ App. Phys. 103, 113516 (2008)
   1.0000000000000000
   2.21379000000000   -3.83439675728800    0.00000000000000
   2.21379000000000    3.83439675728800    0.00000000000000
   0.00000000000000    0.00000000000000    6.36805000000000
   Cr    Si
    3     6
Direct
   0.00000000000000    0.50000000000000    0.16666666666667    Cr    (3d)
   0.50000000000000    0.00000000000000    0.50000000000000    Cr    (3d)
   0.50000000000000    0.50000000000000    0.83333333333333    Cr    (3d)
   0.16559100000000    0.33118200000000    0.50000000000000    Si    (6j)
   0.16559100000000    0.83440900000000    0.83333333333333    Si    (6j)
   0.33118200000000    0.16559100000000    0.16666666666667    Si    (6j)
   0.66881800000000    0.83440900000000    0.16666666666667    Si    (6j)
   0.83440900000000    0.16559100000000    0.83333333333333    Si    (6j)
   0.83440900000000    0.66881800000000    0.50000000000000    Si    (6j)
```

β-Quartz (SiO_2, C8): A2B_hP9_180_j_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'quartz (beta)'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'A. F. Wright'
 'M. S. Lehmann'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 36
_journal_year 1981
_journal_page_first 371
_journal_page_last 380
_publ_Section_title
;
 The Structure of Quartz at 25 and 590$^\circ$C Determined by Neutron
      ↪ Diffraction
;

# Found in  http://www.minweb.co.uk/quartz/betaquartz.html

_aflow_proto 'A2B_hP9_180_j_c'
_aflow_params 'a,c/a,x2'
_aflow_params_values '4.9977,1.09252256038,0.2072'
_aflow_Strukturbericht 'C8'
_aflow_Pearson 'hP9'

_symmetry_space_group_name_Hall "P 62 2c (0 0 1)"
_symmetry_space_group_name_H-M "P 62 2 2"
_symmetry_Int_Tables_number 180

_cell_length_a     4.99770
_cell_length_b     4.99770
_cell_length_c     5.46010
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/3
3 -y,x-y,z+2/3
4 -x,-y,z
5 -x+y,-x,z+1/3
6 y,-x+y,z+2/3
7 x-y,-y,-z
8 x,x-y,-z+1/3
9 y,x,-z+2/3
10 -x+y,y,-z
11 -x,-x+y,-z+1/3
12 -y,-x,-z+2/3

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1  Si    3  c  0.50000  0.00000  0.00000  1.00000
O1   O     6  j  0.20720  0.41440  0.50000  1.00000
```

β-Quartz (SiO_2, C8): A2B_hP9_180_j_c - POSCAR

```
A2B_hP9_180_j_c & a,c/a,x2 --params=4.9977,1.09252256038,0.2072 & P6_222
      ↪      D_6^4 #180 (cj) & hP9 & C8 & SiO2 & beta-quartz & A. F.
      ↪ Wright and M. S. Lehmann, J. Solid State. Chem. 36, 371-380 (
      ↪ 1981)
   1.0000000000000000
   2.49885000000000   -4.32813516049349    0.00000000000000
   2.49885000000000    4.32813516049349    0.00000000000000
   0.00000000000000    0.00000000000000    5.46010000000000
    O    Si
    6     3
Direct
   0.20720000000000    0.41440000000000    0.50000000000000    O    (6j)
   0.20720000000000    0.79280000000000    0.83333333333333    O    (6j)
   0.41440000000000    0.20720000000000    0.16666666666667    O    (6j)
   0.58560000000000    0.79280000000000    0.16666666666667    O    (6j)
   0.79280000000000    0.20720000000000    0.83333333333333    O    (6j)
   0.79280000000000    0.58560000000000    0.50000000000000    O    (6j)
   0.00000000000000    0.50000000000000    0.66666666666667    Si   (3c)
   0.50000000000000    0.00000000000000    0.00000000000000    Si   (3c)
   0.50000000000000    0.50000000000000    0.33333333333333    Si   (3c)
```

Bainite (Fe_3C): AB3_hP8_182_c_g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Upper Bainite'
_chemical_formula_sum 'Fe3 C'

loop_
_publ_author_name
 'Marianne Reibold'
 'Alexander A. Levin'
 'Dirk C. Meyer'
 'Peter Paufler'
 'Werner Kochmann'
_journal_name_full
;
International Journal of Materials Research
;
_journal_volume 97
_journal_year 2006
_journal_page_first 1172
_journal_page_last 1182
_publ_Section_title
;
 Microstructure of a Damascene sabre after annealing
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
      ↪ sd_1817306

_aflow_proto 'AB3_hP8_182_c_g'
_aflow_params 'a,c/a,x2'
_aflow_params_values '4.8507,0.866967654153,0.3249'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP8'

_symmetry_space_group_name_Hall "P 6c 2c"
_symmetry_space_group_name_H-M "P 63 2 2"
_symmetry_Int_Tables_number 182

_cell_length_a     4.85070
_cell_length_b     4.85070
_cell_length_c     4.20540
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1   C     2  c  0.33333  0.66667  0.25000  1.00000
Fe1  Fe    6  g  0.32490  0.00000  0.00000  1.00000
```

Bainite (Fe_3C): AB3_hP8_182_c_g - POSCAR

```
AB3_hP8_182_c_g & a,c/a,x2 --params=4.8507,0.866967654153,0.3249 &
    ↪ P6_322     D_6^3 #182 (cg) & hP8 & & Fe3C & Upper Bainite & M.
    ↪ Reibold et al., Int. J. Mater. Res. 97, 1172-1182 (2006)
   1.0000000000000000
   2.42535000000000  -4.20082942613700   0.00000000000000
   2.42535000000000   4.20082942613700   0.00000000000000
   0.00000000000000   0.00000000000000   4.20540000000000
    C    Fe
    2     6
Direct
   0.33333333333333   0.66666666666667   0.25000000000000    C    (2c)
   0.66666666666667   0.33333333333333   0.75000000000000    C    (2c)
   0.00000000000000   0.32490000000000   0.00000000000000   Fe    (6g)
  -0.00000000000000   0.67510000000000   0.50000000000000   Fe    (6g)
   0.32490000000000   0.00000000000000   0.00000000000000   Fe    (6g)
   0.32490000000000   0.32490000000000   0.50000000000000   Fe    (6g)
   0.67510000000000  -0.00000000000000   0.50000000000000   Fe    (6g)
   0.67510000000000   0.67510000000000   0.00000000000000   Fe    (6g)
```

Buckled Graphite: A_hP4_186_ab - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'graphite'
_chemical_formula_sum 'C'

loop_
_publ_author_name
 'A. W. Hull'
_journal_name_full
;
Physical Review
;
_journal_volume 10
_journal_year 1917
_journal_page_first 661
_journal_page_last 696
_publ_Section_title
;
 A New Method of X-Ray Crystal Analysis
;

# Found in  Wyckoff, Vol. I, pp. 254

_aflow_proto 'A_hP4_186_ab'
_aflow_params 'a,c/a,z1,z2'
_aflow_params_values '2.47,2.75303643725,0.0,0.07143'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP4'

_symmetry_space_group_name_Hall "P 6c -2c"
_symmetry_space_group_name_H-M "P 63 m c"
_symmetry_Int_Tables_number 186

_cell_length_a     2.47000
_cell_length_b     2.47000
_cell_length_c     6.80000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 -x+y,y,z
8 -x,-x+y,z+1/2
9 -y,-x,z
10 x-y,-y,z+1/2
11 x,x-y,z
12 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1 C    2 a 0.00000 0.00000 0.00000 1.00000
C2 C    2 b 0.33333 0.66667 0.07143 1.00000
```

Buckled Graphite: A_hP4_186_ab - POSCAR

```
A_hP4_186_ab & a,c/a,z1,z2 --params=2.47,2.75303643725,0.0,0.07143 &
    ↪ P6_3mc     C_{6v}^4 #186 (ab) & hP4 & & C & Graphite (buckled) &
    ↪ A. W. Hull, Phys. Rev. 10, 661-696 (1917)
   1.0000000000000000
   1.23500000000000  -2.13908274734800   0.00000000000000
   1.23500000000000   2.13908274734800   0.00000000000000
   0.00000000000000   0.00000000000000   6.80000000000000
    C
    4
Direct
   0.00000000000000   0.00000000000000   0.00000000000000    C    (2a)
   0.00000000000000   0.00000000000000   0.50000000000000    C    (2a)
   0.33333333333333   0.66666666666667   0.07142857142857    C    (2b)
   0.66666666666667   0.33333333333333   0.57142857142857    C    (2b)
```

Moissanite-4H SiC (B5): AB_hP8_186_ab_ab - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Moissanite-4H'
_chemical_formula_sum 'Si C'

loop_
_publ_author_name
 'A. Bauer'
 'P. Reischauer'
 'J. Kr\"{a}usslich'
 'N. Schell'
 'W. Matz'
 'K. Goetz'
_journal_name_full
;
Acta Crystallographica A
;
_journal_volume 57
_journal_year 2001
_journal_page_first 60
_journal_page_last 67
_publ_Section_title
;
 Structure refinement of the silicon carbide polytypes 4H and 6H:
    ↪ unambiguous determination of the refinement parameters
;

_aflow_proto 'AB_hP8_186_ab_ab'
_aflow_params 'a,c/a,z1,z2,z3,z4'
_aflow_params_values '3.08051,3.27374363336,0.18784,0.0,0.43671,0.24982'
_aflow_Strukturbericht 'B5'
_aflow_Pearson 'hP8'

_symmetry_space_group_name_Hall "P 6c -2c"
_symmetry_space_group_name_H-M "P 63 m c"
_symmetry_Int_Tables_number 186

_cell_length_a     3.08051
_cell_length_b     3.08051
_cell_length_c     10.08480
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 -x+y,y,z
8 -x,-x+y,z+1/2
9 -y,-x,z
10 x-y,-y,z+1/2
11 x,x-y,z
12 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    2 a 0.00000 0.00000 0.18784 1.00000
Si1 Si   2 a 0.00000 0.00000 0.00000 1.00000
C2  C    2 b 0.33333 0.66667 0.43671 1.00000
Si2 Si   2 b 0.33333 0.66667 0.24982 1.00000
```

Moissanite-4H SiC (B5): AB_hP8_186_ab_ab - POSCAR

```
AB_hP8_186_ab_ab & a,c/a,z1,z2,z3,z4 --params=3.08051,3.27374363336,
    ↪ 0.18784,0.0,0.43671,0.24982 & P6_3mc     C_{6v}^4 #186 (a^2b^2)
    ↪ & hP8 & B5 & SiC & Moissanite-4H & A. Bauer, P. Reischauer, J.
    ↪ Kr\"{a}usslich, N. Schell, W. Matz and K. Goetz, Acta Cryst. A
    ↪ 57, 60-67 (2001)
   1.0000000000000000
   1.54025500000000  -2.66779991661200   0.00000000000000
   1.54025500000000   2.66779991661200   0.00000000000000
   0.00000000000000   0.00000000000000  10.08480000000000
    C    Si
    4     4
Direct
   0.00000000000000   0.00000000000000   0.18783750000000    C    (2a)
   0.00000000000000   0.00000000000000   0.68783750000000    C    (2a)
   0.33333333333333   0.66666666666667   0.43671250000000    C    (2b)
   0.66666666666667   0.33333333333333  -0.06328750000000    C    (2b)
   0.00000000000000   0.00000000000000   0.00000000000000   Si    (2a)
   0.00000000000000   0.00000000000000   0.50000000000000   Si    (2a)
   0.33333333333333   0.66666666666667   0.24982500000000   Si    (2b)
```

```
    0.66666666666667     0.33333333333333     0.74982500000000     Si      (2b)
```

Wurtzite (ZnS, B4): AB_hP4_186_b_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Wurtzite'
_chemical_formula_sum 'Zn S'

loop_
_publ_author_name
 'Erich H. Kisi'
 'Margaret M. Elcombe'
_journal_name_full
;
Acta Crystallographica C
;
_journal_volume 45
_journal_year 1989
_journal_page_first 1867
_journal_page_last 1870
_publ_Section_title
;
 $u$ parameters for the wurtzite structure of ZnS and ZnO using powder
      ↪ neutron diffraction
;

# Found in  AMS Database

_aflow_proto 'AB_hP4_186_b_b'
_aflow_params 'a,c/a,z1,z2'
_aflow_params_values '3.8227,1.63776911607,0.3748,0.0'
_aflow_Strukturbericht 'B4'
_aflow_Pearson 'hP4'

_symmetry_space_group_name_Hall "P 6c -2c"
_symmetry_space_group_name_H-M "P 63 m c"
_symmetry_Int_Tables_number 186

_cell_length_a      3.82270
_cell_length_b      3.82270
_cell_length_c      6.26070
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 -x+y,y,z
8 -x,-x+y,z+1/2
9 -y,-x,z
10 x-y,-y,z+1/2
11 x,x-y,z
12 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
S1   S     2 b 0.33333 0.66667 0.37480 1.00000
Zn1  Zn    2 b 0.33333 0.66667 0.00000 1.00000
```

Wurtzite (ZnS, B4): AB_hP4_186_b_b - POSCAR

```
AB_hP4_186_b_b & a,c/a,z1,z2 --params=3.8227,1.63776911607,0.3748,0.0 &
      ↪ P6_3mc      C_{6v}^4 #186 (b^2) & hP4 & B4 & ZnS & Wurtzite & E.
      ↪ H. Kisi and M. M. Elcombe, Acta Cryst. C 45, 1867-870 (1989)
   1.0000000000000000
   1.91135000000000   -3.31055531104700    0.00000000000000
   1.91135000000000    3.31055531104700    0.00000000000000
   0.00000000000000    0.00000000000000    6.26070000000000
    S    Zn
    2     2
Direct
   0.33333333333333    0.66666666666667    0.37480000000000     S      (2b)
   0.66666666666667    0.33333333333333    0.87480000000000     S      (2b)
   0.33333333333333    0.66666666666667    0.00000000000000    Zn      (2b)
   0.66666666666667    0.33333333333333    0.50000000000000    Zn      (2b)
```

Moissanite-6H SiC (B6): AB_hP12_186_a2b_a2b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Moissanite-6H'
_chemical_formula_sum 'Si C'

loop_
_publ_author_name
 'A. Bauer'
 'P. Reischauer'
 'J. Kr\"{a}usslich'
 'N. Schell'
 'W. Matz'
 'K. Goetz'
_journal_name_full
;
Acta Crystallographica A
;
_journal_volume 57
_journal_year 2001
_journal_page_first 60
_journal_page_last 67
_publ_Section_title
;
 Structure refinement of the silicon carbide polytypes 4H and 6H:
      ↪ unambiguous determination of the refinement parameters
;

_aflow_proto 'AB_hP12_186_a2b_a2b'
_aflow_params 'a,c/a,z1,z2,z3,z4,z5,z6'
_aflow_params_values '3.08129,4.90695780014,0.1254,0.0,0.29215,-0.0415,
      ↪ 0.16675,0.8335'
_aflow_Strukturbericht 'B6'
_aflow_Pearson 'hP12'

_symmetry_space_group_name_Hall "P 6c -2c"
_symmetry_space_group_name_H-M "P 63 m c"
_symmetry_Int_Tables_number 186

_cell_length_a      3.08129
_cell_length_b      3.08129
_cell_length_c      15.11976
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 -x+y,y,z
8 -x,-x+y,z+1/2
9 -y,-x,z
10 x-y,-y,z+1/2
11 x,x-y,z
12 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1   C     2 a 0.00000 0.00000 0.12540   1.00000
Si1  Si    2 a 0.00000 0.00000 0.00000   1.00000
C2   C     2 b 0.33333 0.66667 0.29215   1.00000
C3   C     2 b 0.33333 0.66667 -0.04150  1.00000
Si2  Si    2 b 0.33333 0.66667 0.16675   1.00000
Si3  Si    2 b 0.33333 0.66667 0.83350   1.00000
```

Moissanite-6H SiC (B6): AB_hP12_186_a2b_a2b - POSCAR

```
AB_hP12_186_a2b_a2b & a,c/a,z1,z2,z3,z4,z5,z6 --params=3.08129,
      ↪ 4.90695780014,0.1254,0.0,0.29215,-0.0415,0.16675,0.8335 &
      ↪ P6_3mc      C_{6v}^4 #186 (a^2b^4) & hP12 & B6 & SiC &
      ↪ Moissanite-6H & A. Bauer, P. Reischauer, J. Kr\"{a}usslich, N.
      ↪ Schell, W. Matz and K. Goetz, Acta Cryst. A 57, 60-67 (2001)
   1.0000000000000000
   1.54064500000000   -2.66847541642695    0.00000000000000
   1.54064500000000    2.66847541642695    0.00000000000000
   0.00000000000000    0.00000000000000   15.11976000000000
    C    Si
    6     6
Direct
   0.00000000000000    0.00000000000000    0.12540000000000     C      (2a)
   0.00000000000000    0.00000000000000    0.62540000000000     C      (2a)
   0.33333333333333    0.66666666666667    0.29214666666667     C      (2b)
   0.66666666666667    0.33333333333333    0.79214666666667     C      (2b)
   0.33333333333333    0.66666666666667   -0.04149666666667     C      (2b)
   0.66666666666667    0.33333333333333    0.45850333333333     C      (2b)
   0.00000000000000    0.00000000000000    0.00000000000000    Si      (2a)
   0.00000000000000    0.00000000000000    0.50000000000000    Si      (2a)
   0.33333333333333    0.66666666666667    0.16674666666667    Si      (2b)
   0.66666666666667    0.33333333333333    0.66674666666667    Si      (2b)
   0.33333333333333    0.66666666666667    0.83350333333333    Si      (2b)
   0.66666666666667    0.33333333333333    0.33350333333333    Si      (2b)
```

Al_5C_3N (E9$_4$): A5B3C_hP18_186_2a3b_2ab_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM
```

```
_chemical_name_mineral 'Aluminum carbonitride'
_chemical_formula_sum 'Al5 C3 N'

loop_
_publ_author_name
 'G. A. Jeffrey'
 'Victor Y. Wu'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 20
_journal_year 1966
_journal_page_first 538
_journal_page_last 547
_publ_Section_title
;
 The structure of the aluminum carbonitrides. II
;

# Found in  http://materials.springer.com/lb/docs/
      ↪ sm_lbs_978-3-540-44820-4_208

_aflow_proto 'A5B3C_hP18_186_2a3b_2ab_b'
_aflow_params 'a,c/a,z1,z2,z3,z4,z5,z6,z7,z8,z9'
_aflow_params_values '3.281,6.57726302956,0.155,0.345,0.0,0.248,0.045,
      ↪ 0.261,0.455,0.367,0.137'
_aflow_Strukturbericht 'E9_4'
_aflow_Pearson 'hP18'

_symmetry_space_group_name_Hall "P 6c -2c"
_symmetry_space_group_name_H-M "P 63 m c"
_symmetry_Int_Tables_number 186

_cell_length_a      3.28100
_cell_length_b      3.28100
_cell_length_c      21.58000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 -x+y,y,z
8 -x,-x+y,z+1/2
9 -y,-x,z
10 x-y,-y,z+1/2
11 x,x-y,z
12 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1 Al   2 a 0.00000 0.00000 0.15500 1.00000
Al2 Al   2 a 0.00000 0.00000 0.34500 1.00000
C1  C    2 a 0.00000 0.00000 0.00000 1.00000
C2  C    2 a 0.00000 0.00000 0.24800 1.00000
Al3 Al   2 b 0.33333 0.66667 0.04500 1.00000
Al4 Al   2 b 0.33333 0.66667 0.26100 1.00000
Al5 Al   2 b 0.33333 0.66667 0.45500 1.00000
C3  C    2 b 0.33333 0.66667 0.36700 1.00000
N1  N    2 b 0.33333 0.66667 0.13700 1.00000
```

Al_5C_3N ($E9_4$): A5B3C_hP18_186_2a3b_2ab_b - POSCAR

```
A5B3C_hP18_186_2a3b_2ab_b & a,c/a,z1,z2,z3,z4,z5,z6,z7,z8,z9 --params=
      ↪ 3.281,6.57726302956,0.155,0.345,0.0,0.248,0.045,0.261,0.455,
      ↪ 0.367,0.137 & P6_3mc  C_{6v}^4 #186 (a^4b^5) & hP18 & E9_4 &
      ↪ Al5C3N & & G. A. Jeffrey and V. Y. Wu, Acta Cryst. 20, 538-547
      ↪ (1966)
   1.0000000000000000
   1.64050000000000  -2.84142934981674   0.00000000000000
   1.64050000000000   2.84142934981674   0.00000000000000
   0.00000000000000   0.00000000000000  21.58000000000000
   Al   C   N
   10   6   2
Direct
   0.00000000000000   0.00000000000000   0.15500000000000   Al   (2a)
   0.00000000000000   0.00000000000000   0.65500000000000   Al   (2a)
   0.00000000000000   0.00000000000000   0.34500000000000   Al   (2a)
   0.00000000000000   0.00000000000000   0.84500000000000   Al   (2a)
   0.33333333333333   0.66666666666667   0.04500000000000   Al   (2b)
   0.66666666666667   0.33333333333333   0.54500000000000   Al   (2b)
   0.33333333333333   0.66666666666667   0.26100000000000   Al   (2b)
   0.66666666666667   0.33333333333333   0.76100000000000   Al   (2b)
   0.33333333333333   0.66666666666667   0.45500000000000   Al   (2b)
   0.66666666666667   0.33333333333333  -0.04500000000000   Al   (2b)
   0.00000000000000   0.00000000000000   0.00000000000000    C   (2a)
   0.00000000000000   0.00000000000000   0.50000000000000    C   (2a)
   0.00000000000000   0.00000000000000   0.24800000000000    C   (2a)
   0.00000000000000   0.00000000000000   0.74800000000000    C   (2a)
   0.33333333333333   0.66666666666667   0.36700000000000    C   (2b)
   0.66666666666667   0.33333333333333   0.86700000000000    C   (2b)
   0.33333333333333   0.66666666666667   0.13700000000000    N   (2b)
   0.66666666666667   0.33333333333333   0.63700000000000    N   (2b)
```

Original BN (B12): AB_hP4_186_b_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'B N'

loop_
_publ_author_name
 'A. Brager'
_journal_name_full
;
Acta Physicochimica URSS
;
_journal_volume 7
_journal_year 1937
_journal_page_first 699
_journal_page_last 706
_publ_Section_title
;
 X-ray examination of the structure of boron nitride
;

# Found in  Structure Reports, Vol 18, 125-126 (1940-41)

_aflow_proto 'AB_hP4_186_b_a'
_aflow_params 'a,c/a,z1,z2'
_aflow_params_values '2.51,2.66932270916,0.0,0.05'
_aflow_Strukturbericht 'B12'
_aflow_Pearson 'hP4'

_symmetry_space_group_name_Hall "P 6c -2c"
_symmetry_space_group_name_H-M "P 63 m c"
_symmetry_Int_Tables_number 186

_cell_length_a      2.51000
_cell_length_b      2.51000
_cell_length_c      6.70000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 -x+y,y,z
8 -x,-x+y,z+1/2
9 -y,-x,z
10 x-y,-y,z+1/2
11 x,x-y,z
12 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
N1 N   2 a 0.00000 0.00000 0.00000 1.00000
B1 B   2 b 0.33333 0.66667 0.05000 1.00000
```

Original BN (B12): AB_hP4_186_b_a - POSCAR

```
AB_hP4_186_b_a & a,c/a,z1,z2 --params=2.51,2.66932270916,0.0,0.05 &
      ↪ P6_3mc  C_{6v}^4 #186 (ab) & hP4 & B12 & BN & & A. Bragrer,
      ↪ Acta Physicochimica URSS 7, 699-706 (1937)
   1.0000000000000000
   1.25500000000000  -2.17372376349894   0.00000000000000
   1.25500000000000   2.17372376349894   0.00000000000000
   0.00000000000000   0.00000000000000   6.70000000000000
    B   N
    2   2
Direct
   0.33333333333333   0.66666666666667   0.05000000000000    B   (2b)
   0.66666666666667   0.33333333333333   0.55000000000000    B   (2b)
   0.00000000000000   0.00000000000000   0.00000000000000    N   (2a)
   0.00000000000000   0.00000000000000   0.50000000000000    N   (2a)
```

BaPtSb: ABC_hP3_187_a_d_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ba Pt Sb'
```

```
loop_
_publ_author_name
 'G. Wenski'
 'A. Mewis'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 535
_journal_year 1986
_journal_page_first 110
_journal_page_last 122
_publ_Section_title
;
 Trigonal-planar koordiniertes Platin: Darstellung und Struktur von
      ↪ SrPtAs (Sb), BaPtP (As, Sb), SrPt$_x$P$_{2-x}$, SrPt$_x$As$_{
      ↪ 0.90}$ und BaPt$_x$As$_{0.90}$
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
     ↪ sd_2080134

_aflow_proto 'ABC_hP3_187_a_d_f'
_aflow_params 'a,c/a'
_aflow_params_values '4.535,1.0769570011'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP3'

_symmetry_space_group_name_Hall "P -6 2"
_symmetry_space_group_name_H-M "P -6 m 2"
_symmetry_Int_Tables_number 187

_cell_length_a      4.53500
_cell_length_b      4.53500
_cell_length_c      4.88400
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x,x-y,-z
5 -x+y,y,-z
6 -y,-x,-z
7 -x+y,-x,-z
8 x,y,-z
9 -y,x-y,-z
10 -x+y,y,z
11 -y,-x,z
12 x,x-y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ba1 Ba   1 a 0.00000 0.00000 0.00000 1.00000
Pt1 Pt   1 d 0.33333 0.66667 0.50000 1.00000
Sb1 Sb   1 f 0.66667 0.33333 0.50000 1.00000
```

BaPtSb: ABC_hP3_187_a_d_f - POSCAR

```
ABC_hP3_187_a_d_f & a,c/a --params=4.535,1.0769570011 & P(-6)m2   D_{3h
      ↪ }^1 #187 (adf) & hP3 & & BaPtSb & & G. Wenski and A. Mewis, Z.
      ↪ anorg. allg. Chem. 535, 110-122 (1986)
   1.0000000000000000
   2.26750000000000  -3.92742520616200   0.00000000000000
   2.26750000000000   3.92742520616200   0.00000000000000
   0.00000000000000   0.00000000000000   4.88400000000000
   Ba   Pt   Sb
    1    1    1
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Ba   (1a)
   0.33333333333333   0.66666666666667   0.50000000000000   Pt   (1d)
   0.66666666666667   0.33333333333333   0.50000000000000   Sb   (1f)
```

Tungsten Carbide (B_h): AB_hP2_187_d_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Tungsten Carbide'
_chemical_formula_sum 'W C'

loop_
_publ_author_name
 'J. Leciejewicz'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 14
_journal_year 1961
_journal_page_first 200
_journal_page_last 200
_publ_Section_title
;
 A note on the structure of tungsten carbide
;

# Found in  Pearson's Alloys, pp. 479

_aflow_proto 'AB_hP2_187_d_a'
_aflow_params 'a,c/a'
_aflow_params_values '2.9065,0.975950455875'
_aflow_Strukturbericht 'B_h'
_aflow_Pearson 'hP2'

_symmetry_space_group_name_Hall "P -6 2"
_symmetry_space_group_name_H-M "P -6 m 2"
_symmetry_Int_Tables_number 187

_cell_length_a      2.90650
_cell_length_b      2.90650
_cell_length_c      2.83660
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x,x-y,-z
5 -x+y,y,-z
6 -y,-x,-z
7 -x+y,-x,-z
8 x,y,-z
9 -y,x-y,-z
10 -x+y,y,z
11 -y,-x,z
12 x,x-y,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
W1 W   1 a 0.00000 0.00000 0.00000 1.00000
C1 C   1 d 0.33333 0.66667 0.50000 1.00000
```

Tungsten Carbide (B_h): AB_hP2_187_d_a - POSCAR

```
AB_hP2_187_d_a & a,c/a --params=2.9065,0.975950455875 & P(-6)m2   D_{3h
      ↪ }^1 #187 (ad) & hP2 & B_h & WC & & J. Leciejewicz, Acta Cryst.
      ↪ 14, 200 (1961)
   1.0000000000000000
   1.45325000000000  -2.51710283609900   0.00000000000000
   1.45325000000000   2.51710283609900   0.00000000000000
   0.00000000000000   0.00000000000000   2.83660000000000
    C    W
    1    1
Direct
   0.33333333333333   0.66666666666667   0.50000000000000   C   (1d)
   0.00000000000000   0.00000000000000   0.00000000000000   W   (1a)
```

Revised Fe_2P (C22): A2B_hP9_189_fg_bc - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Fe2 P'

loop_
_publ_author_name
 'Hironobu Fujii'
 'Shigehiro Komura'
 'Takayoshi Takeda'
 'Tetsuhiko Okamoto'
 'Yuji Ito'
 'Jun Akimitsu'
_journal_name_full
;
Journal of the Physical Society of Japan
;
_journal_volume 46
_journal_year 1979
_journal_page_first 1616
_journal_page_last 1621
_publ_Section_title
;
 Polarized Neutron Diffraction Study of Fe$_2$P Single Crystal
;

# Found in  Wyckoff, Vol. I, (IV,h1) pp. 360

_aflow_proto 'A2B_hP9_189_fg_bc'
_aflow_params 'a,c/a,x3,x4'
_aflow_params_values '5.877,0.584822188191,0.256,0.589'
_aflow_Strukturbericht 'C22'
```

```
_aflow_Pearson 'hP9'

_symmetry_space_group_name_Hall "P -6 -2"
_symmetry_space_group_name_H-M "P -6 2 m"
_symmetry_Int_Tables_number 189

_cell_length_a      5.87700
_cell_length_b      5.87700
_cell_length_c      3.43700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
_aflow_Strukturbericht 'C22'
_aflow_Pearson 'hP9'

_symmetry_space_group_name_Hall "P -6 -2"
_symmetry_space_group_name_H-M "P -6 2 m"
_symmetry_Int_Tables_number 189

_cell_length_a      5.87700
_cell_length_b      5.87700
_cell_length_c      3.43700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 -y,x-y,z
3 -x+y,-x,z
4 x-y,-y,-z
5 y,x,-z
6 -x,-x+y,-z
7 -x+y,-x,-z
8 x,y,-z
9 -y,x-y,-z
10 -x,-x+y,z
11 x-y,-y,z
12 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
P1  P   1 b 0.00000 0.00000 0.50000 1.00000
P2  P   2 c 0.33333 0.66667 0.00000 1.00000
Fe1 Fe  3 f 0.25600 0.00000 0.00000 1.00000
Fe2 Fe  3 g 0.58900 0.00000 0.50000 1.00000
```

Revised Fe_2P (C22): A2B_hP9_189_fg_bc - POSCAR

```
A2B_hP9_189_fg_bc & a,c/a,x3,x4 --params=5.877,0.584822188191,0.256,
    ↪ 0.589 & P(-6)2m  D_{3h}^3 #189 (bcfg) & hP9 & C22 & Fe2P & &
    ↪ H. Fujii et al., J. Phys. Soc. Japan 46, 1616-1621 (1979)
  1.0000000000000000
  2.93850000000000  -5.08963129804115   0.00000000000000
  2.93850000000000   5.08963129804115   0.00000000000000
  0.00000000000000   0.00000000000000   3.43700000000000
  Fe   P
   6   3
Direct
  0.00000000000000   0.25600000000000   0.00000000000000   Fe   (3f)
  0.25600000000000   0.00000000000000   0.00000000000000   Fe   (3f)
  0.74400000000000   0.74400000000000   0.00000000000000   Fe   (3f)
  0.00000000000000   0.58900000000000   0.50000000000000   Fe   (3g)
  0.41100000000000   0.41100000000000   0.50000000000000   Fe   (3g)
  0.58900000000000   0.00000000000000   0.50000000000000   Fe   (3g)
  0.00000000000000   0.00000000000000   0.50000000000000    P   (1b)
  0.33333333333333   0.66666666666667   0.00000000000000    P   (2c)
  0.66666666666667   0.33333333333333   0.00000000000000    P   (2c)
```

AlB_4Mg: AB4C_hP6_191_a_h_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Al B4 Mg'

loop_
_publ_author_name
 'Serena Margadonna'
 'Kosmas Prassides'
 'Ioannis Arvanitidis'
 'Michael Pissas'
 'Georgios Papavassiliou'
 'Andrew N. Fitch'
_journal_name_full
;
Physical Review B
;
_journal_volume 66
_journal_year 2002
_journal_page_first 014518
_journal_page_last 014518
_publ_Section_title
;
 Crystal structure of the Mg$_{1-x}$Al$_x$B$_2$ superconductors near $x
    ↪ \approx 0.5$
;

_aflow_proto 'AB4C_hP6_191_a_h_b'
_aflow_params 'a,c/a,z3'
_aflow_params_values '3.04436,2.20489035462,0.2413'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6 2 "
_symmetry_space_group_name_H-M "P 6/m m m"
_symmetry_Int_Tables_number 191

_cell_length_a      3.04436
_cell_length_b      3.04436
_cell_length_c      6.71248
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z
3 -y,x-y,z
4 -x,-y,z
5 -x+y,-x,z
6 y,-x+y,z
7 x-y,-y,-z
8 x,x-y,-z
9 y,x,-z
10 -x+y,y,-z
11 -x,-x+y,-z
12 -y,-x,-z
13 -x,-y,-z
14 -x+y,-x,-z
15 y,-x+y,-z
16 x,y,-z
17 x-y,x,-z
18 -y,x-y,-z
19 -x+y,y,z
20 -x,-x+y,z
21 -y,-x,z
22 x-y,-y,z
23 x,x-y,z
24 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1 Al   1 a 0.00000 0.00000 0.00000 1.00000
Mg1 Mg   1 b 0.00000 0.00000 0.50000 1.00000
B1  B    4 h 0.33333 0.66667 0.24130 1.00000
```

AlB_4Mg: AB4C_hP6_191_a_h_b - POSCAR

```
AB4C_hP6_191_a_h_b & a,c/a,z3 --params=3.04436,2.20489035462,0.2413 & P6
    ↪ /mmm  D_{6h}^{1} #191 (abh) & hP6 & & AlB4Mg &  & S.
    ↪ Margadonna et al., PRB 66, 014518 (2002)
  1.0000000000000000
  1.52218000000000  -2.63649309826500   0.00000000000000
  1.52218000000000   2.63649309826500   0.00000000000000
  0.00000000000000   0.00000000000000   6.71248000000000
  Al   B   Mg
   1   4    1
Direct
  0.00000000000000   0.00000000000000   0.00000000000000   Al   (1a)
  0.33333333333333   0.66666666666667   0.24130000000000    B   (4h)
  0.33333333333333   0.66666666666667   0.75870000000000    B   (4h)
  0.66666666666667   0.33333333333333   0.24130000000000    B   (4h)
  0.66666666666667   0.33333333333333   0.75870000000000    B   (4h)
  0.00000000000000   0.00000000000000   0.50000000000000   Mg   (1b)
```

$CaCu_5$ ($D2_d$): AB5_hP6_191_a_cg - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ca Cu5'

loop_
_publ_author_name
 'Werner Haucke'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
```

```
;
_journal_volume 244
_journal_year 1940
_journal_page_first 17
_journal_page_last 22
_publ_Section_title
;
 Kristallstruktur von CaZn$_5$ und CaCu$_5$
;

# Found in  Pearson's Alloys, pp. 645

_aflow_proto 'AB5_hP6_191_a_cg'
_aflow_params 'a,c/a'
_aflow_params_values '5.405,0.773913043478'
_aflow_Strukturbericht 'D2_d'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6 2"
_symmetry_space_group_name_H-M "P 6/m m m"
_symmetry_Int_Tables_number 191

_cell_length_a      5.40500
_cell_length_b      5.40500
_cell_length_c      4.18300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z
3 -y,x-y,z
4 -x,-y,z
5 -x+y,-x,z
6 y,-x+y,z
7 x-y,-y,-z
8 x,x-y,-z
9 y,x,-z
10 -x+y,y,-z
11 -x,-x+y,-z
12 -y,-x,-z
13 -x,-y,-z
14 -x+y,-x,-z
15 y,-x+y,-z
16 x,y,-z
17 x-y,x,-z
18 -y,x-y,-z
19 -x+y,y,z
20 -x,-x+y,z
21 -y,-x,z
22 x-y,-y,z
23 x,x-y,z
24 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ca1 Ca    1 a 0.00000 0.00000 0.00000 1.00000
Cu1 Cu    2 c 0.33333 0.66667 0.00000 1.00000
Cu2 Cu    3 g 0.50000 0.00000 0.50000 1.00000
```

$CaCu_5$ ($D2_d$): AB5_hP6_191_a_cg - POSCAR

```
AB5_hP6_191_a_cg & a,c/a --params=5.405,0.773913043478 & P6/mmm     D_{6h
    ↪ }^{1} #191 (acg) & hP6 & D2_d & CaCu5 &  & W. Haucke, ZAAC 244,
    ↪ 17-22 (1940)
   1.0000000000000000
   2.70250000000000   -4.68086730745489    0.00000000000000
   2.70250000000000    4.68086730745489    0.00000000000000
   0.00000000000000    0.00000000000000    4.18300000000000
   Ca    Cu
    1     5
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Ca     (1a)
   0.33333333333333    0.66666666666667    0.00000000000000    Cu     (2c)
   0.66666666666667    0.33333333333333    0.00000000000000    Cu     (2c)
   0.00000000000000    0.50000000000000    0.50000000000000    Cu     (3g)
   0.50000000000000    0.00000000000000    0.50000000000000    Cu     (3g)
   0.50000000000000    0.50000000000000    0.50000000000000    Cu     (3g)
```

Simple Hexagonal Lattice (A_f): A_hP1_191_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Hg_xSn'
_chemical_formula_sum 'Sn'

loop_
_publ_author_name
 'G. V. Raynor'
 'J. A. Lee'
_journal_name_full
;
Acta Metallurgica
;
_journal_volume 2
_journal_year 1954
_journal_page_first 616
_journal_page_last 620
_publ_Section_title
;
 The tin-rich intermediate phases in the alloys of tin with cadmium,
    ↪ indium and mercury
;

# Found in  Pearson's Handbook, III, pp. 3947

_aflow_proto 'A_hP1_191_a'
_aflow_params 'a,c/a'
_aflow_params_values '3.2062,0.931195808122'
_aflow_Strukturbericht 'A_f'
_aflow_Pearson 'hP1'

_symmetry_space_group_name_Hall "-P 6 2"
_symmetry_space_group_name_H-M "P 6/m m m"
_symmetry_Int_Tables_number 191

_cell_length_a      3.20620
_cell_length_b      3.20620
_cell_length_c      2.98560
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z
3 -y,x-y,z
4 -x,-y,z
5 -x+y,-x,z
6 y,-x+y,z
7 x-y,-y,-z
8 x,x-y,-z
9 y,x,-z
10 -x+y,y,-z
11 -x,-x+y,-z
12 -y,-x,-z
13 -x,-y,-z
14 -x+y,-x,-z
15 y,-x+y,-z
16 x,y,-z
17 x-y,x,-z
18 -y,x-y,-z
19 -x+y,y,z
20 -x,-x+y,z
21 -y,-x,z
22 x-y,-y,z
23 x,x-y,z
24 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Sn1 Sn   1 a 0.00000 0.00000 0.00000 1.00000
```

Simple Hexagonal Lattice (A_f): A_hP1_191_a - POSCAR

```
A_hP1_191_a & a,c/a --params=3.2062,0.931195808122 & P6/mmm     D_{6h}^{1
    ↪ } #191 (a) & hP1 & A_f & HgSn6-10 &  & G. V. Raynor and J. A.
    ↪ Lee, Acta Metallurgica 2, 616-620 (1954)
   1.0000000000000000
   1.60310000000000   -2.77665064961367    0.00000000000000
   1.60310000000000    2.77665064961367    0.00000000000000
   0.00000000000000    0.00000000000000    2.98560000000076
   M
    1
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    M     (1a)
```

Li_3N: A3B_hP4_191_bc_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Li3 N'

loop_
_publ_author_name
 'Duncan H. Gregory'
 'Paul M. O'Meara'
 'Alexandra G. Gordon'
 'Jason P. Hodges'
 'Simine Short'
 'James D. Jorgensen'
_journal_name_full
;
Chemistry of Materials
```

```
;
_journal_volume 14
_journal_year 2002
_journal_page_first 2063
_journal_page_last 2070
_publ_Section_title
;
 Structure of Lithium Nitride and Transition-Metal-Doped Derivatives,
      ↪ Li$_{3-x-y}$M$_x$N (M = Ni, Cu): A Powder Neutron Diffraction
      ↪ Study
;

# Found in  http://materials.springer.com/lb/docs/
      ↪ sm_lbs_978-3-540-32682-3_554}

_aflow_proto 'A3B_hP4_191_bc_a'
_aflow_params 'a,c/a'
_aflow_params_values '3.6576,1.05902777778'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP4'

_symmetry_space_group_name_Hall "-P 6 2"
_symmetry_space_group_name_H-M "P 6/m m m"
_symmetry_Int_Tables_number 191

_cell_length_a      3.65760
_cell_length_b      3.65760
_cell_length_c      3.87350
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z
3 -y,x-y,z
4 -x,-y,z
5 -x+y,-x,z
6 y,-x+y,z
7 x-y,-y,-z
8 x,x-y,-z
9 y,x,-z
10 -x+y,y,-z
11 -x,-x+y,-z
12 -y,-x,-z
13 -x,-y,-z
14 -x+y,-x,-z
15 y,-x+y,-z
16 x,y,-z
17 x-y,x,-z
18 -y,x-y,-z
19 -x+y,y,z
20 -x,-x+y,z
21 -y,-x,z
22 x-y,-y,z
23 x,x-y,z
24 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
N1  N    1 a 0.00000 0.00000 0.00000 1.00000
Li1 Li   1 b 0.00000 0.00000 0.50000 1.00000
Li2 Li   2 c 0.33333 0.66667 0.00000 1.00000
```

Li_3N: A3B_hP4_191_bc_a - POSCAR

```
A3B_hP4_191_bc_a & a,c/a --params=3.6576,1.05902777778 & P6/mmm     D_{6h
      ↪ }^4 #191 (abc) & hP4 & Li3N & D. H. Gregory et al., Chem.
      ↪ Mater. 14, 2063-2070 (2002)
   1.0000000000000000
   1.82880000000000   -3.16757451688196    0.00000000000000
   1.82880000000000    3.16757451688196    0.00000000000000
   0.00000000000000    0.00000000000000    3.87350000000000
   Li    N
    3    1
Direct
   0.00000000000000    0.00000000000000    0.50000000000000    Li    (1b)
   0.33333333333333    0.66666666666667    0.00000000000000    Li    (2c)
   0.66666666666667    0.33333333333333    0.00000000000000    Li    (2c)
   0.00000000000000    0.00000000000000    0.00000000000000     N    (1a)
```

Hexagonal ω (C32): AB2_hP3_191_a_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'hexagonal omega structure'
_chemical_formula_sum 'Al B2'

loop_
_publ_author_name
 'Ulrich Burkhardt'
 'Vladimir Gurin'
 'Frank Haarmann'
 'Horst Borrmann'
 'Walter Schnelle'
 'Alexander Yaresko'
 'Yuri Grin'
_journal_name_full
;
Journal of Solid State Chemistry
;
_journal_volume 177
_journal_year 2004
_journal_page_first 389
_journal_page_last 394
_publ_Section_title
;
 On the electronic and structural properties of aluminum diboride Al$_{
      ↪ 0.9}$B$_2$
;

# Found in  http://en.wikipedia.org/wiki/Aluminium_diboride

_aflow_proto 'AB2_hP3_191_a_d'
_aflow_params 'a,c/a'
_aflow_params_values '3.005,1.08276206323'
_aflow_Strukturbericht 'C32'
_aflow_Pearson 'hP3'

_symmetry_space_group_name_Hall "-P 6 2"
_symmetry_space_group_name_H-M "P 6/m m m"
_symmetry_Int_Tables_number 191

_cell_length_a      3.00500
_cell_length_b      3.00500
_cell_length_c      3.25370
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z
3 -y,x-y,z
4 -x,-y,z
5 -x+y,-x,z
6 y,-x+y,z
7 x-y,-y,-z
8 x,x-y,-z
9 y,x,-z
10 -x+y,y,-z
11 -x,-x+y,-z
12 -y,-x,-z
13 -x,-y,-z
14 -x+y,-x,-z
15 y,-x+y,-z
16 x,y,-z
17 x-y,x,-z
18 -y,x-y,-z
19 -x+y,y,z
20 -x,-x+y,z
21 -y,-x,z
22 x-y,-y,z
23 x,x-y,z
24 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1 Al   1 a 0.00000 0.00000 0.00000 1.00000
B1  B    2 d 0.33333 0.66667 0.50000 1.00000
```

Hexagonal ω (C32): AB2_hP3_191_a_d - POSCAR

```
AB2_hP3_191_a_d & a,c/a --params=3.005,1.08276206323 & P6/mmm     D_{6h
      ↪ }^{1} #191 (ad) & hP3 & C32 & AlB2 & hexagonal omega & U.
      ↪ Burkhardt et al., JSSC 177, 389-394 (2004)
   1.0000000000000000
   1.50250000000000   -2.60240633837224    0.00000000000000
   1.50250000000000    2.60240633837224    0.00000000000000
   0.00000000000000    0.00000000000000    3.25370000000000
   Al    B
    1    2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Al    (1a)
   0.33333333333333    0.66666666666667    0.50000000000000     B    (2d)
   0.66666666666667    0.33333333333333    0.50000000000000     B    (2d)
```

Cu_2Te (C_h): A2B_hP6_191_h_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cu2 Te'

loop_
_publ_author_name
```

```
 'H. Nowotny'
_journal_name_full
;
Zeitschrift f\"{u}r Metallkunde
;
_journal_volume 37
_journal_year 1946
_journal_page_first 40
_journal_page_last 42
_publ_Section_title
;
 Die Kristallstruktur von Cu$_2$Te
;

# Found in  Pearson's Handbook, Vol. III, pp. 3014

_aflow_proto 'A2B_hP6_191_h_e'
_aflow_params 'a,c/a,z1,z2'
_aflow_params_values '4.237,1.71040830776,0.306,0.16'
_aflow_Strukturbericht 'C_h'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6 2"
_symmetry_space_group_name_H-M "P 6/m m m"
_symmetry_Int_Tables_number 191

_cell_length_a      4.23700
_cell_length_b      4.23700
_cell_length_c      7.24700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z
3 -y,x-y,z
4 -x,-y,z
5 -x+y,-x,z
6 y,-x+y,z
7 x-y,-y,-z
8 x,x-y,-z
9 y,x,-z
10 -x+y,y,-z
11 -x,-x+y,-z
12 -y,-x,-z
13 -x,-y,-z
14 -x+y,-x,-z
15 y,-x+y,-z
16 x,y,-z
17 x-y,x,-z
18 -y,x-y,-z
19 -x+y,y,z
20 -x,-x+y,z
21 -y,-x,z
22 x-y,-y,z
23 x,x-y,z
24 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Te1 Te    2 e 0.00000 0.00000 0.30600 1.00000
Cu1 Cu    4 h 0.33333 0.66667 0.16000 1.00000
```

Cu_2Te (C_h): A2B_hP6_191_h_e - POSCAR

```
A2B_hP6_191_h_e & a,c/a,z1,z2 --params=4.237,1.71040830776,0.306,0.16 &
    ↪ P6/mmm     D_{6h}^{1} #191 (eh) & hP6 & C_h & Cu2Te & & H.
    ↪ Nowotny, Z. Metallkd. 37, 40-42 (1946)
   1.0000000000000000
   2.11850000000000   -3.66934963583467    0.00000000000000
   2.11850000000000    3.66934963583467    0.00000000000000
   0.00000000000000    0.00000000000000    7.24700000000000
   Cu    Te
    4     2
Direct
   0.33333333333333    0.66666666666667    0.16000000000000    Cu    (4h)
   0.33333333333333    0.66666666666667    0.84000000000000    Cu    (4h)
   0.66666666666667    0.33333333333333    0.16000000000000    Cu    (4h)
   0.66666666666667    0.33333333333333    0.84000000000000    Cu    (4h)
   0.00000000000000    0.00000000000000    0.30600000000000    Te    (2e)
   0.00000000000000    0.00000000000000    0.69400000000000    Te    (2e)
```

CoSn (B35): AB_hP6_191_f_ad - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Co Sn'

loop_
_publ_author_name
 'A.K. Larsson'
 'M. Haeberlein'
 'S. Lidin'
 'U. Schwarz'
_journal_name_full
;
Journal of Alloys and Compounds
;
_journal_volume 240
_journal_year 1996
_journal_page_first 79
_journal_page_last 84
_publ_Section_title
;
 Single crystal structure refinement and high-pressure properties of
    ↪ CoSn
;

_aflow_proto 'AB_hP6_191_f_ad'
_aflow_params 'a,c/a'
_aflow_params_values '5.279,0.806914188293'
_aflow_Strukturbericht 'B35'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6 2"
_symmetry_space_group_name_H-M "P 6/m m m"
_symmetry_Int_Tables_number 191

_cell_length_a      5.27900
_cell_length_b      5.27900
_cell_length_c      4.25970
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z
3 -y,x-y,z
4 -x,-y,z
5 -x+y,-x,z
6 y,-x+y,z
7 x-y,-y,-z
8 x,x-y,-z
9 y,x,-z
10 -x+y,y,-z
11 -x,-x+y,-z
12 -y,-x,-z
13 -x,-y,-z
14 -x+y,-x,-z
15 y,-x+y,-z
16 x,y,-z
17 x-y,x,-z
18 -y,x-y,-z
19 -x+y,y,z
20 -x,-x+y,z
21 -y,-x,z
22 x-y,-y,z
23 x,x-y,z
24 y,x,z

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Sn1 Sn    1 a 0.00000 0.00000 0.00000 1.00000
Sn2 Sn    2 d 0.33333 0.66667 0.50000 1.00000
Co1 Co    3 f 0.50000 0.00000 0.00000 1.00000
```

CoSn (B35): AB_hP6_191_f_ad - POSCAR

```
AB_hP6_191_f_ad & a,c/a --params=5.279,0.806914188293 & P6/mmm     D_{6h
    ↪ }^{1} #191 (adf) & hP6 & B35 & CoSn & & A. K. Larsson et al.,
    ↪ J. Alloys Comp. 240, 79-84 (1996)
   1.0000000000000000
   2.63950000000000   -4.57174810657805    0.00000000000000
   2.63950000000000    4.57174810657805    0.00000000000000
   0.00000000000000    0.00000000000000    4.25970000000000
   Co    Sn
    3     3
Direct
   0.00000000000000    0.50000000000000    0.00000000000000    Co    (3f)
   0.50000000000000    0.00000000000000    0.00000000000000    Co    (3f)
   0.50000000000000    0.50000000000000    0.00000000000000    Co    (3f)
   0.00000000000000    0.00000000000000    0.00000000000000    Sn    (1a)
   0.33333333333333    0.66666666666667    0.50000000000000    Sn    (2d)
   0.66666666666667    0.33333333333333    0.50000000000000    Sn    (2d)
```

AsTi (B_f): AB_hP8_194_ad_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'As Ti'

loop_
```

```
_publ_author_name
 'K. Bachmayer'
 'H. Nowotny'
 'A. Kohl'
_journal_name_full
;
Monatshefte f\"{u}r Chemie und verwandte Teile anderer Wissenschaften
;
_journal_volume 86
_journal_year 1955
_journal_page_first 39
_journal_page_last 43
_publ_Section_title
;
 Die Struktur von TiAs
;

# Found in  Wyckoff, Vol. I, pp. 146-149

_aflow_proto 'AB_hP8_194_ad_f'
_aflow_params 'a,c/a,z3'
_aflow_params_values '3.64,3.37362637363,0.125'
_aflow_Strukturbericht 'B_i'
_aflow_Pearson 'hP8'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      3.64000
_cell_length_b      3.64000
_cell_length_c      12.28000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
As1 As    2 a 0.00000 0.00000 0.00000 1.00000
As2 As    2 d 0.33333 0.66667 0.75000 1.00000
Ti1 Ti    4 f 0.33333 0.66667 0.12500 1.00000
```

AsTi (B_i): AB_hP8_194_ad_f - POSCAR

```
AB_hP8_194_ad_f & a,c/a,z3 --params=3.64,3.37362637363,0.125 & P6_3/mmc
    ↪ D_{6h}^4 #194 (adf) & hP8 & B_i & AsTi & & K. Bachmayer, H.
    ↪ Nowtny and A. Kohl, Monatshefte f"{u}r Chemie 86, 39-43 (1955)
   1.0000000000000000
   1.82000000000000   -3.15233246977536    0.00000000000000
   1.82000000000000    3.15233246977536    0.00000000000000
   0.00000000000000    0.00000000000000   12.28000000000000
   As    Ti
    4     4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    As    (2a)
   0.00000000000000    0.00000000000000    0.50000000000000    As    (2a)
   0.33333333333333    0.66666666666667    0.75000000000000    As    (2d)
   0.66666666666667    0.33333333333333    0.25000000000000    As    (2d)
   0.33333333333333    0.66666666666667    0.12500000000000    Ti    (4f)
   0.33333333333333    0.66666666666667    0.37500000000000    Ti    (4f)
   0.66666666666667    0.33333333333333    0.62500000000000    Ti    (4f)
   0.66666666666667    0.33333333333333    0.87500000000000    Ti    (4f)
```

Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Theoretical Carbon Structure'
_chemical_formula_sum 'C'

loop_
_publ_author_name
 'Peter A. Schultz'
 'Kevin Leung'
 'E. B. Stechel'
_journal_name_full
;
Physical Review B
;
_journal_volume 59
_journal_year 1999
_journal_page_first 733
_journal_page_last 741
_publ_Section_title
;
 Small rings and amorphous tetrahedral carbon
;

_aflow_proto 'A_hP6_194_h'
_aflow_params 'a,c/a,x1'
_aflow_params_values '4.40445,0.568892824303,0.44799'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      4.40445
_cell_length_b      4.40445
_cell_length_c      2.50566
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1 C    6 h 0.44799 0.89598 0.25000 1.00000
```

Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h - POSCAR

```
A_hP6_194_h & a,c/a,x1 --params=4.40445,0.568892824303,0.44799 & P6_3/
    ↪ mmc D_{6h}^4 #194 (h) & hP6 & & C & hypothetical 3-member ring
    ↪  structure & P. A. Schultz, K. Leung and E. B. Stechel, PRB 59,
    ↪ 733-741 (1999)
   1.0000000000000000
   2.20222418612552   -3.81436418002642    0.00000000000000
   2.20222418612552    3.81436418002642    0.00000000000000
   0.00000000000000    0.00000000000000    2.50566256627303
    C
    6
Direct
   0.10401971341143    0.55200985670572    0.25000000000000    C    (6h)
   0.44799014329428    0.55200985670572    0.25000000000000    C    (6h)
   0.44799014329428    0.89598028658856    0.25000000000000    C    (6h)
   0.55200985670572    0.10401971341143    0.75000000000000    C    (6h)
   0.55200985670572    0.44799014329428    0.75000000000000    C    (6h)
   0.89598028658856    0.44799014329428    0.75000000000000    C    (6h)
```

CMo: AB_hP12_194_af_bf - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Molybdenum Carbide MAX Phase'
```

```
_chemical_formula_sum 'C Mo'

loop_
_publ_author_name
 'H. Nowotny'
 'R. Parth\'{e}'
 'R. Kieffer'
 'F. Benesovsky'
_journal_name_full
;
Monatshefte f\"{u}r Chemie und verwandte Teile anderer Wissenschaften
;
_journal_volume 85
_journal_year 1954
_journal_page_first 255
_journal_page_last 272
_publ_Section_title
;
 Das Dreistoffsystem: Molybd\"{a}n--Silizium--Kohlenstoff
;

_aflow_proto 'AB_hP12_194_af_bf'
_aflow_params 'a,c/a,z3,z4'
_aflow_params_values '3.01,4.85382059801,0.166,0.583'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP12'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      3.01000
_cell_length_b      3.01000
_cell_length_c      14.61000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    2 a 0.00000 0.00000 0.00000 1.00000
Mo1 Mo   2 b 0.00000 0.00000 0.25000 1.00000
C2  C    4 f 0.33333 0.66667 0.16600 1.00000
Mo2 Mo   4 f 0.33333 0.66667 0.58300 1.00000
```

CMo: AB_hP12_194_af_bf - POSCAR

```
AB_hP12_194_af_bf & a,c/a,z3,z4 --params=3.01,4.85382059801,0.166,0.583
    ↪ & P6_3/mmc  D_{6h}^4 #194 (abf^2) & hP12 & & CMo & MAX Phase &
    ↪ H. Nowotny et al. Monatsh.\ Chem.\ Verw.\ Tl. 85, 255-272 (1954
    ↪ )
   1.0000000000000000
   1.50500000000000   -2.60673646539116    0.00000000000000
   1.50500000000000    2.60673646539116    0.00000000000000
   0.00000000000000    0.00000000000000   14.61000000000000
    C    Mo
    6    6
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   C   (2a)
   0.00000000000000   0.00000000000000   0.50000000000000   C   (2a)
   0.33333333333333   0.66666666666667   0.16600000000000   C   (4f)
   0.33333333333333   0.66666666666667   0.33400000000000   C   (4f)
   0.66666666666667   0.33333333333333   0.66600000000000   C   (4f)
   0.66666666666667   0.33333333333333   0.83400000000000   C   (4f)
   0.00000000000000   0.00000000000000   0.25000000000000  Mo   (2b)
   0.00000000000000   0.00000000000000   0.75000000000000  Mo   (2b)
   0.33333333333333   0.66666666666667   0.58300000000000  Mo   (4f)
   0.33333333333333   0.66666666666667  -0.08300000000000  Mo   (4f)
   0.66666666666667   0.33333333333333   0.41700000000000  Mo   (4f)
   0.66666666666667   0.33333333333333   0.08300000000000  Mo   (4f)
```

α-La (A3'): A_hP4_194_ac - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha La'
_chemical_formula_sum 'La'

loop_
_publ_author_name
 'F.H. Spedding'
 'J.J. Hanak'
 'A.H. Daane'
_journal_name_full
;
Journal of the Less Common Metals
;
_journal_volume 3
_journal_year 1961
_journal_page_first 110
_journal_page_last 124
_publ_Section_title
;
 High temperature allotropy and thermal expansion of the rare-earth
    ↪ metals
;

# Found in  Donohue, pp. 83-86

_aflow_proto 'A_hP4_194_ac'
_aflow_params 'a,c/a'
_aflow_params_values '3.77,3.2175066313'
_aflow_Strukturbericht 'A3''
_aflow_Pearson 'hP4'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      3.77000
_cell_length_b      3.77000
_cell_length_c      12.13000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
La1 La   2 a 0.00000 0.00000 0.00000 1.00000
La2 La   2 c 0.33333 0.66667 0.25000 1.00000
```

α-La (A3'): A_hP4_194_ac - POSCAR

```
A_hP4_194_ac & a,c/a --params=3.77,3.2175066313 & P6_3/mmc  D_{6h}^4 #
    ↪ 194 (ac) & hP4 & A3' & La & alpha & F. H. Spedding, J. J. Hanak
    ↪ and A. H. Daane, J. Less-Common Metals 3, 110-124 (1961)
   1.0000000000000000
   1.88500000000000   -3.26491577226700    0.00000000000000
   1.88500000000000    3.26491577226700    0.00000000000000
   0.00000000000000    0.00000000000000   12.13000000000000
   La
    4
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   La   (2a)
   0.00000000000000   0.00000000000000   0.50000000000000   La   (2a)
   0.33333333333333   0.66666666666667   0.25000000000000   La   (2c)
   0.66666666666667   0.33333333333333   0.75000000000000   La   (2c)
```

Na_3As ($D0_{18}$): AB3_hP8_194_c_bf - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Sodium arsenide'
_chemical_formula_sum 'Na3 As'

loop_
_publ_author_name
 'G. Brauer'
 'E. Zintl'
_journal_name_full
;
Zeitschrift f\"{u}r Physikalische Chemie
;
_journal_volume 37B
_journal_year 1937
_journal_page_first 323
_journal_page_last 352
_publ_Section_title
;
 Konstitution von Phosphiden, Arseniden, Antimoniden und Wismutiden des
      ↪ Lithiums, Natriums und Kaliums
;

# Found in  Pearson's Handbook, Vol. I, pp. 1187

_aflow_proto 'AB3_hP8_194_c_bf'
_aflow_params 'a,c/a,z3'
_aflow_params_values '5.088,1.76533018868,-0.083'
_aflow_Strukturbericht 'D0_18'
_aflow_Pearson 'hP8'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      5.08800
_cell_length_b      5.08800
_cell_length_c      8.98200
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Na1 Na    2 b 0.00000 0.00000 0.25000 1.00000
As1 As    2 c 0.33333 0.66667 0.25000 1.00000
Na2 Na    4 f 0.33333 0.66667 -0.08300 1.00000
```

Na_3As ($D0_{18}$): AB3_hP8_194_c_bf - POSCAR

```
AB3_hP8_194_c_bf & a,c/a,z3 --params=5.088,1.76533018868,-0.083 & P6_3/
      ↪ mmc  D_{6h}^4 #194 (bcf) & hP8 & D0_18 & Na3As & & G. Brauer
      ↪ and E. Zintl, Zeitschrift f\"{u}r Physikalische Chemie 37B,
      ↪ 323-352 (1937)
   1.0000000000000000
   2.54400000000000   -4.40633725445500    0.00000000000000
   2.54400000000000    4.40633725445500    0.00000000000000
   0.00000000000000    0.00000000000000    8.98200000000000
   As    Na
    2     6
Direct
   0.33333333333333    0.66666666666667    0.25000000000000    As    (2c)
   0.66666666666667    0.33333333333333    0.75000000000000    As    (2c)
   0.00000000000000    0.00000000000000    0.25000000000000    Na    (2b)
   0.00000000000000    0.00000000000000    0.75000000000000    Na    (2b)
   0.33333333333333    0.66666666666667   -0.08300000000000    Na    (4f)
   0.33333333333333    0.66666666666667    0.58300000000000    Na    (4f)
   0.66666666666667    0.33333333333333    0.08300000000000    Na    (4f)
   0.66666666666667    0.33333333333333    0.41700000000000    Na    (4f)
```

$CaIn_2$: AB2_hP6_194_b_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ca In2'

loop_
_publ_author_name
 'A. Iandelli'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 330
_journal_year 1964
_journal_page_first 221
_journal_page_last 232
_publ_Section_title
;
 MX$_2$-Verbindungen der Erdalkali- und Seltenen Erdmetalle mit Gallium,
      ↪ Indium und Thallium
;

# Found in  Pearson's Alloys, pp. 499-501

_aflow_proto 'AB2_hP6_194_b_f'
_aflow_params 'a,c/a,z2'
_aflow_params_values '4.895,1.58324821246,0.045'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      4.89500
_cell_length_b      4.89500
_cell_length_c      7.75000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ca1 Ca    2 b 0.00000 0.00000 0.25000 1.00000
In1 In    4 f 0.33333 0.66667 0.04500 1.00000
```

$CaIn_2$: AB2_hP6_194_b_f - POSCAR

```
AB2_hP6_194_b_f & a,c/a,z2 --params=4.895,1.58324821246,0.045 & P6_3/mmc
      ↪  D_{6h}^4 #194 (bf) & hP6 & & CaIn2 & & A. Iandelli, ZAAC 330,
      ↪  221-232 (1964)
   1.0000000000000000
   2.44750000000000   -4.23919435152483    0.00000000000000
   2.44750000000000    4.23919435152483    0.00000000000000
   0.00000000000000    0.00000000000000    7.75000000000000
   Ca    In
    2     4
Direct
   0.00000000000000    0.00000000000000    0.25000000000000    Ca    (2b)
   0.00000000000000    0.00000000000000    0.75000000000000    Ca    (2b)
```

```
    0.33333333333333    0.66666666666667    0.04500000000000    In    (4f)
    0.33333333333333    0.66666666666667    0.45500000000000    In    (4f)
    0.66666666666667    0.33333333333333   -0.04500000000000    In    (4f)
    0.66666666666667    0.33333333333333    0.54500000000000    In    (4f)
```

BN (B_k): AB_hP4_194_c_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Boron Nitride'
_chemical_formula_sum 'B N'

loop_
_publ_author_name
 'R. S. Pease'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 5
_journal_year 1952
_journal_page_first 356
_journal_page_last 361
_publ_Section_title
;
 An X-ray study of boron nitride
;

# Found in  Wyckoff, Vol. I, pp. 184-185

_aflow_proto 'AB_hP4_194_c_d'
_aflow_params 'a,c/a'
_aflow_params_values '2.50399,2.66023426611'
_aflow_Strukturbericht 'B_k'
_aflow_Pearson 'hP4'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      2.50399
_cell_length_b      2.50399
_cell_length_c      6.66120
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1 B    2 c 0.33333 0.66667 0.25000 1.00000
N1 N    2 d 0.33333 0.66667 0.75000 1.00000
```

BN (B_k): AB_hP4_194_c_d - POSCAR

```
AB_hP4_194_c_d & a,c/a --params=2.50399,2.66023426611 & P6_3/mmc  D_{6h
    ↪ }^4 #194 (cd) & hP4 & B_k & BN & & R. S. Pease, Acta Cryst. 5,
    ↪ 356-361 (1952)
   1.0000000000000000
   1.25199500000000   -2.16851895082220    0.00000000000000
   1.25199500000000    2.16851895082220    0.00000000000000
   0.00000000000000    0.00000000000000    6.66120000000000
    B    N
    2    2
Direct
   0.33333333333333    0.66666666666667    0.25000000000000    B    (2c)
   0.66666666666667    0.33333333333333    0.75000000000000    B    (2c)
   0.33333333333333    0.66666666666667    0.75000000000000    N    (2d)
   0.66666666666667    0.33333333333333    0.25000000000000    N    (2d)
```

$AlCCr_2$: ABC2_hP8_194_d_a_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'H-Phase'
_chemical_formula_sum 'Al C Cr2'

loop_
_publ_author_name
 'W. Jeitschko'
 'H. Nowotny'
 'F. Benesovsky'
_journal_name_full
;
Monatshefte f\"{u}r Chemie und verwandte Teile anderer Wissenschaften
;
_journal_volume 94
_journal_year 1963
_journal_page_first 672
_journal_page_last 676
_publ_Section_title
;
 Kohlenstoffhaltige tern\"{a}re Verbindungen (H-Phase)
;

# Found in  Pearson's Handbook, Vol. I, pp. 677

_aflow_proto 'ABC2_hP8_194_d_a_f'
_aflow_params 'a,c/a,z3'
_aflow_params_values '2.86,4.48251748252,0.086'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP8'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      2.86000
_cell_length_b      2.86000
_cell_length_c      12.82000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    2 a 0.00000 0.00000 0.00000 1.00000
Al1 Al   2 d 0.33333 0.66667 0.75000 1.00000
Cr1 Cr   4 f 0.33333 0.66667 0.08600 1.00000
```

$AlCCr_2$: ABC2_hP8_194_d_a_f - POSCAR

```
ABC2_hP8_194_d_a_f & a,c/a,z3 --params=2.86,4.48251748252,0.086 & P6_3/
    ↪ mmc      D_{6h}^4 #194 (adf) & hP8 & & AlCCr2 & H-Phase & W.
    ↪ Jeitschko, H. Nowotny and F. Benesovsky, Monatshefte f"{u}r
    ↪ Chemie 94, 672-676 (1963)
   1.0000000000000000
   1.43000000000000   -2.47683265482300    0.00000000000000
   1.43000000000000    2.47683265482300    0.00000000000000
   0.00000000000000    0.00000000000000   12.82000000000000
   Al    C    Cr
    2    2    4
Direct
   0.33333333333333    0.66666666666667    0.75000000000000    Al    (2d)
   0.66666666666667    0.33333333333333    0.25000000000000    Al    (2d)
```

```
    0.00000000000000    0.00000000000000    0.00000000000000    C    (2a)
    0.00000000000000    0.00000000000000    0.50000000000000    C    (2a)
    0.33333333333333    0.66666666666667    0.08600000000000    Cr   (4f)
    0.33333333333333    0.66666666666667    0.41400000000000    Cr   (4f)
    0.66666666666667    0.33333333333333   -0.08600000000000    Cr   (4f)
    0.66666666666667    0.33333333333333    0.58600000000000    Cr   (4f)
```

Ni_3Sn ($D0_{19}$): A3B_hP8_194_h_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ni3 Sn'

loop_
_publ_author_name
 'Andrei L. Lyubimtsev'
 'Alexey I. Baranov'
 'Andreas Fischer'
 'Lars Kloo'
 'Boris A. Popovkin'
_journal_name_full
;
Journal of Alloys and Compounds
;
_journal_volume 340
_journal_year 2002
_journal_page_first 167
_journal_page_last 172
_publ_Section_title
;
 The structure and bonding of Ni$_3$Sn
;

_aflow_proto 'A3B_hP8_194_h_c'
_aflow_params 'a,c/a,x2'
_aflow_params_values '5.295,0.802077431539,0.8392'
_aflow_Strukturbericht 'D0_19'
_aflow_Pearson 'hP8'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      5.29500
_cell_length_b      5.29500
_cell_length_c      4.24700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Sn1 Sn    2 c 0.33333 0.66667 0.25000 1.00000
Ni1 Ni    6 h 0.83920 0.67840 0.25000 1.00000
```

Ni_3Sn ($D0_{19}$): A3B_hP8_194_h_c - POSCAR

```
A3B_hP8_194_h_c & a,c/a,x2 --params=5.295,0.802077431539,0.8392 & P6_3/
    ↪ mmc D_{6h}^4 #194 (ch) & hP8 & D0_19 & Ni3Sn & & A. L.
    ↪ Lyubimtsev et al., J. Alloys Compd. 340, 167-172 (2002)
   1.0000000000000000
   2.64750000000000   -4.58560451303900    0.00000000000000
   2.64750000000000    4.58560451303900    0.00000000000000
   0.00000000000000    0.00000000000000    4.24700000000000
   Ni    Sn
    6     2
Direct
   0.16080000000000    0.32160000000000    0.75000000000000    Ni    (6h)
   0.16080000000000    0.83920000000000    0.75000000000000    Ni    (6h)
   0.32160000000000    0.16080000000000    0.25000000000000    Ni    (6h)
   0.67840000000000    0.83920000000000    0.75000000000000    Ni    (6h)
   0.83920000000000    0.16080000000000    0.25000000000000    Ni    (6h)
   0.83920000000000    0.67840000000000    0.25000000000000    Ni    (6h)
   0.33333333333333    0.66666666666667    0.25000000000000    Sn    (2c)
   0.66666666666667    0.33333333333333    0.75000000000000    Sn    (2c)
```

Hexagonal Graphite (A9): A_hP4_194_bc - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Graphite'
_chemical_formula_sum 'C'

loop_
_publ_author_name
 'Peter Trucano'
 'Ruey Chen'
_journal_name_full
;
Nature
;
_journal_volume 258
_journal_year 1975
_journal_page_first 136
_journal_page_last 137
_publ_Section_title
;
 Structure of graphite by neutron diffraction
;

# Found in AMS Database

_aflow_proto 'A_hP4_194_bc'
_aflow_params 'a,c/a'
_aflow_params_values '2.464,2.72362012987'
_aflow_Strukturbericht 'A9'
_aflow_Pearson 'hP4'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      2.46400
_cell_length_b      2.46400
_cell_length_c      6.71100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1 C    2 b 0.00000 0.00000 0.25000 1.00000
C2 C    2 c 0.33333 0.66667 0.25000 1.00000
```

Hexagonal Graphite (A9): A_hP4_194_bc - POSCAR

```
A_hP4_194_bc & a,c/a --params=2.464,2.72362012987 & P6_3/mmc D_{6h}^
    ↪ 4 #194 (bc) & hP4 & A9 & C & Graphite (unbuckled) & P. Trucano
    ↪ and R. Chen, Nature 258, 136-137 (1975)
   1.0000000000000000
   1.23200000000000   -2.13388659492486    0.00000000000000
   1.23200000000000    2.13388659492486    0.00000000000000
   0.00000000000000    0.00000000000000    6.71100000000000
```

```
    C
    4
Direct
   0.00000000000000   0.00000000000000   0.25000000000000   C   (2b)
   0.00000000000000   0.00000000000000   0.75000000000000   C   (2b)
   0.33333333333333   0.66666666666667   0.25000000000000   C   (2c)
   0.66666666666667   0.33333333333333   0.75000000000000   C   (2c)
```

Molybdenite (MoS_2, C7): AB2_hP6_194_c_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Molybdenite'
_chemical_formula_sum 'Mo S2'

loop_
_publ_author_name
 'B. Sch\"{o}nfeld'
 'J. J. Huang'
 'S. C. Moss'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 39
_journal_year 1983
_journal_page_first 404
_journal_page_last 407
_publ_Section_title
;
 Anisotropic Mean-Square Displacements (MSD) in single Crystals of 2H-
      ↪ and 3R-MoS$_2$
;

# Found in  AMS Database

_aflow_proto 'AB2_hP6_194_c_f'
_aflow_params 'a,c/a,z2'
_aflow_params_values '3.161,3.8895919013,0.6275'
_aflow_Strukturbericht 'C7'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a     3.16100
_cell_length_b     3.16100
_cell_length_c     12.29500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mo1 Mo   2 c 0.33333 0.66667 0.25000 1.00000
S1  S    4 f 0.33333 0.66667 0.62750 1.00000
```

Molybdenite (MoS_2, C7): AB2_hP6_194_c_f - POSCAR

```
AB2_hP6_194_c_f & a,c/a,z2 --params=3.161,3.8895919013,0.6275 & P6_3/mmc
      ↪ D_{6h}^4 #194 (cf) & hP6 & C7 & MoS2 & & B. Sch"{o}nfeld, J.
      ↪ J. Huang and S. C. Moss, Acta Cryst. B 39, 404-407 (1983)
   1.0000000000000000
   1.58050000000000   -2.73750630136261   0.00000000000000
   1.58050000000000    2.73750630136261   0.00000000000000
   0.00000000000000    0.00000000000000  12.29500000000000
   Mo    S
    2    4
Direct
   0.33333333333333   0.66666666666667   0.25000000000000   Mo   (2c)
   0.66666666666667   0.33333333333333   0.75000000000000   Mo   (2c)
   0.33333333333333   0.66666666666667  -0.12750000000000   S    (4f)
   0.33333333333333   0.66666666666667   0.62750000000000   S    (4f)
   0.66666666666667   0.33333333333333   0.12750000000000   S    (4f)
   0.66666666666667   0.33333333333333   0.37250000000000   S    (4f)
```

W_2B_5 ($D8_h$): A5B2_hP14_194_abdf_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Tungsten boride'
_chemical_formula_sum 'W2 B5'

loop_
_publ_author_name
 'Roland Kiessling'
_journal_name_full
;
Acta Chemica Scandinavica
;
_journal_volume 1
_journal_year 1947
_journal_page_first 893
_journal_page_last 916
_publ_Section_title
;
 The Crystal Structures of Molybdenum and Tungsten Borides
;

# Found in  Wyckoff, Vol. II, pp. 188-189

_aflow_proto 'A5B2_hP14_194_abdf_f'
_aflow_params 'a,c/a,z4,z5'
_aflow_params_values '2.982,4.651240778,0.528,0.139'
_aflow_Strukturbericht 'D8_h'
_aflow_Pearson 'hP14'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a     2.98200
_cell_length_b     2.98200
_cell_length_c     13.87000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
B1 B   2 a 0.00000 0.00000 0.00000 1.00000
B2 B   2 b 0.00000 0.00000 0.25000 1.00000
B3 B   2 d 0.33333 0.66667 0.75000 1.00000
B4 B   4 f 0.33333 0.66667 0.52800 1.00000
W1 W   4 f 0.33333 0.66667 0.13900 1.00000
```

W_2B_5 ($D8_h$): A5B2_hP14_194_abdf_f - POSCAR

```
A5B2_hP14_194_abdf_f & a,c/a,z4,z5 --params=2.982,4.651240778,0.528,
      ↪ 0.139 & P6_3/mmc D_{6h}^4 #194 (abdf^2) & hP14 & D8_h & W2B5 &
      ↪ epsilon & R Kiessling, Acta Chem. Scand. 1, 893-916 (1947)
   1.0000000000000000
   1.49100000000000   -2.58248775408520   0.00000000000000
```

```
   1.49100000000000   2.58248775408520   0.00000000000000
   0.00000000000000   0.00000000000000  13.87000000000000
    B    W
   10    4
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   B   (2a)
   0.00000000000000   0.00000000000000   0.50000000000000   B   (2a)
   0.00000000000000   0.00000000000000   0.25000000000000   B   (2b)
   0.00000000000000   0.00000000000000   0.75000000000000   B   (2b)
   0.33333333333333   0.66666666666667   0.75000000000000   B   (2d)
   0.66666666666667   0.33333333333333   0.25000000000000   B   (2d)
   0.33333333333333   0.66666666666667  -0.02800000000000   B   (4f)
   0.33333333333333   0.66666666666667   0.52800000000000   B   (4f)
   0.66666666666667   0.33333333333333   0.02800000000000   B   (4f)
   0.66666666666667   0.33333333333333   0.47200000000000   B   (4f)
   0.33333333333333   0.66666666666667   0.13900000000000   W   (4f)
   0.33333333333333   0.66666666666667   0.36100000000000   W   (4f)
   0.66666666666667   0.33333333333333  -0.13900000000000   W   (4f)
   0.66666666666667   0.33333333333333   0.63900000000000   W   (4f)
```

$MgZn_2$ Hexagonal Laves (C14): AB2_hP12_194_f_ah - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Hexagonal Laves'
_chemical_formula_sum 'Mg Zn2'

loop_
_publ_author_name
 'T. Ohba'
 'Y. Kitano'
 'Y. Komura'
_journal_name_full
;
Acta Crystallographic C
;
_journal_volume 40
_journal_year 1984
_journal_page_first 1
_journal_page_last 5
_publ_Section_title
;
 The charge-density study of the Laves phases, MgZn$_2$ and MgCu$_2$
;

_aflow_proto 'AB2_hP12_194_f_ah'
_aflow_params 'a,c/a,z2,x3'
_aflow_params_values '5.223,1.64005360904,0.06286,0.83048'
_aflow_Strukturbericht 'C14'
_aflow_Pearson 'hP12'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      5.22300
_cell_length_b      5.22300
_cell_length_c      8.56600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Zn1 Zn   2 a 0.00000 0.00000 0.00000 1.00000
Mg1 Mg   4 f 0.33333 0.66667 0.06286 1.00000
Zn2 Zn   6 h 0.83048 0.16952 0.25000 1.00000
```

$MgZn_2$ Hexagonal Laves (C14): AB2_hP12_194_f_ah - POSCAR

```
AB2_hP12_194_f_ah & a,c/a,z2,x3 --params=5.223,1.64005360904,0.06286,
    ↪ 0.83048 & P6_3/mmc D_{6h}^4 #194 (afh) & hP12 & C14 & MgZn2 &
    ↪ Laves & T. Ohba, Y. Kitano and Y. Komura, Acta Cryst. C 40, 1-5
    ↪ (1984)
   1.000000000000000
   2.61150000000000  -4.52325068396612   0.00000000000000
   2.61150000000000   4.52325068396612   0.00000000000000
   0.00000000000000   0.00000000000000   8.56600000000000
   Mg   Zn
    4    8
Direct
   0.33333333333333   0.66666666666667   0.06286000000000   Mg   (4f)
   0.33333333333333   0.66666666666667   0.43714000000000   Mg   (4f)
   0.66666666666667   0.33333333333333  -0.06286000000000   Mg   (4f)
   0.66666666666667   0.33333333333333   0.56286000000000   Mg   (4f)
   0.00000000000000   0.00000000000000   0.00000000000000   Zn   (2a)
   0.00000000000000   0.00000000000000   0.50000000000000   Zn   (2a)
   0.16952000000000   0.33904000000000   0.75000000000000   Zn   (6h)
   0.16952000000000   0.83048000000000   0.75000000000000   Zn   (6h)
   0.33904000000000   0.16952000000000   0.25000000000000   Zn   (6h)
   0.66096000000000   0.83048000000000   0.75000000000000   Zn   (6h)
   0.83048000000000   0.16952000000000   0.25000000000000   Zn   (6h)
   0.83048000000000   0.66096000000000   0.25000000000000   Zn   (6h)
```

LiBC: ABC_hP6_194_c_d_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Li B C'

loop_
_publ_author_name
 'Michael W\"{o}rle'
 'Reinhard Nesper'
 'Gunter Mair'
 'Martin Schwarz'
 'Hans Georg Von Schnering'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 621
_journal_year 1995
_journal_page_first 1153
_journal_page_last 1159
_publ_Section_title
;
 LiBC -- ein vollst\"{a}ndig interkalierter Heterographit
;

_aflow_proto 'ABC_hP6_194_c_d_a'
_aflow_params 'a,c/a'
_aflow_params_values '2.752,2.56468023256'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      2.75200
_cell_length_b      2.75200
_cell_length_c      7.05800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
```

```
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Li1  Li    2  a  0.00000  0.00000  0.00000  1.00000
B1   B     2  c  0.33333  0.66667  0.25000  1.00000
C1   C     2  d  0.33333  0.66667  0.75000  1.00000
```

LiBC: ABC_hP6_194_c_d_a - POSCAR

```
ABC_hP6_194_c_d_a & a,c/a --params=2.752,2.56468023256 & P6_3/mmc  D_{6h
    ↪ }^4 #194 (acd) & hP6 & & LiBC & & W\"orle et al., Z. Anorg.
    ↪ Allg. Chem. 621, 1153-1159 (1995)
   1.0000000000000000
   1.37600000000000   -2.38330191121500    0.00000000000000
   1.37600000000000    2.38330191121500    0.00000000000000
   0.00000000000000    0.00000000000000    7.05800000000000
    B    C    Li
    2    2    2
Direct
   0.33333333333333    0.66666666666667    0.25000000000000    B    (2c)
   0.66666666666667    0.33333333333333    0.75000000000000    B    (2c)
   0.33333333333333    0.66666666666667    0.75000000000000    C    (2d)
   0.66666666666667    0.33333333333333    0.25000000000000    C    (2d)
   0.00000000000000    0.00000000000000    0.00000000000000   Li    (2a)
   0.00000000000000    0.00000000000000    0.50000000000000   Li    (2a)
```

Lonsdaleite (Hexagonal Diamond): A_hP4_194_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Lonsdaleite'
_chemical_formula_sum 'C'

loop_
_publ_author_name
 'Akira Yoshiasa'
 'Yu Murai'
 'Osamu Ohtaka'
 'Tomoo Katsura'
_journal_name_full
;
Japanese Journal of Applied Physics
;
_journal_volume 42
_journal_year 2003
_journal_page_first 1694
_journal_page_last 1704
_publ_Section_title
;
 Detailed Structures of Hexagonal Diamond (lonsdaleite) and
    ↪ Wurtzite-type BN
;

_aflow_proto 'A_hP4_194_f'
_aflow_params 'a,c/a,z1'
_aflow_params_values '2.508,1.66786283892,0.05995'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP4'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      2.50800
_cell_length_b      2.50800
_cell_length_c      4.18300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    4  f  0.33333  0.66667  0.05995  1.00000
```

Lonsdaleite (Hexagonal Diamond): A_hP4_194_f - POSCAR

```
A_hP4_194_f & a,c/a,z1 --params=2.508,1.66786283892,0.05995 & P6_3/mmc
    ↪ D_{6h}^4 #194 (f) & hP4 & & C & Lonsdaleite (hexagonal diamond)
    ↪ & A. Yoshiasa, Y. Murai, O. Ohtaka and T. Katsura, Jpn. J.
    ↪ Appl. Phys. 42, 1694-1704 (2003)
   1.0000000000000000
   1.25400000000000   -2.17199171269100    0.00000000000000
   1.25400000000000    2.17199171269100    0.00000000000000
   0.00000000000000    0.00000000000000    4.18300000000000
    C
    4
Direct
   0.33333333333333    0.66666666666667    0.05994501553900    C    (4f)
   0.33333333333333    0.66666666666667    0.44005498446100    C    (4f)
   0.66666666666667    0.33333333333333   -0.05994501553900    C    (4f)
   0.66666666666667    0.33333333333333    0.55994501553900    C    (4f)
```

Ni_2In ($B8_2$): AB2_hP6_194_c_ad - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ni2 In'

loop_
_publ_author_name
 'M. Ellner'
_journal_name_full
;
Journal of the Less Common Metals
;
_journal_volume 48
_journal_year 1976
_journal_page_first 21
_journal_page_last 52
_publ_Section_title
;
 "{U}ber die kristallchemischen parameter der Ni-, Co- und Fe-haltigen
    ↪ phasen vom NiAs-Typ
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_0450621

_aflow_proto 'AB2_hP6_194_c_ad'
_aflow_params 'a,c/a'
_aflow_params_values '4.186,1.22527472527'
_aflow_Strukturbericht 'B8_2'
_aflow_Pearson 'hP6'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      4.18600
_cell_length_b      4.18600
_cell_length_c      5.12900
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
```

```
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ni1  Ni    2  a  0.00000  0.00000  0.00000  1.00000
In1  In    2  c  0.33333  0.66667  0.25000  1.00000
Ni2  Ni    2  d  0.33333  0.66667  0.75000  1.00000
```

Ni_2In ($B8_2$): AB2_hP6_194_c_ad - POSCAR

```
AB2_hP6_194_c_ad & a,c/a --params=4.186,1.22527472527 & P6_3/mmc  D_{6h
    ↪ }^4 #194 (acd) & hP6 & B8_2 & Ni2In & & M. Ellner, J.
    ↪ Less-Common Met. 48, 21-52 (1976)
   1.0000000000000000
   2.09300000000000   -3.62518234024200    0.00000000000000
   2.09300000000000    3.62518234024200    0.00000000000000
   0.00000000000000    0.00000000000000    5.12900000000000
   In    Ni
    2     4
Direct
   0.33333333333333    0.66666666666667    0.25000000000000    In    (2c)
   0.66666666666667    0.33333333333333    0.75000000000000    In    (2c)
   0.00000000000000    0.00000000000000    0.00000000000000    Ni    (2a)
   0.00000000000000    0.00000000000000    0.50000000000000    Ni    (2a)
   0.33333333333333    0.66666666666667    0.75000000000000    Ni    (2d)
   0.66666666666667    0.33333333333333    0.25000000000000    Ni    (2d)
```

AlN_3Ti_4: AB3C4_hP16_194_c_af_ef - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'MAX Phase'
_chemical_formula_sum 'Al N3 Ti4'

loop_
_publ_author_name
 'M. W. Barsoum'
 'C. J. Rawn'
 'T. El-Raghy'
 'A. T. Procopio'
 'W. D. Porter'
 'H. Wang'
 'C. R. Hubbard'
_journal_name_full
;
Journal of Applied Physics
;
_journal_volume 87
_journal_year 2000
_journal_page_first 8407
_journal_page_last 8414
_publ_Section_title
;
 Thermal Properties of Ti$_4$AlN$_3$
;

_aflow_proto 'AB3C4_hP16_194_c_af_ef'
_aflow_params 'a,c/a,z3,z4,z5'
_aflow_params_values '2.988,7.82195448461,0.1543,0.605,0.0539'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'hP16'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      2.98800
_cell_length_b      2.98800
_cell_length_c      23.37200
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
N1  N    2  a  0.00000  0.00000  0.00000  1.00000
Al1  Al  2  c  0.33333  0.66667  0.25000  1.00000
Ti1  Ti  4  e  0.00000  0.00000  0.15430  1.00000
N2  N    4  f  0.33333  0.66667  0.60500  1.00000
Ti2  Ti  4  f  0.33333  0.66667  0.05390  1.00000
```

AlN_3Ti_4: AB3C4_hP16_194_c_af_ef - POSCAR

```
AB3C4_hP16_194_c_af_ef & a,c/a,z3,z4,z5 --params=2.988,7.82195448461,
    ↪ 0.1543,0.605,0.0539 & P6_3/mmc  D_{6h}^4 #194 (acef^2) & hP16 &
    ↪ & AlN3Ti4 & MAX Phase & M. W. Barsoum et al., JAP 87,
    ↪ 8407-8414 (2000)
   1.0000000000000000
   1.49400000000000   -2.58768390650800    0.00000000000000
   1.49400000000000    2.58768390650800    0.00000000000000
   0.00000000000000    0.00000000000000   23.37200000000000
   Al    N    Ti
    2    6     8
Direct
   0.33333333333333    0.66666666666667    0.25000000000000    Al    (2c)
   0.66666666666667    0.33333333333333    0.75000000000000    Al    (2c)
   0.00000000000000    0.00000000000000    0.00000000000000    N     (2a)
   0.00000000000000    0.00000000000000    0.50000000000000    N     (2a)
   0.33333333333333    0.66666666666667    0.60500000000000    N     (4f)
   0.33333333333333    0.66666666666667    0.89500000000000    N     (4f)
   0.66666666666667    0.33333333333333    0.10500000000000    N     (4f)
   0.66666666666667    0.33333333333333    0.39500000000000    N     (4f)
   0.00000000000000    0.00000000000000    0.15430000000000    Ti    (4e)
   0.00000000000000    0.00000000000000    0.34570000000000    Ti    (4e)
   0.00000000000000    0.00000000000000    0.65430000000000    Ti    (4e)
   0.00000000000000    0.00000000000000    0.84570000000000    Ti    (4e)
   0.33333333333333    0.66666666666667    0.05390000000000    Ti    (4f)
   0.33333333333333    0.66666666666667    0.44610000000000    Ti    (4f)
   0.66666666666667    0.33333333333333   -0.05390000000000    Ti    (4f)
   0.66666666666667    0.33333333333333    0.55390000000000    Ti    (4f)
```

Hexagonal Close Packed (Mg, A3): A_hP2_194_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Magnesium'
_chemical_formula_sum 'Mg'

loop_
_publ_author_name
 'F. W. von Batchelder'
 'R. F. Raeuchle'
_journal_name_full
;
Physical Review
;
_journal_volume 105
_journal_year 1957
_journal_page_first 59
_journal_page_last 61
_publ_Section_title
;
 Lattice Constants and Brillouin Zone Overlap in Dilute Magnesium Alloys
;

# Found in  Donohue, pp. 39-40

_aflow_proto 'A_hP2_194_c'
_aflow_params 'a,c/a'
_aflow_params_values '3.2093,1.62359393014'
_aflow_Strukturbericht 'A3'
_aflow_Pearson 'hP2'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a      3.20930
_cell_length_b      3.20930
_cell_length_c      5.21060
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
```

```
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mg1 Mg    2 c 0.33333 0.66667 0.25000 1.00000
```

Hexagonal Close Packed (Mg, A3): A_hP2_194_c - POSCAR

```
A_hP2_194_c & a,c/a --params=3.2093,1.62359393014 & P6_3/mmc D_{6h}^4 #
    ↪ 194 (c) & hP2 & A3 & Mg & hcp & F. W. von Batchelder and R. F.
    ↪ Raeuchle, Phys. Rev. 105, 59-61 (1957)
   1.0000000000000000
   1.60465000000000  -2.77933532836500   0.00000000000000
   1.60465000000000   2.77933532836500   0.00000000000000
   0.00000000000000   0.00000000000000   5.21060000000000
   Mg
    2
Direct
   0.33333333333333   0.66666666666667   0.25000000000000   Mg   (2c)
   0.66666666666667   0.33333333333333   0.75000000000000   Mg   (2c)
```

$MgNi_2$ Hexagonal Laves (C36): AB2_hP24_194_ef_fgh - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Hexagonal Laves'
_chemical_formula_sum 'Mg Ni2'

loop_
_publ_author_name
 'Y. Komura'
 'K. Tokunaga'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 36
_journal_year 1980
_journal_page_first 1548
_journal_page_last 1554
_publ_Section_title
;
 Structural studies of stacking variants in Mg-base Friauf-Laves phases
;

_aflow_proto 'AB2_hP24_194_ef_fgh'
_aflow_params 'a,c/a,z1,z2,z3,x5'
_aflow_params_values '4.824,3.28067993367,0.04598,0.84417,0.12514,
    ↪ 0.16429'
_aflow_Strukturbericht 'C36'
_aflow_Pearson 'hP24'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a    4.82400
_cell_length_b    4.82400
_cell_length_c    15.82600
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mg1 Mg    4 e 0.00000 0.00000 0.04598 1.00000
Mg2 Mg    4 f 0.33333 0.66667 0.84417 1.00000
Ni1 Ni    4 f 0.33333 0.66667 0.12514 1.00000
Ni2 Ni    6 g 0.50000 0.00000 0.00000 1.00000
Ni3 Ni    6 h 0.16429 0.32858 0.25000 1.00000
```

$MgNi_2$ Hexagonal Laves (C36): AB2_hP24_194_ef_fgh - POSCAR

```
AB2_hP24_194_ef_fgh & a,c/a,z1,z2,z3,x5 --params=4.824,3.28067993367,
    ↪ 0.04598,0.84417,0.12514,0.16429 & P6_3/mmc D_{6h}^4 #194 (ef^
    ↪ 2gh) & hP24 & C36 & MgNi2 & Laves & Y. Komura and K. Tokunaga,
    ↪ Acta Cryst. B 36, 1548-1554 (1980)
   1.0000000000000000
   2.41200000000000  -4.17770654785613   0.00000000000000
   2.41200000000000   4.17770654785613   0.00000000000000
   0.00000000000000   0.00000000000000  15.82600000000000
   Mg   Ni
    8   16
Direct
   0.00000000000000   0.00000000000000   0.04598000000000   Mg   (4e)
   0.00000000000000   0.00000000000000  -0.04598000000000   Mg   (4e)
   0.00000000000000   0.00000000000000   0.45402000000000   Mg   (4e)
   0.00000000000000   0.00000000000000   0.54598000000000   Mg   (4e)
   0.33333333333333   0.66666666666667   0.65583000000000   Mg   (4f)
   0.33333333333333   0.66666666666667   0.84417000000000   Mg   (4f)
   0.66666666666667   0.33333333333333   0.15583000000000   Mg   (4f)
   0.66666666666667   0.33333333333333   0.34417000000000   Mg   (4f)
   0.33333333333333   0.66666666666667   0.12514000000000   Ni   (4f)
   0.33333333333333   0.66666666666667   0.37486000000000   Ni   (4f)
   0.66666666666667   0.33333333333333   0.62514000000000   Ni   (4f)
   0.66666666666667   0.33333333333333   0.87486000000000   Ni   (4f)
   0.00000000000000   0.50000000000000   0.00000000000000   Ni   (6g)
   0.00000000000000   0.50000000000000   0.50000000000000   Ni   (6g)
   0.50000000000000   0.00000000000000   0.00000000000000   Ni   (6g)
   0.50000000000000   0.00000000000000   0.50000000000000   Ni   (6g)
   0.50000000000000   0.50000000000000   0.00000000000000   Ni   (6g)
   0.50000000000000   0.50000000000000   0.50000000000000   Ni   (6g)
   0.16429000000000   0.32858000000000   0.25000000000000   Ni   (6h)
   0.16429000000000   0.83571000000000   0.25000000000000   Ni   (6h)
   0.32858000000000   0.16429000000000   0.75000000000000   Ni   (6h)
   0.67142000000000   0.83571000000000   0.25000000000000   Ni   (6h)
   0.83571000000000   0.16429000000000   0.75000000000000   Ni   (6h)
   0.83571000000000   0.67142000000000   0.75000000000000   Ni   (6h)
```

Covellite (CuS, B18): AB_hP12_194_df_ce - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Covellite'
_chemical_formula_sum 'Cu S'

loop_
_publ_author_name
 'Masaaki Ohmasa'
 'Masatoshi Suzuki'
 'Yoshio Tak\'{e}uchi'
_journal_name_full
;
Mineralogical Journal
;
_journal_volume 8
_journal_year 1977
_journal_page_first 311
_journal_page_last 319
_publ_Section_title
;
 A refinement of the crystal structure of covellite, CuS
;

_aflow_proto 'AB_hP12_194_df_ce'
_aflow_params 'a,c/a,z3,z4'
_aflow_params_values '3.976,4.12022132797,0.0637,0.10724'
_aflow_Strukturbericht 'B18'
_aflow_Pearson 'hP12'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a    3.97600
_cell_length_b    3.97600
_cell_length_c    16.38200
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
```

```
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x-y,x,z+1/2
3  -y,x-y,z
4  -x,-y,z+1/2
5  -x+y,-x,z
6  y,-x+y,z+1/2
7  x-y,-y,-z
8  x,x-y,-z+1/2
9  y,x,-z
10  -x+y,y,-z+1/2
11  -x,-x+y,-z
12  -y,-x,-z+1/2
13  -x,-y,-z
14  -x+y,-x,-z+1/2
15  y,-x+y,-z
16  x,y,-z+1/2
17  x-y,x,-z
18  -y,x-y,-z+1/2
19  -x+y,y,z
20  -x,-x+y,z+1/2
21  -y,-x,z
22  x-y,-y,z+1/2
23  x,x-y,z
24  y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
S1  S     2  c  0.33333  0.66667  0.25000  1.00000
Cu1  Cu   2  d  0.33333  0.66667  0.75000  1.00000
S2  S     4  e  0.00000  0.00000  0.06370  1.00000
Cu2  Cu   4  f  0.33333  0.66667  0.10724  1.00000
```

Covellite (CuS, B18): AB_hP12_194_df_ce - POSCAR

```
AB_hP12_194_df_ce & a,c/a,z3,z4 --params=3.976,4.12022132797,0.0637,
    ↪ 0.10724 & P6_3/mmc  D_{6h}^4 #194 (cdef) & hP12 & B18 & CuS &
    ↪ Covellite & M. Ohmasa, M. Suzuki and Y. Tak\'{e}uchi,
    ↪ Mineralogical Journal 8, 311-319 (1977)
   1.0000000000000000
   1.98800000000000   -3.44331700544700    0.00000000000000
   1.98800000000000    3.44331700544700    0.00000000000000
   0.00000000000000    0.00000000000000   16.38200000000000
   Cu    S
    6    6
Direct
   0.33333333333300    0.66666666666700    0.75000000000000   Cu    (2d)
   0.66666666666700    0.33333333333300    0.25000000000000   Cu    (2d)
   0.33333333333300    0.66666666666700    0.10724000000000   Cu    (4f)
   0.33333333333300    0.66666666666700    0.39276000000000   Cu    (4f)
   0.66666666666700    0.33333333333300    0.60724000000000   Cu    (4f)
   0.66666666666700    0.33333333333300    0.89276000000000   Cu    (4f)
   0.33333333333300    0.66666666666700    0.25000000000000    S    (2c)
   0.66666666666700    0.33333333333300    0.75000000000000    S    (2c)
   0.00000000000000    0.00000000000000    0.06370000000000    S    (4e)
   0.00000000000000    0.00000000000000   -0.06370000000000    S    (4e)
   0.00000000000000    0.00000000000000    0.43630000000000    S    (4e)
   0.00000000000000    0.00000000000000    0.56370000000000    S    (4e)
```

NiAs ($B8_1$): AB_hP4_194_c_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ni As'

loop_
_publ_author_name
 'P. Brand'
 'J. Briest'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 337
_journal_year 1965
_journal_page_first 209
_journal_page_last 213
_publ_Section_title
;
 Das quasi-bin\"{a}re System NiAs--Ni$_{1.5}$Sn
;

# Found in  Pearson's Handbook, Vol. I, pp. 1192

_aflow_proto 'AB_hP4_194_c_a'
_aflow_params 'a,c/a'
_aflow_params_values '3.619,1.39375518099'
_aflow_Strukturbericht 'B8_1'
_aflow_Pearson 'hP4'
_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
_symmetry_Int_Tables_number 194

_cell_length_a     3.61900
_cell_length_b     3.61900
_cell_length_c     5.04400
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x-y,x,z+1/2
3  -y,x-y,z
4  -x,-y,z+1/2
5  -x+y,-x,z
6  y,-x+y,z+1/2
7  x-y,-y,-z
8  x,x-y,-z+1/2
9  y,x,-z
10  -x+y,y,-z+1/2
11  -x,-x+y,-z
12  -y,-x,-z+1/2
13  -x,-y,-z
14  -x+y,-x,-z+1/2
15  y,-x+y,-z
16  x,y,-z+1/2
17  x-y,x,-z
18  -y,x-y,-z+1/2
19  -x+y,y,z
20  -x,-x+y,z+1/2
21  -y,-x,z
22  x-y,-y,z+1/2
23  x,x-y,z
24  y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ni1  Ni    2  a  0.00000  0.00000  0.00000  1.00000
As1  As    2  c  0.33333  0.66667  0.25000  1.00000
```

NiAs ($B8_1$): AB_hP4_194_c_a - POSCAR

```
AB_hP4_194_c_a & a,c/a --params=3.619,1.39375518099 & P6_3/mmc  D_{6h}^4
    ↪ #194 (ac) & hP4 & B8_1 & NiAs & & P. Brand and J. Briest, ZAAC
    ↪ 337, 209-213 (1965)
   1.0000000000000000
   1.80950000000000   -3.13414593629600    0.00000000000000
   1.80950000000000    3.13414593629600    0.00000000000000
   0.00000000000000    0.00000000000000    5.04400000000000
   As    Ni
    2    2
Direct
   0.33333333333333    0.66666666666667    0.25000000000000   As    (2c)
   0.66666666666667    0.33333333333333    0.75000000000000   As    (2c)
   0.00000000000000    0.00000000000000    0.00000000000000   Ni    (2a)
   0.00000000000000    0.00000000000000    0.50000000000000   Ni    (2a)
```

β-Tridymite (SiO_2) (C10): A2B_hP12_194_cg_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta Tridymite'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'Kuniaki Kihara'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie
;
_journal_volume 148
_journal_year 1978
_journal_page_first 237
_journal_page_last 253
_publ_Section_title
;
 Thermal change in unit-cell dimensions, and a hexagonal structure of
    ↪ tridymite
;

# Found in  Pearson's Handbook, Vol. IV, pp. 4759

_aflow_proto 'A2B_hP12_194_cg_f'
_aflow_params 'a,c/a,z2'
_aflow_params_values '5.052,1.63697545527,0.062'
_aflow_Strukturbericht 'C10'
_aflow_Pearson 'hP12'

_symmetry_space_group_name_Hall "-P 6c 2c"
_symmetry_space_group_name_H-M "P 63/m m c"
```

```
_symmetry_Int_Tables_number 194

_cell_length_a      5.05200
_cell_length_b      5.05200
_cell_length_c      8.27000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma 120.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x-y,x,z+1/2
3 -y,x-y,z
4 -x,-y,z+1/2
5 -x+y,-x,z
6 y,-x+y,z+1/2
7 x-y,-y,-z
8 x,x-y,-z+1/2
9 y,x,-z
10 -x+y,y,-z+1/2
11 -x,-x+y,-z
12 -y,-x,-z+1/2
13 -x,-y,-z
14 -x+y,-x,-z+1/2
15 y,-x+y,-z
16 x,y,-z+1/2
17 x-y,x,-z
18 -y,x-y,-z+1/2
19 -x+y,y,z
20 -x,-x+y,z+1/2
21 -y,-x,z
22 x-y,-y,z+1/2
23 x,x-y,z
24 y,x,z+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O    2 c 0.33333 0.66667 0.25000 1.00000
Si1 Si   4 f 0.33333 0.66667 0.06200 1.00000
O2  O    6 g 0.50000 0.00000 0.00000 1.00000
```

β-Tridymite (SiO_2) (C10): A2B_hP12_194_cg_f - POSCAR

```
A2B_hP12_194_cg_f & a,c/a,z2 --params=5.052,1.63697545527,0.062 & P6_3/
    ↪ mmc  D_{6h}^4 #194 (cfg) & hP12 & C10 & SiO2 & beta tridymite &
    ↪  K. Kihara, Zeitschrift f\"{u}r Kristallographie 148, 237-253 (
    ↪ 1978)
   1.0000000000000000
   2.52600000000000   -4.37516033991899    0.00000000000000
   2.52600000000000    4.37516033991899    0.00000000000000
   0.00000000000000    0.00000000000000    8.27000000000000
    O    Si
    8    4
Direct
   0.33333333333333    0.66666666666667    0.25000000000000    O    (2c)
   0.66666666666667    0.33333333333333    0.75000000000000    O    (2c)
   0.00000000000000    0.50000000000000    0.00000000000000    O    (6g)
   0.00000000000000    0.50000000000000    0.50000000000000    O    (6g)
   0.50000000000000    0.00000000000000    0.00000000000000    O    (6g)
   0.50000000000000    0.00000000000000    0.50000000000000    O    (6g)
   0.50000000000000    0.50000000000000    0.00000000000000    O    (6g)
   0.50000000000000    0.50000000000000    0.50000000000000    O    (6g)
   0.33333333333333    0.66666666666667    0.06200000000000   Si    (4f)
   0.33333333333333    0.66666666666667    0.43800000000000   Si    (4f)
   0.66666666666667    0.33333333333333   -0.06200000000000   Si    (4f)
   0.66666666666667    0.33333333333333    0.56200000000000   Si    (4f)
```

Ga_4Ni: A4B_cI40_197_cde_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ga4 Ni'

loop_
_publ_author_name
 'Liang Jingkui'
 'Xie Sishen'
_journal_name_full
;
Scientia Sinica, Series A: Mathematical, Physical, Astronomical and
    ↪ Technical Sciences, English Edition
;
_journal_volume 26
_journal_year 1983
_journal_page_first 1305
_journal_page_last 1313
_publ_Section_title
;
 The Structure of NiGa$_4$ Crystal -- A New Vacancy Controlled $\
    ↪ gamma$-Brass Phase
;
```

```
# Found in  Pearson's Handbook Vol. III, pp. 3509

_aflow_proto 'A4B_cI40_197_cde_c'
_aflow_params 'a,x1,x2,x3,x4'
_aflow_params_values '8.4295,0.1668,0.3345,0.6476,0.7484'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI40'

_symmetry_space_group_name_Hall "I 2 2 3"
_symmetry_space_group_name_H-M "I 2 3"
_symmetry_Int_Tables_number 197

_cell_length_a      8.42950
_cell_length_b      8.42950
_cell_length_c      8.42950
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 x+1/2,y+1/2,z+1/2
14 x+1/2,-y+1/2,-z+1/2
15 -x+1/2,y+1/2,-z+1/2
16 -x+1/2,-y+1/2,z+1/2
17 y+1/2,z+1/2,x+1/2
18 y+1/2,-z+1/2,-x+1/2
19 -y+1/2,z+1/2,-x+1/2
20 -y+1/2,-z+1/2,x+1/2
21 z+1/2,x+1/2,y+1/2
22 z+1/2,-x+1/2,-y+1/2
23 -z+1/2,x+1/2,-y+1/2
24 -z+1/2,-x+1/2,y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ga1 Ga   8 c 0.16680 0.16680 0.16680 1.00000
Ni1 Ni   8 c 0.33450 0.33450 0.33450 1.00000
Ga2 Ga  12 d 0.64760 0.00000 0.00000 1.00000
Ga3 Ga  12 e 0.74840 0.50000 0.00000 1.00000
```

Ga_4Ni: A4B_cI40_197_cde_c - POSCAR

```
A4B_cI40_197_cde_c & a,x1,x2,x3,x4 --params=8.4295,0.1668,0.3345,0.6476,
    ↪ 0.7484 & I23        T^3 #197 (c^2de) & cI40 & & Ga4Ni & & Liang
    ↪ Jingkui and Xie Sishen, Scientia Sinica A 26, 1305-1313 (1983)
   1.0000000000000000
  -4.21475000000000    4.21475000000000    4.21475000000000
   4.21475000000000   -4.21475000000000    4.21475000000000
   4.21475000000000    4.21475000000000   -4.21475000000000
   Ga    Ni
   16    4
Direct
   0.00000000000000    0.35240000000000    0.35240000000000    Ga    (12d)
   0.00000000000000    0.64760000000000    0.64760000000000    Ga    (12d)
   0.35240000000000    0.00000000000000    0.35240000000000    Ga    (12d)
   0.35240000000000    0.35240000000000    0.00000000000000    Ga    (12d)
   0.64760000000000    0.00000000000000    0.64760000000000    Ga    (12d)
   0.64760000000000    0.64760000000000    0.00000000000000    Ga    (12d)
   0.24840000000000    0.50000000000000    0.74840000000000    Ga    (12e)
   0.25160000000000    0.75160000000000    0.50000000000000    Ga    (12e)
   0.50000000000000    0.25160000000000    0.75160000000000    Ga    (12e)
   0.50000000000000    0.74840000000000    0.24840000000000    Ga    (12e)
   0.74840000000000    0.24840000000000    0.50000000000000    Ga    (12e)
   0.75160000000000    0.50000000000000    0.25160000000000    Ga    (12e)
   0.00000000000000    0.00000000000000    0.66640000000000    Ga     (8c)
   0.00000000000000    0.66640000000000    0.00000000000000    Ga     (8c)
   0.33360000000000    0.33360000000000    0.33360000000000    Ga     (8c)
   0.66640000000000    0.00000000000000    0.00000000000000    Ga     (8c)
   0.00000000000000    0.00000000000000    0.33100000000000    Ni     (8c)
   0.00000000000000    0.33100000000000    0.00000000000000    Ni     (8c)
   0.33100000000000    0.00000000000000    0.00000000000000    Ni     (8c)
   0.66900000000000    0.66900000000000    0.66900000000000    Ni     (8c)
```

Ullmanite (NiSSb, $F0_1$): ABC_cP12_198_a_a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Ullmanite'
_chemical_formula_sum 'Ni S Sb'

loop_
```

```
_publ_author_name
 'Yoshio Tak\'{e}uchi'
_journal_name_full
;
Mineralogical Journal
;
_journal_volume 2
_journal_year 1957
_journal_page_first 90
_journal_page_last 102
_publ_Section_title
;
 The Absolute Structure of Ullmanite, NiSbS
;

_aflow_proto 'ABC_cP12_198_a_a_a'
_aflow_params 'a,x1,x2,x3'
_aflow_params_values '5.881,-0.024,0.39,0.875'
_aflow_Strukturbericht 'F0_1'
_aflow_Pearson 'cP12'

_symmetry_space_group_name_Hall "P 2ac 2ab 3 P2_13"
_symmetry_space_group_name_H-M "P 21 3"
_symmetry_Int_Tables_number 198

_cell_length_a      5.88100
_cell_length_b      5.88100
_cell_length_c      5.88100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ni1 Ni   4 a -0.02400 -0.02400 -0.02400 1.00000
S1  S    4 a 0.39000  0.39000  0.39000  1.00000
Sb1 Sb   4 a 0.87500  0.87500  0.87500  1.00000
```

Ullmanite (NiSSb, $F0_1$): ABC_cP12_198_a_a_a - POSCAR

```
ABC_cP12_198_a_a_a & a,x1,x2,x3 --params=5.881,-0.024,0.39,0.875 & P2_13
    ↪        T^4 #198 (a^3) & cP12 & F0_1 & NiSSb & Ullmanite & Y.
    ↪ Takeuchi, Mineralogical Journal 2, 90-102 (1957)
   1.0000000000000000
   5.88100000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.88100000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.88100000000000
   Ni    S    Sb
    4    4    4
Direct
  -0.02400000000000  -0.02400000000000  -0.02400000000000   Ni    (4a)
   0.02400000000000   0.47600000000000   0.52400000000000   Ni    (4a)
   0.47600000000000   0.52400000000000   0.02400000000000   Ni    (4a)
   0.52400000000000   0.02400000000000   0.47600000000000   Ni    (4a)
   0.11000000000000   0.61000000000000   0.89000000000000    S    (4a)
   0.39000000000000   0.39000000000000   0.39000000000000    S    (4a)
   0.61000000000000   0.89000000000000   0.11000000000000    S    (4a)
   0.89000000000000   0.11000000000000   0.61000000000000    S    (4a)
   0.12500000000000   0.37500000000000   0.62500000000000   Sb    (4a)
   0.37500000000000   0.62500000000000   0.12500000000000   Sb    (4a)
   0.62500000000000   0.12500000000000   0.37500000000000   Sb    (4a)
   0.87500000000000   0.87500000000000   0.87500000000000   Sb    (4a)
```

Ammonia (NH_3, D1): A3B_cP16_198_b_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Ammonia'
_chemical_formula_sum 'N H3'

loop_
_publ_author_name
 'R. Boese'
 'N. Niederpr\"{u}m'
 'D. Bl\"{a}ser'
 'Andreas Maulitz'
 'Mikhael Yu. Antipin'
 'Paul R. Mallinson'
_journal_name_full
;
Journal of Physical Chemistry B
;
_journal_volume 101
_journal_year 1997
_journal_page_first 5794
_journal_page_last 5799
_publ_Section_title
;
 Single-Crystal Structure and Electron Density Distribution of Ammonia
    ↪ at 160 K on the Basis of X-ray Diffraction Data
;

_aflow_proto 'A3B_cP16_198_b_a'
_aflow_params 'a,x1,x2,y2,z2'
_aflow_params_values '5.1305,0.2107,0.3689,0.2671,0.1159'
_aflow_Strukturbericht 'D1'
_aflow_Pearson 'cP16'

_symmetry_space_group_name_Hall "P 2ac 2ab 3 P2_13"
_symmetry_space_group_name_H-M "P 21 3"
_symmetry_Int_Tables_number 198

_cell_length_a      5.13050
_cell_length_b      5.13050
_cell_length_c      5.13050
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
N1 N   4 a 0.21070 0.21070 0.21070 1.00000
H1 H  12 b 0.36890 0.26710 0.11590 1.00000
```

Ammonia (NH_3, D1): A3B_cP16_198_b_a - POSCAR

```
A3B_cP16_198_b_a & a,x1,x2,y2,z2 --params=5.1305,0.2107,0.3689,0.2671,
    ↪ 0.1159 & P2_13      T^4 #198 (ab) & cP16 & D1 & NH3 & Ammonia &
    ↪ R. Boese et al., J. Phys. Chem. B 101, 5794-5799 (1997)
   1.0000000000000000
   5.13050000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.13050000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.13050000000000
    H    N
   12    4
Direct
   0.11590000000000    0.36890000000000    0.26710000000000    H    (12b)
  -0.11590000000000    0.86890000000000    0.23290000000000    H    (12b)
   0.13110000000000   -0.26710000000000    0.61590000000000    H    (12b)
   0.23290000000000   -0.11590000000000    0.86890000000000    H    (12b)
   0.26710000000000    0.11590000000000    0.36890000000000    H    (12b)
  -0.26710000000000    0.61590000000000    0.13110000000000    H    (12b)
   0.36890000000000    0.26710000000000    0.11590000000000    H    (12b)
  -0.36890000000000    0.76710000000000    0.38410000000000    H    (12b)
   0.38410000000000   -0.36890000000000    0.76710000000000    H    (12b)
   0.61590000000000    0.13110000000000   -0.26710000000000    H    (12b)
   0.76710000000000    0.38410000000000   -0.36890000000000    H    (12b)
   0.86890000000000    0.23290000000000   -0.11590000000000    H    (12b)
   0.21070000000000    0.21070000000000    0.21070000000000    N     (4a)
  -0.21070000000000   -0.28930000000000    0.28930000000000    N     (4a)
   0.28930000000000   -0.21070000000000   -0.28930000000000    N     (4a)
  -0.28930000000000    0.28930000000000   -0.21070000000000    N     (4a)
```

α-N ($P2_13$): A_cP8_198_2a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'N'

loop_
_publ_author_name
 'Sam J. La Placa'
 'Walter C Hamilton'
_journal_name_full
;
Acta Crystallographica B
;
```

```
_journal_volume 28
_journal_year 1972
_journal_page_first 984
_journal_page_last 985
_publ_Section_title
;
 Refinement of the crystal structure of $\alpha$-N$_2$
;

_aflow_proto 'A_cP8_198_2a'
_aflow_params 'a,x1,x2'
_aflow_params_values '5.65,0.0699,-0.0378'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP8'

_symmetry_space_group_name_Hall "P 2ac 2ab 3 P2_13"
_symmetry_space_group_name_H-M "P 21 3"
_symmetry_Int_Tables_number 198

_cell_length_a     5.65000
_cell_length_b     5.65000
_cell_length_c     5.65000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
N1 N    4 a 0.06990 0.06990 0.06990 1.00000
N2 N    4 a -0.03780 -0.03780 -0.03780 1.00000
```

α-N ($P2_13$): A_cP8_198_2a - POSCAR

```
A_cP8_198_2a & a,x1,x2 --params=5.65,0.0699,-0.0378 & P2_13      T^4 #198
    ↪ (a^2) & cP8 & & N & alpha & La Placa and Hamilton, Acta Cryst
    ↪ B28, 984-985 (1972)
   1.0000000000000000
   5.65000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.65000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.65000000000000
    N
    8
Direct
  -0.03780000000000  -0.03780000000000  -0.03780000000000   N    (4a)
   0.03780000000000   0.46220000000000   0.53780000000000   N    (4a)
   0.06990000000000   0.06990000000000   0.06990000000000   N    (4a)
  -0.06990000000000   0.56990000000000   0.43010000000000   N    (4a)
   0.43010000000000  -0.06990000000000   0.56990000000000   N    (4a)
   0.46220000000000   0.53780000000000   0.03780000000000   N    (4a)
   0.53780000000000   0.03780000000000   0.46220000000000   N    (4a)
   0.56990000000000   0.43010000000000  -0.06990000000000   N    (4a)
```

α-CO (B21): AB_cP8_198_a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha carbon monoxide'
_chemical_formula_sum 'C O'

loop_
_publ_author_name
 'Lars Vegard'
_journal_name_full
;
Zeitschrift f\"{u}r Physik
;
_journal_volume 61
_journal_year 1930
_journal_page_first 185
_journal_page_last 190
_publ_Section_title
;
 Struktur und Leuchtf\"{a}higkeit von festem Kohlenoxyd
;

# Found in  AMS Database

_aflow_proto 'AB_cP8_198_a_a'
_aflow_params 'a,x1,x2'
_aflow_params_values '5.63,-0.042,0.067'
_aflow_Strukturbericht 'B21'
_aflow_Pearson 'cP8'

_symmetry_space_group_name_Hall "P 2ac 2ab 3 P2_13"
_symmetry_space_group_name_H-M "P 21 3"
_symmetry_Int_Tables_number 198

_cell_length_a     5.63000
_cell_length_b     5.63000
_cell_length_c     5.63000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1 C    4 a -0.04200 -0.04200 -0.04200 1.00000
O1 O    4 a 0.06700 0.06700 0.06700 1.00000
```

α-CO (B21): AB_cP8_198_a_a - POSCAR

```
AB_cP8_198_a_a & a,x1,x2 --params=5.63,-0.042,0.067 & P2_13      T^4 #198
    ↪ (a^2) & cP8 & B21 & CO & alpha & L. Vegard, Z. Phys. 61,
    ↪ 185-190 (1930)
   1.0000000000000000
   5.63000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.63000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.63000000000000
    C    O
    4    4
Direct
  -0.04200000000000  -0.04200000000000  -0.04200000000000   C    (4a)
   0.04200000000000   0.45800000000000   0.54200000000000   C    (4a)
   0.45800000000000   0.54200000000000   0.04200000000000   C    (4a)
   0.54200000000000   0.04200000000000   0.45800000000000   C    (4a)
   0.06700000000000   0.06700000000000   0.06700000000000   O    (4a)
  -0.06700000000000   0.56700000000000   0.43300000000000   O    (4a)
   0.43300000000000  -0.06700000000000   0.56700000000000   O    (4a)
   0.56700000000000   0.43300000000000  -0.06700000000000   O    (4a)
```

FeSi (B20): AB_cP8_198_a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Fe Si'

loop_
_publ_author_name
 'L. Vo\v{c}adlo'
 'K. S. Knight'
 'G. D. Price'
 'I. G. Wood'
_journal_name_full
;
Physics and Chemistry of Minerals
;
_journal_volume 29
_journal_year 2002
_journal_page_first 132
_journal_page_last 139
_publ_Section_title
;
 Thermal expansion and crystal structure of FeSi between 4 and 1173 K
    ↪ determined by time-of-flight neutron powder diffraction
;

_aflow_proto 'AB_cP8_198_a_a'
_aflow_params 'a,x1,x2'
_aflow_params_values '4.48688,0.13652,0.8424'
_aflow_Strukturbericht 'B20'
_aflow_Pearson 'cP8'

_symmetry_space_group_name_Hall "P 2ac 2ab 3 P2_13"
_symmetry_space_group_name_H-M "P 21 3"
_symmetry_Int_Tables_number 198

_cell_length_a     4.48688
```

```
_cell_length_b      4.48688
_cell_length_c      4.48688
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Fe1 Fe    4 a 0.13652 0.13652 0.13652 1.00000
Si1 Si    4 a 0.84240 0.84240 0.84240 1.00000
```

FeSi (B20): AB_cP8_198_a_a - POSCAR

```
AB_cP8_198_a_a & a,x1,x2 --params=4.48688,0.13652,0.8424 & P2_13        T^4
    ↪ #198 (a^2) & cP8 & B20 & FeSi & & L. Vo\v{c}adlo, K. S. Knight
    ↪ , G. D. Price and I. G. Wood, Phys. Chem. Minerals 29, 132-139
    ↪ (2002)
   1.0000000000000000
   4.48687533818500    0.00000000000000    0.00000000000000
   0.00000000000000    4.48687533818500    0.00000000000000
   0.00000000000000    0.00000000000000    4.48687533818500
   Fe    Si
    4     4
Direct
   0.13652000000000    0.13652000000000    0.13652000000000    Fe    (4a)
   0.36348000000000    0.86348000000000    0.63652000000000    Fe    (4a)
   0.63652000000000    0.36348000000000    0.86348000000000    Fe    (4a)
   0.86348000000000    0.63652000000000    0.36348000000000    Fe    (4a)
   0.15760000000000    0.34240000000000    0.65760000000000    Si    (4a)
   0.34240000000000    0.65760000000000    0.15760000000000    Si    (4a)
   0.65760000000000    0.15760000000000    0.34240000000000    Si    (4a)
   0.84240000000000    0.84240000000000    0.84240000000000    Si    (4a)
```

CoU (B_a): AB_cI16_199_a_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Co U'

loop_
_publ_author_name
 'N. C. Baenziger'
 'R. E. Rundle'
 'A. I. Snow'
 'A. S. Wilson'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 3
_journal_year 1950
_journal_page_first 34
_journal_page_last 40
_publ_Section_title
;
 Compounds of uranium with the transition metals of the first long
    ↪ period
;

# Found in  rough58:UTh

_aflow_proto 'AB_cI16_199_a_a'
_aflow_params 'a,x1,x2'
_aflow_params_values '6.3557,0.294,0.0347'
_aflow_Strukturbericht 'B_a'
_aflow_Pearson 'cI16'

_symmetry_space_group_name_Hall "I 2b 2c 3"
_symmetry_space_group_name_H-M "I 21 3"
_symmetry_Int_Tables_number 199

_cell_length_a      6.35570
_cell_length_b      6.35570
_cell_length_c      6.35570
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x+1/2,y,-z
4 -x,-y+1/2,z
5 y,z,x
6 y,-z,-x+1/2
7 -y+1/2,z,-x
8 -y,-z+1/2,x
9 z,x,y
10 z,-x,-y+1/2
11 -z+1/2,x,-y
12 -z,-x+1/2,y
13 x+1/2,y+1/2,z+1/2
14 x+1/2,-y+1/2,-z
15 -x,y+1/2,-z+1/2
16 -x+1/2,-y,z+1/2
17 y+1/2,z+1/2,x+1/2
18 y+1/2,-z+1/2,-x
19 -y,z+1/2,-x+1/2
20 -y+1/2,-z,x+1/2
21 z+1/2,x+1/2,y+1/2
22 z+1/2,-x+1/2,-y
23 -z,x+1/2,-y+1/2
24 -z+1/2,-x,y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Co1 Co    8 a 0.29400 0.29400 0.29400 1.00000
U1  U     8 a 0.03470 0.03470 0.03470 1.00000
```

CoU (B_a): AB_cI16_199_a_a - POSCAR

```
AB_cI16_199_a_a & a,x1,x2 --params=6.3557,0.294,0.0347 & I2_13        T^5 #
    ↪ 199 (a^2) & cI16 & B_a & CoU & & N. C. Baenziger, R. E. Rundele
    ↪ , A. I. Snow and A. S. Wilson, Acta Cryst. 3, 34-40 (1950)
   1.0000000000000000
  -3.17785000000000    3.17785000000000    3.17785000000000
   3.17785000000000   -3.17785000000000    3.17785000000000
   3.17785000000000    3.17785000000000   -3.17785000000000
   Co    U
    4    4
Direct
   0.00000000000000   -0.08800000000000    0.50000000000000    Co    (8a)
  -0.08800000000000    0.50000000000000    0.00000000000000    Co    (8a)
   0.50000000000000    0.00000000000000   -0.08800000000000    Co    (8a)
   0.58800000000000    0.58800000000000    0.58800000000000    Co    (8a)
   0.00000000000000    0.43060000000000    0.50000000000000    U     (8a)
   0.06940000000000    0.06940000000000    0.06940000000000    U     (8a)
   0.43060000000000    0.50000000000000    0.00000000000000    U     (8a)
   0.50000000000000    0.00000000000000    0.43060000000000    U     (8a)
```

Bergman [$Mg_{32}(Al,Zn)_{49}$]: AB32C48_cI162_204_a_2efg_2gh - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Bergman Structure: Mg32(Al,Zn)49 Bergman'
_chemical_formula_sum 'Al Mg32 Zn48'

loop_
_publ_author_name
 'Gunnar Bergman'
 'John L. T. Waugh'
 'Linus Pauling'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 10
_journal_year 1957
_journal_page_first 254
_journal_page_last 259
_publ_Section_title
;
 The crystal structure of the metallic phase Mg$_{32}$(Al, Zn)$_{49}$
;

_aflow_proto 'AB32C48_cI162_204_a_2efg_2gh'
_aflow_params 'a,x2,x3,x4,y5,z5,y6,z6,y7,z7,x8,y8,z8'
_aflow_params_values '14.16,0.8203,0.5998,0.1836,0.2942,0.8806,0.0908,
    ↪ 0.8499,0.1748,0.6993,0.686,0.0969,0.332'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI162'

_symmetry_space_group_name_Hall "-I 2 2 3"
_symmetry_space_group_name_H-M "I m -3"
_symmetry_Int_Tables_number 204

_cell_length_a      14.16000
_cell_length_b      14.16000
_cell_length_c      14.16000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
```

```
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x,−y,−z
3  −x,y,−z
4  −x,−y,z
5  y,z,x
6  y,−z,−x
7  −y,z,−x
8  −y,−z,x
9  z,x,y
10  z,−x,−y
11  −z,x,−y
12  −z,−x,y
13  −x,−y,−z
14  −x,y,z
15  x,−y,z
16  x,y,−z
17  −y,−z,−x
18  −y,z,x
19  y,−z,x
20  y,z,−x
21  −z,−x,−y
22  −z,x,y
23  z,−x,y
24  z,x,−y
25  x+1/2,y+1/2,z+1/2
26  x+1/2,−y+1/2,−z+1/2
27  −x+1/2,y+1/2,−z+1/2
28  −x+1/2,−y+1/2,z+1/2
29  y+1/2,z+1/2,x+1/2
30  y+1/2,−z+1/2,−x+1/2
31  −y+1/2,z+1/2,−x+1/2
32  −y+1/2,−z+1/2,x+1/2
33  z+1/2,x+1/2,y+1/2
34  z+1/2,−x+1/2,−y+1/2
35  −z+1/2,x+1/2,−y+1/2
36  −z+1/2,−x+1/2,y+1/2
37  −x+1/2,−y+1/2,−z+1/2
38  −x+1/2,y+1/2,z+1/2
39  x+1/2,−y+1/2,z+1/2
40  x+1/2,y+1/2,−z+1/2
41  −y+1/2,−z+1/2,−x+1/2
42  −y+1/2,z+1/2,x+1/2
43  y+1/2,−z+1/2,x+1/2
44  y+1/2,z+1/2,−x+1/2
45  −z+1/2,−x+1/2,−y+1/2
46  −z+1/2,x+1/2,y+1/2
47  z+1/2,−x+1/2,y+1/2
48  z+1/2,x+1/2,−y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1  Al    2  a  0.00000  0.00000  0.00000  1.00000
Mg1  Mg   12  e  0.82030  0.00000  0.50000  1.00000
Mg2  Mg   12  e  0.59980  0.00000  0.50000  1.00000
Mg3  Mg   16  f  0.18360  0.18360  0.18360  1.00000
Mg4  Mg   24  g  0.00000  0.29420  0.88060  1.00000
Zn1  Zn   24  g  0.00000  0.09080  0.84990  1.00000
Zn2  Zn   24  g  0.00000  0.17480  0.69930  1.00000
Zn3  Zn   48  h  0.68600  0.09690  0.33200  1.00000
```

Bergman [$Mg_{32}(Al,Zn)_{49}$]: AB32C48_cI162_204_a_2efg_2gh - POSCAR

```
AB32C48_cI162_204_a_2efg_2gh & a,x2,x3,x4,y5,z5,y6,z6,y7,z7,x8,y8,z8 --
      ↪ params=14.16,0.8203,0.5998,0.1836,0.2942,0.8806,0.0908,0.8499,
      ↪ 0.1748,0.6993,0.686,0.0969,0.332 & Im(−3)      T_h^5 #204 (ae^2fg
      ↪ ^3h) & cI162 &  & Mg32(Al,Zn)49 & Bergman & G. Bergman, J. L.
      ↪ T. Waugh and L. Pauling, Acta Cryst. 10, 254−259 (1957)
   1.0000000000000000
  −7.08000000000000    7.08000000000000    7.08000000000000
   7.08000000000000   −7.08000000000000    7.08000000000000
   7.08000000000000    7.08000000000000   −7.08000000000000
   Al    Mg    Zn
    1    32    48
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Al    (2a)
   0.17970000000000    0.50000000000000    0.67970000000000    Mg    (12e)
   0.32030000000000    0.82030000000000    0.50000000000000    Mg    (12e)
   0.50000000000000    0.32030000000000    0.82030000000000    Mg    (12e)
   0.50000000000000    0.67970000000000    0.17970000000000    Mg    (12e)
   0.67970000000000    0.17970000000000    0.50000000000000    Mg    (12e)
   0.82030000000000    0.50000000000000    0.32030000000000    Mg    (12e)
  −0.09980000000000    0.40020000000000    0.50000000000000    Mg    (12e)
   0.09980000000000    0.59980000000000    0.50000000000000    Mg    (12e)
   0.40020000000000    0.50000000000000   −0.09980000000000    Mg    (12e)
   0.50000000000000   −0.09980000000000    0.40020000000000    Mg    (12e)
   0.50000000000000    0.09980000000000    0.59980000000000    Mg    (12e)
   0.59980000000000    0.50000000000000    0.09980000000000    Mg    (12e)
   0.00000000000000    0.00000000000000    0.36720000000000    Mg    (16f)
   0.00000000000000    0.00000000000000    0.63280000000000    Mg    (16f)
   0.00000000000000    0.36720000000000    0.00000000000000    Mg    (16f)
   0.00000000000000    0.63280000000000    0.00000000000000    Mg    (16f)
   0.36720000000000    0.00000000000000    0.00000000000000    Mg    (16f)
   0.36720000000000    0.36720000000000    0.36720000000000    Mg    (16f)
   0.63280000000000    0.00000000000000    0.00000000000000    Mg    (16f)
   0.63280000000000    0.63280000000000    0.63280000000000    Mg    (16f)
   0.11940000000000    0.29420000000000    0.41360000000000    Mg    (24g)
   0.11940000000000    0.70580000000000    0.82520000000000    Mg    (24g)
   0.17480000000000    0.88060000000000    0.29420000000000    Mg    (24g)
   0.29420000000000    0.17480000000000    0.88060000000000    Mg    (24g)
   0.29420000000000    0.41360000000000    0.11940000000000    Mg    (24g)
   0.41360000000000    0.11940000000000    0.29420000000000    Mg    (24g)
   0.58640000000000    0.88060000000000    0.70580000000000    Mg    (24g)
   0.70580000000000    0.58640000000000    0.88060000000000    Mg    (24g)
   0.70580000000000    0.82520000000000    0.11940000000000    Mg    (24g)
   0.82520000000000    0.11940000000000    0.70580000000000    Mg    (24g)
   0.88060000000000    0.29420000000000    0.17480000000000    Mg    (24g)
   0.88060000000000    0.70580000000000    0.58640000000000    Mg    (24g)
   0.05930000000000    0.15010000000000   −0.09080000000000    Zn    (24g)
  −0.05930000000000    0.84990000000000    0.09080000000000    Zn    (24g)
  −0.09080000000000    0.05930000000000    0.15010000000000    Zn    (24g)
   0.09080000000000   −0.05930000000000    0.84990000000000    Zn    (24g)
   0.09080000000000    0.24090000000000    0.15010000000000    Zn    (24g)
  −0.09080000000000    0.75910000000000    0.84990000000000    Zn    (24g)
   0.15010000000000   −0.09080000000000    0.05930000000000    Zn    (24g)
   0.15010000000000    0.09080000000000    0.24090000000000    Zn    (24g)
   0.24090000000000    0.15010000000000    0.09080000000000    Zn    (24g)
   0.75910000000000    0.84990000000000   −0.09080000000000    Zn    (24g)
   0.84990000000000    0.09080000000000   −0.05930000000000    Zn    (24g)
   0.84990000000000   −0.09080000000000    0.75910000000000    Zn    (24g)
   0.12590000000000    0.30070000000000    0.82520000000000    Zn    (24g)
   0.17480000000000    0.47550000000000    0.30070000000000    Zn    (24g)
   0.17480000000000    0.87410000000000    0.69930000000000    Zn    (24g)
   0.30070000000000    0.17480000000000    0.47550000000000    Zn    (24g)
   0.30070000000000    0.82520000000000    0.12590000000000    Zn    (24g)
   0.47550000000000    0.30070000000000    0.17480000000000    Zn    (24g)
   0.52450000000000    0.69930000000000    0.82520000000000    Zn    (24g)
   0.69930000000000    0.17480000000000    0.87410000000000    Zn    (24g)
   0.69930000000000    0.82520000000000    0.52450000000000    Zn    (24g)
   0.82520000000000    0.12590000000000    0.30070000000000    Zn    (24g)
   0.82520000000000    0.52450000000000    0.69930000000000    Zn    (24g)
   0.87410000000000    0.69930000000000    0.17480000000000    Zn    (24g)
  −0.01800000000000    0.21710000000000    0.57110000000000    Zn    (48h)
  −0.01800000000000    0.41090000000000    0.76490000000000    Zn    (48h)
   0.01800000000000    0.58910000000000    0.23510000000000    Zn    (48h)
   0.01800000000000    0.78290000000000    0.42890000000000    Zn    (48h)
   0.21710000000000    0.23510000000000    0.64600000000000    Zn    (48h)
   0.21710000000000    0.57110000000000   −0.01800000000000    Zn    (48h)
   0.23510000000000    0.01800000000000    0.58910000000000    Zn    (48h)
   0.23510000000000    0.64600000000000    0.21710000000000    Zn    (48h)
   0.35400000000000    0.58910000000000    0.57110000000000    Zn    (48h)
   0.35400000000000    0.78290000000000    0.76490000000000    Zn    (48h)
   0.41090000000000    0.42890000000000    0.64600000000000    Zn    (48h)
   0.41090000000000    0.76490000000000   −0.01800000000000    Zn    (48h)
   0.42890000000000    0.01800000000000    0.78290000000000    Zn    (48h)
   0.42890000000000    0.64600000000000    0.41090000000000    Zn    (48h)
   0.57110000000000   −0.01800000000000    0.21710000000000    Zn    (48h)
   0.57110000000000    0.35400000000000    0.58910000000000    Zn    (48h)
   0.58910000000000    0.23510000000000    0.01800000000000    Zn    (48h)
   0.58910000000000    0.57110000000000    0.35400000000000    Zn    (48h)
   0.64600000000000    0.21710000000000    0.23510000000000    Zn    (48h)
   0.64600000000000    0.41090000000000    0.42890000000000    Zn    (48h)
   0.76490000000000   −0.01800000000000    0.41090000000000    Zn    (48h)
   0.76490000000000    0.35400000000000    0.78290000000000    Zn    (48h)
   0.78290000000000    0.42890000000000    0.01800000000000    Zn    (48h)
   0.78290000000000    0.76490000000000    0.35400000000000    Zn    (48h)
```

Skutterudite ($CoAs_3$, $D0_2$): A3B_cI32_204_g_c - CIF

```
# CIF file

data_findsym−output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Skutterudite'
_chemical_formula_sum 'Co As3'

loop_
_publ_author_name
 'Neil Mandel'
 'Jerry Donohue'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 27
_journal_year 1971
_journal_page_first 2288
_journal_page_last 2289
_publ_Section_title
;
 The refinement of the crystal structure of skutterudite, CoAs$_3$
;

_aflow_proto 'A3B_cI32_204_g_c'
_aflow_params 'a,y2,z2'
_aflow_params_values '7.58,0.3431,0.8497'
_aflow_Strukturbericht 'D0_2'
_aflow_Pearson 'cI32'

_symmetry_space_group_name_Hall "−I 2 2 3"
_symmetry_space_group_name_H−M "I m −3"
_symmetry_Int_Tables_number 204

_cell_length_a     7.58000
_cell_length_b     7.58000
_cell_length_c     7.58000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
```

```
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x,-y,-z
3  -x,y,-z
4  -x,-y,z
5  y,z,x
6  y,-z,-x
7  -y,z,-x
8  -y,-z,x
9  z,x,y
10  z,-x,-y
11  -z,x,-y
12  -z,-x,y
13  -x,-y,-z
14  -x,y,z
15  x,-y,z
16  x,y,-z
17  -y,-z,-x
18  -y,z,x
19  y,-z,x
20  y,z,-x
21  -z,-x,-y
22  -z,x,y
23  z,-x,y
24  z,x,-y
25  x+1/2,y+1/2,z+1/2
26  x+1/2,-y+1/2,-z+1/2
27  -x+1/2,y+1/2,-z+1/2
28  -x+1/2,-y+1/2,z+1/2
29  y+1/2,z+1/2,x+1/2
30  y+1/2,-z+1/2,-x+1/2
31  -y+1/2,z+1/2,-x+1/2
32  -y+1/2,-z+1/2,x+1/2
33  z+1/2,x+1/2,y+1/2
34  z+1/2,-x+1/2,-y+1/2
35  -z+1/2,x+1/2,-y+1/2
36  -z+1/2,-x+1/2,y+1/2
37  -x+1/2,-y+1/2,-z+1/2
38  -x+1/2,y+1/2,z+1/2
39  x+1/2,-y+1/2,z+1/2
40  x+1/2,y+1/2,-z+1/2
41  -y+1/2,-z+1/2,-x+1/2
42  -y+1/2,z+1/2,x+1/2
43  y+1/2,-z+1/2,x+1/2
44  y+1/2,z+1/2,-x+1/2
45  -z+1/2,-x+1/2,-y+1/2
46  -z+1/2,x+1/2,y+1/2
47  z+1/2,-x+1/2,y+1/2
48  z+1/2,x+1/2,-y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Co1  Co    8  c  0.25000  0.25000  0.25000  1.00000
As1  As   24  g  0.00000  0.34310  0.84970  1.00000
```

Skutterudite ($CoAs_3$, $D0_2$): A3B_cI32_204_g_c - POSCAR

```
A3B_cI32_204_g_c & a,y2,z2 --params=7.58,0.3431,0.8497 & Im(-3)      T_h^5
    ↪ #204 (cg) & cI32 & D0_2 & CoAs3 & Skutterudite & Neil Mandel
    ↪ and Jerry Donohue, Acta Cryst. B 27, 2288-2289 (1971)
   1.00000000000000000
  -3.79000000000000     3.79000000000000     3.79000000000000
   3.79000000000000    -3.79000000000000     3.79000000000000
   3.79000000000000     3.79000000000000    -3.79000000000000
   As     Co
   12      4
Direct
   0.15030000000000     0.34310000000000     0.49340000000000     As     (24g)
   0.15030000000000     0.65690000000000     0.80720000000000     As     (24g)
   0.19280000000000     0.84970000000000     0.34310000000000     As     (24g)
   0.34310000000000     0.19280000000000     0.84970000000000     As     (24g)
   0.34310000000000     0.49340000000000     0.15030000000000     As     (24g)
   0.49340000000000     0.15030000000000     0.34310000000000     As     (24g)
   0.50660000000000     0.84970000000000     0.65690000000000     As     (24g)
   0.65690000000000     0.50660000000000     0.84970000000000     As     (24g)
   0.65690000000000     0.80720000000000     0.15030000000000     As     (24g)
   0.80720000000000     0.15030000000000     0.65690000000000     As     (24g)
   0.84970000000000     0.34310000000000     0.19280000000000     As     (24g)
   0.84970000000000     0.65690000000000     0.50660000000000     As     (24g)
   0.00000000000000     0.00000000000000     0.50000000000000     Co      (8c)
   0.00000000000000     0.50000000000000     0.00000000000000     Co      (8c)
   0.50000000000000     0.00000000000000     0.00000000000000     Co      (8c)
   0.50000000000000     0.50000000000000     0.50000000000000     Co      (8c)
```

$Al_{12}W$: A12B_cI26_204_g_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method  FINDSYM

_chemical_name_mineral  ''
_chemical_formula_sum  'Al12 W'

loop_
_publ_author_name
 'J. Adam'
 'J. B. Rich'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume  7
_journal_year  1954
_journal_page_first  813
_journal_page_last  816
_publ_Section_title
;
 The crystal structure of WAl$_{12}$, MoAl$_{12}$ and (Mn, Cr)Al$_{12}$
;

_aflow_proto  'A12B_cI26_204_g_a'
_aflow_params  'a,y2,z2'
_aflow_params_values  '7.58,0.184,0.691'
_aflow_Strukturbericht  'None'
_aflow_Pearson  'cI26'

_symmetry_space_group_name_Hall "-I 2 2 3"
_symmetry_space_group_name_H-M "I m -3"
_symmetry_Int_Tables_number  204

_cell_length_a      7.58000
_cell_length_b      7.58000
_cell_length_c      7.58000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x,-y,-z
3  -x,y,-z
4  -x,-y,z
5  y,z,x
6  y,-z,-x
7  -y,z,-x
8  -y,-z,x
9  z,x,y
10  z,-x,-y
11  -z,x,-y
12  -z,-x,y
13  -x,-y,-z
14  -x,y,z
15  x,-y,z
16  x,y,-z
17  -y,-z,-x
18  -y,z,x
19  y,-z,x
20  y,z,-x
21  -z,-x,-y
22  -z,x,y
23  z,-x,y
24  z,x,-y
25  x+1/2,y+1/2,z+1/2
26  x+1/2,-y+1/2,-z+1/2
27  -x+1/2,y+1/2,-z+1/2
28  -x+1/2,-y+1/2,z+1/2
29  y+1/2,z+1/2,x+1/2
30  y+1/2,-z+1/2,-x+1/2
31  -y+1/2,z+1/2,-x+1/2
32  -y+1/2,-z+1/2,x+1/2
33  z+1/2,x+1/2,y+1/2
34  z+1/2,-x+1/2,-y+1/2
35  -z+1/2,x+1/2,-y+1/2
36  -z+1/2,-x+1/2,y+1/2
37  -x+1/2,-y+1/2,-z+1/2
38  -x+1/2,y+1/2,z+1/2
39  x+1/2,-y+1/2,z+1/2
40  x+1/2,y+1/2,-z+1/2
41  -y+1/2,-z+1/2,-x+1/2
42  -y+1/2,z+1/2,x+1/2
43  y+1/2,-z+1/2,x+1/2
44  y+1/2,z+1/2,-x+1/2
45  -z+1/2,-x+1/2,-y+1/2
46  -z+1/2,x+1/2,y+1/2
47  z+1/2,-x+1/2,y+1/2
48  z+1/2,x+1/2,-y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
W1  W     2  a  0.00000  0.00000  0.00000  1.00000
Al1  Al   24  g  0.00000  0.18400  0.69100  1.00000
```

$Al_{12}W$: A12B_cI26_204_g_a - POSCAR

```
A12B_cI26_204_g_a & a,y2,z2 --params=7.58,0.184,0.691 & Im(-3)      T_h^5
    ↪ #204 (ag) & cI26 & & Al12W & & J. Adam and J. B. Rich, Acta
    ↪ Cryst. 7, 813-816 (1954)
   1.00000000000000000
  -3.79000000000000     3.79000000000000     3.79000000000000
```

```
   3.79000000000000  -3.79000000000000   3.79000000000000
   3.79000000000000   3.79000000000000  -3.79000000000000
   Al    W
   12    1
Direct
   0.12500000000000   0.30900000000000   0.81600000000000   Al   (24g)
   0.18400000000000   0.49300000000000   0.30900000000000   Al   (24g)
   0.18400000000000   0.87500000000000   0.69100000000000   Al   (24g)
   0.30900000000000   0.18400000000000   0.49300000000000   Al   (24g)
   0.30900000000000   0.81600000000000   0.12500000000000   Al   (24g)
   0.49300000000000   0.30900000000000   0.18400000000000   Al   (24g)
   0.50700000000000   0.69100000000000   0.81600000000000   Al   (24g)
   0.69100000000000   0.18400000000000   0.87500000000000   Al   (24g)
   0.69100000000000   0.81600000000000   0.50700000000000   Al   (24g)
   0.81600000000000   0.12500000000000   0.30900000000000   Al   (24g)
   0.81600000000000   0.50700000000000   0.69100000000000   Al   (24g)
   0.87500000000000   0.69100000000000   0.18400000000000   Al   (24g)
   0.00000000000000   0.00000000000000   0.00000000000000   W    (2a)
```

α-N (Pa$\bar{3}$): A_cP8_205_c - CIF

```
# CIF file
# This file was generated by FINDSYM
# Harold T. Stokes, Branton J. Campbell, Dorian M. Hatch
# Brigham Young University, Provo, Utah, USA

data_findsym-output
_audit_creation_method FINDSYM

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Cubic alpha N2'
_chemical_formula_sum 'N'

loop_
_publ_author_name
 'Truman H. Jordan'
 'H. Warren Smith'
 'William E. Streib'
 'William N. Lipscomb'
_journal_name_full
;
Journal of Chemical Physics
;
_journal_volume 41
_journal_year 1964
_journal_page_first 756
_journal_page_last 759
_publ_Section_title
;
 Single-Crystal X-Ray Diffractions Studies of $\alpha$-N$_2$ and $\
      ↪ beta$-N$_2$
;

# Found in  Donohue, pp. 280-285

_aflow_proto 'A_cP8_205_c'
_aflow_params 'a,x1'
_aflow_params_values '5.65,0.05569'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP8'

_symmetry_space_group_name_Hall "-P 2ac 2ab 3 Pa(-3)"
_symmetry_space_group_name_H-M "P 21/a -3"
_symmetry_Int_Tables_number 205

_cell_length_a      5.65000
_cell_length_b      5.65000
_cell_length_c      5.65000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2
13 -x,-y,-z
14 -x+1/2,y+1/2,z
15 x,-y+1/2,z+1/2
16 x+1/2,y,-z+1/2
17 -y,-z,-x
18 -y+1/2,z+1/2,x
19 y,-z+1/2,x+1/2
20 y+1/2,z,-x+1/2
21 -z,-x,-y
22 -z+1/2,x+1/2,y
23 z,-x+1/2,y+1/2
24 z+1/2,x,-y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
N1 N    8 c 0.05569 0.05569 0.05569 1.00000
```

α-N (Pa$\bar{3}$): A_cP8_205_c - POSCAR

```
A_cP8_205_c & a,x1 --params=5.65,0.05569 & Pa(-3)     T_h^6 #205 (c) &
      ↪ cP8 & & N & alpha & T. H. Jordan et al., J. Chem Phys. 41,
      ↪ 756-759 (1964)
   1.0000000000000000
   5.65000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.65000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.65000000000000
    N
    8
Direct
   0.05569130915200    0.05569130915200    0.05569130915200    N    (8c)
  -0.05569130915200   -0.05569130915200   -0.05569130915200    N    (8c)
   0.05569130915200    0.44430869084800    0.55569130915200    N    (8c)
  -0.05569130915200    0.55569130915200    0.44430869084800    N    (8c)
   0.44430869084800   -0.05569130915200    0.55569130915200    N    (8c)
   0.44430869084800    0.55569130915200    0.05569130915200    N    (8c)
   0.55569130915200    0.05569130915200    0.44430869084800    N    (8c)
   0.55569130915200    0.44430869084800   -0.05569130915200    N    (8c)
```

SC16 (CuCl): AB_cP16_205_c_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'SC16 CuCl, stable at 5GPa'
_chemical_formula_sum 'Cu Cl'

loop_
_publ_author_name
 'S. Hull'
 'D. A. Keen'
_journal_name_full
;
Physical Review B
;
_journal_volume 50
_journal_year 1994
_journal_page_first 5868
_journal_page_last 5885
_publ_Section_title
;
 High-pressure polymorphism of the copper(I) halides: A
      ↪ neutron-diffraction study to ~10 GPa
;

# Found in  Crain, RPP 58, pp. 705 (1995)

_aflow_proto 'AB_cP16_205_c_c'
_aflow_params 'a,x1,x2'
_aflow_params_values '6.4162,0.1527,0.6297'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP16'

_symmetry_space_group_name_Hall "-P 2ac 2ab 3 Pa(-3)"
_symmetry_space_group_name_H-M "P a -3"
_symmetry_Int_Tables_number 205

_cell_length_a      6.41620
_cell_length_b      6.41620
_cell_length_c      6.41620
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2
13 -x,-y,-z
14 -x+1/2,y+1/2,z
15 x,-y+1/2,z+1/2
16 x+1/2,y,-z+1/2
17 -y,-z,-x
18 -y+1/2,z+1/2,x
19 y,-z+1/2,x+1/2
20 y+1/2,z,-x+1/2
21 -z,-x,-y
22 -z+1/2,x+1/2,y
23 z,-x+1/2,y+1/2
24 z+1/2,x,-y+1/2

loop_
```

```
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cl1 Cl    8 c 0.15270 0.15270 0.15270 1.00000
Cu1 Cu    8 c 0.62970 0.62970 0.62970 1.00000
```

SC16 (CuCl): AB_cP16_205_c_c - POSCAR

```
AB_cP16_205_c_c & a,x1,x2 --params=6.4162,0.1527,0.6297 & Pa(-3)     T_h^
    ↪ 6 #205 (c^2) & cP16 & & CuCl & SC16 (P = 5.52 GPa) & S. Hull
    ↪ and D. A. Keen, PRB 50, 5868-5885 (1994)
   1.0000000000000000
   6.41620000000000    0.00000000000000    0.00000000000000
   0.00000000000000    6.41620000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.41620000000000
   Cl    Cu
    8     8
Direct
   0.15270000000000    0.15270000000000    0.15270000000000    Cl    (8c)
   0.15270000000000    0.34730000000000    0.65270000000000    Cl    (8c)
   0.34730000000000    0.65270000000000    0.15270000000000    Cl    (8c)
   0.34730000000000    0.84730000000000    0.65270000000000    Cl    (8c)
   0.65270000000000    0.15270000000000    0.34730000000000    Cl    (8c)
   0.65270000000000    0.34730000000000    0.84730000000000    Cl    (8c)
   0.84730000000000    0.65270000000000    0.34730000000000    Cl    (8c)
   0.84730000000000    0.84730000000000    0.84730000000000    Cl    (8c)
  -0.12970000000000    0.12970000000000    0.62970000000000    Cu    (8c)
   0.12970000000000    0.62970000000000   -0.12970000000000    Cu    (8c)
   0.12970000000000    0.87030000000000    0.37030000000000    Cu    (8c)
   0.37030000000000    0.12970000000000    0.87030000000000    Cu    (8c)
   0.37030000000000    0.37030000000000    0.37030000000000    Cu    (8c)
   0.62970000000000   -0.12970000000000    0.12970000000000    Cu    (8c)
   0.62970000000000    0.62970000000000    0.62970000000000    Cu    (8c)
   0.87030000000000    0.37030000000000    0.12970000000000    Cu    (8c)
```

Pyrite (FeS_2, C2): AB2_cP12_205_a_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Pyrite'
_chemical_formula_sum 'Fe S2'

loop_
_publ_author_name
 'Peter Bayliss'
_journal_name_full
;
American Mineralogist
;
_journal_volume 62
_journal_year 1977
_journal_page_first 1168
_journal_page_last 1172
_publ_Section_title
;
 Crystal structure refinement of a weakly anisotropic pyrite
;

# Found in AMS Database

_aflow_proto 'AB2_cP12_205_a_c'
_aflow_params 'a,x2'
_aflow_params_values '5.417,0.3851'
_aflow_Strukturbericht 'C2'
_aflow_Pearson 'cP12'

_symmetry_space_group_name_Hall "-P 2ac 2ab 3 Pa(-3)"
_symmetry_space_group_name_H-M "P a -3"
_symmetry_Int_Tables_number 205

_cell_length_a      5.41700
_cell_length_b      5.41700
_cell_length_c      5.41700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2
13 -x,-y,-z
14 -x+1/2,y+1/2,z
15 x,-y+1/2,z+1/2
16 x+1/2,y,-z+1/2
17 -y,-z,-x
18 -y+1/2,z+1/2,x
19 y,-z+1/2,x+1/2
20 y+1/2,z,-x+1/2
21 -z,-x,-y
22 -z+1/2,x+1/2,y
23 z,-x+1/2,y+1/2
24 z+1/2,x,-y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Fe1 Fe    4 a 0.00000 0.00000 0.00000 1.00000
S1  S     8 c 0.38510 0.38510 0.38510 1.00000
```

Pyrite (FeS_2, C2): AB2_cP12_205_a_c - POSCAR

```
AB2_cP12_205_a_c & a,x2 --params=5.417,0.3851 & Pa-3        T_h^6 #205 (
    ↪ ac) & cP12 & C2 & FeS2 & Pyrite & Bayliss, Am. Mineral. 62,
    ↪ 1168-1172 (1977)
   1.0000000000000000
   5.41700000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.41700000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.41700000000000
   Fe    S
    4    8
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Fe    (4a)
   0.00000000000000    0.50000000000000    0.50000000000000    Fe    (4a)
   0.50000000000000    0.00000000000000    0.50000000000000    Fe    (4a)
   0.50000000000000    0.50000000000000    0.00000000000000    Fe    (4a)
   0.11490000000000    0.61490000000000    0.88510000000000    S     (8c)
   0.11490000000000    0.88510000000000    0.38510000000000    S     (8c)
   0.38510000000000    0.11490000000000    0.88510000000000    S     (8c)
   0.38510000000000    0.38510000000000    0.38510000000000    S     (8c)
   0.61490000000000    0.61490000000000    0.61490000000000    S     (8c)
   0.61490000000000    0.88510000000000    0.11490000000000    S     (8c)
   0.88510000000000    0.11490000000000    0.61490000000000    S     (8c)
   0.88510000000000    0.38510000000000    0.11490000000000    S     (8c)
```

Bixbyite (Mn_2O_3, $D5_3$): AB3C6_cI80_206_a_d_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Bixbyite (Mn,Fe)2O4'
_chemical_formula_sum 'Fe Mn3 O6'

loop_
_publ_author_name
 'H. Dachs'
_journal_name_full
;
Zeitschrift f\"{u}r Kristallographie - Crystalline Materials
;
_journal_volume 107
_journal_year 1956
_journal_page_first 370
_journal_page_last 395
_publ_Section_title
;
 Die Kristallstruktur des Bixbyits (Fe,Mn)$_2$O$_3$
;

# Found in AMS Database

_aflow_proto 'AB3C6_cI80_206_a_d_e'
_aflow_params 'a,x2,x3,y3,z3'
_aflow_params_values '9.4,-0.0344,0.338,0.1,0.125'
_aflow_Strukturbericht 'D5_3'
_aflow_Pearson 'cI80'

_symmetry_space_group_name_Hall "-I 2b 2c 3"
_symmetry_space_group_name_H-M "I a -3"
_symmetry_Int_Tables_number 206

_cell_length_a      9.40000
_cell_length_b      9.40000
_cell_length_c      9.40000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x+1/2,y,-z
4 -x,-y+1/2,z
5 y,z,x
6 y,-z,-x+1/2
7 -y+1/2,z,-x
8 -y,-z+1/2,x
9 z,x,y
10 z,-x,-y+1/2
11 -z+1/2,x,-y
12 -z,-x+1/2,y
```

```
13 -x,-y,-z
14 -x,y,z+1/2
15 x+1/2,-y,z
16 x,y+1/2,-z
17 -y,-z,-x
18 -y,z,x+1/2
19 y+1/2,-z,x
20 y,z+1/2,-x
21 -z,-x,-y
22 -z,x,y+1/2
23 z+1/2,-x,y
24 z,x+1/2,-y
25 x+1/2,y+1/2,z+1/2
26 x+1/2,-y+1/2,-z
27 -x,y+1/2,-z+1/2
28 -x+1/2,-y,z+1/2
29 y+1/2,z+1/2,x+1/2
30 y+1/2,-z+1/2,-x
31 -y,z+1/2,-x+1/2
32 -y+1/2,-z,x+1/2
33 z+1/2,x+1/2,y+1/2
34 z+1/2,-x+1/2,-y
35 -z,x+1/2,-y+1/2
36 -z+1/2,-x,y+1/2
37 -x+1/2,-y+1/2,-z+1/2
38 -x+1/2,y+1/2,z
39 x,-y+1/2,z+1/2
40 x+1/2,y,-z+1/2
41 -y+1/2,-z+1/2,-x+1/2
42 -y+1/2,z+1/2,x
43 y,-z+1/2,x+1/2
44 y+1/2,z,-x+1/2
45 -z+1/2,-x+1/2,-y+1/2
46 -z+1/2,x+1/2,y
47 z,-x+1/2,y+1/2
48 z+1/2,x,-y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Fe1 Fe   8 a 0.0.0000   0.00000 0.00000 1.00000
Mn1 Mn  24 d -0.03440  0.00000 0.25000 1.00000
O1  O   48 e 0.33800   0.10000 0.12500 1.00000
```

Bixbyite (Mn_2O_3, $D5_3$): AB3C6_cI80_206_a_d_e - POSCAR

```
AB3C6_cI80_206_a_d_e & a,x2,x3,y3,z3 --params=9.4,-0.0344,0.338,0.1,
    ↪ 0.125 & Ia(-3)    T_h^3 #206 (ade) & cI80 & D5_3 & (Mn,Fe)2O3 &
    ↪  Bixbyite & H. Dachs, Zeitschrift f\"{u}r Kristallographie -
    ↪ Crystalline Materials, 107, 370-395 (1956)
   1.0000000000000000
  -4.70000000000000   4.70000000000000   4.70000000000000
   4.70000000000000  -4.70000000000000   4.70000000000000
   4.70000000000000   4.70000000000000  -4.70000000000000
   Fe   Mn   O
    4   12  24
Direct
   0.00000000000000   0.00000000000000  -0.50000000000000   Fe   (8a)
   0.00000000000000  -0.50000000000000   0.00000000000000   Fe   (8a)
  -0.50000000000000   0.00000000000000   0.00000000000000   Fe   (8a)
   0.50000000000000   0.50000000000000   0.50000000000000   Fe   (8a)
  -0.03440000000000   0.25000000000000   0.21560000000000   Mn  (24d)
   0.03440000000000   0.75000000000000   0.78440000000000   Mn  (24d)
   0.21560000000000  -0.03440000000000   0.25000000000000   Mn  (24d)
   0.25000000000000   0.21560000000000  -0.03440000000000   Mn  (24d)
   0.25000000000000   0.71560000000000   0.46560000000000   Mn  (24d)
   0.46560000000000   0.25000000000000   0.71560000000000   Mn  (24d)
   0.53440000000000   0.75000000000000   1.28440000000000   Mn  (24d)
   0.71560000000000   0.46560000000000   0.25000000000000   Mn  (24d)
   0.75000000000000   0.78440000000000   0.03440000000000   Mn  (24d)
   0.75000000000000   1.28440000000000   0.53440000000000   Mn  (24d)
   0.78440000000000   0.03440000000000   0.75000000000000   Mn  (24d)
   1.28440000000000   0.53440000000000   0.75000000000000   Mn  (24d)
   0.03700000000000   0.26200000000000   0.97500000000000   O   (48e)
  -0.03700000000000  -0.26200000000000  -0.97500000000000   O   (48e)
   0.06200000000000   0.52500000000000   0.78700000000000   O   (48e)
  -0.06200000000000  -0.52500000000000  -0.78700000000000   O   (48e)
   0.22500000000000   0.46300000000000   0.43800000000000   O   (48e)
  -0.22500000000000  -0.46300000000000  -0.43800000000000   O   (48e)
   0.26200000000000   0.97500000000000   0.03700000000000   O   (48e)
  -0.26200000000000  -0.97500000000000  -0.03700000000000   O   (48e)
   0.27500000000000   0.71300000000000   1.23800000000000   O   (48e)
  -0.27500000000000  -0.71300000000000  -1.23800000000000   O   (48e)
   0.43800000000000   0.22500000000000   0.46300000000000   O   (48e)
  -0.43800000000000  -0.22500000000000  -0.46300000000000   O   (48e)
   0.46300000000000   0.43800000000000   0.22500000000000   O   (48e)
  -0.46300000000000  -0.43800000000000  -0.22500000000000   O   (48e)
   0.52500000000000   0.78700000000000   0.06200000000000   O   (48e)
  -0.52500000000000  -0.78700000000000  -0.06200000000000   O   (48e)
   0.71300000000000   1.23800000000000   0.27500000000000   O   (48e)
  -0.71300000000000  -1.23800000000000  -0.27500000000000   O   (48e)
   0.78700000000000   0.06200000000000   0.52500000000000   O   (48e)
  -0.78700000000000  -0.06200000000000  -0.52500000000000   O   (48e)
   0.97500000000000   0.03700000000000   0.26200000000000   O   (48e)
  -0.97500000000000  -0.03700000000000  -0.26200000000000   O   (48e)
   1.23800000000000   0.27500000000000   0.71300000000000   O   (48e)
  -1.23800000000000  -0.27500000000000  -0.71300000000000   O   (48e)
```

BC8 (Si): A_cI16_206_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'BC8'
_chemical_formula_sum 'Si'

loop_
_publ_author_name
 'J. Crain'
 'G. J. Ackland'
 'S. J. Clark'
_journal_name_full
;
Reports on Progress in Physics
;
_journal_volume 58
_journal_year 1995
_journal_page_first 705
_journal_page_last 754
_publ_Section_title
;
Exotic structures of tetrahedral semiconductors
;

_aflow_proto 'A_cI16_206_c'
_aflow_params 'a,x1'
_aflow_params_values '4.11971,0.1001'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI16'

_symmetry_space_group_name_Hall "-I 2b 2c 3"
_symmetry_space_group_name_H-M "I a -3"
_symmetry_Int_Tables_number 206

_cell_length_a    4.11971
_cell_length_b    4.11971
_cell_length_c    4.11971
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x+1/2,y,-z
4 -x,-y+1/2,z
5 y,z,x
6 y,-z,-x+1/2
7 -y+1/2,z,-x
8 -y,-z+1/2,x
9 z,x,y
10 z,-x,-y+1/2
11 -z+1/2,x,-y
12 -z,-x+1/2,y
13 -x,-y,-z
14 -x,y,z+1/2
15 x+1/2,-y,z
16 x,y+1/2,-z
17 -y,-z,-x
18 -y,z,x+1/2
19 y+1/2,-z,x
20 y,z+1/2,-x
21 -z,-x,-y
22 -z,x,y+1/2
23 z+1/2,-x,y
24 z,x+1/2,-y
25 x+1/2,y+1/2,z+1/2
26 x+1/2,-y+1/2,-z
27 -x,y+1/2,-z+1/2
28 -x+1/2,-y,z+1/2
29 y+1/2,z+1/2,x+1/2
30 y+1/2,-z+1/2,-x
31 -y,z+1/2,-x+1/2
32 -y+1/2,-z,x+1/2
33 z+1/2,x+1/2,y+1/2
34 z+1/2,-x+1/2,-y
35 -z,x+1/2,-y+1/2
36 -z+1/2,-x,y+1/2
37 -x+1/2,-y+1/2,-z+1/2
38 -x+1/2,y+1/2,z
39 x,-y+1/2,z+1/2
40 x+1/2,y,-z+1/2
41 -y+1/2,-z+1/2,-x+1/2
42 -y+1/2,z+1/2,x
43 y,-z+1/2,x+1/2
44 y+1/2,z,-x+1/2
45 -z+1/2,-x+1/2,-y+1/2
46 -z+1/2,x+1/2,y
47 z,-x+1/2,y+1/2
48 z+1/2,x,-y+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si  16 c 0.10010 0.10010 0.10010 1.00000
```

BC8 (Si): A_cI16_206_c - POSCAR

```
A_cI16_206_c & a,x1 --params=4.11971,0.1001 & Ia(-3)     T_h^7 #206 (c) &
      ↪ cI16 & & Si & BC8 & J. Crain, G. J. Ackland, and S. J. Clark,
      ↪ Rep. Prog. Phys. 58, 705-754 (1995)
   1.0000000000000000
  -2.05985734394000    2.05985734394000    2.05985734394000
   2.05985734394000   -2.05985734394000    2.05985734394000
   2.05985734394000    2.05985734394000   -2.05985734394000
   Si
    8
Direct
  -0.00000000000000    0.29980000000000    0.50000000000000    Si    (16c)
   0.00000000000000    0.70020000000000    0.50000000000000    Si    (16c)
   0.20020000000000    0.20020000000000    0.20020000000000    Si    (16c)
   0.29980000000000    0.50000000000000   -0.00000000000000    Si    (16c)
   0.50000000000000   -0.00000000000000    0.29980000000000    Si    (16c)
   0.50000000000000    0.00000000000000    0.70020000000000    Si    (16c)
   0.70020000000000    0.50000000000000    0.00000000000000    Si    (16c)
   0.79980000000000    0.79980000000000    0.79980000000000    Si    (16c)
```

β-Mn (A13): A_cP20_213_cd - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'beta'
_chemical_formula_sum 'Mn'

loop_
_publ_author_name
 'Clara Brink Shoemaker'
 'David P. Shoemaker'
 'Ted E. Hopkins'
 'Somrat Yindepit'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 34
_journal_year 1978
_journal_page_first 3573
_journal_page_last 3576
_publ_Section_title
;
 Refinement of the structure of $\beta$-manganese and of a related phase
      ↪ in the Mn-Ni-Si system
;

_aflow_proto 'A_cP20_213_cd'
_aflow_params 'a,x1,y2'
_aflow_params_values '6.315,0.06361,0.20224'
_aflow_Strukturbericht 'A13'
_aflow_Pearson 'cP20'

_symmetry_space_group_name_Hall "P 4bd 2ab 3 P4_132"
_symmetry_space_group_name_H-M "P 41 3 2"
_symmetry_Int_Tables_number 213

_cell_length_a    6.31500
_cell_length_b    6.31500
_cell_length_c    6.31500
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x+1/2,-y+1/2,-z
3 -x,y+1/2,-z+1/2
4 -x+1/2,-y,z+1/2
5 y,z,x
6 y+1/2,-z+1/2,-x
7 -y,z+1/2,-x+1/2
8 -y+1/2,-z,x+1/2
9 z,x,y
10 z+1/2,-x+1/2,-y
11 -z,x+1/2,-y+1/2
12 -z+1/2,-x,y+1/2
13 -y+3/4,-x+3/4,-z+3/4
14 -y+1/4,x+3/4,z+1/4
15 y+1/4,-x+1/4,z+3/4
16 y+3/4,x+1/4,-z+1/4
17 -x+3/4,-z+3/4,-y+3/4
18 -x+1/4,z+3/4,y+1/4
19 x+1/4,-z+1/4,y+3/4
20 x+3/4,z+1/4,-y+1/4
21 -z+3/4,-y+3/4,-x+3/4
22 -z+1/4,y+3/4,x+1/4
23 z+1/4,-y+1/4,x+3/4
24 z+3/4,y+1/4,-x+1/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mn1 Mn   8 c 0.06361 0.06361 0.06361 1.00000
Mn2 Mn  12 d 0.12500 0.20224 0.45224 1.00000
```

β-Mn (A13): A_cP20_213_cd - POSCAR

```
A_cP20_213_cd & a,x1,y2 --params=6.315,0.06361,0.20224 & P4_132     O^7 #
      ↪ 213 (cd) & cP20 & A13 & Mn & beta & C.B. Shoemaker, D.P.
      ↪ Shoemaker, T.E. Hopkins and S. Yindepit, Acta Cryst. B 34,
      ↪ 3573-3576 (1978)
   1.0000000000000000
   6.31500000000000    0.00000000000000    0.00000000000000
   0.00000000000000    6.31500000000000    0.00000000000000
   0.00000000000000    0.00000000000000    6.31500000000000
   Mn
   20
Direct
  -0.04776000000000    0.37500000000000    0.79776000000000    Mn    (12d)
   0.04776000000000    0.87500000000000    0.70224000000000    Mn    (12d)
   0.12500000000000    0.20224000000000    0.45224000000000    Mn    (12d)
   0.20224000000000    0.45224000000000    0.12500000000000    Mn    (12d)
   0.29776000000000    0.54776000000000    0.62500000000000    Mn    (12d)
   0.37500000000000    0.79776000000000   -0.04776000000000    Mn    (12d)
   0.45224000000000    0.12500000000000    0.20224000000000    Mn    (12d)
   0.54776000000000    0.62500000000000    0.29776000000000    Mn    (12d)
   0.62500000000000    0.29776000000000    0.54776000000000    Mn    (12d)
   0.70224000000000    0.04776000000000    0.87500000000000    Mn    (12d)
   0.79776000000000   -0.04776000000000    0.37500000000000    Mn    (12d)
   0.87500000000000    0.70224000000000    0.04776000000000    Mn    (12d)
   0.06361000000000    0.06361000000000    0.06361000000000    Mn     (8c)
  -0.06361000000000    0.56361000000000    0.43639000000000    Mn     (8c)
   0.18639000000000    0.81361000000000    0.31361000000000    Mn     (8c)
   0.31361000000000    0.18639000000000    0.81361000000000    Mn     (8c)
   0.43639000000000   -0.06361000000000    0.56361000000000    Mn     (8c)
   0.56361000000000    0.43639000000000   -0.06361000000000    Mn     (8c)
   0.68639000000000    0.68639000000000    0.68639000000000    Mn     (8c)
   0.81361000000000    0.31361000000000    0.18639000000000    Mn     (8c)
```

Sulvanite (Cu_3S_4V, $H2_4$): A3B4C_cP8_215_d_e_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Sulvanite'
_chemical_formula_sum 'Cu3 S4 V'

loop_
_publ_author_name
 'Felix J. Trojer'
_journal_name_full
;
American Mineralogist
;
_journal_volume 51
_journal_year 1966
_journal_page_first 890
_journal_page_last 894
_publ_Section_title
;
 Refinement of the Structure of Sulvanite
;

# Found in AMS Database

_aflow_proto 'A3B4C_cP8_215_d_e_a'
_aflow_params 'a,x3'
_aflow_params_values '5.3912,0.2372'
_aflow_Strukturbericht 'H2_4'
_aflow_Pearson 'cP8'

_symmetry_space_group_name_Hall "P -4 2 3"
_symmetry_space_group_name_H-M "P -4 3 m"
_symmetry_Int_Tables_number 215

_cell_length_a    5.39120
_cell_length_b    5.39120
_cell_length_c    5.39120
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x,z,y
18 x,-z,-y
```

```
19 -x,z,-y
20 -x,-z,y
21 z,y,x
22 z,-y,-x
23 -z,y,-x
24 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
V1  V    1 a 0.00000 0.00000 0.00000 1.00000
Cu1 Cu   3 d 0.50000 0.00000 0.00000 1.00000
S1  S    4 e 0.23720 0.23720 0.23720 1.00000
```

Sulvanite (Cu_3S_4V, H_2): A3B4C_cP8_215_d_e_a - POSCAR

```
A3B4C_cP8_215_d_e_a & a,x3 --params=5.3912,0.2372 & P(-4)3m   T_d^1 #215
    ↪ (ade) & cP8 & H2_4 & Cu3S4V & Sulvanite & F. J. Trojer, Am.
    ↪ Mineral. 51, 890-894 (1966)
   1.0000000000000000
   5.39120000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.39120000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.39120000000000
   Cu    S    V
    3    4    1
Direct
   0.00000000000000    0.00000000000000    0.50000000000000   Cu    (3d)
   0.00000000000000    0.50000000000000    0.00000000000000   Cu    (3d)
   0.50000000000000    0.00000000000000    0.00000000000000   Cu    (3d)
   0.23720000000000    0.23720000000000    0.23720000000000   S     (4e)
   0.23720000000000    0.76280000000000    0.76280000000000   S     (4e)
   0.76280000000000    0.23720000000000    0.76280000000000   S     (4e)
   0.76280000000000    0.76280000000000    0.23720000000000   S     (4e)
   0.00000000000000    0.00000000000000    0.00000000000000   V     (1a)
```

Fe_4C: AB4_cP5_215_a_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Iron carbide'
_chemical_formula_sum 'Fe4 C'

loop_
_publ_author_name
 'Z. G. Pinsker'
 'S. V. Kaverin'
_journal_name_full
;
Soviet Physics-Crystallography, translated from Kristallografiya
;
_journal_volume 1
_journal_year 1956
_journal_page_first 48
_journal_page_last 53
_publ_Section_title
;
 Electron-Diffraction Determination of the Structure of Iron Carbide
    ↪ Fe$_4$C
;

# Found in  Pearson's Handbook, Vol. II, pp. 1895

_aflow_proto 'AB4_cP5_215_a_e'
_aflow_params 'a,x2'
_aflow_params_values '3.878,0.265'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP5'

_symmetry_space_group_name_Hall "P -4 2 3"
_symmetry_space_group_name_H-M "P -4 3 m"
_symmetry_Int_Tables_number 215

_cell_length_a      3.87800
_cell_length_b      3.87800
_cell_length_c      3.87800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x,z,y
18 x,-z,-y
19 -x,z,-y
20 -x,-z,y
21 z,y,x
22 z,-y,-x
23 -z,y,-x
24 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C    1 a 0.00000 0.00000 0.00000 1.00000
Fe1 Fe   4 e 0.26500 0.26500 0.26500 1.00000
```

Fe_4C: AB4_cP5_215_a_e - POSCAR

```
AB4_cP5_215_a_e & a,x2 --params=3.878,0.265 & P(-4)3m   T_d^1 #215 (ae)
    ↪ & cP5 & Fe4C & & Z. G. Pinsker and S. V. Kaverin, Sov.
    ↪ Physics Cryst. 1, 48-53 (1956)
   1.0000000000000000
   3.87800000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.87800000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.87800000000000
    C    Fe
    1    4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000   C     (1a)
   0.26500000000000    0.26500000000000    0.26500000000000   Fe    (4e)
   0.26500000000000    0.73500000000000    0.73500000000000   Fe    (4e)
   0.73500000000000    0.26500000000000    0.73500000000000   Fe    (4e)
   0.73500000000000    0.73500000000000    0.26500000000000   Fe    (4e)
```

Cubic Lazarevićite ($AsCu_3S_4$): AB3C4_cP8_215_a_c_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Lavarevi\'{c}ite'
_chemical_formula_sum 'As Cu3 S4'

loop_
_publ_author_name
 'C. B. Sclar'
 'M. Drovenik'
_journal_name_full
;
Geological Society of America Bulletin
;
_journal_volume 71
_journal_year 1960
_journal_page_first 1970
_journal_page_last 1970
_publ_Section_title
;
 Lazarevi\'{c}ite, A New Cubic Copper-Arsenic Sulfied from Bor,
    ↪ Jugoslavia
;

# Found in  Pearson's Handbook, Vol. I, pp. 1111-1112, Fleischer 1961

_aflow_proto 'AB3C4_cP8_215_a_c_e'
_aflow_params 'a,x3'
_aflow_params_values '5.28,0.25'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP8'

_symmetry_space_group_name_Hall "P -4 2 3"
_symmetry_space_group_name_H-M "P -4 3 m"
_symmetry_Int_Tables_number 215

_cell_length_a      5.28000
_cell_length_b      5.28000
_cell_length_c      5.28000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 y,x,z
14 y,-x,-z
```

```
-y,x,-z
-y,-x,z
x,z,y
x,-z,-y
-x,z,-y
-x,-z,y
z,y,x
z,-y,-x
-z,y,-x
-z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
As1  As    1  a  0.00000  0.00000  0.00000  1.00000
Cu1  Cu    3  c  0.00000  0.50000  0.50000  1.00000
S1   S     4  e  0.25000  0.25000  0.25000  1.00000
```

Cubic Lazarevićite ($AsCu_3S_4$): AB3C4_cP8_215_a_c_e - POSCAR

```
AB3C4_cP8_215_a_c_e & a,x3 --params=5.28,0.25 & P(-4)3m    T_d^1 #215 (
    ↪ ace) & cP8 & & AsCu3S4 & Lazarevicite & C. B. Sclar and M.
    ↪ Drovenik, Bull. Geo. Soc. Am. 71, 1970 (1960)
   1.00000000000000000
   5.28000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.28000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.28000000000000
   As    Cu    S
    1     3     4
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    As    (1a)
   0.00000000000000    0.50000000000000    0.50000000000000    Cu    (3c)
   0.50000000000000    0.00000000000000    0.50000000000000    Cu    (3c)
   0.50000000000000    0.50000000000000    0.00000000000000    Cu    (3c)
   0.25000000000000    0.25000000000000    0.25000000000000    S     (4e)
   0.25000000000000    0.75000000000000    0.75000000000000    S     (4e)
   0.75000000000000    0.25000000000000    0.75000000000000    S     (4e)
   0.75000000000000    0.75000000000000    0.25000000000000    S     (4e)
```

$AuBe_5$ ($C15_b$): AB5_cF24_216_a_ce - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Au Be5'

loop_
_publ_author_name
 'F. W. von Batchelder'
 'R. F. Raeuchle'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 11
_journal_year 1958
_journal_page_first 122
_journal_page_last 122
_publ_Section_title
;
 The tetragonal MBe$_{12}$ structure of silver, palladium, platinum and
    ↪ gold
;

# Found in  pearson58:C15b

_aflow_proto 'AB5_cF24_216_a_ce'
_aflow_params 'a,x3'
_aflow_params_values '6.1,0.625'
_aflow_Strukturbericht 'C15_b'
_aflow_Pearson 'cF24'

_symmetry_space_group_name_Hall "F -4 2 3"
_symmetry_space_group_name_H-M "F -4 3 m"
_symmetry_Int_Tables_number 216

_cell_length_a     6.10000
_cell_length_b     6.10000
_cell_length_c     6.10000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x,z,y
18 x,-z,-y
19 -x,z,-y
20 -x,-z,y
21 z,y,x
22 z,-y,-x
23 -z,y,-x
24 -z,-y,x
25 x,y+1/2,z+1/2
26 x,-y+1/2,-z+1/2
27 -x,y+1/2,-z+1/2
28 -x,-y+1/2,z+1/2
29 y,z+1/2,x+1/2
30 y,-z+1/2,-x+1/2
31 -y,z+1/2,-x+1/2
32 -y,-z+1/2,x+1/2
33 z,x+1/2,y+1/2
34 z,-x+1/2,-y+1/2
35 -z,x+1/2,-y+1/2
36 -z,-x+1/2,y+1/2
37 y,x+1/2,z+1/2
38 y,-x+1/2,-z+1/2
39 -y,x+1/2,-z+1/2
40 -y,-x+1/2,z+1/2
41 x,z+1/2,y+1/2
42 x,-z+1/2,-y+1/2
43 -x,z+1/2,-y+1/2
44 -x,-z+1/2,y+1/2
45 z,y+1/2,x+1/2
46 z,-y+1/2,-x+1/2
47 -z,y+1/2,-x+1/2
48 -z,-y+1/2,x+1/2
49 x+1/2,y,z+1/2
50 x+1/2,-y,-z+1/2
51 -x+1/2,y,-z+1/2
52 -x+1/2,-y,z+1/2
53 y+1/2,z,x+1/2
54 y+1/2,-z,-x+1/2
55 -y+1/2,z,-x+1/2
56 -y+1/2,-z,x+1/2
57 z+1/2,x,y+1/2
58 z+1/2,-x,-y+1/2
59 -z+1/2,x,-y+1/2
60 -z+1/2,-x,y+1/2
61 y+1/2,x,z+1/2
62 y+1/2,-x,-z+1/2
63 -y+1/2,x,-z+1/2
64 -y+1/2,-x,z+1/2
65 x+1/2,z,y+1/2
66 x+1/2,-z,-y+1/2
67 -x+1/2,z,-y+1/2
68 -x+1/2,-z,y+1/2
69 z+1/2,y,x+1/2
70 z+1/2,-y,-x+1/2
71 -z+1/2,y,-x+1/2
72 -z+1/2,-y,x+1/2
73 x+1/2,y+1/2,z
74 x+1/2,-y+1/2,-z
75 -x+1/2,y+1/2,-z
76 -x+1/2,-y+1/2,z
77 y+1/2,z+1/2,x
78 y+1/2,-z+1/2,-x
79 -y+1/2,z+1/2,-x
80 -y+1/2,-z+1/2,x
81 z+1/2,x+1/2,y
82 z+1/2,-x+1/2,-y
83 -z+1/2,x+1/2,-y
84 -z+1/2,-x+1/2,y
85 y+1/2,x+1/2,z
86 y+1/2,-x+1/2,-z
87 -y+1/2,x+1/2,-z
88 -y+1/2,-x+1/2,z
89 x+1/2,z+1/2,y
90 x+1/2,-z+1/2,-y
91 -x+1/2,z+1/2,-y
92 -x+1/2,-z+1/2,y
93 z+1/2,y+1/2,x
94 z+1/2,-y+1/2,-x
95 -z+1/2,y+1/2,-x
96 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Au1  Au    4  a  0.00000  0.00000  0.00000  1.00000
Be1  Be    4  c  0.25000  0.25000  0.25000  1.00000
Be2  Be   16  e  0.62500  0.62500  0.62500  1.00000
```

$AuBe_5$ ($C15_b$): AB5_cF24_216_a_ce - POSCAR

```
AB5_cF24_216_a_ce & a,x3 --params=6.1,0.625 & F(-4)3m    T_d^2 #216 (ace)
    ↪ & cF24 & C15_b & AuBe5 & & F. W. von Batchelder and R. F.
    ↪ Raeuchle, Acta Cryst. 11, 122 (1958)
```

```
   1.0000000000000000
   0.00000000000000    3.05000000000000    3.05000000000000
   3.05000000000000    0.00000000000000    3.05000000000000
   3.05000000000000    3.05000000000000    0.00000000000000
   Au    Be
    1     5
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Au     (4a)
   0.12500000000000    0.62500000000000    0.62500000000000    Be    (16e)
   0.62500000000000    0.12500000000000    0.62500000000000    Be    (16e)
   0.62500000000000    0.62500000000000    0.12500000000000    Be    (16e)
   0.62500000000000    0.62500000000000    0.62500000000000    Be    (16e)
   0.25000000000000    0.25000000000000    0.25000000000000    Be     (4c)
```

Half-Heusler ($C1_b$): ABC_cF12_216_b_c_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'half-Heusler'
_chemical_formula_sum 'Ag As Mg'

loop_
_publ_author_name
 'H. Nowotny'
 'W. Sibert'
_journal_name_full
;
Zeitschrift f\"{u}r Metallkunde
;
_journal_volume 33
_journal_year 1941
_journal_page_first 391
_journal_page_last 394
_publ_Section_title
;
 Tern\"{a}re Valenzverbindungen in den Systemen Kupfer(Silber)-Arsen(
      ↪ Antimon,Wismut)-Magnesium
;

# Found in  Pearson, Alloys, pp. 386

_aflow_proto 'ABC_cF12_216_b_c_a'
_aflow_params 'a'
_aflow_params_values '6.24'
_aflow_Strukturbericht 'C1_b'
_aflow_Pearson 'cF12'

_symmetry_space_group_name_Hall "F -4 2 3"
_symmetry_space_group_name_H-M "F -4 3 m"
_symmetry_Int_Tables_number 216

_cell_length_a      6.24000
_cell_length_b      6.24000
_cell_length_c      6.24000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x,z,y
18 x,-z,-y
19 -x,z,-y
20 -x,-z,y
21 z,y,x
22 z,-y,-x
23 -z,y,-x
24 -z,-y,x
25 x,y+1/2,z+1/2
26 x,-y+1/2,-z+1/2
27 -x,y+1/2,-z+1/2
28 -x,-y+1/2,z+1/2
29 y,z+1/2,x+1/2
30 y,-z+1/2,-x+1/2
31 -y,z+1/2,-x+1/2
32 -y,-z+1/2,x+1/2
33 z,x+1/2,y+1/2
34 z,-x+1/2,-y+1/2
35 -z,x+1/2,-y+1/2
36 -z,-x+1/2,y+1/2
37 y,x+1/2,z+1/2
38 y,-x+1/2,-z+1/2
39 -y,x+1/2,-z+1/2
40 -y,-x+1/2,z+1/2
41 x,z+1/2,y+1/2
42 x,-z+1/2,-y+1/2
43 -x,z+1/2,-y+1/2
44 -x,-z+1/2,y+1/2
45 z,y+1/2,x+1/2
46 z,-y+1/2,-x+1/2
47 -z,y+1/2,-x+1/2
48 -z,-y+1/2,x+1/2
49 x+1/2,y,z+1/2
50 x+1/2,-y,-z+1/2
51 -x+1/2,y,-z+1/2
52 -x+1/2,-y,z+1/2
53 y+1/2,z,x+1/2
54 y+1/2,-z,-x+1/2
55 -y+1/2,z,-x+1/2
56 -y+1/2,-z,x+1/2
57 z+1/2,x,y+1/2
58 z+1/2,-x,-y+1/2
59 -z+1/2,x,-y+1/2
60 -z+1/2,-x,y+1/2
61 y+1/2,x,z+1/2
62 y+1/2,-x,-z+1/2
63 -y+1/2,x,-z+1/2
64 -y+1/2,-x,z+1/2
65 x+1/2,z,y+1/2
66 x+1/2,-z,-y+1/2
67 -x+1/2,z,-y+1/2
68 -x+1/2,-z,y+1/2
69 z+1/2,y,x+1/2
70 z+1/2,-y,-x+1/2
71 -z+1/2,y,-x+1/2
72 -z+1/2,-y,x+1/2
73 x+1/2,y+1/2,z
74 x+1/2,-y+1/2,-z
75 -x+1/2,y+1/2,-z
76 -x+1/2,-y+1/2,z
77 y+1/2,z+1/2,x
78 y+1/2,-z+1/2,-x
79 -y+1/2,z+1/2,-x
80 -y+1/2,-z+1/2,x
81 z+1/2,x+1/2,y
82 z+1/2,-x+1/2,-y
83 -z+1/2,x+1/2,-y
84 -z+1/2,-x+1/2,y
85 y+1/2,x+1/2,z
86 y+1/2,-x+1/2,-z
87 -y+1/2,x+1/2,-z
88 -y+1/2,-x+1/2,z
89 x+1/2,z+1/2,y
90 x+1/2,-z+1/2,-y
91 -x+1/2,z+1/2,-y
92 -x+1/2,-z+1/2,y
93 z+1/2,y+1/2,x
94 z+1/2,-y+1/2,-x
95 -z+1/2,y+1/2,-x
96 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mg1 Mg   4 a 0.00000 0.00000 0.00000 1.00000
Ag1 Ag   4 b 0.50000 0.50000 0.50000 1.00000
As1 As   4 c 0.25000 0.25000 0.25000 1.00000
```

Half-Heusler ($C1_b$): ABC_cF12_216_b_c_a - POSCAR

```
ABC_cF12_216_b_c_a & a --params=6.24 & F(-4)3m   T_d^2 #216 (abc) & cF12
      ↪ & C1_b & AgAsMg & Half-Heulser & H. Nowotny and W. Sibert, Z.
      ↪ Metallkd. 33, 391-394 (1941)
   1.0000000000000000
   0.00000000000000    3.12000000000000    3.12000000000000
   3.12000000000000    0.00000000000000    3.12000000000000
   3.12000000000000    3.12000000000000    0.00000000000000
   Ag    As    Mg
    1     1     1
Direct
   0.50000000000000    0.50000000000000    0.50000000000000    Ag     (4b)
   0.25000000000000    0.25000000000000    0.25000000000000    As     (4c)
   0.00000000000000    0.00000000000000    0.00000000000000    Mg     (4a)
```

Zincblende (ZnS, B3): AB_cF8_216_c_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Zincblende, Sphalerite'
_chemical_formula_sum 'Zn S'

loop_
_publ_author_name
 'Brian J. Skinner'
_journal_name_full
;
American Mineralogist
;
_journal_volume 46
_journal_year 1961
_journal_page_first 1399
```

```
_journal_page_last 1411
_publ_Section_title
;
 Unit-Cell Edges of Natural and Synthetic Sphalerites
;

# Found in  AMC Database

_aflow_proto 'AB_cF8_216_c_a'
_aflow_params 'a'
_aflow_params_values '5.4093'
_aflow_Strukturbericht 'B3'
_aflow_Pearson 'cF8'

_symmetry_space_group_name_Hall "F -4 2 3"
_symmetry_space_group_name_H-M "F -4 3 m"
_symmetry_Int_Tables_number 216

_cell_length_a      5.40930
_cell_length_b      5.40930
_cell_length_c      5.40930
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x,z,y
18 x,-z,-y
19 -x,z,-y
20 -x,-z,y
21 z,y,x
22 z,-y,-x
23 -z,y,-x
24 -z,-y,x
25 x,y+1/2,z+1/2
26 x,-y+1/2,-z+1/2
27 -x,y+1/2,-z+1/2
28 -x,-y+1/2,z+1/2
29 y,z+1/2,x+1/2
30 y,-z+1/2,-x+1/2
31 -y,z+1/2,-x+1/2
32 -y,-z+1/2,x+1/2
33 z,x+1/2,y+1/2
34 z,-x+1/2,-y+1/2
35 -z,x+1/2,-y+1/2
36 -z,-x+1/2,y+1/2
37 y,x+1/2,z+1/2
38 y,-x+1/2,-z+1/2
39 -y,x+1/2,-z+1/2
40 -y,-x+1/2,z+1/2
41 x,z+1/2,y+1/2
42 x,-z+1/2,-y+1/2
43 -x,z+1/2,-y+1/2
44 -x,-z+1/2,y+1/2
45 z,y+1/2,x+1/2
46 z,-y+1/2,-x+1/2
47 -z,y+1/2,-x+1/2
48 -z,-y+1/2,x+1/2
49 x+1/2,y,z+1/2
50 x+1/2,-y,-z+1/2
51 -x+1/2,y,-z+1/2
52 -x+1/2,-y,z+1/2
53 y+1/2,z,x+1/2
54 y+1/2,-z,-x+1/2
55 -y+1/2,z,-x+1/2
56 -y+1/2,-z,x+1/2
57 z+1/2,x,y+1/2
58 z+1/2,-x,-y+1/2
59 -z+1/2,x,-y+1/2
60 -z+1/2,-x,y+1/2
61 y+1/2,x,z+1/2
62 y+1/2,-x,-z+1/2
63 -y+1/2,x,-z+1/2
64 -y+1/2,-x,z+1/2
65 x+1/2,z,y+1/2
66 x+1/2,-z,-y+1/2
67 -x+1/2,z,-y+1/2
68 -x+1/2,-z,y+1/2
69 z+1/2,y,x+1/2
70 z+1/2,-y,-x+1/2
71 -z+1/2,y,-x+1/2
72 -z+1/2,-y,x+1/2
73 x+1/2,y+1/2,z
74 x+1/2,-y+1/2,-z
75 -x+1/2,y+1/2,-z
76 -x+1/2,-y+1/2,z
77 y+1/2,z+1/2,x
78 y+1/2,-z+1/2,-x
79 -y+1/2,z+1/2,-x
80 -y+1/2,-z+1/2,x
81 z+1/2,x+1/2,y
82 z+1/2,-x+1/2,-y
83 -z+1/2,x+1/2,-y
84 -z+1/2,-x+1/2,y
85 y+1/2,x+1/2,z
86 y+1/2,-x+1/2,-z
87 -y+1/2,x+1/2,-z
88 -y+1/2,-x+1/2,z
89 x+1/2,z+1/2,y
90 x+1/2,-z+1/2,-y
91 -x+1/2,z+1/2,-y
92 -x+1/2,-z+1/2,y
93 z+1/2,y+1/2,x
94 z+1/2,-y+1/2,-x
95 -z+1/2,y+1/2,-x
96 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Zn1 Zn    4 a 0.00000 0.00000 0.00000 1.00000
S1  S     4 c 0.25000 0.25000 0.25000 1.00000
```

Zincblende (ZnS, B3): AB_cF8_216_c_a - POSCAR

```
AB_cF8_216_c_a & a --params=5.4093 & F(-4)3m          T_d^2 #216 (ac) &
    ↪ cF8 & B3 & ZnS (cubic) & Zincblende/Sphalerite & B. J. Skinner,
    ↪  Am. Mineral. 46, 1399-1411 (1961)
   1.0000000000000000
   0.00000000000000    2.70465000000000    2.70465000000000
   2.70465000000000    0.00000000000000    2.70465000000000
   2.70465000000000    2.70465000000000    0.00000000000000
    S    Zn
    1    1
Direct
   0.25000000000000    0.25000000000000    0.25000000000000    S    (4c)
   0.00000000000000    0.00000000000000    0.00000000000000    Zn   (4a)
```

SiF_4: A4B_cI10_217_c_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Silicon tetrafluoride'
_chemical_formula_sum 'Si F4'

loop_
_publ_author_name
 'Maso Atoji'
 'William N. Lipscomb'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 7
_journal_year 1954
_journal_page_first 597
_journal_page_last 597
_publ_Section_title
;
 The structure of SiF$_4$
;

_aflow_proto 'A4B_cI10_217_c_a'
_aflow_params 'a,x2'
_aflow_params_values '5.45858,0.165'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI10'

_symmetry_space_group_name_Hall "I -4 2 3"
_symmetry_space_group_name_H-M "I -4 3 m"
_symmetry_Int_Tables_number 217

_cell_length_a      5.45858
_cell_length_b      5.45858
_cell_length_c      5.45858
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
```

```
12 -z,-x,y
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x,z,y
18 x,-z,-y
19 -x,z,-y
20 -x,-z,y
21 z,y,x
22 z,-y,-x
23 -z,y,-x
24 -z,-y,x
25 x+1/2,y+1/2,z+1/2
26 x+1/2,-y+1/2,-z+1/2
27 -x+1/2,y+1/2,-z+1/2
28 -x+1/2,-y+1/2,z+1/2
29 y+1/2,z+1/2,x+1/2
30 y+1/2,-z+1/2,-x+1/2
31 -y+1/2,z+1/2,-x+1/2
32 -y+1/2,-z+1/2,x+1/2
33 z+1/2,x+1/2,y+1/2
34 z+1/2,-x+1/2,-y+1/2
35 -z+1/2,x+1/2,-y+1/2
36 -z+1/2,-x+1/2,y+1/2
37 y+1/2,x+1/2,z+1/2
38 y+1/2,-x+1/2,-z+1/2
39 -y+1/2,x+1/2,-z+1/2
40 -y+1/2,-x+1/2,z+1/2
41 x+1/2,z+1/2,y+1/2
42 x+1/2,-z+1/2,-y+1/2
43 -x+1/2,z+1/2,-y+1/2
44 -x+1/2,-z+1/2,y+1/2
45 z+1/2,y+1/2,x+1/2
46 z+1/2,-y+1/2,-x+1/2
47 -z+1/2,y+1/2,-x+1/2
48 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   2 a 0.00000 0.00000 0.00000 1.00000
F1  F    8 c 0.16500 0.16500 0.16500 1.00000
```

SiF_4: A4B_cI10_217_c_a - POSCAR

```
A4B_cI10_217_c_a & a,x2 --params=5.45858,0.165 & I(-4)3m   T_d^3 #217 (
    ↪ ac) & cI10 & & SiF4 & & M. Atoji and W. N. Lipscomb, Acta
    ↪ Cryst. 7, 597 (1954)
   1.0000000000000000
  -2.72929218000000   2.72929218000000   2.72929218000000
   2.72929218000000  -2.72929218000000   2.72929218000000
   2.72929218000000   2.72929218000000  -2.72929218000000
    F   Si
    4    1
Direct
   0.00000000000000   0.00000000000000  -0.33000000000000   F   (8c)
   0.00000000000000  -0.33000000000000   0.00000000000000   F   (8c)
  -0.33000000000000   0.00000000000000   0.00000000000000   F   (8c)
   0.33000000000000   0.33000000000000   0.33000000000000   F   (8c)
   0.00000000000000   0.00000000000000   0.00000000000000  Si   (2a)
```

α-Mn (A12): A_cI58_217_ac2g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha'
_chemical_formula_sum 'Mn'

loop_
_publ_author_name
 'J. A. Oberteuffer'
 'James A. Ibers'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 26
_journal_year 1970
_journal_page_first 1499
_journal_page_last 1504
_publ_Section_title
;
 A refinement of the atomic and thermal parameters of $\alpha$-manganese
    ↪ from a single crystal
;

# Found in Donohue, pp. 191-196

_aflow_proto 'A_cI58_217_ac2g'
_aflow_params 'a,x2,x3,z3,x4,z4'
_aflow_params_values '8.911,0.31787,-0.08958,0.28194,0.64294,0.03457'
_aflow_Strukturbericht 'A12'
_aflow_Pearson 'cI58'

_symmetry_space_group_name_Hall "I -4 2 3"
_symmetry_space_group_name_H-M "I -4 3 m"
_symmetry_Int_Tables_number 217

_cell_length_a      8.91100
_cell_length_b      8.91100
_cell_length_c      8.91100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x,z,y
18 x,-z,-y
19 -x,z,-y
20 -x,-z,y
21 z,y,x
22 z,-y,-x
23 -z,y,-x
24 -z,-y,x
25 x+1/2,y+1/2,z+1/2
26 x+1/2,-y+1/2,-z+1/2
27 -x+1/2,y+1/2,-z+1/2
28 -x+1/2,-y+1/2,z+1/2
29 y+1/2,z+1/2,x+1/2
30 y+1/2,-z+1/2,-x+1/2
31 -y+1/2,z+1/2,-x+1/2
32 -y+1/2,-z+1/2,x+1/2
33 z+1/2,x+1/2,y+1/2
34 z+1/2,-x+1/2,-y+1/2
35 -z+1/2,x+1/2,-y+1/2
36 -z+1/2,-x+1/2,y+1/2
37 y+1/2,x+1/2,z+1/2
38 y+1/2,-x+1/2,-z+1/2
39 -y+1/2,x+1/2,-z+1/2
40 -y+1/2,-x+1/2,z+1/2
41 x+1/2,z+1/2,y+1/2
42 x+1/2,-z+1/2,-y+1/2
43 -x+1/2,z+1/2,-y+1/2
44 -x+1/2,-z+1/2,y+1/2
45 z+1/2,y+1/2,x+1/2
46 z+1/2,-y+1/2,-x+1/2
47 -z+1/2,y+1/2,-x+1/2
48 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mn1 Mn   2 a 0.00000  0.00000  0.00000 1.00000
Mn2 Mn   8 c 0.31787  0.31787  0.31787 1.00000
Mn3 Mn  24 g -0.08958 -0.08958 0.28194 1.00000
Mn4 Mn  24 g 0.64294  0.64294  0.03457 1.00000
```

α-Mn (A12): A_cI58_217_ac2g - POSCAR

```
A_cI58_217_ac2g & a,x2,x3,z3,x4,z4 --params=8.911,0.31787,-0.08958,
    ↪ 0.28194,0.64294,0.03457 & I(-4)3m   T_d^3 #217 (acg^2) & cI58 &
    ↪ A12 & Mn & alpha & J. A. Oberteuffer and J. A. Ibers, Acta
    ↪ Cryst. B 26, 1499-1504 (1970)
   1.0000000000000000
  -4.45550000000000   4.45550000000000   4.45550000000000
   4.45550000000000  -4.45550000000000   4.45550000000000
   4.45550000000000   4.45550000000000  -4.45550000000000
   Mn
   29
Direct
   0.00000000000000   0.62848000000000   0.80764000000000   Mn   (24g)
   0.00000000000000   0.80764000000000   0.62848000000000   Mn   (24g)
   0.17916000000000   0.37152000000000   0.37152000000000   Mn   (24g)
   0.19236000000000   0.19236000000000   0.82084000000000   Mn   (24g)
   0.19236000000000   0.82084000000000   0.19236000000000   Mn   (24g)
   0.37152000000000   0.17916000000000   0.37152000000000   Mn   (24g)
   0.37152000000000   0.37152000000000   0.17916000000000   Mn   (24g)
   0.62848000000000   0.00000000000000   0.80764000000000   Mn   (24g)
   0.62848000000000   0.80764000000000   0.00000000000000   Mn   (24g)
   0.80764000000000   0.00000000000000   0.62848000000000   Mn   (24g)
   0.80764000000000   0.62848000000000   0.00000000000000   Mn   (24g)
   0.82084000000000   0.19236000000000   0.19236000000000   Mn   (24g)
   0.00000000000000   0.32249000000000   0.60837000000000   Mn   (24g)
   0.00000000000000   0.60837000000000   0.32249000000000   Mn   (24g)
   0.28588000000000   0.67751000000000   0.67751000000000   Mn   (24g)
   0.32249000000000   0.00000000000000   0.60837000000000   Mn   (24g)
```

```
    0.32249000000000    0.60837000000000    0.00000000000000    Mn    (24g)
    0.39163000000000    0.39163000000000    0.71412000000000    Mn    (24g)
    0.39163000000000    0.71412000000000    0.39163000000000    Mn    (24g)
    0.60837000000000    0.00000000000000    0.32249000000000    Mn    (24g)
    0.60837000000000    0.32249000000000    0.00000000000000    Mn    (24g)
    0.67751000000000    0.28588000000000    0.67751000000000    Mn    (24g)
    0.67751000000000    0.67751000000000    0.28588000000000    Mn    (24g)
    0.71412000000000    0.39163000000000    0.39163000000000    Mn    (24g)
    0.00000000000000    0.00000000000000    0.00000000000000    Mn     (2a)
    0.00000000000000    0.00000000000000    0.36426000000000    Mn     (8c)
    0.00000000000000    0.36426000000000    0.00000000000000    Mn     (8c)
    0.36426000000000    0.00000000000000    0.00000000000000    Mn     (8c)
    0.63574000000000    0.63574000000000    0.63574000000000    Mn     (8c)
```

γ-Brass (Cu_5Zn_8): A5B8_cI52_217_ce_cg - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'gamma-brass'
_chemical_formula_sum 'Cu5 Zn8'

loop_
_publ_author_name
 'Olivier Gourdon'
 'Delphine Gout'
 'Darrick J. Williams'
 'Thomas Proffen'
 'Sara Hobbs'
 'Gordon J. Miller'
_journal_name_full
;
Inorganic Chemistry
;
_journal_volume 46
_journal_year 2007
_journal_page_first 251
_journal_page_last 260
_publ_Section_title
;
 Atomic Distributions in the $\gamma$-Brass Structure of the Cu-Zn
      ↪ System: A Structural and Theoretical Study
;

_aflow_proto 'A5B8_cI52_217_ce_cg'
_aflow_params 'a,x1,x2,x3,x4,z4'
_aflow_params_values '8.8664,0.32774,0.10781,0.64421,0.68844,0.03674'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI52'

_symmetry_space_group_name_Hall "I -4 2 3"
_symmetry_space_group_name_H-M "I -4 3 m"
_symmetry_Int_Tables_number 217

_cell_length_a      8.86640
_cell_length_b      8.86640
_cell_length_c      8.86640
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 y,x,z
14 y,-x,-z
15 -y,x,-z
16 -y,-x,z
17 x,z,y
18 x,-z,-y
19 -x,z,-y
20 -x,-z,y
21 z,y,x
22 z,-y,-x
23 -z,y,-x
24 -z,-y,x
25 x+1/2,y+1/2,z+1/2
26 x+1/2,-y+1/2,-z+1/2
27 -x+1/2,y+1/2,-z+1/2
28 -x+1/2,-y+1/2,z+1/2
29 y+1/2,z+1/2,x+1/2
30 y+1/2,-z+1/2,-x+1/2
31 -y+1/2,z+1/2,-x+1/2
32 -y+1/2,-z+1/2,x+1/2
33 z+1/2,x+1/2,y+1/2
34 z+1/2,-x+1/2,-y+1/2
35 -z+1/2,x+1/2,-y+1/2
36 -z+1/2,-x+1/2,y+1/2
37 y+1/2,x+1/2,z+1/2
38 y+1/2,-x+1/2,-z+1/2
39 -y+1/2,x+1/2,-z+1/2
40 -y+1/2,-x+1/2,z+1/2
41 x+1/2,z+1/2,y+1/2
42 x+1/2,-z+1/2,-y+1/2
43 -x+1/2,z+1/2,-y+1/2
44 -x+1/2,-z+1/2,y+1/2
45 z+1/2,y+1/2,x+1/2
46 z+1/2,-y+1/2,-x+1/2
47 -z+1/2,y+1/2,-x+1/2
48 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu   8 c 0.32774 0.32774 0.32774 1.00000
Zn1 Zn   8 c 0.10781 0.10781 0.10781 1.00000
Cu2 Cu  12 e 0.64421 0.00000 0.00000 1.00000
Zn2 Zn  24 g 0.68844 0.68844 0.03674 1.00000
```

γ-Brass (Cu_5Zn_8): A5B8_cI52_217_ce_cg - POSCAR

```
A5B8_cI52_217_ce_cg & a,x1,x2,x3,x4,z4 --params=8.8664,0.32774,0.10781,
      ↪ 0.64421,0.68844,0.03674 & I(-4)3m   T_d^3 #217 (c^2eg) & cI52 &
      ↪  & Cu5Zn8 & gamma brass & O. Gourdon et al., Inorg. Chem. 46,
      ↪ 251-260 (2007)
   1.0000000000000000
  -4.43320000000000    4.43320000000000    4.43320000000000
   4.43320000000000   -4.43320000000000    4.43320000000000
   4.43320000000000    4.43320000000000   -4.43320000000000
   Cu    Zn
   10    16
Direct
   0.00000000000000    0.35579000000000    0.35579000000000    Cu    (12e)
   0.00000000000000    0.64421000000000    0.64421000000000    Cu    (12e)
   0.35579000000000    0.00000000000000    0.35579000000000    Cu    (12e)
   0.35579000000000    0.35579000000000    0.00000000000000    Cu    (12e)
   0.64421000000000    0.00000000000000    0.64421000000000    Cu    (12e)
   0.64421000000000    0.64421000000000    0.00000000000000    Cu    (12e)
   0.00000000000000    0.00000000000000    0.34452000000000    Cu     (8c)
   0.00000000000000    0.34452000000000    0.00000000000000    Cu     (8c)
   0.34452000000000    0.00000000000000    0.00000000000000    Cu     (8c)
   0.65548000000000    0.65548000000000    0.65548000000000    Cu     (8c)
   0.00000000000000    0.27482000000000    0.65170000000000    Zn    (24g)
   0.00000000000000    0.65170000000000    0.27482000000000    Zn    (24g)
   0.27482000000000    0.00000000000000    0.65170000000000    Zn    (24g)
   0.27482000000000    0.65170000000000    0.00000000000000    Zn    (24g)
   0.34830000000000    0.34830000000000    0.62312000000000    Zn    (24g)
   0.34830000000000    0.62312000000000    0.34830000000000    Zn    (24g)
   0.37688000000000    0.72518000000000    0.72518000000000    Zn    (24g)
   0.62312000000000    0.34830000000000    0.34830000000000    Zn    (24g)
   0.65170000000000    0.00000000000000    0.27482000000000    Zn    (24g)
   0.65170000000000    0.27482000000000    0.00000000000000    Zn    (24g)
   0.72518000000000    0.37688000000000    0.72518000000000    Zn    (24g)
   0.72518000000000    0.72518000000000    0.37688000000000    Zn    (24g)
   0.00000000000000    0.00000000000000    0.78438000000000    Zn     (8c)
   0.00000000000000    0.78438000000000    0.00000000000000    Zn     (8c)
   0.21562000000000    0.21562000000000    0.21562000000000    Zn     (8c)
   0.78438000000000    0.00000000000000    0.00000000000000    Zn     (8c)
```

High-Pressure cI16 Li: A_cI16_220_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'High pressure (38.9 GPa) phase of lithium'
_chemical_formula_sum 'Li'

loop_
_publ_author_name
 'M. Hanfland'
 'K. Syassen'
 'N. E. Christensen'
 'D. L. Novikov'
_journal_name_full
;
Nature
;
_journal_volume 408
_journal_year 2000
_journal_page_first 174
_journal_page_last 178
_publ_Section_title
;
 New high-pressure phases of lithium
;

_aflow_proto 'A_cI16_220_c'
_aflow_params 'a,x1'
_aflow_params_values '5.2716,0.049'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI16'

_symmetry_space_group_name_Hall "I -4bd 2c 3 I(-4)3d"
_symmetry_space_group_name_H-M "I -4 3 d"
_symmetry_Int_Tables_number 220

_cell_length_a      5.27160
_cell_length_b      5.27160
```

```
_cell_length_c      5.27160
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x+1/2,y,-z
4 -x,-y+1/2,z
5 y,z,x
6 y,-z,-x+1/2
7 -y+1/2,z,-x
8 -y,-z+1/2,x
9 z,x,y
10 z,-x,-y+1/2
11 -z+1/2,x,-y
12 -z,-x+1/2,y
13 y+1/4,x+1/4,z+1/4
14 y+1/4,-x+3/4,-z+1/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+3/4,-x+1/4,z+1/4
17 x+1/4,z+1/4,y+1/4
18 x+1/4,-z+3/4,-y+1/4
19 -x+1/4,z+1/4,-y+3/4
20 -x+3/4,-z+1/4,y+1/4
21 z+1/4,y+1/4,x+1/4
22 z+1/4,-y+3/4,-x+1/4
23 -z+1/4,y+1/4,-x+3/4
24 -z+3/4,-y+1/4,x+1/4
25 x+1/2,y+1/2,z+1/2
26 x+1/2,-y+1/2,-z
27 -x,y+1/2,-z+1/2
28 -x+1/2,-y,z+1/2
29 y+1/2,z+1/2,x+1/2
30 y+1/2,-z+1/2,-x
31 -y,z+1/2,-x+1/2
32 -y+1/2,-z,x+1/2
33 z+1/2,x+1/2,y+1/2
34 z+1/2,-x+1/2,-y
35 -z,x+1/2,-y+1/2
36 -z+1/2,-x,y+1/2
37 y+3/4,x+3/4,z+3/4
38 y+3/4,-x+1/4,-z+3/4
39 -y+3/4,x+3/4,-z+1/4
40 -y+1/4,-x+3/4,z+3/4
41 x+3/4,z+3/4,y+3/4
42 x+3/4,-z+1/4,-y+3/4
43 -x+3/4,z+3/4,-y+1/4
44 -x+1/4,-z+3/4,y+3/4
45 z+3/4,y+3/4,x+3/4
46 z+3/4,-y+1/4,-x+3/4
47 -z+3/4,y+3/4,-x+1/4
48 -z+1/4,-y+3/4,x+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Li1 Li   16 c 0.04900 0.04900 0.04900 1.00000
```

High-Pressure cI16 Li: A_cI16_220_c - POSCAR

```
A_cI16_220_c & a,x1 --params=5.2716,0.049 & I(-4)3d    T_d^6 #220 (c) &
      ↪ cI16 & & Li & 38.9 GPa & M. Hanfland, K. Syassen, N. E.
      ↪ Christensen and D. L. Novikov, Nature 408, 174-178 (2000)
   1.0000000000000000
  -2.63580000000000    2.63580000000000    2.63580000000000
   2.63580000000000   -2.63580000000000    2.63580000000000
   2.63580000000000    2.63580000000000   -2.63580000000000
   Li
    8
Direct
   0.00000000000000   -0.09800000000000    0.50000000000000    Li    (16c)
   0.00000000000000    0.40200000000000    0.50000000000000    Li    (16c)
   0.09800000000000    0.09800000000000    0.09800000000000    Li    (16c)
  -0.09800000000000    0.50000000000000    0.00000000000000    Li    (16c)
   0.40200000000000    0.50000000000000    0.00000000000000    Li    (16c)
   0.50000000000000    0.00000000000000   -0.09800000000000    Li    (16c)
   0.50000000000000    0.00000000000000    0.40200000000000    Li    (16c)
   0.59800000000000    0.59800000000000    0.59800000000000    Li    (16c)
```

Pu_2C_3 ($D5_c$): A3B2_cI40_220_d_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Plutonium carbide'
_chemical_formula_sum 'Pu2 C3'

loop_
_publ_author_name
 'J. L. Green'
 'G. P. Arnold'
 'J. A. Leary'
 'N. G. Nereson'
_journal_name_full
;
Journal of Nuclear Materials
;
_journal_volume 34
_journal_year 1970
_journal_page_first 281
_journal_page_last 289
_publ_Section_title
;
 Crystallographic and magnetic ordering studies of plutonium carbides
      ↪ using neutron diffraction
;

#Found in Pearson's Handbook, Vol. IV, pp 1993

_aflow_proto 'A3B2_cI40_220_d_c'
_aflow_params 'a,x1,x2'
_aflow_params_values '8.135,0.0492,0.2896'
_aflow_Strukturbericht 'D5_c'
_aflow_Pearson 'cI40'

_symmetry_space_group_name_Hall "I -4bd 2c 3 I(-4)3d"
_symmetry_space_group_name_H-M "I -4 3 d"
_symmetry_Int_Tables_number 220

_cell_length_a      8.13500
_cell_length_b      8.13500
_cell_length_c      8.13500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x+1/2,y,-z
4 -x,-y+1/2,z
5 y,z,x
6 y,-z,-x+1/2
7 -y+1/2,z,-x
8 -y,-z+1/2,x
9 z,x,y
10 z,-x,-y+1/2
11 -z+1/2,x,-y
12 -z,-x+1/2,y
13 y+1/4,x+1/4,z+1/4
14 y+1/4,-x+3/4,-z+1/4
15 -y+1/4,x+1/4,-z+3/4
16 -y+3/4,-x+1/4,z+1/4
17 x+1/4,z+1/4,y+1/4
18 x+1/4,-z+3/4,-y+1/4
19 -x+1/4,z+1/4,-y+3/4
20 -x+3/4,-z+1/4,y+1/4
21 z+1/4,y+1/4,x+1/4
22 z+1/4,-y+3/4,-x+1/4
23 -z+1/4,y+1/4,-x+3/4
24 -z+3/4,-y+1/4,x+1/4
25 x+1/2,y+1/2,z+1/2
26 x+1/2,-y+1/2,-z
27 -x,y+1/2,-z+1/2
28 -x+1/2,-y,z+1/2
29 y+1/2,z+1/2,x+1/2
30 y+1/2,-z+1/2,-x
31 -y,z+1/2,-x+1/2
32 -y+1/2,-z,x+1/2
33 z+1/2,x+1/2,y+1/2
34 z+1/2,-x+1/2,-y
35 -z,x+1/2,-y+1/2
36 -z+1/2,-x,y+1/2
37 y+3/4,x+3/4,z+3/4
38 y+3/4,-x+1/4,-z+3/4
39 -y+3/4,x+3/4,-z+1/4
40 -y+1/4,-x+3/4,z+3/4
41 x+3/4,z+3/4,y+3/4
42 x+3/4,-z+1/4,-y+3/4
43 -x+3/4,z+3/4,-y+1/4
44 -x+1/4,-z+3/4,y+3/4
45 z+3/4,y+3/4,x+3/4
46 z+3/4,-y+1/4,-x+3/4
47 -z+3/4,y+3/4,-x+1/4
48 -z+1/4,-y+3/4,x+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pu1 Pu   16 c 0.04920 0.04920 0.04920 1.00000
C1  C    24 d 0.28960 0.00000 0.25000 1.00000
```

Pu_2C_3 ($D5_c$): A3B2_cI40_220_d_c - POSCAR

```
A3B2_cI40_220_d_c & a,x1,x2 --params=8.135,0.0492,0.2896 & I(-4)3d    T_d
      ↪ ^6 #220 (cd) & cI40 & D5_c & Pu2C3 & & J.L. Green, G.P. Arnold,
      ↪ J.A. Leary and N.G. Nereson, J. Nucl. Mater. 34, 281-289 (1970
      ↪ )
   1.0000000000000000
  -4.06750000000000    4.06750000000000    4.06750000000000
```

```
   4.06750000000000  -4.06750000000000   4.06750000000000
   4.06750000000000   4.06750000000000  -4.06750000000000
    C    Pu
   12    8
Direct
  -0.03960000000000   0.21040000000000   0.75000000000000   C    (24d)
   0.03960000000000   0.75000000000000   0.78960000000000   C    (24d)
   0.21040000000000   0.75000000000000  -0.03960000000000   C    (24d)
   0.25000000000000   0.53960000000000   0.28960000000000   C    (24d)
   0.25000000000000   0.71040000000000   0.46040000000000   C    (24d)
   0.28960000000000   0.25000000000000   0.53960000000000   C    (24d)
   0.46040000000000   0.25000000000000   0.71040000000000   C    (24d)
   0.53960000000000   0.28960000000000   0.25000000000000   C    (24d)
   0.71040000000000   0.46040000000000   0.25000000000000   C    (24d)
   0.75000000000000  -0.03960000000000   0.21040000000000   C    (24d)
   0.75000000000000   0.78960000000000   0.03960000000000   C    (24d)
   0.78960000000000   0.03960000000000   0.75000000000000   C    (24d)
   0.00000000000000  -0.09840000000000   0.50000000000000  Pu    (16c)
   0.00000000000000   0.40160000000000   0.50000000000000  Pu    (16c)
   0.09840000000000   0.09840000000000   0.09840000000000  Pu    (16c)
  -0.09840000000000   0.50000000000000   0.00000000000000  Pu    (16c)
   0.40160000000000   0.50000000000000   0.00000000000000  Pu    (16c)
   0.50000000000000   0.00000000000000  -0.09840000000000  Pu    (16c)
   0.50000000000000   0.00000000000000   0.40160000000000  Pu    (16c)
   0.59840000000000   0.59840000000000   0.59840000000000  Pu    (16c)
```

CsCl (B2): AB_cP2_221_b_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cs Cl'

loop_
_publ_author_name
 'V. Ganesan'
 'K. S. Girirajan'
_journal_name_full
;
Paramana -- Journal of Physics
;
_journal_volume 27
_journal_year 1986
_journal_page_first 469
_journal_page_last 474
_publ_Section_title
;
 Lattice parameter and thermal expansion of CsCl and CsBr by x-ray
      ↪ powder diffraction. I. Thermal expansion of CsCl from room
      ↪ temperature to 90$^{\circ}$ K
;

_aflow_proto 'AB_cP2_221_b_a'
_aflow_params 'a'
_aflow_params_values '4.07925'
_aflow_Strukturbericht 'B2'
_aflow_Pearson 'cP2'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a     4.07925
_cell_length_b     4.07925
_cell_length_c     4.07925
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cs1 Cs    1 a 0.00000 0.00000 0.00000 1.00000
Cl1 Cl    1 b 0.50000 0.50000 0.50000 1.00000
```

CsCl (B2): AB_cP2_221_b_a - POSCAR

```
AB_cP2_221_b_a & a --params=4.07925 & Pm(-3)m    O_h^1 #221 (ab) & cP2 &
      ↪ B2 & CsCl & & V. Ganesan and K. S. Girirajan, Parmana --
      ↪ Journal of Physics 27, 469-474 (1986)
   1.0000000000000000
   4.07925000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.07925000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.07925000000000
   Cl    Cs
    1     1
Direct
   0.50000000000000    0.50000000000000    0.50000000000000    Cl    (1b)
   0.00000000000000    0.00000000000000    0.00000000000000    Cs    (1a)
```

NbO: AB_cP6_221_c_d - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Nb O'

loop_
_publ_author_name
 'A. L. Bowman'
 'T. C. Wallace'
 'J. L. Yarnell'
 'R. G. Wenzel'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 21
_journal_year 1966
_journal_page_first 843
_journal_page_last 843
_publ_Section_title
;
 The crystal structure of niobium monoxide
;

# Found in  Pearson's Handbook, Vol. IV, pp. 4535

_aflow_proto 'AB_cP6_221_c_d'
_aflow_params 'a'
_aflow_params_values '4.2101'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP6'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a     4.21010
_cell_length_b     4.21010
_cell_length_c     4.21010
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
```

```
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Nb1 Nb    3 c 0.00000 0.50000 0.50000 1.00000
O1  O     3 d 0.50000 0.00000 0.00000 1.00000
```

NbO: AB_cP6_221_c_d - POSCAR

```
AB_cP6_221_c_d & a --params=4.2101 & Pm(-3)m    O_h^1 #221 (cd) & cP6 & &
    ↪ NbO & & A. L. Bowman, T. C. Wallace, J. L. Yarnell and R. G.
    ↪ Wenzel, Acta Cryst. 21, 843 (1966)
   1.0000000000000000
   4.21010000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.21010000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.21010000000000
   Nb    O
    3    3
Direct
   0.00000000000000    0.50000000000000    0.50000000000000    Nb    (3c)
   0.50000000000000    0.00000000000000    0.50000000000000    Nb    (3c)
   0.50000000000000    0.50000000000000    0.00000000000000    Nb    (3c)
   0.00000000000000    0.00000000000000    0.50000000000000     O    (3d)
   0.00000000000000    0.50000000000000    0.00000000000000     O    (3d)
   0.50000000000000    0.00000000000000    0.00000000000000     O    (3d)
```

Cubic Perovskite ($CaTiO_3$, $E2_1$): AB3C_cP5_221_a_c_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral '(Cubic) Perovskite'
_chemical_formula_sum 'Ca Ti O3'

loop_
_publ_author_name
 'T. Barth'
_journal_name_full
;
Norsk Geologisk Tidsskrift
;
_journal_volume 8
_journal_year 1925
_journal_page_first 14
_journal_page_last 19
_publ_Section_title
;
 Die Kristallstruktur von Perowskit und verwandten Verbidungen
;

# Found in AMS Database

_aflow_proto 'AB3C_cP5_221_a_c_b'
_aflow_params 'a'
_aflow_params_values '3.795'
_aflow_Strukturbericht 'E2_1'
_aflow_Pearson 'cP5'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a      3.79500
_cell_length_b      3.79500
_cell_length_c      3.79500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ca1 Ca    1 a 0.00000 0.00000 0.00000 1.00000
Ti1 Ti    1 b 0.50000 0.50000 0.50000 1.00000
O1  O     3 c 0.00000 0.50000 0.50000 1.00000
```

Cubic Perovskite ($CaTiO_3$, $E2_1$): AB3C_cP5_221_a_c_b - POSCAR

```
AB3C_cP5_221_a_c_b & a --params=3.795 & Pm(-3)m    O_h^1 #221 (abc) & cP5
    ↪ & E2_1 & CaTiO3 & Perovskite & T. Barth, Norsk. Geol. Tidssk.
    ↪ 8, 14-29 (1925)
   1.0000000000000000
   3.79500000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.79500000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.79500000000000
   Ca    O    Ti
    1    3     1
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Ca    (1a)
   0.00000000000000    0.50000000000000    0.50000000000000     O    (3c)
   0.50000000000000    0.00000000000000    0.50000000000000     O    (3c)
   0.50000000000000    0.50000000000000    0.00000000000000     O    (3c)
   0.50000000000000    0.50000000000000    0.50000000000000    Ti    (1b)
```

Model of Austenite (cP32): AB27CD3_cP32_221_a_dij_b_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr Fe27 Mo Ni3'
```

```
loop_
_publ_author_name
 'Michael J. Mehl'
_journal_name_full
;
None
;
_journal_volume 0
_journal_year 2008
_journal_page_first 0
_journal_page_last 0
_publ_Section_title
;
 Hypothetical cP32 Austenite Structure
;

_aflow_proto 'AB27CD3_cP32_221_a_dij_b_c'
_aflow_params 'a,y5,y6'
_aflow_params_values '7.04,0.245,0.26'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP32'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a      7.04000
_cell_length_b      7.04000
_cell_length_c      7.04000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1  Cr    1  a  0.00000  0.00000  0.00000  1.00000
Mo1  Mo    1  b  0.50000  0.50000  0.50000  1.00000
Ni1  Ni    3  c  0.00000  0.50000  0.50000  1.00000
Fe1  Fe    3  d  0.50000  0.00000  0.00000  1.00000
Fe2  Fe   12  i  0.00000  0.24500  0.24500  1.00000
Fe3  Fe   12  j  0.50000  0.26000  0.26000  1.00000
```

Model of Austenite (cP32): AB27CD3_cP32_221_a_dij_b_c - POSCAR

```
AB27CD3_cP32_221_a_dij_b_c & a,y5,y6 --params=7.04,0.245,0.26 & Pm(-3)m
    ↪ O_h^1 #221 (abcdij) & cP32 & & CrFe27MoNi3 & Hypothetical
    ↪ Austenitic Phase &
   1.0000000000000000
   7.04000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    7.04000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    7.04000000000000
   Cr   Fe   Mo   Ni
    1   27    1    3
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cr    (1a)
   0.00000000000000    0.24500000000000    0.24500000000000    Fe   (12i)
   0.00000000000000    0.24500000000000    0.75500000000000    Fe   (12i)
  -0.00000000000000    0.75500000000000    0.24500000000000    Fe   (12i)
   0.00000000000000    0.75500000000000    0.75500000000000    Fe   (12i)
   0.24500000000000    0.00000000000000    0.24500000000000    Fe   (12i)
   0.24500000000000    0.00000000000000    0.75500000000000    Fe   (12i)
   0.24500000000000    0.24500000000000    0.00000000000000    Fe   (12i)
   0.24500000000000    0.75500000000000    0.00000000000000    Fe   (12i)
   0.75500000000000    0.00000000000000    0.24500000000000    Fe   (12i)
   0.75500000000000    0.00000000000000    0.75500000000000    Fe   (12i)
   0.75500000000000    0.24500000000000    0.00000000000000    Fe   (12i)
   0.75500000000000    0.75500000000000    0.00000000000000    Fe   (12i)
   0.26000000000000    0.26000000000000    0.50000000000000    Fe   (12j)
   0.26000000000000    0.50000000000000    0.26000000000000    Fe   (12j)
   0.26000000000000    0.50000000000000    0.74000000000000    Fe   (12j)
   0.26000000000000    0.74000000000000    0.50000000000000    Fe   (12j)
   0.50000000000000    0.26000000000000    0.26000000000000    Fe   (12j)
   0.50000000000000    0.26000000000000    0.74000000000000    Fe   (12j)
   0.50000000000000    0.74000000000000    0.26000000000000    Fe   (12j)
   0.50000000000000    0.74000000000000    0.74000000000000    Fe   (12j)
   0.74000000000000    0.26000000000000    0.50000000000000    Fe   (12j)
   0.74000000000000    0.50000000000000    0.26000000000000    Fe   (12j)
   0.74000000000000    0.50000000000000    0.74000000000000    Fe   (12j)
   0.74000000000000    0.74000000000000    0.50000000000000    Fe   (12j)
   0.00000000000000    0.00000000000000    0.50000000000000    Fe    (3d)
   0.00000000000000    0.50000000000000    0.00000000000000    Fe    (3d)
   0.50000000000000    0.00000000000000    0.00000000000000    Fe    (3d)
   0.50000000000000    0.50000000000000    0.50000000000000    Mo    (1b)
   0.00000000000000    0.50000000000000    0.50000000000000    Ni    (3c)
   0.50000000000000    0.00000000000000    0.50000000000000    Ni    (3c)
   0.50000000000000    0.50000000000000    0.00000000000000    Ni    (3c)
```

Cu_3Au ($L1_2$): AB3_cP4_221_a_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cu3 Au'

loop_
_publ_author_name
 'E. A. Owen'
 'Y. H. Liu'
_journal_name_full
;
Philosophical Magazine
;
_journal_volume 38
_journal_year 1947
_journal_page_first 354
_journal_page_last 360
_publ_Section_title
;
 The Thermal Expansion of the Gold-Copper Alloy AuCu$_3$
;

# Found in Pearson's Handbook, Vol. 1, pp. 1273

_aflow_proto 'AB3_cP4_221_a_c'
_aflow_params 'a'
_aflow_params_values '3.7402'
_aflow_Strukturbericht 'L1_2'
_aflow_Pearson 'cP4'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a      3.74020
_cell_length_b      3.74020
_cell_length_c      3.74020
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
```

```
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Au1 Au   1 a 0.00000 0.00000 0.00000 1.00000
Cu1 Cu   3 c 0.00000 0.50000 0.50000 1.00000
```

Cu_3Au ($L1_2$): AB3_cP4_221_a_c - POSCAR

```
AB3_cP4_221_a_c & a --params=3.7402 & Pm(-3)m   O_h^1 #221 (ac) & cP4 &
    ↪ L1_2 & Cu3Au & & E. A. Owen and Y. H. Liu, Phil. Mag. 38,
    ↪ 354-360 (1947)
   1.0000000000000000
   3.74020000000000   0.00000000000000   0.00000000000000
   0.00000000000000   3.74020000000000   0.00000000000000
   0.00000000000000   0.00000000000000   3.74020000000000
   Au   Cu
    1    3
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Au   (1a)
   0.00000000000000   0.50000000000000   0.50000000000000   Cu   (3c)
   0.50000000000000   0.00000000000000   0.50000000000000   Cu   (3c)
   0.50000000000000   0.50000000000000   0.00000000000000   Cu   (3c)
```

α-Po (A_h): A_cP1_221_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha Po'
_chemical_formula_sum 'Po'

loop_
_publ_author_name
 'William H. Beamer'
 'Charles R. Maxwell'
_journal_name_full
;
Journal of Chemical Physics
;
_journal_volume 14
_journal_year 1946
_journal_page_first 569
_journal_page_last 569
_publ_Section_title
;
 The Crystal Structure of Polonium
;

# Found in  Donohue, pp. 390-391

_aflow_proto 'A_cP1_221_a'
_aflow_params 'a'
_aflow_params_values '3.34'
_aflow_Strukturbericht 'A_h'
_aflow_Pearson 'cP1'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a    3.34000
_cell_length_b    3.34000
_cell_length_c    3.34000
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Po1 Po   1 a 0.00000 0.00000 0.00000 1.00000
```

α-Po (A_h): A_cP1_221_a - POSCAR

```
A_cP1_221_a & a --params=3.34 & Pm(-3)m   O_h^1 #221 (a) & cP1 & A_h &
    ↪ Po & alpha & W. H. Beamer and C. R. Maxwell, J. Chem. Physics
    ↪ 14, 569 (1946)
   1.0000000000000000
   3.34000000000000   0.00000000000000   0.00000000000000
   0.00000000000000   3.34000000000000   0.00000000000000
   0.00000000000000   0.00000000000000   3.34000000000000
   Po
    1
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Po   (1a)
```

$BaHg_{11}$ ($D2_e$): AB11_cP36_221_c_agij - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ba Hg11'

loop_
_publ_author_name
 'G. Peyronel'
_journal_name_full
;
Gazzetta Chimica Italiana
;
_journal_volume 82
_journal_year 1952
_journal_page_first 679
_journal_page_last 690
_publ_Section_title
;
 Struttura della fase BaHg$_{11}$
```

```
;

# Found in http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_1251135

_aflow_proto 'AB11_cP36_221_c_agij'
_aflow_params 'a,x3,y4,y5'
_aflow_params_values '9.6,0.345,0.225,0.115'
_aflow_Strukturbericht 'D2_e'
_aflow_Pearson 'cP36'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a      9.60000
_cell_length_b      9.60000
_cell_length_c      9.60000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Hg1 Hg   1 a 0.00000 0.00000 0.00000 1.00000
Ba1 Ba   3 c 0.00000 0.50000 0.50000 1.00000
Hg2 Hg   8 g 0.34500 0.34500 0.34500 1.00000
Hg3 Hg  12 i 0.00000 0.22500 0.22500 1.00000
Hg4 Hg  12 j 0.50000 0.11500 0.11500 1.00000
```

$BaHg_{11}$ ($D2_e$): AB11_cP36_221_c_agij - POSCAR

```
AB11_cP36_221_c_agij & a,x3,y4,y5 --params=9.6,0.345,0.225,0.115 & Pm(-3
    ↪ )m O_h^1 #221 (acgij) & cP36 & D2_e & BaHg11 & & G. Peyronel,
    ↪ Gazz. Chim. Ital. 82, 679-90 (1952)
   1.0000000000000000
   9.60000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    9.60000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    9.60000000000000
   Ba   Hg
    3   33
Direct
   0.00000000000000    0.50000000000000    0.50000000000000    Ba    (3c)
   0.50000000000000    0.00000000000000    0.50000000000000    Ba    (3c)
   0.50000000000000    0.50000000000000    0.00000000000000    Ba    (3c)
   0.00000000000000    0.22500000000000    0.22500000000000    Hg    (12i)
   0.00000000000000    0.22500000000000    0.77500000000000    Hg    (12i)
   0.00000000000000    0.77500000000000    0.22500000000000    Hg    (12i)
   0.00000000000000    0.77500000000000    0.77500000000000    Hg    (12i)
   0.22500000000000    0.00000000000000    0.22500000000000    Hg    (12i)
   0.22500000000000    0.00000000000000    0.77500000000000    Hg    (12i)
   0.22500000000000    0.22500000000000    0.00000000000000    Hg    (12i)
   0.22500000000000    0.77500000000000    0.00000000000000    Hg    (12i)
   0.77500000000000    0.00000000000000    0.22500000000000    Hg    (12i)
   0.77500000000000    0.00000000000000    0.77500000000000    Hg    (12i)
   0.77500000000000    0.22500000000000    0.00000000000000    Hg    (12i)
   0.77500000000000    0.77500000000000    0.00000000000000    Hg    (12i)
   0.11500000000000    0.11500000000000    0.50000000000000    Hg    (12j)
   0.11500000000000    0.50000000000000    0.11500000000000    Hg    (12j)
   0.11500000000000    0.50000000000000    0.88500000000000    Hg    (12j)
   0.11500000000000    0.88500000000000    0.50000000000000    Hg    (12j)
   0.50000000000000    0.11500000000000    0.11500000000000    Hg    (12j)
   0.50000000000000    0.11500000000000    0.88500000000000    Hg    (12j)
   0.50000000000000    0.88500000000000    0.11500000000000    Hg    (12j)
   0.50000000000000    0.88500000000000    0.88500000000000    Hg    (12j)
   0.88500000000000    0.11500000000000    0.50000000000000    Hg    (12j)
   0.88500000000000    0.50000000000000    0.11500000000000    Hg    (12j)
   0.88500000000000    0.50000000000000    0.88500000000000    Hg    (12j)
   0.88500000000000    0.88500000000000    0.50000000000000    Hg    (12j)
   0.00000000000000    0.00000000000000    0.00000000000000    Hg    (1a)
   0.34500000000000    0.34500000000000    0.34500000000000    Hg    (8g)
   0.34500000000000    0.34500000000000    0.65500000000000    Hg    (8g)
   0.34500000000000    0.65500000000000    0.34500000000000    Hg    (8g)
   0.34500000000000    0.65500000000000    0.65500000000000    Hg    (8g)
   0.65500000000000    0.34500000000000    0.34500000000000    Hg    (8g)
   0.65500000000000    0.34500000000000    0.65500000000000    Hg    (8g)
   0.65500000000000    0.65500000000000    0.34500000000000    Hg    (8g)
   0.65500000000000    0.65500000000000    0.65500000000000    Hg    (8g)
```

Model of Ferrite (cP16): AB11CD3_cP16_221_a_dg_b_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr Fe11 Mo Ni3'

loop_
_publ_author_name
 'Michael J. Mehl'
_journal_name_full
;
None
;
_journal_volume 0
_journal_year 2008
_journal_page_first 0
_journal_page_last 0
_publ_Section_title
;
 Hypothetical cP16 Austenite Structure
;

_aflow_proto 'AB11CD3_cP16_221_a_dg_b_c'
_aflow_params 'a,x5'
_aflow_params_values '5.74,0.245'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP16'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a      5.74000
_cell_length_b      5.74000
_cell_length_c      5.74000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
```

```
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1 Cr   1 a 0.00000 0.00000 0.00000 1.00000
Mo1 Mo   1 b 0.50000 0.50000 0.50000 1.00000
Ni1 Ni   3 c 0.00000 0.50000 0.50000 1.00000
Fe1 Fe   3 d 0.50000 0.00000 0.00000 1.00000
Fe2 Fe   8 g 0.24500 0.24500 0.24500 1.00000
```

Model of Ferrite (cP16): AB11CD3_cP16_221_a_dg_b_c - POSCAR

```
AB11CD3_cP16_221_a_dg_b_c & a,x5 --params=5.74,0.245 & Pm(-3)m   O_h^1 #
    ↪ 221 (abcdg) & cP16 & & CrFe11MoNi3 & Hypothetical Ferritic
    ↪ Phase &
   1.0000000000000000
   5.74000000000000    0.00000000000000    0.00000000000000
   0.00000000000000    5.74000000000000    0.00000000000000
   0.00000000000000    0.00000000000000    5.74000000000000
   Cr   Fe   Mo   Ni
    1   11    1    3
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cr    (1a)
   0.00000000000000    0.00000000000000    0.50000000000000    Fe    (3d)
   0.00000000000000    0.50000000000000    0.00000000000000    Fe    (3d)
   0.50000000000000    0.00000000000000    0.00000000000000    Fe    (3d)
   0.24500000000000    0.24500000000000    0.24500000000000    Fe    (8g)
   0.24500000000000    0.24500000000000    0.75500000000000    Fe    (8g)
   0.24500000000000    0.75500000000000    0.24500000000000    Fe    (8g)
   0.24500000000000    0.75500000000000    0.75500000000000    Fe    (8g)
   0.75500000000000    0.24500000000000    0.24500000000000    Fe    (8g)
   0.75500000000000    0.24500000000000    0.75500000000000    Fe    (8g)
   0.75500000000000    0.75500000000000    0.24500000000000    Fe    (8g)
   0.75500000000000    0.75500000000000    0.75500000000000    Fe    (8g)
   0.50000000000000    0.50000000000000    0.50000000000000    Mo    (1b)
   0.00000000000000    0.50000000000000    0.50000000000000    Ni    (3c)
   0.50000000000000    0.00000000000000    0.50000000000000    Ni    (3c)
   0.50000000000000    0.50000000000000    0.00000000000000    Ni    (3c)
```

α-ReO_3 ($D0_9$): A3B_cP4_221_d_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha Rhenium trioxide'
_chemical_formula_sum 'Re O3'

loop_
_publ_author_name
 'Karl Meisel'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 207
_journal_year 1932
_journal_page_first 121
_journal_page_last 128
_publ_Section_title
;
 Rheniumtrioxyd. III. Mitteilung. \"{U}ber die Kristallstruktur des
    ↪ Rheniumtrioxyds
;

# Found in AMS Database

_aflow_proto 'A3B_cP4_221_d_a'
_aflow_params 'a'
_aflow_params_values '3.734'
_aflow_Strukturbericht 'D0_9'
_aflow_Pearson 'cP4'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a      3.73400
_cell_length_b      3.73400
_cell_length_c      3.73400
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Re1 Re   1 a 0.00000 0.00000 0.00000 1.00000
O1  O    3 d 0.50000 0.00000 0.00000 1.00000
```

α-ReO_3 ($D0_9$): A3B_cP4_221_d_a - POSCAR

```
A3B_cP4_221_d_a & a --params=3.734 & Pm(-3)m   O_h^1 #221 (ad) & cP4 &
    ↪ D0_9 & ReO3 & & K. Meisel, ZAAC 207, 121-128 (1932)
   1.0000000000000000
   3.73400000000000    0.00000000000000    0.00000000000000
   0.00000000000000    3.73400000000000    0.00000000000000
   0.00000000000000    0.00000000000000    3.73400000000000
    O   Re
    3    1
Direct
   0.00000000000000    0.00000000000000    0.50000000000000    O    (3d)
   0.00000000000000    0.50000000000000    0.00000000000000    O    (3d)
   0.50000000000000    0.00000000000000    0.00000000000000    O    (3d)
   0.00000000000000    0.00000000000000    0.00000000000000   Re    (1a)
```

CaB_6 ($D2_1$): A6B_cP7_221_f_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Calcium hexaboride'
_chemical_formula_sum 'Ca B6'

loop_
_publ_author_name
 'Z. Yahia'
 'S. Turrell'
 'G. Turrell'
 'J. P. Mercurio'
_journal_name_full
```

```
;
Journal of Molecular Structure
;
_journal_volume 224
_journal_year 1990
_journal_page_first 303
_journal_page_last 312
_publ_Section_title
;
 Infrared and Raman spectra of hexaborides: force-field calculations,
      ↪ and isotopic effects
;

_aflow_proto 'A6B_cP7_221_f_a'
_aflow_params 'a,x2'
_aflow_params_values '4.145,0.2117'
_aflow_Strukturbericht 'D2_1'
_aflow_Pearson 'cP7'

_symmetry_space_group_name_Hall "-P 4 2 3"
_symmetry_space_group_name_H-M "P m -3 m"
_symmetry_Int_Tables_number 221

_cell_length_a     4.14500
_cell_length_b     4.14500
_cell_length_c     4.14500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ca1 Ca    1 a 0.00000 0.00000 0.00000 1.00000
B1  B     6 f 0.21170 0.50000 0.50000 1.00000
```

CaB_6 ($D2_1$): A6B_cP7_221_f_a - POSCAR

```
A6B_cP7_221_f_a & a,x2 --params=4.145,0.2117 & Pm(-3)m    O_h^1 #221 (af)
      ↪ & cP7 & D2_1 & CaB6 & & Z. Yahia, S. Turrell, G. Turrell and
      ↪ J. P. Mercurio, J. Mol. Struct. 224, 303-312 (1990)
   1.0000000000000000
   4.14500000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.14500000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.14500000000000
    B    Ca
    6     1
Direct
   0.21170084439100    0.50000000000000    0.50000000000000    B    (6f)
   0.50000000000000    0.21170084439100    0.50000000000000    B    (6f)
   0.50000000000000    0.50000000000000    0.21170084439100    B    (6f)
   0.50000000000000    0.50000000000000    0.78829915560900    B    (6f)
   0.50000000000000    0.78829915560900    0.50000000000000    B    (6f)
   0.78829915560900    0.50000000000000    0.50000000000000    B    (6f)
   0.00000000000000    0.00000000000000    0.00000000000000   Ca    (1a)
```

Cr_3Si (A15): A3B_cP8_223_c_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr3 Si'

loop_
_publ_author_name
 'W. Jauch'
 'A. J. Schultz'
 'G. Heger'
_journal_name_full
;
Journal of Applied Crystallography
;
_journal_volume 20
_journal_year 1987
_journal_page_first 117
_journal_page_last 119
_publ_Section_title
;
 Single-crystal time-of-flight neutron diffraction of Cr$_3$Si and
      ↪ MnF$_2$ comparison with monochromatic-beam techniques
;

# Found in  Pearson's Handbook Vol. III, pp. 2742

_aflow_proto 'A3B_cP8_223_c_a'
_aflow_params 'a'
_aflow_params_values '4.556'
_aflow_Strukturbericht 'A15'
_aflow_Pearson 'cP8'

_symmetry_space_group_name_Hall "-P 4n 2 3"
_symmetry_space_group_name_H-M "P m -3 n"
_symmetry_Int_Tables_number 223

_cell_length_a     4.55600
_cell_length_b     4.55600
_cell_length_c     4.55600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y+1/2,-x+1/2,-z+1/2
14 -y+1/2,x+1/2,z+1/2
15 y+1/2,-x+1/2,z+1/2
16 y+1/2,x+1/2,-z+1/2
17 -x+1/2,-z+1/2,-y+1/2
18 -x+1/2,z+1/2,y+1/2
19 x+1/2,-z+1/2,y+1/2
20 x+1/2,z+1/2,-y+1/2
21 -z+1/2,-y+1/2,-x+1/2
22 -z+1/2,y+1/2,x+1/2
23 z+1/2,-y+1/2,x+1/2
24 z+1/2,y+1/2,-x+1/2
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y+1/2,x+1/2,z+1/2
38 y+1/2,-x+1/2,-z+1/2
39 -y+1/2,x+1/2,-z+1/2
40 -y+1/2,-x+1/2,z+1/2
41 x+1/2,z+1/2,y+1/2
42 x+1/2,-z+1/2,-y+1/2
43 -x+1/2,z+1/2,-y+1/2
44 -x+1/2,-z+1/2,y+1/2
45 z+1/2,y+1/2,x+1/2
```

```
46 z+1/2,-y+1/2,-x+1/2
47 -z+1/2,y+1/2,-x+1/2
48 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   2 a 0.00000 0.00000 0.00000 1.00000
Cr1 Cr   6 c 0.25000 0.00000 0.50000 1.00000
```

Cr_3Si (A15): A3B_cP8_223_c_a - POSCAR

```
A3B_cP8_223_c_a & a --params=4.556 & Pm(-3)n   O_h^3 #223 (ac) & cP8 &
    ↪ A15 & Cr3Si & & W. Jauch, A. J. Schultz and G. Heger, J. Appl.
    ↪ Crystallogr. 20, 117-119 (1987)
   1.0000000000000000
   4.55600000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.55600000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.55600000000000
   Cr   Si
    6    2
Direct
   0.00000000000000    0.50000000000000    0.25000000000000    Cr    (6c)
   0.00000000000000    0.50000000000000    0.75000000000000    Cr    (6c)
   0.25000000000000    0.00000000000000    0.50000000000000    Cr    (6c)
   0.50000000000000    0.25000000000000    0.00000000000000    Cr    (6c)
   0.50000000000000    0.75000000000000    0.00000000000000    Cr    (6c)
   0.75000000000000    0.00000000000000    0.50000000000000    Cr    (6c)
   0.00000000000000    0.00000000000000    0.00000000000000    Si    (2a)
   0.50000000000000    0.50000000000000    0.50000000000000    Si    (2a)
```

Si_{46} Clathrate: A_cP46_223_dik - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Clathrate'
_chemical_formula_sum 'Si'

loop_
_publ_author_name
 'Gary B. Adams'
 'Michael O'Keeffe'
 'Alexander A. Demkov'
 'Otto F. Sankey'
 'Yin-Min Huang'
_journal_name_full
;
Physical Review B
;
_journal_volume 49
_journal_year 1994
_journal_page_first 8048
_journal_page_last 8053
_publ_Section_title
;
 Wide-band-gap Si in open fourfold-coordinated clathrate structures
;

_aflow_proto 'A_cP46_223_dik'
_aflow_params 'a,x2,y3,z3'
_aflow_params_values '10.355,0.1837,0.1172,0.3077'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cP46'

_symmetry_space_group_name_Hall "-P 4n 2 3"
_symmetry_space_group_name_H-M "P m -3 n"
_symmetry_Int_Tables_number 223

_cell_length_a      10.35500
_cell_length_b      10.35500
_cell_length_c      10.35500
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y+1/2,-x+1/2,-z+1/2
14 -y+1/2,x+1/2,z+1/2
15 y+1/2,-x+1/2,z+1/2
16 y+1/2,x+1/2,-z+1/2
17 -x+1/2,-z+1/2,-y+1/2
18 -x+1/2,z+1/2,y+1/2
19 x+1/2,-z+1/2,y+1/2
20 x+1/2,z+1/2,-y+1/2
21 -z+1/2,-y+1/2,-x+1/2
22 -z+1/2,y+1/2,x+1/2
23 z+1/2,-y+1/2,x+1/2
24 z+1/2,y+1/2,-x+1/2
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y+1/2,x+1/2,z+1/2
38 y+1/2,-x+1/2,-z+1/2
39 -y+1/2,x+1/2,-z+1/2
40 -y+1/2,-x+1/2,z+1/2
41 x+1/2,z+1/2,y+1/2
42 x+1/2,-z+1/2,-y+1/2
43 -x+1/2,z+1/2,-y+1/2
44 -x+1/2,-z+1/2,y+1/2
45 z+1/2,y+1/2,x+1/2
46 z+1/2,-y+1/2,-x+1/2
47 -z+1/2,y+1/2,-x+1/2
48 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   6 d 0.25000 0.50000 0.00000 1.00000
Si2 Si  16 i 0.18370 0.18370 0.18370 1.00000
Si3 Si  24 k 0.00000 0.11720 0.30770 1.00000
```

Si_{46} Clathrate: A_cP46_223_dik - POSCAR

```
A_cP46_223_dik & a,x2,y3,z3 --params=10.355,0.1837,0.1172,0.3077 & Pm(-3
    ↪ )n   O_h^3 #223 (dik) & cP46 & & Si & clathrate & G. B. Adams,
    ↪ M. O'Keefe, A. A. Demkov, O. F. Sankey and Y.-M. Huang, Phys.
    ↪ Rev. B 49, 8048-8053 (1994)
   1.0000000000000000
  10.35500000000000    0.00000000000000    0.00000000000000
   0.00000000000000   10.35500000000000    0.00000000000000
   0.00000000000000    0.00000000000000   10.35500000000000
   Si
   46
Direct
   0.18370000000000    0.18370000000000    0.18370000000000    Si    (16i)
   0.18370000000000    0.18370000000000    0.81630000000000    Si    (16i)
   0.18370000000000    0.81630000000000    0.18370000000000    Si    (16i)
   0.18370000000000    0.81630000000000    0.81630000000000    Si    (16i)
   0.31630000000000    0.31630000000000    0.31630000000000    Si    (16i)
   0.31630000000000    0.31630000000000    0.68370000000000    Si    (16i)
   0.31630000000000    0.68370000000000    0.31630000000000    Si    (16i)
   0.31630000000000    0.68370000000000    0.68370000000000    Si    (16i)
   0.68370000000000    0.31630000000000    0.31630000000000    Si    (16i)
   0.68370000000000    0.31630000000000    0.68370000000000    Si    (16i)
   0.68370000000000    0.68370000000000    0.31630000000000    Si    (16i)
   0.68370000000000    0.68370000000000    0.68370000000000    Si    (16i)
   0.81630000000000    0.18370000000000    0.18370000000000    Si    (16i)
   0.81630000000000    0.18370000000000    0.81630000000000    Si    (16i)
   0.81630000000000    0.81630000000000    0.18370000000000    Si    (16i)
   0.81630000000000    0.81630000000000    0.81630000000000    Si    (16i)
   0.00000000000000    0.11720000000000    0.30770000000000    Si    (24k)
   0.00000000000000    0.11720000000000    0.69230000000000    Si    (24k)
   0.00000000000000    0.88280000000000    0.30770000000000    Si    (24k)
   0.00000000000000    0.88280000000000    0.69230000000000    Si    (24k)
   0.11720000000000    0.30770000000000    0.00000000000000    Si    (24k)
   0.11720000000000    0.69230000000000    0.00000000000000    Si    (24k)
   0.19230000000000    0.38280000000000    0.50000000000000    Si    (24k)
   0.19230000000000    0.61720000000000    0.50000000000000    Si    (24k)
   0.30770000000000    0.00000000000000    0.11720000000000    Si    (24k)
   0.30770000000000    0.00000000000000    0.88280000000000    Si    (24k)
   0.38280000000000    0.50000000000000    0.19230000000000    Si    (24k)
   0.38280000000000    0.50000000000000    0.80770000000000    Si    (24k)
   0.50000000000000    0.19230000000000    0.38280000000000    Si    (24k)
   0.50000000000000    0.19230000000000    0.61720000000000    Si    (24k)
   0.50000000000000    0.80770000000000    0.38280000000000    Si    (24k)
   0.50000000000000    0.80770000000000    0.61720000000000    Si    (24k)
   0.61720000000000    0.50000000000000    0.19230000000000    Si    (24k)
   0.61720000000000    0.50000000000000    0.80770000000000    Si    (24k)
   0.69230000000000    0.00000000000000    0.11720000000000    Si    (24k)
   0.69230000000000    0.00000000000000    0.88280000000000    Si    (24k)
   0.80770000000000    0.38280000000000    0.50000000000000    Si    (24k)
   0.80770000000000    0.61720000000000    0.50000000000000    Si    (24k)
   0.88280000000000    0.30770000000000    0.00000000000000    Si    (24k)
   0.88280000000000    0.69230000000000    0.00000000000000    Si    (24k)
   0.00000000000000    0.25000000000000    0.50000000000000    Si     (6d)
   0.00000000000000    0.75000000000000    0.50000000000000    Si     (6d)
   0.25000000000000    0.50000000000000    0.00000000000000    Si     (6d)
   0.50000000000000    0.00000000000000    0.25000000000000    Si     (6d)
   0.50000000000000    0.00000000000000    0.75000000000000    Si     (6d)
   0.75000000000000    0.50000000000000    0.00000000000000    Si     (6d)
```

Cuprite (Cu_2O, C3): A2B_cP6_224_b_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Cuprite'
_chemical_formula_sum 'Cu2 O'

loop_
_publ_author_name
 'R. Restori'
 'D. Schwarzenbach'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 42
_journal_year 1986
_journal_page_first 201
_journal_page_last 208
_publ_Section_title
;
 Charge Density in Cuprite, Cu$_2$O
;

# Found in  A. Kirfel and K. Eichhorn, Acta Cryst. A 46, pp. 271-284 (
    ↪ 1990)

_aflow_proto 'A2B_cP6_224_b_a'
_aflow_params 'a'
_aflow_params_values '4.267'
_aflow_Strukturbericht 'C3'
_aflow_Pearson 'cP6'

_symmetry_space_group_name_Hall "-P 4bc 2bc 3 Pn(-3)m"
_symmetry_space_group_name_H-M "P n -3 m:2"
_symmetry_Int_Tables_number 224

_cell_length_a     4.26700
_cell_length_b     4.26700
_cell_length_c     4.26700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/2,-z+1/2
3 -x+1/2,y,-z+1/2
4 -x+1/2,-y+1/2,z
5 y,z,x
6 y,-z+1/2,-x+1/2
7 -y+1/2,z,-x+1/2
8 -y+1/2,-z+1/2,x
9 z,x,y
10 z,-x+1/2,-y+1/2
11 -z+1/2,x,-y+1/2
12 -z+1/2,-x+1/2,y
13 -y,-x,-z
14 -y,x+1/2,z+1/2
15 y+1/2,-x,z+1/2
16 y+1/2,x+1/2,-z
17 -x,-z,-y
18 -x,z+1/2,y+1/2
19 x+1/2,-z,y+1/2
20 x+1/2,z+1/2,-y
21 -z,-y,-x
22 -z,y+1/2,x+1/2
23 z+1/2,-y,x+1/2
24 z+1/2,y+1/2,-x
25 -x,-y,-z
26 -x,y+1/2,z+1/2
27 x+1/2,-y,z+1/2
28 x+1/2,y+1/2,-z
29 -y,-z,-x
30 -y,z+1/2,x+1/2
31 y+1/2,-z,x+1/2
32 y+1/2,z+1/2,-x
33 -z,-x,-y
34 -z,x+1/2,y+1/2
35 z+1/2,-x,y+1/2
36 z+1/2,x+1/2,-y
37 y,x,z
38 y,-x+1/2,-z+1/2
39 -y+1/2,x,-z+1/2
40 -y+1/2,-x+1/2,z
41 x,z,y
42 x,-z+1/2,-y+1/2
43 -x+1/2,z,-y+1/2
44 -x+1/2,-z+1/2,y
45 z,y,x
46 z,-y+1/2,-x+1/2
47 -z+1/2,y,-x+1/2
48 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
O1  O    2 a 0.25000 0.25000 0.25000 1.00000
Cu1 Cu   4 b 0.00000 0.00000 0.00000 1.00000
```

Cuprite (Cu_2O, C3): A2B_cP6_224_b_a - POSCAR

```
A2B_cP6_224_b_a & a --params=4.267 & Pn(-3)m   O_h^4 #224 (ab) & cP6 &
    ↪ C3 & Cu2O & Cuprite & R. Restori and D. Schwarzenbach, Acta
    ↪ Crystallogr. B 42, 201-208 (1986)
   1.0000000000000000
   4.26700000000000    0.00000000000000    0.00000000000000
   0.00000000000000    4.26700000000000    0.00000000000000
   0.00000000000000    0.00000000000000    4.26700000000000
   Cu    O
    4    2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cu    (4b)
   0.00000000000000    0.50000000000000    0.50000000000000    Cu    (4b)
   0.50000000000000    0.00000000000000    0.50000000000000    Cu    (4b)
   0.50000000000000    0.50000000000000    0.00000000000000    Cu    (4b)
   0.25000000000000    0.25000000000000    0.25000000000000     O    (2a)
   0.75000000000000    0.75000000000000    0.75000000000000     O    (2a)
```

Ca_7Ge: A7B_cF32_225_bd_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ca7 Ge'

loop_
_publ_author_name
 'O. Helleis'
 'H. Kandler'
 'E. Leicht'
 'W. Quiring'
 'E. W\"{o}lfel'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische und allgemeine Chemie
;
_journal_volume 320
_journal_year 1963
_journal_page_first 86
_journal_page_last 100
_publ_Section_title
;
 Die Kristallstrukturen der intermetallischen Phasen Ca$_{33}$Ge,
    ↪ Ca$_7$Ge, Ca$_3$Pb und Ca$_5$Pb$_3$
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_1301069

_aflow_proto 'A7B_cF32_225_bd_a'
_aflow_params 'a'
_aflow_params_values '9.45'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cF32'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a     9.45000
_cell_length_b     9.45000
_cell_length_c     9.45000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
```

```
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z,y+1/2
115 x+1/2,-z,y+1/2
116 x+1/2,z,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y,x+1/2
119 z+1/2,-y,x+1/2
120 z+1/2,y,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y,z+1/2
123 x+1/2,-y,z+1/2
124 x+1/2,y,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z,x+1/2
127 y+1/2,-z,x+1/2
128 y+1/2,z,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x,y+1/2
131 z+1/2,-x,y+1/2
132 z+1/2,x,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x,-z+1/2
135 -y+1/2,x,-z+1/2
136 -y+1/2,-x,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z,-y+1/2
139 -x+1/2,z,-y+1/2
140 -x+1/2,-z,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y,-x+1/2
143 -z+1/2,y,-x+1/2
144 -z+1/2,-y,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+1/2,-z
147 -x+1/2,y+1/2,-z
148 -x+1/2,-y+1/2,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+1/2,-x
151 -y+1/2,z+1/2,-x
152 -y+1/2,-z+1/2,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+1/2,-y
155 -z+1/2,x+1/2,-y
156 -z+1/2,-x+1/2,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+1/2,z
159 y+1/2,-x+1/2,z
160 y+1/2,x+1/2,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+1/2,y
163 x+1/2,-z+1/2,y
164 x+1/2,z+1/2,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+1/2,x
167 z+1/2,-y+1/2,x
168 z+1/2,y+1/2,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+1/2,z
171 x+1/2,-y+1/2,z
172 x+1/2,y+1/2,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+1/2,x
175 y+1/2,-z+1/2,x
176 y+1/2,z+1/2,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+1/2,y
179 z+1/2,-x+1/2,y
180 z+1/2,x+1/2,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+1/2,-z
183 -y+1/2,x+1/2,-z
184 -y+1/2,-x+1/2,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+1/2,-y
187 -x+1/2,z+1/2,-y
188 -x+1/2,-z+1/2,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+1/2,-x
191 -z+1/2,y+1/2,-x
192 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ge1 Ge   4 a 0.00000 0.00000 0.00000 1.00000
Ca1 Ca   4 b 0.50000 0.50000 0.50000 1.00000
Ca2 Ca  24 d 0.00000 0.25000 0.25000 1.00000
```

Ca_7Ge: A7B_cF32_225_bd_a - POSCAR

```
A7B_cF32_225_bd_a & a --params=9.45 & Fm(-3)m   O_h^5 #225 (abd) & cF32
    ↪ & & Ca7Ge & & O. Helleis, H. Kandler, E. Leicht, W. Quiring and
    ↪ E. Wolfel, ZAAC 320, 86-100 (1963)
   1.0000000000000000
   0.00000000000000    4.72500000000000    4.72500000000000
   4.72500000000000    0.00000000000000    4.72500000000000
   4.72500000000000    4.72500000000000    0.00000000000000
   Ca    Ge
    7     1
Direct
   0.00000000000000    0.00000000000000    0.50000000000000    Ca    (24d)
   0.00000000000000    0.50000000000000    0.00000000000000    Ca    (24d)
   0.00000000000000    0.50000000000000    0.50000000000000    Ca    (24d)
   0.50000000000000    0.00000000000000    0.00000000000000    Ca    (24d)
   0.50000000000000    0.00000000000000    0.50000000000000    Ca    (24d)
   0.50000000000000    0.50000000000000    0.00000000000000    Ca    (24d)
   0.50000000000000    0.50000000000000    0.50000000000000    Ca     (4b)
   0.00000000000000    0.00000000000000    0.00000000000000    Ge     (4a)
```

BiF_3 ($D0_3$): AB3_cF16_225_a_bc - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'alpha bismuth trifluoride'
_chemical_formula_sum 'Bi F3'

loop_
```

```
_publ_author_name
 'F. Hund'
 'R. Fricke'
_journal_name_full
;
Zeitschrift f\"{u}r anorganische Chemie
;
_journal_volume 258
_journal_year 1949
_journal_page_first 198
_journal_page_last 204
_publ_Section_title
;
 Der Kristallbau von $\alpha$-BiF$_3$
;

# Found in  Pearson's Handbook, Vol. II, pp. 1774

_aflow_proto 'AB3_cF16_225_a_bc'
_aflow_params 'a'
_aflow_params_values '5.853'
_aflow_Strukturbericht 'D0_3'
_aflow_Pearson 'cF16'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a      5.85300
_cell_length_b      5.85300
_cell_length_c      5.85300
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z,y+1/2
115 x+1/2,-z,y+1/2
116 x+1/2,z,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y,x+1/2
119 z+1/2,-y,x+1/2
120 z+1/2,y,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y,z+1/2
123 x+1/2,-y,z+1/2
124 x+1/2,y,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z,x+1/2
127 y+1/2,-z,x+1/2
128 y+1/2,z,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x,y+1/2
131 z+1/2,-x,y+1/2
132 z+1/2,x,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x,-z+1/2
135 -y+1/2,x,-z+1/2
136 -y+1/2,-x,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z,-y+1/2
139 -x+1/2,z,-y+1/2
140 -x+1/2,-z,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y,-x+1/2
143 -z+1/2,y,-x+1/2
144 -z+1/2,-y,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+1/2,-z
147 -x+1/2,y+1/2,-z
148 -x+1/2,-y+1/2,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+1/2,-x
151 -y+1/2,z+1/2,-x
152 -y+1/2,-z+1/2,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+1/2,-y
155 -z+1/2,x+1/2,-y
156 -z+1/2,-x+1/2,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+1/2,z
159 y+1/2,-x+1/2,z
160 y+1/2,x+1/2,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+1/2,y
163 x+1/2,-z+1/2,y
164 x+1/2,z+1/2,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+1/2,x
167 z+1/2,-y+1/2,x
168 z+1/2,y+1/2,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+1/2,z
171 x+1/2,-y+1/2,z
172 x+1/2,y+1/2,-z
```

```
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+1/2,x
175 y+1/2,-z+1/2,x
176 y+1/2,z+1/2,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+1/2,y
179 z+1/2,-x+1/2,y
180 z+1/2,x+1/2,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+1/2,-z
183 -y+1/2,x+1/2,-z
184 -y+1/2,-x+1/2,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+1/2,-y
187 -x+1/2,z+1/2,-y
188 -x+1/2,-z+1/2,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+1/2,-x
191 -z+1/2,y+1/2,-x
192 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Bi1 Bi    4 a 0.00000 0.00000 0.00000 1.00000
F1  F     4 b 0.50000 0.50000 0.50000 1.00000
F2  F     8 c 0.25000 0.25000 0.25000 1.00000
```

BiF_3 ($D0_3$): AB3_cF16_225_a_bc - POSCAR

```
AB3_cF16_225_a_bc & a --params=5.853 & Fm(-3)m    O_h^5 #225 (abc) & cF16
    ↪ & D0_3 & BiF3 & alpha & F. Hund and R. Fricke, ZAAC 258,
    ↪ 198-204 (1949)
   1.0000000000000000
   0.00000000000000    2.92650000000000    2.92650000000000
   2.92650000000000    0.00000000000000    2.92650000000000
   2.92650000000000    2.92650000000000    0.00000000000000
   Bi    F
    1    3
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Bi    (4a)
   0.50000000000000    0.50000000000000    0.50000000000000    F     (4b)
   0.25000000000000    0.25000000000000    0.25000000000000    F     (8c)
   0.75000000000000    0.75000000000000    0.75000000000000    F     (8c)
```

Model of Ferrite (cF128): A9B16C7_cF128_225_acd_2f_be - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr9 Fe16 Ni7'

loop_
_publ_author_name
 'Michael J. Mehl'
_journal_name_full
;
None
;
_journal_volume 0
_journal_year 2008
_journal_page_first 0
_journal_page_last 0
_publ_Section_title
;
 Hypothetical cF128 Austenite Structure
;

_aflow_proto 'A9B16C7_cF128_225_acd_2f_be'
_aflow_params 'a,x5,x6,x7'
_aflow_params_values '11.48,0.25,0.875,0.625'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cF128'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a      11.48000
_cell_length_b      11.48000
_cell_length_c      11.48000
_cell_angle_alpha   90.00000
_cell_angle_beta    90.00000
_cell_angle_gamma   90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
```

```
-x+1/2,z,y+1/2
x+1/2,-z,y+1/2
x+1/2,z,-y+1/2
-z+1/2,-y,-x+1/2
-z+1/2,y,x+1/2
z+1/2,-y,x+1/2
z+1/2,y,-x+1/2
-x+1/2,-y,-z+1/2
-x+1/2,y,z+1/2
x+1/2,-y,z+1/2
x+1/2,y,-z+1/2
-y+1/2,-z,-x+1/2
-y+1/2,z,x+1/2
y+1/2,-z,x+1/2
y+1/2,z,-x+1/2
-z+1/2,-x,-y+1/2
-z+1/2,x,y+1/2
z+1/2,-x,y+1/2
z+1/2,x,-y+1/2
y+1/2,x,z+1/2
y+1/2,-x,-z+1/2
-y+1/2,x,-z+1/2
-y+1/2,-x,z+1/2
x+1/2,z,y+1/2
x+1/2,-z,-y+1/2
-x+1/2,z,-y+1/2
-x+1/2,-z,y+1/2
z+1/2,y,x+1/2
z+1/2,-y,-x+1/2
-z+1/2,y,-x+1/2
-z+1/2,-y,x+1/2
x+1/2,y+1/2,z
x+1/2,-y+1/2,-z
-x+1/2,y+1/2,-z
-x+1/2,-y+1/2,z
y+1/2,z+1/2,x
y+1/2,-z+1/2,-x
-y+1/2,z+1/2,-x
-y+1/2,-z+1/2,x
z+1/2,x+1/2,y
z+1/2,-x+1/2,-y
-z+1/2,x+1/2,-y
-z+1/2,-x+1/2,y
-y+1/2,-x+1/2,-z
-y+1/2,x+1/2,z
y+1/2,-x+1/2,z
y+1/2,x+1/2,-z
-x+1/2,-z+1/2,-y
-x+1/2,z+1/2,y
x+1/2,-z+1/2,y
x+1/2,z+1/2,-y
-z+1/2,-y+1/2,-x
-z+1/2,y+1/2,x
z+1/2,-y+1/2,x
z+1/2,y+1/2,-x
-x+1/2,-y+1/2,-z
-x+1/2,y+1/2,z
x+1/2,-y+1/2,z
x+1/2,y+1/2,-z
-y+1/2,-z+1/2,-x
-y+1/2,z+1/2,x
y+1/2,-z+1/2,x
y+1/2,z+1/2,-x
-z+1/2,-x+1/2,-y
-z+1/2,x+1/2,y
z+1/2,-x+1/2,y
z+1/2,x+1/2,-y
y+1/2,x+1/2,z
y+1/2,-x+1/2,-z
-y+1/2,x+1/2,-z
-y+1/2,-x+1/2,z
x+1/2,z+1/2,y
x+1/2,-z+1/2,-y
-x+1/2,z+1/2,-y
-x+1/2,-z+1/2,y
z+1/2,y+1/2,x
z+1/2,-y+1/2,-x
-z+1/2,y+1/2,-x
-z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1 Cr   4 a 0.00000 0.00000 0.00000 1.00000
Ni1 Ni   4 b 0.50000 0.50000 0.50000 1.00000
Cr2 Cr   8 c 0.25000 0.25000 0.25000 1.00000
Cr3 Cr  24 d 0.00000 0.25000 0.25000 1.00000
Ni2 Ni  24 e 0.25000 0.00000 0.00000 1.00000
Fe1 Fe  32 f 0.87500 0.87500 0.87500 1.00000
Fe2 Fe  32 f 0.62500 0.62500 0.62500 1.00000
```

Model of Ferrite (cF128): A9B16C7_cF128_225_acd_2f_be - POSCAR

```
A9B16C7_cF128_225_acd_2f_be & a,x5,x6,x7 --params=11.48,0.25,0.875,0.625
    ↪ & Fm(-3)m   O_h^5 #225 (abcdef^2) & cF128 && Cr9Fe16Ni7 &
    ↪ Hypothetical Ferrite &
   1.0000000000000000
   0.00000000000000   5.74000000000000   5.74000000000000
   5.74000000000000   0.00000000000000   5.74000000000000
   5.74000000000000   5.74000000000000   0.00000000000000
   Cr   Fe   Ni
    9   16    7
Direct
   0.00000000000000   0.00000000000000   0.50000000000000   Cr   (24d)
   0.00000000000000   0.50000000000000   0.00000000000000   Cr   (24d)
   0.00000000000000   0.50000000000000   0.50000000000000   Cr   (24d)
   0.50000000000000   0.00000000000000   0.00000000000000   Cr   (24d)
   0.50000000000000   0.00000000000000   0.50000000000000   Cr   (24d)
   0.50000000000000   0.50000000000000   0.00000000000000   Cr   (24d)
   0.00000000000000   0.00000000000000   0.00000000000000   Cr    (4a)
   0.25000000000000   0.25000000000000   0.25000000000000   Cr    (8c)
   0.75000000000000   0.75000000000000   0.75000000000000   Cr    (8c)
   0.12500000000000   0.12500000000000   0.12500000000000   Fe   (32f)
   0.12500000000000   0.12500000000000   0.62500000000000   Fe   (32f)
   0.12500000000000   0.62500000000000   0.12500000000000   Fe   (32f)
   0.37500000000000   0.87500000000000   0.87500000000000   Fe   (32f)
   0.62500000000000   0.12500000000000   0.12500000000000   Fe   (32f)
   0.87500000000000   0.37500000000000   0.87500000000000   Fe   (32f)
   0.87500000000000   0.87500000000000   0.37500000000000   Fe   (32f)
   0.87500000000000   0.87500000000000   0.87500000000000   Fe   (32f)
  -0.12500000000000   0.37500000000000   0.37500000000000   Fe   (32f)
   0.12500000000000   0.62500000000000   0.62500000000000   Fe   (32f)
   0.37500000000000  -0.12500000000000   0.37500000000000   Fe   (32f)
   0.37500000000000   0.37500000000000  -0.12500000000000   Fe   (32f)
   0.37500000000000   0.37500000000000   0.37500000000000   Fe   (32f)
   0.62500000000000   0.12500000000000   0.62500000000000   Fe   (32f)
   0.62500000000000   0.62500000000000   0.12500000000000   Fe   (32f)
   0.62500000000000   0.62500000000000   0.62500000000000   Fe   (32f)
   0.25000000000000   0.25000000000000   0.75000000000000   Ni   (24e)
   0.25000000000000   0.75000000000000   0.25000000000000   Ni   (24e)
   0.25000000000000   0.75000000000000   0.75000000000000   Ni   (24e)
   0.75000000000000   0.25000000000000   0.25000000000000   Ni   (24e)
   0.75000000000000   0.25000000000000   0.75000000000000   Ni   (24e)
   0.75000000000000   0.75000000000000   0.25000000000000   Ni   (24e)
   0.50000000000000   0.50000000000000   0.50000000000000   Ni    (4b)
```

UB_{12}: A12B_cF52_225_i_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'U B12'

loop_
_publ_author_name
 'Pierre Blum'
 'F\'{e}lix Bertaut'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 7
_journal_year 1954
_journal_page_first 81
_journal_page_last 86
_publ_Section_title
;
 Contribution \'{a} l'\'{E}tude des Borures \'{a} Teneur \'{E}lev\'{e}e
    ↪ en Bore
;

# Found in  Pearson, Alloys, pp. 757-759

_aflow_proto 'A12B_cF52_225_i_a'
_aflow_params 'a,y2'
_aflow_params_values '7.468,0.666'
_aflow_Strukturbericht 'D2_f'
_aflow_Pearson 'cF52'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a    7.46800
_cell_length_b    7.46800
_cell_length_c    7.46800
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
```

```
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z,y+1/2
115 x+1/2,-z,y+1/2
116 x+1/2,z,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y,x+1/2
119 z+1/2,-y,x+1/2
120 z+1/2,y,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y,z+1/2
123 x+1/2,-y,z+1/2
124 x+1/2,y,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z,x+1/2
127 y+1/2,-z,x+1/2
128 y+1/2,z,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x,y+1/2
131 z+1/2,-x,y+1/2
132 z+1/2,x,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x,-z+1/2
135 -y+1/2,x,-z+1/2
136 -y+1/2,-x,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z,-y+1/2
139 -x+1/2,z,-y+1/2
140 -x+1/2,-z,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y,-x+1/2
143 -z+1/2,y,-x+1/2
144 -z+1/2,-y,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+1/2,-z
147 -x+1/2,y+1/2,-z
148 -x+1/2,-y+1/2,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+1/2,-x
151 -y+1/2,z+1/2,-x
152 -y+1/2,-z+1/2,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+1/2,-y
155 -z+1/2,x+1/2,-y
156 -z+1/2,-x+1/2,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+1/2,z
159 y+1/2,-x+1/2,z
160 y+1/2,x+1/2,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+1/2,y
163 x+1/2,-z+1/2,y
164 x+1/2,z+1/2,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+1/2,x
167 z+1/2,-y+1/2,x
168 z+1/2,y+1/2,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+1/2,z
171 x+1/2,-y+1/2,z
172 x+1/2,y+1/2,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+1/2,x
175 y+1/2,-z+1/2,x
176 y+1/2,z+1/2,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+1/2,y
179 z+1/2,-x+1/2,y
180 z+1/2,x+1/2,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+1/2,-z
183 -y+1/2,x+1/2,-z
184 -y+1/2,-x+1/2,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+1/2,-y
187 -x+1/2,z+1/2,-y
188 -x+1/2,-z+1/2,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+1/2,-x
191 -z+1/2,y+1/2,-x
192 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
U1 U   4 a 0.00000 0.00000 0.00000 1.00000
B1 B  48 i 0.50000 0.66600 0.66600 1.00000
```

UB_{12}: A12B_cF52_225_i_a - POSCAR

```
A12B_cF52_225_i_a & a,y2 --params=7.468,0.666 & Fm(-3)m  O_h^5 #225 (ai
    ↪ ) & cF52 & D2_f & UB12 & & P. Blum and F. Bertaut, Acta Cryst.
    ↪ 7, 81-86 (1954)
   1.0000000000000000
   0.00000000000000   3.73400000000000   3.73400000000000
   3.73400000000000   0.00000000000000   3.73400000000000
   3.73400000000000   3.73400000000000   0.00000000000000
    B    U
   12    1
Direct
   0.16800000000000   0.50000000000000   0.50000000000000   B   (48i)
   0.16800000000000   0.50000000000000   0.83200000000000   B   (48i)
   0.16800000000000   0.83200000000000   0.50000000000000   B   (48i)
   0.50000000000000   0.16800000000000   0.50000000000000   B   (48i)
   0.50000000000000   0.16800000000000   0.83200000000000   B   (48i)
   0.50000000000000   0.50000000000000   0.16800000000000   B   (48i)
   0.50000000000000   0.50000000000000   0.83200000000000   B   (48i)
   0.50000000000000   0.83200000000000   0.16800000000000   B   (48i)
   0.50000000000000   0.83200000000000   0.50000000000000   B   (48i)
   0.83200000000000   0.16800000000000   0.50000000000000   B   (48i)
   0.83200000000000   0.50000000000000   0.16800000000000   B   (48i)
```

```
    0.83200000000000    0.50000000000000    0.50000000000000    B    (48i)
    0.00000000000000    0.00000000000000    0.00000000000000    U     (4a)
```

Fluorite (CaF_2, C1): AB2_cF12_225_a_c - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Fluorite'
_chemical_formula_sum 'Ca F2'

loop_
_publ_author_name
 'S. Speziale'
 'T. S. Duffy'
_journal_name_full
;
Physics and Chemistry of Minerals
;
_journal_volume 29
_journal_year 2002
_journal_page_first 465
_journal_page_last 472
_publ_Section_title
;
 Single-crystal elastic constants of fluorite (CaF$_2$) to 9.3 GPa
;

# Found in  AMS Database

_aflow_proto 'AB2_cF12_225_a_c'
_aflow_params 'a'
_aflow_params_values '5.4631'
_aflow_Strukturbericht 'C1'
_aflow_Pearson 'cF12'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a      5.46310
_cell_length_b      5.46310
_cell_length_c      5.46310
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z,y+1/2
115 x+1/2,-z,y+1/2
116 x+1/2,z,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y,x+1/2
119 z+1/2,-y,x+1/2
120 z+1/2,y,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y,z+1/2
123 x+1/2,-y,z+1/2
124 x+1/2,y,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z,x+1/2
127 y+1/2,-z,x+1/2
128 y+1/2,z,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x,y+1/2
131 z+1/2,-x,y+1/2
132 z+1/2,x,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x,-z+1/2
135 -y+1/2,x,-z+1/2
136 -y+1/2,-x,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z,-y+1/2
139 -x+1/2,z,-y+1/2
140 -x+1/2,-z,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y,-x+1/2
143 -z+1/2,y,-x+1/2
144 -z+1/2,-y,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+1/2,-z
147 -x+1/2,y+1/2,-z
148 -x+1/2,-y+1/2,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+1/2,-x
151 -y+1/2,z+1/2,-x
152 -y+1/2,-z+1/2,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+1/2,-y
155 -z+1/2,x+1/2,-y
156 -z+1/2,-x+1/2,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+1/2,z
```

```
159 y+1/2,-x+1/2,z
160 y+1/2,x+1/2,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+1/2,y
163 x+1/2,-z+1/2,y
164 x+1/2,z+1/2,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+1/2,x
167 z+1/2,-y+1/2,x
168 z+1/2,y+1/2,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+1/2,z
171 x+1/2,-y+1/2,z
172 x+1/2,y+1/2,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+1/2,x
175 y+1/2,-z+1/2,x
176 y+1/2,z+1/2,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+1/2,y
179 z+1/2,-x+1/2,y
180 z+1/2,x+1/2,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+1/2,-z
183 -y+1/2,x+1/2,-z
184 -y+1/2,-x+1/2,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+1/2,-y
187 -x+1/2,z+1/2,-y
188 -x+1/2,-z+1/2,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+1/2,-x
191 -z+1/2,y+1/2,-x
192 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ca1 Ca    4 a 0.00000 0.00000 0.00000 1.00000
F1  F     8 c 0.25000 0.25000 0.25000 1.00000
```

Fluorite (CaF_2, C1): AB2_cF12_225_a_c - POSCAR

```
AB2_cF12_225_a_c & a --params=5.4631 & Fm(-3)m    O_h^5 #225 (ac) & cF12
    ↪ & C1 & CaF2 & Fluorite & S. Speziale and T. S. Duffy, Phys.
    ↪ Chem. Minerals 29, 465-472 (2002)
   1.0000000000000000
   0.00000000000000    2.73155000000000    2.73155000000000
   2.73155000000000    0.00000000000000    2.73155000000000
   2.73155000000000    2.73155000000000    0.00000000000000
   Ca    F
    1    2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Ca    (4a)
   0.25000000000000    0.25000000000000    0.25000000000000    F     (8c)
   0.75000000000000    0.75000000000000    0.75000000000000    F     (8c)
```

$Cr_{23}C_6$ ($D8_4$): A6B23_cF116_225_e_acfh - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr23 C6'

loop_
_publ_author_name
 'A. L. Bowman'
 'G. P. Arnold'
 'E. K. Storms'
 'N. G. Nereson'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 28
_journal_year 1972
_journal_page_first 3102
_journal_page_last 3103
_publ_Section_title
;
 The crystal structure of Cr$_{23}$C$_6$
;

_aflow_proto 'A6B23_cF116_225_e_acfh'
_aflow_params 'a,x3,x4,y5'
_aflow_params_values '10.65,0.2765,0.6191,0.6699'
_aflow_Strukturbericht 'D8_4'
_aflow_Pearson 'cF116'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a      10.65000
_cell_length_b      10.65000
_cell_length_c      10.65000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
```

```
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z,y+1/2
115 x+1/2,-z,y+1/2
116 x+1/2,z,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y,x+1/2
119 z+1/2,-y,x+1/2
120 z+1/2,y,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y,z+1/2
123 x+1/2,-y,z+1/2
124 x+1/2,y,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z,x+1/2
127 y+1/2,-z,x+1/2
128 y+1/2,z,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x,y+1/2
131 z+1/2,-x,y+1/2
132 z+1/2,x,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x,-z+1/2
135 -y+1/2,x,-z+1/2
136 -y+1/2,-x,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z,-y+1/2
139 -x+1/2,z,-y+1/2
140 -x+1/2,-z,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y,-x+1/2
143 -z+1/2,y,-x+1/2
144 -z+1/2,-y,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+1/2,-z
147 -x+1/2,y+1/2,-z
148 -x+1/2,-y+1/2,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+1/2,-x
151 -y+1/2,z+1/2,-x
152 -y+1/2,-z+1/2,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+1/2,-y
155 -z+1/2,x+1/2,-y
156 -z+1/2,-x+1/2,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+1/2,z
159 y+1/2,-x+1/2,z
160 y+1/2,x+1/2,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+1/2,y
163 x+1/2,-z+1/2,y
164 x+1/2,z+1/2,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+1/2,x
167 z+1/2,-y+1/2,x
168 z+1/2,y+1/2,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+1/2,z
171 x+1/2,-y+1/2,z
172 x+1/2,y+1/2,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+1/2,x
175 y+1/2,-z+1/2,x
176 y+1/2,z+1/2,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+1/2,y
179 z+1/2,-x+1/2,y
180 z+1/2,x+1/2,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+1/2,-z
183 -y+1/2,x+1/2,-z
184 -y+1/2,-x+1/2,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+1/2,-y
187 -x+1/2,z+1/2,-y
188 -x+1/2,-z+1/2,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+1/2,-x
191 -z+1/2,y+1/2,-x
192 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1 Cr    4 a 0.00000 0.00000 0.00000 1.00000
Cr2 Cr    8 c 0.25000 0.25000 0.25000 1.00000
C1  C    24 e 0.27650 0.00000 0.00000 1.00000
Cr3 Cr   32 f 0.61910 0.61910 0.61910 1.00000
Cr4 Cr   48 h 0.00000 0.66990 0.66990 1.00000
```

$Cr_{23}C_6$ ($D8_4$): A6B23_cF116_225_e_acfh - POSCAR

```
A6B23_cF116_225_e_acfh & a,x3,x4,y5 --params=10.65,0.2765,0.6191,0.6699
    ↪ & Fm(-3)m    O_h^5 #225 (acefh) & cF116 & D8_4 & Cr23C6 & & A.
    ↪ L. Bowman, G. P. Arnold, E. K. Storms and N. G. Nereson, Acta
    ↪ Cryst. B 28, 3102-3103 (1972)
   1.0000000000000000
   0.00000000000000   5.32500000000000   5.32500000000000
   5.32500000000000   0.00000000000000   5.32500000000000
   5.32500000000000   5.32500000000000   0.00000000000000
    C    Cr
    6    23
Direct
   0.27650000000000   0.27650000000000   0.72350000000000    C   (24e)
   0.27650000000000   0.72350000000000   0.27650000000000    C   (24e)
   0.27650000000000   0.72350000000000   0.72350000000000    C   (24e)
   0.72350000000000   0.27650000000000   0.27650000000000    C   (24e)
   0.72350000000000   0.27650000000000   0.72350000000000    C   (24e)
   0.72350000000000   0.72350000000000   0.27650000000000    C   (24e)
  -0.14270000000000   0.38090000000000   0.38090000000000   Cr   (32f)
   0.14270000000000   0.61910000000000   0.61910000000000   Cr   (32f)
   0.38090000000000  -0.14270000000000   0.38090000000000   Cr   (32f)
   0.38090000000000   0.38090000000000  -0.14270000000000   Cr   (32f)
   0.38090000000000   0.38090000000000   0.38090000000000   Cr   (32f)
   0.61910000000000   0.14270000000000   0.61910000000000   Cr   (32f)
   0.61910000000000   0.61910000000000   0.14270000000000   Cr   (32f)
   0.61910000000000   0.61910000000000   0.61910000000000   Cr   (32f)
   0.00000000000000   0.00000000000000   0.33980000000000   Cr   (48h)
   0.00000000000000   0.00000000000000   0.66020000000000   Cr   (48h)
   0.00000000000000   0.33980000000000   0.00000000000000   Cr   (48h)
   0.00000000000000   0.33980000000000   0.66020000000000   Cr   (48h)
   0.00000000000000   0.66020000000000   0.00000000000000   Cr   (48h)
   0.00000000000000   0.66020000000000   0.33980000000000   Cr   (48h)
   0.33980000000000   0.00000000000000   0.00000000000000   Cr   (48h)
   0.33980000000000   0.00000000000000   0.66020000000000   Cr   (48h)
   0.33980000000000   0.66020000000000   0.00000000000000   Cr   (48h)
   0.66020000000000   0.00000000000000   0.00000000000000   Cr   (48h)
   0.66020000000000   0.00000000000000   0.33980000000000   Cr   (48h)
   0.66020000000000   0.33980000000000   0.00000000000000   Cr   (48h)
   0.00000000000000   0.00000000000000   0.00000000000000   Cr    (4a)
   0.25000000000000   0.25000000000000   0.25000000000000   Cr    (8c)
   0.75000000000000   0.75000000000000   0.75000000000000   Cr    (8c)
```

Heusler ($L2_1$): AB2C_cF16_225_a_c_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Heusler'
_chemical_formula_sum 'Al Cu2 Mn'

loop_
_publ_author_name
 'A. J. Bradley'
 'J. W. Rodgers'
_journal_name_full
;
Proceedings of the Royal Society of London, Series A
;
_journal_volume 144
_journal_year 1934
_journal_page_first 340
_journal_page_last 359
_publ_Section_title
;
 The Crystal Structure of Heusler Alloys
;

_aflow_proto 'AB2C_cF16_225_a_c_b'
_aflow_params 'a'
_aflow_params_values '5.95'
_aflow_Strukturbericht 'L2_1'
_aflow_Pearson 'cF16'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a     5.95000
_cell_length_b     5.95000
_cell_length_c     5.95000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
```

```
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z,y+1/2
115 x+1/2,-z,y+1/2
116 x+1/2,z,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y,x+1/2
119 z+1/2,-y,x+1/2
120 z+1/2,y,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y,z+1/2
123 x+1/2,-y,z+1/2
124 x+1/2,y,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z,x+1/2
127 y+1/2,-z,x+1/2
128 y+1/2,z,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x,y+1/2
131 z+1/2,-x,y+1/2
132 z+1/2,x,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x,-z+1/2
135 -y+1/2,x,-z+1/2
136 -y+1/2,-x,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z,-y+1/2
139 -x+1/2,z,-y+1/2
140 -x+1/2,-z,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y,-x+1/2
143 -z+1/2,y,-x+1/2
144 -z+1/2,-y,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+1/2,-z
147 -x+1/2,y+1/2,-z
148 -x+1/2,-y+1/2,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+1/2,-x
151 -y+1/2,z+1/2,-x
152 -y+1/2,-z+1/2,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+1/2,-y
155 -z+1/2,x+1/2,-y
156 -z+1/2,-x+1/2,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+1/2,z
159 y+1/2,-x+1/2,z
160 y+1/2,x+1/2,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+1/2,y
163 x+1/2,-z+1/2,y
164 x+1/2,z+1/2,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+1/2,x
167 z+1/2,-y+1/2,x
168 z+1/2,y+1/2,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+1/2,z
171 x+1/2,-y+1/2,z
172 x+1/2,y+1/2,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+1/2,x
175 y+1/2,-z+1/2,x
176 y+1/2,z+1/2,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+1/2,y
179 z+1/2,-x+1/2,y
180 z+1/2,x+1/2,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+1/2,-z
183 -y+1/2,x+1/2,-z
184 -y+1/2,-x+1/2,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+1/2,-y
187 -x+1/2,z+1/2,-y
188 -x+1/2,-z+1/2,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+1/2,-x
191 -z+1/2,y+1/2,-x
192 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Al1 Al   4 a 0.00000 0.00000 0.00000 1.00000
Mn1 Mn   4 b 0.50000 0.50000 0.50000 1.00000
Cu1 Cu   8 c 0.25000 0.25000 0.25000 1.00000
```

Heusler ($L2_1$): AB2C_cF16_225_a_c_b - POSCAR

```
AB2C_cF16_225_a_c_b & a --params=5.95 & Fm(-3)m   O_h^5 #225 (abc) &
    ↪ cF16 & L2_1 & AlCu2Mn & Heusler & A. J. Bradley and J. W.
    ↪ Rodgers, Proc. Roy. Soc. A 144, 340-359 (1934)
  1.0000000000000000
  0.00000000000000   2.97500000000000   2.97500000000000
  2.97500000000000   0.00000000000000   2.97500000000000
  2.97500000000000   2.97500000000000   0.00000000000000
  Al   Cu   Mn
   1    2    1
Direct
  0.00000000000000   0.00000000000000   0.00000000000000   Al   (4a)
  0.25000000000000   0.25000000000000   0.25000000000000   Cu   (8c)
```

0.75000000000000	0.75000000000000	0.75000000000000	Cu	(8c)
0.50000000000000	0.50000000000000	0.50000000000000	Mn	(4b)

Face-Centered Cubic (Cu, A1): A_cF4_225_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Copper'
_chemical_formula_sum 'Cu'

loop_
_publ_author_name
 'M. E. Straumanis'
 'L. S. Yu'
_journal_name_full
;
Acta Crystallographica A
;
_journal_volume 25
_journal_year 1969
_journal_page_first 676
_journal_page_last 682
_publ_Section_title
;
 Lattice parameters, densities, expansion coefficients and perfection of
      ↪ structure of Cu and of Cu-In $\alpha$ phase
;

_aflow_proto 'A_cF4_225_a'
_aflow_params 'a'
_aflow_params_values '3.61491'
_aflow_Strukturbericht 'A1'
_aflow_Pearson 'cF4'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a      3.61491
_cell_length_b      3.61491
_cell_length_c      3.61491
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z,y+1/2
115 x+1/2,-z,y+1/2
116 x+1/2,z,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y,x+1/2
119 z+1/2,-y,x+1/2
120 z+1/2,y,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y,z+1/2
123 x+1/2,-y,z+1/2
124 x+1/2,y,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z,x+1/2
127 y+1/2,-z,x+1/2
128 y+1/2,z,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x,y+1/2
131 z+1/2,-x,y+1/2
132 z+1/2,x,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x,-z+1/2
135 -y+1/2,x,-z+1/2
136 -y+1/2,-x,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z,-y+1/2
139 -x+1/2,z,-y+1/2
140 -x+1/2,-z,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y,-x+1/2
143 -z+1/2,y,-x+1/2
144 -z+1/2,-y,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+1/2,-z
147 -x+1/2,y+1/2,-z
148 -x+1/2,-y+1/2,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+1/2,-x
151 -y+1/2,z+1/2,-x
152 -y+1/2,-z+1/2,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+1/2,-y
155 -z+1/2,x+1/2,-y
156 -z+1/2,-x+1/2,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+1/2,z
159 y+1/2,-x+1/2,z
```

```
160 y+1/2,x+1/2,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+1/2,y
163 x+1/2,-z+1/2,y
164 x+1/2,z+1/2,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+1/2,x
167 z+1/2,-y+1/2,x
168 z+1/2,y+1/2,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+1/2,z
171 x+1/2,-y+1/2,z
172 x+1/2,y+1/2,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+1/2,x
175 y+1/2,-z+1/2,x
176 y+1/2,z+1/2,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+1/2,y
179 z+1/2,-x+1/2,y
180 z+1/2,x+1/2,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+1/2,-z
183 -y+1/2,x+1/2,-z
184 -y+1/2,-x+1/2,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+1/2,-y
187 -x+1/2,z+1/2,-y
188 -x+1/2,-z+1/2,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+1/2,-x
191 -z+1/2,y+1/2,-x
192 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cu1 Cu  4 a 0.00000 0.00000 0.00000 1.00000
```

Face-Centered Cubic (Cu, A1): A_cF4_225_a - POSCAR

```
A_cF4_225_a & a --params=3.61491 & Fm(-3)m  O_h^5 #225 (a) & cF4 & A1 &
    ↪ Cu & & M. E. Straumanis and L. S. Yu, Acta Cryst. A 25,
    ↪ 676-682 (1969)
  1.0000000000000000
  0.00000000000000  1.80745500000000  1.80745500000000
  1.80745500000000  0.00000000000000  1.80745500000000
  1.80745500000000  1.80745500000000  0.00000000000000
  Cu
   1
Direct
  0.00000000000000  0.00000000000000  0.00000000000000  Cu  (4a)
```

Model of Austenite (cF108): AB18C8_cF108_225_a_eh_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr Fe18 Ni8'

loop_
_publ_author_name
 'Michael J. Mehl'
_journal_name_full
;
None
;
_journal_volume 0
_journal_year 2008
_journal_page_first 0
_journal_page_last 0
_publ_Section_title
;
 Hypothetical cF108 Austenite Structure
;

_aflow_proto 'AB18C8_cF108_225_a_eh_f'
_aflow_params 'a,x2,x3,y4'
_aflow_params_values '10.56,0.325,0.65833,0.66'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cF108'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a    10.56000
_cell_length_b    10.56000
_cell_length_c    10.56000
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
```

```
z+1/2,-x,-y+1/2
-z+1/2,x,-y+1/2
-z+1/2,-x,y+1/2
-y+1/2,-x,-z+1/2
-y+1/2,x,z+1/2
y+1/2,-x,z+1/2
y+1/2,x,-z+1/2
-x+1/2,-z,-y+1/2
-x+1/2,z,y+1/2
x+1/2,-z,y+1/2
x+1/2,z,-y+1/2
-z+1/2,-y,-x+1/2
-z+1/2,y,x+1/2
z+1/2,-y,x+1/2
z+1/2,y,-x+1/2
-x+1/2,-y,-z+1/2
-x+1/2,y,z+1/2
x+1/2,-y,z+1/2
x+1/2,y,-z+1/2
-y+1/2,-z,-x+1/2
-y+1/2,z,x+1/2
y+1/2,-z,x+1/2
y+1/2,z,-x+1/2
-z+1/2,-x,-y+1/2
-z+1/2,x,y+1/2
z+1/2,-x,y+1/2
z+1/2,x,-y+1/2
y+1/2,x,z+1/2
y+1/2,-x,-z+1/2
-y+1/2,x,-z+1/2
-y+1/2,-x,z+1/2
x+1/2,z,y+1/2
x+1/2,-z,-y+1/2
-x+1/2,z,-y+1/2
-x+1/2,-z,y+1/2
z+1/2,y,x+1/2
z+1/2,-y,-x+1/2
-z+1/2,y,-x+1/2
-z+1/2,-y,x+1/2
x+1/2,y+1/2,z
x+1/2,-y+1/2,-z
-x+1/2,y+1/2,-z
-x+1/2,-y+1/2,z
y+1/2,z+1/2,x
y+1/2,-z+1/2,-x
-y+1/2,z+1/2,-x
-y+1/2,-z+1/2,x
z+1/2,x+1/2,y
z+1/2,-x+1/2,-y
-z+1/2,x+1/2,-y
-z+1/2,-x+1/2,y
-y+1/2,-x+1/2,-z
-y+1/2,x+1/2,z
y+1/2,-x+1/2,z
y+1/2,x+1/2,-z
-x+1/2,-z+1/2,-y
-x+1/2,z+1/2,y
x+1/2,-z+1/2,y
x+1/2,z+1/2,-y
-z+1/2,-y+1/2,-x
-z+1/2,y+1/2,x
z+1/2,-y+1/2,x
z+1/2,y+1/2,-x
-x+1/2,-y+1/2,-z
-x+1/2,y+1/2,z
x+1/2,-y+1/2,z
x+1/2,y+1/2,-z
-y+1/2,-z+1/2,-x
-y+1/2,z+1/2,x
y+1/2,-z+1/2,x
y+1/2,z+1/2,-x
-z+1/2,-x+1/2,-y
-z+1/2,x+1/2,y
z+1/2,-x+1/2,y
z+1/2,x+1/2,-y
-y+1/2,-x+1/2,z
y+1/2,-x+1/2,-z
-y+1/2,x+1/2,-z
-y+1/2,-x+1/2,z
x+1/2,z+1/2,y
x+1/2,-z+1/2,-y
-x+1/2,z+1/2,-y
-x+1/2,-z+1/2,y
z+1/2,y+1/2,x
z+1/2,-y+1/2,-x
-z+1/2,y+1/2,-x
-z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1  Cr   4  a  0.00000  0.00000  0.00000  1.00000
Fe1  Fe  24  e  0.32500  0.00000  0.00000  1.00000
Ni1  Ni  32  f  0.65833  0.65833  0.65833  1.00000
Fe2  Fe  48  h  0.00000  0.66000  0.66000  1.00000
```

Model of Austenite (cF108): AB18C8_cF108_225_a_eh_f - POSCAR

```
AB18C8_cF108_225_a_eh_f & a,x2,x3,y4 --params=10.56,0.325,0.65833,0.66 &
    ↪ Fm(-3)m  O_h^5 #225 (aefh) & cF108 & & CrFe18Ni8 & &
    ↪ Hypothetical ordered austenite
  1.0000000000000000
  0.00000000000000   5.28000000000000   5.28000000000000
  5.28000000000000   0.00000000000000   5.28000000000000
  5.28000000000000   5.28000000000000   0.00000000000000
  Cr   Fe   Ni
   1   18    8
Direct
  0.00000000000000   0.00000000000000   0.00000000000000   Cr   (4a)
  0.32500000000000   0.32500000000000   0.67500000000000   Fe   (24e)
  0.32500000000000   0.67500000000000   0.32500000000000   Fe   (24e)
  0.32500000000000   0.67500000000000   0.67500000000000   Fe   (24e)
  0.67500000000000   0.32500000000000   0.32500000000000   Fe   (24e)
  0.67500000000000   0.32500000000000   0.67500000000000   Fe   (24e)
  0.67500000000000   0.67500000000000   0.32500000000000   Fe   (24e)
  0.00000000000000   0.00000000000000   0.32000000000000   Fe   (48h)
  0.00000000000000   0.00000000000000   0.68000000000000   Fe   (48h)
  0.00000000000000   0.32000000000000   0.00000000000000   Fe   (48h)
  0.00000000000000   0.32000000000000   0.68000000000000   Fe   (48h)
  0.00000000000000   0.68000000000000   0.00000000000000   Fe   (48h)
  0.00000000000000   0.68000000000000   0.32000000000000   Fe   (48h)
  0.32000000000000   0.00000000000000   0.00000000000000   Fe   (48h)
  0.32000000000000   0.00000000000000   0.68000000000000   Fe   (48h)
  0.32000000000000   0.68000000000000   0.00000000000000   Fe   (48h)
  0.68000000000000   0.00000000000000   0.00000000000000   Fe   (48h)
  0.68000000000000   0.00000000000000   0.32000000000000   Fe   (48h)
  0.68000000000000   0.32000000000000   0.00000000000000   Fe   (48h)
 -0.02501000000000   0.34167000000000   0.34167000000000   Ni   (32f)
  0.02501000000000   0.65833000000000   0.65833000000000   Ni   (32f)
  0.34167000000000  -0.02501000000000   0.34167000000000   Ni   (32f)
  0.34167000000000   0.34167000000000  -0.02501000000000   Ni   (32f)
  0.34167000000000   0.34167000000000   0.34167000000000   Ni   (32f)
  0.65833000000000   0.02501000000000   0.65833000000000   Ni   (32f)
  0.65833000000000   0.65833000000000   0.02501000000000   Ni   (32f)
  0.65833000000000   0.65833000000000   0.65833000000000   Ni   (32f)
```

Rock Salt (NaCl, B1): AB_cF8_225_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Halite, Rock Salt'
_chemical_formula_sum 'Na Cl'

loop_
_publ_author_name
 'David Walker'
 'Pramod K. Verma'
 'Lachlan M. D. Cranswick'
 'Raymond L. Jones'
 'Simon M. Clark'
 'Stephan Buhre'
_journal_name_full
;
American Mineralogist
;
_journal_volume 89
_journal_year 2004
_journal_page_first 204
_journal_page_last 210
_publ_Section_title
;
 Halite-sylvite thermoelasticity
;

# Found in AMS Database

_aflow_proto 'AB_cF8_225_a_b'
_aflow_params 'a'
_aflow_params_values '5.63931'
_aflow_Strukturbericht 'B1'
_aflow_Pearson 'cF8'

_symmetry_space_group_name_Hall "-F 4 2 3"
_symmetry_space_group_name_H-M "F m -3 m"
_symmetry_Int_Tables_number 225

_cell_length_a     5.63931
_cell_length_b     5.63931
_cell_length_c     5.63931
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
```

```
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x,y+1/2,z+1/2
50 x,-y+1/2,-z+1/2
51 -x,y+1/2,-z+1/2
52 -x,-y+1/2,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+1/2,-x+1/2
55 -y,z+1/2,-x+1/2
56 -y,-z+1/2,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+1/2,-y+1/2
59 -z,x+1/2,-y+1/2
60 -z,-x+1/2,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+1/2,z+1/2
63 y,-x+1/2,z+1/2
64 y,x+1/2,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+1/2,y+1/2
67 x,-z+1/2,y+1/2
68 x,z+1/2,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+1/2,x+1/2
71 z,-y+1/2,x+1/2
72 z,y+1/2,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+1/2,z+1/2
75 x,-y+1/2,z+1/2
76 x,y+1/2,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+1/2,x+1/2
79 y,-z+1/2,x+1/2
80 y,z+1/2,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+1/2,y+1/2
83 z,-x+1/2,y+1/2
84 z,x+1/2,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+1/2,-z+1/2
87 -y,x+1/2,-z+1/2
88 -y,-x+1/2,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+1/2,-y+1/2
91 -x,z+1/2,-y+1/2
92 -x,-z+1/2,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+1/2,-x+1/2
95 -z,y+1/2,-x+1/2
96 -z,-y+1/2,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y,-z+1/2
99 -x+1/2,y,-z+1/2
100 -x+1/2,-y,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z,-x+1/2
103 -y+1/2,z,-x+1/2
104 -y+1/2,-z,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x,-y+1/2
107 -z+1/2,x,-y+1/2
108 -z+1/2,-x,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x,z+1/2
111 y+1/2,-x,z+1/2
112 y+1/2,x,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z,y+1/2
115 x+1/2,-z,y+1/2
116 x+1/2,z,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y,x+1/2
119 z+1/2,-y,x+1/2
120 z+1/2,y,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y,z+1/2
123 x+1/2,-y,z+1/2
124 x+1/2,y,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z,x+1/2
127 y+1/2,-z,x+1/2
128 y+1/2,z,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x,y+1/2
131 z+1/2,-x,y+1/2
132 z+1/2,x,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x,-z+1/2
135 -y+1/2,x,-z+1/2
136 -y+1/2,-x,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z,-y+1/2
139 -x+1/2,z,-y+1/2
140 -x+1/2,-z,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y,-x+1/2
143 -z+1/2,y,-x+1/2
144 -z+1/2,-y,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+1/2,-z
147 -x+1/2,y+1/2,-z
148 -x+1/2,-y+1/2,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+1/2,-x
151 -y+1/2,z+1/2,-x
152 -y+1/2,-z+1/2,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+1/2,-y
155 -z+1/2,x+1/2,-y
156 -z+1/2,-x+1/2,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+1/2,z
159 y+1/2,-x+1/2,z
160 y+1/2,x+1/2,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+1/2,y
163 x+1/2,-z+1/2,y
164 x+1/2,z+1/2,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+1/2,x
167 z+1/2,-y+1/2,x
168 z+1/2,y+1/2,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+1/2,z
171 x+1/2,-y+1/2,z
172 x+1/2,y+1/2,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+1/2,x
175 y+1/2,-z+1/2,x
176 y+1/2,z+1/2,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+1/2,y
179 z+1/2,-x+1/2,y
180 z+1/2,x+1/2,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+1/2,-z
183 -y+1/2,x+1/2,-z
184 -y+1/2,-x+1/2,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+1/2,-y
187 -x+1/2,z+1/2,-y
188 -x+1/2,-z+1/2,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+1/2,-x
191 -z+1/2,y+1/2,-x
192 -z+1/2,-y+1/2,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cl1 Cl    4 a 0.00000 0.00000 0.00000 1.00000
Na1 Na    4 b 0.50000 0.50000 0.50000 1.00000
```

Rock Salt (NaCl, B1): AB_cF8_225_a_b - POSCAR

```
AB_cF8_225_a_b & a --params=5.63931 & Fm(-3)m    O_h^5 #225 (ab) & cF8 &
    ↪ B1 & NaCl & Halite/Rock Salt & D. Walker et al., Am. Mineral.
    ↪ 89, 204-210 (2004)
   1.0000000000000000
   0.00000000000000    2.81965339535660    2.81965339535660
   2.81965339535660    0.00000000000000    2.81965339535660
   2.81965339535660    2.81965339535660    0.00000000000000
   Cl    Na
    1     1
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    Cl    (4a)
   0.50000000000000    0.50000000000000    0.50000000000000    Na    (4b)
```

Ideal β-Cristobalite (SiO_2, C9): A2B_cF24_227_c_a - CIF

```
# CIF file

data_findsym-output
```

```
_audit_creation_method FINDSYM

_chemical_name_mineral 'high (beta) Cristobalite'
_chemical_formula_sum 'Si O2'

loop_
_publ_author_name
 'Donald R. Peacor'
_journal_name_full
;
Zeitschrift f\"{u}r kristallographie
;
_journal_volume 138
_journal_year 1973
_journal_page_first 274
_journal_page_last 298
_publ_Section_title
;
 High-temperature single-crystal study of the cristobalite inversion
;

# Found in  AMS Database

_aflow_proto 'A2B_cF24_227_c_a'
_aflow_params 'a'
_aflow_params_values '7.166'
_aflow_Strukturbericht 'C9'
_aflow_Pearson 'cF24'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a     7.16600
_cell_length_b     7.16600
_cell_length_c     7.16600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/4,-z+1/4
3 -x+1/4,y,-z+1/4
4 -x+1/4,-y+1/4,z
5 y,z,x
6 y,-z+1/4,-x+1/4
7 -y+1/4,z,-x+1/4
8 -y+1/4,-z+1/4,x
9 z,x,y
10 z,-x+1/4,-y+1/4
11 -z+1/4,x,-y+1/4
12 -z+1/4,-x+1/4,y
13 -y,-x,-z
14 -y,x+1/4,z+1/4
15 y+1/4,-x,z+1/4
16 y+1/4,x+1/4,-z
17 -x,-z,-y
18 -x,z+1/4,y+1/4
19 x+1/4,-z,y+1/4
20 x+1/4,z+1/4,-y
21 -z,-y,-x
22 -z,y+1/4,x+1/4
23 z+1/4,-y,x+1/4
24 z+1/4,y+1/4,-x
25 -x,-y,-z
26 -x,y+1/4,z+1/4
27 x+1/4,-y,z+1/4
28 x+1/4,y+1/4,-z
29 -y,-z,-x
30 -y,z+1/4,x+1/4
31 y+1/4,-z,x+1/4
32 y+1/4,z+1/4,-x
33 -z,-x,-y
34 -z,x+1/4,y+1/4
35 z+1/4,-x,y+1/4
36 z+1/4,x+1/4,-y
37 y,x,z
38 y,-x+1/4,-z+1/4
39 -y+1/4,x,-z+1/4
40 -y+1/4,-x+1/4,z
41 x,z,y
42 x,-z+1/4,-y+1/4
43 -x+1/4,z,-y+1/4
44 -x+1/4,-z+1/4,y
45 z,y,x
46 z,-y+1/4,-x+1/4
47 -z+1/4,y,-x+1/4
48 -z+1/4,-y+1/4,x
49 x,y+1/2,z+1/2
50 x,-y+3/4,-z+3/4
51 -x+1/4,y+1/2,-z+3/4
52 -x+1/4,-y+3/4,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+3/4,-x+3/4
55 -y+1/4,z+1/2,-x+3/4
56 -y+1/4,-z+3/4,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+3/4,-y+3/4
59 -z+1/4,x+1/2,-y+3/4
60 -z+1/4,-x+3/4,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+3/4,z+3/4
63 y+1/4,-x+1/2,z+3/4
64 y+1/4,x+3/4,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+3/4,y+3/4
67 x+1/4,-z+1/2,y+3/4
68 x+1/4,z+3/4,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+3/4,x+3/4
71 z+1/4,-y+1/2,x+3/4
72 z+1/4,y+3/4,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+3/4,z+3/4
75 x+1/4,-y+1/2,z+3/4
76 x+1/4,y+3/4,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+3/4,x+3/4
79 y+1/4,-z+1/2,x+3/4
80 y+1/4,z+3/4,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+3/4,y+3/4
83 z+1/4,-x+1/2,y+3/4
84 z+1/4,x+3/4,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+3/4,-z+3/4
87 -y+1/4,x+1/2,-z+3/4
88 -y+1/4,-x+3/4,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+3/4,-y+3/4
91 -x+1/4,z+1/2,-y+3/4
92 -x+1/4,-z+3/4,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+3/4,-x+3/4
95 -z+1/4,y+1/2,-x+3/4
96 -z+1/4,-y+3/4,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y+1/4,-z+3/4
99 -x+3/4,y,-z+3/4
100 -x+3/4,-y+1/4,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z+1/4,-x+3/4
103 -y+3/4,z,-x+3/4
104 -y+3/4,-z+1/4,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x+1/4,-y+3/4
107 -z+3/4,x,-y+3/4
108 -z+3/4,-x+1/4,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x+1/4,z+3/4
111 y+3/4,-x,z+3/4
112 y+3/4,x+1/4,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z+1/4,y+3/4
115 x+3/4,-z,y+3/4
116 x+3/4,z+1/4,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y+1/4,x+3/4
119 z+3/4,-y,x+3/4
120 z+3/4,y+1/4,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y+1/4,z+3/4
123 x+3/4,-y,z+3/4
124 x+3/4,y+1/4,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z+1/4,x+3/4
127 y+3/4,-z,x+3/4
128 y+3/4,z+1/4,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x+1/4,y+3/4
131 z+3/4,-x,y+3/4
132 z+3/4,x+1/4,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x+1/4,-z+3/4
135 -y+3/4,x,-z+3/4
136 -y+3/4,-x+1/4,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z+1/4,-y+3/4
139 -x+3/4,z,-y+3/4
140 -x+3/4,-z+1/4,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y+1/4,-x+3/4
143 -z+3/4,y,-x+3/4
144 -z+3/4,-y+1/4,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+3/4,-z+1/4
147 -x+3/4,y+1/2,-z+1/4
148 -x+3/4,-y+3/4,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+3/4,-x+1/4
151 -y+3/4,z+1/2,-x+1/4
152 -y+3/4,-z+3/4,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+3/4,-y+1/4
155 -z+3/4,x+1/2,-y+1/4
156 -z+3/4,-x+3/4,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+3/4,z+1/4
159 y+3/4,-x+1/2,z+1/4
160 y+3/4,x+3/4,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+3/4,y+1/4
163 x+3/4,-z+1/2,y+1/4
164 x+3/4,z+3/4,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+3/4,x+1/4
167 z+3/4,-y+1/2,x+1/4
```

```
168 z+3/4,y+3/4,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+3/4,z+1/4
171 x+3/4,-y+1/2,z+1/4
172 x+3/4,y+3/4,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+3/4,x+1/4
175 y+3/4,-z+1/2,x+1/4
176 y+3/4,z+3/4,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+3/4,y+1/4
179 z+3/4,-x+1/2,y+1/4
180 z+3/4,x+3/4,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+3/4,-z+1/4
183 -y+3/4,x+1/2,-z+1/4
184 -y+3/4,-x+3/4,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+3/4,-y+1/4
187 -x+3/4,z+1/2,-y+1/4
188 -x+3/4,-z+3/4,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+3/4,-x+1/4
191 -z+3/4,y+1/2,-x+1/4
192 -z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   8 a 0.12500 0.12500 0.12500 1.00000
O1  O   16 c 0.00000 0.00000 0.00000 1.00000
```

Ideal β-Cristobalite (SiO_2, C9): A2B_cF24_227_c_a - POSCAR

```
A2B_cF24_227_c_a & a --params=7.166 & Fd(-3)m   O_h^7 #227 (ac) & cF24 &
    ↪ C9 & SiO2 & beta (high) Cristobalite -- idealized structure &
    ↪ D. R. Peacor, Zeitschrift f\"{u}r kristallographie 138, 274-298
    ↪ (1973)
   1.0000000000000000
   0.00000000000000    3.58300000000000    3.58300000000000
   3.58300000000000    0.00000000000000    3.58300000000000
   3.58300000000000    3.58300000000000    0.00000000000000
    O   Si
    4    2
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    O    (16c)
   0.00000000000000    0.00000000000000    0.50000000000000    O    (16c)
   0.00000000000000    0.50000000000000    0.00000000000000    O    (16c)
   0.50000000000000    0.00000000000000    0.00000000000000    O    (16c)
   0.12500000000000    0.12500000000000    0.12500000000000    Si   (8a)
   0.87500000000000    0.87500000000000    0.87500000000000    Si   (8a)
```

$NiTi_2$: AB2_cF96_227_e_cf - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ni Ti2'

loop_
_publ_author_name
 'G. A. Yurko'
 'J. W. Barton'
 'J. Gordon Parr'
_journal_name_full
;
Acta Crystallographica
;
_journal_volume 12
_journal_year 1959
_journal_page_first 909
_journal_page_last 911
_publ_Section_title
;
 The crystal structure of Ti$_2$Ni
;

# Found in  Pearson's Handbook Vol IV, pp. 4715

_aflow_proto 'AB2_cF96_227_e_cf'
_aflow_params 'a,x2,x3'
_aflow_params_values '11.278,0.215,0.44'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cF96'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a      11.27800
_cell_length_b      11.27800
_cell_length_c      11.27800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/4,-z+1/4
3 -x+1/4,y,-z+1/4
4 -x+1/4,-y+1/4,z
5 y,z,x
6 y,-z+1/4,-x+1/4
7 -y+1/4,z,-x+1/4
8 -y+1/4,-z+1/4,x
9 z,x,y
10 z,-x+1/4,-y+1/4
11 -z+1/4,x,-y+1/4
12 -z+1/4,-x+1/4,y
13 -y,-x,-z
14 -y,x+1/4,z+1/4
15 y+1/4,-x,z+1/4
16 y+1/4,x+1/4,-z
17 -x,-z,-y
18 -x,z+1/4,y+1/4
19 x+1/4,-z,y+1/4
20 x+1/4,z+1/4,-y
21 -z,-y,-x
22 -z,y+1/4,x+1/4
23 z+1/4,-y,x+1/4
24 z+1/4,y+1/4,-x
25 -x,-y,-z
26 -x,y+1/4,z+1/4
27 x+1/4,-y,z+1/4
28 x+1/4,y+1/4,-z
29 -y,-z,-x
30 -y,z+1/4,x+1/4
31 y+1/4,-z,x+1/4
32 y+1/4,z+1/4,-x
33 -z,-x,-y
34 -z,x+1/4,y+1/4
35 z+1/4,-x,y+1/4
36 z+1/4,x+1/4,-y
37 y,x,z
38 y,-x+1/4,-z+1/4
39 -y+1/4,x,-z+1/4
40 -y+1/4,-x+1/4,z
41 x,z,y
42 x,-z+1/4,-y+1/4
43 -x+1/4,z,-y+1/4
44 -x+1/4,-z+1/4,y
45 z,y,x
46 z,-y+1/4,-x+1/4
47 -z+1/4,y,-x+1/4
48 -z+1/4,-y+1/4,x
49 x,y+1/2,z+1/2
50 x,-y+3/4,-z+3/4
51 -x+1/4,y+1/2,-z+3/4
52 -x+1/4,-y+3/4,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+3/4,-x+3/4
55 -y+1/4,z+1/2,-x+3/4
56 -y+1/4,-z+3/4,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+3/4,-y+3/4
59 -z+1/4,x+1/2,-y+3/4
60 -z+1/4,-x+3/4,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+3/4,z+3/4
63 y+1/4,-x+1/2,z+3/4
64 y+1/4,x+3/4,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+3/4,y+3/4
67 x+1/4,-z+1/2,y+3/4
68 x+1/4,z+3/4,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+3/4,x+3/4
71 z+1/4,-y+1/2,x+3/4
72 z+1/4,y+3/4,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+3/4,z+3/4
75 x+1/4,-y+1/2,z+3/4
76 x+1/4,y+3/4,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+3/4,x+3/4
79 y+1/4,-z+1/2,x+3/4
80 y+1/4,z+3/4,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+3/4,y+3/4
83 z+1/4,-x+1/2,y+3/4
84 z+1/4,x+3/4,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+3/4,-z+3/4
87 -y+1/4,x+1/2,-z+3/4
88 -y+1/4,-x+3/4,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+3/4,-y+3/4
91 -x+1/4,z+1/2,-y+3/4
92 -x+1/4,-z+3/4,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+3/4,-x+3/4
95 -z+1/4,y+1/2,-x+3/4
96 -z+1/4,-y+3/4,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y+1/4,-z+3/4
99 -x+3/4,y,-z+3/4
100 -x+3/4,-y+1/4,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z+1/4,-x+3/4
```

```
-y+3/4,z,-x+3/4
-y+3/4,-z+1/4,x+1/2
z+1/2,x,y+1/2
z+1/2,-x+1/4,-y+3/4
-z+3/4,x,-y+3/4
-z+3/4,-x+1/4,y+1/2
-y+1/2,-x,-z+1/2
-y+1/2,x+1/4,z+3/4
y+3/4,-x,z+3/4
y+3/4,x+1/4,-z+1/2
-x+1/2,-z,-y+1/2
-x+1/2,z+1/4,y+3/4
x+3/4,-z,y+3/4
x+3/4,z+1/4,-y+1/2
-z+1/2,-y,-x+1/2
-z+1/2,y+1/4,x+3/4
z+3/4,-y,x+3/4
z+3/4,y+1/4,-x+1/2
-x+1/2,-y,-z+1/2
-x+1/2,y+1/4,z+3/4
x+3/4,-y,z+3/4
x+3/4,y+1/4,-z+1/2
-y+1/2,-z,-x+1/2
-y+1/2,z+1/4,x+3/4
y+3/4,-z,x+3/4
y+3/4,z+1/4,-x+1/2
-z+1/2,-x,-y+1/2
-z+1/2,x+1/4,y+3/4
z+3/4,-x,y+3/4
z+3/4,x+1/4,-y+1/2
y+1/2,x,z+1/2
y+1/2,-x+1/4,-z+3/4
-y+3/4,x,-z+3/4
-y+3/4,-x+1/4,z+1/2
x+1/2,z,y+1/2
x+1/2,-z+1/4,-y+3/4
-x+3/4,z,-y+3/4
-x+3/4,-z+1/4,y+1/2
z+1/2,y,x+1/2
z+1/2,-y+1/4,-x+3/4
-z+3/4,y,-x+3/4
-z+3/4,-y+1/4,x+1/2
x+1/2,y+1/2,z
x+1/2,-y+3/4,-z+1/4
-x+3/4,y+1/2,-z+1/4
-x+3/4,-y+3/4,z
y+1/2,z+1/2,x
y+1/2,-z+3/4,-x+1/4
-y+3/4,z+1/2,-x+1/4
-y+3/4,-z+3/4,x
z+1/2,x+1/2,y
z+1/2,-x+3/4,-y+1/4
-z+3/4,x+1/2,-y+1/4
-z+3/4,-x+3/4,y
-y+1/2,-x+1/2,-z
-y+1/2,x+3/4,z+1/4
y+3/4,-x+1/2,z+1/4
y+3/4,x+3/4,-z
-x+1/2,-z+1/2,-y
-x+1/2,z+3/4,y+1/4
x+3/4,-z+1/2,y+1/4
x+3/4,z+3/4,-y
-z+1/2,-y+1/2,-x
-z+1/2,y+3/4,x+1/4
z+3/4,-y+1/2,x+1/4
z+3/4,y+3/4,-x
-x+1/2,-y+1/2,-z
-x+1/2,y+3/4,z+1/4
x+3/4,-y+1/2,z+1/4
x+3/4,y+3/4,-z
-y+1/2,-z+1/2,-x
-y+1/2,z+3/4,x+1/4
y+3/4,-z+1/2,x+1/4
y+3/4,z+3/4,-x
-z+1/2,-x+1/2,-y
-z+1/2,x+3/4,y+1/4
z+3/4,-x+1/2,y+1/4
z+3/4,x+3/4,-y
y+1/2,x+1/2,z
y+1/2,-x+3/4,-z+1/4
-y+3/4,x+1/2,-z+1/4
-y+3/4,-x+3/4,z
x+1/2,z+1/2,y
x+1/2,-z+3/4,-y+1/4
-x+3/4,z+1/2,-y+1/4
-x+3/4,-z+3/4,y
z+1/2,y+1/2,x
z+1/2,-y+3/4,-x+1/4
-z+3/4,y+1/2,-x+1/4
-z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ti1 Ti  16 c 0.00000 0.00000 0.00000 1.00000
Ni1 Ni  32 e 0.21500 0.21500 0.21500 1.00000
Ti2 Ti  48 f 0.44000 0.12500 0.12500 1.00000
```

$NiTi_2$: AB2_cF96_227_e_cf - POSCAR

```
AB2_cF96_227_e_cf & a,x2,x3 --params=11.278,0.215,0.44 & Fd(-3)m   O_h^7
    ↪ #227 (cef) & cF96 & & NiTi2 & & G. A. Yurko, J. W. Barton and
    ↪ J. G. Parr, Acta Cyrst. 12, 909-911 (1959)
   1.0000000000000000
   0.00000000000000   5.63900000000000   5.63900000000000
   5.63900000000000   0.00000000000000   5.63900000000000
   5.63900000000000   5.63900000000000   0.00000000000000
   Ni    Ti
    8    16
Direct
   0.14500000000000  -0.21500000000000  -0.21500000000000   Ni   (32e)
  -0.14500000000000   0.21500000000000   0.21500000000000   Ni   (32e)
   0.21500000000000  -0.14500000000000   0.21500000000000   Ni   (32e)
  -0.21500000000000   0.14500000000000  -0.21500000000000   Ni   (32e)
   0.21500000000000   0.21500000000000  -0.14500000000000   Ni   (32e)
  -0.21500000000000  -0.21500000000000   0.14500000000000   Ni   (32e)
   0.21500000000000   0.21500000000000   0.21500000000000   Ni   (32e)
  -0.21500000000000  -0.21500000000000  -0.21500000000000   Ni   (32e)
   0.00000000000000   0.00000000000000   0.00000000000000   Ti   (16c)
   0.00000000000000   0.00000000000000   0.50000000000000   Ti   (16c)
   0.00000000000000   0.50000000000000   0.00000000000000   Ti   (16c)
   0.50000000000000   0.00000000000000   0.00000000000000   Ti   (16c)
  -0.19000000000000  -0.19000000000000   0.44000000000000   Ti   (48f)
   0.19000000000000   0.19000000000000   0.56000000000000   Ti   (48f)
  -0.19000000000000   0.44000000000000  -0.19000000000000   Ti   (48f)
  -0.19000000000000   0.44000000000000   0.44000000000000   Ti   (48f)
   0.19000000000000   0.56000000000000   0.19000000000000   Ti   (48f)
   0.19000000000000   0.56000000000000   0.56000000000000   Ti   (48f)
   0.44000000000000  -0.19000000000000  -0.19000000000000   Ti   (48f)
   0.44000000000000  -0.19000000000000   0.44000000000000   Ti   (48f)
   0.44000000000000   0.44000000000000  -0.19000000000000   Ti   (48f)
   0.56000000000000   0.19000000000000   0.19000000000000   Ti   (48f)
   0.56000000000000   0.19000000000000   0.56000000000000   Ti   (48f)
   0.56000000000000   0.56000000000000   0.19000000000000   Ti   (48f)
```

NaTl (B32): AB_cF16_227_a_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Zintl Phase'
_chemical_formula_sum 'Na Tl'

loop_
_publ_author_name
 'K. Kuriyama'
 'S. Saito'
 'K. Iwamura'
_journal_name_full
;
Journal of Physics and Chemistry of Solids
;
_journal_volume 40
_journal_year 1979
_journal_page_first 457
_journal_page_last 461
_publ_Section_title
;
 Ultrasonic study on the elastic moduli of the NaTl (B32) structure
;

# Found in  http://materials.springer.com/isp/crystallographic/docs/
    ↪ sd_0528644

_aflow_proto 'AB_cF16_227_a_b'
_aflow_params 'a'
_aflow_params_values '7.483'
_aflow_Strukturbericht 'B32'
_aflow_Pearson 'cF16'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a    7.48300
_cell_length_b    7.48300
_cell_length_c    7.48300
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/4,-z+1/4
3 -x+1/4,y,-z+1/4
4 -x+1/4,-y+1/4,z
5 y,z,x
6 y,-z+1/4,-x+1/4
7 -y+1/4,z,-x+1/4
8 -y+1/4,-z+1/4,x
9 z,x,y
10 z,-x+1/4,-y+1/4
11 -z+1/4,x,-y+1/4
12 -z+1/4,-x+1/4,y
13 -y,-x,-z
14 -y,x+1/4,z+1/4
15 y+1/4,-x,z+1/4
16 y+1/4,x+1/4,-z
17 -x,-z,-y
18 -x,z+1/4,y+1/4
19 x+1/4,-z,y+1/4
```

```
x+1/4,z+1/4,-y
-z,-y,-x
-z,y+1/4,x+1/4
z+1/4,-y,x+1/4
z+1/4,y+1/4,-x
-x,-y,-z
-x,y+1/4,z+1/4
x+1/4,-y,z+1/4
x+1/4,y+1/4,-z
-y,-z,-x
-y,z+1/4,x+1/4
y+1/4,-z,x+1/4
y+1/4,z+1/4,-x
-z,-x,-y
-z,x+1/4,y+1/4
z+1/4,-x,y+1/4
z+1/4,x+1/4,-y
y,x,z
y,-x+1/4,-z+1/4
-y+1/4,x,-z+1/4
-y+1/4,-x+1/4,z
x,z,y
x,-z+1/4,-y+1/4
-x+1/4,z,-y+1/4
-x+1/4,-z+1/4,y
z,y,x
z,-y+1/4,-x+1/4
-z+1/4,y,-x+1/4
-z+1/4,-y+1/4,x
x,y+1/2,z+1/2
x,-y+3/4,-z+3/4
-x+1/4,y+1/2,-z+3/4
-x+1/4,-y+3/4,z+1/2
y,z+1/2,x+1/2
y,-z+3/4,-x+3/4
-y+1/4,z+1/2,-x+3/4
-y+1/4,-z+3/4,x+1/2
z,x+1/2,y+1/2
z,-x+3/4,-y+3/4
-z+1/4,x+1/2,-y+3/4
-z+1/4,-x+3/4,y+1/2
-y,-x+1/2,-z+1/2
-y,x+3/4,z+3/4
y+1/4,-x+1/2,z+3/4
y+1/4,x+3/4,-z+1/2
-x,-z+1/2,-y+1/2
-x,z+3/4,y+3/4
x+1/4,-z+1/2,y+3/4
x+1/4,z+3/4,-y+1/2
-z,-y+1/2,-x+1/2
-z,y+3/4,x+3/4
z+1/4,-y+1/2,x+3/4
z+1/4,y+3/4,-x+1/2
-x,-y+1/2,-z+1/2
-x,y+3/4,z+3/4
x+1/4,-y+1/2,z+3/4
x+1/4,y+3/4,-z+1/2
-y,-z+1/2,-x+1/2
-y,z+3/4,x+3/4
y+1/4,-z+1/2,x+3/4
y+1/4,z+3/4,-x+1/2
-z,-x+1/2,-y+1/2
-z,x+3/4,y+3/4
z+1/4,-x+1/2,y+3/4
z+1/4,x+3/4,-y+1/2
y,x+1/2,z+1/2
y,-x+3/4,-z+3/4
-y+1/4,x+1/2,-z+3/4
-y+1/4,-x+3/4,z+1/2
x,z+1/2,y+1/2
x,-z+3/4,-y+3/4
-x+1/4,z+1/2,-y+3/4
-x+1/4,-z+3/4,y+1/2
z,y+1/2,x+1/2
z,-y+3/4,-x+3/4
-z+1/4,y+1/2,-x+3/4
-z+1/4,-y+3/4,x+1/2
x+1/2,y,z+1/2
x+1/2,-y+1/4,-z+3/4
-x+3/4,y,-z+3/4
-x+3/4,-y+1/4,z+1/2
y+1/2,z,x+1/2
y+1/2,-z+1/4,-x+3/4
-y+3/4,z,-x+3/4
-y+3/4,-z+1/4,x+1/2
z+1/2,x,y+1/2
z+1/2,-x+1/4,-y+3/4
-z+3/4,x,-y+3/4
-z+3/4,-x+1/4,y+1/2
-y+1/2,-x,-z+1/2
-y+1/2,x+1/4,z+3/4
y+3/4,-x,z+3/4
y+3/4,x+1/4,-z+1/2
-x+1/2,-z,-y+1/2
-x+1/2,z+1/4,y+3/4
x+3/4,-z,y+3/4
x+3/4,z+1/4,-y+1/2
-z+1/2,-y,-x+1/2
-z+1/2,y+1/4,x+3/4
z+3/4,-y,x+3/4
z+3/4,y+1/4,-x+1/2
-x+1/2,-y,-z+1/2
-x+1/2,y+1/4,z+3/4
x+3/4,-y,z+3/4
x+3/4,y+1/4,-z+1/2
-y+1/2,-z,-x+1/2
-y+1/2,z+1/4,x+3/4
y+3/4,-z,x+3/4
y+3/4,z+1/4,-x+1/2
-z+1/2,-x,-y+1/2
-z+1/2,x+1/4,y+3/4
z+3/4,-x,y+3/4
z+3/4,x+1/4,-y+1/2
y+1/2,x,z+1/2
y+1/2,-x+1/4,-z+3/4
-y+3/4,x,-z+3/4
-y+3/4,-x+1/4,z+1/2
x+1/2,z,y+1/2
x+1/2,-z+1/4,-y+3/4
-x+3/4,z,-y+3/4
-x+3/4,-z+1/4,y+1/2
z+1/2,y,x+1/2
z+1/2,-y+1/4,-x+3/4
-z+3/4,y,-x+3/4
-z+3/4,-y+1/4,x+1/2
x+1/2,y+1/2,z
x+1/2,-y+3/4,-z+1/4
-x+3/4,y+1/2,-z+1/4
-x+3/4,-y+3/4,z
y+1/2,z+1/2,x
y+1/2,-z+3/4,-x+1/4
-y+3/4,z+1/2,-x+1/4
-y+3/4,-z+3/4,x
z+1/2,x+1/2,y
z+1/2,-x+3/4,-y+1/4
-z+3/4,x+1/2,-y+1/4
-z+3/4,-x+3/4,y
-y+1/2,-x+1/2,-z
-y+1/2,x+3/4,z+1/4
y+3/4,-x+1/2,z+1/4
y+3/4,x+3/4,-z
-x+1/2,-z+1/2,-y
-x+1/2,z+3/4,y+1/4
x+3/4,-z+1/2,y+1/4
x+3/4,z+3/4,-y
-z+1/2,-y+1/2,-x
-z+1/2,y+3/4,x+1/4
z+3/4,-y+1/2,x+1/4
z+3/4,y+3/4,-x
-x+1/2,-y+1/2,-z
-x+1/2,y+3/4,z+1/4
x+3/4,-y+1/2,z+1/4
x+3/4,y+3/4,-z
-y+1/2,-z+1/2,-x
-y+1/2,z+3/4,x+1/4
y+3/4,-z+1/2,x+1/4
y+3/4,z+3/4,-x
-z+1/2,-x+1/2,-y
-z+1/2,x+3/4,y+1/4
z+3/4,-x+1/2,y+1/4
z+3/4,x+3/4,-y
y+1/2,x+1/2,z
y+1/2,-x+3/4,-z+1/4
-y+3/4,x+1/2,-z+1/4
-y+3/4,-x+3/4,z
x+1/2,z+1/2,y
x+1/2,-z+3/4,-y+1/4
-x+3/4,z+1/2,-y+1/4
-x+3/4,-z+3/4,y
z+1/2,y+1/2,x
z+1/2,-y+3/4,-x+1/4
-z+3/4,y+1/2,-x+1/4
-z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Na1 Na   8 a 0.12500 0.12500 0.12500 1.00000
Tl1 Tl   8 b 0.37500 0.37500 0.37500 1.00000
```

NaTl (B32): AB_cF16_227_a_b - POSCAR

```
AB_cF16_227_a_b & a --params=7.483 & Fd(-3)m   O_h^7 #227 (ab) & cF16 &
    ↪ B32 & NaTl & Zintl Phase & K. Kuriyama and S. Saito and K.
    ↪ Iwamura, J. Phys. Chem. Solids 40, 457-461 (1979)
   1.000000000000000
   0.00000000000000    3.74150000000000    3.74150000000000
   3.74150000000000    0.00000000000000    3.74150000000000
   3.74150000000000    3.74150000000000    0.00000000000000
   Na   Tl
    2    2
Direct
   0.12500000000000    0.12500000000000    0.12500000000000    Na    (8a)
   0.87500000000000    0.87500000000000    0.87500000000000    Na    (8a)
   0.37500000000000    0.37500000000000    0.37500000000000    Tl    (8b)
   0.62500000000000    0.62500000000000    0.62500000000000    Tl    (8b)
```

Si_{34} Clathrate: A_cF136_227_aeg - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM
```

```
_chemical_name_mineral 'Clathrate'
_chemical_formula_sum 'Si'

loop_
_publ_author_name
 'Gary B. Adams'
 'Michael O'Keeffe'
 'Alexander A. Demkov'
 'Otto F. Sankey'
 'Yin-Min Huang'
_journal_name_full
;
Physical Review B
;
_journal_volume 49
_journal_year 1994
_journal_page_first 8048
_journal_page_last 8053
_publ_Section_title
;
 Wide-band-gap Si in open fourfold-coordinated clathrate structures
;

_aflow_proto 'A_cF136_227_aeg'
_aflow_params 'a,x2,x3,z3'
_aflow_params_values '14.864,0.2624,0.1824,0.3701'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cF136'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a    14.86400
_cell_length_b    14.86400
_cell_length_c    14.86400
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/4,-z+1/4
3 -x+1/4,y,-z+1/4
4 -x+1/4,-y+1/4,z
5 y,z,x
6 y,-z+1/4,-x+1/4
7 -y+1/4,z,-x+1/4
8 -y+1/4,-z+1/4,x
9 z,x,y
10 z,-x+1/4,-y+1/4
11 -z+1/4,x,-y+1/4
12 -z+1/4,-x+1/4,y
13 -y,-x,-z
14 -y,x+1/4,z+1/4
15 y+1/4,-x,z+1/4
16 y+1/4,x+1/4,-z
17 -x,-z,-y
18 -x,z+1/4,y+1/4
19 x+1/4,-z,y+1/4
20 x+1/4,z+1/4,-y
21 -z,-y,-x
22 -z,y+1/4,x+1/4
23 z+1/4,-y,x+1/4
24 z+1/4,y+1/4,-x
25 -x,-y,-z
26 -x,y+1/4,z+1/4
27 x+1/4,-y,z+1/4
28 x+1/4,y+1/4,-z
29 -y,-z,-x
30 -y,z+1/4,x+1/4
31 y+1/4,-z,x+1/4
32 y+1/4,z+1/4,-x
33 -z,-x,-y
34 -z,x+1/4,y+1/4
35 z+1/4,-x,y+1/4
36 z+1/4,x+1/4,-y
37 y,x,z
38 y,-x+1/4,-z+1/4
39 -y+1/4,x,-z+1/4
40 -y+1/4,-x+1/4,z
41 x,z,y
42 x,-z+1/4,-y+1/4
43 -x+1/4,z,-y+1/4
44 -x+1/4,-z+1/4,y
45 z,y,x
46 z,-y+1/4,-x+1/4
47 -z+1/4,y,-x+1/4
48 -z+1/4,-y+1/4,x
49 x,y+1/2,z+1/2
50 x,-y+3/4,-z+3/4
51 -x+1/4,y+1/2,-z+3/4
52 -x+1/4,-y+3/4,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+3/4,-x+3/4
55 -y+1/4,z+1/2,-x+3/4
56 -y+1/4,-z+3/4,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+3/4,-y+3/4
59 -z+1/4,x+1/2,-y+3/4
60 -z+1/4,-x+3/4,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+3/4,z+3/4
63 y+1/4,-x+1/2,z+3/4
64 y+1/4,x+3/4,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+3/4,y+3/4
67 x+1/4,-z+1/2,y+3/4
68 x+1/4,z+3/4,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+3/4,x+3/4
71 z+1/4,-y+1/2,x+3/4
72 z+1/4,y+3/4,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+3/4,z+3/4
75 x+1/4,-y+1/2,z+3/4
76 x+1/4,y+3/4,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+3/4,x+3/4
79 y+1/4,-z+1/2,x+3/4
80 y+1/4,z+3/4,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+3/4,y+3/4
83 z+1/4,-x+1/2,y+3/4
84 z+1/4,x+3/4,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+3/4,-z+3/4
87 -y+1/4,x+1/2,-z+3/4
88 -y+1/4,-x+3/4,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+3/4,-y+3/4
91 -x+1/4,z+1/2,-y+3/4
92 -x+1/4,-z+3/4,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+3/4,-x+3/4
95 -z+1/4,y+1/2,-x+3/4
96 -z+1/4,-y+3/4,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y+1/4,-z+3/4
99 -x+3/4,y,-z+3/4
100 -x+3/4,-y+1/4,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z+1/4,-x+3/4
103 -y+3/4,z,-x+3/4
104 -y+3/4,-z+1/4,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x+1/4,-y+3/4
107 -z+3/4,x,-y+3/4
108 -z+3/4,-x+1/4,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x+1/4,z+3/4
111 y+3/4,-x,z+3/4
112 y+3/4,x+1/4,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z+1/4,y+3/4
115 x+3/4,-z,y+3/4
116 x+3/4,z+1/4,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y+1/4,x+3/4
119 z+3/4,-y,x+3/4
120 z+3/4,y+1/4,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y+1/4,z+3/4
123 x+3/4,-y,z+3/4
124 x+3/4,y+1/4,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z+1/4,x+3/4
127 y+3/4,-z,x+3/4
128 y+3/4,z+1/4,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x+1/4,y+3/4
131 z+3/4,-x,y+3/4
132 z+3/4,x+1/4,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x+1/4,-z+3/4
135 -y+3/4,x,-z+3/4
136 -y+3/4,-x+1/4,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z+1/4,-y+3/4
139 -x+3/4,z,-y+3/4
140 -x+3/4,-z+1/4,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y+1/4,-x+3/4
143 -z+3/4,y,-x+3/4
144 -z+3/4,-y+1/4,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+3/4,-z+1/4
147 -x+3/4,y+1/2,-z+1/4
148 -x+3/4,-y+3/4,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+3/4,-x+1/4
151 -y+3/4,z+1/2,-x+1/4
152 -y+3/4,-z+3/4,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+3/4,-y+1/4
155 -z+3/4,x+1/2,-y+1/4
156 -z+3/4,-x+3/4,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+3/4,z+1/4
159 y+3/4,-x+1/2,z+1/4
160 y+3/4,x+3/4,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+3/4,y+1/4
163 x+3/4,-z+1/2,y+1/4
164 x+3/4,z+3/4,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+3/4,x+1/4
167 z+3/4,-y+1/2,x+1/4
```

```
168 z+3/4,y+3/4,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+3/4,z+1/4
171 x+3/4,-y+1/2,z+1/4
172 x+3/4,y+3/4,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+3/4,x+1/4
175 y+3/4,-z+1/2,x+1/4
176 y+3/4,z+3/4,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+3/4,y+1/4
179 z+3/4,-x+1/2,y+1/4
180 z+3/4,x+3/4,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+3/4,-z+1/4
183 -y+3/4,x+1/2,-z+1/4
184 -y+3/4,-x+3/4,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+3/4,-y+1/4
187 -x+3/4,z+1/2,-y+1/4
188 -x+3/4,-z+3/4,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+3/4,-x+1/4
191 -z+3/4,y+1/2,-x+1/4
192 -z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Si1 Si   8 a 0.12500 0.12500 0.12500 1.00000
Si2 Si  32 e 0.26240 0.26240 0.26240 1.00000
Si3 Si  96 g 0.18240 0.18240 0.37010 1.00000
```

Si_{34} Clathrate: A_cF136_227_aeg - POSCAR

```
A_cF136_227_aeg & a,x2,x3,z3 --params=14.864,0.2624,0.1824,0.3701 & Fd(-
    ↪ 3)m   O_h^7 #227 (aeg) & cF136 & & Si & Clathrate & G. B. Adams
    ↪ , M. O'Keefe, A. A. Demkov, O. F. Sankey and Y.-M. Huang, Phys.
    ↪  Rev. B 49, 8048-8053 (1994)
   1.0000000000000000
   0.00000000000000   7.43200000000000   7.43200000000000
   7.43200000000000   0.00000000000000   7.43200000000000
   7.43200000000000   7.43200000000000   0.00000000000000
   Si
   34
Direct
   0.26240000000000   0.26240000000000   0.26240000000000   Si   (32e)
   0.26240000000000   0.26240000000000   0.71280000000000   Si   (32e)
  -0.26240000000000   0.28720000000000   0.73760000000000   Si   (32e)
   0.26240000000000   0.71280000000000   0.26240000000000   Si   (32e)
   0.28720000000000   0.73760000000000  -0.26240000000000   Si   (32e)
   0.71280000000000   0.26240000000000   0.26240000000000   Si   (32e)
   0.73760000000000  -0.26240000000000   0.28720000000000   Si   (32e)
   0.73760000000000   0.73760000000000   0.73760000000000   Si   (32e)
   0.12500000000000   0.12500000000000   0.12500000000000   Si    (8a)
   0.87500000000000   0.87500000000000   0.87500000000000   Si    (8a)
   0.00530000000000   0.23490000000000   0.62990000000000   Si   (96g)
   0.00530000000000  -0.37010000000000   0.23490000000000   Si   (96g)
  -0.00530000000000   0.37010000000000   0.37010000000000   Si   (96g)
  -0.00530000000000   0.37010000000000   0.76510000000000   Si   (96g)
   0.00530000000000   0.62990000000000   0.62990000000000   Si   (96g)
   0.23490000000000   0.00530000000000  -0.37010000000000   Si   (96g)
   0.23490000000000   0.62990000000000   0.00530000000000   Si   (96g)
   0.23490000000000   0.62990000000000  -0.37010000000000   Si   (96g)
   0.37010000000000  -0.00530000000000   0.37010000000000   Si   (96g)
  -0.37010000000000   0.23490000000000   0.00530000000000   Si   (96g)
  -0.37010000000000   0.23490000000000   0.62990000000000   Si   (96g)
   0.37010000000000   0.37010000000000  -0.00530000000000   Si   (96g)
   0.37010000000000   0.37010000000000   0.76510000000000   Si   (96g)
   0.37010000000000   0.76510000000000  -0.00530000000000   Si   (96g)
   0.37010000000000   0.76510000000000   0.37010000000000   Si   (96g)
   0.37010000000000   0.99470000000000   0.76510000000000   Si   (96g)
   0.62990000000000   0.00530000000000   0.23490000000000   Si   (96g)
   0.62990000000000   0.00530000000000   0.62990000000000   Si   (96g)
   0.62990000000000  -0.37010000000000   0.23490000000000   Si   (96g)
   0.62990000000000   0.62990000000000   0.00530000000000   Si   (96g)
   0.76510000000000  -0.00530000000000   0.37010000000000   Si   (96g)
   0.76510000000000   0.37010000000000   0.37010000000000   Si   (96g)
   0.76510000000000   0.37010000000000   0.99470000000000   Si   (96g)
   0.99470000000000   0.76510000000000   0.37010000000000   Si   (96g)
```

Cu_2Mg Cubic Laves (C15): A2B_cF24_227_d_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Cubic Laves'
_chemical_formula_sum 'Cu2 Mg'

loop_
_publ_author_name
 'James B. Friauf'
_journal_name_full
;
Journal of the American Chemical Society
;
_journal_volume 49
_journal_year 1927
_journal_page_first 3107
_journal_page_last 3114
_publ_Section_title
;
 The Crystal Structures of Two Intermetallic Compounds
;

# Found in  Wyckoff, Vol. I, pp. 365-367

_aflow_proto 'A2B_cF24_227_d_a'
_aflow_params 'a'
_aflow_params_values '7.02'
_aflow_Strukturbericht 'C15'
_aflow_Pearson 'cF24'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a     7.02000
_cell_length_b     7.02000
_cell_length_c     7.02000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/4,-z+1/4
3 -x+1/4,y,-z+1/4
4 -x+1/4,-y+1/4,z
5 y,z,x
6 y,-z+1/4,-x+1/4
7 -y+1/4,z,-x+1/4
8 -y+1/4,-z+1/4,x
9 z,x,y
10 z,-x+1/4,-y+1/4
11 -z+1/4,x,-y+1/4
12 -z+1/4,-x+1/4,y
13 -y,-x,-z
14 -y,x+1/4,z+1/4
15 y+1/4,-x,z+1/4
16 y+1/4,x+1/4,-z
17 -x,-z,-y
18 -x,z+1/4,y+1/4
19 x+1/4,-z,y+1/4
20 x+1/4,z+1/4,-y
21 -z,-y,-x
22 -z,y+1/4,x+1/4
23 z+1/4,-y,x+1/4
24 z+1/4,y+1/4,-x
25 -x,-y,-z
26 -x,y+1/4,z+1/4
27 x+1/4,-y,z+1/4
28 x+1/4,y+1/4,-z
29 -y,-z,-x
30 -y,z+1/4,x+1/4
31 y+1/4,-z,x+1/4
32 y+1/4,z+1/4,-x
33 -z,-x,-y
34 -z,x+1/4,y+1/4
35 z+1/4,-x,y+1/4
36 z+1/4,x+1/4,-y
37 y,x,z
38 y,-x+1/4,-z+1/4
39 -y+1/4,x,-z+1/4
40 -y+1/4,-x+1/4,z
41 x,z,y
42 x,-z+1/4,-y+1/4
43 -x+1/4,z,-y+1/4
44 -x+1/4,-z+1/4,y
45 z,y,x
46 z,-y+1/4,-x+1/4
47 -z+1/4,y,-x+1/4
48 -z+1/4,-y+1/4,x
49 x,y+1/2,z+1/2
50 x,-y+3/4,-z+3/4
51 -x+1/4,y+1/2,-z+3/4
52 -x+1/4,-y+3/4,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+3/4,-x+3/4
55 -y+1/4,z+1/2,-x+3/4
56 -y+1/4,-z+3/4,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+3/4,-y+3/4
59 -z+1/4,x+1/2,-y+3/4
60 -z+1/4,-x+3/4,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+3/4,z+3/4
63 y+1/4,-x+1/2,z+3/4
64 y+1/4,x+3/4,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+3/4,y+3/4
67 x+1/4,-z+1/2,y+3/4
68 x+1/4,z+3/4,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+3/4,x+3/4
71 z+1/4,-y+1/2,x+3/4
72 z+1/4,y+3/4,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+3/4,z+3/4
75 x+1/4,-y+1/2,z+3/4
```

```
76 x+1/4,y+3/4,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+3/4,x+3/4
79 y+1/4,-z+1/2,x+3/4
80 y+1/4,z+3/4,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+3/4,y+3/4
83 z+1/4,-x+1/2,y+3/4
84 z+1/4,x+3/4,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+3/4,-z+3/4
87 -y+1/4,x+1/2,-z+3/4
88 -y+1/4,-x+3/4,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+3/4,-y+3/4
91 -x+1/4,z+1/2,-y+3/4
92 -x+1/4,-z+3/4,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+3/4,-x+3/4
95 -z+1/4,y+1/2,-x+3/4
96 -z+1/4,-y+3/4,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y+1/4,-z+3/4
99 -x+3/4,y,-z+3/4
100 -x+3/4,-y+1/4,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z+1/4,-x+3/4
103 -y+3/4,z,-x+3/4
104 -y+3/4,-z+1/4,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x+1/4,-y+3/4
107 -z+3/4,x,-y+3/4
108 -z+3/4,-x+1/4,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x+1/4,z+3/4
111 y+3/4,-x,z+3/4
112 y+3/4,x+1/4,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z+1/4,y+3/4
115 x+3/4,-z,y+3/4
116 x+3/4,z+1/4,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y+1/4,x+3/4
119 z+3/4,-y,x+3/4
120 z+3/4,y+1/4,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y+1/4,z+3/4
123 x+3/4,-y,z+3/4
124 x+3/4,y+1/4,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z+1/4,x+3/4
127 y+3/4,-z,x+3/4
128 y+3/4,z+1/4,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x+1/4,y+3/4
131 z+3/4,-x,y+3/4
132 z+3/4,x+1/4,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x+1/4,-z+3/4
135 -y+3/4,x,-z+3/4
136 -y+3/4,-x+1/4,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z+1/4,-y+3/4
139 -x+3/4,z,-y+3/4
140 -x+3/4,-z+1/4,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y+1/4,-x+3/4
143 -z+3/4,y,-x+3/4
144 -z+3/4,-y+1/4,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+3/4,-z+1/4
147 -x+3/4,y+1/2,-z+1/4
148 -x+3/4,-y+3/4,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+3/4,-x+1/4
151 -y+3/4,z+1/2,-x+1/4
152 -y+3/4,-z+3/4,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+3/4,-y+1/4
155 -z+3/4,x+1/2,-y+1/4
156 -z+3/4,-x+3/4,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+3/4,z+1/4
159 y+3/4,-x+1/2,z+1/4
160 y+3/4,x+3/4,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+3/4,y+1/4
163 x+3/4,-z+1/2,y+1/4
164 x+3/4,z+3/4,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+3/4,x+1/4
167 z+3/4,-y+1/2,x+1/4
168 z+3/4,y+3/4,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+3/4,z+1/4
171 x+3/4,-y+1/2,z+1/4
172 x+3/4,y+3/4,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+3/4,x+1/4
175 y+3/4,-z+1/2,x+1/4
176 y+3/4,z+3/4,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+3/4,y+1/4
179 z+3/4,-x+1/2,y+1/4
180 z+3/4,x+3/4,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+3/4,-z+1/4
183 -y+3/4,x+1/2,-z+1/4
184 -y+3/4,-x+3/4,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+3/4,-y+1/4
187 -x+3/4,z+1/2,-y+1/4
188 -x+3/4,-z+3/4,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+3/4,-x+1/4
191 -z+3/4,y+1/2,-x+1/4
192 -z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mg1 Mg   8 a 0.12500 0.12500 0.12500 1.00000
Cu1 Cu  16 d 0.50000 0.50000 0.50000 1.00000
```

Cu_2Mg Cubic Laves (C15): A2B_cF24_227_d_a - POSCAR

```
A2B_cF24_227_d_a & a --params=7.02 & Fd(-3)m   O_h^7 #227 (ad) & cF24 &
    ↪ C15 & Cu2Mg & Cubic Laves & J. B. Friauf, J. Am. Chem. Soc. 49,
    ↪  3107-3114 (1927)
   1.0000000000000000
   0.00000000000000    3.51000000000000    3.51000000000000
   3.51000000000000    0.00000000000000    3.51000000000000
   3.51000000000000    3.51000000000000    0.00000000000000
   Cu    Mg
    4     2
Direct
   0.00000000000000    0.50000000000000    0.50000000000000    Cu    (16d)
   0.50000000000000    0.00000000000000    0.50000000000000    Cu    (16d)
   0.50000000000000    0.50000000000000    0.00000000000000    Cu    (16d)
   0.50000000000000    0.50000000000000    0.50000000000000    Cu    (16d)
   0.12500000000000    0.12500000000000    0.12500000000000    Mg     (8a)
   0.87500000000000    0.87500000000000    0.87500000000000    Mg     (8a)
```

Diamond (A4): A_cF8_227_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'diamond'
_chemical_formula_sum 'C'

loop_
_publ_author_name
 'W. H. Bragg'
 'W. L. Bragg'
_journal_name_full
;
Proceedings of the Royal Society of London, Series A
;
_journal_volume 89
_journal_year 1913
_journal_page_first 277
_journal_page_last 291
_publ_Section_title
;
 The Structure of Diamond
;

_aflow_proto 'A_cF8_227_a'
_aflow_params 'a'
_aflow_params_values '3.55'
_aflow_Strukturbericht 'A4'
_aflow_Pearson 'cF8'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a     3.55000
_cell_length_b     3.55000
_cell_length_c     3.55000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/4,-z+1/4
3 -x+1/4,y,-z+1/4
4 -x+1/4,-y+1/4,z
5 y,z,x
6 y,-z+1/4,-x+1/4
7 -y+1/4,z,-x+1/4
8 -y+1/4,-z+1/4,x
9 z,x,y
10 z,-x+1/4,-y+1/4
11 -z+1/4,x,-y+1/4
12 -z+1/4,-x+1/4,y
13 -y,-x,-z
14 -y,x+1/4,z+1/4
```

```
15 y+1/4,-x,z+1/4
16 y+1/4,x+1/4,-z
17 -x,-z,-y
18 -x,z+1/4,y+1/4
19 x+1/4,-z,y+1/4
20 x+1/4,z+1/4,-y
21 -z,-y,-x
22 -z,y+1/4,x+1/4
23 z+1/4,-y,x+1/4
24 z+1/4,y+1/4,-x
25 -x,-y,-z
26 -x,y+1/4,z+1/4
27 x+1/4,-y,z+1/4
28 x+1/4,y+1/4,-z
29 -y,-z,-x
30 -y,z+1/4,x+1/4
31 y+1/4,-z,x+1/4
32 y+1/4,z+1/4,-x
33 -z,-x,-y
34 -z,x+1/4,y+1/4
35 z+1/4,-x,y+1/4
36 z+1/4,x+1/4,-y
37 y,x,z
38 y,-x+1/4,-z+1/4
39 -y+1/4,x,-z+1/4
40 -y+1/4,-x+1/4,z
41 x,z,y
42 x,-z+1/4,-y+1/4
43 -x+1/4,z,-y+1/4
44 -x+1/4,-z+1/4,y
45 z,y,x
46 z,-y+1/4,-x+1/4
47 -z+1/4,y,-x+1/4
48 -z+1/4,-y+1/4,x
49 x,y+1/2,z+1/2
50 x,-y+3/4,-z+3/4
51 -x+1/4,y+1/2,-z+3/4
52 -x+1/4,-y+3/4,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+3/4,-x+3/4
55 -y+1/4,z+1/2,-x+3/4
56 -y+1/4,-z+3/4,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+3/4,-y+3/4
59 -z+1/4,x+1/2,-y+3/4
60 -z+1/4,-x+3/4,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+3/4,z+3/4
63 y+1/4,-x+1/2,z+3/4
64 y+1/4,x+3/4,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+3/4,y+3/4
67 x+1/4,-z+1/2,y+3/4
68 x+1/4,z+3/4,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+3/4,x+3/4
71 z+1/4,-y+1/2,x+3/4
72 z+1/4,y+3/4,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+3/4,z+3/4
75 x+1/4,-y+1/2,z+3/4
76 x+1/4,y+3/4,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+3/4,x+3/4
79 y+1/4,-z+1/2,x+3/4
80 y+1/4,z+3/4,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+3/4,y+3/4
83 z+1/4,-x+1/2,y+3/4
84 z+1/4,x+3/4,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+3/4,-z+3/4
87 -y+1/4,x+1/2,-z+3/4
88 -y+1/4,-x+3/4,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+3/4,-y+3/4
91 -x+1/4,z+1/2,-y+3/4
92 -x+1/4,-z+3/4,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+3/4,-x+3/4
95 -z+1/4,y+1/2,-x+3/4
96 -z+1/4,-y+3/4,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y+1/4,-z+3/4
99 -x+3/4,y,-z+3/4
100 -x+3/4,-y+1/4,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z+1/4,-x+3/4
103 -y+3/4,z,-x+3/4
104 -y+3/4,-z+1/4,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x+1/4,-y+3/4
107 -z+3/4,x,-y+3/4
108 -z+3/4,-x+1/4,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x+1/4,z+3/4
111 y+3/4,-x,z+3/4
112 y+3/4,x+1/4,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z+1/4,y+3/4
115 x+3/4,-z,y+3/4
116 x+3/4,z+1/4,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y+1/4,x+3/4
119 z+3/4,-y,x+3/4
120 z+3/4,y+1/4,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y+1/4,z+3/4
123 x+3/4,-y,z+3/4
124 x+3/4,y+1/4,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z+1/4,x+3/4
127 y+3/4,-z,x+3/4
128 y+3/4,z+1/4,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x+1/4,y+3/4
131 z+3/4,-x,y+3/4
132 z+3/4,x+1/4,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x+1/4,-z+3/4
135 -y+3/4,x,-z+3/4
136 -y+3/4,-x+1/4,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z+1/4,-y+3/4
139 -x+3/4,z,-y+3/4
140 -x+3/4,-z+1/4,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y+1/4,-x+3/4
143 -z+3/4,y,-x+3/4
144 -z+3/4,-y+1/4,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+3/4,-z+1/4
147 -x+3/4,y+1/2,-z+1/4
148 -x+3/4,-y+3/4,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+3/4,-x+1/4
151 -y+3/4,z+1/2,-x+1/4
152 -y+3/4,-z+3/4,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+3/4,-y+1/4
155 -z+3/4,x+1/2,-y+1/4
156 -z+3/4,-x+3/4,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+3/4,z+1/4
159 y+3/4,-x+1/2,z+1/4
160 y+3/4,x+3/4,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+3/4,y+1/4
163 x+3/4,-z+1/2,y+1/4
164 x+3/4,z+3/4,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+3/4,x+1/4
167 z+3/4,-y+1/2,x+1/4
168 z+3/4,y+3/4,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+3/4,z+1/4
171 x+3/4,-y+1/2,z+1/4
172 x+3/4,y+3/4,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+3/4,x+1/4
175 y+3/4,-z+1/2,x+1/4
176 y+3/4,z+3/4,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+3/4,y+1/4
179 z+3/4,-x+1/2,y+1/4
180 z+3/4,x+3/4,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+3/4,-z+1/4
183 -y+3/4,x+1/2,-z+1/4
184 -y+3/4,-x+3/4,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+3/4,-y+1/4
187 -x+3/4,z+1/2,-y+1/4
188 -x+3/4,-z+3/4,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+3/4,-x+1/4
191 -z+3/4,y+1/2,-x+1/4
192 -z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1 C    8 a 0.12500 0.12500 0.12500 1.00000
```

Diamond (A4): A_cF8_227_a - POSCAR

```
A_cF8_227_a & a --params=3.55 & Fd(-3)m    O_h^7 #227 (a) & cF8 & A4 & C
      ↪ & diamond & W. H. Bragg and W. L. Bragg, Proc. R. Soc. A Math.
      ↪ Phys. Eng. Sci. 89, 277-291 (1913)
   1.0000000000000000
   0.00000000000000    1.77500000000000    1.77500000000000
   1.77500000000000    0.00000000000000    1.77500000000000
   1.77500000000000    1.77500000000000    0.00000000000000
    C
    2
Direct
   0.12500000000000    0.12500000000000    0.12500000000000    C    (8a)
   0.87500000000000    0.87500000000000    0.87500000000000    C    (8a)
```

Spinel (Al_2MgO_4, $H1_1$): A2BC4_cF56_227_d_a_e - CIF

```
# CIF file

data_findsym-output
```

```
_audit_creation_method FINDSYM

_chemical_name_mineral 'Spinel'
_chemical_formula_sum 'Al2 Mg O4'

loop_
_publ_author_name
 'Roderick J. Hill'
 'James R. Craig'
 'G. V. Gibbs'
_journal_name_full
;
Physics and Chemistry of Minerals
;
_journal_volume 4
_journal_year 1979
_journal_page_first 317
_journal_page_last 339
_publ_Section_title
;
 Systematics of the Spinel Structure Type
;

_aflow_proto 'A2BC4_cF56_227_d_a_e'
_aflow_params 'a,x3'
_aflow_params_values '8.0832,0.7376'
_aflow_Strukturbericht 'H1_1'
_aflow_Pearson 'cF56'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a     8.08320
_cell_length_b     8.08320
_cell_length_c     8.08320
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/4,-z+1/4
3 -x+1/4,y,-z+1/4
4 -x+1/4,-y+1/4,z
5 y,z,x
6 y,-z+1/4,-x+1/4
7 -y+1/4,z,-x+1/4
8 -y+1/4,-z+1/4,x
9 z,x,y
10 z,-x+1/4,-y+1/4
11 -z+1/4,x,-y+1/4
12 -z+1/4,-x+1/4,y
13 -y,-x,-z
14 -y,x+1/4,z+1/4
15 y+1/4,-x,z+1/4
16 y+1/4,x+1/4,-z
17 -x,-z,-y
18 -x,z+1/4,y+1/4
19 x+1/4,-z,y+1/4
20 x+1/4,z+1/4,-y
21 -z,-y,-x
22 -z,y+1/4,x+1/4
23 z+1/4,-y,x+1/4
24 z+1/4,y+1/4,-x
25 -x,-y,-z
26 -x,y+1/4,z+1/4
27 x+1/4,-y,z+1/4
28 x+1/4,y+1/4,-z
29 -y,-z,-x
30 -y,z+1/4,x+1/4
31 y+1/4,-z,x+1/4
32 y+1/4,z+1/4,-x
33 -z,-x,-y
34 -z,x+1/4,y+1/4
35 z+1/4,-x,y+1/4
36 z+1/4,x+1/4,-y
37 y,x,z
38 y,-x+1/4,-z+1/4
39 -y+1/4,x,-z+1/4
40 -y+1/4,-x+1/4,z
41 x,z,y
42 x,-z+1/4,-y+1/4
43 -x+1/4,z,-y+1/4
44 -x+1/4,-z+1/4,y
45 z,y,x
46 z,-y+1/4,-x+1/4
47 -z+1/4,y,-x+1/4
48 -z+1/4,-y+1/4,x
49 x,y+1/2,z+1/2
50 x,-y+3/4,-z+3/4
51 -x+1/4,y+1/2,-z+3/4
52 -x+1/4,-y+3/4,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+3/4,-x+3/4
55 -y+1/4,z+1/2,-x+3/4
56 -y+1/4,-z+3/4,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+3/4,-y+3/4
59 -z+1/4,x+1/2,-y+3/4
60 -z+1/4,-x+3/4,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+3/4,z+3/4
63 y+1/4,-x+1/2,z+3/4
64 y+1/4,x+3/4,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+3/4,y+3/4
67 x+1/4,-z+1/2,y+3/4
68 x+1/4,z+3/4,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+3/4,x+3/4
71 z+1/4,-y+1/2,x+3/4
72 z+1/4,y+3/4,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+3/4,z+3/4
75 x+1/4,-y+1/2,z+3/4
76 x+1/4,y+3/4,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+3/4,x+3/4
79 y+1/4,-z+1/2,x+3/4
80 y+1/4,z+3/4,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+3/4,y+3/4
83 z+1/4,-x+1/2,y+3/4
84 z+1/4,x+3/4,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+3/4,-z+3/4
87 -y+1/4,x+1/2,-z+3/4
88 -y+1/4,-x+3/4,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+3/4,-y+3/4
91 -x+1/4,z+1/2,-y+3/4
92 -x+1/4,-z+3/4,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+3/4,-x+3/4
95 -z+1/4,y+1/2,-x+3/4
96 -z+1/4,-y+3/4,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y+1/4,-z+3/4
99 -x+3/4,y,-z+3/4
100 -x+3/4,-y+1/4,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z+1/4,-x+3/4
103 -y+3/4,z,-x+3/4
104 -y+3/4,-z+1/4,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x+1/4,-y+3/4
107 -z+3/4,x,-y+3/4
108 -z+3/4,-x+1/4,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x+1/4,z+3/4
111 y+3/4,-x,z+3/4
112 y+3/4,x+1/4,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z+1/4,y+3/4
115 x+3/4,-z,y+3/4
116 x+3/4,z+1/4,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y+1/4,x+3/4
119 z+3/4,-y,x+3/4
120 z+3/4,y+1/4,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y+1/4,z+3/4
123 x+3/4,-y,z+3/4
124 x+3/4,y+1/4,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z+1/4,x+3/4
127 y+3/4,-z,x+3/4
128 y+3/4,z+1/4,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x+1/4,y+3/4
131 z+3/4,-x,y+3/4
132 z+3/4,x+1/4,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x+1/4,-z+3/4
135 -y+3/4,x,-z+3/4
136 -y+3/4,-x+1/4,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z+1/4,-y+3/4
139 -x+3/4,z,-y+3/4
140 -x+3/4,-z+1/4,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y+1/4,-x+3/4
143 -z+3/4,y,-x+3/4
144 -z+3/4,-y+1/4,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+3/4,-z+1/4
147 -x+3/4,y+1/2,-z+1/4
148 -x+3/4,-y+3/4,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+3/4,-x+1/4
151 -y+3/4,z+1/2,-x+1/4
152 -y+3/4,-z+3/4,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+3/4,-y+1/4
155 -z+3/4,x+1/2,-y+1/4
156 -z+3/4,-x+3/4,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+3/4,z+1/4
159 y+3/4,-x+1/2,z+1/4
160 y+3/4,x+3/4,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+3/4,y+1/4
163 x+3/4,-z+1/2,y+1/4
164 x+3/4,z+3/4,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+3/4,x+1/4
167 z+3/4,-y+1/2,x+1/4
```

```
168 z+3/4,y+3/4,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+3/4,z+1/4
171 x+3/4,-y+1/2,z+1/4
172 x+3/4,y+3/4,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+3/4,x+1/4
175 y+3/4,-z+1/2,x+1/4
176 y+3/4,z+3/4,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+3/4,y+1/4
179 z+3/4,-x+1/2,y+1/4
180 z+3/4,x+3/4,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+3/4,-z+1/4
183 -y+3/4,x+1/2,-z+1/4
184 -y+3/4,-x+3/4,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+3/4,-y+1/4
187 -x+3/4,z+1/2,-y+1/4
188 -x+3/4,-z+3/4,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+3/4,-x+1/4
191 -z+3/4,y+1/2,-x+1/4
192 -z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Mg1 Mg   8 a 0.12500 0.12500 0.12500 1.00000
Al1 Al  16 d 0.50000 0.50000 0.50000 1.00000
O1  O   32 e 0.73760 0.73760 0.73760 1.00000
```

Spinel (Al_2MgO_4, $H1_1$): A2BC4_cF56_227_d_a_e - POSCAR

```
A2BC4_cF56_227_d_a_e & a,x3 --params=8.0832,0.7376 & Fd(-3)m   O_h^7 #
    ↪ 227 (ade) & cF56 & H1_1 & Al2MgO4 & Spinel & R. J. Hill, J. R.
    ↪ Craig and G. V. Gibbs, Phys. Chem. Minerals 4, 317-339 (1979)
   1.0000000000000000
   0.00000000000000    4.04160000000000    4.04160000000000
   4.04160000000000    0.00000000000000    4.04160000000000
   4.04160000000000    4.04160000000000    0.00000000000000
   Al   Mg   O
    4    2   8
Direct
   0.00000000000000    0.50000000000000    0.50000000000000    Al   (16d)
   0.50000000000000    0.00000000000000    0.50000000000000    Al   (16d)
   0.50000000000000    0.50000000000000    0.00000000000000    Al   (16d)
   0.50000000000000    0.50000000000000    0.50000000000000    Al   (16d)
   0.12500000000000    0.12500000000000    0.12500000000000    Mg    (8a)
   0.87500000000000    0.87500000000000    0.87500000000000    Mg    (8a)
   0.26240000000000    0.26240000000000    0.26240000000000    O   (32e)
   0.26240000000000    0.26240000000000    0.71280000000000    O   (32e)
  -0.26240000000000    0.28720000000000    0.73760000000000    O   (32e)
   0.26240000000000    0.71280000000000    0.26240000000000    O   (32e)
   0.28720000000000    0.73760000000000   -0.26240000000000    O   (32e)
   0.71280000000000    0.26240000000000    0.26240000000000    O   (32e)
   0.73760000000000   -0.26240000000000    0.28720000000000    O   (32e)
   0.73760000000000    0.73760000000000    0.73760000000000    O   (32e)
```

CTi_2: AB2_cF48_227_c_e - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'C Ti2'

loop_
_publ_author_name
 'H. Goretzki'
_journal_name_full
;
Physica Status Solidi B
;
_journal_volume 20
_journal_year 1967
_journal_page_first K141
_journal_page_last K143
_publ_Section_title
;
 Neutron Diffraction Studies on Titanium-Carbon and Zirconium-Carbon
    ↪ Alloys
;

_aflow_proto 'AB2_cF48_227_c_e'
_aflow_params 'a,x2'
_aflow_params_values '8.6,0.245'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cF48'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a      8.60000
_cell_length_b      8.60000
_cell_length_c      8.60000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y+1/4,-z+1/4
3 -x+1/4,y,-z+1/4
4 -x+1/4,-y+1/4,z
5 y,z,x
6 y,-z+1/4,-x+1/4
7 -y+1/4,z,-x+1/4
8 -y+1/4,-z+1/4,x
9 z,x,y
10 z,-x+1/4,-y+1/4
11 -z+1/4,x,-y+1/4
12 -z+1/4,-x+1/4,y
13 -y,-x,-z
14 -y,x+1/4,z+1/4
15 y+1/4,-x,z+1/4
16 y+1/4,x+1/4,-z
17 -x,-z,-y
18 -x,z+1/4,y+1/4
19 x+1/4,-z,y+1/4
20 x+1/4,z+1/4,-y
21 -z,-y,-x
22 -z,y+1/4,x+1/4
23 z+1/4,-y,x+1/4
24 z+1/4,y+1/4,-x
25 -x,-y,-z
26 -x,y+1/4,z+1/4
27 x+1/4,-y,z+1/4
28 x+1/4,y+1/4,-z
29 -y,-z,-x
30 -y,z+1/4,x+1/4
31 y+1/4,-z,x+1/4
32 y+1/4,z+1/4,-x
33 -z,-x,-y
34 -z,x+1/4,y+1/4
35 z+1/4,-x,y+1/4
36 z+1/4,x+1/4,-y
37 y,x,z
38 y,-x+1/4,-z+1/4
39 -y+1/4,x,-z+1/4
40 -y+1/4,-x+1/4,z
41 x,z,y
42 x,-z+1/4,-y+1/4
43 -x+1/4,z,-y+1/4
44 -x+1/4,-z+1/4,y
45 z,y,x
46 z,-y+1/4,-x+1/4
47 -z+1/4,y,-x+1/4
48 -z+1/4,-y+1/4,x
49 x,y+1/2,z+1/2
50 x,-y+3/4,-z+3/4
51 -x+1/4,y+1/2,-z+3/4
52 -x+1/4,-y+3/4,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+3/4,-x+3/4
55 -y+1/4,z+1/2,-x+3/4
56 -y+1/4,-z+3/4,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+3/4,-y+3/4
59 -z+1/4,x+1/2,-y+3/4
60 -z+1/4,-x+3/4,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+3/4,z+3/4
63 y+1/4,-x+1/2,z+3/4
64 y+1/4,x+3/4,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+3/4,y+3/4
67 x+1/4,-z+1/2,y+3/4
68 x+1/4,z+3/4,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+3/4,x+3/4
71 z+1/4,-y+1/2,x+3/4
72 z+1/4,y+3/4,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+3/4,z+3/4
75 x+1/4,-y+1/2,z+3/4
76 x+1/4,y+3/4,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+3/4,x+3/4
79 y+1/4,-z+1/2,x+3/4
80 y+1/4,z+3/4,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+3/4,y+3/4
83 z+1/4,-x+1/2,y+3/4
84 z+1/4,x+3/4,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+3/4,-z+3/4
87 -y+1/4,x+1/2,-z+3/4
88 -y+1/4,-x+3/4,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+3/4,-y+3/4
91 -x+1/4,z+1/2,-y+3/4
92 -x+1/4,-z+3/4,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+3/4,-x+3/4
95 -z+1/4,y+1/2,-x+3/4
96 -z+1/4,-y+3/4,x+1/2
97 x+1/2,y,z+1/2
```

```
98  x+1/2,-y+1/4,-z+3/4
99  -x+3/4,y,-z+3/4
100  -x+3/4,-y+1/4,z+1/2
101  y+1/2,z,x+1/2
102  y+1/2,-z+1/4,-x+3/4
103  -y+3/4,z,-x+3/4
104  -y+3/4,-z+1/4,x+1/2
105  z+1/2,x,y+1/2
106  z+1/2,-x+1/4,-y+3/4
107  -z+3/4,x,-y+3/4
108  -z+3/4,-x+1/4,y+1/2
109  -y+1/2,-x,-z+1/2
110  -y+1/2,x+1/4,z+3/4
111  y+3/4,-x,z+3/4
112  y+3/4,x+1/4,-z+1/2
113  -x+1/2,-z,-y+1/2
114  -x+1/2,z+1/4,y+3/4
115  x+3/4,-z,y+3/4
116  x+3/4,z+1/4,-y+1/2
117  -z+1/2,-y,-x+1/2
118  -z+1/2,y+1/4,x+3/4
119  z+3/4,-y,x+3/4
120  z+3/4,y+1/4,-x+1/2
121  -x+1/2,-y,-z+1/2
122  -x+1/2,y+1/4,z+3/4
123  x+3/4,-y,z+3/4
124  x+3/4,y+1/4,-z+1/2
125  -y+1/2,-z,-x+1/2
126  -y+1/2,z+1/4,x+3/4
127  y+3/4,-z,x+3/4
128  y+3/4,z+1/4,-x+1/2
129  -z+1/2,-x,-y+1/2
130  -z+1/2,x+1/4,y+3/4
131  z+3/4,-x,y+3/4
132  z+3/4,x+1/4,-y+1/2
133  y+1/2,x,z+1/2
134  y+1/2,-x+1/4,-z+3/4
135  -y+3/4,x,-z+3/4
136  -y+3/4,-x+1/4,z+1/2
137  x+1/2,z,y+1/2
138  x+1/2,-z+1/4,-y+3/4
139  -x+3/4,z,-y+3/4
140  -x+3/4,-z+1/4,y+1/2
141  z+1/2,y,x+1/2
142  z+1/2,-y+1/4,-x+3/4
143  -z+3/4,y,-x+3/4
144  -z+3/4,-y+1/4,x+1/2
145  x+1/2,y+1/2,z
146  x+1/2,-y+3/4,-z+1/4
147  -x+3/4,y+1/2,-z+1/4
148  -x+3/4,-y+3/4,z
149  y+1/2,z+1/2,x
150  y+1/2,-z+3/4,-x+1/4
151  -y+3/4,z+1/2,-x+1/4
152  -y+3/4,-z+3/4,x
153  z+1/2,x+1/2,y
154  z+1/2,-x+3/4,-y+1/4
155  -z+3/4,x+1/2,-y+1/4
156  -z+3/4,-x+3/4,y
157  -y+1/2,-x+1/2,-z
158  -y+1/2,x+3/4,z+1/4
159  y+3/4,-x+1/2,z+1/4
160  y+3/4,x+3/4,-z
161  -x+1/2,-z+1/2,-y
162  -x+1/2,z+3/4,y+1/4
163  x+3/4,-z+1/2,y+1/4
164  x+3/4,z+3/4,-y
165  -z+1/2,-y+1/2,-x
166  -z+1/2,y+3/4,x+1/4
167  z+3/4,-y+1/2,x+1/4
168  z+3/4,y+3/4,-x
169  -x+1/2,-y+1/2,-z
170  -x+1/2,y+3/4,z+1/4
171  x+3/4,-y+1/2,z+1/4
172  x+3/4,y+3/4,-z
173  -y+1/2,-z+1/2,-x
174  -y+1/2,z+3/4,x+1/4
175  y+3/4,-z+1/2,x+1/4
176  y+3/4,z+3/4,-x
177  -z+1/2,-x+1/2,-y
178  -z+1/2,x+3/4,y+1/4
179  z+3/4,-x+1/2,y+1/4
180  z+3/4,x+3/4,-y
181  y+1/2,x+1/2,z
182  y+1/2,-x+3/4,-z+1/4
183  -y+3/4,x+1/2,-z+1/4
184  -y+3/4,-x+3/4,z
185  x+1/2,z+1/2,y
186  x+1/2,-z+3/4,-y+1/4
187  -x+3/4,z+1/2,-y+1/4
188  -x+3/4,-z+3/4,y
189  z+1/2,y+1/2,x
190  z+1/2,-y+3/4,-x+1/4
191  -z+3/4,y+1/2,-x+1/4
192  -z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1   C    16 c  0.00000  0.00000  0.00000  1.00000
Ti1  Ti   32 e  0.24500  0.24500  0.24500  1.00000
```

CTi_2: AB2_cF48_227_c_e - POSCAR

```
AB2_cF48_227_c_e & a,x2 --params=8.6,0.245 & Fd(-3)m      O_h^7 #227 (ce)
    ↪ & cF48 & & CTi2 & & H. Goretzki, Phys. Status Solidi B 20,
    ↪ K141-K143 (1967)
   1.0000000000000000
   0.00000000000000    4.30000000000000    4.30000000000000
   4.30000000000000    0.00000000000000    4.30000000000000
   4.30000000000000    4.30000000000000    0.00000000000000
    C    Ti
    4    8
Direct
   0.00000000000000    0.00000000000000    0.00000000000000    C    (16c)
   0.00000000000000   -0.00000000000000    0.50000000000000    C    (16c)
  -0.00000000000000    0.50000000000000    0.00000000000000    C    (16c)
   0.50000000000000    0.00000000000000    0.00000000000000    C    (16c)
   0.23500000000000   -0.24500000000000   -0.24500000000000   Ti    (32e)
  -0.23500000000000    0.24500000000000    0.24500000000000   Ti    (32e)
   0.24500000000000   -0.23500000000000    0.24500000000000   Ti    (32e)
  -0.24500000000000    0.23500000000000   -0.24500000000000   Ti    (32e)
   0.24500000000000    0.24500000000000   -0.23500000000000   Ti    (32e)
  -0.24500000000000   -0.24500000000000    0.23500000000000   Ti    (32e)
   0.24500000000000    0.24500000000000    0.24500000000000   Ti    (32e)
  -0.24500000000000   -0.24500000000000   -0.24500000000000   Ti    (32e)
```

Fe_3W_3C: AB3C3_cF112_227_c_de_f - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Fe3 W3 C'

loop_
_publ_author_name
 'Qi-Bin Yang'
 'Sten Andersson'
_journal_name_full
;
Acta Crystallographica B
;
_journal_volume 43
_journal_year 1987
_journal_page_first 1
_journal_page_last 14
_publ_Section_title
;
 Application of coincidence site lattices for crystal structure
    ↪ description. Part I: $\Sigma = 3$
;

_aflow_proto 'AB3C3_cF112_227_c_de_f'
_aflow_params 'a,x3,x4'
_aflow_params_values '11.087,0.7047,0.323'
_aflow_Strukturbericht 'E9_3'
_aflow_Pearson 'cF112'

_symmetry_space_group_name_Hall "-F 4vw 2vw 3 Fd(-3)m"
_symmetry_space_group_name_H-M "F d -3 m:2"
_symmetry_Int_Tables_number 227

_cell_length_a     11.08700
_cell_length_b     11.08700
_cell_length_c     11.08700
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1  x,y,z
2  x,-y+1/4,-z+1/4
3  -x+1/4,y,-z+1/4
4  -x+1/4,-y+1/4,z
5  y,z,x
6  y,-z+1/4,-x+1/4
7  -y+1/4,z,-x+1/4
8  -y+1/4,-z+1/4,x
9  z,x,y
10  z,-x+1/4,-y+1/4
11  -z+1/4,x,-y+1/4
12  -z+1/4,-x+1/4,y
13  -y,-x,-z
14  -y,x+1/4,z+1/4
15  y+1/4,-x,z+1/4
16  y+1/4,x+1/4,-z
17  -x,-z,-y
18  -x,z+1/4,y+1/4
19  x+1/4,-z,y+1/4
20  x+1/4,z+1/4,-y
21  -z,-y,-x
22  -z,y+1/4,x+1/4
23  z+1/4,-y,x+1/4
24  z+1/4,y+1/4,-x
25  -x,-y,-z
26  -x,y+1/4,z+1/4
27  x+1/4,-y,z+1/4
28  x+1/4,y+1/4,-z
29  -y,-z,-x
```

```
30 -y,z+1/4,x+1/4
31 y+1/4,-z,x+1/4
32 y+1/4,z+1/4,-x
33 -z,-x,-y
34 -z,x+1/4,y+1/4
35 z+1/4,-x,y+1/4
36 z+1/4,x+1/4,-y
37 y,x,z
38 y,-x+1/4,-z+1/4
39 -y+1/4,x,-z+1/4
40 -y+1/4,-x+1/4,z
41 x,z,y
42 x,-z+1/4,-y+1/4
43 -x+1/4,z,-y+1/4
44 -x+1/4,-z+1/4,y
45 z,y,x
46 z,-y+1/4,-x+1/4
47 -z+1/4,y,-x+1/4
48 -z+1/4,-y+1/4,x
49 x,y+1/2,z+1/2
50 x,-y+3/4,-z+3/4
51 -x+1/4,y+1/2,-z+3/4
52 -x+1/4,-y+3/4,z+1/2
53 y,z+1/2,x+1/2
54 y,-z+3/4,-x+3/4
55 -y+1/4,z+1/2,-x+3/4
56 -y+1/4,-z+3/4,x+1/2
57 z,x+1/2,y+1/2
58 z,-x+3/4,-y+3/4
59 -z+1/4,x+1/2,-y+3/4
60 -z+1/4,-x+3/4,y+1/2
61 -y,-x+1/2,-z+1/2
62 -y,x+3/4,z+3/4
63 y+1/4,-x+1/2,z+3/4
64 y+1/4,x+3/4,-z+1/2
65 -x,-z+1/2,-y+1/2
66 -x,z+3/4,y+3/4
67 x+1/4,-z+1/2,y+3/4
68 x+1/4,z+3/4,-y+1/2
69 -z,-y+1/2,-x+1/2
70 -z,y+3/4,x+3/4
71 z+1/4,-y+1/2,x+3/4
72 z+1/4,y+3/4,-x+1/2
73 -x,-y+1/2,-z+1/2
74 -x,y+3/4,z+3/4
75 x+1/4,-y+1/2,z+3/4
76 x+1/4,y+3/4,-z+1/2
77 -y,-z+1/2,-x+1/2
78 -y,z+3/4,x+3/4
79 y+1/4,-z+1/2,x+3/4
80 y+1/4,z+3/4,-x+1/2
81 -z,-x+1/2,-y+1/2
82 -z,x+3/4,y+3/4
83 z+1/4,-x+1/2,y+3/4
84 z+1/4,x+3/4,-y+1/2
85 y,x+1/2,z+1/2
86 y,-x+3/4,-z+3/4
87 -y+1/4,x+1/2,-z+3/4
88 -y+1/4,-x+3/4,z+1/2
89 x,z+1/2,y+1/2
90 x,-z+3/4,-y+3/4
91 -x+1/4,z+1/2,-y+3/4
92 -x+1/4,-z+3/4,y+1/2
93 z,y+1/2,x+1/2
94 z,-y+3/4,-x+3/4
95 -z+1/4,y+1/2,-x+3/4
96 -z+1/4,-y+3/4,x+1/2
97 x+1/2,y,z+1/2
98 x+1/2,-y+1/4,-z+3/4
99 -x+3/4,y,-z+3/4
100 -x+3/4,-y+1/4,z+1/2
101 y+1/2,z,x+1/2
102 y+1/2,-z+1/4,-x+3/4
103 -y+3/4,z,-x+3/4
104 -y+3/4,-z+1/4,x+1/2
105 z+1/2,x,y+1/2
106 z+1/2,-x+1/4,-y+3/4
107 -z+3/4,x,-y+3/4
108 -z+3/4,-x+1/4,y+1/2
109 -y+1/2,-x,-z+1/2
110 -y+1/2,x+1/4,z+3/4
111 y+3/4,-x,z+3/4
112 y+3/4,x+1/4,-z+1/2
113 -x+1/2,-z,-y+1/2
114 -x+1/2,z+1/4,y+3/4
115 x+3/4,-z,y+3/4
116 x+3/4,z+1/4,-y+1/2
117 -z+1/2,-y,-x+1/2
118 -z+1/2,y+1/4,x+3/4
119 z+3/4,-y,x+3/4
120 z+3/4,y+1/4,-x+1/2
121 -x+1/2,-y,-z+1/2
122 -x+1/2,y+1/4,z+3/4
123 x+3/4,-y,z+3/4
124 x+3/4,y+1/4,-z+1/2
125 -y+1/2,-z,-x+1/2
126 -y+1/2,z+1/4,x+3/4
127 y+3/4,-z,x+3/4
128 y+3/4,z+1/4,-x+1/2
129 -z+1/2,-x,-y+1/2
130 -z+1/2,x+1/4,y+3/4
131 z+3/4,-x,y+3/4
132 z+3/4,x+1/4,-y+1/2
133 y+1/2,x,z+1/2
134 y+1/2,-x+1/4,-z+3/4
135 -y+3/4,x,-z+3/4
136 -y+3/4,-x+1/4,z+1/2
137 x+1/2,z,y+1/2
138 x+1/2,-z+1/4,-y+3/4
139 -x+3/4,z,-y+3/4
140 -x+3/4,-z+1/4,y+1/2
141 z+1/2,y,x+1/2
142 z+1/2,-y+1/4,-x+3/4
143 -z+3/4,y,-x+3/4
144 -z+3/4,-y+1/4,x+1/2
145 x+1/2,y+1/2,z
146 x+1/2,-y+3/4,-z+1/4
147 -x+3/4,y+1/2,-z+1/4
148 -x+3/4,-y+3/4,z
149 y+1/2,z+1/2,x
150 y+1/2,-z+3/4,-x+1/4
151 -y+3/4,z+1/2,-x+1/4
152 -y+3/4,-z+3/4,x
153 z+1/2,x+1/2,y
154 z+1/2,-x+3/4,-y+1/4
155 -z+3/4,x+1/2,-y+1/4
156 -z+3/4,-x+3/4,y
157 -y+1/2,-x+1/2,-z
158 -y+1/2,x+3/4,z+1/4
159 y+3/4,-x+1/2,z+1/4
160 y+3/4,x+3/4,-z
161 -x+1/2,-z+1/2,-y
162 -x+1/2,z+3/4,y+1/4
163 x+3/4,-z+1/2,y+1/4
164 x+3/4,z+3/4,-y
165 -z+1/2,-y+1/2,-x
166 -z+1/2,y+3/4,x+1/4
167 z+3/4,-y+1/2,x+1/4
168 z+3/4,y+3/4,-x
169 -x+1/2,-y+1/2,-z
170 -x+1/2,y+3/4,z+1/4
171 x+3/4,-y+1/2,z+1/4
172 x+3/4,y+3/4,-z
173 -y+1/2,-z+1/2,-x
174 -y+1/2,z+3/4,x+1/4
175 y+3/4,-z+1/2,x+1/4
176 y+3/4,z+3/4,-x
177 -z+1/2,-x+1/2,-y
178 -z+1/2,x+3/4,y+1/4
179 z+3/4,-x+1/2,y+1/4
180 z+3/4,x+3/4,-y
181 y+1/2,x+1/2,z
182 y+1/2,-x+3/4,-z+1/4
183 -y+3/4,x+1/2,-z+1/4
184 -y+3/4,-x+3/4,z
185 x+1/2,z+1/2,y
186 x+1/2,-z+3/4,-y+1/4
187 -x+3/4,z+1/2,-y+1/4
188 -x+3/4,-z+3/4,y
189 z+1/2,y+1/2,x
190 z+1/2,-y+3/4,-x+1/4
191 -z+3/4,y+1/2,-x+1/4
192 -z+3/4,-y+3/4,x

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
C1  C   16 c 0.00000 0.00000 0.00000 1.00000
Fe1 Fe  16 d 0.50000 0.50000 0.50000 1.00000
Fe2 Fe  32 e 0.70470 0.70470 0.70470 1.00000
W1  W   48 f 0.32300 0.12500 0.12500 1.00000
```

Fe_3W_3C: AB3C3_cF112_227_c_de_f - POSCAR

```
AB3C3_cF112_227_c_de_f & a,x3,x4 --params=11.087,0.7047,0.323 & Fd(-3)m
    ↪ O_h^7 #227 (cdef) & cF112 & E9_3 & Fe3W3C & & Q.-B. Yang and
    ↪ S. Andersson, Acta Cryst. B 43, 1-14 (1987)
   1.0000000000000000
   0.00000000000000   5.54350000000000   5.54350000000000
   5.54350000000000   0.00000000000000   5.54350000000000
   5.54350000000000   5.54350000000000   0.00000000000000
    C    Fe    W
    4    12    12
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   C   (16c)
  -0.00000000000000   0.00000000000000   0.50000000000000   C   (16c)
   0.00000000000000   0.50000000000000  -0.00000000000000   C   (16c)
   0.50000000000000  -0.00000000000000   0.00000000000000   C   (16c)
   0.00000000000000   0.50000000000000   0.50000000000000  Fe   (16d)
   0.50000000000000   0.00000000000000   0.50000000000000  Fe   (16d)
   0.50000000000000   0.50000000000000   0.00000000000000  Fe   (16d)
   0.50000000000000   0.50000000000000   0.50000000000000  Fe   (16d)
   0.29530000000000   0.29530000000000   0.29530000000000  Fe   (32e)
   0.29530000000000   0.29530000000000  -0.38590000000000  Fe   (32e)
   0.29530000000000  -0.38590000000000   0.29530000000000  Fe   (32e)
  -0.29530000000000   0.70470000000000   0.38590000000000  Fe   (32e)
  -0.38590000000000   0.29530000000000   0.29530000000000  Fe   (32e)
   0.38590000000000  -0.29530000000000   0.70470000000000  Fe   (32e)
   0.70470000000000   0.38590000000000  -0.29530000000000  Fe   (32e)
   0.70470000000000   0.70470000000000   0.70470000000000  Fe   (32e)
  -0.07300000000000  -0.07300000000000   0.32300000000000   W   (48f)
   0.07300000000000   0.07300000000000   0.67700000000000   W   (48f)
  -0.07300000000000   0.32300000000000  -0.07300000000000   W   (48f)
   0.07300000000000   0.67700000000000   0.07300000000000   W   (48f)
```

```
  0.07300000000000   0.67700000000000   0.67700000000000   W   (48f)
  0.32300000000000  -0.07300000000000  -0.07300000000000   W   (48f)
  0.32300000000000   0.32300000000000   0.92700000000000   W   (48f)
  0.32300000000000   0.92700000000000   0.32300000000000   W   (48f)
  0.67700000000000   0.07300000000000   0.07300000000000   W   (48f)
  0.67700000000000   0.07300000000000   0.67700000000000   W   (48f)
  0.67700000000000   0.67700000000000   0.07300000000000   W   (48f)
  0.92700000000000   0.32300000000000   0.32300000000000   W   (48f)
```

Body-Centered Cubic (W, A2): A_cI2_229_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'Tungsten'
_chemical_formula_sum 'W'

loop_
_publ_author_name
 'Wheller P. Davey'
_journal_name_full
;
Physical Review
;
_journal_volume 26
_journal_year 1925
_journal_page_first 736
_journal_page_last 738
_publ_Section_title
;
 The Lattice Parameter and Density of Pure Tungsten
;

_aflow_proto 'A_cI2_229_a'
_aflow_params 'a'
_aflow_params_values '3.155'
_aflow_Strukturbericht 'A2'
_aflow_Pearson 'cI2'

_symmetry_space_group_name_Hall "-I 4 2 3"
_symmetry_space_group_name_H-M "I m -3 m"
_symmetry_Int_Tables_number 229

_cell_length_a    3.15500
_cell_length_b    3.15500
_cell_length_c    3.15500
_cell_angle_alpha 90.00000
_cell_angle_beta  90.00000
_cell_angle_gamma 90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x+1/2,y+1/2,z+1/2
50 x+1/2,-y+1/2,-z+1/2
51 -x+1/2,y+1/2,-z+1/2
52 -x+1/2,-y+1/2,z+1/2
53 y+1/2,z+1/2,x+1/2
54 y+1/2,-z+1/2,-x+1/2
55 -y+1/2,z+1/2,-x+1/2
56 -y+1/2,-z+1/2,x+1/2
57 z+1/2,x+1/2,y+1/2
58 z+1/2,-x+1/2,-y+1/2
59 -z+1/2,x+1/2,-y+1/2
60 -z+1/2,-x+1/2,y+1/2
61 -y+1/2,-x+1/2,-z+1/2
62 -y+1/2,x+1/2,z+1/2
63 y+1/2,-x+1/2,z+1/2
64 y+1/2,x+1/2,-z+1/2
65 -x+1/2,-z+1/2,-y+1/2
66 -x+1/2,z+1/2,y+1/2
67 x+1/2,-z+1/2,y+1/2
68 x+1/2,z+1/2,-y+1/2
69 -z+1/2,-y+1/2,-x+1/2
70 -z+1/2,y+1/2,x+1/2
71 z+1/2,-y+1/2,x+1/2
72 z+1/2,y+1/2,-x+1/2
73 -x+1/2,-y+1/2,-z+1/2
74 -x+1/2,y+1/2,z+1/2
75 x+1/2,-y+1/2,z+1/2
76 x+1/2,y+1/2,-z+1/2
77 -y+1/2,-z+1/2,-x+1/2
78 -y+1/2,z+1/2,x+1/2
79 y+1/2,-z+1/2,x+1/2
80 y+1/2,z+1/2,-x+1/2
81 -z+1/2,-x+1/2,-y+1/2
82 -z+1/2,x+1/2,y+1/2
83 z+1/2,-x+1/2,y+1/2
84 z+1/2,x+1/2,-y+1/2
85 y+1/2,x+1/2,z+1/2
86 y+1/2,-x+1/2,-z+1/2
87 -y+1/2,x+1/2,-z+1/2
88 -y+1/2,-x+1/2,z+1/2
89 x+1/2,z+1/2,y+1/2
90 x+1/2,-z+1/2,-y+1/2
91 -x+1/2,z+1/2,-y+1/2
92 -x+1/2,-z+1/2,y+1/2
93 z+1/2,y+1/2,x+1/2
94 z+1/2,-y+1/2,-x+1/2
95 -z+1/2,y+1/2,-x+1/2
96 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
W1 W   2 a 0.00000 0.00000 0.00000 1.00000
```

Body-Centered Cubic (W, A2): A_cI2_229_a - POSCAR

```
A_cI2_229_a & a --params=3.155 & Im(-3)m   O_h^9 #229 (a) & cI2 & A2 & W
      ↪ & & W. P. Davey, Phys. Rev. 26, 736-738 (1925)
   1.0000000000000000
  -1.57750000000000   1.57750000000000   1.57750000000000
   1.57750000000000  -1.57750000000000   1.57750000000000
   1.57750000000000   1.57750000000000  -1.57750000000000
    W
     1
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   W   (2a)
```

High-Pressure H_3S: A3B_cI8_229_b_a - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral 'High-temperature superconductor'
_chemical_formula_sum 'H3 S'

loop_
_publ_author_name
 'Defang Duan'
 'Yunxian Liu'
 'Fubo Tian'
 'Da Li'
 'Xiaoli Huang'
 'Zhonglong Zhao'
 'Hongyu Yu'
 'Bingbing Liu'
 'Wenjing Tian'
 'Tian Cui'
_journal_name_full
;
Scientific Reports
;
_journal_volume 4
_journal_year 2014
_journal_page_first 6968
_journal_page_last 6968
_publ_Section_title
;
 Pressure-induced metallization of dense (H$_2$S)$_2$H$_2$ with
      ↪ high-T$_c$ superconductivity
```

```
;

_aflow_proto 'A3B_cI8_229_b_a'
_aflow_params 'a'
_aflow_params_values '2.984'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI8'

_symmetry_space_group_name_Hall "-I 4 2 3"
_symmetry_space_group_name_H-M "I m -3 m"
_symmetry_Int_Tables_number 229

_cell_length_a      2.98400
_cell_length_b      2.98400
_cell_length_c      2.98400
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x+1/2,y+1/2,z+1/2
50 x+1/2,-y+1/2,-z+1/2
51 -x+1/2,y+1/2,-z+1/2
52 -x+1/2,-y+1/2,z+1/2
53 y+1/2,z+1/2,x+1/2
54 y+1/2,-z+1/2,-x+1/2
55 -y+1/2,z+1/2,-x+1/2
56 -y+1/2,-z+1/2,x+1/2
57 z+1/2,x+1/2,y+1/2
58 z+1/2,-x+1/2,-y+1/2
59 -z+1/2,x+1/2,-y+1/2
60 -z+1/2,-x+1/2,y+1/2
61 -y+1/2,-x+1/2,-z+1/2
62 -y+1/2,x+1/2,z+1/2
63 y+1/2,-x+1/2,z+1/2
64 y+1/2,x+1/2,-z+1/2
65 -x+1/2,-z+1/2,-y+1/2
66 -x+1/2,z+1/2,y+1/2
67 x+1/2,-z+1/2,y+1/2
68 x+1/2,z+1/2,-y+1/2
69 -z+1/2,-y+1/2,-x+1/2
70 -z+1/2,y+1/2,x+1/2
71 z+1/2,-y+1/2,x+1/2
72 z+1/2,y+1/2,-x+1/2
73 -x+1/2,-y+1/2,-z+1/2
74 -x+1/2,y+1/2,z+1/2
75 x+1/2,-y+1/2,z+1/2
76 x+1/2,y+1/2,-z+1/2
77 -y+1/2,-z+1/2,-x+1/2
78 -y+1/2,z+1/2,x+1/2
79 y+1/2,-z+1/2,x+1/2
80 y+1/2,z+1/2,-x+1/2
81 -z+1/2,-x+1/2,-y+1/2
82 -z+1/2,x+1/2,y+1/2
83 z+1/2,-x+1/2,y+1/2
84 z+1/2,x+1/2,-y+1/2
85 y+1/2,x+1/2,z+1/2
86 y+1/2,-x+1/2,-z+1/2
87 -y+1/2,x+1/2,-z+1/2
88 -y+1/2,-x+1/2,z+1/2
89 x+1/2,z+1/2,y+1/2
90 x+1/2,-z+1/2,-y+1/2
91 -x+1/2,z+1/2,-y+1/2
92 -x+1/2,-z+1/2,y+1/2
93 z+1/2,y+1/2,x+1/2
94 z+1/2,-y+1/2,-x+1/2
95 -z+1/2,y+1/2,-x+1/2
96 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
S1 S    2 a 0.00000 0.00000 0.00000 1.00000
H1 H    6 b 0.00000 0.50000 0.50000 1.00000
```

High-Pressure H_3S: A3B_cI8_229_b_a - POSCAR

```
A3B_cI8_229_b_a & a --params=2.984 & Im(-3)m    O_h^9 #229 (ab) & cI8 & &
      ↪ H3S & Predicted high pressure phase ~ 200 GPa & D. Duan et al.
      ↪ , Sci. Rep. 4, 6968 (2014)
   1.0000000000000000
  -1.49200000000000    1.49200000000000    1.49200000000000
   1.49200000000000   -1.49200000000000    1.49200000000000
   1.49200000000000    1.49200000000000   -1.49200000000000
    H     S
    3     1
Direct
   0.00000000000000    0.50000000000000    0.50000000000000     H     (6b)
   0.50000000000000    0.00000000000000    0.50000000000000     H     (6b)
   0.50000000000000    0.50000000000000    0.00000000000000     H     (6b)
   0.00000000000000    0.00000000000000    0.00000000000000     S     (2a)
```

Pt_3O_4: A4B3_cI14_229_c_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Pt3 O4'

loop_
_publ_author_name
 'Ernesto E. Galloni'
 'Angel E. Roffo Jr.'
_journal_name_full
;
The Journal of Chemical Physics
;
_journal_volume 9
_journal_year 1941
_journal_page_first 875
_journal_page_last 877
_publ_Section_title
;
 The Crystalline Structure of Pt$_3$O$_4$
;

_aflow_proto 'A4B3_cI14_229_c_b'
_aflow_params 'a'
_aflow_params_values '6.226'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI14'

_symmetry_space_group_name_Hall "-I 4 2 3"
_symmetry_space_group_name_H-M "I m -3 m"
_symmetry_Int_Tables_number 229

_cell_length_a      6.22600
_cell_length_b      6.22600
_cell_length_c      6.22600
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
```

```
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x+1/2,y+1/2,z+1/2
50 x+1/2,-y+1/2,-z+1/2
51 -x+1/2,y+1/2,-z+1/2
52 -x+1/2,-y+1/2,z+1/2
53 y+1/2,z+1/2,x+1/2
54 y+1/2,-z+1/2,-x+1/2
55 -y+1/2,z+1/2,-x+1/2
56 -y+1/2,-z+1/2,x+1/2
57 z+1/2,x+1/2,y+1/2
58 z+1/2,-x+1/2,-y+1/2
59 -z+1/2,x+1/2,-y+1/2
60 -z+1/2,-x+1/2,y+1/2
61 -y+1/2,-x+1/2,-z+1/2
62 -y+1/2,x+1/2,z+1/2
63 y+1/2,-x+1/2,z+1/2
64 y+1/2,x+1/2,-z+1/2
65 -x+1/2,-z+1/2,-y+1/2
66 -x+1/2,z+1/2,y+1/2
67 x+1/2,-z+1/2,y+1/2
68 x+1/2,z+1/2,-y+1/2
69 -z+1/2,-y+1/2,-x+1/2
70 -z+1/2,y+1/2,x+1/2
71 z+1/2,-y+1/2,x+1/2
72 z+1/2,y+1/2,-x+1/2
73 -x+1/2,-y+1/2,-z+1/2
74 -x+1/2,y+1/2,z+1/2
75 x+1/2,-y+1/2,z+1/2
76 x+1/2,y+1/2,-z+1/2
77 -y+1/2,-z+1/2,-x+1/2
78 -y+1/2,z+1/2,x+1/2
79 y+1/2,-z+1/2,x+1/2
80 y+1/2,z+1/2,-x+1/2
81 -z+1/2,-x+1/2,-y+1/2
82 -z+1/2,x+1/2,y+1/2
83 z+1/2,-x+1/2,y+1/2
84 z+1/2,x+1/2,-y+1/2
85 y+1/2,x+1/2,z+1/2
86 y+1/2,-x+1/2,-z+1/2
87 -y+1/2,x+1/2,-z+1/2
88 -y+1/2,-x+1/2,z+1/2
89 x+1/2,z+1/2,y+1/2
90 x+1/2,-z+1/2,-y+1/2
91 -x+1/2,z+1/2,-y+1/2
92 -x+1/2,-z+1/2,y+1/2
93 z+1/2,y+1/2,x+1/2
94 z+1/2,-y+1/2,-x+1/2
95 -z+1/2,y+1/2,-x+1/2
96 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Pt1  Pt    6 b 0.00000  0.50000  0.50000  1.00000
O1   O     8 c 0.25000  0.25000  0.25000  1.00000
```

Pt_3O_4: A4B3_cI14_229_c_b - POSCAR

```
A4B3_cI14_229_c_b & a --params=6.226 & Im(-3)m    O_h^9 #229 (bc) & cI14
    ↪ & & Pt3O4 & & E. E. Galloni and A. E. Roffo Jr., J. Chem. Phys.
    ↪ 9, 857-859 (1941)
   1.0000000000000000
  -3.11300000000000    3.11300000000000    3.11300000000000
   3.11300000000000   -3.11300000000000    3.11300000000000
   3.11300000000000    3.11300000000000   -3.11300000000000
    O    Pt
    4    3
Direct
   0.00000000000000   0.00000000000000   0.50000000000000   O   (8c)
   0.00000000000000   0.50000000000000   0.00000000000000   O   (8c)
   0.50000000000000   0.00000000000000   0.00000000000000   O   (8c)
   0.50000000000000   0.50000000000000   0.50000000000000   O   (8c)
   0.00000000000000   0.50000000000000   0.50000000000000   Pt  (6b)
   0.50000000000000   0.00000000000000   0.50000000000000   Pt  (6b)
   0.50000000000000   0.50000000000000   0.00000000000000   Pt  (6b)
```

Sb_2Tl_7 ($L2_2$): A2B7_cI54_229_e_afh - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Sb2 Tl7'

loop_
_publ_author_name
 'Rolf Stokhuyzen'
 'Chung Chieh'
 'William B. Pearson'
_journal_name_full
;
Canadian Journal of Chemistry
;
_journal_volume 55
_journal_year 1977
_journal_page_first 1120
_journal_page_last 1122
_publ_Section_title
;
 Crystal Structure of Sb$_2$Tl$_7$
;

_aflow_proto 'A2B7_cI54_229_e_afh'
_aflow_params 'a,x2,x3,y4'
_aflow_params_values '11.618,0.6862,0.1704,0.6503'
_aflow_Strukturbericht 'L2_2'
_aflow_Pearson 'cI54'

_symmetry_space_group_name_Hall "-I 4 2 3"
_symmetry_space_group_name_H-M "I m -3 m"
_symmetry_Int_Tables_number 229

_cell_length_a     11.61800
_cell_length_b     11.61800
_cell_length_c     11.61800
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
```

```
49 x+1/2,y+1/2,z+1/2
50 x+1/2,-y+1/2,-z+1/2
51 -x+1/2,y+1/2,-z+1/2
52 -x+1/2,-y+1/2,z+1/2
53 y+1/2,z+1/2,x+1/2
54 y+1/2,-z+1/2,-x+1/2
55 -y+1/2,z+1/2,-x+1/2
56 -y+1/2,-z+1/2,x+1/2
57 z+1/2,x+1/2,y+1/2
58 z+1/2,-x+1/2,-y+1/2
59 -z+1/2,x+1/2,-y+1/2
60 -z+1/2,-x+1/2,y+1/2
61 -y+1/2,-x+1/2,-z+1/2
62 -y+1/2,x+1/2,z+1/2
63 y+1/2,-x+1/2,z+1/2
64 y+1/2,x+1/2,-z+1/2
65 -x+1/2,-z+1/2,-y+1/2
66 -x+1/2,z+1/2,y+1/2
67 x+1/2,-z+1/2,y+1/2
68 x+1/2,z+1/2,-y+1/2
69 -z+1/2,-y+1/2,-x+1/2
70 -z+1/2,y+1/2,x+1/2
71 z+1/2,-y+1/2,x+1/2
72 z+1/2,y+1/2,-x+1/2
73 -x+1/2,-y+1/2,-z+1/2
74 -x+1/2,y+1/2,z+1/2
75 x+1/2,-y+1/2,z+1/2
76 x+1/2,y+1/2,-z+1/2
77 -y+1/2,-z+1/2,-x+1/2
78 -y+1/2,z+1/2,x+1/2
79 y+1/2,-z+1/2,x+1/2
80 y+1/2,z+1/2,-x+1/2
81 -z+1/2,-x+1/2,-y+1/2
82 -z+1/2,x+1/2,y+1/2
83 z+1/2,-x+1/2,y+1/2
84 z+1/2,x+1/2,-y+1/2
85 y+1/2,x+1/2,z+1/2
86 y+1/2,-x+1/2,-z+1/2
87 -y+1/2,x+1/2,-z+1/2
88 -y+1/2,-x+1/2,z+1/2
89 x+1/2,z+1/2,y+1/2
90 x+1/2,-z+1/2,-y+1/2
91 -x+1/2,z+1/2,-y+1/2
92 -x+1/2,-z+1/2,y+1/2
93 z+1/2,y+1/2,x+1/2
94 z+1/2,-y+1/2,-x+1/2
95 -z+1/2,y+1/2,-x+1/2
96 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Tl1 Tl   2 a 0.00000 0.00000 0.00000 1.00000
Sb1 Sb  12 e 0.68620 0.00000 0.00000 1.00000
Tl2 Tl  16 f 0.17040 0.17040 0.17040 1.00000
Tl3 Tl  24 h 0.00000 0.65030 0.65030 1.00000
```

Sb_2Tl_7 ($L2_2$): A2B7_cI54_229_e_afh - POSCAR

```
A2B7_cI54_229_e_afh & a,x2,x3,y4 --params=11.618,0.6862,0.1704,0.6503 &
    ↪ Im(-3)m   O_h^9 #229 (aefh) & cI54 & L2_2 & Sb2Tl7 & & R.
    ↪ Stokhuyzen, C. Cheih and W. B. Pearson, Can. J. Chem. 55,
    ↪ 1120-1122 (1977)
  1.0000000000000000
 -5.80900000000000   5.80900000000000   5.80900000000000
  5.80900000000000  -5.80900000000000   5.80900000000000
  5.80900000000000   5.80900000000000  -5.80900000000000
  Sb   Tl
   6   21
Direct
  0.00000000000000   0.31380000000000   0.31380000000000   Sb   (12e)
 -0.00000000000000   0.68620000000000   0.68620000000000   Sb   (12e)
  0.31380000000000   0.00000000000000   0.31380000000000   Sb   (12e)
  0.31380000000000   0.31380000000000   0.00000000000000   Sb   (12e)
  0.68620000000000  -0.00000000000000   0.68620000000000   Sb   (12e)
  0.68620000000000   0.68620000000000  -0.00000000000000   Sb   (12e)
  0.00000000000000   0.00000000000000   0.34080000000000   Tl   (16f)
  0.00000000000000   0.00000000000000   0.65920000000000   Tl   (16f)
  0.00000000000000   0.34080000000000   0.00000000000000   Tl   (16f)
  0.00000000000000   0.65920000000000   0.00000000000000   Tl   (16f)
  0.34080000000000   0.00000000000000   0.00000000000000   Tl   (16f)
  0.34080000000000   0.34080000000000   0.34080000000000   Tl   (16f)
  0.65920000000000   0.00000000000000   0.00000000000000   Tl   (16f)
  0.65920000000000   0.65920000000000   0.65920000000000   Tl   (16f)
  0.00000000000000   0.34970000000000   0.65030000000000   Tl   (24h)
  0.00000000000000   0.65030000000000   0.34970000000000   Tl   (24h)
  0.30060000000000   0.65030000000000   0.65030000000000   Tl   (24h)
  0.34970000000000   0.00000000000000   0.65030000000000   Tl   (24h)
  0.34970000000000   0.34970000000000   0.69940000000000   Tl   (24h)
  0.34970000000000   0.65030000000000   0.00000000000000   Tl   (24h)
  0.34970000000000   0.69940000000000   0.34970000000000   Tl   (24h)
  0.65030000000000   0.00000000000000   0.34970000000000   Tl   (24h)
  0.65030000000000   0.30060000000000   0.65030000000000   Tl   (24h)
  0.65030000000000   0.34970000000000   0.00000000000000   Tl   (24h)
  0.65030000000000   0.65030000000000   0.30060000000000   Tl   (24h)
  0.69940000000000   0.34970000000000   0.34970000000000   Tl   (24h)
  0.00000000000000   0.00000000000000   0.00000000000000   Tl    (2a)
```

Model of Austenite (cI32): AB12C3_cI32_229_a_h_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr Fe12 Ni3'

loop_
_publ_author_name
 'Michael J. Mehl'
_journal_name_full
;
None
;
_journal_volume 0
_journal_year 2008
_journal_page_first 0
_journal_page_last 0
_publ_Section_title
;
 Hypothetical cI32 Austenite Structure
;

_aflow_proto 'AB12C3_cI32_229_a_h_b'
_aflow_params 'a,y3'
_aflow_params_values '7.04,0.7625'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI32'

_symmetry_space_group_name_Hall "-I 4 2 3"
_symmetry_space_group_name_H-M "I m -3 m"
_symmetry_Int_Tables_number 229

_cell_length_a      7.04000
_cell_length_b      7.04000
_cell_length_c      7.04000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x+1/2,y+1/2,z+1/2
50 x+1/2,-y+1/2,-z+1/2
51 -x+1/2,y+1/2,-z+1/2
52 -x+1/2,-y+1/2,z+1/2
53 y+1/2,z+1/2,x+1/2
54 y+1/2,-z+1/2,-x+1/2
55 -y+1/2,z+1/2,-x+1/2
56 -y+1/2,-z+1/2,x+1/2
57 z+1/2,x+1/2,y+1/2
58 z+1/2,-x+1/2,-y+1/2
59 -z+1/2,x+1/2,-y+1/2
60 -z+1/2,-x+1/2,y+1/2
61 -y+1/2,-x+1/2,-z+1/2
```

```
62 -y+1/2,x+1/2,z+1/2
63 y+1/2,-x+1/2,z+1/2
64 y+1/2,x+1/2,-z+1/2
65 -x+1/2,-z+1/2,-y+1/2
66 -x+1/2,z+1/2,y+1/2
67 x+1/2,-z+1/2,y+1/2
68 x+1/2,z+1/2,-y+1/2
69 -z+1/2,-y+1/2,-x+1/2
70 -z+1/2,y+1/2,x+1/2
71 z+1/2,-y+1/2,x+1/2
72 z+1/2,y+1/2,-x+1/2
73 -x+1/2,-y+1/2,-z+1/2
74 -x+1/2,y+1/2,z+1/2
75 x+1/2,-y+1/2,z+1/2
76 x+1/2,y+1/2,-z+1/2
77 -y+1/2,-z+1/2,-x+1/2
78 -y+1/2,z+1/2,x+1/2
79 y+1/2,-z+1/2,x+1/2
80 y+1/2,z+1/2,-x+1/2
81 -z+1/2,-x+1/2,-y+1/2
82 -z+1/2,x+1/2,y+1/2
83 z+1/2,-x+1/2,y+1/2
84 z+1/2,x+1/2,-y+1/2
85 y+1/2,x+1/2,z+1/2
86 y+1/2,-x+1/2,-z+1/2
87 -y+1/2,x+1/2,-z+1/2
88 -y+1/2,-x+1/2,z+1/2
89 x+1/2,z+1/2,y+1/2
90 x+1/2,-z+1/2,-y+1/2
91 -x+1/2,z+1/2,-y+1/2
92 -x+1/2,-z+1/2,y+1/2
93 z+1/2,y+1/2,x+1/2
94 z+1/2,-y+1/2,-x+1/2
95 -z+1/2,y+1/2,-x+1/2
96 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1 Cr   2 a 0.00000 0.00000 0.00000 1.00000
Ni1 Ni   6 b 0.00000 0.50000 0.50000 1.00000
Fe1 Fe  24 h 0.00000 0.76250 0.76250 1.00000
```

Model of Austenite (cI32): AB12C3_cI32_229_a_h_b - POSCAR

```
AB12C3_cI32_229_a_h_b & a,y3 --params=7.04,0.7625 & Im(-3)m   O_h^9 #229
    ↪ (abh) & cI32 & & CrFe12Ni3 & Hypothetical austenite &
   1.0000000000000000
  -3.52000000000000   3.52000000000000   3.52000000000000
   3.52000000000000  -3.52000000000000   3.52000000000000
   3.52000000000000   3.52000000000000  -3.52000000000000
   Cr   Fe   Ni
    1   12    3
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Cr   (2a)
   0.00000000000000   0.23750000000000   0.76250000000000   Fe   (24h)
   0.00000000000000   0.76250000000000   0.23750000000000   Fe   (24h)
   0.23750000000000   0.00000000000000   0.76250000000000   Fe   (24h)
   0.23750000000000   0.23750000000000   0.47500000000000   Fe   (24h)
   0.23750000000000   0.47500000000000   0.23750000000000   Fe   (24h)
   0.23750000000000   0.76250000000000   0.00000000000000   Fe   (24h)
   0.47500000000000   0.23750000000000   0.23750000000000   Fe   (24h)
   0.52500000000000   0.76250000000000   0.76250000000000   Fe   (24h)
   0.76250000000000   0.00000000000000   0.23750000000000   Fe   (24h)
   0.76250000000000   0.23750000000000   0.00000000000000   Fe   (24h)
   0.76250000000000   0.52500000000000   0.76250000000000   Fe   (24h)
   0.76250000000000   0.76250000000000   0.52500000000000   Fe   (24h)
   0.00000000000000   0.50000000000000   0.50000000000000   Ni   (6b)
   0.50000000000000   0.00000000000000   0.50000000000000   Ni   (6b)
   0.50000000000000   0.50000000000000   0.00000000000000   Ni   (6b)
```

Model of Ferrite (cI16): AB4C3_cI16_229_a_c_b - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Cr Fe4 Ni3'

loop_
_publ_author_name
 'Michael J. Mehl'
_journal_name_full
;
None
;
_journal_volume 0
_journal_year 2008
_journal_page_first 0
_journal_page_last 0
_publ_Section_title
;
 Hypothetical cI16 Austenite Structure
;

_aflow_proto 'AB4C3_cI16_229_a_c_b'
_aflow_params 'a'
_aflow_params_values '5.74'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI16'

_symmetry_space_group_name_Hall "-I 4 2 3"
_symmetry_space_group_name_H-M "I m -3 m"
_symmetry_Int_Tables_number 229

_cell_length_a      5.74000
_cell_length_b      5.74000
_cell_length_c      5.74000
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z
3 -x,y,-z
4 -x,-y,z
5 y,z,x
6 y,-z,-x
7 -y,z,-x
8 -y,-z,x
9 z,x,y
10 z,-x,-y
11 -z,x,-y
12 -z,-x,y
13 -y,-x,-z
14 -y,x,z
15 y,-x,z
16 y,x,-z
17 -x,-z,-y
18 -x,z,y
19 x,-z,y
20 x,z,-y
21 -z,-y,-x
22 -z,y,x
23 z,-y,x
24 z,y,-x
25 -x,-y,-z
26 -x,y,z
27 x,-y,z
28 x,y,-z
29 -y,-z,-x
30 -y,z,x
31 y,-z,x
32 y,z,-x
33 -z,-x,-y
34 -z,x,y
35 z,-x,y
36 z,x,-y
37 y,x,z
38 y,-x,-z
39 -y,x,-z
40 -y,-x,z
41 x,z,y
42 x,-z,-y
43 -x,z,-y
44 -x,-z,y
45 z,y,x
46 z,-y,-x
47 -z,y,-x
48 -z,-y,x
49 x+1/2,y+1/2,z+1/2
50 x+1/2,-y+1/2,-z+1/2
51 -x+1/2,y+1/2,-z+1/2
52 -x+1/2,-y+1/2,z+1/2
53 y+1/2,z+1/2,x+1/2
54 y+1/2,-z+1/2,-x+1/2
55 -y+1/2,z+1/2,-x+1/2
56 -y+1/2,-z+1/2,x+1/2
57 z+1/2,x+1/2,y+1/2
58 z+1/2,-x+1/2,-y+1/2
59 -z+1/2,x+1/2,-y+1/2
60 -z+1/2,-x+1/2,y+1/2
61 -y+1/2,-x+1/2,-z+1/2
62 -y+1/2,x+1/2,z+1/2
63 y+1/2,-x+1/2,z+1/2
64 y+1/2,x+1/2,-z+1/2
65 -x+1/2,-z+1/2,-y+1/2
66 -x+1/2,z+1/2,y+1/2
67 x+1/2,-z+1/2,y+1/2
68 x+1/2,z+1/2,-y+1/2
69 -z+1/2,-y+1/2,-x+1/2
70 -z+1/2,y+1/2,x+1/2
71 z+1/2,-y+1/2,x+1/2
72 z+1/2,y+1/2,-x+1/2
73 -x+1/2,-y+1/2,-z+1/2
74 -x+1/2,y+1/2,z+1/2
75 x+1/2,-y+1/2,z+1/2
76 x+1/2,y+1/2,-z+1/2
77 -y+1/2,-z+1/2,-x+1/2
78 -y+1/2,z+1/2,x+1/2
79 y+1/2,-z+1/2,x+1/2
80 y+1/2,z+1/2,-x+1/2
81 -z+1/2,-x+1/2,-y+1/2
82 -z+1/2,x+1/2,y+1/2
83 z+1/2,-x+1/2,y+1/2
84 z+1/2,x+1/2,-y+1/2
85 y+1/2,x+1/2,z+1/2
86 y+1/2,-x+1/2,-z+1/2
87 -y+1/2,x+1/2,-z+1/2
```

```
88 -y+1/2,-x+1/2,z+1/2
89 x+1/2,z+1/2,y+1/2
90 x+1/2,-z+1/2,-y+1/2
91 -x+1/2,z+1/2,-y+1/2
92 -x+1/2,-z+1/2,y+1/2
93 z+1/2,y+1/2,x+1/2
94 z+1/2,-y+1/2,-x+1/2
95 -z+1/2,y+1/2,-x+1/2
96 -z+1/2,-y+1/2,x+1/2

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Cr1 Cr   2 a 0.00000 0.00000 0.00000 1.00000
Ni1 Ni   6 b 0.00000 0.50000 0.50000 1.00000
Fe1 Fe   8 c 0.25000 0.25000 0.25000 1.00000
```

Model of Ferrite (cI16): AB4C3_cI16_229_a_c_b - POSCAR

```
AB4C3_cI16_229_a_c_b & a --params=5.74 & Im(-3)m   O_h^9 #229 (abc) &
    ↪ cI16 & & CrFe4Ni3 & hypothetical ferrite &
   1.0000000000000000
  -2.87000000000000   2.87000000000000   2.87000000000000
   2.87000000000000  -2.87000000000000   2.87000000000000
   2.87000000000000   2.87000000000000  -2.87000000000000
   Cr   Fe   Ni
    1    4    3
Direct
   0.00000000000000   0.00000000000000   0.00000000000000   Cr   (2a)
   0.00000000000000   0.00000000000000   0.50000000000000   Fe   (8c)
   0.00000000000000   0.50000000000000   0.00000000000000   Fe   (8c)
   0.50000000000000   0.00000000000000   0.00000000000000   Fe   (8c)
   0.50000000000000   0.50000000000000   0.50000000000000   Fe   (8c)
   0.00000000000000   0.50000000000000   0.50000000000000   Ni   (6b)
   0.50000000000000   0.00000000000000   0.50000000000000   Ni   (6b)
   0.50000000000000   0.50000000000000   0.00000000000000   Ni   (6b)
```

Ga_4Ni_3: A4B3_cI112_230_af_g - CIF

```
# CIF file

data_findsym-output
_audit_creation_method FINDSYM

_chemical_name_mineral ''
_chemical_formula_sum 'Ga4 Ni3'

loop_
_publ_author_name
 'M. Ellner'
 'K. J. Best'
 'H. Jacobi'
 'K. Schubert'
_journal_name_full
;
Journal of the Less-Common Metals
;
_journal_volume 19
_journal_year 1969
_journal_page_first 294
_journal_page_last 296
_publ_Section_title
;
 Struktur von Ni$_3$Ga$_4$
;

# Found in  http://materials.springer.com/lb/docs/
    ↪ sm_lbs_978-3-540-45199-0_4

_aflow_proto 'A4B3_cI112_230_af_g'
_aflow_params 'a,x2,y3'
_aflow_params_values '11.411,0.0,0.625'
_aflow_Strukturbericht 'None'
_aflow_Pearson 'cI112'

_symmetry_space_group_name_Hall "-I 4bd 2c 3"
_symmetry_space_group_name_H-M "I a -3 d"
_symmetry_Int_Tables_number 230

_cell_length_a     11.41100
_cell_length_b     11.41100
_cell_length_c     11.41100
_cell_angle_alpha  90.00000
_cell_angle_beta   90.00000
_cell_angle_gamma  90.00000

loop_
_space_group_symop_id
_space_group_symop_operation_xyz
1 x,y,z
2 x,-y,-z+1/2
3 -x+1/2,y,-z
4 -x,-y+1/2,z
5 y,z,x
6 y,-z,-x+1/2
7 -y+1/2,z,-x
8 -y,-z+1/2,x
9 z,x,y
10 z,-x,-y+1/2
11 -z+1/2,x,-y
12 -z,-x+1/2,y
13 -y+1/4,-x+1/4,-z+1/4
14 -y+1/4,x+3/4,z+1/4
15 y+1/4,-x+1/4,z+3/4
16 y+3/4,x+1/4,-z+1/4
17 -x+1/4,-z+1/4,-y+1/4
18 -x+1/4,z+3/4,y+1/4
19 x+1/4,-z+1/4,y+3/4
20 x+3/4,z+1/4,-y+1/4
21 -z+1/4,-y+1/4,-x+1/4
22 -z+1/4,y+3/4,x+1/4
23 z+1/4,-y+1/4,x+3/4
24 z+3/4,y+1/4,-x+1/4
25 -x,-y,-z
26 -x,y,z+1/2
27 x+1/2,-y,z
28 x,y+1/2,-z
29 -y,-z,-x
30 -y,z,x+1/2
31 y+1/2,-z,x
32 y,z+1/2,-x
33 -z,-x,-y
34 -z,x,y+1/2
35 z+1/2,-x,y
36 z,x+1/2,-y
37 y+1/4,x+1/4,z+1/4
38 y+1/4,-x+3/4,-z+1/4
39 -y+1/4,x+1/4,-z+3/4
40 -y+3/4,-x+1/4,z+1/4
41 x+1/4,z+1/4,y+1/4
42 x+1/4,-z+3/4,-y+1/4
43 -x+1/4,z+1/4,-y+3/4
44 -x+3/4,-z+1/4,y+1/4
45 z+1/4,y+1/4,x+1/4
46 z+1/4,-y+3/4,-x+1/4
47 -z+1/4,y+1/4,-x+3/4
48 -z+3/4,-y+1/4,x+1/4
49 x+1/2,y+1/2,z+1/2
50 x+1/2,-y+1/2,-z
51 -x,y+1/2,-z+1/2
52 -x+1/2,-y,z+1/2
53 y+1/2,z+1/2,x+1/2
54 y+1/2,-z+1/2,-x
55 -y,z+1/2,-x+1/2
56 -y+1/2,-z,x+1/2
57 z+1/2,x+1/2,y+1/2
58 z+1/2,-x+1/2,-y
59 -z,x+1/2,-y+1/2
60 -z+1/2,-x,y+1/2
61 -y+3/4,-x+3/4,-z+3/4
62 -y+3/4,x+1/4,z+3/4
63 y+3/4,-x+3/4,z+1/4
64 y+1/4,x+3/4,-z+3/4
65 -x+3/4,-z+3/4,-y+3/4
66 -x+3/4,z+1/4,y+3/4
67 x+3/4,-z+3/4,y+1/4
68 x+1/4,z+3/4,-y+3/4
69 -z+3/4,-y+3/4,-x+3/4
70 -z+3/4,y+1/4,x+3/4
71 z+3/4,-y+3/4,x+1/4
72 z+1/4,y+3/4,-x+3/4
73 -x+1/2,-y+1/2,-z+1/2
74 -x+1/2,y+1/2,z
75 x,-y+1/2,z+1/2
76 x+1/2,y,-z+1/2
77 -y+1/2,-z+1/2,-x+1/2
78 -y+1/2,z+1/2,x
79 y,-z+1/2,x+1/2
80 y+1/2,z,-x+1/2
81 -z+1/2,-x+1/2,-y+1/2
82 -z+1/2,x+1/2,y
83 z,-x+1/2,y+1/2
84 z+1/2,x,-y+1/2
85 y+3/4,x+3/4,z+3/4
86 y+3/4,-x+1/4,-z+3/4
87 -y+3/4,x+3/4,-z+1/4
88 -y+1/4,-x+3/4,z+3/4
89 x+3/4,z+3/4,y+3/4
90 x+3/4,-z+1/4,-y+3/4
91 -x+3/4,z+3/4,-y+1/4
92 -x+1/4,-z+3/4,y+3/4
93 z+3/4,y+3/4,x+3/4
94 z+3/4,-y+1/4,-x+3/4
95 -z+3/4,y+3/4,-x+1/4
96 -z+1/4,-y+3/4,x+3/4

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_symmetry_multiplicity
_atom_site_Wyckoff_label
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
Ga1 Ga  16 a 0.00000 0.00000 0.00000 1.00000
Ga2 Ga  48 f 0.00000 0.00000 0.25000 1.00000
Ni1 Ni  48 g 0.12500 0.62500 0.62500 1.00000
```

Ga_4Ni_3: A4B3_cI112_230_af_g - POSCAR

```
A4B3_cI112_230_af_g & a,x2,y3 --params=11.411,0.0,0.625 & Ia(-3)d   O_h
    ↪ ^{10} #230 (afg) & cI112 & & Ga4Ni3 & & M. Ellner, K. J. Best,
    ↪ H. Jacobi and K. Schubert, J. Less-Common Metals 19, 294-296 (
```

```
    ↪ 1969)
  1.0000000000000000
 -5.70550000000000   5.70550000000000   5.70550000000000
  5.70550000000000  -5.70550000000000   5.70550000000000
  5.70550000000000   5.70550000000000  -5.70550000000000
  Ga   Ni
  32   24
Direct
  0.00000000000000   0.00000000000000   0.00000000000000   Ga   (16a)
  0.00000000000000   0.00000000000000   0.50000000000000   Ga   (16a)
  0.00000000000000   0.50000000000000   0.00000000000000   Ga   (16a)
  0.00000000000000   0.50000000000000   0.50000000000000   Ga   (16a)
  0.50000000000000   0.00000000000000   0.00000000000000   Ga   (16a)
  0.50000000000000   0.00000000000000   0.50000000000000   Ga   (16a)
  0.50000000000000   0.50000000000000   0.00000000000000   Ga   (16a)
  0.50000000000000   0.50000000000000   0.50000000000000   Ga   (16a)
  0.00000000000000   0.25000000000000   0.25000000000000   Ga   (48f)
  0.00000000000000  -0.25000000000000   0.25000000000000   Ga   (48f)
  0.00000000000000   0.25000000000000   0.75000000000000   Ga   (48f)
  0.00000000000000   0.75000000000000   0.75000000000000   Ga   (48f)
  0.25000000000000   0.00000000000000   0.25000000000000   Ga   (48f)
  0.25000000000000   0.00000000000000  -0.25000000000000   Ga   (48f)
  0.25000000000000   0.25000000000000   0.00000000000000   Ga   (48f)
 -0.25000000000000   0.25000000000000   0.00000000000000   Ga   (48f)
  0.25000000000000   0.25000000000000   0.50000000000000   Ga   (48f)
  0.25000000000000  -0.25000000000000   0.50000000000000   Ga   (48f)
  0.25000000000000   0.50000000000000   0.25000000000000   Ga   (48f)
 -0.25000000000000   0.50000000000000   0.25000000000000   Ga   (48f)
  0.25000000000000   0.50000000000000   0.75000000000000   Ga   (48f)
 -0.25000000000000   0.50000000000000   0.75000000000000   Ga   (48f)
  0.25000000000000   0.75000000000000   0.00000000000000   Ga   (48f)
  0.50000000000000   0.25000000000000   0.25000000000000   Ga   (48f)
  0.50000000000000   0.25000000000000  -0.25000000000000   Ga   (48f)
  0.50000000000000   0.75000000000000   0.25000000000000   Ga   (48f)
  0.50000000000000   0.75000000000000  -0.25000000000000   Ga   (48f)
  0.75000000000000   0.00000000000000   0.25000000000000   Ga   (48f)
  0.75000000000000   0.00000000000000   0.75000000000000   Ga   (48f)
  0.75000000000000   0.25000000000000   0.50000000000000   Ga   (48f)
  0.75000000000000  -0.25000000000000   0.50000000000000   Ga   (48f)
  0.75000000000000   0.75000000000000   0.00000000000000   Ga   (48f)
  0.00000000000000   0.00000000000000   0.25000000000000   Ni   (48g)
  0.00000000000000   0.00000000000000   0.75000000000000   Ni   (48g)
  0.00000000000000   0.25000000000000   0.00000000000000   Ni   (48g)
  0.00000000000000   0.50000000000000   0.25000000000000   Ni   (48g)
  0.00000000000000   0.50000000000000  -0.25000000000000   Ni   (48g)
  0.00000000000000   0.75000000000000   0.00000000000000   Ni   (48g)
  0.25000000000000   0.00000000000000   0.00000000000000   Ni   (48g)
  0.25000000000000   0.00000000000000   0.50000000000000   Ni   (48g)
 -0.25000000000000   0.00000000000000   0.50000000000000   Ni   (48g)
  0.25000000000000   0.25000000000000   0.75000000000000   Ni   (48g)
  0.25000000000000   0.75000000000000   0.25000000000000   Ni   (48g)
  0.25000000000000   0.75000000000000   0.75000000000000   Ni   (48g)
  0.50000000000000   0.25000000000000   0.00000000000000   Ni   (48g)
  0.50000000000000  -0.25000000000000   0.00000000000000   Ni   (48g)
  0.50000000000000   0.50000000000000   0.75000000000000   Ni   (48g)
 -0.50000000000000  -0.50000000000000  -0.75000000000000   Ni   (48g)
  0.50000000000000   0.75000000000000   0.50000000000000   Ni   (48g)
 -0.50000000000000  -0.75000000000000  -0.50000000000000   Ni   (48g)
  0.75000000000000   0.00000000000000   0.00000000000000   Ni   (48g)
  0.75000000000000   0.25000000000000   0.25000000000000   Ni   (48g)
  0.75000000000000   0.25000000000000   0.75000000000000   Ni   (48g)
  0.75000000000000   0.50000000000000   0.50000000000000   Ni   (48g)
 -0.75000000000000  -0.50000000000000  -0.50000000000000   Ni   (48g)
  0.75000000000000   0.75000000000000   0.25000000000000   Ni   (48g)
```

Prototype Index

1. "ST12" of Si: A_tP12_96_ab S227
2. α-As[‖]: A_hR2_166_c S375
3. α-B: A_hR12_166_2h S391
4. α-CO[‡‡]: AB_cP8_198_a_a S504
5. α-Cristobalite: A2B_tP12_92_b_a S222
6. α-Ga[§]: A_oC8_64_f S183
7. α-Hg[**]: A_hR1_166_a S385
8. α-IrV: AB_oC8_65_j_g S192
9. α-La: A_hP4_194_ac S458
10. α-Mn: A_cI58_217_ac2g S546
11. α-N: A_cP8_198_2a S502
12. α-N: A_cP8_205_c S518
13. α-Np: A_oP8_62_2c S169
14. α-O: A_mC4_12_i S60
15. α-Pa[¶]: A_tI2_139_a S302
16. α-Po: A_cP1_221_a S564
17. α-Pu: A_mP16_11_8e S50
18. α-Quartz: A2B_hP9_152_c_a S345
19. α-ReO_3: A3B_cP4_221_d_a S571
20. α-S: A_oF128_70_4h S204
21. α-Sm: A_hR3_166_ac S381
22. α-U: A_oC4_63_c S181
23. β-B: A_hR105_166_bc9h4i S397
24. β-BeO: AB_tP8_136_g_f S267
25. β-In_2S_3: A2B3_tI80_141_ceh_3h S324
26. β-Mn: A_cP20_213_cd S530
27. β-Np: A_tP4_129_ac S249
28. β-O[‖]: A_hR2_166_c S395
29. β-Po[**]: A_hR1_166_a S377
30. β-Pu: A_mC34_12_ah3i2j S54
31. β-Quartz: A2B_hP9_180_j_c S416
32. β-Se: A_mP32_14_8e S70
33. β-Sn: A_tI4_141_a S312
34. β-$TiCu_3$: A3B_oP8_59_bf_a S140
35. β-Tridymite: A2B_hP12_194_cg_f S494
36. β-U: A_tP30_136_bf2ij S264
37. β-V_2N: AB2_hP9_162_ad_k S361
38. β'-AuCd: AB_oP4_51_e_f S122
39. η-Fe_2C[*]: AB2_oP6_58_a_g S132
40. γ-Brass: A5B8_cI52_217_ce_cg S548
41. γ-CuTi: AB_tP4_129_c_c S257
42. γ-N: A_tP4_136_f S274
43. γ-Pu: A_oF8_70_a S200
44. γ-Se: A_hP3_152_a S347
45. ω Phase: AB2_hP3_164_a_d S368
46. σ-CrFe: sigma_tP30_136_bf2ij S271
47. ζ-AgZn: A2B_hP9_147_g_ad S329
48. 0201 [$(La,Ba)_2CuO_4$]: AB2C4_tI14_139_a_e_ce S282
49. 1212C [$YBa_2Cu_3O_{7-x}$]: A2B3C7D_oP13_47_t_aq_eqrs_h S120
50. $Al_{12}W$: A12B_cI26_204_g_a S516
51. Al_3Ni_2: A3B2_hP5_164_ad_d S366
52. Al_3Ti: A3B_tI8_139_bd_a S290
53. Al_3Zr: A3B_tI16_139_cde_e S278
54. Al_4Ba: A4B_tI10_139_de_a S296
55. Al_5C_3N: A5B3C_hP18_186_2a3b_2ab_b S428
56. AlB_4Mg: AB4C_hP6_191_a_h_b S438
57. $AlCCr_2$: ABC2_hP8_194_d_a_f S466
58. $AlCl_3$: AB3_mC16_12_g_ij S56
59. AlF_3 : AB3_hR8_155_c_de S351
60. AlN_3Ti_4: AB3C4_hP16_194_c_af_ef S484
61. $AlPS_4$: ABC4_oP12_16_ag_cd_2u S86
62. Ammonia: A3B_cP16_198_b_a S500
63. Anatase: A2B_tI12_141_e_a S316
64. AsCuSiZr: ABCD_tP8_129_c_b_a_c S247
65. AsK_3S_4: AB3C4_oP32_33_a_3a_4a S102
66. $AsKSe_2$: ABC2_aP16_1_4a_4a_8a S27
67. AsTi: AB_hP8_194_ad_f S452
68. Au_2V: A2B_oC12_38_de_ab S109
69. Au_5Mn_2: A5B2_mC14_12_a2i_i S58
70. $AuBe_5$: AB5_cF24_216_a_ce S538
71. B_2Pd_5: A2B5_mC28_15_f_e2f S78
72. BC8: A_cI16_206_c S528
73. BN: AB_hP4_194_c_d S464
74. BPO_4: AB4C_tI12_82_c_g_a S212
75. $BaHg_{11}$: AB11_cP36_221_c_agij S566
76. BaPtSb: ABC_hP3_187_a_d_f S432
77. BaS_3: AB3_oP16_18_ab_3c S88
78. BaS_3: AB3_tP8_113_a_ce S231
79. Baddeleyite: A2B_mP12_14_2e_e S68
80. Bainite: AB3_hP8_182_c_g S418
81. Bergman [$Mg_{32}(Al,Zn)_{49}$]: AB32C48_cI162_204_a_2efg_2gh S510
82. Bi_2Te_3: A2B3_hR5_166_c_ac S383
83. BiF_3: AB3_cF16_225_a_bc S584
84. BiI_3: AB3_hR8_148_c_f S333

[‖] α-As, rhombohedral graphite, and β-O have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡‡] α-CO and FeSi have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[§] α-Ga, black phosphorus, and molecular iodine have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[**] β-Po and α-Hg have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[¶] In and α-Pa have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[*] Hydrophilite, η-Fe_2C, and marcasite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

85. Bixbyite: AB3C6_cI80_206_a_d_e S524
86. Black Phosphorus[§]: A_oC8_64_f S188
87. Body-Centered Cubic: A_cI2_229_a S622
88. Brookite: A2B_oP24_61_2c_c S144
89. Buckled Graphite: A_hP4_186_ab S420
90. C_2CeNi: A2BC_oC8_38_e_a_b S107
91. C_3Cr_7: A3B7_oP40_62_cd_3c2d S166
92. CMo: AB_hP12_194_af_bf S456
93. CNCl: ABC_oP6_59_a_a_a S138
94. CTi_2: AB2_cF48_227_c_e S618
95. Ca_7Ge: A7B_cF32_225_bd_a S582
96. CaB_6: A6B_cP7_221_f_a S573
97. CaC_6: A6B_hR7_166_g_a S404
98. $CaCu_5$: AB5_hP6_191_a_cg S440
99. $CaCuO_2$: ABC2_tP4_123_d_a_f S243
100. $CaIn_2$: AB2_hP6_194_b_f S462
101. $CaTiO_3$ Pnma Perovskite: AB3C_oP20_62_c_cd_a S148
102. Calaverite: AB2_mC6_12_a_i S52
103. Calcite[††]: ABC3_hR10_167_a_b_e S408
104. Caswellsilverite: ABC2_hR4_166_a_b_c S393
105. $CdAl_2S_4$: A2BC4_tI14_82_bc_a_g S214
106. CdSb: AB_oP16_61_c_c S142
107. Cementite: AB3_oP16_62_c_cd S164
108. Cf: A_aP4_2_aci S31
109. Chalcopyrite: ABC2_tI16_122_a_b_d S235
110. Chalcostibite: AB2C_oP16_62_c_2c_c S152
111. Cinnabar: AB_hP6_154_a_b S349
112. Cl: A_tP16_138_j S276
113. Co_2Si[†]: A2B_oP12_62_2c_c S154
114. CoSn: AB_hP6_191_f_ad S450
115. CoU: AB_cI16_199_a_a S508
116. Coesite: A2B_mC48_15_ae3f_2f S82
117. Corundum: A2B3_hR10_167_c_e S410
118. Cotunnite[†]: A2B_oP12_62_2c_c S158
119. Covellite: AB_hP12_194_df_ce S490
120. $Cr_{23}C_6$: A6B23_cF116_225_e_acfh S593
121. Cr_3Si: A3B_cP8_223_c_a S575
122. CrB: AB_oC8_63_c_c S179
123. $CrCl_3$: A3B_hP24_151_3c_2a S342
124. $CrSi_2$: AB2_hP9_180_d_j S414
125. CsCl: AB_cP2_221_b_a S554
126. Cu_2Mg Cubic Laves: A2B_cF24_227_d_a S612
127. Cu_2Sb: A2B_tP6_129_ac_c S253
128. Cu_2Te: A2B_hP6_191_h_e S448
129. Cu_3Au: AB3_cP4_221_a_c S562
130. CuAu: AB_tP2_123_a_d S241
131. CuPt: AB_hR2_166_a_b S373
132. $CuTi_3$: AB3_tP4_123_a_ce S239
133. Cubic Lazarevićite: AB3C4_cP8_215_a_c_e S536
134. Cubic Perovskite: AB3C_cP5_221_a_c_b S558
135. Cuprite: A2B_cP6_224_b_a S580
136. Diamond: A_cF8_227_a S614
137. Enargite: AB3C4_oP16_31_a_ab_2ab S98
138. Esseneite: ABC6D2_mC40_15_e_e_3f_f S84
139. Face-Centered Cubic: A_cF4_225_a S597
140. Fe_3W_3C: AB3C3_cF112_227_c_de_f S620
141. Fe_4C: AB4_cP5_215_a_e S534
142. Fe_7W_6 μ-phase: A7B6_hR13_166_ah_3c S379
143. FeB[‡]: AB_oP8_62_c_c S171
144. FeS_2: AB2_aP12_1_4a_8a S25
145. FeSi[‡‡]: AB_cP8_198_a_a S506
146. Ferroelectric $LiNbO_3$: ABC3_hR10_161_a_a_b S359
147. Fluorite: AB2_cF12_225_a_c S591
148. Ga_2Hf: A2B_tI24_141_2e_e S320
149. Ga_3Pt_5: A3B5_oC16_65_ah_bej S194
150. Ga_4Ni: A4B_cI40_197_cde_c S496
151. Ga_4Ni_3: A4B3_cI112_230_af_g S634
152. GeS[‡]: AB_oP8_62_c_c S160
153. GeS_2: AB2_oF72_43_ab_3b S115
154. H_3Ho: A3B_hP24_165_adg_f S370
155. Half-Heusler: ABC_cF12_216_b_c_a S540
156. Hausmannite: A3B4_tI28_141_ad_h S314
157. Hazelwoodite : A3B2_hR5_155_e_c S353
158. Heusler: AB2C_cF16_225_a_c_b S595
159. Hexagonal ω: AB2_hP3_191_a_d S446
160. Hexagonal Close Packed: A_hP2_194_c S486
161. Hexagonal Graphite: A_hP4_194_bc S470
162. $HgBr_2$: A2B_oC12_36_2a_a S105
163. $HgCl_2$[†]: A2B_oP12_62_2c_c S156
164. High-Pressure cI16 Li: A_cI16_220_c S550
165. High-Pressure CdTe: AB_oP2_25_b_a S94
166. High-Pressure H_3S: A3B_cI8_229_b_a S624
167. High-Pressure Te: A_mP4_4_2a S35
168. High-pressure GaAs: AB_oI4_44_a_b S118
169. $HoCoGa_5$: AB5C_tP7_123_b_ci_a S237
170. Hydrophilite[*]: AB2_oP6_58_a_g S130
171. Hypothetical BCT5 Si: A_tI4_139_e S280
172. Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h S454
173. Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h S288
174. Ideal β-Cristobalite: A2B_cF24_227_c_a S603
175. Ilmenite: AB3C_hR10_148_c_f_c S338

[††]Paraelectric $LiNbO_3$ and calcite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[†]Co_2Si, $HgCl_2$, and cotunnite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡]GeS, MnP, FeB, and SnS have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

176. In[¶]: A_tI2_139_a S286
177. $KAg(CN)_2$: AB2CD2_hP36_163_h_i_bf_i S363
178. KCNS: ABCD_oP16_57_d_c_d_d S126
179. $KClO_3$: ABC3_mP10_11_e_e_ef S48
180. Keatite: A2B_tP36_96_3b_ab S224
181. Khatyrkite: A2B_tI12_140_h_a S304
182. Krennerite: AB2_oP24_28_acd_2c3d S96
183. Li_3N: A3B_hP4_191_bc_a S444
184. LiBC: ABC_hP6_194_c_d_a S478
185. Lonsdaleite: A_hP4_194_f S480
186. Marcasite[*]: AB2_oP6_58_a_g S134
187. Matlockite: ABC_tP6_129_c_a_c S251
188. Mg_2Ni: A2B_hP18_180_fi_bd S412
189. MgB_2C_2: A2B2C_oC80_64_efg_efg_df S185
190. MgB_4: A4B_oP20_62_2cd_c S150
191. $MgNi_2$ Hexagonal Laves: AB2_hP24_194_ef_fgh S488
192. $MgZn_2$ Hexagonal Laves: AB2_hP12_194_f_ah . S476
193. Millerite: AB_hR6_160_b_b S355
194. $Mn_{12}Th$: A12B_tI26_139_fij_a S284
195. MnP[‡]: AB_oP8_62_c_c S162
196. Mo_2B_5: A5B2_hR7_166_a2c_c S387
197. MoB: AB_tI16_141_e_e S318
198. Model of Austenite: AB12C3_cI32_229_a_h_b .. S630
199. Model of Austenite: AB18C8_cF108_225_a_eh_f S599
200. Model of Austenite: AB27CD3_cP32_221_a_dij_b_c S560
201. Model of Ferrite: A9B16C7_cF128_225_acd_2f_be S586
202. Model of Ferrite: AB4C3_cI16_229_a_c_b S632
203. Model of Ferrite: AB11CD3_cP16_221_a_dg_b_c S569
204. $MoPt_2$: AB2_oI6_71_a_g S208
205. $MoSi_2$: AB2_tI6_139_a_e S292
206. Modderite: AB_oP8_33_a_a S100
207. Moissanite 9R: AB_hR6_160_3a_3a S357
208. Moissanite-4H SiC: AB_hP8_186_ab_ab S422
209. Moissanite-6H SiC: AB_hP12_186_a2b_a2b S426
210. Molecular Iodine[§]: A_oC8_64_f S190
211. Molybdenite: AB2_hP6_194_c_f S472
212. Monoclinic Low Tridymite: A2B_mC144_9_24a_12a S41
213. Monoclinic PZT $[Pb(Zr_xTi_{1-x})O_3]$: A3BC_mC10_8_ab_a_a S39
214. Monoclinic Phosphorus: A_mP84_13_21g S63
215. Na_3As: AB3_hP8_194_c_bf S460
216. NaTl: AB_cF16_227_a_b S607
217. Naumannite: A2B_oP12_19_2a_a S90
218. NbO: AB_cP6_221_c_d S556
219. NbP: AB_tI8_141_a_b S322
220. Ni_2In: AB2_hP6_194_c_ad S482
221. Ni_3Sn: A3B_hP8_194_h_c S468
222. Ni_4Mo: AB4_tI10_87_a_h S220
223. NiAs: AB_hP4_194_c_a S492
224. NiTi: AB_mP4_11_e_e S46
225. $NiTi_2$: AB2_cF96_227_e_cf S605
226. Original BN: AB_hP4_186_b_a S430
227. Original Fe_2P: A2B_hP9_150_ef_bd S340
228. Orthorhombic Tridymite: A2B_oC24_20_abc_c .. S92
229. P_2I_4: A2B_aP6_2_2i_i S29
230. $PPrS_4$: ABC4_tI96_142_e_ab_2g S326
231. Paraelectric $LiNbO_3$[††]: ABC3_hR10_167_a_b_e . S406
232. PbO: AB_tP4_129_a_c S255
233. PdAl: AB_hR26_148_b2f_a2f S335
234. PdS: AB_tP16_84_cej_k S216
235. $PdSn_2$: AB2_oC24_41_2a_2b S113
236. Po: A_mC12_5_3c S37
237. Predicted $CdPt_3$: AB3_oC8_65_a_bf S196
238. Pt_3O_4: A4B3_cI14_229_c_b S626
239. Pt_8Ti: A8B_tI18_139_hi_a S298
240. PtS: AB_tP4_131_c_e S259
241. $PtSn_4$: AB4_oC20_41_a_2b S111
242. Pu_2C_3: A3B2_cI40_220_d_c S552
243. Pyrite: AB2_cP12_205_a_c S522
244. $ReSi_2$: AB2_oI6_71_a_i S207
245. Revised Fe_2P: A2B_hP9_189_fg_bc S436
246. Rhombohedral Graphite[‖]: A_hR2_166_c S389
247. Rock Salt: AB_cF8_225_a_b S601
248. Rutile: A2B_tP6_136_f_a S269
249. SC16: AB_cP16_205_c_c S520
250. Sb_2O_3: A3B2_oP20_56_ce_e S124
251. Sb_2Tl_7: A2B7_cI54_229_e_afh S628
252. Se: A_mP64_14_16e S73
253. SeTl: AB_tI16_140_ab_h S308
254. Si_2U_3: A2B3_tP10_127_g_ah S245
255. Si_{34} Clathrate: A_cF136_227_aeg S609
256. Si_{46} Clathrate: A_cP46_223_dik S577
257. SiF_4: A4B_cI10_217_c_a S544
258. SiO_2: A2B_mP12_3_bc3e_2e S33
259. SiS_2: A2B_oI12_72_j_a S210
260. SiU_3: AB3_tI16_140_b_ah S306
261. Simple Hexagonal Lattice: A_hP1_191_a S442
262. Skutterudite: A3B_cI32_204_g_c S514
263. SnS[‡]: AB_oP8_62_c_c S173
264. Solid Cubane: AB_hR16_148_cf_cf S331
265. Spinel: A2BC4_cF56_227_d_a_e S616
266. $SrCuO_2$: AB2C_oC16_63_c_2c_c S175
267. Stannite: A2BC4D_tI16_121_d_a_i_b S233
268. Stibnite: A3B2_oP20_62_3c_2c S146
269. Sulvanite: A3B4C_cP8_215_d_e_a S532
270. Sylvanite: ABC4_mP12_13_e_a_2g S61
271. T-50 B: A_tP50_134_b2m2n S261
272. Tenorite: AB_mC8_15_c_e S80
273. Tetragonal PZT $[Pb(Zr_xTi_{1-x})O_3]$: A3BC_tP5_99_bc_a_b S229
274. ThH_2: A2B_tI6_139_d_a S300
275. Ti_5Te_4: A4B5_tI18_87_h_ah S218

276. $TiSi_2$: A2B_oF24_70_e_a S202
277. TlF: AB_oF8_69_a_b S198
278. TlF-II: AB_oP8_57_d_d S128
279. Tungsten Carbide: AB_hP2_187_d_a S434
280. UB_{12}: A12B_cF52_225_i_a S589
281. Ullmanite: ABC_cP12_198_a_a_a S498
282. V_4Zn_5: A4B5_tI18_139_i_ah S294
283. Vulcanite: AB_oP4_59_a_b S136
284. W_2B_5: A5B2_hP14_194_abdf_f S474
285. Wurtzite: AB_hP4_186_b_b S424
286. Zincblende: AB_cF8_216_c_a S542
287. Zircon: A4BC_tI24_141_h_b_a S310
288. $ZrSi_2$: A2B_oC12_63_2c_c S177

Pearson Symbol Index

aP .....
1. **aP4** .....
1.1. Cf: A_aP4_2_aci S31
2. **aP6** .....
2.1. P_2I_4: A2B_aP6_2_2i_i S29
3. **aP12** .....
3.1. FeS_2: AB2_aP12_1_4a_8a S25
4. **aP16** .....
4.1. $AsKSe_2$: ABC2_aP16_1_4a_4a_8a S27

cF .....
1. **cF4** .....
1.1. Face-Centered Cubic: A_cF4_225_a S597
2. **cF8** .....
2.1. Zincblende: AB_cF8_216_c_a S542
2.2. Rock Salt: AB_cF8_225_a_b S601
2.3. Diamond: A_cF8_227_a S614
3. **cF12** .....
3.1. Half-Heusler: ABC_cF12_216_b_c_a S540
3.2. Fluorite: AB2_cF12_225_a_c S591
4. **cF16** .....
4.1. BiF_3: AB3_cF16_225_a_bc S584
4.2. Heusler: AB2C_cF16_225_a_c_b S595
4.3. NaTl: AB_cF16_227_a_b S607
5. **cF24** .....
5.1. $AuBe_5$: AB5_cF24_216_a_ce S538
5.2. Ideal β-Cristobalite: A2B_cF24_227_c_a .. S603
5.3. Cu_2Mg Cubic Laves: A2B_cF24_227_d_a . S612
6. **cF32** .....
6.1. Ca_7Ge: A7B_cF32_225_bd_a S582
7. **cF48** .....
7.1. CTi_2: AB2_cF48_227_c_e S618
8. **cF52** .....
8.1. UB_{12}: A12B_cF52_225_i_a S589
9. **cF56** .....
9.1. Spinel: A2BC4_cF56_227_d_a_e S616
10. **cF96** .....
10.1. $NiTi_2$: AB2_cF96_227_e_cf S605
11. **cF108** .....
11.1. Model of Austenite: AB18C8_cF108_225_a_eh_f S599
12. **cF112** .....
12.1. Fe_3W_3C: AB3C3_cF112_227_c_de_f S620
13. **cF116** .....
13.1. $Cr_{23}C_6$: A6B23_cF116_225_e_acfh S593
14. **cF128** .....
14.1. Model of Ferrite: A9B16C7_cF128_225_acd_2f_be S586
15. **cF136** .....
15.1. Si_{34} Clathrate: A_cF136_227_aeg S609

cI .....
1. **cI2** .....
1.1. Body-Centered Cubic: A_cI2_229_a S622
2. **cI8** .....
2.1. High-Pressure H_3S: A3B_cI8_229_b_a S624
3. **cI10** .....
3.1. SiF_4: A4B_cI10_217_c_a S544
4. **cI14** .....
4.1. Pt_3O_4: A4B3_cI14_229_c_b S626
5. **cI16** .....
5.1. CoU: AB_cI16_199_a_a S508
5.2. BC8: A_cI16_206_c S528
5.3. High-Pressure cI16 Li: A_cI16_220_c S550
5.4. Model of Ferrite: AB4C3_cI16_229_a_c_b . S632
6. **cI26** .....
6.1. $Al_{12}W$: A12B_cI26_204_g_a S516
7. **cI32** .....
7.1. Skutterudite: A3B_cI32_204_g_c S514
7.2. Model of Austenite: AB12C3_cI32_229_a_h_b S630
8. **cI40** .....
8.1. Ga_4Ni: A4B_cI40_197_cde_c S496
8.2. Pu_2C_3: A3B2_cI40_220_d_c S552
9. **cI52** .....
9.1. γ-Brass: A5B8_cI52_217_ce_cg S548
10. **cI54** .....
10.1. Sb_2Tl_7: A2B7_cI54_229_e_afh S628
11. **cI58** .....
11.1. α-Mn: A_cI58_217_ac2g S546
12. **cI80** .....
12.1. Bixbyite: AB3C6_cI80_206_a_d_e S524
13. **cI112** .....
13.1. Ga_4Ni_3: A4B3_cI112_230_af_g S634
14. **cI162** .....
14.1. Bergman $[Mg_{32}(Al,Zn)_{49}]$: AB32C48_cI162_204_a_2efg_2gh S510

cP .....
1. **cP1** .....
1.1. α-Po: A_cP1_221_a S564
2. **cP2** .....
2.1. CsCl: AB_cP2_221_b_a S554

3. **cP4** .....
   3.1. Cu_3Au: AB3_cP4_221_a_c S562
   3.2. α-ReO_3: A3B_cP4_221_d_a S571
4. **cP5** .....
   4.1. Fe_4C: AB4_cP5_215_a_e S534
   4.2. Cubic Perovskite: AB3C_cP5_221_a_c_b .. S558
5. **cP6** .....
   5.1. NbO: AB_cP6_221_c_d S556
   5.2. Cuprite: A2B_cP6_224_b_a S580
6. **cP7** .....
   6.1. CaB_6: A6B_cP7_221_f_a S573
7. **cP8** .....
   7.1. α-N: A_cP8_198_2a S502
   7.2. α-CO[‡‡]: AB_cP8_198_a_a S504
   7.3. FeSi[‡‡]: AB_cP8_198_a_a S506
   7.4. α-N: A_cP8_205_c S518
   7.5. Sulvanite: A3B4C_cP8_215_d_e_a S532
   7.6. Cubic Lazarevićite: AB3C4_cP8_215_a_c_e S536
   7.7. Cr_3Si: A3B_cP8_223_c_a S575
8. **cP12** .....
   8.1. Ullmanite: ABC_cP12_198_a_a_a S498
   8.2. Pyrite: AB2_cP12_205_a_c S522
9. **cP16** .....
   9.1. Ammonia: A3B_cP16_198_b_a S500
   9.2. SC16: AB_cP16_205_c_c S520
   9.3. Model of Ferrite: AB11CD3_cP16_221_a_dg_b_c S569
10. **cP20** .....
   10.1. β-Mn: A_cP20_213_cd S530
11. **cP32** .....
   11.1. Model of Austenite: AB27CD3_cP32_221_a_dij_b_c S560
12. **cP36** .....
   12.1. $BaHg_{11}$: AB11_cP36_221_c_agij S566
13. **cP46** .....
   13.1. Si_{46} Clathrate: A_cP46_223_dik S577

hP .....
1. **hP1** .....
   1.1. Simple Hexagonal Lattice: A_hP1_191_a .. S442
2. **hP2** .....
   2.1. Tungsten Carbide: AB_hP2_187_d_a S434
   2.2. Hexagonal Close Packed: A_hP2_194_c ... S486
3. **hP3** .....
   3.1. γ-Se: A_hP3_152_a S347
   3.2. ω Phase: AB2_hP3_164_a_d S368
   3.3. BaPtSb: ABC_hP3_187_a_d_f S432
   3.4. Hexagonal ω: AB2_hP3_191_a_d S446
4. **hP4** .....
   4.1. Buckled Graphite: A_hP4_186_ab S420
   4.2. Wurtzite: AB_hP4_186_b_b S424
   4.3. Original BN: AB_hP4_186_b_a S430
   4.4. Li_3N: A3B_hP4_191_bc_a S444
   4.5. α-La: A_hP4_194_ac S458
   4.6. BN: AB_hP4_194_c_d S464
   4.7. Hexagonal Graphite: A_hP4_194_bc S470
   4.8. Lonsdaleite: A_hP4_194_f S480
   4.9. NiAs: AB_hP4_194_c_a S492
5. **hP5** .....
   5.1. Al_3Ni_2: A3B2_hP5_164_ad_d S366
6. **hP6** .....
   6.1. Cinnabar: AB_hP6_154_a_b S349
   6.2. AlB_4Mg: AB4C_hP6_191_a_h_b S438
   6.3. $CaCu_5$: AB5_hP6_191_a_cg S440
   6.4. Cu_2Te: A2B_hP6_191_h_e S448
   6.5. CoSn: AB_hP6_191_f_ad S450
   6.6. Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h S454
   6.7. $CaIn_2$: AB2_hP6_194_b_f S462
   6.8. Molybdenite: AB2_hP6_194_c_f S472
   6.9. LiBC: ABC_hP6_194_c_d_a S478
   6.10. Ni_2In: AB2_hP6_194_c_ad S482
7. **hP8** .....
   7.1. Bainite: AB3_hP8_182_c_g S418
   7.2. Moissanite-4H SiC: AB_hP8_186_ab_ab ... S422
   7.3. AsTi: AB_hP8_194_ad_f S452
   7.4. Na_3As: AB3_hP8_194_c_bf S460
   7.5. $AlCCr_2$: ABC2_hP8_194_d_a_f S466
   7.6. Ni_3Sn: A3B_hP8_194_h_c S468
8. **hP9** .....
   8.1. ζ-AgZn: A2B_hP9_147_g_ad S329
   8.2. Original Fe_2P: A2B_hP9_150_ef_bd S340
   8.3. α-Quartz: A2B_hP9_152_c_a S345
   8.4. β-V_2N: AB2_hP9_162_ad_k S361
   8.5. $CrSi_2$: AB2_hP9_180_d_j S414
   8.6. β-Quartz: A2B_hP9_180_j_c S416
   8.7. Revised Fe_2P: A2B_hP9_189_fg_bc S436
9. **hP12** .....
   9.1. Moissanite-6H SiC: AB_hP12_186_a2b_a2b S426
   9.2. CMo: AB_hP12_194_af_bf S456
   9.3. $MgZn_2$ Hexagonal Laves: AB2_hP12_194_f_ah S476
   9.4. Covellite: AB_hP12_194_df_ce S490
   9.5. β-Tridymite: A2B_hP12_194_cg_f S494
10. **hP14** .....
   10.1. W_2B_5: A5B2_hP14_194_abdf_f S474
11. **hP16** .....
   11.1. AlN_3Ti_4: AB3C4_hP16_194_c_af_ef S484
12. **hP18** .....
   12.1. Mg_2Ni: A2B_hP18_180_fi_bd S412
   12.2. Al_5C_3N: A5B3C_hP18_186_2a3b_2ab_b ... S428
13. **hP24** .....
   13.1. $CrCl_3$: A3B_hP24_151_3c_2a S342
   13.2. H_3Ho: A3B_hP24_165_adg_f S370
   13.3. $MgNi_2$ Hexagonal Laves: AB2_hP24_194_ef_fgh S488
14. **hP36** .....
   14.1. $KAg(CN)_2$: AB2CD2_hP36_163_h_i_bf_i .. S363

hR .....

[‡‡] α-CO and FeSi have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

1. **hR1** .....
   1.1. β-Po[**]: A_hR1_166_a S377
   1.2. α-Hg[**]: A_hR1_166_a S385
2. **hR2** .....
   2.1. CuPt: AB_hR2_166_a_b S373
   2.2. α-As[‖]: A_hR2_166_c S375
   2.3. Rhombohedral Graphite[‖]: A_hR2_166_c .. S389
   2.4. β-O[‖]: A_hR2_166_c S395
3. **hR3** .....
   3.1. α-Sm: A_hR3_166_ac S381
4. **hR4** .....
   4.1. Caswellsilverite: ABC2_hR4_166_a_b_c ... S393
5. **hR5** .....
   5.1. Hazelwoodite : A3B2_hR5_155_e_c S353
   5.2. Bi_2Te_3: A2B3_hR5_166_c_ac S383
6. **hR6** .....
   6.1. Millerite: AB_hR6_160_b_b S355
   6.2. Moissanite 9R: AB_hR6_160_3a_3a S357
7. **hR7** .....
   7.1. Mo_2B_5: A5B2_hR7_166_a2c_c S387
   7.2. CaC_6: A6B_hR7_166_g_a S404
8. **hR8** .....
   8.1. BiI_3: AB3_hR8_148_c_f S333
   8.2. AlF_3 : AB3_hR8_155_c_de S351
9. **hR10** .....
   9.1. Ilmenite: AB3C_hR10_148_c_f_c S338
   9.2. Ferroelectric $LiNbO_3$: ABC3_hR10_161_a_a_b S359
   9.3. Paraelectric $LiNbO_3$[††]: ABC3_hR10_167_a_b_e S406
   9.4. Calcite[††]: ABC3_hR10_167_a_b_e S408
   9.5. Corundum: A2B3_hR10_167_c_e S410
10. **hR12** .....
   10.1. α-B: A_hR12_166_2h S391
11. **hR13** .....
   11.1. Fe_7W_6 μ-phase: A7B6_hR13_166_ah_3c ... S379
12. **hR16** .....
   12.1. Solid Cubane: AB_hR16_148_cf_cf S331
13. **hR26** .....
   13.1. PdAl: AB_hR26_148_b2f_a2f S335
14. **hR105** .....
   14.1. β-B: A_hR105_166_bc9h4i S397

mC .....
1. **mC4** .....
   1.1. α-O: A_mC4_12_i S60
2. **mC6** .....
   2.1. Calaverite: AB2_mC6_12_a_i S52
3. **mC8** .....
   3.1. Tenorite: AB_mC8_15_c_e S80
4. **mC10** .....
   4.1. Monoclinic PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_mC10_8_ab_a_a S39
5. **mC12** .....
   5.1. Po: A_mC12_5_3c S37
6. **mC14** .....
   6.1. Au_5Mn_2: A5B2_mC14_12_a2i_i S58
7. **mC16** .....
   7.1. $AlCl_3$: AB3_mC16_12_g_ij S56
8. **mC28** .....
   8.1. B_2Pd_5: A2B5_mC28_15_f_e2f S78
9. **mC34** .....
   9.1. β-Pu: A_mC34_12_ah3i2j S54
10. **mC40** .....
   10.1. Esseneite: ABC6D2_mC40_15_e_e_3f_f S84
11. **mC48** .....
   11.1. Coesite: A2B_mC48_15_ae3f_2f S82
12. **mC144** .....
   12.1. Monoclinic Low Tridymite: A2B_mC144_9_24a_12a S41

mP .....
1. **mP4** .....
   1.1. High-Pressure Te: A_mP4_4_2a S35
   1.2. NiTi: AB_mP4_11_e_e S46
2. **mP10** .....
   2.1. $KClO_3$: ABC3_mP10_11_e_e_ef S48
3. **mP12** .....
   3.1. SiO_2: A2B_mP12_3_bc3e_2e S33
   3.2. Sylvanite: ABC4_mP12_13_e_a_2g S61
   3.3. Baddeleyite: A2B_mP12_14_2e_e S68
4. **mP16** .....
   4.1. α-Pu: A_mP16_11_8e S50
5. **mP32** .....
   5.1. β-Se: A_mP32_14_8e S70
6. **mP64** .....
   6.1. Se: A_mP64_14_16e S73
7. **mP84** .....
   7.1. Monoclinic Phosphorus: A_mP84_13_21g .. S63

oC .....
1. **oC4** .....
   1.1. α-U: A_oC4_63_c S181
2. **oC8** .....
   2.1. C_2CeNi: A2BC_oC8_38_e_a_b S107
   2.2. CrB: AB_oC8_63_c_c S179
   2.3. α-Ga[§]: A_oC8_64_f S183

[**] β-Po and α-Hg have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‖] α-As, rhombohedral graphite, and β-O have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[††] Paraelectric $LiNbO_3$ and calcite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[§] α-Ga, black phosphorus, and molecular iodine have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

2.4. Black Phosphorus[§]: A_oC8_64_f S188
2.5. Molecular Iodine[§]: A_oC8_64_f S190
2.6. α-IrV: AB_oC8_65_j_g S192
2.7. Predicted $CdPt_3$: AB3_oC8_65_a_bf S196

3. **oC12** .....
3.1. $HgBr_2$: A2B_oC12_36_2a_a S105
3.2. Au_2V: A2B_oC12_38_de_ab S109
3.3. $ZrSi_2$: A2B_oC12_63_2c_c S177

4. **oC16** .....
4.1. $SrCuO_2$: AB2C_oC16_63_c_2c_c S175
4.2. Ga_3Pt_5: A3B5_oC16_65_ah_bej S194

5. **oC20** .....
5.1. $PtSn_4$: AB4_oC20_41_a_2b S111

6. **oC24** .....
6.1. Orthorhombic Tridymite: A2B_oC24_20_abc_c S92
6.2. $PdSn_2$: AB2_oC24_41_2a_2b S113

7. **oC80** .....
7.1. MgB_2C_2: A2B2C_oC80_64_efg_efg_df S185

oF .....

1. **oF8** .....
1.1. TlF: AB_oF8_69_a_b S198
1.2. γ-Pu: A_oF8_70_a S200

2. **oF24** .....
2.1. $TiSi_2$: A2B_oF24_70_e_a S202

3. **oF72** .....
3.1. GeS_2: AB2_oF72_43_ab_3b S115

4. **oF128** .....
4.1. α-S: A_oF128_70_4h S204

oI .....

1. **oI4** .....
1.1. High-pressure GaAs: AB_oI4_44_a_b S118

2. **oI6** .....
2.1. $ReSi_2$: AB2_oI6_71_a_i S207
2.2. $MoPt_2$: AB2_oI6_71_a_g S208

3. **oI12** .....
3.1. SiS_2: A2B_oI12_72_j_a S210

oP .....

1. **oP2** .....
1.1. High-Pressure CdTe: AB_oP2_25_b_a S94

2. **oP4** .....
2.1. β'-AuCd: AB_oP4_51_e_f S122
2.2. Vulcanite: AB_oP4_59_a_b S136

3. **oP6** .....
3.1. Hydrophilite[*]: AB2_oP6_58_a_g S130
3.2. η-Fe_2C[*]: AB2_oP6_58_a_g S132
3.3. Marcasite[*]: AB2_oP6_58_a_g S134
3.4. CNCl: ABC_oP6_59_a_a_a S138

4. **oP8** .....
4.1. Modderite: AB_oP8_33_a_a S100
4.2. TlF-II: AB_oP8_57_d_d S128
4.3. β-$TiCu_3$: A3B_oP8_59_bf_a S140
4.4. GeS[‡]: AB_oP8_62_c_c S160
4.5. MnP[‡]: AB_oP8_62_c_c S162
4.6. α-Np: A_oP8_62_2c S169
4.7. FeB[‡]: AB_oP8_62_c_c S171
4.8. SnS[‡]: AB_oP8_62_c_c S173

5. **oP12** .....
5.1. $AlPS_4$: ABC4_oP12_16_ag_cd_2u S86
5.2. Naumannite: A2B_oP12_19_2a_a S90
5.3. Co_2Si[†]: A2B_oP12_62_2c_c S154
5.4. $HgCl_2$[†]: A2B_oP12_62_2c_c S156
5.5. Cotunnite[†]: A2B_oP12_62_2c_c S158

6. **oP13** .....
6.1. 1212C [$YBa_2Cu_3O_{7-x}$]: A2B3C7D_oP13_47_t_aq_eqrs_h S120

7. **oP16** .....
7.1. BaS_3: AB3_oP16_18_ab_3c S88
7.2. Enargite: AB3C4_oP16_31_a_ab_2ab S98
7.3. KCNS: ABCD_oP16_57_d_c_d_d S126
7.4. CdSb: AB_oP16_61_c_c S142
7.5. Chalcostibite: AB2C_oP16_62_c_2c_c S152
7.6. Cementite: AB3_oP16_62_c_cd S164

8. **oP20** .....
8.1. Sb_2O_3: A3B2_oP20_56_ce_e S124
8.2. Stibnite: A3B2_oP20_62_3c_2c S146
8.3. $CaTiO_3$ Pnma Perovskite: AB3C_oP20_62_c_cd_a S148
8.4. MgB_4: A4B_oP20_62_2cd_c S150

9. **oP24** .....
9.1. Krennerite: AB2_oP24_28_acd_2c3d S96
9.2. Brookite: A2B_oP24_61_2c_c S144

10. **oP32** .....
10.1. AsK_3S_4: AB3C4_oP32_33_a_3a_4a S102

11. **oP40** .....
11.1. C_3Cr_7: A3B7_oP40_62_cd_3c2d S166

tI .....

1. **tI2** .....
1.1. In[¶]: A_tI2_139_a S286
1.2. α-Pa[¶]: A_tI2_139_a S302

2. **tI4** .....
2.1. Hypothetical BCT5 Si: A_tI4_139_e S280
2.2. β-Sn: A_tI4_141_a S312

3. **tI6** .....
3.1. $MoSi_2$: AB2_tI6_139_a_e S292
3.2. ThH_2: A2B_tI6_139_d_a S300

4. **tI8** .....

[*]Hydrophilite, η-Fe_2C, and marcasite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡]GeS, MnP, FeB, and SnS have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[†]Co_2Si, $HgCl_2$, and cotunnite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[¶]In and α-Pa have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

4.1. Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h S288
4.2. Al_3Ti: A3B_tI8_139_bd_a S290
4.3. NbP: AB_tI8_141_a_b S322

5. **tI10** .....
5.1. Ni_4Mo: AB4_tI10_87_a_h S220
5.2. Al_4Ba: A4B_tI10_139_de_a S296

6. **tI12** .....
6.1. BPO_4: AB4C_tI12_82_c_g_a S212
6.2. Khatyrkite: A2B_tI12_140_h_a S304
6.3. Anatase: A2B_tI12_141_e_a S316

7. **tI14** .....
7.1. $CdAl_2S_4$: A2BC4_tI14_82_bc_a_g S214
7.2. 0201 [$(La,Ba)_2CuO_4$]: AB2C4_tI14_139_a_e_ce S282

8. **tI16** .....
8.1. Stannite: A2BC4D_tI16_121_d_a_i_b S233
8.2. Chalcopyrite: ABC2_tI16_122_a_b_d S235
8.3. Al_3Zr: A3B_tI16_139_cde_e S278
8.4. SiU_3: AB3_tI16_140_b_ah S306
8.5. SeTl: AB_tI16_140_ab_h S308
8.6. MoB: AB_tI16_141_e_e S318

9. **tI18** .....
9.1. Ti_5Te_4: A4B5_tI18_87_h_ah S218
9.2. V_4Zn_5: A4B5_tI18_139_i_ah S294
9.3. Pt_8Ti: A8B_tI18_139_hi_a S298

10. **tI24** .....
10.1. Zircon: A4BC_tI24_141_h_b_a S310
10.2. Ga_2Hf: A2B_tI24_141_2e_e S320

11. **tI26** .....
11.1. $Mn_{12}Th$: A12B_tI26_139_fij_a S284

12. **tI28** .....
12.1. Hausmannite: A3B4_tI28_141_ad_h S314

13. **tI80** .....
13.1. β-In_2S_3: A2B3_tI80_141_ceh_3h S324

14. **tI96** .....
14.1. $PPrS_4$: ABC4_tI96_142_e_ab_2g S326

tP .....

1. **tP2** .....
1.1. CuAu: AB_tP2_123_a_d S241

2. **tP4** .....
2.1. $CuTi_3$: AB3_tP4_123_a_ce S239
2.2. $CaCuO_2$: ABC2_tP4_123_d_a_f S243
2.3. β-Np: A_tP4_129_ac S249
2.4. PbO: AB_tP4_129_a_c S255
2.5. γ-CuTi: AB_tP4_129_c_c S257
2.6. PtS: AB_tP4_131_c_e S259
2.7. γ-N: A_tP4_136_f S274

3. **tP5** .....
3.1. Tetragonal PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_tP5_99_bc_a_b S229

4. **tP6** .....
4.1. Matlockite: ABC_tP6_129_c_a_c S251
4.2. Cu_2Sb: A2B_tP6_129_ac_c S253
4.3. Rutile: A2B_tP6_136_f_a S269

5. **tP7** .....
5.1. $HoCoGa_5$: AB5C_tP7_123_b_ci_a S237

6. **tP8** .....
6.1. BaS_3: AB3_tP8_113_a_ce S231
6.2. AsCuSiZr: ABCD_tP8_129_c_b_a_c S247
6.3. β-BeO: AB_tP8_136_g_f S267

7. **tP10** .....
7.1. Si_2U_3: A2B3_tP10_127_g_ah S245

8. **tP12** .....
8.1. α-Cristobalite: A2B_tP12_92_b_a S222
8.2. "ST12" of Si: A_tP12_96_ab S227

9. **tP16** .....
9.1. PdS: AB_tP16_84_cej_k S216
9.2. Cl: A_tP16_138_j S276

10. **tP30** .....
10.1. β-U: A_tP30_136_bf2ij S264
10.2. σ-CrFe: sigma_tP30_136_bf2ij S271

11. **tP36** .....
11.1. Keatite: A2B_tP36_96_3b_ab S224

12. **tP50** .....
12.1. T-50 B: A_tP50_134_b2m2n S261

Strukturbericht Designation Index

"40" .....
1. NbP: AB_tI8_141_a_b S322

A1 .....
1. Face-Centered Cubic: A_cF4_225_a S597

A2 .....
1. Body-Centered Cubic: A_cI2_229_a S622

A3' .....
1. α-La: A_hP4_194_ac S458

A3 .....
1. Hexagonal Close Packed: A_hP2_194_c S486

A4 .....
1. Diamond: A_cF8_227_a S614

A5 .....
1. β-Sn: A_tI4_141_a S312

A6 .....
1. In[¶]: A_tI2_139_a S286

A7 .....
1. α-As[‖]: A_hR2_166_c S375

A8 .....
1. γ-Se: A_hP3_152_a S347

A9 .....
1. Hexagonal Graphite: A_hP4_194_bc S470

A10 .....

[¶]In and α-Pa have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‖]α-As, rhombohedral graphite, and β-O have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

1. α-Hg[**]: A_hR1_166_a S385
A11 .....
1. α-Ga[§]: A_oC8_64_f S183
A12 .....
1. α-Mn: A_cI58_217_ac2g S546
A13 .....
1. β-Mn: A_cP20_213_cd S530
A14 .....
1. Molecular Iodine[§]: A_oC8_64_f S190
A15 .....
1. Cr_3Si: A3B_cP8_223_c_a S575
A16 .....
1. α-S: A_oF128_70_4h S204
A17 .....
1. Black Phosphorus[§]: A_oC8_64_f S188
A18 .....
1. Cl: A_tP16_138_j S276
A19 .....
1. Po: A_mC12_5_3c S37
A20 .....
1. α-U: A_oC4_63_c S181
A_a .....
1. α-Pa[¶]: A_tI2_139_a S302
A_b .....
1. β-U: A_tP30_136_bf2ij S264
A_c .....
1. α-Np: A_oP8_62_2c S169
A_d .....
1. β-Np: A_tP4_129_ac S249
A_f .....
1. Simple Hexagonal Lattice: A_hP1_191_a S442
A_g .....
1. T-50 B: A_tP50_134_b2m2n S261
A_h .....
1. α-Po: A_cP1_221_a S564
A_i .....
1. β-Po[**]: A_hR1_166_a S377
A_k .....
1. Se: A_mP64_14_16e S73
A_l .....
1. β-Se: A_mP32_14_8e S70
B1 .....
1. Rock Salt: AB_cF8_225_a_b S601
B2 .....
1. CsCl: AB_cP2_221_b_a S554
B3 .....
1. Zincblende: AB_cF8_216_c_a S542
B4 .....
1. Wurtzite: AB_hP4_186_b_b S424
B5 .....
1. Moissanite-4H SiC: AB_hP8_186_ab_ab S422
B6 .....
1. Moissanite-6H SiC: AB_hP12_186_a2b_a2b S426
$B8_1$ .....
1. NiAs: AB_hP4_194_c_a S492
$B8_2$ .....
1. Ni_2In: AB2_hP6_194_c_ad S482
B9 .....
1. Cinnabar: AB_hP6_154_a_b S349
B10 .....
1. PbO: AB_tP4_129_a_c S255
B11 .....
1. γ-CuTi: AB_tP4_129_c_c S257
B12 .....
1. Original BN: AB_hP4_186_b_a S430
B13 .....
1. Millerite: AB_hR6_160_b_b S355
B16 .....
1. GeS[‡]: AB_oP8_62_c_c S160
B17 .....
1. PtS: AB_tP4_131_c_e S259
B18 .....
1. Covellite: AB_hP12_194_df_ce S490
B19 .....
1. β'-AuCd: AB_oP4_51_e_f S122
B20 .....
1. FeSi[‡‡]: AB_cP8_198_a_a S506
B21 .....
1. α-CO[‡‡]: AB_cP8_198_a_a S504
B24 .....
1. TlF: AB_oF8_69_a_b S198
B26 .....
1. Tenorite: AB_mC8_15_c_e S80
B27 .....
1. FeB[‡]: AB_oP8_62_c_c S171
B29 .....
1. SnS[‡]: AB_oP8_62_c_c S173
B31 .....
1. MnP[‡]: AB_oP8_62_c_c S162
B32 .....
1. NaTl: AB_cF16_227_a_b S607
B33 .....

[**] β-Po and α-Hg have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[§] α-Ga, black phosphorus, and molecular iodine have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡] GeS, MnP, FeB, and SnS have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡‡] α-CO and FeSi have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

1. CrB: AB_oC8_63_c_c S179

B34 .....

1. PdS: AB_tP16_84_cej_k S216

B35 .....

1. CoSn: AB_hP6_191_f_ad S450

B37 .....

1. SeTl: AB_tI16_140_ab_h S308

B_a .....

1. CoU: AB_cI16_199_a_a S508

B_b .....

1. ζ-AgZn: A2B_hP9_147_g_ad S329

B_e .....

1. CdSb: AB_oP16_61_c_c S142

B_g .....

1. MoB: AB_tI16_141_e_e S318

B_h .....

1. Tungsten Carbide: AB_hP2_187_d_a S434

B_i .....

1. AsTi: AB_hP8_194_ad_f S452

B_k .....

1. BN: AB_hP4_194_c_d S464

C1 .....

1. Fluorite: AB2_cF12_225_a_c S591

$C1_b$ .....

1. Half-Heusler: ABC_cF12_216_b_c_a S540

C2 .....

1. Pyrite: AB2_cP12_205_a_c S522

C3 .....

1. Cuprite: A2B_cP6_224_b_a S580

C4 .....

1. Rutile: A2B_tP6_136_f_a S269

C5 .....

1. Anatase: A2B_tI12_141_e_a S316

C6 .....

1. ω Phase: AB2_hP3_164_a_d S368

C7 .....

1. Molybdenite: AB2_hP6_194_c_f S472

C8 .....

1. β-Quartz: A2B_hP9_180_j_c S416

C9 .....

1. Ideal β-Cristobalite: A2B_cF24_227_c_a S603

C10 .....

1. β-Tridymite: A2B_hP12_194_cg_f S494

$C11_b$ .....

1. $MoSi_2$: AB2_tI6_139_a_e S292

C14 .....

1. $MgZn_2$ Hexagonal Laves: AB2_hP12_194_f_ah . S476

C15 .....

1. Cu_2Mg Cubic Laves: A2B_cF24_227_d_a S612

$C15_b$ .....

1. $AuBe_5$: AB5_cF24_216_a_ce S538

C16 .....

1. Khatyrkite: A2B_tI12_140_h_a S304

C18 .....

1. Marcasite*: AB2_oP6_58_a_g S134

C19 .....

1. α-Sm: A_hR3_166_ac S381

C21 .....

1. Brookite: A2B_oP24_61_2c_c S144

C22 .....

1. Original Fe_2P: A2B_hP9_150_ef_bd S340
2. Revised Fe_2P: A2B_hP9_189_fg_bc S436

C23 .....

1. Cotunnite†: A2B_oP12_62_2c_c S158

C24 .....

1. $HgBr_2$: A2B_oC12_36_2a_a S105

C25 .....

1. $HgCl_2$†: A2B_oP12_62_2c_c S156

C32 .....

1. Hexagonal ω: AB2_hP3_191_a_d S446

C33 .....

1. Bi_2Te_3: A2B3_hR5_166_c_ac S383

C34 .....

1. Calaverite: AB2_mC6_12_a_i S52

C35 .....

1. Hydrophilite*: AB2_oP6_58_a_g S130

C36 .....

1. $MgNi_2$ Hexagonal Laves: AB2_hP24_194_ef_fgh S488

C37 .....

1. Co_2Si†: A2B_oP12_62_2c_c S154

C38 .....

1. Cu_2Sb: A2B_tP6_129_ac_c S253

C40 .....

1. $CrSi_2$: AB2_hP9_180_d_j S414

C42 .....

1. SiS_2: A2B_oI12_72_j_a S210

C43 .....

1. Baddeleyite: A2B_mP12_14_2e_e S68

C44 .....

1. GeS_2: AB2_oF72_43_ab_3b S115

C46 .....

1. Krennerite: AB2_oP24_28_acd_2c3d S96

C49 .....

1. $ZrSi_2$: A2B_oC12_63_2c_c S177

C54 .....

1. $TiSi_2$: A2B_oF24_70_e_a S202

C_a .....

1. Mg_2Ni: A2B_hP18_180_fi_bd S412

C_e .....

1. $PdSn_2$: AB2_oC24_41_2a_2b S113

C_h .....

*Hydrophilite, η-Fe_2C, and marcasite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

†Co_2Si, $HgCl_2$, and cotunnite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

1. Cu_2Te: A2B_hP6_191_h_e S448
$D0_2$ .....
1. Skutterudite: A3B_cI32_204_g_c S514
$D0_3$ .....
1. BiF_3: AB3_cF16_225_a_bc S584
$D0_4$ .....
1. $CrCl_3$: A3B_hP24_151_3c_2a S342
$D0_5$ .....
1. BiI_3: AB3_hR8_148_c_f S333
$D0_9$ .....
1. α-ReO_3: A3B_cP4_221_d_a S571
$D0_{11}$ .....
1. Cementite: AB3_oP16_62_c_cd S164
$D0_{14}$ .....
1. AlF_3 : AB3_hR8_155_c_de S351
$D0_{15}$ .....
1. $AlCl_3$: AB3_mC16_12_g_ij S56
$D0_{17}$ .....
1. BaS_3: AB3_tP8_113_a_ce S231
$D0_{18}$ .....
1. Na_3As: AB3_hP8_194_c_bf S460
$D0_{19}$ .....
1. Ni_3Sn: A3B_hP8_194_h_c S468
$D0_{22}$ .....
1. Al_3Ti: A3B_tI8_139_bd_a S290
$D0_{23}$ .....
1. Al_3Zr: A3B_tI16_139_cde_e S278
$D0_a$ .....
1. β-$TiCu_3$: A3B_oP8_59_bf_a S140
$D0_c$ .....
1. SiU_3: AB3_tI16_140_b_ah S306
D1 .....
1. Ammonia: A3B_cP16_198_b_a S500
$D1_3$ .....
1. Al_4Ba: A4B_tI10_139_de_a S296
$D1_a$ .....
1. Ni_4Mo: AB4_tI10_87_a_h S220
$D1_c$ .....
1. $PtSn_4$: AB4_oC20_41_a_2b S111
$D2_1$ .....
1. CaB_6: A6B_cP7_221_f_a S573
$D2_b$ .....
1. $Mn_{12}Th$: A12B_tI26_139_fij_a S284
$D2_d$ .....
1. $CaCu_5$: AB5_hP6_191_a_cg S440
$D2_e$ .....
1. $BaHg_{11}$: AB11_cP36_221_c_agij S566
$D2_f$ .....
1. UB_{12}: A12B_cF52_225_i_a S589
$D5_1$ .....
1. Corundum: A2B3_hR10_167_c_e S410
$D5_3$ .....
1. Bixbyite: AB3C6_cI80_206_a_d_e S524
$D5_8$ .....
1. Stibnite: A3B2_oP20_62_3c_2c S146
$D5_{11}$ .....
1. Sb_2O_3: A3B2_oP20_56_ce_e S124
$D5_{13}$ .....
1. Al_3Ni_2: A3B2_hP5_164_ad_d S366
$D5_a$ .....
1. Si_2U_3: A2B3_tP10_127_g_ah S245
$D5_c$ .....
1. Pu_2C_3: A3B2_cI40_220_d_c S552
$D5_e$ .....
1. Hazelwoodite : A3B2_hR5_155_e_c S353
$D8_4$ .....
1. $Cr_{23}C_6$: A6B23_cF116_225_e_acfh S593
$D8_5$ .....
1. Fe_7W_6 μ-phase: A7B6_hR13_166_ah_3c S379
$D8_b$ .....
1. σ-CrFe: sigma_tP30_136_bf2ij S271
$D8_h$ .....
1. W_2B_5: A5B2_hP14_194_abdf_f S474
$D8_i$ .....
1. Mo_2B_5: A5B2_hR7_166_a2c_c S387
$D10_1$ .....
1. C_3Cr_7: A3B7_oP40_62_cd_3c2d S166
$E0_1$ .....
1. Matlockite: ABC_tP6_129_c_a_c S251
$E1_1$ .....
1. Chalcopyrite: ABC2_tI16_122_a_b_d S235
$E1_b$ .....
1. Sylvanite: ABC4_mP12_13_e_a_2g S61
$E2_1$ .....
1. Cubic Perovskite: AB3C_cP5_221_a_c_b S558
E3 .....
1. $CdAl_2S_4$: A2BC4_tI14_82_bc_a_g S214
$E9_3$ .....
1. Fe_3W_3C: AB3C3_cF112_227_c_de_f S620
$E9_4$ .....
1. Al_5C_3N: A5B3C_hP18_186_2a3b_2ab_b S428
$F0_1$ .....
1. Ullmanite: ABC_cP12_198_a_a_a S498
$F5_1$ .....
1. Caswellsilverite: ABC2_hR4_166_a_b_c S393
$F5_6$ .....
1. Chalcostibite: AB2C_oP16_62_c_2c_c S152
$F5_9$ .....
1. KCNS: ABCD_oP16_57_d_c_d_d S126
$F5_{10}$ .....
1. $KAg(CN)_2$: AB2CD2_hP36_163_h_i_bf_i S363
$G0_6$ .....
1. $KClO_3$: ABC3_mP10_11_e_e_ef S48
$G0_1$ .....

1. Calcite[††]: ABC3_hR10_167_a_b_e S408

$H0_7$ .....

1. BPO_4: AB4C_tI12_82_c_g_a S212

$H1_1$ .....

1. Spinel: A2BC4_cF56_227_d_a_e S616

$H2_4$ .....

1. Sulvanite: A3B4C_cP8_215_d_e_a S532

$H2_5$ .....

1. Enargite: AB3C4_oP16_31_a_ab_2ab S98

$H2_6$ .....

1. Stannite: A2BC4D_tI16_121_d_a_i_b S233

$L1_0$ .....

1. CuAu: AB_tP2_123_a_d S241

$L1_1$ .....

1. CuPt: AB_hR2_166_a_b S373

$L1_2$ .....

1. Cu_3Au: AB3_cP4_221_a_c S562

$L1_3$ .....

1. Predicted $CdPt_3$: AB3_oC8_65_a_bf S196

$L2_1$ .....

1. Heusler: AB2C_cF16_225_a_c_b S595

$L2_2$ .....

1. Sb_2Tl_7: A2B7_cI54_229_e_afh S628

$L6_0$ .....

1. $CuTi_3$: AB3_tP4_123_a_ce S239

L'2 .....

1. ThH_2: A2B_tI6_139_d_a S300

None .....

1. FeS_2: AB2_aP12_1_4a_8a S25
2. $AsKSe_2$: ABC2_aP16_1_4a_4a_8a S27
3. P_2I_4: A2B_aP6_2_2i_i S29
4. Cf: A_aP4_2_aci S31
5. SiO_2: A2B_mP12_3_bc3e_2e S33
6. High-Pressure Te: A_mP4_4_2a S35
7. Monoclinic PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_mC10_8_ab_a_a S39
8. Monoclinic Low Tridymite: A2B_mC144_9_24a_12a S41
9. NiTi: AB_mP4_11_e_e S46
10. α-Pu: A_mP16_11_8e S50
11. β-Pu: A_mC34_12_ah3i2j S54
12. Au_5Mn_2: A5B2_mC14_12_a2i_i S58
13. α-O: A_mC4_12_i S60
14. Monoclinic Phosphorus: A_mP84_13_21g S63
15. B_2Pd_5: A2B5_mC28_15_f_e2f S78
16. Coesite: A2B_mC48_15_ae3f_2f S82
17. Esseneite: ABC6D2_mC40_15_e_e_3f_f S84
18. $AlPS_4$: ABC4_oP12_16_ag_cd_2u S86
19. BaS_3: AB3_oP16_18_ab_3c S88
20. Naumannite: A2B_oP12_19_2a_a S90
21. Orthorhombic Tridymite: A2B_oC24_20_abc_c S92
22. High-Pressure CdTe: AB_oP2_25_b_a S94
23. Modderite: AB_oP8_33_a_a S100
24. AsK_3S_4: AB3C4_oP32_33_a_3a_4a S102
25. C_2CeNi: A2BC_oC8_38_e_a_b S107
26. Au_2V: A2B_oC12_38_de_ab S109
27. High-pressure GaAs: AB_oI4_44_a_b S118
28. 1212C [$YBa_2Cu_3O_{7-x}$]: A2B3C7D_oP13_47_t_aq_eqrs_h S120
29. TlF-II: AB_oP8_57_d_d S128
30. η-Fe_2C[*]: AB2_oP6_58_a_g S132
31. Vulcanite: AB_oP4_59_a_b S136
32. CNCl: ABC_oP6_59_a_a_a S138
33. $CaTiO_3$ Pnma Perovskite: AB3C_oP20_62_c_cd_a S148
34. MgB_4: A4B_oP20_62_2cd_c S150
35. $SrCuO_2$: AB2C_oC16_63_c_2c_c S175
36. MgB_2C_2: A2B2C_oC80_64_efg_efg_df S185
37. α-IrV: AB_oC8_65_j_g S192
38. Ga_3Pt_5: A3B5_oC16_65_ah_bej S194
39. γ-Pu: A_oF8_70_a S200
40. $ReSi_2$: AB2_oI6_71_a_i S207
41. $MoPt_2$: AB2_oI6_71_a_g S208
42. Ti_5Te_4: A4B5_tI18_87_h_ah S218
43. α-Cristobalite: A2B_tP12_92_b_a S222
44. Keatite: A2B_tP36_96_3b_ab S224
45. "ST12" of Si: A_tP12_96_ab S227
46. Tetragonal PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_tP5_99_bc_a_b S229
47. $HoCoGa_5$: AB5C_tP7_123_b_ci_a S237
48. $CaCuO_2$: ABC2_tP4_123_d_a_f S243
49. AsCuSiZr: ABCD_tP8_129_c_b_a_c S247
50. β-BeO: AB_tP8_136_g_f S267
51. γ-N: A_tP4_136_f S274
52. Hypothetical BCT5 Si: A_tI4_139_e S280
53. 0201 [$(La,Ba)_2CuO_4$]: AB2C4_tI14_139_a_e_ce . S282
54. Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h S288
55. V_4Zn_5: A4B5_tI18_139_i_ah S294
56. Pt_8Ti: A8B_tI18_139_hi_a S298
57. Zircon: A4BC_tI24_141_h_b_a S310
58. Hausmannite: A3B4_tI28_141_ad_h S314
59. Ga_2Hf: A2B_tI24_141_2e_e S320
60. β-In_2S_3: A2B3_tI80_141_ceh_3h S324
61. $PPrS_4$: ABC4_tI96_142_e_ab_2g S326
62. Solid Cubane: AB_hR16_148_cf_cf S331
63. PdAl: AB_hR26_148_b2f_a2f S335
64. Ilmenite: AB3C_hR10_148_c_f_c S338
65. α-Quartz: A2B_hP9_152_c_a S345
66. Moissanite 9R: AB_hR6_160_3a_3a S357
67. Ferroelectric $LiNbO_3$: ABC3_hR10_161_a_a_b .. S359
68. β-V_2N: AB2_hP9_162_ad_k S361

[††]Paraelectric $LiNbO_3$ and calcite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

69. H_3Ho: A3B_hP24_165_adg_f S370
70. Rhombohedral Graphite[‖]: A_hR2_166_c S389
71. α-B: A_hR12_166_2h S391
72. β-O[‖]: A_hR2_166_c S395
73. β-B: A_hR105_166_bc9h4i S397
74. CaC_6: A6B_hR7_166_g_a S404
75. Paraelectric $LiNbO_3$[††]: ABC3_hR10_167_a_b_e . S406
76. Bainite: AB3_hP8_182_c_g S418
77. Buckled Graphite: A_hP4_186_ab S420
78. BaPtSb: ABC_hP3_187_a_d_f S432
79. AlB_4Mg: AB4C_hP6_191_a_h_b S438
80. Li_3N: A3B_hP4_191_bc_a S444
81. Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h S454
82. CMo: AB_hP12_194_af_bf S456
83. $CaIn_2$: AB2_hP6_194_b_f S462
84. $AlCCr_2$: ABC2_hP8_194_d_a_f S466
85. LiBC: ABC_hP6_194_c_d_a S478
86. Lonsdaleite: A_hP4_194_f S480
87. AlN_3Ti_4: AB3C4_hP16_194_c_af_ef S484
88. Ga_4Ni: A4B_cI40_197_cde_c S496
89. α-N: A_cP8_198_2a S502
90. Bergman [$Mg_{32}(Al,Zn)_{49}$]: AB32C48_cI162_204_a_2efg_2gh S510
91. $Al_{12}W$: A12B_cI26_204_g_a S516
92. α-N: A_cP8_205_c S518
93. SC16: AB_cP16_205_c_c S520
94. BC8: A_cI16_206_c S528
95. Fe_4C: AB4_cP5_215_a_e S534
96. Cubic Lazarevićite: AB3C4_cP8_215_a_c_e S536
97. SiF_4: A4B_cI10_217_c_a S544
98. γ-Brass: A5B8_cI52_217_ce_cg S548
99. High-Pressure cI16 Li: A_cI16_220_c S550
100. NbO: AB_cP6_221_c_d S556
101. Model of Austenite: AB27CD3_cP32_221_a_dij_b_c S560
102. Model of Ferrite: AB11CD3_cP16_221_a_dg_b_c S569
103. Si_{46} Clathrate: A_cP46_223_dik S577
104. Ca_7Ge: A7B_cF32_225_bd_a S582
105. Model of Ferrite: A9B16C7_cF128_225_acd_2f_be S586
106. Model of Austenite: AB18C8_cF108_225_a_eh_f S599
107. $NiTi_2$: AB2_cF96_227_e_cf S605
108. Si_{34} Clathrate: A_cF136_227_aeg S609
109. CTi_2: AB2_cF48_227_c_e S618
110. High-Pressure H_3S: A3B_cI8_229_b_a S624
111. Pt_3O_4: A4B3_cI14_229_c_b S626
112. Model of Austenite: AB12C3_cI32_229_a_h_b .. S630
113. Model of Ferrite: AB4C3_cI16_229_a_c_b S632
114. Ga_4Ni_3: A4B3_cI112_230_af_g S634

Duplicate AFLOW Label Index

AB2_oP6_58_a_g .....
1. Hydrophilite S130
2. η-Fe_2C S132
3. Marcasite S134

A2B_oP12_62_2c_c .....
1. Co_2Si S154
2. $HgCl_2$ S156
3. Cotunnite S158

AB_oP8_62_c_c .....
1. GeS S160
2. MnP S162
3. FeB S171
4. SnS S173

A_oC8_64_f .....
1. α-Ga S183
2. Black Phosphorus S188
3. Molecular Iodine S190

A_tI2_139_a .....
1. In S286
2. α-Pa S302

A_hR2_166_c .....
1. α-As S375
2. Rhombohedral Graphite S389
3. β-O S395

A_hR1_166_a .....
1. β-Po S377
2. α-Hg S385

ABC3_hR10_167_a_b_e .....
1. Paraelectric $LiNbO_3$ S406
2. Calcite S408

AB_cP8_198_a_a .....
1. α-CO S504
2. FeSi S506

CIF Index

1. "ST12" of Si: A_tP12_96_ab S684
2. α-As[‖]: A_hR2_166_c S720
3. α-B: A_hR12_166_2h S724
4. α-CO[‡‡]: AB_cP8_198_a_a S753
5. α-Cristobalite: A2B_tP12_92_b_a S683
6. α-Ga[§]: A_oC8_64_f S674

[‖] α-As, rhombohedral graphite, and β-O have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡‡] α-CO and FeSi have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[§] α-Ga, black phosphorus, and molecular iodine have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

7. α-Hg[**]: A_hR1_166_a S723
8. α-IrV: AB_oC8_65_j_g S676
9. α-La: A_hP4_194_ac S741
10. α-Mn: A_cI58_217_ac2g S765
11. α-N: A_cP8_198_2a S752
12. α-N: A_cP8_205_c S757
13. α-Np: A_oP8_62_2c S670
14. α-O: A_mC4_12_i S645
15. α-Pa[¶]: A_tI2_139_a S702
16. α-Po: A_cP1_221_a S771
17. α-Pu: A_mP16_11_8e S643
18. α-Quartz: A2B_hP9_152_c_a S713
19. α-ReO_3: A3B_cP4_221_d_a S773
20. α-S: A_oF128_70_4h S679
21. α-Sm: A_hR3_166_ac S722
22. α-U: A_oC4_63_c S673
23. β-B: A_hR105_166_bc9h4i S726
24. β-BeO: AB_tP8_136_g_f S693
25. β-In_2S_3: A2B3_tI80_141_ceh_3h S708
26. β-Mn: A_cP20_213_cd S760
27. β-Np: A_tP4_129_ac S689
28. β-O[‖]: A_hR2_166_c S726
29. β-Po[**]: A_hR1_166_a S721
30. β-Pu: A_mC34_12_ah3i2j S644
31. β-Quartz: A2B_hP9_180_j_c S731
32. β-Se: A_mP32_14_8e S648
33. β-Sn: A_tI4_141_a S705
34. β-$TiCu_3$: A3B_oP8_59_bf_a S663
35. β-Tridymite: A2B_hP12_194_cg_f S750
36. β-U: A_tP30_136_bf2ij S693
37. β-V_2N: AB2_hP9_162_ad_k S717
38. β'-AuCd: AB_oP4_51_e_f S659
39. η-Fe_2C[*]: AB2_oP6_58_a_g S662
40. γ-Brass: A5B8_cI52_217_ce_cg S766
41. γ-CuTi: AB_tP4_129_c_c S691
42. γ-N: A_tP4_136_f S695
43. γ-Pu: A_oF8_70_a S677
44. γ-Se: A_hP3_152_a S714
45. ω Phase: AB2_hP3_164_a_d S719
46. σ-CrFe: sigma_tP30_136_bf2ij S694
47. ζ-AgZn: A2B_hP9_147_g_ad S710
48. 0201 [$(La,Ba)_2CuO_4$]: AB2C4_tI14_139_a_e_ce . S697
49. 1212C [$YBa_2Cu_3O_{7-x}$]: A2B3C7D_oP13_47_t_aq_eqrs_h S659
50. $Al_{12}W$: A12B_cI26_204_g_a S756
51. Al_3Ni_2: A3B2_hP5_164_ad_d S718
52. Al_3Ti: A3B_tI8_139_bd_a S699
53. Al_3Zr: A3B_tI16_139_cde_e S696
54. Al_4Ba: A4B_tI10_139_de_a S701
55. Al_5C_3N: A5B3C_hP18_186_2a3b_2ab_b S733
56. AlB_4Mg: AB4C_hP6_191_a_h_b S736
57. $AlCCr_2$: ABC2_hP8_194_d_a_f S743
58. $AlCl_3$: AB3_mC16_12_g_ij S645
59. AlF_3 : AB3_hR8_155_c_de S715
60. AlN_3Ti_4: AB3C4_hP16_194_c_af_ef S748
61. $AlPS_4$: ABC4_oP12_16_ag_cd_2u S651
62. Ammonia: A3B_cP16_198_b_a S752
63. Anatase: A2B_tI12_141_e_a S706
64. AsCuSiZr: ABCD_tP8_129_c_b_a_c S689
65. AsK_3S_4: AB3C4_oP32_33_a_3a_4a S655
66. $AsKSe_2$: ABC2_aP16_1_4a_4a_8a S638
67. AsTi: AB_hP8_194_ad_f S739
68. Au_2V: A2B_oC12_38_de_ab S656
69. Au_5Mn_2: A5B2_mC14_12_a2i_i S645
70. $AuBe_5$: AB5_cF24_216_a_ce S762
71. B_2Pd_5: A2B5_mC28_15_f_e2f S649
72. BC8: A_cI16_206_c S759
73. BN: AB_hP4_194_c_d S743
74. BPO_4: AB4C_tI12_82_c_g_a S681
75. $BaHg_{11}$: AB11_cP36_221_c_agij S771
76. BaPtSb: ABC_hP3_187_a_d_f S734
77. BaS_3: AB3_oP16_18_ab_3c S652
78. BaS_3: AB3_tP8_113_a_ce S685
79. Baddeleyite: A2B_mP12_14_2e_e S647
80. Bainite: AB3_hP8_182_c_g S731
81. Bergman [$Mg_{32}(Al,Zn)_{49}$]: AB32C48_cI162_204_a_2efg_2gh S754
82. Bi_2Te_3: A2B3_hR5_166_c_ac S722
83. BiF_3: AB3_cF16_225_a_bc S777
84. BiI_3: AB3_hR8_148_c_f S711
85. Bixbyite: AB3C6_cI80_206_a_d_e S758
86. Black Phosphorus[§]: A_oC8_64_f S675
87. Body-Centered Cubic: A_cI2_229_a S802
88. Brookite: A2B_oP24_61_2c_c S664
89. Buckled Graphite: A_hP4_186_ab S732
90. C_2CeNi: A2BC_oC8_38_e_a_b S656
91. C_3Cr_7: A3B7_oP40_62_cd_3c2d S670
92. CMo: AB_hP12_194_af_bf S740
93. CNCl: ABC_oP6_59_a_a_a S663
94. CTi_2: AB2_cF48_227_c_e S799
95. Ca_7Ge: A7B_cF32_225_bd_a S776
96. CaB_6: A6B_cP7_221_f_a S773
97. CaC_6: A6B_hR7_166_g_a S727
98. $CaCu_5$: AB5_hP6_191_a_cg S736
99. $CaCuO_2$: ABC2_tP4_123_d_a_f S688
100. $CaIn_2$: AB2_hP6_194_b_f S742

[**] β-Po and α-Hg have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[¶] In and α-Pa have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[*] Hydrophilite, η-Fe_2C, and marcasite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

101. $CaTiO_3$ Pnma Perovskite: AB3C_oP20_62_c_cd_a S665
102. Calaverite: AB2_mC6_12_a_i S644
103. Calcite[††]: ABC3_hR10_167_a_b_e S728
104. Caswellsilverite: ABC2_hR4_166_a_b_c S725
105. $CdAl_2S_4$: A2BC4_tI14_82_bc_a_g S681
106. CdSb: AB_oP16_61_c_c S664
107. Cementite: AB3_oP16_62_c_cd S669
108. Cf: A_aP4_2_aci S639
109. Chalcopyrite: ABC2_tI16_122_a_b_d S686
110. Chalcostibite: AB2C_oP16_62_c_2c_c S666
111. Cinnabar: AB_hP6_154_a_b S714
112. Cl: A_tP16_138_j S695
113. Co_2Si[†]: A2B_oP12_62_2c_c S667
114. CoSn: AB_hP6_191_f_ad S739
115. CoU: AB_cI16_199_a_a S754
116. Coesite: A2B_mC48_15_ae3f_2f S650
117. Corundum: A2B3_hR10_167_c_e S729
118. Cotunnite[†]: A2B_oP12_62_2c_c S668
119. Covellite: AB_hP12_194_df_ce S749
120. $Cr_{23}C_6$: A6B23_cF116_225_e_acfh S783
121. Cr_3Si: A3B_cP8_223_c_a S774
122. CrB: AB_oC8_63_c_c S673
123. $CrCl_3$: A3B_hP24_151_3c_2a S713
124. $CrSi_2$: AB2_hP9_180_d_j S730
125. CsCl: AB_cP2_221_b_a S768
126. Cu_2Mg Cubic Laves: A2B_cF24_227_d_a S795
127. Cu_2Sb: A2B_tP6_129_ac_c S690
128. Cu_2Te: A2B_hP6_191_h_e S738
129. Cu_3Au: AB3_cP4_221_a_c S770
130. CuAu: AB_tP2_123_a_d S687
131. CuPt: AB_hR2_166_a_b S720
132. $CuTi_3$: AB3_tP4_123_a_ce S687
133. Cubic Lazarevićite: AB3C4_cP8_215_a_c_e S761
134. Cubic Perovskite: AB3C_cP5_221_a_c_b S769
135. Cuprite: A2B_cP6_224_b_a S775
136. Diamond: A_cF8_227_a S796
137. Enargite: AB3C4_oP16_31_a_ab_2ab S654
138. Esseneite: ABC6D2_mC40_15_e_e_3f_f S651
139. Face-Centered Cubic: A_cF4_225_a S786
140. Fe_3W_3C: AB3C3_cF112_227_c_de_f S800
141. Fe_4C: AB4_cP5_215_a_e S761
142. Fe_7W_6 μ-phase: A7B6_hR13_166_ah_3c S721
143. FeB[‡]: AB_oP8_62_c_c S671
144. FeS_2: AB2_aP12_1_4a_8a S638
145. FeSi[‡‡]: AB_cP8_198_a_a S753
146. Ferroelectric $LiNbO_3$: ABC3_hR10_161_a_a_b S717
147. Fluorite: AB2_cF12_225_a_c S782
148. Ga_2Hf: A2B_tI24_141_2e_e S707
149. Ga_3Pt_5: A3B5_oC16_65_ah_bej S676
150. Ga_4Ni: A4B_cI40_197_cde_c S751
151. Ga_4Ni_3: A4B3_cI112_230_af_g S807
152. GeS[‡]: AB_oP8_62_c_c S668
153. GeS_2: AB2_oF72_43_ab_3b S658
154. H_3Ho: A3B_hP24_165_adg_f S719
155. Half-Heusler: ABC_cF12_216_b_c_a S763
156. Hausmannite: A3B4_tI28_141_ad_h S706
157. Hazelwoodite : A3B2_hR5_155_e_c S715
158. Heusler: AB2C_cF16_225_a_c_b S784
159. Hexagonal ω: AB2_hP3_191_a_d S738
160. Hexagonal Close Packed: A_hP2_194_c S748
161. Hexagonal Graphite: A_hP4_194_bc S744
162. $HgBr_2$: A2B_oC12_36_2a_a S656
163. $HgCl_2$[†]: A2B_oP12_62_2c_c S667
164. High-Pressure cI16 Li: A_cI16_220_c S766
165. High-Pressure CdTe: AB_oP2_25_b_a S653
166. High-Pressure H_3S: A3B_cI8_229_b_a S802
167. High-Pressure Te: A_mP4_4_2a S640
168. High-pressure GaAs: AB_oI4_44_a_b S658
169. $HoCoGa_5$: AB5C_tP7_123_b_ci_a S686
170. Hydrophilite[*]: AB2_oP6_58_a_g S661
171. Hypothetical BCT5 Si: A_tI4_139_e S696
172. Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h S740
173. Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h S699
174. Ideal β-Cristobalite: A2B_cF24_227_c_a S789
175. Ilmenite: AB3C_hR10_148_c_f_c S712
176. In[¶]: A_tI2_139_a S698
177. $KAg(CN)_2$: AB2CD2_hP36_163_h_i_bf_i S718
178. KCNS: ABCD_oP16_57_d_c_d_d S660
179. $KClO_3$: ABC3_mP10_11_e_e_ef S643
180. Keatite: A2B_tP36_96_3b_ab S683
181. Khatyrkite: A2B_tI12_140_h_a S703
182. Krennerite: AB2_oP24_28_acd_2c3d S653
183. Li_3N: A3B_hP4_191_bc_a S737
184. LiBC: ABC_hP6_194_c_d_a S746
185. Lonsdaleite: A_hP4_194_f S747
186. Marcasite[*]: AB2_oP6_58_a_g S662
187. Matlockite: ABC_tP6_129_c_a_c S690
188. Mg_2Ni: A2B_hP18_180_fi_bd S730
189. MgB_2C_2: A2B2C_oC80_64_efg_efg_df S674
190. MgB_4: A4B_oP20_62_2cd_c S666
191. $MgNi_2$ Hexagonal Laves: AB2_hP24_194_ef_fgh S749
192. $MgZn_2$ Hexagonal Laves: AB2_hP12_194_f_ah . S746
193. Millerite: AB_hR6_160_b_b S716

[††]Paraelectric $LiNbO_3$ and calcite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[†]Co_2Si, $HgCl_2$, and cotunnite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡]GeS, MnP, FeB, and SnS have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

194. $Mn_{12}Th$: A12B_tI26_139_fij_a S697
195. MnP[‡]: AB_oP8_62_c_c S669
196. Mo_2B_5: A5B2_hR7_166_a2c_c S723
197. MoB: AB_tI16_141_e_e S707
198. Model of Austenite: AB12C3_cI32_229_a_h_b .. S805
199. Model of Austenite: AB18C8_cF108_225_a_eh_f S787
200. Model of Austenite: AB27CD3_cP32_221_a_dij_b_c S769
201. Model of Ferrite: A9B16C7_cF128_225_acd_2f_be S779
202. Model of Ferrite: AB4C3_cI16_229_a_c_b S806
203. Model of Ferrite: AB11CD3_cP16_221_a_dg_b_c S772
204. $MoPt_2$: AB2_oI6_71_a_g S680
205. $MoSi_2$: AB2_tI6_139_a_e S700
206. Modderite: AB_oP8_33_a_a S655
207. Moissanite 9R: AB_hR6_160_3a_3a S716
208. Moissanite-4H SiC: AB_hP8_186_ab_ab S732
209. Moissanite-6H SiC: AB_hP12_186_a2b_a2b S733
210. Molecular Iodine[§]: A_oC8_64_f S675
211. Molybdenite: AB2_hP6_194_c_f S745
212. Monoclinic Low Tridymite: A2B_mC144_9_24a_12a S641
213. Monoclinic PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_mC10_8_ab_a_a S641
214. Monoclinic Phosphorus: A_mP84_13_21g S646
215. Na_3As: AB3_hP8_194_c_bf S741
216. NaTl: AB_cF16_227_a_b S792
217. Naumannite: A2B_oP12_19_2a_a S652
218. NbO: AB_cP6_221_c_d S768
219. NbP: AB_tI8_141_a_b S708
220. Ni_2In: AB2_hP6_194_c_ad S747
221. Ni_3Sn: A3B_hP8_194_h_c S744
222. Ni_4Mo: AB4_tI10_87_a_h S683
223. NiAs: AB_hP4_194_c_a S750
224. NiTi: AB_mP4_11_e_e S642
225. $NiTi_2$: AB2_cF96_227_e_cf S791
226. Original BN: AB_hP4_186_b_a S734
227. Original Fe_2P: A2B_hP9_150_ef_bd S712
228. Orthorhombic Tridymite: A2B_oC24_20_abc_c . S653
229. P_2I_4: A2B_aP6_2_2i_i S639
230. $PPrS_4$: ABC4_tI96_142_e_ab_2g S709
231. Paraelectric $LiNbO_3$[††]: ABC3_hR10_167_a_b_e . S728
232. PbO: AB_tP4_129_a_c S691
233. PdAl: AB_hR26_148_b2f_a2f S711
234. PdS: AB_tP16_84_cej_k S682
235. $PdSn_2$: AB2_oC24_41_2a_2b S657
236. Po: A_mC12_5_3c S640
237. Predicted $CdPt_3$: AB3_oC8_65_a_bf S677
238. Pt_3O_4: A4B3_cI14_229_c_b S803
239. Pt_8Ti: A8B_tI18_139_hi_a S701
240. PtS: AB_tP4_131_c_e S692
241. $PtSn_4$: AB4_oC20_41_a_2b S657
242. Pu_2C_3: A3B2_cI40_220_d_c S767
243. Pyrite: AB2_cP12_205_a_c S758
244. $ReSi_2$: AB2_oI6_71_a_i S679
245. Revised Fe_2P: A2B_hP9_189_fg_bc S735
246. Rhombohedral Graphite[‖]: A_hR2_166_c S724
247. Rock Salt: AB_cF8_225_a_b S788
248. Rutile: A2B_tP6_136_f_a S694
249. SC16: AB_cP16_205_c_c S757
250. Sb_2O_3: A3B2_oP20_56_ce_e S660
251. Sb_2Tl_7: A2B7_cI54_229_e_afh S804
252. Se: A_mP64_14_16e S648
253. SeTl: AB_tI16_140_ab_h S704
254. Si_2U_3: A2B3_tP10_127_g_ah S688
255. Si_{34} Clathrate: A_cF136_227_aeg S793
256. Si_{46} Clathrate: A_cP46_223_dik S775
257. SiF_4: A4B_cI10_217_c_a S764
258. SiO_2: A2B_mP12_3_bc3e_2e S639
259. SiS_2: A2B_oI12_72_j_a S680
260. SiU_3: AB3_tI16_140_b_ah S703
261. Simple Hexagonal Lattice: A_hP1_191_a S737
262. Skutterudite: A3B_cI32_204_g_c S755
263. SnS[‡]: AB_oP8_62_c_c S671
264. Solid Cubane: AB_hR16_148_cf_cf S710
265. Spinel: A2BC4_cF56_227_d_a_e S797
266. $SrCuO_2$: AB2C_oC16_63_c_2c_c S672
267. Stannite: A2BC4D_tI16_121_d_a_i_b S685
268. Stibnite: A3B2_oP20_62_3c_2c S665
269. Sulvanite: A3B4C_cP8_215_d_e_a S760
270. Sylvanite: ABC4_mP12_13_e_a_2g S646
271. T-50 B: A_tP50_134_b2m2n S692
272. Tenorite: AB_mC8_15_c_e S650
273. Tetragonal PZT [$Pb(Zr_xTi_{1-x})O_3$]: A3BC_tP5_99_bc_a_b S685
274. ThH_2: A2B_tI6_139_d_a S702
275. Ti_5Te_4: A4B5_tI18_87_h_ah S682
276. $TiSi_2$: A2B_oF24_70_e_a S678
277. TlF: AB_oF8_69_a_b S677
278. TlF-II: AB_oP8_57_d_d S661
279. Tungsten Carbide: AB_hP2_187_d_a S735
280. UB_{12}: A12B_cF52_225_i_a S780
281. Ullmanite: ABC_cP12_198_a_a_a S751
282. V_4Zn_5: A4B5_tI18_139_i_ah S700
283. Vulcanite: AB_oP4_59_a_b S662
284. W_2B_5: A5B2_hP14_194_abdf_f S745
285. Wurtzite: AB_hP4_186_b_b S733
286. Zincblende: AB_cF8_216_c_a S763
287. Zircon: A4BC_tI24_141_h_b_a S705
288. $ZrSi_2$: A2B_oC12_63_2c_c S672

POSCAR Index

1. "ST12" of Si: A_tP12_96_ab S684
2. α-As[‖]: A_hR2_166_c S721
3. α-B: A_hR12_166_2h S725
4. α-CO[‡‡]: AB_cP8_198_a_a S753
5. α-Cristobalite: A2B_tP12_92_b_a S683
6. α-Ga[§]: A_oC8_64_f S674
7. α-Hg[**]: A_hR1_166_a S723
8. α-IrV: AB_oC8_65_j_g S676
9. α-La: A_hP4_194_ac S741
10. α-Mn: A_cI58_217_ac2g S765
11. α-N: A_cP8_198_2a S753
12. α-N: A_cP8_205_c S757
13. α-Np: A_oP8_62_2c S671
14. α-O: A_mC4_12_i S646
15. α-Pa[¶]: A_tI2_139_a S703
16. α-Po: A_cP1_221_a S771
17. α-Pu: A_mP16_11_8e S643
18. α-Quartz: A2B_hP9_152_c_a S714
19. α-ReO_3: A3B_cP4_221_d_a S773
20. α-S: A_oF128_70_4h S679
21. α-Sm: A_hR3_166_ac S722
22. α-U: A_oC4_63_c S673
23. β-B: A_hR105_166_bc9h4i S727
24. β-BeO: AB_tP8_136_g_f S694
25. β-In_2S_3: A2B3_tI80_141_ceh_3h S709
26. β-Mn: A_cP20_213_cd S760
27. β-Np: A_tP4_129_ac S690
28. β-O[‖]: A_hR2_166_c S726
29. β-Po[**]: A_hR1_166_a S721
30. β-Pu: A_mC34_12_ah3i2j S644
31. β-Quartz: A2B_hP9_180_j_c S731
32. β-Se: A_mP32_14_8e S648
33. β-Sn: A_tI4_141_a S706
34. β-$TiCu_3$: A3B_oP8_59_bf_a S664
35. β-Tridymite: A2B_hP12_194_cg_f S751
36. β-U: A_tP30_136_bf2ij S693
37. β-V_2N: AB2_hP9_162_ad_k S717
38. β'-AuCd: AB_oP4_51_e_f S660
39. η-Fe_2C[*]: AB2_oP6_58_a_g S662
40. γ-Brass: A5B8_cI52_217_ce_cg S766
41. γ-CuTi: AB_tP4_129_c_c S691
42. γ-N: A_tP4_136_f S695
43. γ-Pu: A_oF8_70_a S678
44. γ-Se: A_hP3_152_a S714
45. ω Phase: AB2_hP3_164_a_d S719
46. σ-CrFe: sigma_tP30_136_bf2ij S695
47. ζ-AgZn: A2B_hP9_147_g_ad S710
48. 0201 [$(La,Ba)_2CuO_4$]: AB2C4_tI14_139_a_e_ce S697
49. 1212C [$YBa_2Cu_3O_{7-x}$]: A2B3C7D_oP13_47_t_aq_eqrs_h S659
50. $Al_{12}W$: A12B_cI26_204_g_a S756
51. Al_3Ni_2: A3B2_hP5_164_ad_d S718
52. Al_3Ti: A3B_tI8_139_bd_a S700
53. Al_3Zr: A3B_tI16_139_cde_e S696
54. Al_4Ba: A4B_tI10_139_de_a S701
55. Al_5C_3N: A5B3C_hP18_186_2a3b_2ab_b S734
56. AlB_4Mg: AB4C_hP6_191_a_h_b S736
57. $AlCCr_2$: ABC2_hP8_194_d_a_f S743
58. $AlCl_3$: AB3_mC16_12_g_ij S645
59. AlF_3 : AB3_hR8_155_c_de S715
60. AlN_3Ti_4: AB3C4_hP16_194_c_af_ef S748
61. $AlPS_4$: ABC4_oP12_16_ag_cd_2u S652
62. Ammonia: A3B_cP16_198_b_a S752
63. Anatase: A2B_tI12_141_e_a S707
64. AsCuSiZr: ABCD_tP8_129_c_b_a_c S689
65. AsK_3S_4: AB3C4_oP32_33_a_3a_4a S655
66. $AsKSe_2$: ABC2_aP16_1_4a_4a_8a S638
67. AsTi: AB_hP8_194_ad_f S740
68. Au_2V: A2B_oC12_38_de_ab S657
69. Au_5Mn_2: A5B2_mC14_12_a2i_i S645
70. $AuBe_5$: AB5_cF24_216_a_ce S762
71. B_2Pd_5: A2B5_mC28_15_f_e2f S650
72. BC8: A_cI16_206_c S760
73. BN: AB_hP4_194_c_d S743
74. BPO_4: AB4C_tI12_82_c_g_a S681
75. $BaHg_{11}$: AB11_cP36_221_c_agij S772
76. BaPtSb: ABC_hP3_187_a_d_f S735
77. BaS_3: AB3_oP16_18_ab_3c S652
78. BaS_3: AB3_tP8_113_a_ce S685
79. Baddeleyite: A2B_mP12_14_2e_e S648
80. Bainite: AB3_hP8_182_c_g S731
81. Bergman [$Mg_{32}(Al,Zn)_{49}$]: AB32C48_cI162_204_a_2efg_2gh S755
82. Bi_2Te_3: A2B3_hR5_166_c_ac S723
83. BiF_3: AB3_cF16_225_a_bc S779
84. BiI_3: AB3_hR8_148_c_f S711

[‖] α-As, rhombohedral graphite, and β-O have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡‡] α-CO and FeSi have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[§] α-Ga, black phosphorus, and molecular iodine have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[**] β-Po and α-Hg have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[¶] In and α-Pa have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[*] Hydrophilite, η-Fe_2C, and marcasite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

85. Bixbyite: AB3C6_cI80_206_a_d_e S759
86. Black Phosphorus[§]: A_oC8_64_f S675
87. Body-Centered Cubic: A_cI2_229_a S802
88. Brookite: A2B_oP24_61_2c_c S665
89. Buckled Graphite: A_hP4_186_ab S732
90. C_2CeNi: A2BC_oC8_38_e_a_b S656
91. C_3Cr_7: A3B7_oP40_62_cd_3c2d S670
92. CMo: AB_hP12_194_af_bf S741
93. CNCl: ABC_oP6_59_a_a_a S663
94. CTi_2: AB2_cF48_227_c_e S800
95. Ca_7Ge: A7B_cF32_225_bd_a S777
96. CaB_6: A6B_cP7_221_f_a S774
97. CaC_6: A6B_hR7_166_g_a S728
98. $CaCu_5$: AB5_hP6_191_a_cg S737
99. $CaCuO_2$: ABC2_tP4_123_d_a_f S688
100. $CaIn_2$: AB2_hP6_194_b_f S742
101. $CaTiO_3$ Pnma Perovskite: AB3C_oP20_62_c_cd_a S666
102. Calaverite: AB2_mC6_12_a_i S644
103. Calcite[††]: ABC3_hR10_167_a_b_e S729
104. Caswellsilverite: ABC2_hR4_166_a_b_c S726
105. $CdAl_2S_4$: A2BC4_tI14_82_bc_a_g S681
106. CdSb: AB_oP16_61_c_c S664
107. Cementite: AB3_oP16_62_c_cd S669
108. Cf: A_aP4_2_aci S639
109. Chalcopyrite: ABC2_tI16_122_a_b_d S686
110. Chalcostibite: AB2C_oP16_62_c_2c_c S667
111. Cinnabar: AB_hP6_154_a_b S715
112. Cl: A_tP16_138_j S696
113. Co_2Si[†]: A2B_oP12_62_2c_c S667
114. CoSn: AB_hP6_191_f_ad S739
115. CoU: AB_cI16_199_a_a S754
116. Coesite: A2B_mC48_15_ae3f_2f S650
117. Corundum: A2B3_hR10_167_c_e S730
118. Cotunnite[†]: A2B_oP12_62_2c_c S668
119. Covellite: AB_hP12_194_df_ce S750
120. $Cr_{23}C_6$: A6B23_cF116_225_e_acfh S784
121. Cr_3Si: A3B_cP8_223_c_a S775
122. CrB: AB_oC8_63_c_c S673
123. $CrCl_3$: A3B_hP24_151_3c_2a S713
124. $CrSi_2$: AB2_hP9_180_d_j S731
125. CsCl: AB_cP2_221_b_a S768
126. Cu_2Mg Cubic Laves: A2B_cF24_227_d_a S796
127. Cu_2Sb: A2B_tP6_129_ac_c S691
128. Cu_2Te: A2B_hP6_191_h_e S739
129. Cu_3Au: AB3_cP4_221_a_c S771
130. CuAu: AB_tP2_123_a_d S688
131. CuPt: AB_hR2_166_a_b S720
132. $CuTi_3$: AB3_tP4_123_a_ce S687
133. Cubic Lazarevićite: AB3C4_cP8_215_a_c_e S762
134. Cubic Perovskite: AB3C_cP5_221_a_c_b S769
135. Cuprite: A2B_cP6_224_b_a S776
136. Diamond: A_cF8_227_a S797
137. Enargite: AB3C4_oP16_31_a_ab_2ab S654
138. Esseneite: ABC6D2_mC40_15_e_e_3f_f S651
139. Face-Centered Cubic: A_cF4_225_a S787
140. Fe_3W_3C: AB3C3_cF112_227_c_de_f S801
141. Fe_4C: AB4_cP5_215_a_e S761
142. Fe_7W_6 μ-phase: A7B6_hR13_166_ah_3c S722
143. FeB[‡]: AB_oP8_62_c_c S671
144. FeS_2: AB2_aP12_1_4a_8a S638
145. FeSi[‡‡]: AB_cP8_198_a_a S754
146. Ferroelectric $LiNbO_3$: ABC3_hR10_161_a_a_b S717
147. Fluorite: AB2_cF12_225_a_c S783
148. Ga_2Hf: A2B_tI24_141_2e_e S708
149. Ga_3Pt_5: A3B5_oC16_65_ah_bej S676
150. Ga_4Ni: A4B_cI40_197_cde_c S751
151. Ga_4Ni_3: A4B3_cI112_230_af_g S807
152. GeS[‡]: AB_oP8_62_c_c S669
153. GeS_2: AB2_oF72_43_ab_3b S658
154. H_3Ho: A3B_hP24_165_adg_f S719
155. Half-Heusler: ABC_cF12_216_b_c_a S763
156. Hausmannite: A3B4_tI28_141_ad_h S706
157. Hazelwoodite : A3B2_hR5_155_e_c S716
158. Heusler: AB2C_cF16_225_a_c_b S785
159. Hexagonal ω: AB2_hP3_191_a_d S738
160. Hexagonal Close Packed: A_hP2_194_c S749
161. Hexagonal Graphite: A_hP4_194_bc S744
162. $HgBr_2$: A2B_oC12_36_2a_a S656
163. $HgCl_2$[†]: A2B_oP12_62_2c_c S668
164. High-Pressure cI16 Li: A_cI16_220_c S767
165. High-Pressure CdTe: AB_oP2_25_b_a S653
166. High-Pressure H_3S: A3B_cI8_229_b_a S803
167. High-Pressure Te: A_mP4_4_2a S640
168. High-pressure GaAs: AB_oI4_44_a_b S659
169. $HoCoGa_5$: AB5C_tP7_123_b_ci_a S687
170. Hydrophilite[*]: AB2_oP6_58_a_g S662
171. Hypothetical BCT5 Si: A_tI4_139_e S697
172. Hypothetical Tetrahedrally Bonded Carbon with 3-Member Rings: A_hP6_194_h S740
173. Hypothetical Tetrahedrally Bonded Carbon with 4-Member Rings: A_tI8_139_h S699
174. Ideal β-Cristobalite: A2B_cF24_227_c_a S791
175. Ilmenite: AB3C_hR10_148_c_f_c S712

[††]Paraelectric $LiNbO_3$ and calcite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[†]Co_2Si, $HgCl_2$, and cotunnite have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

[‡]GeS, MnP, FeB, and SnS have the same AFLOW prototype label. They are generated by the same symmetry operations with different sets of parameters.

176. In[¶]: A_tI2_139_a S699
177. $KAg(CN)_2$: AB2CD2_hP36_163_h_i_bf_i S718
178. KCNS: ABCD_oP16_57_d_c_d_d S661
179. $KClO_3$: ABC3_mP10_11_e_e_ef S643
180. Keatite: A2B_tP36_96_3b_ab S684
181. Khatyrkite: A2B_tI12_140_h_a S703
182. Krennerite: AB2_oP24_28_acd_2c3d S654
183. Li_3N: A3B_hP4_191_bc_a S738
184. LiBC: ABC_hP6_194_c_d_a S747
185. Lonsdaleite: A_hP4_194_f S747
186. Marcasite[*]: AB2_oP6_58_a_g S662
187. Matlockite: ABC_tP6_129_c_a_c S690
188. Mg_2Ni: A2B_hP18_180_fi_bd S730
189. MgB_2C_2: A2B2C_oC80_64_efg_efg_df S674
190. MgB_4: A4B_oP20_62_2cd_c S666
191. $MgNi_2$ Hexagonal Laves: AB2_hP24_194_ef_fgh S749
192. $MgZn_2$ Hexagonal Laves: AB2_hP12_194_f_ah . S746
193. Millerite: AB_hR6_160_b_b S716
194. $Mn_{12}Th$: A12B_tI26_139_fij_a S698
195. MnP[‡]: AB_oP8_62_c_c S669
196. Mo_2B_5: A5B2_hR7_166_a2c_c S724
197. MoB: AB_tI16_141_e_e S707
198. Model of Austenite: AB12C3_cI32_229_a_h_b .. S806
199. Model of Austenite: AB18C8_cF108_225_a_eh_f S788
200. Model of Austenite:
AB27CD3_cP32_221_a_dij_b_c S770
201. Model of Ferrite: A9B16C7_cF128_225_acd_2f_be S780
202. Model of Ferrite: AB4C3_cI16_229_a_c_b S807
203. Model of Ferrite: AB11CD3_cP16_221_a_dg_b_c S773
204. $MoPt_2$: AB2_oI6_71_a_g S680
205. $MoSi_2$: AB2_tI6_139_a_e S700
206. Modderite: AB_oP8_33_a_a S655
207. Moissanite 9R: AB_hR6_160_3a_3a S716
208. Moissanite-4H SiC: AB_hP8_186_ab_ab S732
209. Moissanite-6H SiC: AB_hP12_186_a2b_a2b S733
210. Molecular Iodine[§]: A_oC8_64_f S675
211. Molybdenite: AB2_hP6_194_c_f S745
212. Monoclinic Low Tridymite:
A2B_mC144_9_24a_12a S642
213. Monoclinic PZT $[Pb(Zr_xTi_{1-x})O_3]$:
A3BC_mC10_8_ab_a_a S641
214. Monoclinic Phosphorus: A_mP84_13_21g S647
215. Na_3As: AB3_hP8_194_c_bf S742
216. NaTl: AB_cF16_227_a_b S793
217. Naumannite: A2B_oP12_19_2a_a S652
218. NbO: AB_cP6_221_c_d S769
219. NbP: AB_tI8_141_a_b S708
220. Ni_2In: AB2_hP6_194_c_ad S748
221. Ni_3Sn: A3B_hP8_194_h_c S744
222. Ni_4Mo: AB4_tI10_87_a_h S683
223. NiAs: AB_hP4_194_c_a S750
224. NiTi: AB_mP4_11_e_e S643
225. $NiTi_2$: AB2_cF96_227_e_cf S792
226. Original BN: AB_hP4_186_b_a S734
227. Original Fe_2P: A2B_hP9_150_ef_bd S713
228. Orthorhombic Tridymite: A2B_oC24_20_abc_c . S653
229. P_2I_4: A2B_aP6_2_2i_i S639
230. $PPrS_4$: ABC4_tI96_142_e_ab_2g S710
231. Paraelectric $LiNbO_3$[††]: ABC3_hR10_167_a_b_e . S728
232. PbO: AB_tP4_129_a_c S691
233. PdAl: AB_hR26_148_b2f_a2f S712
234. PdS: AB_tP16_84_cej_k S682
235. $PdSn_2$: AB2_oC24_41_2a_2b S658
236. Po: A_mC12_5_3c S641
237. Predicted $CdPt_3$: AB3_oC8_65_a_bf S677
238. Pt_3O_4: A4B3_cI14_229_c_b S804
239. Pt_8Ti: A8B_tI18_139_hi_a S702
240. PtS: AB_tP4_131_c_e S692
241. $PtSn_4$: AB4_oC20_41_a_2b S657
242. Pu_2C_3: A3B2_cI40_220_d_c S767
243. Pyrite: AB2_cP12_205_a_c S758
244. $ReSi_2$: AB2_oI6_71_a_i S680
245. Revised Fe_2P: A2B_hP9_189_fg_bc S736
246. Rhombohedral Graphite[‖]: A_hR2_166_c S724
247. Rock Salt: AB_cF8_225_a_b S789
248. Rutile: A2B_tP6_136_f_a S694
249. SC16: AB_cP16_205_c_c S758
250. Sb_2O_3: A3B2_oP20_56_ce_e S660
251. Sb_2Tl_7: A2B7_cI54_229_e_afh S805
252. Se: A_mP64_14_16e S649
253. SeTl: AB_tI16_140_ab_h S704
254. Si_2U_3: A2B3_tP10_127_g_ah S689
255. Si_{34} Clathrate: A_cF136_227_aeg S795
256. Si_{46} Clathrate: A_cP46_223_dik S775
257. SiF_4: A4B_cI10_217_c_a S765
258. SiO_2: A2B_mP12_3_bc3e_2e S640
259. SiS_2: A2B_oI12_72_j_a S681
260. SiU_3: AB3_tI16_140_b_ah S704
261. Simple Hexagonal Lattice: A_hP1_191_a S737
262. Skutterudite: A3B_cI32_204_g_c S756
263. SnS[‡]: AB_oP8_62_c_c S672
264. Solid Cubane: AB_hR16_148_cf_cf S711
265. Spinel: A2BC4_cF56_227_d_a_e S799
266. $SrCuO_2$: AB2C_oC16_63_c_2c_c S672
267. Stannite: A2BC4D_tI16_121_d_a_i_b S686
268. Stibnite: A3B2_oP20_62_3c_2c S665
269. Sulvanite: A3B4C_cP8_215_d_e_a S761
270. Sylvanite: ABC4_mP12_13_e_a_2g S646
271. T-50 B: A_tP50_134_b2m2n S692
272. Tenorite: AB_mC8_15_c_e S650
273. Tetragonal PZT $[Pb(Zr_xTi_{1-x})O_3]$:
A3BC_tP5_99_bc_a_b S685
274. ThH_2: A2B_tI6_139_d_a S702
275. Ti_5Te_4: A4B5_tI18_87_h_ah S682

276. $TiSi_2$: A2B_oF24_70_e_a S678
277. TlF: AB_oF8_69_a_b S677
278. TlF-II: AB_oP8_57_d_d S661
279. Tungsten Carbide: AB_hP2_187_d_a S735
280. UB_{12}: A12B_cF52_225_i_a S781
281. Ullmanite: ABC_cP12_198_a_a_a S752
282. V_4Zn_5: A4B5_tI18_139_i_ah S701
283. Vulcanite: AB_oP4_59_a_b S663
284. W_2B_5: A5B2_hP14_194_abdf_f S745
285. Wurtzite: AB_hP4_186_b_b S733
286. Zincblende: AB_cF8_216_c_a S764
287. Zircon: A4BC_tI24_141_h_b_a S705
288. $ZrSi_2$: A2B_oC12_63_2c_c S673