

PVA-100, $T = 0.88$, clusters via nematic20cc, $z =$

