

PVA-100, $T = 0.88$, crystallisation via nematic20cc, z

