# Predicting Frictional Properties of Graphene Kirigami Using Molecular Dynamics and Neural Networks

## Designs for a negative friction coefficient

Mikkel Metzsch Jensen

University of Oslo

Juni 02, 2023

UiO : Department of Physics
University of Oslo

# Outline

# Overview

## Three main parts

1. **Sheet kirigami**: Alter a graphene sheet using atomic scale cuts and stretching
2. **Forward simulation**: Calculate the frictional properties of the sheet using MD simulations
3. **Accelerated search**: Use machine learning to replace the MD simulations and perform an accelerated search for new designs

Can we control the frictional properties of a graphene sheet using this technique?

# Motivation

- Kirigami: Variation of origami with cuts permitted
- Desgins: Macroscale $\rightarrow$ nanoscale




Figure: Example of macroscale Kirigami designs implemented on a nanoscale using a focused ion beam (FIB). Black scale bars: $1\ \mu\mathrm{m}$. Reproduced from [1].

# Motivation

## Out-of-plane buckling

- Hanakata et al. [2, 3] found out-of-plane buckling with Kirigami designs
- Surface properties are predicted to be important for friction properties
    - Asperity theory: Contact area
    - Frenkel–Kontorova models: Commensurability



(a) Small load.



(b) High load.

Figure: Reproduced from [4].




(a) Numerical MD results using an amorphous carbon tip and a diamond sample. Reproduced from [5] with permission from the Springer Nature.




(b) Experimental results of a graphene sheet sliding on graphite. Adapted from [6], reproduced from [7] with permission from the American Physical Society.

# Creating a graphene Kirigami system

## System setup



Figure: Graphene sheet on a silicon substrate. Blue: Substrate, Red: Inner sheet, Grey: Pull blocks. test 1

# Creating a graphene Kirigami system

## System setup




(a) Side view.




(b) Top view.

# Creating a graphene Kirigami system
## Sheet Kirigami



(a)

(b)

Figure: Macroscale kirigami cut patterns used as inspiration for the nanoscale implementation. (a) Tetrahedron: Alternating perpendicular cuts producing a tetrahedron-shaped surface buckling when stretched. Reproduced from [8]. (b) Honeycomb: Scotch™ Cushion Lock™ [9] producing a honeycomb-shaped surface buckling when stretched. Reproduced from [9].

# References


[1] J. Li and L. Zhiguang, "Focused-ion-beam-based nano-kirigami: from art to photonics", Nanophotonics **7**, 10.1515/nanoph-2018-0117 (2018).

[2] P. Z. Hanakata, E. D. Cubuk, D. K. Campbell, and H. S. Park, "Accelerated search and design of stretchable graphene kirigami using machine learning", Phys. Rev. Lett. **121**, 255304 (2018).

[3] P. Z. Hanakata, E. D. Cubuk, D. K. Campbell, and H. S. Park, "Forward and inverse design of kirigami via supervised autoencoder", Phys. Rev. Res. **2**, 042006 (2020).

[4] W. Commons, *File:asperities.svg — wikimedia commons, the free media repository*, (2023) https://commons.wikimedia.org/w/index.php?title=File:Asperities.svg&oldid=659167170 (visited on 02/03/2023).

[5] Y. Mo, K. T. Turner, and I. Szlufarska, "Friction laws at the nanoscale", Nature **457**, 1116–1119 (2009).

[6] M. Dienwiebel, N. Pradeep, G. S. Verhoeven, H. W. Zandbergen, and J. W. Frenken, "Model experiments of superlubricity of graphite", Surface Science **576**, 197–211 (2005).