

Tuning Frictional Properties of Kirigami Altered Graphene Sheets using Molecular Dynamics and Machine Learning

Designing a Negative Friction Coefficient

Mikkel Metzsch Jensen



Thesis submitted for the degree of
Master in Computational Science: Materials Science
60 credits

Department of Physics
Faculty of mathematics and natural sciences

UNIVERSITY OF OSLO

Spring 2023

Tuning Frictional Properties of Kirigami Altered Graphene Sheets using Molecular Dynamics and Machine Learning

Designing a Negative Friction Coefficient

Mikkel Metzsch Jensen



© 2023 Mikkel Metzsch Jensen

Tuning Frictional Properties of Kirigami Altered Graphene Sheets using Molecular Dynamics and Machine Learning

<http://www.duo.uio.no/>

Printed: Reprocentralen, University of Oslo

Abstract

Abstract.

Acknowledgments

Acknowledgments.

List of Symbols

F_N Normal force (normal load)

Acronyms

AFM atomic force microscope. 16, 17, 18

FFM friction force microscopes. 16, 17, 18

FK Frenkel-Kontorova. 12, 13, 14, 15, 16, 18, 19

GS ground state. 13, 14

MD molecular dynamics. 2, 3, 19

ML machine learning. 2, 3

SFM scanning force microscopies. 16

SPM scanning probe microscopy. 16

Contents

1	Introduction	1
1.1	Motivation	1
1.2	Goals	3
1.3	Contributions	3
1.4	Thesis structure	3
I	Background Theory	5
2	Friction	7
2.1	Friction across scales	7
2.2	Macroscale	7
2.2.1	Amontons' law	8
2.3	Microscopic scale	9
2.3.1	Surface roughness — Asperity theories	9
2.4	Nanoscale - Atomic scale	10
2.4.1	Frenkel-Kontorova	12
2.4.1.1	Commensurability	13
2.4.1.2	Kinetic friction	15
2.4.2	Experimental procedures	16
2.4.2.1	Scanning Probe Microscopy	16
2.4.2.2	Surface Force Apparatus (SFA)	17
2.4.3	Numerical procedures	17
2.5	Expected frictional properties of graphene	17
2.6	Research questions	21
II	Simulations	23
Appendices		25
Appendix A		27
Appendix B		29
Appendix C		31

Chapter 1

Introduction

Structure of Motivation section:

1. Introduce and motivate friction broadly.
2. Motives for friction control using a grasping robot as example.
3. Analog to gecko feet where adhesive properties are turned on and off.
4. Interest in origin of friction through nanoscale studies which further motivates the use of MD.
5. Intro to metamaterials and the use of kirigami designs,
6. How to optimize kirigami designs with reference to Hanakata and motivating the use of ML.
7. Out-of-plane buckling motivates the use of kirigami for frictional properties.

Does some of the latter paragraphs belong to the approach section?

1.1 Motivation

Friction is a fundamental force that takes part in most of all interactions with physical matter. Even though the everyday person might not be familiar with the term *friction* we recognize it as the inherent resistance to sliding motion. Some surfaces appear slippery and some rough, and we know intuitively that sliding down a snow covered hill is much more exciting than its grassy counterpart. Without friction, it would not be possible to walk across a flat surface, lean against the wall without falling over or secure an object by the use of nails or screws [p. 5] [1]. It is probably safe to say that the concept of friction is integrated in our everyday life to such an extent that most people take it for granted. However, the efforts to control friction dates back to the early civilization (3500 B.C.) with the use of the wheel and lubricants to reduce friction in translational motion [2]. Today, friction is considered a part of the wider field *tribology* derived from the Greek word *Tribos* meaning “rubbing” and includes the science of friction, wear and lubrication [2]. The most compelling motivation to study tribology is ultimately to gain full control of friction and wear for various technical applications. Especially, reducing friction is of great interest as this has tremendous advantages for energy efficiency. It has been reported that tribological problems have a significant potential for economic and environmental improvements [3]:

“On global scale, these savings would amount to 1.4% of the GDP annually and 8.7% of the total energy consumption in the long term.” [4].

On the other hand, the reduction of friction is not the only sensible application for tribological studies. Controlling frictional properties, besides minimization, might be of interest in the development of a grasping robot where a finetuned object handling is required. While achieving a certain “constant” friction response is readily obtained through appropriate material choices during manufacturing, we are yet to unlock the capabilities to alter friction dynamically on the go. One example from nature inspiring us to think along these lines are the gecko feet. More precisely, the Tokay gecko has received a lot of attention in scientific studies aiming to unravel the underlying

mechanism of its “toggable” adhesion properties. Although geckos are able to produce large adhesive forces, they retain the ability to remove their feet from an attachment surface at will [5]. This makes the gecko able to achieve a high adhesion on the feet when climbing a vertical surface while lifting it for the next step remains relatively effortless. For a grasping robot we might consider an analog frictional concept of a surface material that can change from slippery to rough on demand depending on specific tasks.

In the recent years an increasing amount of interest has gone into the studies of the microscopic origin of friction, due to the increased possibilities in surface preparation and the development of nanoscale experimental methods. Nano-friction is also of great concern for the field of nano-machining where the frictional properties between the tool and the workpiece dictates machining characteristics [3]. With concurrent progress in computational power and development of Molecular Dynamics (MD), numerical investigations serve as an extremely useful tool for getting insight into the nanoscale mechanics associated with friction. This simulation based approach can be considered as a “numerical experiment” enabling us to create and probe a variety of high complexity systems which are still out of reach for modern experimental methods.

In materials science such MD-based numerical studies have been used to explore the concept of so-called *metamaterials* where material compositions are designed meticulously to enhance certain physical properties [6][7][8][9][10][11]. This is often achieved either by intertwining different material types or removing certain regions completely. In recent papers by Hanakata et al. [6](2018) [7](2020) numerical studies have showcased that mechanical properties of a graphene sheet, in this case yield stress and yield strain, can be altered through the introduction of so-called *kirigami* inspired cuts into the sheet. Kirigami is a variation of origami where the paper is cut additionally to being folded. While these methods originate as an art form, aiming to produce various artistic objects, they have proven to be applicable in a wide range of fields such as optics, physics, biology, chemistry and engineering [12]. Various forms of stimuli enable direct 2D to 3D transformations through folding, bending, and twisting of microstructures. While original human designs have contributed to specific scientific applications in the past, the future of this field is highly driven by the question of how to generate new designs optimized for certain physical properties. However, the complexity of such systems and the associated design space makes for seemingly intractable problems ruling out analytic solutions.

Earlier architecture design approaches such as bioinspiration, looking at gecko feet for instance, and Edisonian, based on trial and error, generally rely on prior knowledge and an experienced designer [9]. While the Edisonian approach is certainly more feasible through numerical studies than real world experiments, the number of combinations in the design space rather quickly becomes too large for a systematic search, even when considering the simulation time on modern day hardware. However, this computational time constraint can be relaxed by the use of machine learning (ML) which have proven successful in the establishment of a mapping from the design space to physical properties of interest. This gives rise to two new styles of design approaches: One, by utilizing the prediction from a trained network we can skip the MD simulations all together resulting in an *accelerated search* of designs. This can be further improved by guiding the search accordingly to the most promising candidates, as for instance done with the *genetic algorithm* which suggest new designs based on mutation and crossing of the best candidates so far. Another, even more sophisticated approach, is through generative methods such as *Generative Adversarial Networks* (GAN). By working with a so-called *encoder-decoder* network structure, one can build a model that reverses the prediction process. That is, the model predicts a design from a set of physical target properties. In the papers by Hanakata et al. both the *accelerated search* and the *inverse design* approach was proven successful to create novel metamaterial kirigami designs with the graphene sheet.

Hanakata et al. attributes the variety in yield properties to the non-linear effects arising from the out-of-plane buckling of the sheet. Since it is generally accepted that the surface roughness is of great importance for frictional properties it can be hypothesized that the kirigami cut and stretch procedure can also be exploited for the design of frictional metamaterials. For certain designs we might hope to find a relationship between stretching of the sheet and frictional properties. If significant, this could give rise to a variability of the friction response beyond manufacturing material choice. For instance, the grasping robot might apply such a material as artificial skin for which stretching or relaxing of the surface could result in a changeable friction strength; Slippery and smooth when in contact with people and rough and firmly gripping when moving heavy objects. In addition, a possible coupling between stretch and the normal load through a nanomachine design would allow for an altered friction coefficient. This invites the idea of non-linear friction coefficients which might in theory also take on negative values given the right response from stretching. The latter would constitute an extremely rare property. This has (**only?**) been reported indirectly for bulk graphite by Deng et al. [13] where the friction kept increasing during the unloading phase. **Check for other cases and what I can really say here.**

To the best of our knowledge, kirigami has not yet been implemented to alter the frictional properties of a nanoscale system. In a recent paper by Liefferink et al. [14](2021) it is reported that macroscale kirigami can be used to dynamically control the macroscale roughness of a surface through stretching which was used to change the frictional coefficient by more than one order of magnitude. This supports the idea that kirigami designs can in fact be used to alter friction, but we believe that taking this concept to the nanoscale regime would involve a different set of underlying mechanisms and thus contribute to new insight in this field.

1.2 Goals

In this thesis we investigate the possibility to alter and control the frictional properties of a graphene sheet through application of kirigami inspired cuts and stretching of the sheet. With the use of MD simulations we evaluate the friction properties under different physical conditions in order to get insight into the prospects of this field. By evaluating variations of two kirigami inspired patterns and a series of random walk generated patterns we create a dataset containing information of the frictional properties associated with each design under different load and stretch conditions. We apply ML to the dataset and use an accelerated search approach to optimize for different properties of interest. The subtask of the thesis are presented more comprehensively in the following.

1. Define a sheet indexing that allows for a unique mapping of patterns between a hexagonal graphene lattice representation to a matrix representation suited for numerical analysis.
2. Design a MD simulation procedure to evaluate the frictional properties of a given graphene sheet under specified physical conditions such as load, stretch, temperature etc.
3. Find and implement suitable kirigami patterns which exhibit out-of-plane buckling under tensile load. This includes the creation of a framework for creating variations within each pattern class. Additionally create a procedure for generating different styles of random walk patterns.
4. Perform a pilot study of a representative subset of patterns in order to determine appropriate simulation parameters to use for the further study along with an analysis of the frictional properties shown in the subset.
5. Create a dataset consisting of the chosen kirigami variations and random walk patterns and analyse data trends.
6. Train a neural network to map from the design space to physical properties such as mean friction, maximum friction, contact area etc. and evaluate the performance.
7. Perform an accelerated search optimizing for interesting frictional properties using the ML model. This should be done both through the pattern generation procedures and by following a genetic algorithm approach.
8. Use the most promising candidates from the accelerated search to investigate the prospects of creating a nanomachine setup which exhibits a negative friction coefficient.
9. Study certain designs of interest with the scope of revealing underlying mechanism. This includes simple correlation analysis but also a visualization of feature and gradient maps of the ML network.

Is the list of subtask too specific? Some of the details here might be better suited for the thesis structure section.

1.3 Contributions

What did I actually achieve

1.4 Thesis structure

How is the thesis structured.

Part I

Background Theory

Chapter 2

Friction

Friction plays a central role for the topic of this thesis, as this is the key concept that we want to explore through design of microstructures. In this chapter we review relevant theoretical understanding and highlight the theoretical expectations for our study.

Friction is a part of the wider field tribology which includes the study of friction, wear and lubrication between two surfaces in relative motion [1, p. 1]. In this thesis we will only concern ourselves with so-called wearless dry friction. That is, without any use of lubrication and without any resulting wear of the contacting surfaces.

2.1 Friction across scales

Tribological systems take place across a broad range of time and length scales, ranging from geological stratum layers involved in earthquakes [3] to microscopic atomistic processes, as in the gliding motion of a nanocluster of a nanomotor [15]. This vast difference in scale gives rises to different frictional mechanism being dominating at different scales. On a macro scale the system is usually subject to relatively high load and sliding speed leading to high contact stress and wear. On the other hand, the micro-/nanoscale regime occupies the opposite domain operating under relatively small load and sliding speed with negligible wear [3] [2, p. 5]. While macroscale friction is often reduced into a few variables such as load, material type, sliding speed and surface roughness it is clear that the micro-/nanoscale friction cannot be generalized under such a simple representation. On the micro-/nanoscale the tribological properties are dominated by surface properties which will introduce an additional sensitivity to variables such as temperature, humidity and even sliding history. The works of Bhushan and Kulkarni [16, (1996)] showed that the friction coefficient decreased with scale even though the materials used was unchanged. This reveals an intrinsic relationship between friction and scale as the contact condition is altered.

The phenomenological descriptions of macroscale friction cannot yet be derived from the fundamental atomic principles, and bridging the gap between different length scales in tribological systems remains an open challenge [15]. Hence, the following sections will be organized into macro-, micro- and nanoscale representing the theoretical understanding governing each scale regime. While our study of the graphene sheet is based on a nanoscale perspective the hypothesizing about application possibilities will eventually draw upon a macroscale perspective as well. Thus, we argue that a brief theoretical introduction to all three major scales is suitable for a more complete interpretation of the findings in this thesis.

2.2 Macroscale

Our working definition of the *macroscale* is everything on the scale of visible objects. This is usually denoted to the size of millimeters 10^{-3} m and above. Most importantly, we want to make a distinction to the microscale,

where the prefix indicates the size of micrometers m^{-6} . Hence, we essentially consider everything larger than *micro* to belong to the macroscale¹.

2.2.1 Amontons' law

In order to start and keep a solid block moving against a solid surface we must overcome certain frictional forces F_{fric} [1]. The static friction force F_s corresponds to the minimum tangential force required to initiate the sliding while the kinetic friction force F_k corresponds to the tangential force needed to sustain such a sliding at steady speed. The work of Leonardo da Vinci (1452–1519), Guillaume Amontons (1663–705) and Charles de Coulomb (1736–1806) all contributed to the empirical law, commonly known as *Amontons' law*, which serves as a common base for macroscale friction. Amontons' law states that the frictional forces is entirely independent of contact area and sliding velocity. Instead, it relies only on the normal force F_N , acting perpendicular to the surface, and the material specific friction coefficient μ as

$$F_{\text{fric}} = \mu F_N. \quad (2.1)$$

Notice that the term *Normal force* is often used interchangeably with *load* and *normal load* although the latter two terms refer to the applied force, “pushing” the object into the surface, and the first is the reaction force acting from the surface on the object. In equilibrium, these forces are equal in magnitude and hence we will not make a distinction between these terms. On the same note, the frictional force is different from a conventional force which in the Newtonian definition acts on a body from the outside and make it accelerate [17]. Rather than being an independent external force the friction force is an internal *reaction* force opposing the externally applied “sliding” force.

The friction coefficient μ is typically different for the cases of static (μ_s) and kinetic (μ_k) friction, usually both with values lower than one and $\mu_s \geq \mu_k$ in all cases [1, p. 6]. The friction coefficient is taken to be a constant defined by either [17]

$$\mu_1 = \frac{F_{\text{fric}}}{F_N}, \quad (2.2a) \quad \text{or} \quad \mu_2 = \frac{dF_{\text{fric}}}{dF_N}. \quad (2.2b)$$

The first definition Eq. (2.2a) requires zero friction at zero load, i.e. $F_{\text{fric}} = 0$ at $F_N = 0$, while the second definition (Eq. (2.2b)) allows for a finite friction force at zero load since the coefficient is instead given by the slope of the F_{fric} vs. F_N curve. The consequences of the two different definitions are illustrated in Fig. 2.1. Usually the friction force is not zero under zero load (red curve: Linear + shift) due to adhesive forces **source**, which constitutes an additional constant added to Amontons' law in Eq. (2.1). Using the first definition (Eq. (2.2a)) would make the friction coefficient diverge for low load as illustrated in Fig. 2.1, and thus we will use the second definition (Eq. (2.2b)) moving forward. This also allows for a better interpretation in cases where Amontons' law does not hold true and the friction force change non-linear with load (Purple curve in Fig. 2.1).




Figure 2.1: CAPTION

¹The width of a human hair is often used as a reference for the limit of human perception. Since the width of a human hair is on the length scale 10^{-5} to 10^{-4} m we find that this definition of the lower perceptual limit aligns rather well with the transition from macro- to microscale.

Although Amontons' law has been successful in its description of the majority of rubbing surfaces, involving both dry and lubricated, ductile and brittle and rough and smooth (as long as they are not adhesive) surfaces [17], it has its limitations. It is now known that Eq. (2.1) is not valid over a large range of loads and sliding velocities and that it completely breaks down for atomically smooth surfaces in strongly adhesive contact [17]. The independency of sliding velocity disappears at low velocities as thermal effects becomes important and for high velocities due to inertial effects [1, pp. 5-6]. For the case of static friction, it was discovered to be dependent on the so-called contact history with increasing friction as the logarithm of time of stationary contact.

In cases where amontons' law breaks down we might still use the conceptual definition of the friction coefficient as defined by (Eq. (2.2b)). Especially, in the context of achieving negative friction coefficients (in certain load ranges) we would refer to this definition, since (Eq. (2.2a)) would imply a truly unphysical situation of the frictional force acting in the same direction as the sliding motion. This would accelerate the object indefinitely².

Due to the emperical foundation of Amontons' law it does not provide any physical insight into the underlying mechanisms of friction. However, as we will later discuss in more detail, we can understand the overall phenomena of friction through statistical mechanics by the concept of *equipartition of energy* [15]. A system in equilibrium has its kinetic energy uniformly distributed among all its degrees of freedom. When a macroscale object is sliding in a given direction it is clearly not in equilibrium since one of its degrees of freedom carries considerable more kinetic energy. Thus, the system will have a tendency to transfer that kinetic energy to the remaining degrees of freedom as heat. This heat will dissipate to the sourroundings and the object will slow down as a result. Hence, we can understand friction simply as the tendency of going toward equilibrium energy equipartitioning among many interacting degrees of freedom [15]. From this point of view it is clear that friction is an inevitable part of contact physics, but even though friction cannot be removed altogether, we are still capable of manipulating it in usefull ways.

The attentive reader might point out that we have already moved the discussion partly into the microscopic regime as *statistical mechanics* generally aim to explain macroscale behaviour by microscopic interactions. In fact, this highlight the nessecity to consider smaller scales in order to achieve a more fundamental understdadning of friction.

2.3 Microscopic scale

Going from a macro- to microscale perspective, to a length scale of order 10^{-6} m, it was realized that most surfaces is in fact rough [18]. The contact between two surfaces consist of numerous smaller contact point, so-called asperities, for which the friction between two opposing surfaces involves interlocking of those asperities as visualized in Fig. 2.2. Small junctions of asperities are formed due to contact pressure and adhesion [3].

In the macroscale perspective of Amonton's law we refer to time- and space-averaged values, i.e. the "apparent" contact area and the average sliding speed [17]. However, microspocially we find the real contact area to be smaller than the macroscale apparent area and the shearing of local microjunctions can happen at large fluctuations or in a stick-slip fashion.

It is generally accepted that friction is caused by two mechanism: mechanical friction and chemical friction [3]. The mechanical friction is the "plowing" of the surface by hard particles or said asperities with an energy loss attributed to deformations of the asperity. While plastic deformations, corresponding to wear, gives rise to an obvious attribution for the energy loss, elastic deformations is also sufficient in explaining energy loss due to phonon excitations. In fact the assumption of plastic deformations has been critizised as this is theorized only to be present in the beginning of a surface contact while it is neglible for prolonged or repeated contact of the same surfaces [19]. That is, when machine parts slide against each other for millions of cycle the plastic deformation would only take place in the beginning for which the system then reaches a steady state with only elastic deformations. The chemical friction arrises from adhesion between microscopic contacting surfaces, with an energy loss attributed to breaking and forming of bonds.

2.3.1 Surface roughness — Asperity theories

Asperity theories are based on the observation that microscopic rough surfaces, with contacting asperities each with a contact area of A_{asp} , will have a true contact area $\sum A_{\text{asp}}$ much smaller than the apperent macrosopic

²You would most likely have a good shot at the Nobel Prize with that paper.

area [3]. The friction force has been shown to be proportional to the true contact area as

$$F_{\text{fric}} = \tau \sum A_{\text{asp}},$$

where τ is an effective shear strength of the contacting bodies. Note that this is still compatible with Amontons' law in Eq. (2.1) by having a linear relationship between the real contact area and the applied load. In Fig. 2.2 we see a visualization on how the contact area might intuitively increase with load as the asperity tips are deformed (plastically or elastically) into broader contact points.




Figure 2.2: Qualitative illustration of the microscopic asperity deformation under increasing load from frame (a) to (b) [20]. While this figure seemingly portrays plastic deformation the concept of increased contact area under increased load applies for elastic deformation as well.

Many studies have focused on single asperity contacts to reveal the relationship between the contact area and load [21][22][23]. By assuming perfectly smooth asperities, with radii of curvature from micrometers all the way down to nanometers, continuum mechanics can be used to predict the deformation of asperities as load is applied. A model for non-adhesive contact between homogenous, isotropic, linear elastic spheres was first developed by Hertz [24], which predicted $A_{\text{asp}} \propto F_N^{2/3}$. Later adhesion effects were included in a number of subsequent models, including Maugis-Dugdale theory [25], which also predicts a sublinear relationship between A_{asp} and F_N . Thus, the common feature of all single-asperity theories is that A_{asp} is a sublinear function of F_N , leading to a similar sublinear relationship for $F_{\text{fric}}(F_N)$, which fails to align with the macroscale observations modelled by Amontons' law (eq. (2.1)).

Concurrently with single-asperity studies, roughness contact theories are being developed [26][27][28][29] to bridge the gap between single asperities and macroscopic contacts [18]. A variety of multi-asperity theories has attempted to combine single asperity mechanics by statistical modelling of the asperity height and spatial distributions [19]. This has led to a partially success in the establishment of a linear relationship between A_{asp} and F_N . Unfortunately, these results are restricted in terms of the magnitude of the load and contact area, where multi-asperity contact models based on the original ideas of Greenwood and Williamson [28] only predicts linearity at vanishing low loads, or Persson [27] which works for more reasonable loads but only up to 10-15 % of the macroscale contact area. However, as the load is further increased all multi-asperity models predict the contact area to fall into the sublinear dependency of normal force as seen for single asperity theories as well [19].

2.4 Nanoscale - Atomic scale

Going from a micro- to a nanoscale, on the order of 10^{-9} m, it has been predicted that continuum mechanics will break down [30] due to the discreteness of individual atoms. Note that atom spacing lies in the domain of a few ångströms Å (10^{-10} m) and thus we take the so-called atomic-scale to be a part of the nanoscale regime. In a numerical study by Mo et al. [18] (considering asperity radii of 5-30 nm) it has been shown that the asperity area A_{asp} , defined by the circumference of the contact zone, is sublinear with F_N . This is accommodated by the observation that not all atoms within the circumference make chemical contact with the substrate. By modelling the real contact area $A_{\text{real}} = N A_{\text{atom}}$, where N is the amount of atoms within the range of chemical interaction and A_{atom} the associated surface area for an atom, they found a consistent linear relationship between friction and the real contact area. Without adhesive forces this lead to a similar linear relationship $F_{\text{fric}} \propto F_N$, while adding van der Waals adhesion to the simulation gave a sublinear relationship, even though the $F_{\text{fric}} \propto A_{\text{real}}$

was maintained. This result emphasizes that the contact area is still expected to be play an important role at the nanoscale for asperity theory. It is simply the definition of the contact area that undergoes a change when transitioning from micro- to nanoscale.

While the study by Mo et al. [18] considers a single asperity on a nanoscale, we are going to study a nanoscale system with no initial asperities present. Our system of interest, an initially atomically flat graphene sheet imposed on a flat silicon substrate, make it unfounded to rely on asperity theories. Although both numerical [31][32][33] and experimental [34, p. 2005][35] studies have been done for so-called nanoflakes sliding on a substrate, the dependence of friction force on contact area is not investigated. One reasonable explanation is that the contact area is already at its maximum for atomically smooth contacting surfaces and hence does not play an important role. In a numerical study of atomic-scale frictional behavior of corrugated nano-structured surfaces [C2NR30691C] they reported that the contact area only affected the friction significantly for big corrugations as opposed to small. Since an increasing friction is still reported under increasing load in most nanoflake studies (see Sec. 2.5 for a more detailed discussion), this suggests that some other mechanisms are governing friction at this level.

“Load-independent friction has also been observed in FFM experiments on thermally oxidized MoS₂, and it was proposed that MoO₃ nanocrystals, that grew during the oxidation process on the MoS₂ surface [35], acted as a spacer between the tip and the sample, such that the contact area remained unchanged upon loading. In the present case, the contact area would be completely determined by the flake size, which would be independent of the loading force. Hence, the friction would only increase slightly with normal load as the result of the increase in contact pressure.” [34]

Before diving into alternative theoretical approaches to address this issue we point out that exactly this transition, between nanoscale asperities and atomically smooth surfaces, is of outermost importance for the objective of the thesis. By introducing kirigami cuts and stretching the sheet we expect to see an out of plane buckling which induce an ensemble of asperities on the sheet. Hence, we might hypothesize that such a transition will contribute to a significant change in the governing mechanism of friction bridging the two domains of nanoscale asperity and smooth surface theory.

In the lack of noteworthy structural asperities, friction can instead be modelled as a consequence of the rough potential of the atomic landscape. A series of models builds on this idea by considering different ways for the atoms to interact interatomically, with the moving body, and the substrate. In figure Fig. 2.3 three of the most common 1D models are displayed. The time-honored Prandtl-Tomlinson (PT) model describes a point-like tip sliding over a space-periodic fixed crystalline surface with a harmonic coupling to the moving body. This is analog to that of an experimental cantilever used for Atomic Force Microscopy (see Sec. 2.4.2.1). Further extensions were added in the Frenkel-Kontorova (FK) model by substituting the tip with a chain of harmonic coupled atoms dragged from the end (**I am not sure that the figure is 100% correct by drawing a spring like that**), and finally combined in the Frenkel-Kontorova-Tomlinson (FKT) with the addition of a harmonic coupling between the chain and the moving body. In the following we will discuss the FK model as the underlying basis for the understanding of smooth nanoscale friction.




Figure 2.3: Temporary figure from https://www.researchgate.net/figure/Illustrations-of-the-1D-PT-FK-and-FKT-models-Large/fig1_257670317

2.4.1 Frenkel-Kontorova

The standard Frenkel-Kontorova (FK) model consists of a 1D chain of N classical particles of equal mass, representing atoms, interacting via harmonic forces and moving in a sinusoidal potential as sketched in Fig. 2.4 [15]. The hamiltonian is

$$H = \sum_{i=1}^N \left[\frac{p_i^2}{2m} + \frac{1}{2}K(x_{i+1} - x_i - a_c)^2 + \frac{1}{2}U_0 \cos\left(\frac{2\pi x_i}{a_b}\right) \right], \quad (2.3)$$

where the atoms are labelled sequently $i = 1, \dots, N$. The first term $p_i^2/2m$ represents the kinetic energy with momentum p_i and mass m . Often the effects of inertia are neglected, referred to as the static FK model, while the inclusion in Eq. (2.3) is known as the dynamic FK model [36]. The next term describes the harmonic interaction with elastic constant K , nearest neighbour distance $\Delta x = x_{i+1} - x_i$ and corresponding nearest neighbour equilibrium distance a_c . The final term represents the periodic substrate potential, serving as the external potential on site, with amplitude U_0 and period a_b . Different boundary choices can be made where both free ends and periodic conditions gives similar results. The choice of fixed ends however makes the chain incapable of sliding.




Figure 1. A sketch of the FK model, showing the two competing lengths: the average interparticle spacing and the lattice periodicity of the substrate.

Figure 2.4: Temporary figure from [15]

To probe static friction one can apply an external adiabatically increasing force until sliding accours. This corresponds to the static FK model, and it turns out that the sliding properties are entirely governed by its topological excitations referred to as so-called *kinks* and *antikinks*

2.4.1.1 Commensurability

We can subdivide the frictional behaviour in terms of commensurability, that is, how well the spacing of the atoms match the periodic substrate potential. We describe this by the length ratio $\theta = a_b/a_c = N/M$ where M denotes the number of minemas in the potential (within the length of the chain). A rational number for θ means that we can achieve a perfect alignment between the atoms in the chain and the potential minemas, without stretching the chain, corresponding to a *commensurate* case. If θ is irrational the chain and substrate cannot fully align without some stretching of the chain, and we denote this as being *incommensurate*.

We begin with the simplest commensurate case of $\theta = 1$ where the spacing of the atoms matches perfectly with the substrate potential periodicity, i.e. $a_c = a_b$, $N = M$. The ground state (GS) is the configuration where each atom is aligned with one of the substrate minemas. By adding an extra atom to the chain we would effectively shift some of the atoms out of this ideal state, giving rise to a kink excitation. This leads to the case where two atoms will have to “share” the same potential corrugation as sketched in Fig. 2.6. On the other hand, removing an atom from the chain results in an antikink excitation where one potential corrugation will be left “atomless”. In order to reach a local minimum the kink (antikink) will expand in space over a finite length such that the chain undertakes a local compression (expansion). When applying a tangential force to the chain it is much easier for an excitation to move along the chain than it is for the non-excited atoms since the activation energy ϵ_{PN} for a kink/antikink displacement is systematically smaller (often much smaller) than the potential barrier U_0 . Thus, the motion of kinks (antikinks), i.e. the displacement of extra atoms (atom vacancies), is represententing the fundamental mechanism for mass transport. These displacements are responsible for the mobility, diffusivity and conductivity within this model.

In the zero temperature commensurable case with an adiabatical increase in force, all atoms would be put into an accelerating motion as soon as the potential barrier energy is present. However, in reality any thermal excitation would excite the system before this point is reached resulting in kink-antikink pairs traveling down the chain. For a chain of finite length these often accrour at the end of the chain running in opposite direction. As a kink travels down the chain the atoms are advanced by one lattice spacing a_b along the substrate potential. This cascade of kink-antikink exications is shown in Fig. 2.5




Figure 2. Time dependence of the atomic trajectories for the fully matched ($\theta = 1$) FK model at the (low-temperature) onset of depinning. Motion starts with the nucleation of a kink-antikink pair. The kink and the antikink depart in opposite directions cross the periodic boundary conditions, and collide quasielastically. A second kink-antikink pair forms in the wake of the initial kink. Further kink-antikink pairs are generated, with an avalanche-like increase of the kink-antikink concentration, eventually leading to a sliding state. Adapted from Ref. [21], Copyright (1997) by The American Physical Society.

Figure 2.5: Temporary figure from [15]

For the 2D case where an island (or flake) is deposited on a surface, in our case the graphene sheet on the Si substrate, we generally also expect the sliding to be initiated by kink-antikink pairs at the boundary.

For the case of incommensurability, i.e. $\theta = a_b/a_c$ is irrational, the GS is characterized by a sort of ‘‘staircase’’ deformation. That is, the chain will exhibit regular periods of regions where the chain is slightly compressed (expanded) to match the substrate potential, separated by kinks (antikinks), where the increased stress is eventually released as illustrated in Fig. 2.6



Figure 2.6: Temporary figure from [urlhttp://www.iop.kiev.ua/~obraun/myreprints/surveyfk.pdf](http://www.iop.kiev.ua/~obraun/myreprints/surveyfk.pdf) p. 14. Incommensurable case ($\theta = ?$) where atoms sit slightly closer than otherwise dictated by the substrate potential for which this regularly result in a kink here seen as the presence of two atoms closely together in one of the potential corrugations.

The incommensurable FK model contains a critical elastic constant K_c , such that for $K > K_c$ the static friction F_s drops to zero, making the chain able to initiate a slide at no energy cost, while the low-velocity kinetic friction is dramatically reduced. This can be explained by the fact that the displacement occurring in the incommensurable case will yield just as many atoms climbing up a corrugation as there are atoms climbing down. For a big (infinite) chain this will exactly balance the forces making it non-resistant to sliding. Generally, incommensurability guarantees that the total energy (at $T = 0$) is independent of the relative position to the potential. However, when sliding freely a single atom will eventually occupy a maximum of the potential. When increasing the potential magnitude U_0 or softening the chain stiffness, lowering K , the possibility to occupy such a maximum disappears. This marks the so-called Aubry transition at the critical elastic constant $K = K_c(U_0, \theta)$ where the chain goes from a free sliding to a *pinned state* with a nonzero static friction. K_c is a discontinuous

function of the ratio θ , due to the reliance on irrational numbers for incommensurability. The minimal value $K_c \simeq 1.0291926$ in units $[2U_0(\pi/a_b)^2]$ is achieved for the golden-mean ratio $\theta = (1 + \sqrt{5}/2)$. Notice that the pinning is provided despite translational invariance due to the inaccessibility to move past the energy barrier which act as a dynamical constraint. The Aubry transition can be investigated as a first-order phase transition for which power laws can be defined for the order parameter, but this is beyond the scope of this thesis.

The phenomena of non-pinned configurations is named *superlubricity* in tribological context. Despite the misleading name this refers to the case where the static friction is zero while the kinetic friction is nonzero but reduced. For the case of a 2D sheet it is possible to alter the commensurability, not only by changing the lattice spacing through material choice, but also by changing the orientation of the sheet relative to the substrate. Dienwiebel et al. [34] have shown that the kinetic friction, for a graphene flake sliding over a graphite surface (multiple layers of graphene), exhibits extremely low friction at certain orientations as shown in Fig. 2.7. We clearly see that friction changes as a function of orientation angles with only two spikes of considerable friction force.




Fig. 6. Average friction force versus rotation angle Φ of the graphite sample around an axis normal to the sample surface. Two narrow peaks of high friction are observed at 0° and 61° , respectively. Between these peaks a wide angular range with ultra-low friction, close the detection limit of the instrument, is found. The first peak has a maximum friction force of 306 ± 40 pN, and the second peak has a maximum of 203 ± 20 pN. The curve through the data points shows results from a Tomlinson model for a symmetric 96-atom graphite flake sliding over the graphite surface (for details about the calculation see [39]).

Figure 2.7: [Temporary] figure from [34] showing superlubricity for incommensurable orientations between graphene and graphite. [temporary]

2.4.1.2 Kinetic friction

In the FK model the kinetic friction is primarily caused by resonance between the sliding induced vibrations and phonon modes in the chain [36]. The specific dynamics is found to be highly model and dimension specific, and even for the 1D case this is rather complex. However, we make a simplified analysis of the 1D rigid chain case to showcase the reasoning behind the phenomena.

When all atoms are sliding rigidly with center of mass velocity v_{CM} the atoms will pass the potential maxima with the so-called *washboard frequency* $\Omega = 2\pi v_{CM}/a_b$. For a weak coupling between the chain and the potential we can use the zero potential case as an approximation for which the known dispersion relation for the 1D harmonic chain is given [37, p. 92]

$$\omega_k = \sqrt{\frac{4K}{m}} \left| \sin \left(\frac{k}{2} \right) \right|,$$

where ω_k is the phonon frequency and $k = 2\pi i/N$ the wavenumber with $i \in [N/2, N/2]$. Resonance will occur when the washboard frequency Ω is close to the frequency of the phonon modes ω_q in the chain with wavenumber $q = 2\pi a_c/a_b = 2\pi\theta^{-1}$ or its harmonics nq for $n = 1, 2, 3, \dots$ [38]. Thus, we can approximate the resonance center of mass speed as

$$\begin{aligned} n\Omega &\sim \omega_{nq} \\ n\frac{2\pi v_{CM}}{a_b} &\sim \sqrt{\frac{4K}{m}} \left| \sin\left(\frac{2n\pi\theta^{-1}}{2}\right) \right| \\ v_{CM} &\sim \frac{\sin(n\pi\theta^{-1})}{n\pi} \sqrt{\frac{Ka_b^2}{m}}. \end{aligned}$$

When the chain slides with a velocity around resonance speed, the washboard frequency can excite acoustic phonons which will dissipate to other phonon modes as well. At zero temperature the energy will transform back and forth between internal degrees of freedom and center of mass movement of the chain. Hence, at zero temperature this is in fact theorized to speed up the translational decay [36]. However, for the more realistic case of a non-zero temperature the substrate serves as a thermostat, for which energy will dissipate from the chain to the substrate degrees of freedom, giving rise to kinetic friction. This suggests that certain sliding speeds will exhibit relatively high kinetic friction while others will be subject to extremely low kinetic friction. Simulations of concentric nanotubes in relative motion (telescopic sliding) have revealed the occurrence of certain velocities at which the friction is enhanced, corresponding to the washboard frequency of the system [15]. The friction response was observed to be highly non-linear as the resonance velocities were approached.

A common way to model the non-zero temperature case is by the use of a Langevin thermostat, which models the dissipation of heat by adding a viscous damping force and thermal fluctuations by the addition of Gaussian random forces with variance proportional to the temperature (see ?? for more details). In combination, this gives rise to a kinetic friction that is both velocity and temperature dependent. By extending the FK model into 2D [36] it can be shown numerically that the friction coefficient generally increases with increasing velocity and temperature respectively, although the specific of the trend is highly sensitive to model parameters.

2.4.2 Experimental procedures

Experimentally, the study of nanoscale friction is challenging due to the low forces on the scale of nano-newtons along with difficulties of mapping the nano-scale topography of the sample. In opposition to numerical simulations, which provides full transparency regarding atomic-scale structures, sampling of forces, velocities and temperature, the experimental results are limited by the state-of-the-art experimental methods. In order to compare numerical and experimental results it is useful to address the most common experimental.

2.4.2.1 Scanning Probe Microscopy

Scanning probe microscopy (SPM) includes a variety of experimental methods which is used to examine surfaces with atomic resolution [39, pp. 6-27]. This was originally developed for surface topography imaging, but today it plays a crucial role in nanoscale science as it is used for probe-sampling regarding tribological, electronic, magnetic, biological and chemical character. The family of methods involving the measurement of forces is generally referred to as *scanning force microscopies* (SFM) or for friction purposes *friction force microscopes* (FFM).

One such method arose from the *atomic force microscope* AFM, which consists of a sharp micro-fabricated tip attached to a cantilever force sensor, usually with a sensitivity below 1 nN all the way down to pN. The force is measured by recording the bending of the cantilever, either as a change in electrical conduction or more commonly, by a light beam reflected from the back of the cantilever into a photodetector [1, p. 183]. By adjusting the tip-sample height to keep a constant normal force while scanning across the surface this can be used to produce a surface topography map. By tapping the material (dynamic force microscopy) with sinusoidally vibrated tip the effects from friction and other disturbing forces can be minimized in order to produce an even clearer image (include example, preferable showing the surface structure of graphene). However, when scanning perpendicularly to the cantilever axis, one is also able to measure the frictional force as torsion of the cantilever. By having four quadrants in the photodetector (as shown in figure Fig. 2.8), one can simultaneously measure the normal force and friction force as the probe scans across the surface.




Figure 17.1 Schematic diagram of a beam-deflection atomic force microscope.

Figure 2.8: Temporary figure from [1, p. 184]

AFM can also be used to drag a nanoflake accross the substrate as done by Dienwiebel et al. [34], where a graphene flake was attahced to a FFM tip and dragged accross graphite. Notice that this makes the normal loading concentrated to a single point on the flake rather than achieving an evenly distributed load.

2.4.2.2 Surface Force Apparatus (SFA)

I think this referses to having two interfaces sliding against each other with (optionally I think) lubrication between. This is often mirroed in MD simulations and often experimental results refer to this. So it might be worth saying a few words about, but I'm not sure yet.

2.4.3 Numerical procedures

2.5 Expected frictional properties of graphene

Several studies have investigated the frictional behaviour of graphene by varying different parameters such as normal force, sliding velocity, temperature, commensurability and graphene thickness [40]. In general, we find three types of systems being studied: 1) An FFM type setup where the graphene, either resting on a substrate or suspended, is probed by a AFM tip scanning across the surface. 2) Graphene “sandwiched” (=SFA) in between two substrate layers moving relative to each other using the graphene as a solid lubricant. 3) A graphene flake sliding on a substrate, either being dragged by an AFM tip or by more complex arrangements in numerical simulations. While only the latter cases matches our intended system setup, we will consider results from all three categories due to the sparse results available. The relevant studies which we consider are listed in Table 2.1.

Table 2.1: Update multirow line span after completing the table...

System	Type	Year	Researcher	Materials	Key words
AFM	Exp.	2015 [41]	G. Paolicelli et al.	Graphene on SiO ₂ and Ni(111) substrate	Layers, load, shear strength
		2019 [42]	Zhang et al.	Monolayer graphene	Straining sheet
	Mix	2019 [43]	Vazirisereshk et al.	Graphene, MoS ₂ and Graphene/MoS ₂ heterostructure	Low friction?
	Num.	2015 [44]	Yoon et al.	Si tip, graphene on SiO ₂	Stick-slip: tip size, scan angle, layer thickness, substrate flexibility
		2016 [45]	Li et al.	Si tip, graphene on a-Si substrate	Increasing layers
SFA	Num.	2011 [46]	Wijn et al.	Graphene flakes between graphite	Rotational dynamics, superlubricity, temperature
		2012 [47]	H. J. Kim and D. E. Kim.	Carbon sheet	Corrugated nano-structured surfaces
Flake	Exp	2005 [34]	Dienwiebel et al.	Graphene on graphite	Commensurability, superlubricity
		2013 [35]	Feng et al.	Graphene on graphite	Free sliding (relevant?)
	Num.	2009 [33]	Bonelli et al.	Graphene on graphite	Tight-binding, commensurability, load, flake size
		2012 [48]	Reguzzoni et al.	Graphene on graphite	Graphite thickness
		2014 [49]	Liu et al.	Graphene on graphite	Thickness, deformations, high speed
		2018 [31]	P. Zhu and Li	Graphene on gold	Flake size, commensurability
		2019 [32]	Zhang et al.	Graphene on diamond	Temperature, sliding angle, friction coefficient

One of the earliest tribological simulations of graphene was carried out by Bonelli et al. [33] in 2009 using a tight-binding method to simulate a graphene flake on an infinite graphene sheet [40]. They implemented a FKT-like setup where each atom in the flake is coupled horizontally to a rigid support by elastic springs, however excluding thermal excitations. They recovered the stick-slip behaviour which is also observed in FFM setups both experimentally [42] and numerically [45], and they found an agreement with the qualitative observation that soft spring allows for clean stick-slip while hard springs inhibit it (below 40 nN/m?). In AFM and SFA Not mentioned before experiments, the stick-slip motion tends to transition into smooth sliding when the speed exceeds $\sim 1 \mu\text{m/s}$ while in MD modelling the same transition is observed in the $\sim 1 \text{ m/s}$ region [15]. This 6 order of magnitude discrepancy has been largely discussed in connection to simplifying assumptions in MD simulations. Moreover, Bonelli et al. [33] found that commensurability, through orientation of the support and the angle of pulling, to be of high importance for the frictional behaviour which generally aligns with the predictions of the FK type models. They confirmed qualitatively the experimental observation of superlubricity for certain incommensurable orientations as shown experimentally by Dienwiebel et al. [34] and further supported by experimental measurements of interaction energies by Feng et al. [35]. Although, the friction force and friction coefficient is found to be one order of magnitude higher than that of the experimental results which is attributed to the details of the numerical modelling. Experimental studies. Generally the experimental found coefficients between graphite and most materials lies in the range 0.08-0.18 [34] and while Dienwiebel et al. [34] reported very different frictional forces on the order 0.01-0.45 nN (all the way down to inmeasureable by their equipment) in a load range of roughly 30 nN, the change in friction with applied load was as low as 0.05-0.4 % (coef of 0.0005-0.004).

The experimental studies generally give coefficients in the range $\sim [0.01, 0.2]$ [40] [34] (what definition?)

Furthermore, Bonelli et al. [33] found friction to decrease with flake size which is mainly attributed to the idea that boundary atoms are dominant in increasing friction, but also due to their system setup decreasing the rotational freedom as size increases. However, a numerical MD study of monolayer islands of krypton on copper by Reguzzoni and Righi [50] reports that the effective commensurability drastically below a critical flake radius on the order of 10 Å. This supports the idea that increasing flake size will decrease friction though a reduction in commensurability, which is also in agreement with numerical studies by Zhu and Li [31]. In a numerical study by Varini et al. [51], based on Kr islands adsorbed on Pb(111), this is further elaborated as they found that finite size effects are especially important for static friction as a pinning barrier rise from the edge (preventing otherwise superlubricity due to incommensurability). They reported a relationship $F_s \sim A^{\gamma_s}$ not only sublinear $\gamma_s < 1$ but also sublinear with respect to the island perimeter $P \propto A^{1/2}$ by having $\gamma_s = 0.25$ for a hexagonal edge and $\gamma_s = 0.37$ when circular, indicating that only a subset of the edge is responsible for the pinning effect. Additionally, the edge pinning effect was found to decrease with increasing temperature as the edge energy barriers are reduced. In general this aligns with the FK models prediction a lowering of friction due to thermal activation of the atoms overcoming the energy barriers which is also found the numerical study by Wijn et al. [46]

Evolution effects, or fiction strengthening, were observed experimentally by Zhang et al. [42] (only when on substrate) and numerically by Li et al. [45], meaning that the friction force will increase during the initial period of sliding. This is attributed to ... and was found to diminish for an increasing number of layers in the substrate and was observed only when the two-dimensional material was loosely adhering to a substrate. On the same note they found in general that the friction between graphene and graphite increased with increasing layers which is also supported by the findings in XXX

In an experimental study of suspended monolayer graphene by Zhang et al. [42] they found that straining the graphene sheet increased the dynamic friction

In the following we summarize the qualitative expectations for the nanofriction behaviour for the unstretched and non-cut graphene sheet.

Table 2.2: Qualitative trends

Stick slip	Generally we expect to observe periodic stick-slip motion with a period matching the lattice constant(s) involved [18]. This is however inhibited for high stiffness of the springs to the coupled support and at large sliding velocity. Flake size and temperature?
Static friction	The static friction is highly related to the presence of stick-slip motion. The static friction is most pronounced for commensurable configurations. Reduce with friction?
Commensurability	Both static and dynamic friction is expected to be highly sensitive to commensurability, both through lattice spacing and orientation but also by the path the flake is forced along. A low spring stiffness will effect the freedom to shift around which affects commensurability.
Friction evolution	For a monolayer graphene sheet on a substrate
Thickness	Friction increase with increasing graphite layers (Is this relevant?)
Negative coef	Observed, or only with subtracting force

Table 2.3: Quantitative nano friction dependence on various variables. work in progress.

Variable	Dependency	Numerical studies	Experimental
Normal force F_N	$F_{\text{fric}} \propto F_N^\alpha$ $\alpha \leq 1$	Zhang et al. [32] finds a seemingly linear relationship $F_{\text{fric}} \propto F_N$ while Bonelli et al. [33] reports a sublinear relationship. The latter corresponds with that of nanosasperity simulations where Mo et al. [18], using an amorphous carbon tip on a diamond sample, also found a sublinear relationship when including adhesion and linear without adhesion.	Experimentally rather different trends have been observed, although the majority agree on increasing friction with increasing load [1, p. 200]. For the graphebne flake Dienwiebel et al. [34] found a seemingly non-dependent relationship while Feng et al. [35] did not report on this. FFM analog to the single asperity setup have yielded both linear relationship [17] (silicon tip on gold) while Schwarz et al. [52] found that FFM with well-defined spherical tips matched with theoretical results (DMT, elastic spheres pressed together [1, p. 200]), yielding a power law $F_{\text{fric}} = F_N^{2/3}$.
Velocity v	$F_{\text{fric}} \propto \ln v$ (exp.) or $F_{\text{fric}} \propto v$ (num.)	Studies of gold clusters on graphite suggest that friction is viscous, i.e. proportional to velocity [15].	Logarithmic velocity dependence of friction has been measured for nanotip friction [1, p. 201] associated to thermal activation and possibly the time available to form bond between the tip and the substrate. At higher velocities thermally activated processes are less important and friction becomes independent of velocity. This has been observed for Si tips and diamond, graphite and amorphous carbon surfaces with scan velocities above $1 \mu\text{s}$.
Temperature T	Either increase (MD) or decrease as $F_{\text{fric}} \propto \exp(1/T)$ (experimental)	Zhang et al. [32] found simply that friction increased with temperature. The [15] gold cluster on graphite study (get reference) found that the temperature dependence was dependent on velocity regime. Low speed (diffusive) friction decreases upon heating while high speed (ballistic) friction rises with temperature.	Zhao et al. [53] found $F_{\text{fric}} \propto \exp(1/T)$.
Real contact area A	$F_{\text{fric}} \propto A$	Mo et al. [18] found that $F_{\text{fric}} \propto A$ where A is the real contact area defined by atoms within chemical range. This is not studied for the case of a nanoflake where the contact area is presumably rather constant.	

2.6 Research questions

Part II

Simulations

Appendices

Appendix A

Appendix B

Appendix C

Bibliography

- ¹E. Gnecco and E. Meyer, *Elements of friction theory and nanotribology* (Cambridge University Press, 2015).
- ²Bhusnur, “Introduction”, in *Introduction to tribology* (John Wiley & Sons, Ltd, 2013) Chap. 1, 1–?
- ³H.-J. Kim and D.-E. Kim, “Nano-scale friction: a review”, *International Journal of Precision Engineering and Manufacturing* **10**, 141–151 (2009).
- ⁴K. Holmberg and A. Erdemir, “Influence of tribology on global energy consumption, costs and emissions”, *Friction* **5**, 263–284 (2017).
- ⁵B. Bhushan, “Gecko feet: natural hairy attachment systems for smart adhesion – mechanism, modeling and development of bio-inspired materials”, in *Nanotribology and nanomechanics: an introduction* (Springer Berlin Heidelberg, Berlin, Heidelberg, 2008), pp. 1073–1134.
- ⁶P. Z. Hanakata, E. D. Cubuk, D. K. Campbell, and H. S. Park, “Accelerated search and design of stretchable graphene kirigami using machine learning”, *Phys. Rev. Lett.* **121**, 255304 (2018).
- ⁷P. Z. Hanakata, E. D. Cubuk, D. K. Campbell, and H. S. Park, “Forward and inverse design of kirigami via supervised autoencoder”, *Phys. Rev. Res.* **2**, 042006 (2020).
- ⁸L.-K. Wan, Y.-X. Xue, J.-W. Jiang, and H. S. Park, “Machine learning accelerated search of the strongest graphene/h-bn interface with designed fracture properties”, *Journal of Applied Physics* **133**, 024302 (2023).
- ⁹Y. Mao, Q. He, and X. Zhao, “Designing complex architectured materials with generative adversarial networks”, *Science Advances* **6**, eaaz4169 (2020).
- ¹⁰Z. Yang, C.-H. Yu, and M. J. Buehler, “Deep learning model to predict complex stress and strain fields in hierarchical composites”, *Science Advances* **7**, eabd7416 (2021).
- ¹¹A. E. Forte, P. Z. Hanakata, L. Jin, E. Zari, A. Zareei, M. C. Fernandes, L. Sumner, J. Alvarez, and K. Bertoldi, “Inverse design of inflatable soft membranes through machine learning”, *Advanced Functional Materials* **32**, 2111610 (2022).
- ¹²S. Chen, J. Chen, X. Zhang, Z.-Y. Li, and J. Li, “Kirigami/origami: unfolding the new regime of advanced 3D microfabrication/nanofabrication with “folding””, *Light: Science & Applications* **9**, 75 (2020).
- ¹³Z. Deng, A. Smolyanitsky, Q. Li, X.-Q. Feng, and R. J. Cannara, “Adhesion-dependent negative friction coefficient on chemically modified graphite at the nanoscale”, *Nature Materials* **11**, 1032–1037 (2012).
- ¹⁴R. W. Liefferink, B. Weber, C. Coulais, and D. Bonn, “Geometric control of sliding friction”, *Extreme Mechanics Letters* **49**, 101475 (2021).
- ¹⁵N Manini, O. M. Braun, E. Tosatti, R. Guerra, and A. Vanossi, “Friction and nonlinear dynamics”, *Journal of Physics: Condensed Matter* **28**, 293001 (2016).
- ¹⁶B. Bhushan and A. V. Kulkarni, “Effect of normal load on microscale friction measurements”, *Thin Solid Films* **278**, 49–56 (1996).
- ¹⁷J. Gao, W. D. Luedtke, D. Gourdon, M. Ruths, J. N. Israelachvili, and U. Landman, “Frictional forces and amontons’ law: from the molecular to the macroscopic scale”, *The Journal of Physical Chemistry B* **108**, Publisher: American Chemical Society, 3410–3425 (2004).
- ¹⁸Y. Mo, K. T. Turner, and I. Szlufarska, “Friction laws at the nanoscale”, *Nature* **457**, 1116–1119 (2009).
- ¹⁹G. Carbone and F. Bottiglione, “Asperity contact theories: do they predict linearity between contact area and load?”, *Journal of the Mechanics and Physics of Solids* **56**, 2555–2572 (2008).

- ²⁰W. Commons, *File:asperities.svg — wikimedia commons, the free media repository*, [Online; accessed 3-February-2023], 2022.
- ²¹I. Szlufarska, M. Chandross, and R. W. Carpick, “Recent advances in single-asperity nanotribology”, *Journal of Physics D: Applied Physics* **41**, 123001 (2008).
- ²²G. Binnig, C. F. Quate, and C. Gerber, “Atomic force microscope”, *Phys. Rev. Lett.* **56**, 930–933 (1986).
- ²³S. S. Perry, “Scanning Probe Microscopy Measurements of Friction”, *MRS Bulletin* **29**, 478–483 (2004).
- ²⁴Hertz, “On the contact of elastic solids”, *Crelle’s Journal* **92**, 156–171.
- ²⁵D. Maugis, “Adhesion of spheres: the jkr-dmt transition using a dugdale model”, *Journal of Colloid and Interface Science* **150**, 243–269 (1992).
- ²⁶M. H. Müser, “Rigorous field-theoretical approach to the contact mechanics of rough elastic solids”, *Phys. Rev. Lett.* **100**, 055504 (2008).
- ²⁷B. N. J. Persson, “Theory of rubber friction and contact mechanics”, *The Journal of Chemical Physics* **115**, 3840–3861 (2001).
- ²⁸J. A. Greenwood and J. B. P. Williamson, *Contact of nominally flat surfaces*, en, 1966.
- ²⁹A. Bush, R. Gibson, and T. Thomas, “The elastic contact of a rough surface”, *Wear* **35**, 87–111 (1975).
- ³⁰B. Luan and M. O. Robbins, “The breakdown of continuum models for mechanical contacts”, *Nature* **435**, 929–932 (2005).
- ³¹P. Zhu and R. Li, “Study of nanoscale friction behaviors of graphene on gold substrates using molecular dynamics”, *Nanoscale Research Letters* **13**, 34 (2018).
- ³²J. Zhang, E. Osloub, F. Siddiqui, W. Zhang, T. Ragab, and C. Basaran, “Anisotropy of graphene nanoflake–diamond interface frictional properties”, *Materials* **12**, 10.3390/ma12091425 (2019).
- ³³F. Bonelli, N. Manini, E. Cadelano, and L. Colombo, “Atomistic simulations of the sliding friction of graphene flakes”, *The European Physical Journal B* **70**, 449–459 (2009).
- ³⁴M. Dienwiebel, N. Pradeep, G. S. Verhoeven, H. W. Zandbergen, and J. W. Frenken, “Model experiments of superlubricity of graphite”, *Surface Science* **576**, 197–211 (2005).
- ³⁵X. Feng, S. Kwon, J. Y. Park, and M. Salmeron, “Superlubric sliding of graphene nanoflakes on graphene”, *ACS Nano* **7**, Publisher: American Chemical Society, 1718–1724 (2013).
- ³⁶J. Norell, A. Fasolino, and A. Wijn, “Emergent friction in two-dimensional frenkel-kontorova models”, *Physical Review E* **94**, 10.1103/PhysRevE.94.023001 (2016).
- ³⁷C. Kittel, *Introduction to solid state physics*, 8th ed. (Wiley, 2004).
- ³⁸J. A. van den Ende, A. S. de Wijn, and A. Fasolino, “The effect of temperature and velocity on superlubricity”, *Journal of Physics: Condensed Matter* **24**, 445009 (2012).
- ³⁹B. Bhushan, “Nanotribology and nanomechanics”, *Wear* **259**, 15th International Conference on Wear of Materials, 1–? (2005).
- ⁴⁰O. Penkov, H.-J. Kim, H.-J. Kim, and D.-E. Kim, “Tribology of graphene: A review”, *International Journal of Precision Engineering and Manufacturing* **15**, 577–585 (2014).
- ⁴¹G Paolicelli, M Tripathi, V Corradini, A Candini, and S Valeri, “Nanoscale frictional behavior of graphene on sio₂ and ni(111) substrates”, *Nanotechnology* **26**, 055703 (2015).
- ⁴²S. Zhang, Y. Hou, S. Li, L. Liu, Z. Zhang, X.-Q. Feng, and Q. Li, “Tuning friction to a superlubric state via in-plane straining”, *Proceedings of the National Academy of Sciences* **116**, Publisher: Proceedings of the National Academy of Sciences, 24452–24456 (2019).
- ⁴³M. R. Vazirisereshk, H. Ye, Z. Ye, A. Otero-de-la Roza, M.-Q. Zhao, Z. Gao, A. T. C. Johnson, E. R. Johnson, R. W. Carpick, and A. Martini, “Origin of nanoscale friction contrast between supported graphene, mos₂, and a graphene/mos₂ heterostructure”, *Nano Letters* **19**, PMID: 31267757, 5496–5505 (2019).
- ⁴⁴H. M. Yoon, Y. Jung, S. C. Jun, S. Kondaraju, and J. S. Lee, “Molecular dynamics simulations of nanoscale and sub-nanoscale friction behavior between graphene and a silicon tip: analysis of tip apex motion.”, *Nanoscale* **7** **14**, 6295–303 (2015).

- ⁴⁵S. Li, Q. Li, R. W. Carpick, P. Gumbsch, X. Z. Liu, X. Ding, J. Sun, and J. Li, “The evolving quality of frictional contact with graphene”, *Nature* **539**, Number: 7630, 541–545 (2016).
- ⁴⁶A. Wijn, A. Fasolino, A. Filippov, and M. Urbakh, “Low friction and rotational dynamics of crystalline flakes in solid lubrication”, *Europhysics Letters (epl)* **95**, 10.1209/0295-5075/95/66002 (2011).
- ⁴⁷H.-J. Kim and D.-E. Kim, “Molecular dynamics simulation of atomic-scale frictional behavior of corrugated nano-structured surfaces”, *Nanoscale* **4**, 3937–3944 (2012).
- ⁴⁸M. Reguzzoni, A. Fasolino, E. Molinari, and M. C. Righi, “Friction by shear deformations in multilayer graphene”, *The Journal of Physical Chemistry C* **116**, 21104–21108 (2012).
- ⁴⁹Y. Liu, F. Grey, and Q. Zheng, “The high-speed sliding friction of graphene and novel routes to persistent superlubricity”, *Scientific Reports* **4**, 4875 (2014).
- ⁵⁰M. Reguzzoni and M. C. Righi, “Size dependence of static friction between solid clusters and substrates”, *Phys. Rev. B* **85**, 201412 (2012).
- ⁵¹N. Varini, A. Vanossi, R. Guerra, D. Mandelli, R. Capozza, and E. Tosatti, “Static friction scaling of physisorbed islands: the key is in the edge”, *Nanoscale* **7**, 2093–2101 (2015).
- ⁵²U. D. Schwarz, O. Zwörner, P. Köster, and R. Wiesendanger, “Quantitative analysis of the frictional properties of solid materials at low loads. i. carbon compounds”, *Phys. Rev. B* **56**, 6987–6996 (1997).
- ⁵³X. Zhao, M. Hamilton, W. G. Sawyer, and S. S. Perry, “Thermally activated friction”, *Tribology Letters* **27**, 113–117 (2007).