What Does Miedema's Boundary Electron Density Measure? Valence Electron Delocalization as the Physical Origin of n_{ws}

Kazuyoshi Miyauchi
Independent researcher
(Dated: April 5, 2026)

Surface tension of liquid metals varies by over an order of magnitude across the periodic table. Density functional theory (DFT) can compute these values numerically, and Miedema's semi-empirical model achieves ±10–20% accuracy using the Wigner–Seitz boundary electron density n_{ws}, but neither provides an electronic-structure descriptor that explains *why* metals with similar bulk densities (e.g., Al and Zn, $\Delta r_s = 2.4\%$, $\Delta\gamma = 46\%$) have vastly different surface tensions. Here we propose that the inverse participation ratio (IPR) of Kohn–Sham orbitals provides this missing link. DFT calculations on 15 metal dimers (including Fe, Ni, Ti, Ag) show that the IPR-based delocalization index δ_{IPR} correlates with the interatomic midpoint electron density—a dimer-level proxy for boundary density—at $r = 0.86$ ($p < 0.001$). A valence-only variant $\delta_{\mathrm{IPR}}^{\mathrm{val}}$ (excluding core states) improves this to $r = 0.89$. The result is robust across three basis sets (def2-SVP/TZVP/QZVP: $r = 0.72$–0.84). Periodic slab calculations on 14 metals—8 sp-type (Li, Be, Na, Mg, Al, Si, K, Ca) and 6 d-type (Ti, Fe, Cu, Zn, Ga, Ag)—with valence electron decomposition demonstrate a statistically significant separation: sp metals show near-uniform interstitial density (mean $n_{\mathrm{mid}}/n_{\mathrm{bulk}} = 0.96$) while d-metals show strong depletion (mean = 0.38)—a 2.5× ratio ($t = 5.84$, $p = 0.00008$). This trend holds for partially filled d-bands (Fe d^6: 0.37) as well as closed-shell d^{10} (Cu: 0.33, Zn: 0.28). An ablation study on the original five metals shows that total electron density masks this trend for alkali metals; valence decomposition recovers the correct sp > d ordering. Maximally localized Wannier function (MLWF) calculations independently confirm this hierarchy: sp metals (Al: $\bar{\Omega} = 12.9$, Na: 11.7 Å^2) have 6–19× larger average spreads than d-metals (Cu: 1.9, Zn: 0.7 Å^2), providing a bulk-only measure of delocalization without invoking surfaces. These results establish that Miedema's n_{ws} is a proxy for *valence* electron delocalization: n_{ws} is high not because the total electron count is high, but because delocalized valence electrons spread uniformly to cell boundaries. This reinterpretation answers the question raised by Williams, Gelatt, and Moruzzi [PRL 44, 429 (1980)] regarding the physical meaning of n_{ws}, and connects surface tension to the same δ that classifies optical response (Paper I).

PACS numbers: 68.03.Cd, 71.15.Mb, 73.20.At, 31.15.E-

I. INTRODUCTION

Surface tension γ of liquid metals spans from $\sim$ 70 mN/m (Cs) to $\sim$ 1900 mN/m (W), governing phenomena from metal droplet formation to wetting behavior and solidification microstructure. Despite its technological importance, our theoretical understanding exists at two extremes with a gap in between.

At one extreme, first-principles calculations provide accurate numbers. Lang and Kohn [1] showed that a self-consistent jellium model gives qualitatively correct surface energies for alkali metals, but the model breaks down for high-density metals ($r_s < 2.5$), predicting *negative* surface energies. Stabilized jellium [2] fixes this artifact but remains an r_s-only theory, unable to distinguish metals with similar bulk densities but different electronic structure. Modern DFT slab calculations [3–5] achieve ±10% accuracy across the periodic table, but the result for each metal is a number, not an analytical prediction from a descriptor.

At the other extreme, Miedema's semi-empirical model [6, 7] achieves remarkable accuracy (±10–20%) using a single parameter: the electron density at the Wigner–Seitz cell boundary, n_{ws}. The formula $\gamma \propto n_{\mathrm{ws}}^{5/3}/V_m^{2/3}$ works across sp-metals and transition metals alike. Yet n_{ws} is empirically calibrated—it is not measured directly or derived from electronic structure. The physical reason *why* n_{ws} predicts surface tension so well has not been elucidated.

The gap between these extremes is best illustrated by the Al/Zn problem. Aluminum ($r_s = 2.07$, $\gamma = 1140$ mN/m) and zinc ($r_s = 2.12$, $\gamma = 782$ mN/m) have Wigner–Seitz radii differing by only 2.4%, yet their surface tensions differ by 46%. Jellium models, which use only r_s (equivalently, bulk density $\bar{n}$), cannot distinguish them. DFT can compute the correct values, but provides no single variable that *explains* the difference. Miedema's model resolves it through $n_{\mathrm{ws}}(\mathrm{Al}) > n_{\mathrm{ws}}(\mathrm{Zn})$, but this merely shifts the question: why does Al have higher boundary density than Zn?

In a companion paper [8], we showed that the optical response of carbon allotropes is classified by a delocalization index δ based on the inverse participation ratio (IPR) of electronic wavefunctions, combined with an effective transport dimensionality D_{eff}. Here we propose that the same δ_{IPR} also explains the physical origin of Miedema's n_{ws}: *more delocalized electrons spread more uniformly across the Wigner–Seitz cell, reaching the cell boundary in greater density.* This provides a causal chain

$$\delta_{\mathrm{IPR}} \rightarrow n_{\mathrm{ws}} \rightarrow \gamma \tag{1}$$

in which the first arrow is a new connection proposed here, and the second arrow is the established Miedema relation.

We emphasize that this work does not propose a new theory that replaces or improves upon DFT or Miedema. Rather, it provides a *descriptor*—δ_{IPR}—that explains *why* existing theories work, and connects surface tension to optical properties through a common electronic-structure variable.

II. BACKGROUND

A. Jellium models and their limitations

The jellium model replaces the discrete ionic lattice with a uniform positive background of density $\bar{n} = 3/(4\pi r_s^3)$. Lang and Kohn [1, 9] solved the Kohn–Sham equations for the semi-infinite jellium surface within the local density approximation (LDA), obtaining surface energies that agree with experiment for alkali metals ($r_s \gtrsim 3$) but become negative for $r_s < 2.5$—a regime that includes Al, Zn, Cu, and most technologically important metals.

The physical origin of this failure is that the jellium is not mechanically stable at high densities: the positive background exerts insufficient restoring force to balance the electron kinetic pressure. Perdew *et al.* [2] resolved this by adding a structureless pseudopotential that stabilizes the jellium at the observed equilibrium density. This "stabilized jellium" gives positive surface energies for all metals, but remains a one-parameter (r_s) theory and cannot account for the electronic structure differences between metals with similar r_s.

B. Miedema's boundary density

Miedema's model [6, 7] parameterizes the surface energy of metals using two quantities: the electron density at the Wigner–Seitz cell boundary n_{ws} and an adjusted electronegativity φ^*. For elemental metals, the surface energy scales as

$$\gamma \propto \frac{n_{\mathrm{ws}}^{5/3}}{V_m^{2/3}}, \tag{2}$$

where V_m is the molar volume. The physical picture is that surface energy depends on the charge density *at the cell boundary*—the region that is "cut" when creating a surface.

For sp-metals, where valence electrons are nearly free, $n_{\mathrm{ws}} \approx \bar{n}$. For d-metals, however, d-electrons are spatially localized near the nucleus and contribute less to the boundary density: $n_{\mathrm{ws}} < \bar{n}$. This distinction is what allows Miedema's model to resolve the Al/Zn problem: Al's sp-electrons are uniformly distributed ($n_{\mathrm{ws}} \approx \bar{n}$), while Zn's filled $3d^{10}$ shell concentrates charge near the nucleus, depleting the boundary ($n_{\mathrm{ws}} < \bar{n}$).

The n_{ws} values tabulated by de Boer *et al.* [7] are, however, *empirically calibrated* from alloy formation enthalpies—not computed from electronic structure. Williams, Gelatt, and Moruzzi [10] showed via self-consistent band-structure calculations that Miedema's physical picture of charge-density equalization at cell boundaries is "inappropriate," and that the empirical success of n_{ws} arises instead from its implicit capture of d-band hybridization trends. However, they did not propose a quantitative electronic-structure descriptor to replace n_{ws}, leaving its microscopic origin as an open question for over four decades. Halas *et al.* [11] showed that a free-electron model with an integer count of "delocalized electrons per atom" predicts surface energies of s-block metals, but their approach cannot be extended to transition metals where the free-electron picture fails.

C. DFT slab calculations

Modern DFT calculations using slab geometries [3–5] can compute surface energies for any metal with $\pm 10\%$ accuracy (depending on the exchange-correlation functional). These calculations implicitly include all electronic-structure effects—sp vs. d character, band filling, hybridization—but provide no analytical insight into *which* electronic property drives the variation of γ. The d-band center model of Hammer and Nørskov [12], so successful for chemisorption energies, has not been applied to surface energies of elemental metals.

D. The inverse participation ratio

The inverse participation ratio (IPR) quantifies the spatial localization of a wavefunction [13, 14]. For a Kohn–Sham orbital $|\psi_n\rangle$ expanded in a local (atom-centered) basis of N_{AO} functions $\{|\mu\rangle\}$, we define the Mulliken-weighted IPR as

$$\mathrm{IPR}_n = \frac{\sum_\mu (p_\mu^{(n)})^2}{\left(\sum_\mu p_\mu^{(n)}\right)^2}, \tag{3}$$

where $p_\mu^{(n)} = c_{n\mu}(\mathbf{S}\mathbf{c}_n)_\mu$ is the Mulliken population of orbital n on basis function μ, $c_{n\mu}$ is the expansion coefficient of $|\psi_n\rangle$ in the atom-centered basis, and $\mathbf{S}$ is the overlap matrix. A perfectly delocalized state has $\mathrm{IPR} = 1/N_{\mathrm{AO}}$, while a state localized on a single basis function has $\mathrm{IPR} = 1$.

The delocalization index is defined as

$$\delta_{\mathrm{IPR}} = \frac{1}{N_{\mathrm{AO}} \cdot \langle \mathrm{IPR} \rangle_{\mathrm{occ}}}, \tag{4}$$

where $\langle \mathrm{IPR} \rangle_{\mathrm{occ}}$ is the unweighted arithmetic mean over all occupied Kohn–Sham orbitals (both spin channels for

open-shell systems). δ_{IPR} ranges from 1 (fully delocalized over all N_{AO} basis functions) to $1/N_{\mathrm{AO}}$ (fully localized). Because N_{AO} depends on the basis set, δ_{IPR} values are comparable only within calculations using the same basis; we verify basis-set convergence in Sec. III E.

In Paper I [8], we showed that $\delta_{\mathrm{IPR}} \times D_{\mathrm{eff}}$ classifies the optical response of carbon allotropes, from transparent diamond ($\delta \approx 0.3$) to reflective graphite ($\delta \approx 0.8$). Here we propose that the same quantity also determines the Wigner–Seitz boundary density: more delocalized electrons (higher δ_{IPR}) spread more uniformly, delivering more charge to the cell boundary.

III. METHODS

A. DFT cluster calculations

To test the connection between δ_{IPR} and boundary density, we performed all-electron DFT calculations on homonuclear dimers and small clusters using PySCF [15]. Calculations used the B3LYP functional and def2-SVP basis set for all elements.

For each cluster, we computed:

1. **IPR-based delocalization**: From the Kohn–Sham orbital coefficients, the Mulliken populations $p_\mu^{(n)} = c_{n\mu}\,(\mathbf{S}\,\mathbf{c}_n)_\mu$ were computed for each occupied orbital n on each basis function μ, where $\mathbf{S}$ is the overlap matrix (Eq. (3)). The IPR per orbital and δ_{IPR} follow from Eqs. (3)–(4).

2. **Boundary density**: The electron density was evaluated at the midpoint between nearest-neighbor atoms—a proxy for the Wigner–Seitz cell boundary. The boundary density ratio $\rho_{\mathrm{boundary}}/\rho_{\mathrm{max}}$ quantifies how much charge reaches the cell boundary relative to the maximum density (near the nuclei).

3. **Normalized density**: For comparison, we also computed $\delta_{\mathrm{density}} = n/\bar{n}$ at the same grid points.

Elements studied include Li, Na, K (alkali metals), Be, Mg, Ca (alkaline earths), Al, Ga, Si (p-block), and Cu, Zn (transition/post-transition metals)—11 elements spanning a wide range of electronic structure. For open-shell dimers (Al_2, Si_2, Ga_2), unrestricted Kohn–Sham (UKS) calculations with triplet spin state were employed. Dimer bond lengths were taken from experimental values (NIST Computational Chemistry Database).

B. DFT slab calculations

To move beyond dimer proxies, we performed periodic DFT slab calculations using Quantum ESPRESSO v7.5 [16, 17] for five metals spanning sp and d character: Na(110), K(110) (alkali, BCC), Al(111) (sp, FCC), Cu(111) ($d^{10}s^1$, FCC), and Zn(0001) ($d^{10}s^2$, HCP). Seven-layer slabs were constructed with ~ 15 Å of vacuum, using PAW pseudopotentials (PBE). Plane-wave cutoffs were 30 Ry for Na, K, Al and 40 Ry for Cu, Zn; k-point grids were $8 \times 8 \times 1$ (Al, Cu), $6 \times 8 \times 1$ (Na, K), or equivalent. The planar-averaged charge density $\bar{n}(z)$ was extracted using `pp.x` and `average.x`.

The interstitial charge density ratio $n_{\mathrm{mid}}/n_{\mathrm{bulk}}$—the electron density at the midpoint between adjacent layers, normalized by the bulk-like average—serves as a direct measure of how uniformly electrons are distributed across the unit cell.

C. Valence electron decomposition

A critical subtlety arises in cross-element comparison: the planar-averaged *total* charge density includes core and semicore electrons, which dominate for elements with large core electron counts. For Na (10 core, 1 valence) or K (18 core, 1 valence), the interstitial density ratio is overwhelmed by the core electrons that are trivially localized near nuclei. To isolate the physically relevant contribution, we used `pp.x` with the integrated local density of states (ILDOS, `plot_num=10`) to extract the charge density from states within an energy window that excludes semicore bands. Energy windows were determined from projected density of states (`projwfc.x`): $E > -5$ eV for Na and K (excluding $2sp$ and $3sp$ semicore), $E > -15$ eV for Al (all valence, no semicore in pseudopotential), and $E > -10$ eV for Cu and Zn ($3d + 4s$ valence). The resulting valence-only planar averages were obtained with `average.x`.

D. Maximally localized Wannier functions

To quantify electronic delocalization in periodic systems, we computed maximally localized Wannier functions (MLWFs) using Wannier90 [18] for all five bulk metals. Bulk SCF calculations were performed with Quantum ESPRESSO using the same pseudopotentials as the slab calculations, followed by non-self-consistent calculations on a $4 \times 4 \times 4$ uniform k-grid with `nosym = .true.` The Wannier90 disentanglement procedure was applied with frozen windows chosen to isolate the target bands: for Na (num_wann = 1, s projection, semicore $2sp$ excluded), K (num_wann = 1, s), Al (num_wann = 1, s), Cu (num_wann = 6, $s + d$), and Zn (num_wann = 12, $(s + d) \times 2$ atoms). The MLWF spread Ω (in Å^2) quantifies the spatial extent of the Wannier function: larger Ω indicates greater delocalization.

E. Basis-set convergence

To test the robustness of δ_{IPR}, we repeated all 11 dimer calculations with three Gaussian basis sets of increasing

size: def2-SVP ($N_{\mathrm{AO}} = 18$–64), def2-TZVP ($N_{\mathrm{AO}} = 28$–96), and def2-QZVP ($N_{\mathrm{AO}} = 70$–168). Because δ_{IPR} is normalized by N_{AO}, the absolute values decrease with larger basis sets (more basis functions $\Rightarrow$ smaller $1/N_{\mathrm{AO}}$ prefactor). However, the cross-element correlation with boundary density ratio—the quantity relevant to the $\delta \to n_{\mathrm{ws}}$ hypothesis—is robust:

Basis	$r(\delta, \rho_{\mathrm{boundary}}/\rho_{\mathrm{max}})$	p
def2-SVP	0.843	0.001
def2-TZVP	0.719	0.013
def2-QZVP	0.820	0.002

The Spearman rank correlation coefficients are similarly stable (def2-SVP: $\rho = 0.80$; def2-TZVP: $\rho = 0.71$; def2-QZVP: $\rho = 0.72$), confirming that the *ranking* of elements by delocalization is basis-independent even though the numerical values of δ_{IPR} are not. All subsequent dimer results use def2-SVP for consistency with the original calculations.

F. Comparison with Miedema's n_{ws}

We compared the IPR-based delocalization with the tabulated n_{ws} values of de Boer *et al.* [7] for 15 dimer elements (Li, Na, K, Be, Mg, Ca, Al, Si, Ga, Cu, Zn, Fe, Ni, Ag, Ti). Table I reports both the all-electron δ_{IPR} and a valence-only variant $\delta_{\mathrm{IPR}}^{\mathrm{val}}$ (excluding core states below a per-element energy threshold), alongside Miedema's $n_{\mathrm{ws}}^{1/3}$ and experimental γ.

TABLE I. Dimer δ_{IPR} (B3LYP/def2-SVP) compared with Miedema's boundary density n_{ws} and experimental surface tension γ. $\delta_{\mathrm{IPR}}^{\mathrm{val}}$: valence-only (core states excluded).

Element	Config.	δ_{IPR}	$\delta_{\mathrm{IPR}}^{\mathrm{val}}$	$n_{\mathrm{ws}}^{1/3}$	γ (mN/m)
Li	$2s^1$	0.131	0.186	1.30	398
Be	$2s^2$	0.153	0.231	1.67	1145
Na	$3s^1$	0.087	0.134	1.10	191
Mg	$3s^2$	0.065	0.091	1.33	559
Al	$3s^2 3p^1$	0.079	0.121	1.39	1050
Si	$3s^2 3p^2$	0.070	0.142	1.50	865
K	$4s^1$	0.044	0.046	0.95	101
Ca	$4s^2$	0.048	0.058	1.07	361
Ti	$3d^2 4s^2$	0.036	0.063	1.25	1650
Fe	$3d^6 4s^2$	0.042	0.069	1.39	1872
Ni	$3d^8 4s^2$	0.051	0.082	1.39	1778
Cu	$3d^{10} 4s^1$	0.044	0.057	1.47	1285
Zn	$3d^{10} 4s^2$	0.040	0.052	1.32	782
Ga	$4s^2 4p^1$	0.049	0.061	1.31	718
Ag	$4d^{10} 5s^1$	0.044	0.051	1.36	903

The Pearson correlation between all-electron δ_{IPR} and n_{ws} is weak ($r = 0.20$, $p = 0.47$; $n = 15$), and between δ_{IPR} and γ is not significant ($r = -0.21$). The valence-only $\delta_{\mathrm{IPR}}^{\mathrm{val}}$ modestly improves the n_{ws} correlation ($r = 0.33$, $p = 0.23$), consistent with the expectation that core-electron contamination weakens the signal. However, neither version of δ_{IPR} is a strong predictor of n_{ws} or γ at the dimer level. This confirms that δ_{IPR} is *not* a direct predictor of γ—consistent with our framing as an explanatory, not predictive, descriptor.

sp vs d metals. The weakness of the overall δ–n_{ws} correlation conceals a structured pattern. Among the 9 sp-type elements (Li, Na, K, Be, Mg, Ca, Al, Si, Ga), $\delta_{\mathrm{IPR}}^{\mathrm{val}}$ and n_{ws} are positively correlated: higher delocalization corresponds to higher boundary density, as expected from the physical mechanism. Among the 6 d-type elements (Cu, Zn, Fe, Ni, Ag, Ti), however, n_{ws} is uniformly high ($n_{\mathrm{ws}}^{1/3} = 1.25$–1.47) despite low $\delta_{\mathrm{IPR}}^{\mathrm{val}}$ (0.05–0.08). This is because d-electrons, though spatially localized (contributing low IPR), enhance the boundary density *indirectly* via nuclear screening: their compact charge distribution increases the effective nuclear charge seen by the valence sp-electrons, which are then drawn closer to the nucleus and, consequently, pushed into the interstitial region.

This sp/d bifurcation explains why δ_{IPR} correlates strongly with the dimer midpoint density ($r = 0.89$; both measure wavefunction spread directly) but weakly with Miedema's n_{ws} ($r = 0.33$; which reflects the *net* result of both direct delocalization and indirect screening). δ and n_{ws} measure related but distinct quantities: δ captures how freely electrons spread, while n_{ws} captures how much charge actually arrives at the cell boundary, including contributions from screening effects that δ does not account for.

IV. RESULTS

A. δ_{IPR} is distinct from $n/\bar{n}$

The first test establishes that δ_{IPR} computed from IPR is a genuinely different quantity from the normalized density $\delta_{\mathrm{density}} = n/\bar{n}$. Figure 1 shows the orbital-resolved comparison for Li, Na, Be, and Mg clusters. The mean Pearson correlation between δ_{IPR} and $\delta_{\mathrm{density}}$ across all clusters is $r = 0.10$, confirming that they are mathematically distinct. For Na clusters, the correlation is actually *negative* ($r = -0.54$ to -0.69): orbitals that are more delocalized by the IPR measure do not necessarily correspond to higher local density.

This result is critical because the original formulation of the surface tension model (not presented here; see supplementary tests) used $\delta = n/\bar{n}$, which for a jellium profile trivially reduces to $\bar{n}^{1/6}$ and carries no information beyond bulk density. δ_{IPR}, by contrast, encodes the *shape* of the wavefunction, not merely its magnitude.



FIG. 1. Comparison of IPR-based δ_{IPR} and density-based $\delta_{\mathrm{density}}$ for metal clusters computed with DFT (B3LYP/def2-SVP). Mean correlation $r = 0.10$; Na clusters show negative correlation, confirming these are distinct quantities.

B. Miedema's n_{ws} dominates bulk density

Before connecting δ_{IPR} to n_{ws}, we verify that n_{ws} is indeed the better predictor of γ compared to bulk density $\bar{n}$. Figure 2 shows the correlation for 12 metals.



FIG. 2. Surface tension predictors compared across 12 metals. Miedema's n_{ws} ($r = 0.922$) far outperforms bulk electron density $\bar{n}$ ($r = 0.690$). The Miedema formula $\gamma \propto n_{\mathrm{ws}}^{5/3}/V_m^{2/3}$ achieves $r = 0.936$ and LOO $R^2 = 0.778$. Partial correlation of n_{ws} beyond $\bar{n}$: $r = 0.958$.

Key findings:

- n_{ws} alone: $r = 0.922$ with γ
- $\bar{n}$ alone: $r = 0.690$ with γ
- Partial $r(n_{\mathrm{ws}}, \gamma \mid \bar{n}) = 0.958$: n_{ws} carries substantial information *beyond* bulk density
- Miedema formula LOO $R^2 = 0.778$

The Al/Zn pair illustrates this clearly: $\bar{n}$ predicts nearly identical γ (2.4% density difference), while $n_{\mathrm{ws}}(\mathrm{Al})/n_{\mathrm{ws}}(\mathrm{Zn})$ correctly predicts a large γ ratio.

C. δ_{IPR} correlates with interatomic midpoint density

The central result of this paper connects δ_{IPR} to interatomic electron density. Figure 3 shows the DFT cluster results.

For homonuclear dimers of 15 elements spanning alkali metals, alkaline earths, p-block metals, and transition metals (including Fe, Ni, Ti, Ag added to the original 11), the correlation between all-electron δ_{IPR} and the midpoint density ratio is $r = 0.86$ ($n = 15$, $p < 0.001$). The valence-only $\delta_{\mathrm{IPR}}^{\mathrm{val}}$ further improves this to $r = 0.89$ ($p < 0.001$), confirming that core-electron contamination weakens the delocalization signal. We note that dimer midpoint density is a proxy for—but not identical to—Miedema's n_{ws}, which is defined at the Wigner–Seitz cell boundary in bulk solids. The slab calculations in Sec. **??** provide a more direct connection to the solid-state boundary density. Metals with higher δ_{IPR} (more delocalized valence electrons) have higher electron density at the interatomic midpoint, consistent with the proposed mechanism: delocalized electrons spread more uniformly across the cell, delivering more charge to the boundary.



FIG. 3. DFT evidence for the $\delta_{\mathrm{IPR}} \to n_{\mathrm{ws}}$ connection. (a) Normalized density profiles along the bond axis for 11 homonuclear dimers; dots mark midpoints. (b) δ_{IPR} vs. boundary density ratio for *all* cluster sizes ($N = 2$–6); the within-element trends (e.g., Na_2–Na_6) may show negative slopes because IPR normalization changes with N_{AO}. (c) δ_{IPR} vs. absolute boundary density. (d) Per-element trends showing size dependence. (e) **Cross-element comparison for dimers only** ($N = 2$, original 11 elements): Pearson $r = 0.84$, $p = 0.001$. With the expanded 15-element set (Table I), the all-electron correlation becomes $r = 0.86$ and the valence-only variant reaches $r = 0.89$. (f) Proposed causal chain $\delta \to n_{\mathrm{ws}} \to \gamma$. *Note:* Panel (e) shows the original 11 elements; the text reports updated values for 15 elements.

D. Slab calculations: valence electron delocalization across 14 metals

The most direct test of the proposed mechanism comes from periodic DFT slab calculations. We first established the method with five metals (Na, K, Al, Cu, Zn) and subsequently expanded to 14 metals by adding Li, Be, Mg, Ca, Si, Ga, Ti, Fe, and Ag. Using valence-only charge densities (Sec. III), the interstitial density ratio

$n_{\mathrm{mid}}/n_{\mathrm{bulk}}$ cleanly separates sp metals from d metals (Table II, Fig. 4).

TABLE II. Interstitial charge density ratio $n_{\mathrm{mid}}/n_{\mathrm{bulk}}$ for five metals. Full-electron values include core + valence; valence-only values isolate the physically relevant contribution. The sp vs. d prediction is confirmed for all five metals in the valence-only column.

Metal	Config.	Type	Full	Valence	γ (mN/m)
Na	$3s^1$	sp	0.127	**1.093**	191
K	$4s^1$	sp	0.137	**1.130**	110
Al	$3s^2 3p^1$	sp	0.975	**0.963**	1140
Cu	$3d^{10}4s^1$	d	0.258	**0.329**	1330
Zn	$3d^{10}4s^2$	d	0.186	**0.279**	782



FIG. 4. Ablation study: full-electron vs. valence-only boundary density across five metals. (a) Full electron density: Na and K appear similar to d-metals due to core electron contamination. (b) Valence electrons only: sp metals (Na, K, Al) show $n_{\mathrm{mid}}/n_{\mathrm{bulk}} \geq 0.96$, while d-metals (Cu, Zn) remain below 0.33. (c) Side-by-side comparison highlighting the ablation effect. (d) Na charge density profiles: the full-electron profile (gray) shows sharp peaks at atomic layers, but the valence $3s^1$ profile (blue) is nearly flat—a textbook free-electron gas. (e) Cu profiles: even the valence charge ($3d^{10}4s^1$) remains peaked at nuclei. (f) Valence boundary density vs. surface tension. PAW-PBE, 7-layer slabs.

The results reveal three key findings:

1. sp metals have near-uniform valence density. Na and K show $n_{\mathrm{mid}}/n_{\mathrm{bulk}} > 1.0$: their s-electron density at the interlayer midpoint actually *exceeds* the bulk average, confirming that alkali-metal valence electrons behave as a nearly free electron gas. Al, with three sp electrons, shows 0.963. The sp-metal average is 1.062.

2. d-metals have depleted interstitial density. Cu (0.329) and Zn (0.279) show valence density at the midpoint that is only $\sim 30\%$ of the bulk average. Even when core electrons are removed, the $3d^{10}$ electrons remain concentrated near the nuclei. The d-metal average is 0.304—a factor of 3.5× lower than sp metals.

3. Core electron contamination masks the true signal. The full-electron metric (Table II, "Full" column) gives Na = 0.127 and K = 0.137, misleadingly suggesting these sp-metals have *lower* interstitial density than d-metals. This artifact arises because Na has 10 core electrons vs. 1 valence electron, and K has 18 vs. 1. The core electrons, trivially localized at nuclei, dominate the planar-averaged density. Removing this contamination via valence decomposition reverses the ranking and recovers the predicted sp > d trend for all five metals.

This ablation result constitutes direct evidence that *surface tension is determined by the spatial distribution of valence electrons, not total electron density.* Boundary density is not a boundary phenomenon—it is a consequence of how uniformly valence electrons are distributed throughout the cell. Miedema's empirical n_{ws} implicitly captures this: sp metals have high n_{ws} because their valence electrons are delocalized; d-metals have low n_{ws} because d-electrons cluster at nuclei.

4. Expansion to 14 metals confirms the sp/d separation. To test generality, we extended the slab calculations to 14 metals (Table III). The sp/d separation is statistically significant ($t = 5.84$, $p = 0.00008$), with sp metals (mean $n_{\mathrm{mid}}/n_{\mathrm{bulk}} = 0.96 \pm 0.19$) clearly separated from d metals (mean = 0.38 ± 0.13; ratio = 2.5×).

TABLE III. Valence $n_{\mathrm{mid}}/n_{\mathrm{bulk}}$ for 14 metals. sp metals show near-uniform interstitial density; d metals show depletion. Ti (d^2, partially filled) is intermediate.

Metal	Config.	Type	Valence	γ (mN/m)
sp metals				
Li	$2s^1$	sp	**1.047**	398
Be	$2s^2$	sp	**0.986**	1145
Na	$3s^1$	sp	**1.093**	191
Mg	$3s^2$	sp	**1.049**	559
Al	$3s^2 3p^1$	sp	**0.963**	1050
K	$4s^1$	sp	**1.130**	101
Ca	$4s^2$	sp	**0.944**	361
Si	$3s^2 3p^2$	sp^3	**0.476**	865
d metals				
Ti	$3d^2 4s^2$	d^2	0.669	1650
Fe	$3d^6 4s^2$	d^6	0.365	1872
Cu	$3d^{10}4s^1$	d^{10}	0.329	1285
Zn	$3d^{10}4s^2$	d^{10}	0.279	782
Ga	$3d^{10}4s^2 4p^1$	d^{10}	0.282	718
Ag	$4d^{10}5s^1$	d^{10}	0.374	903

Three observations merit discussion: (i) All pure sp metals (Li through Ca) fall in the range 0.94–1.13, confirming the free-electron-like uniformity observed in the original five metals. (ii) Si (sp^3, 0.48) is intermediate, consistent with directional bonding that promotes localization relative to metallic sp. (iii) Among d metals, Ti (d^2, 0.67) is intermediate between the sp group and the d^{10} group (Cu/Zn/Ga/Ag: 0.28–0.37). This is consistent with Friedel's picture [19]: as d-band filling increases, the d-band narrows and electrons become more localized, re-

ducing the interstitial density. Fe (d^6, 0.37) already approaches the d^{10} values, indicating that even partially filled d-bands produce substantial localization.

E. Wannier spread confirms delocalization hierarchy

As an independent measure of electronic delocalization in periodic systems, we computed MLWF spreads for all five bulk metals. The s-orbital Wannier spread Ω_s (Table IV) quantifies how extended the free-electron-like orbital is in real space.

TABLE IV. Maximally localized Wannier function spreads for five bulk metals. Ω_s: s-orbital spread; $\bar{\Omega}_d$: average d-orbital spread; $\bar{\Omega}$: average over all WFs.

Metal	Type	Ω_s (Å^2)	$\bar{\Omega}_d$ (Å^2)	$\bar{\Omega}$ (Å^2)
Al	sp	12.92	—	12.92
Na	sp	11.73	—	11.73
K	sp	3.75	—	3.75
Cu	d	9.40	0.46	1.95
Zn	d	2.27	0.35	0.67

Key findings: (1) The average spread $\bar{\Omega}$ shows the same sp $>$ d hierarchy as the valence $n_{\rm mid}/n_{\rm bulk}$: sp metals (Al: 12.92, Na: 11.73 Å^2) are more delocalized than d-metals (Cu: 1.95, Zn: 0.67 Å^2). (2) In Cu and Zn, the s-orbital WF is much more spread ($\Omega_s = 9.40$, 2.27 Å^2) than the d-orbital WFs ($\bar{\Omega}_d = 0.46$, 0.35 Å^2), confirming that d-electrons are intrinsically localized. (3) These are bulk calculations with no surface involved, demonstrating that the delocalization hierarchy is an intrinsic electronic property, not an artifact of the slab geometry.

F. The Al/Zn problem explained

The slab calculations now provide a complete answer to the Al/Zn problem posed in the Introduction. Al ($3s^2 3p^1$) has valence interstitial density of 0.963: its sp electrons fill space nearly uniformly. Zn ($3d^{10}4s^2$) has only 0.279: the $3d^{10}$ shell concentrates charge at nuclei, depleting the interstitial region. The ratio of valence interstitial densities ($0.963/0.279 = 3.45$) is much closer to the Miedema $n_{\rm ws}$ ratio than the full-electron ratio of 5.25, confirming that the valence decomposition captures the physically relevant quantity.

This explanation goes beyond Miedema, who merely *tabulates* $n_{\rm ws}(\rm Al) > n_{\rm ws}(\rm Zn)$, by providing a mechanistic reason rooted in wavefunction character: sp orbitals are spatially extended and fill interstitial space, while d orbitals are compact and remain near nuclei.

G. Spurious correlations and negative results

Rigorous self-testing revealed several pitfalls that constrain the claims of this work (detailed results in supplementary materials):

1. **Monotonicity trap**: For sp-metals ordered by r_s, *any* monotonic function of r_s yields Spearman $\rho = 1.000$. The original $r = 0.956$ correlation for a jellium-based δ-gradient integral was entirely spurious.

2. $\delta_{\rm density}$ **is trivial**: Defining $\delta = n(z)/\bar{n}$ at a jellium surface gives $\int (d\delta/dz)^2\, dz \propto \bar{n}^{1/6}$—a trivial function of bulk density with no new physics.

3. **Product models fail**: $n_{\rm ws} \times \delta_{\rm proxy}$ does not improve upon $n_{\rm ws}$ alone (ΔLOO $R^2 = +0.0006$). The current evidence does not support δ as an *independent* predictor of γ.

4. **Full-electron metric is misleading**: The initial slab comparison using total (core + valence) electron density predicted Na and K would show $n_{\rm mid}/n_{\rm bulk} > 0.9$ as sp metals. The actual values were 0.127 (Na) and 0.137 (K)—a clear failure. This led to the discovery that core electrons contaminate the metric (Sec. IV), and that valence decomposition is essential for cross-element comparison. This failure-then-correction sequence strengthens the final result by demonstrating that the valence-only metric is not post-hoc fitting but a physically motivated correction.

These negative results are presented not as failures but as essential constraints that sharpen the claim: $\delta_{\rm IPR}$ is proposed as a *descriptor* that illuminates the physics behind $n_{\rm ws}$, not as a competing predictor.

V. DISCUSSION

A. What $\delta_{\rm IPR}$ explains that DFT does not

DFT slab calculations [3, 5] can compute $\gamma_{\rm Al} \neq \gamma_{\rm Zn}$, but the output is two numbers. The $\delta_{\rm IPR}$ framework translates this numerical difference into a physical statement: *Al has higher surface tension because its sp valence electrons are more delocalized, delivering more charge to the cell boundary.* This is the kind of analytical insight that enables extrapolation, chemical intuition, and connection to other properties—capabilities that pure numerical computation does not provide.

B. Reinterpretation of Miedema's $n_{\rm ws}$

Miedema's $n_{\rm ws}$ is one of the most successful empirical parameters in metallurgy, yet its physical basis has remained obscure. Williams *et al.* [10] demonstrated that

the Miedema physical picture of charge-density equalization is inappropriate, and that n_{ws}'s empirical success instead reflects d-band hybridization trends—but they did not identify a replacement descriptor. We propose that δ_{IPR} fills this gap: n_{ws} is a proxy for electronic delocalization. n_{ws} is high when electrons are delocalized (sp-metals) and low when they are localized (d-metals), because delocalized wavefunctions have more uniform spatial extent, reaching the cell boundary in greater density.

This reinterpretation does not invalidate Miedema—it explains *why* n_{ws} works, answering the question raised by Williams *et al.* over four decades ago. Just as the d-band center model [12] explains why chemisorption energies follow Miedema-like trends, δ_{IPR} explains why surface energies follow n_{ws}.

The 14-metal slab data (Table III) provide a finer-grained picture. Among d metals, Ti (d^2: 0.67) is intermediate between the sp group ($\sim$1.0) and the d^{10} group ($\sim$0.3), while Fe (d^6: 0.37) is already close to d^{10}. This progression—Ti > Fe > Cu > Zn—mirrors Friedel's d-band filling picture [19]: as the d-band fills, it narrows and the d-electrons become more localized, reducing the interstitial density. The sp/d bifurcation in boundary density is thus not a binary distinction but a continuous gradient governed by d-band filling, with d^{10} at the extreme localized end.

We note, however, that δ_{IPR} and n_{ws} measure related but distinct quantities. δ captures how freely valence electrons spread (wavefunction delocalization), while n_{ws} captures how much charge arrives at the cell boundary including indirect contributions from d-electron screening. This distinction explains why the dimer δ–n_{ws} correlation is moderate ($r = 0.33$) despite the strong δ–midpoint-density correlation ($r = 0.89$): midpoint density measures the same physics as δ (wavefunction spread), whereas Miedema's n_{ws} incorporates screening effects that δ does not account for.

C. Connection to optical response

In Paper I [8], we showed that $\delta_{\mathrm{IPR}} \times D_{\mathrm{eff}}$ classifies the optical response of carbon allotropes. The present work connects the *same* δ_{IPR} to surface tension via n_{ws}. Together, these results suggest that electronic delocalization is a unifying variable:

- **Optical response**: $\delta \times D_{\mathrm{eff}} \to \varepsilon(\omega) \to R$
- **Surface tension**: $\delta \to n_{\mathrm{ws}} \to \gamma$

Both chains originate from the same electronic property (δ_{IPR}) but connect to different macroscopic observables through different intermediate quantities. No previous framework has identified a single electronic descriptor that governs both optical and thermodynamic interface properties.

The sp–d hierarchy central to the present work—sp-metal electrons are more delocalized than d-metal electrons—receives independent confirmation from first-principles Wannier function calculations. Comparing silicon (period 3, no d core) and germanium (period 4, $3d^{10}$ core) in the same diamond-cubic structure, the Wannier spread is 25% smaller for germanium (Ω/WF = 2.28 Å^2 vs 3.05 Å^2), directly demonstrating d-electron screening of the sp^3 orbitals. This contraction is the solid-state analogue of the d-block contraction known in atomic physics [20], here quantified for the first time via Wannier spread.

D. Unexplored territory

A systematic literature survey confirms that the connection between IPR (or any delocalization index) and surface tension is, to our knowledge, entirely unexplored:

- The electron localization function (ELF) [21] has been applied to metal surfaces by De Santis and Resta [22], who showed it can distinguish jellium-like from atomic-like bonding at different Al facets. However, they did not compute or correlate ELF values with surface energy. No published work establishes a quantitative ELF–γ relationship for metals.
- The d-band center model [12] predicts chemisorption energies, not surface energies.
- No published work connects inverse participation ratio or Wannier function spread to surface tension of metals. The MLWF spread analysis in this work (Table IV) is, to our knowledge, the first such connection. The Wannier spread Ω [23] provides a rigorous first-principles realisation of δ; combined with the optical sum rule of Cardenas-Castillo *et al.* [24], it establishes a mathematical link between electronic delocalization and optical absorption that underpins both the present surface tension analysis and the optical classification in Paper I.
- Halas *et al.* [11] connected "delocalized electrons" to surface energy, but used an integer electron count (1 or 2) within a free-electron model, not a continuous wavefunction-derived descriptor. Their framework applies only to s-block metals and cannot distinguish metals with similar valence electron counts but different orbital character (e.g., Al vs. Zn).

E. Limitations and future work

1. **Element coverage.** The dimer calculations cover 15 elements and the slab calculations cover 14 metals, including partially filled d-bands (Fe d^6, Ti d^2), closed-shell d^{10} (Cu, Zn, Ga, Ag), and a 4d metal

(Ag). The sp/d separation is statistically significant ($p = 0.00008$). Ni did not converge in the slab calculation (spin-polarized SCF instability) and is left for future work, along with heavy $5d$ metals (Au, Pt, W) requiring relativistic pseudopotentials and f-electron metals (Ce, La). The Wannier calculations remain at five metals and would benefit from extension to the expanded set.

2. δ_{IPR} **is explanatory, not predictive.** The direct correlation between dimer δ_{IPR} and Miedema's n_{ws} is moderate ($r = 0.53$), and the correlation with γ is not significant ($r = 0.08$). δ_{IPR} illuminates the physics behind n_{ws} but does not replace it as a predictor.

3. **Core-electron contamination in dimer δ_{IPR}.** The all-electron δ_{IPR} averages the IPR over *all* occupied Kohn–Sham orbitals, including core states. Since core orbitals are strongly localized, they pull δ_{IPR} toward zero irrespective of valence delocalization. To quantify this effect, we computed a valence-only variant $\delta_{\mathrm{IPR}}^{\mathrm{val}}$ by excluding core states below a per-element energy threshold (Table I). The valence-only version improves the correlation with midpoint density from $r = 0.86$ to $r = 0.89$, confirming that core contamination weakens the signal. The improvement is modest, suggesting that the ranking is already largely correct in the all-electron version, but the valence-only formulation is more physically consistent with the slab analysis. The MLWF spreads (Sec. **??**), being computed from valence bands only, are not affected by this issue and serve as an independent confirmation uncontaminated by core states.

4. **Slab convergence.** Systematic convergence tests of $n_{\mathrm{mid}}/n_{\mathrm{bulk}}$ confirm that the reported values are well converged with respect to plane-wave cutoff: increasing ecutwfc from 30 to 70 Ry (Al) or 40 to 80 Ry (Cu) changes the ratio by less than 0.5% (Table V). Slab thickness shows a modest effect for Al (0.982 at 7 layers $\rightarrow$ 0.969 at 11 layers, a 1.3% decrease) while Cu is essentially unchanged (0.326 $\rightarrow$ 0.327). Crucially, the sp/d separation ratio remains above 3× in all cases, confirming that the qualitative conclusion is robust. The use of different surface orientations (BCC(110), FCC(111), HCP(0001)) may introduce structural effects; a single-facet comparison across elements would deconvolute electronic from packing effects.

5. **ILDOS energy-window sensitivity.** The valence decomposition depends on the energy window used for the integrated local density of states. Sensitivity tests shifting the lower bound by ±2–3 eV show that the results are remarkably robust: Al (0.981), Cu (0.326), and Zn (0.279) are completely insensitive to window choice within ±3 eV, while Na shows a small decrease (1.066 to 1.061) only at the most aggressive shift (+3 eV). This robustness arises because the energy windows are chosen to lie in gaps between distinct band manifolds, so moderate shifts do not cross band edges.

TABLE V. Convergence of valence $n_{\mathrm{mid}}/n_{\mathrm{bulk}}$ with respect to plane-wave cutoff (ecutwfc) and slab thickness for Al(111) and Cu(111).

(a) Ecutwfc convergence (7 layers)

Metal	30/40 Ry	50/60 Ry	70/80 Ry
Al(111)	0.982	0.979	0.981
Cu(111)	0.326	0.327	0.327

(b) Slab thickness convergence

Metal	7 layers	9 layers	11 layers
Al(111)	0.982	0.971	0.969
Cu(111)	0.326	0.327	0.327

6. **Solid-to-liquid transferability.** All calculations are performed on crystalline slabs at 0 K, while the application target is liquid-metal surface tension. The implicit assumption is that the delocalization hierarchy (sp > d) persists through melting, as orbital character is determined primarily by atomic species rather than long-range order. This assumption could be tested via ab initio molecular dynamics simulations of liquid slabs, which would also probe the temperature dependence of $n_{\mathrm{mid}}/n_{\mathrm{bulk}}$.

7. **Non-metallic extension.** Extension to molecular liquids and ionic melts requires different definitions of delocalization but may follow the same conceptual framework.

VI. CONCLUSION

We have proposed the inverse participation ratio of Kohn–Sham orbitals as an electronic-structure descriptor for surface tension of liquid metals. Seven key results support this proposal:

1. δ_{IPR} is mathematically distinct from the normalized density $n/\bar{n}$ (DFT verification, mean $r = 0.10$), establishing it as a genuinely new variable.

2. δ_{IPR} correlates with boundary electron density ($r = 0.84$, $p = 0.001$ for 11 metal dimers), supporting the causal chain $\delta \rightarrow n_{\mathrm{ws}} \rightarrow \gamma$.

3. Periodic DFT slab calculations on five metals confirm the mechanism: *valence* interstitial density separates sp metals (Na: 1.093, K: 1.130, Al: 0.963) from d-metals (Cu: 0.329, Zn: 0.279), with a 3.5× ratio between sp and d averages. All five predictions are confirmed.

4. An ablation study demonstrates that total electron density gives misleading cross-element comparisons (Na = 0.127, appearing similar to d-metals), while valence decomposition recovers the correct trend (Na = 1.093). This establishes that *surface tension is governed by valence electron delocalization, not total electron density.*

5. Maximally localized Wannier function spreads independently confirm the delocalization hierarchy: sp metals ($\bar{\Omega}$: Al = 12.9, Na = 11.7 Å^2) have 6–19× larger average spreads than d-metals (Cu = 1.9, Zn = 0.7 Å^2). This bulk-only measure requires no surface calculation, establishing delocalization as an intrinsic electronic property.

6. The cross-element correlation $r(\delta, \rho_{\text{boundary}})$ is robust across basis sets (def2-SVP: 0.84, TZVP: 0.72, QZVP: 0.82), confirming that element ranking by delocalization is basis-independent.

7. Miedema's boundary density is not a boundary phenomenon—it is a consequence of how uniformly valence electrons are distributed throughout the cell.

Combined with the optical classification reported in Paper I [8], δ_{IPR} emerges as a candidate for a unified electronic-structure variable connecting interface properties across optical and thermodynamic domains. The Wannier spread Ω, which independently confirms the delocalization hierarchy (result 5 above), provides a rigorous first-principles realisation of δ that is applicable to both crystalline solids and disordered systems. A precise definition of δ in terms of Ω, and its extension to liquid systems—where both electronic and nuclear delocalization play a role—will be addressed in Paper III.

What δ_{IPR} provides is not better numbers, but a physical *reason*—the first electronic-structure descriptor proposed for surface tension across sp and d metals.

ACKNOWLEDGMENTS

The initial inspiration for this work arose from observing water droplets thrown in a sauna—each droplet simultaneously exhibiting surface tension (spherical shape) and luster (specular reflection)—and recognizing that both phenomena might share a common microscopic origin.

DATA AND CODE AVAILABILITY

All simulation code (DFT cluster calculations, Miedema comparison, self-criticism tests), parameter tables, and figure-generation scripts are publicly available at `https://github.com/miyauchikazuyoshi/sento-optics`.

USE OF AI-ASSISTED TOOLS

The conceptual framework—the hypothesis that δ_{IPR} explains Miedema's n_{ws}, the causal chain $\delta \to n_{\text{ws}} \to \gamma$, the connection between surface tension and optical response via δ, and the ablation study design (full-electron vs. valence-only)—was conceived entirely by the author. Self-criticism tests falsifying earlier hypotheses (e.g., $\gamma \propto \int (d\delta/dz)^2\, dz$), DFT slab calculations, valence decomposition analysis, and Wannier90 MLWF spread calculations were carried out collaboratively with Claude (Anthropic). Idea review and discussion of alternative framings were assisted by ChatGPT (OpenAI) and Gemini (Google). All scientific claims have been verified by the author.

All validation code and research notes are publicly available at `https://github.com/miyauchikazuyoshi/sento-optics`.

[1] N. D. Lang and W. Kohn, Theory of metal surfaces: Charge density and surface energy, Phys. Rev. B **1**, 4555 (1970).

[2] J. P. Perdew, H. Q. Tran, and E. D. Smith, Stabilized jellium: Structureless pseudopotential model for the cohesive and surface properties of metals, Phys. Rev. B **42**, 11627 (1990).

[3] L. Vitos, A. V. Ruban, H. L. Skriver, and J. Kollár, The surface energy of metals, Surf. Sci. **411**, 186 (1998).

[4] N. E. Singh-Miller and N. Marzari, Surface energies, work functions, and surface relaxations of low-index metallic surfaces from first principles, Phys. Rev. B **80**, 235407 (2009).

[5] R. Tran, Z. Xu, D. W. Rappe, W. Sun, and K. A. Persson, Surface energies of elemental crystals, Sci. Data **3**, 160080 (2016).

[6] A. R. Miedema, Surface energies of solid metals, Z. Metallkd. **69**, 287 (1978).

[7] F. R. de Boer, R. Boom, W. C. M. Mattens, A. R. Miedema, and A. K. Niessen, *Cohesion in Metals: Transition Metal Alloys* (North-Holland, 1988).

[8] K. Miyauchi, Optical classification of solids through electronic delocalization, arXiv preprint (2026), companion paper (Paper I).

[9] N. D. Lang and W. Kohn, Theory of metal surfaces: Work function, Phys. Rev. B **3**, 1215 (1971).

[10] A. R. Williams, C. D. Gelatt, Jr., and V. L. Moruzzi, Microscopic basis of Miedema's empirical theory of transition-metal compound formation, Phys. Rev. Lett. **44**, 429 (1980).

[11] S. Halas, T. Durakiewicz, and J. J. Joyce, Surface energy calculation — metals with 1 and 2 delocalized electrons per atom, Chem. Phys. **278**, 111 (2002).

[12] B. Hammer and J. K. Nørskov, Why gold is the noblest

of all the metals, Nature **376**, 238 (1995).

[13] R. J. Bell and P. Dean, Atomic vibrations in vitreous silica, Discuss. Faraday Soc. **50**, 55 (1970).

[14] F. Wegner, Inverse participation ratio in $2+\varepsilon$ dimensions, Z. Phys. B **36**, 209 (1980).

[15] Q. Sun, T. C. Berkelbach, N. S. Blunt, G. H. Booth, S. Guo, Z. Li, J. Liu, J. D. McClain, E. R. Sayfutyarova, S. Sharma, S. Wouters, and G. K.-L. Chan, PySCF: the Python-based simulations of chemistry framework, WIREs Comput. Mol. Sci. **8**, e1340 (2018).

[16] P. Giannozzi, S. Baroni, N. Bonini, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, G. L. Chiarotti, M. Cococcioni, I. Dabo, *et al.*, QUANTUM ESPRESSO: a modular and open-source software project for quantum simulations of materials, J. Phys.: Condens. Matter **21**, 395502 (2009).

[17] P. Giannozzi, O. Andreussi, T. Brumme, O. Bunau, M. B. Nardelli, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, M. Cococcioni, *et al.*, Advanced capabilities for materials modelling with QUANTUM ESPRESSO, J. Phys.: Condens. Matter **29**, 465901 (2017).

[18] G. Pizzi, V. Vitale, R. Arita, S. Blügel, F. Freimuth, G. Géranton, M. Gibertini, D. Gresch, C. Johnson, T. Koretsune, *et al.*, Wannier90 as a community code: new features and applications, J. Phys.: Condens. Matter **32**, 165902 (2020).

[19] J. Friedel, Transition metals. electronic structure of the d-band. its role in the crystalline and magnetic structures, in *The Physics of Metals*, Vol. 1, edited by J. M. Ziman (Cambridge University Press, 1969) pp. 340–408.

[20] P. Pyykkö, Relativistic effects in structural chemistry, Chem. Rev. **88**, 563 (1988).

[21] A. D. Becke and K. E. Edgecombe, A simple measure of electron localization in atomic and molecular systems, J. Chem. Phys. **92**, 5397 (1990).

[22] L. De Santis and R. Resta, Electron localization at metal surfaces, Surf. Sci. **450**, 126 (2000).

[23] N. Marzari and D. Vanderbilt, Maximally localized generalized Wannier functions for composite energy bands, Phys. Rev. B **56**, 12847 (1997).

[24] L. F. Cardenas-Castillo, S. Zhang, F. L. Freire, Jr., D. Kochan, and W. Chen, Detecting the spread of valence-band Wannier functions by optical sum rules, Phys. Rev. B **110**, 075203 (2024).