


Si RPA correlation energy, $n_{\text{band}} = 500$, identical WFK



post-fix offset varies 0.18 mHa across the sampled range; pre-fix varies 11.5 mHa.
 A CONSTANT offset cancels from the EOS; a volume-dependent one does not — that is why the pre-fix curvature ($B_0 = 45$ GPa vs 98-101 reference) was destroyed while a_0 looked fine.

Lower panel on a symlog axis (linear within ± 10 mHa). Both codes consume the bit-identical 500-band WFK, so E_c is the only difference.
 Caveat: the pre-fix series also used looser thresh/tol, so it is not a pure V_{LL} contrast — but the compression defect it carries is itself volume-dependent, which is the same failure mode.