F-7.8-26/3

Material Testing Laboratory

Plot No.-254, Sector-24, Farldabad-121005 (India) Tel.: +91-129-4061739, Mob.: 9871299112, 9810760405





Page 1 of 1

Test Report

Report No.-

ULR TC573925000011959F Issued to : M/s S.S.B. ENGINEERS PVT, LTD.

Customer

133,M.I.A. ALWAR (RAJ.)-301001

Issue Date

16/04/2025

Job Order No.

12240

Sample Receipt Date :

15/04/2025

Sample Description : ROUND DIA 106mm

H.NO.K24-2129 GR.5690QL

Discipline / Group : CHEMICAL- METALS & ALLOYS

| Reference No. | 12140 |
|------------------|--------------------|
| Date of Analysis | 15-04-2025 |
| Test Method | OES/JIS G1253:2013 |

| Test Results | |
|--------------|--------|
| Element | % |
| Carbon | 0.188 |
| Silicon | 0.297 |
| Manganese | 1,235 |
| Chromium | 1.046 |
| Nickel | 1.788 |
| Molybdenum | 0.327 |
| Vanadium | 0.075 |
| Copper | 0.085 |
| Aluminium | 0.025 |
| Sulphur | 0.003 |
| Phosphorus | 0.016 |
| Boron | 0.0004 |
| Titanium | 0.003 |
| Niobium | 0.002 |
| Nitrogen | 0.0093 |



gnatory (QM/TM)

Notes: 1. Sample not drawn by us. Analysis conducted on "As received basis" unless specified otherwise. Sample will be retained only for 16 days.

2. The results listed refer only to the tested sample and applicable parameters. Endorsement of product is neither inferred nor implied.

3. Measurement uncertainty and associated risks are not taken into account when reporting statement of conformity as agreed by the customer. 4. This report can not be used as an evidence in the court of law, and shall not be reproduced except in full, without the written approval of Laboratory.

5. Total liability of our works is limited to the invoiced amount only

E-mail: bhartiyalab@gmail.com

