

2K-Durapur Hardener 7770

special PUR hardener for 2K-Durapur 7740 and 2K-Durapur 7741



Field of application

To be mixed with 2K-Durapur 7740 and 2K-Durapur 7741.

Properties

Special system hardener. The container sizes reflect the mixing ratio.

Material description

| | |
|----------------------|---|
| Color shade | Colorless |
| Base material | Aliphatic polyisocyanate |
| Flash point | > +61°C |
| Density | Approx. 1.09–1.13 g/cm ³ |
| Packaging | 125 ml of hardener for 625 ml of base material 400 ml of hardener for 2.0 l of base material 1.5 l of hardener for 7.5 l of base material (Base enamel and hardener are supplied separately) |

Use

| | |
|--------------------------------|---|
| Mixing | Before adding the hardener, thoroughly stir until even. Mix the base component and hardener in the specified mixing ratio shortly before application. Ensure that the hardener container is completely emptied without residue. Follow the instructions in 2K-Durapur 7740 and 2K-Durapur 7741 data sheets. |
| Compatibility | Can only be mixed with materials specified in this data sheet. |
| Application temperature | Do not apply at temperatures below +5°C or above a max. of +25°C air, substrate and material temperature. Take the dew point temperature into consideration. Do not apply unless the temperature is at least 3°C above the dew point. |

| | |
|----------------------------|---|
| Use | |
| Tool cleaning | Clean tools with water and wetting agent immediately after use. |
| Storage | |
| | Store in a cool, dry and frost-free place. Reseal opened containers tightly. Turn opened containers upside down (risk of thickening). |
| Declaration | |
| Product code | PU50 Comply with the specifications in the current safety data sheet. |
| Notes | |
| Further information | Follow the instructions on the data sheets of the products used. |
| Remark | |
| | <p>This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.</p> <p>When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.</p> <p>Brillux Weseler Straße 401 48163 Münster GERMANY Phone +49 251 7188-0 Fax +49 251 7188-105 info@brillux.de www.brillux.com</p> |