

Lignodur VarioGuard 618



Efficient alkyd resin woodstain with a natural wood look



Color System

Field of application

For weather-resistant glazing coats on all hardwood and coniferous woods, outdoors. As a one-pot system, it can be used on non-dimensionally stable and partially dimensionally stable wooden components, e.g., overlapping wooden paneling, or tongue and groove wooden paneling (roof soffits), fences, pergolas, garden sheds, timber framework and shutters. Furthermore, it can also be used indoors. On surfaces that are highly exposed to moisture, e.g., on roof soffits which are exposed to condensation, there is a risk of fungal infestation. For such surfaces we recommend using Lignodur VarioGuard 618 in Protect quality (for further Information on this, refer to Notes).

Properties

- Aromatics-free
- Alkyd resin woodstain without biocidal agents
- For indoors and outdoors
- Deeply penetrating
- Matt
- Natural look
- Moisture regulating
- Quick drying
- Drip-inhibited, i.e. easy to apply
- Optionally available for external areas in Protect quality (film protection against an algal and fungal infestation of the coating)

Material description

Color shades	Scale no.	Description
	-	0100 transparent ¹⁾
	09.LA.03	1410 oak
	09.LA.02	1411 pine
	21.LA.03	3410 mahogany
	03.LA.08	7410 pebble
	75.LA.02	7411 graphite
	15.LA.03	8410 nutbrown
	15.LA.02	8411 chestnut
	12.LA.05	8412 teak
	18.LA.04	8415 rosewood
	03.LA.03	9410 ebony
	03.LA.01	9510 chalk white
	¹⁾ May only be used indoors; please refer to the information below Notes. Additional color shades from the Brillux Color System.	
Gloss grade	Matt	
Base material	Special alkyd resin, solvent-based	
VOC	EU limit for this product (Cat. A/e): 400 g/l (2010). This product contains max. 400 g/l VOC.	
Flash point	+62°C	
Density	Approx. 0.85–1.0 g/cm ³ , depending on the color shade.	
Packaging	Standard: 750 ml, 3 l and 10 l Color System: 750 ml, 3 l and 10 l	

Use

Thinning	Ready for application. No thinning, since this would result in the EU limit value in accordance with the VOC Directive being exceeded.
Tinting	All colors can be mixed with one another without limitations.
Application	Stir thoroughly before use. Evenly apply Lignodur VarioGuard 618, e.g., with the Uni-Plus Paint Brush, flat 1182. Alternatively, Lignodur VarioGuard 618 can also be applied without Protect additive using the XVL P spray method. In that case, the surfaces are subsequently to be rolled by brush.
Consumption	Approx. 70 ml/m ² per layer. Determine the exact consumption by means of a test application on the object to be coated.
Application temperature	Do not apply if air or object temperature is below +5°C.
Tool cleaning	Clean tools immediately after use with Thinner AF 631 or Quick-acting Brush Cleaner 111.

Use

Spray data

Spray system	Nozzle	Spray angle	Supply air / air quantity	Material pressure / material quantity	Thinning	Cross-spraying
Low pressure ¹⁾	Yellow front end ²⁾	–	75–100%	Ring setting 5–6	Unthinned	1 ³⁾

Only material without Protect additive may be applied using the spray method.

The data is based on substrate and ambient temperatures of +20°C.

¹⁾ Information relating to XVLP technology with Wagner FinishControl FC 3500 or FC 5000.

²⁾ StandardSpray spray attachment (yellow) for all standard enamel paints and woodstains. Also keep the nozzle clean during application. Remove dry paint material with a soft brush. Please follow the equipment manufacturer's instructions.

³⁾ The areas are to be brushed after spray application to achieve a smooth surface.

Drying (+20°C, 65% relative humidity)

Dry after approx. 7 hours. Recoatable after approx. 24 hours.
Allow for longer drying time if the temperature is lower and/or the humidity is higher.

Storage

Store in a cool and dry location. Reseal opened containers tightly.

Declaration

Product code BSL10
Comply with the specifications in the current safety data sheet.

Coating build-up

Substrate preparation The substrate must be solid, dry, clean, with good adhesiveness, load-bearing and free from separating agents. The BFS Leaflet no. 18 specifies that the moisture content for non-dimensionally stable components and components with limited dimensional stability, the moisture content must not exceed 18%. Remove grayed wood down to the load-bearing wood layers. Hazardous particles and vapors may be released while reworking or removing old paint coats, e.g. as a result of sanding, paint removal by heat gun, etc. Perform such work in well ventilated areas only and ensure the use of appropriate protective equipment (including respiratory protective equipment) as required. Pretreat, prime and/or apply the intermediate coat to the substrate, as required. Also see BFS Leaflet no. 18, 4 and 5, as well as VOB Part C, DIN 18363, Paragraph 3.

Coating build-up

Exterior coats on non-dimensionally stable and limited dimensionally stable wooden components

Substrates	Impregnation ¹⁾	Prime coat	Intermediate coat	Top coat
Untreated wood, outdoors, e.g. tongue and groove paneling (roof soffits), fences, pergolas, garden sheds, timber framework, shutters, etc.	Lignodur Contrabol 550	Lignodur VarioGuard 618	Lignodur VarioGuard 618	Lignodur VarioGuard 618
Wooden components with an intact woodstain coat	Raw wooden surfaces with Lignodur Contrabol 550	If necessary, repair damaged areas with Lignodur VarioGuard 618		

¹⁾ Follow the instructions in BFS Leaflet No. 18, Sections 6 and 7.2.1.

Interior coats on wood

Substrates	Prime coat	Intermediate coat	Top coat
Untreated wooden components and wood-based materials, indoors	Lignodur VarioGuard 618	If necessary, Lignodur VarioGuard 618	Lignodur VarioGuard 618
Wooden components and wood-based materials with intact woodstain coating, indoors	If necessary, repair damaged areas with Lignodur VarioGuard 618		

Notes

Sand the substrates Sand the surfaces between work steps.

Check old coatings Check old woodstain coatings for adhesion, for example by scratching the substrate or applying then removing sticky tape. Applying a wet cloth to the surface additionally clarifies whether the coating and/or the wood is suitable for coating build-up. If a dark, damp spot appears on this part of the wood after a brief period, then the surface needs to be sanded back to the load-bearing wooden layer.

Assess woodstain color shade The various kinds of wood and existing, intact woodstain coatings affect the woodstain color shade due to intrinsic color and absorbency. For this reason, we recommend applying a test coat in advance.

Do not use colorless build-up outdoors Colorless woodstain coats are not suitable as a sole coating build-up for use in exterior areas due to their insufficient UV protection.

Shelf life of woodstain coating The shelf life of a woodstain coating depends on countless factors, e.g., the construction and the general impregnation and priming of the (specified) components. To maintain the woodstain coating, we recommend performing checks at regular intervals, but after 2–3 years at the latest, and if necessary, maintenance of the woodstain coating is to be performed, especially in areas exposed to weathering.

Indoor application	Odor and yellowing are typical material features of alkyd resin paints. For large-scale applications indoors (e.g. on ceilings and walls) and for white and light color shades, we recommend using the water-based woodstain Lignodur Grenodecor 236.
Initial gloss	With the current state-of-the-art technical development, the initial gloss is reduced after a couple of days as a result of the curing process.
Cleaning and maintenance	For cleaning the painted surfaces, use a clean, soft cloth, dry or damp, without abrasive, solvent-based or caustic agents. Clean without applying excessive pressure (do not polish the surfaces). Perform a test cleaning beforehand in an inconspicuous area. Only clean surfaces that have completely dried and cured.
Wood-based panels for outdoors	In accordance with the current state of the art, wood-based panels are only conditionally suited for coating in exterior areas. Also refer to BFS Leaflet No. 18, Paragraph 2.2.3. A coating recommendation can only be provided on a case-by-case basis under consideration of the material type and quality, construction, and climatic conditions. Please contact the Brillux Consulting Service if you require assistance in this context.
Protect quality	The material quality marked with Protect is provided with a film preservation against fungal infestation and should therefore only be used outdoors and only applied by brush. The preservatives used minimize and/or delay the risk of fungal infestation. We recommend applying at least two coats. With the current state of the art technical development, a permanent protection against fungal infestation cannot be guaranteed.
Further information	Follow the instructions in the data sheets of the products used.

Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com