

2K-Aqua Hardener 2380

Special hardener for 2K-Aqua Silk Matt Enamel 2388, 2K-Aqua Matt Enamel 2390, 2K-Aqua Durakett 2394 and 2K-Aqua Whiteboard 2384



Field of application

For mixing with 2K-Aqua Silk Matt Enamel 2388, 2K-Aqua Matt Enamel 2390, 2K-Aqua Durakett 2394 and 2K-Aqua Whiteboard 2384.

Properties

Special system hardener. The container sizes reflect the mixing ratio.

Material description

Color shade	Colorless
Base material	Aliphatic polyisocyanate
Flash point	> +61°C
Density	Approx. 1.09–1.13 g/cm ³
Packaging	125 ml of hardener for 875 ml or 625 ml of base material 500 ml of hardener for 3.5 liters or 2.5 liters of base material (Base enamel and hardener are supplied separately)

Use

Mixing	Before adding the hardener, thoroughly stir the 2K-Aqua Silk Matt Enamel 2388, 2K-Aqua Matt Enamel 2390, 2K-Aqua Durakett 2394 or 2K-Aqua Whiteboard 2384 until even. Mix the base component and hardener in the specified mixing ratio shortly before application. Ensure that the hardener container is completely emptied without residue. Follow the instructions on the 2K-Aqua Silk Matt Enamel 2388, 2K-Aqua Matt Enamel 2390, 2K-Aqua Durakett 2394 or 2K-Aqua Whiteboard 2384 data sheets.
Compatibility	Can only be mixed with materials specified in this data sheet.
Application temperature	Do not apply at temperatures below +8°C or above a max. of +25°C air, substrate and material temperature. Take the dew point temperature into consideration. Do not apply unless the temperature is at least 3°C above the dew point.

Use	
Tool cleaning	Clean tools with water and wetting agent immediately after use.
Storage	
	Store in a cool, dry and frost-free place. Reseal opened containers tightly.
Declaration	
Product code	PU50 Comply with the specifications in the current safety data sheet.
Notes	
Further information	Follow the instructions in the data sheets of the products used.
Remark	
	<p>This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.</p> <p>When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.</p> <p>Brillux Weseler Straße 401 48163 Münster GERMANY Phone +49 251 7188-0 Fax +49 251 7188-105 info@brillux.de www.brillux.com</p>