

Profisil 1906

Silicate interior paint, low-emission, solvent- and plasticizer-free, dull matt, wet abrasion resistance Class 2, AgBB certified, suitable for allergy sufferers, for interior use



Farbsystem

Field of application

For high-quality ceiling and wall coats, e.g. interior plaster, concrete and sand-lime brickwork. Particularly suited for silicifying mineral substrates. The complete coating build-up has also been tested in combination with Brillux woodchip wallpaper and is suitable for allergy sufferers.

Properties

- Low-emission solvent- and plasticizer-free
- Complies with the requirements of the Committee for the Health-related Evaluation of Building Products (AgBB)
- White suitable for allergy sufferers (TÜV tested)
- White preservative-free
- Free of fogging-active substances
- Silicate dispersion paint in accordance with DIN 18363
- Highly diffusible, corresponds to Class I in accordance with DIN EN ISO 7783
- Low odor
- Can be processed in airless spray application
- Bonds to the substrate by silification

Material description

Standard color shade	0095 white A number of additional color shades can be mixed with the Brillux Color System. Color shades from the Brillux Color System have not been tested to ensure their suitability for allergy sufferers. Tint color shades suitable for allergy sufferers with Vitamix 9018.
Base material	Potassium water glass with organic stabilizers
Organic content	< 5% in accordance with DIN 18363, 2.4.1.1
Density	approx. 1.5 g/cm ³
Ph value	approx. 11

Material description

Classified according to EN 13300

- Wet abrasion resistance: Class 2
- Contrast ratio (white): Class 1 at 7 m²/l
- Gloss: dull matt
- Maximum grain size: fine

Reaction to fire

A2 – s1,d0 in accordance with DIN EN 13501-1 (“nichtbrennbar”, non-combustible), in accordance with classification report no. 230011570-3
In system build-up with Briplast filler material according to classification report no. 230010838-3.

Water vapor permeability

Diffusion-equivalent air layer thickness: S_d (H₂O) < 0.03 m, in accordance with DIN EN ISO 7783, corresponds to Class V₁ “highly water-vapor-permeable” in accordance with DIN EN 1062-1

Water vapor diffusion current density

$P \geq 2000 \text{ g/m}^2\text{d}$

Packaging

0095 white: 2.5 l, 5 l, 10 l, 15 l
Color system: 2.5 l, 5 l, 15 l

Use

Dilution

Where necessary, with a mixture of Fondosil 1903 and water (mixing ratio 1:1).

Tinting

Tintable up to max. 25 % with Vitamix 9018. Note that the color shades dry lighter.

Compatibility

Can only be mixed with similar materials and those specified in this data sheet.

Application

Before use, stir thoroughly with an electric stirrer. Profisil 1906 can be applied by using a brush, roller and airless spray application.

Consumption

Approx. 130-150 ml/m² per layer.
Determine the exact consumption by means of a test application on the object to be coated.

Application temperature

Do not apply at an air and object temperature below +8 °C.

Cleaning tools

Clean tools immediately after use with water.

Spray data

Spray system	Nozzle	Spraying angle	Pressure	Dilution
High-performance airless system	0.021–0.027 inch	40°–80°	depending on the spraying device and individual requirements	5-15 %

Drying (+20 °C, 65% relative humidity)

Surface-dry and can be processed after approx. 4 -6 hours. Final silification after several days. Allow longer drying times at lower temperatures and/or higher air humidity.

Storage

Store in a cool and frost-free place. Reseal opened containers tightly.

Declaration

Note Do not inhale spray mist.

Product code BSW10
Comply with the specifications in the current Safety Data Sheet.

Coating build-up

Substrate pretreatment The substrate must be solid, dry, clean, load-bearing, and free from efflorescence, sinter layers, separating agents, corrosion-promoting, or other intermediate layers affecting the adhesion. Check existing coatings for their suitability, load-bearing capacity, and adhesive properties. Thoroughly remove defective and unsuitable coatings and dispose of them in accordance with the applicable regulations. Thoroughly wash off limepaint. Treat replastered areas with a fluorine primer, over the entire area for colored coatings. Apply a prime and/or intermediate coat to the substrate as required. Also see VOB Part C, DIN 18363, Section 3.

First and renovation coats

Substrates	Prime coat	Intermediate coat ³⁾	Top coat
Normally absorbent substrates, e.g. interior plaster (compressive strength category CS I–CS IV) ¹⁾ ,		Profisil 1906, thinned where necessary	Profisil 1906
Brillux woodchip wallpaper 31, 51 and 71			
Intact, matt emulsion paint coats			
Highly absorbent substrates, e.g. interior plaster (compressive strength category CS I–CS IV) ¹⁾ ,concrete, sand-lime brickwork, intact silicate paint coats	1–2x wet in moist Fondosil 1903 and water in mixing ratio 1:1		
Intact, gloss emulsion color coatings	Adhesion Primer ELF 3720	Depending on the individual requirements, Profisil 1906, thinned as required	
Gypsum plaster compressive strength category B1–B7), gypsum plasterboard, gypsum wallboard	Wall Primer ELF 3729 or Wall Primer coarse ELF 3728 ²⁾		

¹⁾ Minimum compressive strength > 1,5 N/mm²

²⁾ Prime soft and highly absorbent filler zones and substrates with Lacryl Deep Penetrating Primer ELF 595 as part of the substrate preparation.

³⁾ If filling or texturing properties are required, use Silicate Brush-On Filler ELF 3639 or Klimasil 1908 as an intermediate coat.

Mask surfaces	Mask the surroundings of the surfaces that are to be coated carefully, especially glass, brick and natural stone.
Cracks and flawed areas	Fill cracks and indentations flush with surface after priming with a fillable mixture of silicate paint and quartz sand. Re-prime filled areas. Re-plaster larger flawed areas in the substrate.
Smoothering rough surfaces	Smooth rough surfaces before the coating build-up by filling them with, e.g. Briplast Mineral Hand Applying Light Filler ELF 1886, as required.
Reaction with the substrate	For renovation coats on watery coatings, allergenic substances present in the substrate may be activated due to the moisture impact in rare cases. We therefore recommend applying a test coat to check whether such reactions occur.
Coating on gypsum plasters	For gypsum plasters with high absorbency, an adequate stabilization is not always achieved. We recommend checking the adhesion of the complete coating build-up with an adhesive tape test (e.g. Tesa Precision Masking Tape, gold 4334) to ensure a reliable assessment. Deep penetrating primer should be used where necessary.
Discolorations of gypsum plasterboard	An additional sealing coating should be applied if there is a risk of discolorations penetrating through the untreated gypsum plasterboard. Use e.g. Isolating Primer 924 for this depending on the situation on site. For an accurate assessment, sample coatings of various panel widths, including the joints and filled areas, have proven to be useful.
Gypsum fillers on gypsum plasterboard	The gypsum fillers recommended by gypsum plasterboard manufacturers can be particularly susceptible to moisture, which can result in swelling, bubble formation, and flaking (see also Data Sheet 2 "Filling of gypsum plasterboards, surface qualities" Trade Association of the German Gypsum Plasterboard and Wallboard Industry). It is therefore important to ensure adequate ventilation and appropriate temperatures for rapid drying.
Compatibility with sealing compound	When coating sealing compounds, e.g. acrylic sealing compounds, cracks may occur in the coating material due to the higher elasticity. Discolorations may also occur in the coating. Due to the wide range of sealing compounds available on the market, self-tests must be carried out to assess the adhesion and the processing result in each individual case.
Repairs	Repairs to the surface become more or less strongly apparent depending on the situation on the site. According to BFS Leaflet No. 25, Item 4.2.2.1, Section e, this is unavoidable.
Surface irregularities after drying	Due to the chemical curing process, different discolorations and surface irregularities may occur in unfavorable object parameters, combined with e.g. uneven substrate absorbency, differences in substrate humidity and alkalinity or ingredients in the substrate. This does not constitute a technical-functional defect and does not justify complaint.

Notes

Use in incidence of grazing light

On smooth surfaces with special lighting conditions (grazing light), we recommend using Kalisil 1909 or alternative special interior emulsion paints, such as Glemalux ELF 1000, Superlux ELF 3000 or Vitasense 9005 – preservative-free.

Reducing the surface sensitivity with intense color shades

To increase the strength of the surface and to reduce the “writing effect” on matt coats with intense color shades, we recommend carrying out the coating build-up with Vetrolux ELF 3100. Further information on the properties and application is available in the Data Sheet Vetrolux ELF 3100.

Further information

Follow the instructions on the data sheets of the products used.

Remark

This Data Sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this Data Sheet with updated information is published, the previous version no longer applies. The current version is available on our website. Version I

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com