



**Table 1.18.b.: GRC/ GRFC and GRP Panels on Fire Resistance rated and Non-Load bearing Exterior wall coverings-Test Requirements**

OCCUPANCY AND TYPE OF BUILDING	TEST 1 GRC/ GRFC/ GRP AS PRODUCT	TEST 2 GRC/ GRFC/ GRP AS WALL ASSEMBLY
<b>1. ANY BUILDING</b>  <b>2. ANY INSTALLATION</b>  <b>3. ANY AESTHETICS</b>	i. EN 13501-1 With pass criteria A OR A2-s1-d0  WITH  ii. EN 13823  AND  iii. EN ISO 11925  AND  iv. ASTM D1929 Shall have self ignition temperature of not less than 343°C.  OR  v. ASTM D3841 for GRP only with category CC1	vi. ASTM E 119 With pass criteria "1 Hr or 2 Hr or 3 Hr as per required fire ratings of the wall.  OR  vii. UL 263 With pass criteria "1 Hr or 2 Hr or 3 Hr as per required fire ratings of the wall.  OR  viii. EN 1362-3 With pass criteria "1 Hr or 2 Hr or 3 Hr as per required fire ratings of the wall.  OR  ix. EN 1362-4 With pass criteria "1 Hr or 2 Hr or 3 Hr as per required fire ratings of the wall.