

ACCORDING TO BS EN 771-3:2003 (BS EN 772-1:2011)

BLOCK SIZE: 400*100*200

BLOCK AGE IN DAYS:

CASTING DATE:

MACHINE TYPE:

TESTING DATE:

SAMPLE TYPE: CUBER

SP. Strength (N/mm²): 3.5

METHOD OF CONDITIONING: WATER at 20±5 C

Factory: HIDD

METHOD OF PREPARATION: GRINDING Shape factor

BLOCK TYPE: 4" Hollow Plain Block

Remarks:

No	Length (mm)	Width (mm)	Height (mm)	Load (KN)	Water (N/mm ²)	Air Dry (N/mm ²)	Normalized (N/mm ²)	Density (Kg/m ³)	Wet Weight (Kg)
1	400	100	200	109.1	2.73	3.27	4.42	466.25	3.730
AVERAGE:					2.73	3.27	4.42	466.25	3.730

NOT PASS

Maximum	Minimum	Stan.Dev.
Dry Air Strength	Dry Air Strength	Dry Air Strength
3.27	3.27	