
Capsular Contracture
51.1%
20.1%
Failure of Implant
23.5%
46.3%
Deformity/ Disfigurement
14.5%
25.3%
Seroma
4.1%
1.5%
Breast Discomfort/Pain
2.3%
1.9%
Rupture
1.9%
0.0%
Swollen Lymph Nodes/Glands
1.4%
0.5%
Granuloma
1.3%
0.2%
Unspecified Infection
1.0%
0.6%
Wrinkling
0.8%
0.6%
Silicone (n = 61,672 reports)
Saline (n = 18,309 reports)
0%
10%
20%
30%
40%
50%
Share of reports in each implant group (95% CI)