MOLD SETUP SHEET — Cap, 38mm

Customer:	Acme Plastics Inc.
Mold Number:	M-2231
Part Number:	88-1042-A
Part Wt. (g):	12.4
Shot Weight:	52.8 g
Resin Type:	Polypropylene
Material Color:	Natural
Colorant:	Clariant Blue 5501
Let-down Ratio:	3%
Cavities:	4

Press / Tonnage:	Press 7 / 150 ton
Cycle Time:	18.5 sec
Regrind %:	15
Dryer Temp:	180 °F
Dryer Time:	2 hrs
Nozzle Temp:	430 °F
Barrel Temps:	420 / 410 / 400 °F
Mold Temp:	110 °F
Injection Pressure:	1250 psi
Hold Time:	4.5 sec
Cooling Time:	12 sec

Notes: Check gate vestige every 2 hours.