TECHNICAL DATA

QJ quartz surface specifications

Slab sizes

Standard	12 / 20 / 30 mm	3200 x 1600 mm
Customised	20 / 30 mm	Cut to designated size

Test results

Abrasion resistance (weight loss)	ASTM D 4060	1064 mg
Izod impact strength	ASTM D 256 (Method A)	13.3 J/m
Boiling water resistance	NEMA LD3 2000 3.5	No effect
Colorfastness	ANSI Z124.6.5.1	Pass
Compression strength (dry)	ASTM C 170	209 MPa
Compression strength (wet)	ASTM C 170	203 MPa
Density	KSF 2530	2.3–2.4 g/cm³
Deflection temperature under load (1.82 MPa)	ASTM D 648	243 °C
Flammability: flame spread	ASTM E 84, NFPA 255	Class A
Flammability: smoke developed	ASTM E 84, NFPA 255	Class A
Flexural modulus	ASTM D 790	39.7 GPa
Flexural strength	ASTM D 790	42.4 MPa
Freeze and thaw cycling	ASTM C 1026	Unaffected
Fungal and bacterial resistance	ASTM G 21	No growth
Barcol hardness	ASTM D 2583	86
Rockwell hardness (HRM)	ASTM D 785 (Procedure A)	115
Point impact	ANSI Z124.6.4.2.1	Pass
Static coefficient of friction (dry)	ASTM C 1028	0.67
Static coefficient of friction (wet)	ASTM C 1028	0.49
Stain resistance	ANSI Z124.6.5.2	Pass
Tensile strength	ASTM D 638	17.8 MPa
Thermal expansion	ASTM D 696	1.52 × 10-5 in/in/°C
Water absorption (24 hr immersion)	ASTM D 570	<0.011%
Wear and cleanability	ANSI Z124.6.5.3	Pass