

Mix	Mix ID	7-day strength (MPa)	28-day strength (MPa)
1	0.5 h, RCF 10%, SS 38.24%, A/B 0.450	12.30 ± 0.85	20.41 ± 0.17
2	1 h, RCF 50%, SS 74.98%, A/B 0.476	12.59 ± 1.03	18.21 ± 2.29
3	5 h, RCF 10%, SS 0%, A/B 0.467	3.19 ± 0.16	9.92 ± 1.10
4	1 h, RCF 16.8%, SS 75.00%, A/B 0.420	11.20 ± 0.47	26.54 ± 2.61
5	NC, RCF 10%, SS 67.53%, A/B 0.434	19.23 ± 0.29	21.24 ± 3.38
6	5 h, RCF 36.6%, SS 49.88%, A/B 0.442	15.61 ± 1.05	16.97 ± 1.19
7	NC, RCF 18.2%, SS 16.38%, A/B 0.419	8.34 ± 2.28	35.46 ± 3.23
8	1 h, RCF 27.8%, SS 32.39%, A/B 0.479	13.60 ± 2.28	18.68 ± 2.26
9	NC, RCF 43.95%, SS 0%, A/B 0.442	3.86 ± 0.04	11.38 ± 0.96
10	0.5 h, RCF 30%, SS 0%, A/B 0.450	4.67 ± 0.12	16.22 ± 2.65
11	1 h, RCF 50%, SS 59.59%, A/B 0.420	16.31 ± 3.03	26.53 (n=1)
12	0.5 h, RCF 10%, SS 37.95%, A/B 0.448	16.20 ± 2.60	17.38 ± 2.58
13	NC, RCF 19%, SS 74.81%, A/B 0.468	14.17 ± 0.20	22.55 ± 2.94
14	0.5 h, RCF 30%, SS 0%, A/B 0.450	6.69 ± 0.21	26.22 ± 0.29
15	1 h, RCF 50%, SS 12.42%, A/B 0.420	9.84 ± 1.06	16.63 ± 2.98
16	NC, RCF 10%, SS 0%, A/B 0.480	3.13 ± 0.17	9.63 ± 3.30
17	5 h, RCF 36.6%, SS 49.88%, A/B 0.442	16.91 ± 2.57	19.38 ± 0.95
18	NC, RCF 50%, SS 16.88%, A/B 0.471	8.63 ± 0.40	17.52 ± 3.18
19	0.5 h, RCF 10%, SS 38.23%, A/B 0.450	10.04 ± 0.61	23.17 ± 3.69
20	NC, RCF 48.55%, SS 72.00%, A/B 0.428	16.54 ± 0.49	27.52 ± 2.86
21	5 h, RCF 10%, SS 0%, A/B 0.420	4.00 ± 0.08	13.83 ± 2.69
22	5 h, RCF 50%, SS 0%, A/B 0.480	8.86 ± 0.40	13.88 ± 1.56
23	1 h, RCF 27.8%, SS 32.63%, A/B 0.480	12.82 ± 0.94	24.91 ± 2.30

Mix	Mix ID	7-day strength (MPa)	28-day strength (MPa)
24	5 h, RCF 42.805%, SS 0%, A/B 0.440	8.02 ± 0.53	21.90 ± 1.57
25	NC, RCF 44%, SS 63.75%, A/B 0.466	22.20 ± 6.53	40.55 ± 6.36
26	1 h, RCF 25.4%, SS 29.51%, A/B 0.420	12.96 ± 0.08	26.93 ± 3.12
27	5 h, RCF 10%, SS 75.00%, A/B 0.480	10.57 ± 0.13	15.19 ± 3.15
28	5 h, RCF 36.6%, SS 49.83%, A/B 0.442	20.83 ± 1.49	22.75 ± 2.12
29	1 h, RCF 10%, SS 0%, A/B 0.450	3.08 (n=1)	7.64 (n=1)
30	1 h, RCF 50%, SS 0%, A/B 0.450	5.83 ± 0.44	14.00 (n=1)