

UPM Raflatac Technical Information

25-11-2024 EN SI

Adhesive	RP31 PURUS
Sales Code	R31P
Type	Permanent
Composition	Waterborne acrylic
Use	Designed to meet the labeling requirements of the pharmaceutical industry for low leachable characteristics.

Typical technical values

Tack	12	N	FTM 9
Labelling temperature min	10	°C	
Service temperature min	-40	°C	
Service temperature max	121	°C	

Additional info Stiffness of the face material, die-cutting direction, storage conditions and the container diameter can influence to edge-lifting. Note that heavy ink coverage and overlamination increase the stiffness of the face material. RP31 Purus retains its adhesion in steam autoclave, e-beam, gamma irradiation and EtO. Neither natural rubber latex nor ruminant animal-derived materials are used in the manufacture of RP31 Purus. The Pharmagloss / RP31 Purus laminate is evaluated < 1 in a Sensory Analysis for Indirect Transition of Taste according to EN 1230-2 (Robinson test). Pharmaceutical change management with 12 months' notice of any change. In combination with the 2-year shelf life from date of manufacture, this gives a 3-year window for any requalification requirements.

Approvals Accredited laboratory has approved RP31 Purus according to European requirements for direct contact with dry and moist, non-fatty foodstuffs with the exception of milk and dairy products; according to FDA regulations this adhesive may come into direct contact with dry foodstuffs or it must be separated from foodstuffs by a functional barrier. RP31 Purus is approved from the patient safety point of view (migration tested) for labelling of blood bags. The laboratory has EN ISO 17025 accreditation for analytics and ISO 17065 for certification.

Regulatory info This adhesive is in compliance with the demands of the Code of Federal Regulations, Food and Drug Administration (FDA), 21 CFR Ch. I (April 1, 2018 edition) 175.105. The FDA has assigned Drug Master file (DMF) number 25392, type III for RP31 Purus.

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.