



MultiSeal CWP 2K

Two Component, Flexible, Cementitious, Waterproof Coating

Description:

MultiSeal CWP 2K is a two component, cementitious coating comprising of pre-weighed polymer modified powder & liquid components that when mixed together provide an elastomeric, waterproof coating with exceptional crack bridging capabilities. MultiSeal CWP 2K provides a durable, flexible coating with excellent adhesion characteristics and is non toxic making it suitable for use in contact with potable water.

Uses:

MultiSeal CWP 2K is typically used to waterproof concrete in internal or external applications as potable & storm water tanks, reservoirs, swimming pools and wet areas to kitchens, showers & bathrooms below screed & tile finishes.

Surface Preparation:

Long term durability and function can only be achieved with good preparation to give a strong adhesive & mechanical bond to the substrate. New concrete should be fully cured with a maximum residual relative humidity (RH) of 75%. Prepare concrete surfaces preferably by mechanical methods such as angle grinding to remove laitance, curing compounds and other loose materials to provide a mechanical key for MultiSeal CWP 2K. Thoroughly soak concrete substrates with cleanwater for at least 1 - 2 hours, removing standing and excess water prior to the application of MultiSeal CWP 2K.

Priming:

Priming is not normally required however please ensure the substrate is pre-soaked, clean, sound and free from contamination.

Mixing:

It is essential that the mixing instructions are carefully followed to ensure the correct characteristics of the product are achieved. Failure to do so can result in lower performance or even possible failure of the product. Place the liquid component in a suitable empty container with sufficient volume to accommodate the mixed material. Slowly add the powder to the liquid component and mix continuously for 4 - 5 minutes using a slow speed drill and paddle or forced action mixer, until a homogenous consistency is achieved. Leave the mixed material to stand in the container for several minutes prior to application. No additional water should be used as this will change the performance of the mixed material.

Technical Data

Properties	Test Standards	Typical Values
Appearance		
Part A		: grey or white powder
Part B		: white-milky liquid
Particle size (Part A)		: 0.1 - 0.5 mm
Bulk Density (Part B)		: 1.3 ± 0.1
pH (Part B)		: 7
Pot life		: 30 minutes at 20°C
Recoat time		: 4 - 24 hours
Colours		: grey or white
Pull off strength test @ 7 days @ 28 days	BS 1881 Part 207-1992	: 0.6 N/mm ² : 1 N/mm ²
Crack bridging ability @ 28 days	ASTM C 836:95	: > 1.5 mm
Elongation test @ 28 days	ASTM D 412:98	: 60%
Water permeability @ 28 days resistance to water penetration	BS EN 12390 part 8:2000	: 100%
Non toxicity, @ 28 days	BS 6920:2000	Passed

Application Method :

A minimum of 2 coats of MultiSeal CWP 2K are recommended. Apply the first coat of MultiSeal CWP 2K using brushes or rollers to a theoretical coverage rate of 1 – 1.5 kg per m², in a continuous uniform coating. For high risk applications, we recommend a fabric scrim be embedded into the wet first coat, particularly at floor / wall junctions and joints in concrete substrates, to reinforce the coating. Do not pre-soak between coats, simply apply the second coat of MultiSeal CWP 2K in opposite directions but in the same manner and coverage rate as the first, allowing 4 - 8 hours drying time between coats. Expansion joints must be reflected through the MultiSeal CWP 2K and subsequent floor finishes, and preferably sealed with a sealant from the Multiseal range. MultiSeal CWP 2K will be compatible with most cementitious floor screeds or tile adhesives, however we recommend a trial area is done to confirm compatibility.





MultiSeal CWP 2K Two Component, Flexible, Cementitious, Waterproof Coating

Curing:

Allow MultiSeal CWP 2K to cure fully for 4 - 7 days before screeding, tiling or exposing to full environmental conditions.

Cleaning :

Clean tools and equipment immediately after use with Multicleaner.

Storage :

For application above 40°C we recommend adopting the following guidelines:

Store unmixed materials in a cool preferably air conditioned environment.

Avoid exposure of mixed & unmixed materials to direct sunlight.

Keep equipment that will be in contact with the product cool and away from direct sunlight.

Avoid application during the hottest time of day.

Packaging:

MultiSeal CWP 2K pack size: 20 kg kit. Coverage rate approximately 2 - 3 kg per m² in two coats.

Shelf Life :

MultiSeal CWP 2K has a maximum shelf life of 12 months from the date of manufacture. To maximize shelf life always store products in their original, unopened packaging in a dry environment, away from direct sunlight with a minimum temperature of 10°C but not exceeding 35°C. Damaged packaging, high humidity or extreme temperatures may reduce the shelf life.

Limitations:

Substrate temperatures should be above 5°C and rising. For application in temperatures above 40°C please refer to hot weather condition recommendations. Avoid application if the work area may be subject to the onset of rain or moving water. Do not part mix under any circumstances. All products should be used within the pot life. Materials not used within the specified time should be discarded. If the above general application details do not meet with your requirements, please contact Multitech Chemicals for a project specific method statement.

Disclaimer:

The information supplied in our literature or given by our employees is based upon extensive experience and together with that supplied by our agents or distributors, is given in good faith in order to help our customers. Our company policy is one of continuous research and development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products. However, as we have no control over site conditions or the execution of the work. We accept no liability for any loss or damage which may arise as a result thereof.

Health & Safety:

Always use appropriate PPE including gloves, goggles and a barrier cream to avoid contact with skin and eyes. Should contact with skin or eyes occur, wash immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately. Do not induce vomiting. Avoid inhalation and ensure adequate ventilation or suitable respiratory equipment if working in confined spaces. Do not expose products to fire or naked flames under any circumstances.

