Outdoor Sand Grey

Polyester, TGIC or TGIC-free · RAL 7035

RAL 7035 · Light grey

Product	Code • series	Colour reference	Document
Outdoor Sand Grey 户外砂纹灰	BL-A201 BL-A Architectural Polyester	RAL 7035 · Light grey	TDS BL-A201 Rev. 2026-10

P1000 · tested to AAMA 2603 / QUALICOAT I test items on request — no product certificate held

1. Description

The workhorse exterior texture. It hides weld dressing, grinding marks and small dents, which is why window and enclosure plants use it to cut sanding and rework. TGIC and TGIC-free routes are both available; quote the TGIC-free route for EU tenders and for customers who ask about the label.

2. Typical properties

Property	Value	Method
Chemistry	Polyester, TGIC or TGIC-free	—
Colour reference	RAL 7035 Light grey — approval on a sprayed panel against a physical chip	RAL
Finish and gloss	Sand, 5–12 @60°	ASTM D523
Film build	60–80 µm	ISO 2808
Density	1.50–1.58 g/cm³	ISO 8130-2/3
Coverage	9.3 m²/kg at 100 % film · 8.8 m²/kg planning value at 95 % utilisation (with reclaim)	calculated
Cure schedule	200 °C × 10 min (object temperature)	object temp., not oven set point
Particle size D50	30–45 µm	ISO 8130-1 / -13
Stoving loss	≤ 1–2 %	ISO 8130-7
Storage stability	1 month at 35–40 °C	ISO 8130-8

3. Performance data

Test	Method	Typical result
1. Adhesion, cross-cut	ISO 2409 / ASTM D3359	0–1 (100/100 on aluminium with a conversion coating)
2. Impact, direct and reverse	ASTM D2794	50 kg·cm, no cracking
3. Pencil hardness	ASTM D3363	H (2H typical)
4. Gloss 60°	ASTM D523	Sand texture, 5–12
5. Colour difference	ASTM D2244	ΔE ≤ 1.5 same batch
6. Neutral salt spray	ASTM B117 / ISO 9227	1,000 h (conversion-coated aluminium, 70–80 µm)
7. QUV-A	ASTM G154	1,000 h, gloss retention ≥ 50 %
8. Chemical resistance	ASTM D1308	Per application — detergents and cleaners included

Measured to the method listed, on production batches or the third-party report held for this system. Not a certificate: acceptance values are fixed in the trial report and the purchase specification.

4. Application and cure

01 Aluminium pre-treatment

Degrease → etch → rinse → chromium-free conversion coating → DI rinse → dry. The conversion coating is what the 1,000 h salt-spray figure is built on.

02 Steel pre-treatment

Degrease → zinc phosphate → rinse → DI rinse → dry.

03 Application

Corona 60–90 kV, gun-to-part 150–250 mm, 60–80 µm. Texture is set by film build and cure: below 50 µm the substrate reads through, above 100 µm the texture flattens out.

04 Cure

Object temperature 200 °C for 10 min. TGIC-free has the narrower window — overbake dulls the texture before it changes the colour.

05 Reclaim

Recovered overspray can be blended back at up to 20–25 % without a texture shift. Sieve before reuse.

5. Packaging, storage and ordering

1. Standard pack: 20 kg net, polyethylene-lined carton. Other pack sizes on request.
2. Store below 30 °C, dry, out of direct sunlight, in the unopened pack. Keep away from ovens and hot lines.
3. Shelf life: 12 months from the production date in the original pack. Storage stability is verified at 35–40 °C for one month (ISO 8130-8).
4. A batch test report accompanies every delivery; a retained sample is kept for 12 months.
5. Sample in 3 days; production lead time confirmed per colour and pack size at order.
6. Colour match ΔE ≤ 1.5 within a batch. Cross-batch tolerance is agreed in the purchase specification.
7. Ask for: SDS · third-party test report · batch test report · physical colour chip.

6. Health and safety

1. Not classified as dangerous goods for transport. The SDS is available for every product — ask for it with the TDS.
2. The powder is a combustible dust. Earth the workpiece, the gun and the booth; no open flame or hot work in the booth; extract booth air; avoid dust clouds when emptying or cleaning.
3. Wear a P2 particulate mask, goggles and gloves when handling dry powder or cleaning the booth.
4. Cure volatiles: extract the oven and let parts cool before handling. Do not enter the oven zone without ventilation.

7. Also in this range

Code	Product	Colour	Film build	Cure
BL-A202	Super Durable Champagne	RAL 1015	70–90 µm	200 °C × 12–15 min

8. Document control

Sheet	Revision	Issued	Supersedes	Languages
BL-A201 TDS	2026-10	2026-10	None — first issue	English + 中文 (4 pp.)

9. Limits of this document

What this product is not for:

— Texture is not a colour-matching tool: two batches sprayed at different film builds look different in raking light.

— P1000 is not the coastal curtain-wall grade. Use BL-A202 for UV/salt exposure at that level.

— Hammer and wrinkle variants are different products with their own sheets — do not assume this sheet covers them.

1. Values in this sheet are typical for the product and were measured to the methods listed. They are not a certificate and not a warranty of fitness for a particular purpose. Acceptance values are fixed in the trial report and the purchase specification.
2. Colour: RAL references only. RAL does not define sRGB values, so the swatch in this sheet is a digital approximation — approval is made on a sprayed panel against a physical RAL chip.
3. No AAMA 2603 / 2604 / 2605, QUALICOAT, GSB or UL product certificate is held. We test to those methods and can supply third-party reports and in-house batch reports; if a tender requires the certificate itself, we will say plainly that we do not have it.
4. The 4,000 h salt spray and 10-year South Florida results shown elsewhere on our site belong to the fluorocarbon (PVDF) system, not to this powder product.

Issued by Guangdong Baolilai Industrial Co., Ltd. · jerry888.xu@gmail.com · +86 188 2310 0890
Ask for: SDS · third-party test report · batch report · physical colour chip · sample in 3 days

户外砂纹灰

聚酯，TGIC 或 TGIC-free · RAL 7035

RAL 7035 · 浅灰

产品	编号 • 系列	参照颜色	文件
Outdoor Sand Grey 户外砂纹灰	BL-A201 BL-A 建筑户外聚酯	RAL 7035 · 浅灰	TDS BL-A201 Rev. 2026-10

P1000 · 可按 AAMA 2603 / QUALICOAT I 测试项目送检（可索取报告）——不持有产品认证证书

1. 产品描述

最常用的户外砂纹。它能盖住焊缝打磨痕、砂轮印与轻微凹陷，所以门窗与机柜厂用它来省打磨、降返工。TGIC 与 TGIC-free 两条路线都可供；欧盟招标、以及客户主动问标签时，报 TGIC-free。

2. 典型性能

项目	数值	方法
体系	聚酯，TGIC 或 TGIC-free	—
参照颜色	RAL 7035 浅灰——以喷板对照实物色卡确认	RAL
表面与光泽	砂纹 5–12（60°）	ASTM D523
膜厚	60–80 µm	ISO 2808
比重	1.50–1.58 g/cm³	ISO 8130-2/3
覆盖率	100% 成膜 9.3 m²/kg · 按 95% 利用率（含回收）规划值 8.8 m²/kg	计算值
固化条件	200 °C × 10 min（工件温度）	测工件温度，非炉膛设定
粒径 D50	30–45 µm	ISO 8130-1 / -13
烘烤失重	≤ 1–2 %	ISO 8130-7
贮存稳定性	35–40 °C 下 1 个月	ISO 8130-8

3. 性能数据

检测项目	方法	典型结果
1. 划格附着力	ISO 2409 / ASTM D3359	0–1（铝件经转化膜处理可达 100/100）
2. 正反冲击	ASTM D2794	50 kg·cm 不裂
3. 铅笔硬度	ASTM D3363	H（典型 2H）
4. 光泽 60°	ASTM D523	砂纹 5–12
5. 色差	ASTM D2244	同批 ΔE ≤ 1.5
6. 中性盐雾	ASTM B117 / ISO 9227	1000 h（铝件转化膜，膜厚 70–80 µm）
7. QUV-A 加速老化	ASTM G154	1000 h，保光率 ≥ 50%
8. 耐化学性	ASTM D1308	按工况——包括洗涤剂与清洁剂

按所列方法在量产批次或本体系所持第三方报告上测定。不是证书：验收值以试粉报告与采购规格为准。

4. 施工与固化

01　铝件前处理

脱脂 → 蚀洗 → 水洗 → 无铬转化膜 → 纯水洗 → 干燥。1000 h 盐雾是建立在转化膜之上的。

02　钢件前处理

脱脂 → 锌系磷化 → 水洗 → 纯水洗 → 干燥。

03　喷涂

电晕 60–90 kV，枪距 150–250 mm，膜厚 60–80 µm。纹理由膜厚与固化决定：低于 50 µm 会透底，高于 100 µm 纹理被抹平。

04　固化

工件温度 200 °C × 10 min。TGIC-free 窗口更窄——过烘先让纹理变钝，颜色还没变。

05　回收

回收过喷粉可按 20–25% 掺用，纹理不漂移。掺用前过筛。

5. 包装、贮存与订货

1. 标准包装：20 kg 净重，纸箱内衬聚乙烯袋。其他包装规格可订。
2. 30 °C 以下、干燥、避免阳光直射，保持原包装未开封。远离烘道与高温工位。
3. 保质期：原包装自生产日起 12 个月。贮存稳定性按 ISO 8130-8 于 35–40 °C 验证一个月。
4. 每批附批次检测报告；留样保存 12 个月。
5. 3 天出样；生产交期按颜色与包装规格在订单时确认。
6. 同批色差 ΔE ≤ 1.5；跨批公差在采购规格中约定。
7. 可索取：SDS · 第三方检测报告 · 批次检测报告 · 实物色卡。

6. 健康与安全

1. 不属于运输危险品。每个产品均提供 SDS（安全数据表），可与 TDS 一并索取。
2. 粉末为可燃性粉尘。工件、喷枪与喷房必须接地；喷房内禁止明火与动火作业；喷房须抽风；倒粉与清房时避免扬尘。
3. 处理干粉或清理喷房时，佩戴 P2 防尘口罩、护目镜与手套。
4. 固化挥发物：烘道须抽风；工件冷却后再搬运。无通风不得进入烘道区域。

7. 同系列其他产品

编号	产品	颜色	膜厚	固化
BL-A202	超耐候香槟金	RAL 1015	70–90 µm	200 °C × 12–15 min

8. 文件控制

文件	版本	签发	替代版本	语言
BL-A201 TDS	2026-10	2026-10	无——首版	英文 + 中文（共 4 页）

9. 本文件的边界

这款产品不适合用在：

— 纹理不是配色工具：两批粉以不同膜厚喷出来，在侧光下就是两个颜色。

— P1000 不是沿海幕墙等级。那个等级的紫外与盐雾请用 BL-A202。

— 锤纹与皱纹是另外的产品，各有独立 TDS——不要用本表代替。

1. 本表数值为该产品的典型值，按所列方法测定。它们不是证书，也不构成对特定用途适用性的保证。验收值以试粉报告与采购规格为准。
2. 颜色：仅作 RAL 参照。RAL 未定义 sRGB 数值，本表色块为数字近似——以喷涂样板对照实物 RAL 色卡确认。
3. 我们不持有 AAMA 2603 / 2604 / 2605、QUALICOAT、GSB 或 UL 产品认证证书。我们按这些方法检测，可提供第三方报告与厂内批次报告；若招标硬性要求证书本身，我们会直接说明没有。
4. 我们网站上 4000 小时盐雾与 10 年南佛罗里达曝晒的结果属于氟碳（PVDF）体系，不属于本粉末产品。

签发：广东宝利莱工业有限公司 · jerry888.xu@gmail.com · +86 188 2310 0890
可索取：SDS · 第三方检测报告 · 批次报告 · 实物色卡 · 3 天出样