Super Durable Champagne

Super-durable polyester, high-performance light-stabiliser package · RAL 1015

RAL 1015 · Light ivory

Product	Code • series	Colour reference	Document
Super Durable Champagne 超耐候香槟金	BL-A202 BL-A Architectural Polyester	RAL 1015 · Light ivory	TDS BL-A202 Rev. 2026-10

P1500 · tested to AAMA 2604 / QUALICOAT II test items on request — no product certificate held

1. Description

The exterior grade: a super-durable polyester with a stronger light-stabiliser package, for curtain wall, premium windows and coastal projects, tested to the AAMA 2604 / QUALICOAT II class of test items on request. It is not AAMA 2605 and we hold no AAMA certificate. If a specification names 2605, the fluorocarbon P2000 is the product to quote.

2. Typical properties

Property	Value	Method
Chemistry	Super-durable polyester, high-performance light-stabiliser package	—
Colour reference	RAL 1015 Light ivory — approval on a sprayed panel against a physical chip	RAL
Finish and gloss	Matte, 30 ± 5 @60°	ASTM D523
Film build	70–90 µm	ISO 2808
Density	1.50–1.60 g/cm³	ISO 8130-2/3
Coverage	8.1 m²/kg at 100 % film · 7.7 m²/kg planning value at 95 % utilisation (with reclaim)	calculated
Cure schedule	200 °C × 12–15 min (object temperature)	object temp., not oven set point
Particle size D50	30–45 µm	ISO 8130-1 / -13
Stoving loss	≤ 1–2 %	ISO 8130-7
Storage stability	1 month at 35–40 °C	ISO 8130-8

3. Performance data

Test	Method	Typical result
1. Adhesion, cross-cut	ISO 2409 / ASTM D3359	0–1 (100/100 on aluminium with a conversion coating)
2. Impact, direct and reverse	ASTM D2794	50 kg·cm, no cracking
3. Pencil hardness	ASTM D3363	H
4. Gloss 60°	ASTM D523	Matte, 30 ± 5
5. Colour difference	ASTM D2244	ΔE ≤ 1.5 same batch
6. Neutral salt spray	ASTM B117 / ISO 9227	1,000 h (conversion-coated aluminium, 80 µm)
7. QUV-A	ASTM G154	2,000 h, gloss retention ≥ 50 %
8. South Florida exposure	ASTM D2244 / D523	Not run on this product — the 10-year report we hold is the fluorocarbon system

Measured to the method listed, on production batches or the third-party report held for this system. Not a certificate: acceptance values are fixed in the trial report and the purchase specification.

4. Application and cure

01 Pre-treatment

Degrease → etch → rinse → chromium-free conversion coating → DI rinse → dry. Salt spray lives or dies on the final rinse: check the conductivity of the DI water, not just the bath titration.

02 Application

Corona 60–90 kV, gun-to-part 150–250 mm, 70–90 µm in one pass. No primer required for architectural aluminium.

03 Cure

Object temperature 200 °C for 12–15 min. The matte level moves with cure: a 10 °C difference between oven zones shows as gloss banding on a long profile.

04 Appearance control

Matte and metallic exteriors are the hardest to keep uniform. Fix gun distance and DFT, and approve the panel under raking light, not under a desk lamp.

05 Maintenance note for the specifier

Design life assumes the façade is cleaned on a normal cycle. Salt and industrial fallout left on a coated panel shorten any polyester's life, including this one.

5. Packaging, storage and ordering

1. Standard pack: 20 kg net, polyethylene-lined carton. Other pack sizes on request.
2. Store below 30 °C, dry, out of direct sunlight, in the unopened pack. Keep away from ovens and hot lines.
3. Shelf life: 12 months from the production date in the original pack. Storage stability is verified at 35–40 °C for one month (ISO 8130-8).
4. A batch test report accompanies every delivery; a retained sample is kept for 12 months.
5. Sample in 3 days; production lead time confirmed per colour and pack size at order.
6. Colour match ΔE ≤ 1.5 within a batch. Cross-batch tolerance is agreed in the purchase specification.
7. Ask for: SDS · third-party test report · batch test report · physical colour chip.

6. Health and safety

1. Not classified as dangerous goods for transport. The SDS is available for every product — ask for it with the TDS.
2. The powder is a combustible dust. Earth the workpiece, the gun and the booth; no open flame or hot work in the booth; extract booth air; avoid dust clouds when emptying or cleaning.
3. Wear a P2 particulate mask, goggles and gloves when handling dry powder or cleaning the booth.
4. Cure volatiles: extract the oven and let parts cool before handling. Do not enter the oven zone without ventilation.

7. Also in this range

Code	Product	Colour	Film build	Cure
BL-A201	Outdoor Sand Grey	RAL 7035	60–80 µm	200 °C × 10 min

8. Document control

Sheet	Revision	Issued	Supersedes	Languages
BL-A202 TDS	2026-10	2026-10	None — first issue	English + 中文 (4 pp.)

9. Limits of this document

What this product is not for:

— Not AAMA 2605. If the spec names 2605 or QUALICOAT III, quote P2000 fluorocarbon instead of arguing.

— Champagne metallics need a fixed gun path — a hand-sprayed patch will read as a shade difference on a façade.

— Coastal design life depends on pre-treatment, film build and cleaning regime together, not on the powder grade alone.

1. Values in this sheet are typical for the product and were measured to the methods listed. They are not a certificate and not a warranty of fitness for a particular purpose. Acceptance values are fixed in the trial report and the purchase specification.
2. Colour: RAL references only. RAL does not define sRGB values, so the swatch in this sheet is a digital approximation — approval is made on a sprayed panel against a physical RAL chip.
3. No AAMA 2603 / 2604 / 2605, QUALICOAT, GSB or UL product certificate is held. We test to those methods and can supply third-party reports and in-house batch reports; if a tender requires the certificate itself, we will say plainly that we do not have it.
4. The 4,000 h salt spray and 10-year South Florida results shown elsewhere on our site belong to the fluorocarbon (PVDF) system, not to this powder product.

Issued by Guangdong Baolilai Industrial Co., Ltd. · jerry888.xu@gmail.com · +86 188 2310 0890
Ask for: SDS · third-party test report · batch report · physical colour chip · sample in 3 days

超耐候香槟金

超耐候聚酯，高效光稳定体系 · RAL 1015

RAL 1015 · 浅象牙

产品	编号 • 系列	参照颜色	文件
Super Durable Champagne 超耐候香槟金	BL-A202 BL-A 建筑户外聚酯	RAL 1015 · 浅象牙	TDS BL-A202 Rev. 2026-10

P1500 · 可按 AAMA 2604 / QUALICOAT II 测试项目送检（可索取报告）——不持有产品认证证书

1. 产品描述

户外等级产品：超耐候聚酯配更强光稳定体系，用于幕墙、高端门窗与沿海项目，可按 AAMA 2604 / QUALICOAT II 级别的测试项目送检。它不是 AAMA 2605，我们也不持有 AAMA 证书。若规范点名 2605，应报氟碳 P2000。

2. 典型性能

项目	数值	方法
体系	超耐候聚酯，高效光稳定体系	—
参照颜色	RAL 1015 浅象牙——以喷板对照实物色卡确认	RAL
表面与光泽	哑光 30±5（60°）	ASTM D523
膜厚	70–90 µm	ISO 2808
比重	1.50–1.60 g/cm³	ISO 8130-2/3
覆盖率	100% 成膜 8.1 m²/kg · 按 95% 利用率（含回收）规划值 7.7 m²/kg	计算值
固化条件	200 °C × 12–15 min（工件温度）	测工件温度，非炉膛设定
粒径 D50	30–45 µm	ISO 8130-1 / -13
烘烤失重	≤ 1–2 %	ISO 8130-7
贮存稳定性	35–40 °C 下 1 个月	ISO 8130-8

3. 性能数据

检测项目	方法	典型结果
1. 划格附着力	ISO 2409 / ASTM D3359	0–1（铝件经转化膜处理可达 100/100）
2. 正反冲击	ASTM D2794	50 kg·cm 不裂
3. 铅笔硬度	ASTM D3363	H
4. 光泽 60°	ASTM D523	哑光 30 ± 5
5. 色差	ASTM D2244	同批 ΔE ≤ 1.5
6. 中性盐雾	ASTM B117 / ISO 9227	1000 h（铝件转化膜，膜厚 80 µm）
7. QUV-A 加速老化	ASTM G154	2000 h，保光率 ≥ 50%
8. 南佛罗里达曝晒	ASTM D2244 / D523	本产品未做——我们持有的 10 年报告属于氟碳体系

按所列方法在量产批次或本体系所持第三方报告上测定。不是证书：验收值以试粉报告与采购规格为准。

4. 施工与固化

01　前处理

脱脂 → 蚀洗 → 水洗 → 无铬转化膜 → 纯水洗 → 干燥。盐雾成败在最后一道纯水洗：查纯水电导率，不要只滴定槽液。

02　喷涂

电晕 60–90 kV，枪距 150–250 mm，一次上膜 70–90 µm。建筑铝型材无需底粉。

03　固化

工件温度 200 °C × 12–15 min。哑光度随固化变化：烘道各温区差 10 °C，长型材上就会出现光泽带状差。

04　外观控制

哑光与金属外观最难做匀。固定枪距与膜厚，样板要在侧光下确认，不要在台灯下看。

05　给设计方的维护说明

设计寿命的前提是按常规周期清洗幕墙。盐分与工业落尘长期留在涂层上，会缩短任何聚酯的寿命，包括这一款。

5. 包装、贮存与订货

1. 标准包装：20 kg 净重，纸箱内衬聚乙烯袋。其他包装规格可订。
2. 30 °C 以下、干燥、避免阳光直射，保持原包装未开封。远离烘道与高温工位。
3. 保质期：原包装自生产日起 12 个月。贮存稳定性按 ISO 8130-8 于 35–40 °C 验证一个月。
4. 每批附批次检测报告；留样保存 12 个月。
5. 3 天出样；生产交期按颜色与包装规格在订单时确认。
6. 同批色差 ΔE ≤ 1.5；跨批公差在采购规格中约定。
7. 可索取：SDS · 第三方检测报告 · 批次检测报告 · 实物色卡。

6. 健康与安全

1. 不属于运输危险品。每个产品均提供 SDS（安全数据表），可与 TDS 一并索取。
2. 粉末为可燃性粉尘。工件、喷枪与喷房必须接地；喷房内禁止明火与动火作业；喷房须抽风；倒粉与清房时避免扬尘。
3. 处理干粉或清理喷房时，佩戴 P2 防尘口罩、护目镜与手套。
4. 固化挥发物：烘道须抽风；工件冷却后再搬运。无通风不得进入烘道区域。

7. 同系列其他产品

编号	产品	颜色	膜厚	固化
BL-A201	户外砂纹灰	RAL 7035	60–80 µm	200 °C × 10 min

8. 文件控制

文件	版本	签发	替代版本	语言
BL-A202 TDS	2026-10	2026-10	无——首版	英文 + 中文（共 4 页）

9. 本文件的边界

这款产品不适合用在：

— 不是 AAMA 2605。规范点名 2605 或 QUALICOAT III 时，直接报氟碳 P2000，不要争。

— 香槟金金属色需要固定枪路——手喷补块在幕墙上会看成一个色差。

— 沿海设计寿命取决于前处理、膜厚与清洗制度三者，不只是粉末等级。

1. 本表数值为该产品的典型值，按所列方法测定。它们不是证书，也不构成对特定用途适用性的保证。验收值以试粉报告与采购规格为准。
2. 颜色：仅作 RAL 参照。RAL 未定义 sRGB 数值，本表色块为数字近似——以喷涂样板对照实物 RAL 色卡确认。
3. 我们不持有 AAMA 2603 / 2604 / 2605、QUALICOAT、GSB 或 UL 产品认证证书。我们按这些方法检测，可提供第三方报告与厂内批次报告；若招标硬性要求证书本身，我们会直接说明没有。
4. 我们网站上 4000 小时盐雾与 10 年南佛罗里达曝晒的结果属于氟碳（PVDF）体系，不属于本粉末产品。

签发：广东宝利莱工业有限公司 · jerry888.xu@gmail.com · +86 188 2310 0890
可索取：SDS · 第三方检测报告 · 批次报告 · 实物色卡 · 3 天出样