Head Office
B-66/A, S.I.T.E. Area,
Karachi-75700, Pakistan.
info@vawda.com
+92 (21) 3255 0093-98

Faisalabad Office
P-68, Vawda House, Vawda Street 4,
Zia Town, Faisalabad-38000, Pakistan.
fsd@vawda.com
+92 (41) 852 4576

Lahore Office
307/E, Nadir Streel,Ferry Meadowlane,
West Canel Band, Lahore-54590, Pakistan.
lhr@vawda.com
+92 (42) 3611 3239

Multan Office
Plot # 85, Phase-1 Industrial
Estate, Multan-60900, Pakistan.
mul@vawda.com
+92 (61) 653 8131

favgroupofcompanies
favgroupofcompanies
www.vawda.com

Veechem Industries (Pvt.) Ltd

FAVOPRINT
GOTS
Approved
RANGE

Veechem Industries (Pvt.) Ltd

STANDARD PRINTING RECIPES

Stock Paste:

Water	g/kg		
BINDER	80-150	g/kg	
UREA	10-20	g/kg	
Crosslinking agent	5-10	g/kg	
Ammonia (25%)	1-2	g/kg	(adjust pH 8.5-9.0)
THICKNER	25-30	g/kg	

(to achieve viscosity 7000-9000CPS)

TOTAL 1000 g

Printing Paste

FAVOPRINT Pigment	10-60	g/kg
Stock Paste	990-940	g/kg

TOTAL 1000 g

Print Process:

Print

Dry at 100-120◦C for 1-2min

Cure at 150◦C for 5min

Note:

1- pH of print paste should be **8-9**

2- Viscosity of print paste should be **7000-9000 cps**

3- If necessary use Antifoam, Modifier & Dispering agent as per prescribed by their supplier

SUITABILITY FOR PIGMENT DYEING

Favoprint Pigments are suitable for dyeing by Continuous application as well as for Exhaust dyeing of knitted fabrics.

Key:

1/1 : Full print
1/9 : Reduction
• : Suitable
○ : Not stable
N.D : Not Defined

Veechem Industries (Pvt.) Ltd

INFORMATION ABOUT FASTNESS PROPERTIES

LIGHT FASTNESS: Light Fastness test carried out with Xenone light fastness tester.
according to ISO 105 BO2 for 40hrs.

THERMOSTABILITY : Thermostability being carried out according to ISO 105 PO1at 180oC x 1min
Only Shade change has obseved.

DRY-CLEANING FASTNESS: Staining of solvent not considered, only shade change observed according to ISO 105-DO1

PVC FASTNESS: Migration of pigment into PVC film is observed staining according to test ISO 105 X 10

SUITABLITY IN DISCHARGE: Results are based on testing the print 30g/kg pigment dispersion with discharging agent.
• stable, ○ not stable

Veechem Industries (Pvt.) Ltd

PRODUCTS		S.D 1/1 (gm/kg)	C.I.NO	Fastness to light ISO 105 BO2 (24 hrs)	
30g/kg	1:9			1/1	1/9
		30	Y-17	7	6
FAVOPRINT L.YELLOW AF-3GN					
		30	Y-83	7-8	6-7
FAVOPRINT G.YELLOW AF-GRP					
		30	O-13	6	5
FAVOPRINT ORANGE AF-RF					
		30	R-170	7	7
FAVOPRINT RED AF-KCSP					

Fastness to Dry Cleaning. ISO 105 DO1		Fastness to Hypochlorite Bleach ISO 105 NO1		Fastness to Chlorine ISO 105 EO3-100ppm		Fastness to PVC ISO 105 X-10	Heat stability 1min @ 180°C ISO 105 PO1	Suitiblity in discharge (80g/kg Rongalit)	Oeko Tex Standard 100 (MAK Amines limit ppm)
1/1	1/9	1/1	1/9	1/1	1/9	60g/kg	30g/kg		
4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	•	•
4-5	4-5	4-5	4	4-5	4	4	4-5	•	•
3	2-3	4-5	4	4	4	3-4	4-5	•	•
4	4	4-5	4-5	4	4	4	4-5	•	•

Veechem Industries (Pvt.) Ltd

PRODUCTS		S.D 1/1 (gm/kg)	C.I.NO	Fastness to light ISO 105 BO2 (24 hrs)	
30g/kg	1:9			1/1	1/9
		30	R-266	7	6-7
FAVOPRINT RED AF-KB					
		30	R-238	5	4
FAVOPRINT PINK AF-5BN NEW					
		30	R-122	7	6-7
FAVOPRINT PINK AF-3BL					
		30	R-122	7	6-7
FAVOPRINT PINK AF-3BD					

Fastness to Dry Cleaning. ISO 105 DO1		Fastness to Hypochlorite Bleach ISO 105 NO1		Fastness to Chlorine ISO 105 EO3-100ppm		Fastness to PVC ISO 105 X-10	Heat stability 1min @ 180°C ISO 105 PO1	Suitiblity in discharge (80g/kg Rongalit)	Oeko Tex Standard 100 (MAK Amines limit ppm)
1/1	1/9	1/1	1/9	1/1	1/9	60g/kg	30g/kg		
4	4	4-5	4-5	4	4	4	4-5	•	•
4	4	4	3-4	4	4	2-3	4-5	•	•
4-5	4-5	4	4	1-2	1-2	4-5	4-5	•	•
4-5	4-5	4	4	1-2	1-2	4-5	4-5	•	•

Veechem Industries (Pvt.) Ltd

PRODUCTS		S.D 1/1 (gm/kg)	C.I.NO	Fastness to light ISO 105 BO2 (24 hrs)		Fastness to Dry Cleaning. ISO 105 DO1		Fastness to Hypochlorite Bleach ISO 105 NO1		Fastness to Chlorine ISO 105 EO3-100ppm		Fastness to PVC ISO 105 X-10	Heat stability 1min @ 180°C ISO 105 PO1	Suitiblity in discharge (80g/kg Rongalit)	Oeko Tex Standard 100 (MAK Amines limit ppm)
30g/kg	1:9			1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/9	60g/kg	30g/kg		
		30	V-23	7-8	7	4-5	4	4-5	4-5	4-5	4.5	4	4-5	•	•
FAVOPRINT VIOLET AF-HS															
		30	V-23	7-8	7	4-5	4	4-5	4-5	4-5	4	4	4-5	•	•
FAVOPRINT VIOLET AF-RT															
		30	B-15:3	7	6-7	4-5	4	4-5	4	4	4	4-5	4-5	•	•
FAVOPRINT TURQ AF-RG															
		30	B 15:3	7	6-7	4	4	4-5	4	4	4-5	4-5	4-5	•	•
FAVOPRINT TURQ AF-RNB															

Veechem Industries (Pvt.) Ltd

PRODUCTS

30g/kg	1:9	S.D 1/1 (gm/kg)	C.I.NO	Fastness to light ISO 105 BO2 (24 hrs)		Fastness to Dry Cleaning- ISO 105 DO1		Fastness to Hypochlorite Bleach ISO 105 NO1		Fastness to Chlorine ISO 105 EO3-100ppm		Fastness to PVC ISO 105 X-10	Heat stability 1min @ 180°C ISO 105 PO1	Suitiblity in discharge (80g/kg Rongalit)	Oeko Tex Standard 100 (MAK Amines limit ppm)
				1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/9	60g/kg	30g/kg		
		30	B 15:0	7	6-7	4	3-4	4-5	4	4	4	4	4-5	•	•
FAVOPRINT BLUE AF-KB															
		30	B-15	7	6-7	4	3-4	4-5	4	4	4	4	4-5	•	•
FAVOPRINT BLUE AF-FR															
		30	MIX	6	5-6	4	3-4	4	3-4	4	3-4	3	4	•	•
FAVOPRINT BLUE AF-RHB															
		30	MIX	7	6	4-5	4	4-5	4	4-5	4	4-5	4-5	•	•
FAVOPRINT NAVY AF-RR															

Veechem Industries (Pvt.) Ltd

PRODUCTS

30g/kg	1:9	S.D 1/1 (gm/kg)	C.I.NO	Fastness to light ISO 105 BO2 (24 hrs)		Fastness to Dry Cleaning. ISO 105 DO1		Fastness to Hypochlorite Bleach ISO 105 NO1		Fastness to Chlorine ISO 105 EO3-100ppm		Fastness to PVC ISO 105 X-10	Heat stability 1min @ 180°C ISO 105 PO1	Suitiblity in discharge (80g/kg Rongalit)	Oeko Tex Standard 100 (MAK Amines limit ppm)
				1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/9	60g/kg	30g/kg		
		60	BL-7	7-8	7	4-5	4-5	4-5	4-5	4-5	4-5	4-5	5	•	•
FAVOPRINT BLACK AF-BB															
		60	BL-7	7-8	7	4-5	4-5	4-5	4-5	4-5	4-5	4-5	5	•	•
FAVOPRINT BLACK AF-SP															
		30	O-34	7-8	5-6	3-4	4	4	4	4-5	4-5	4-5	4-5	•	•
FAVOPRINT ORANGE AF-GS															
		30	G-7	7-8	7	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	•	•
FAVOPRINT GREEN AF-G2B															