

Veechem Industries (Pvt.) Ltd



Pigment Powder Shade card

Farid Ahmed Vawda & Co.

S.No	PIGMENT COLOR	PRODUCT NAME	C.I No	Physical data			Heat Resistance	Chemical Resistance		Light Fastness		Weather fastness		Application			
				pH Value	Specific gravity (gr/cm3)	Oil Absorption (gr/100g)		Acid	Alkali	Mass 5%	Tint 1:10	Mass 5%	Tint 1:10	Inks			Paints
														Offset Printing	Gravure Printing	Water base printing	Aqueous
1		VEETONE YELLOW PG	Y-12	5.5-7.5	1.5	40-55	180	5	5	6	5	5	4	●	●	●	o
2		VEETONE YELLOW P2G	Y-14	5.5-7.5	1.6	35-50	180	5	4	6	5	5	4		●	●	●
3		VEETONE YELLOW P3G	Y-17	6.0-8.0	1.33	40-50	200	5	5	6	5	5	3	●	●	●	●
4		VEETONE YELLOW PGR	Y-83	6.0-8.0	1.7	35-50	200	5	5	7	6	5	4-5	o	o	●	●
5		VEETONE YELLOW P2R	Y-85	5.5-7.5	1.5	30-45	180	5	5	6	5-6	5	4-5	o	o	●	●
6		VEETONE ORANGE PR	O-13	6.0-8.0	1.6	35-50	150	5	4	6	5	5	3	●	●	●	●
7		VEETONE ORANGE P2R	O-34	6.0-8.0	1.6	30-45	180	5	4	6	5	5	3	●	●	●	●
8		VEETONE RED PR	R-8	6.0-8.0	1.5	45-60	150	5	3-4	6	5	4	3	o	●	●	●
10		VEETONE RED PHR	R-146	6.5-8.5	1.7	35-50	180	5	5	7	6	5	5	●	o	●	●
9		VEETONE PINK PB	R-238	6.0-7.0	1.6	40-50	150	5	4	5	4	4	3	o	●	●	●
11		VEETONE BRILL PINK P2B	R-122	6.5-8.5	1.6	35-50	250	5	4	7-8	6-7	5	5	o	●	●	●
12		VEETONE RED-PRB	R-150	6.0-8.0	1.5	35-50	200	5	5	6	5	5	5	●	o	●	●

S.No	PIGMENT COLOR	PRODUCT NAME	C.I No	Physical data			Heat Resistance	Chemical Resistance		Light Fastness		Weather fastness		Application			
				pH Value	Specific gravity (gr/cm3)	Oil Absorption (gr/100g)		Acid	Alkali	Mass 5%	Tint 1:10	Mass 5%	Tint 1:10	Inks			Paints
														Offset Printing	Gravure Printing	Water base printing	Aqueous
13		VEETONE RED-PRR	R-210	6.0-7.0	1.5	40-50	180	5	5	6	5	5	5	●	o	●	●
14		VEETONE RED-P5RK	R-170	6.0-8.0	1.5	35-50	200	5	5	7	6	5	4	o	●	●	●
15		VEETONE RED-P7RK	R-266	6.0-8.0	1.5	30-45	180	5	4	7	6	5	4	o	●	●	●
16		VEETONE VIOLET-PRL	V-23	6.0-8.0	1.8	45-60	250	5	5	7-8	7	5	5	o	o	●	●
17		VEETONE BLUE-PR	B15:0	6.5-8.5	1.8	30-45	200	5	5	8	7-8	5	5	o	o	●	●
18		VEETONE BUE-PG	B 15:3	6.5-8.5	1.8	30-45	220	5	5	8	7-8	5	5	●	●	●	●
19		VEETONE GREEN P2G	G-7	6.5-8.5	1.8	30-45	220	5	4-5	7-8	7-8	5	7	●	●	●	●
20		VEETONE BLACK PS	BLK-7	8.0-9.5	0.57	80	220	5	5	8	8	5	5	o	o	●	●

Veechem Industries (Pvt.) Ltd

DENSITY:

The density, unlike the bulk volume, is a property of pigment crystals. It is used for instance, for calculating the pigment volume concentration. The density is determined by the pyknometer method (ISO 787-10)

OIL ABSORPTION:

It is the number of grams of oil needed to bind 100gm of pigment into a coherent, putty like paste. The amount greatly depends on the way the oil is incorporated. Consequently the test results can be very scattered. Value observed are only compairable if the same tester using the same method in quick succession obtains them. The determine is carried out in accordance with ISO 787-5.

FASTNESS TO LIGHT:

Not only does the fastness to light of a pigmented coating depend on the colorant, but a great extent also on the colorant conentration, the film thickness and the binder system. Other factures such as the spectral composition of light or humidity play a significant role as well. In full tone shades, the film thickness has greater influence on the fastness to light than in white white reductions, whose fastness to light is strongly influenced by the titanium dioxide type and stabilization. The change of shade is assessed on the eight point blue wool scale based on ISO 105-BO1.

HEAT STABILITY:

The value quoted indicates up to which temperature the pigments do not significantly alter coloristically. Test performed in alkyd melamine with upper testing testing limit of 200

NOTE:

● MAJOR USE o OTHER POTENTIAL USE

Head Office:
B-66/A,SITE Area
Karachi-75700,Pakistan
www.vawda.com
T +92 (21) 3255 0093-98
F +92 (21) 3255 0099
E info@vawda.com

Lahore Office:
307/E, Nadir Street,
Ferry Meadowland,
West Canal Bank, Lahore.
T +92 (42) 36113239
F +92 (42) 3529 2819
E lhr@vawda.com

Faisalabad Office:
P-68. Vawda House,
Vawda Street 4,
Zia Town, Faisalabad.
T +92 (41) 852 4576
F +92 (41) 852 4947
E fsd@vawda.com

The Classic CD