NAGDEV PRODUCTS PRIVATE LIMITED
Manufacturer of Castor Oil & Specialty Oleochemical Derivatives · Gujarat, India
Survey No. 301 P-2, Sardarpura, Taluka · Deodar, Dist. Vav-Tharad · 385330 | nagdevproducts@gmail.com
Hotline / WhatsApp: +91 63520 98306 | Web: www.nagdevproducts.com

TECHNICAL DATA SHEET
Doc Ref: NPPL-TDS-17
Date: October 2026
Status: Advance Specification

Bio-Polyurethane Polyols (Castor-Oil-Based Polyols)

Proprietary Grade: NDEVPOL· BIO | CAS No: 68441-60-1 | Category: Under Development

Physical Form:	Viscous Liquid	Raw Material:	Castor Oil / Castor-Oil-Derived
Typical Colour:	Pale Yellow to Amber	Shelf Life:	12-18 months
Standard Packing:	200 kg HDPE / MS Drums · 1,000 kg IBC · Bulk in ISO Tank / Flexi Tan		

GUARANTEED ANALYTICAL SPECIFICATIONS

SR	TEST PARAMETER	SPECIFICATION LIMIT	STANDARD METHOD
1	Appearance	Clear to Slightly Hazy, Viscous Pale	Visual
2	Colour, Gardner	4.0 Max	ASTM D1544
3	Hydroxyl Value, mg KOH/g	160 · 180	ASTM D4274
4	Acid Value, mg KOH/g	2.0 Max	ASTM D4662
5	Moisture Content, %	0.20 Max	Karl Fischer / ASTM
6	Viscosity at 25°C, cP	650 · 900	ASTM D4878
7	Specific Gravity at 25°C	0.950 · 0.970	ASTM D4052
8	Average Hydroxyl Functionality	2.5 · 3.0	Calculated / Standar
9	Iodine Value, g I·/100g	80 · 90	AOCS Cd 1d-92
10	Saponification Value, mg KOH/g	175 · 190	AOCS Cd 3-25
11	Unsaponifiable Matter, %	1.0 Max	AOCS Ca 6a-40
12	Flash Point, °C	200 Min	ASTM D92
13	Hydroxyl Content / OH Number Consistency	Within agreed batch specification	ASTM D4274

PRODUCT APPLICATION & CHARACTERISTICS

Used as a renewable, bio-based polyol component in polyurethane coatings, adhesives, sealants and elastomers.
A separate higher-hydroxyl-value grade should be quoted for flexible/rigid foam customers rather than using this coating-grade specification.

IMPORTANT NOTICE & COMMERCIAL AVAILABILITY:
Commercial production begins in 2027 at our new integrated manufacturing facility in Vav-Tharad, Gujarat.
Advance bulk inquiries, long-term supply agreements, and 500g/1kg R&D lab samples are currently accepted.