

INTRODUCING

MODEL 3

**3D Photopolymer Dental resin
for vacuum/pressure thermoforming
(IPA OR WATER-WASHABLE)**

Compatible with most:

**LCD/DLP/SLA
365-405 nm**



**IPA or Water
Washable**



**Anti-Stick
Formula**



**High Heat
Resistance**



**Fast
Curing**



**High Accuracy &
Consistent Models**



**Low
Shrinkage**

Advanced Thermoforming Resin

Resinwork® Model 3 is an advanced, IPA & water-washable 3D printing resin engineered specifically for dental thermoforming applications. Designed to deliver high thermal resistance and dimensional accuracy, Model 3 ensures reliable performance under vacuum and pressure forming conditions.

Formulated with Resinwork's proprietary Anti-Stick Surface Chemistry, Model 3 enables effortless removal of thermoformed appliances—such as retainers, aligners, nightguards, and sportguards—without damage to the model or appliance. This unique surface release property significantly reduces the risk of breakage and enhances workflow efficiency in dental labs.

Unlike conventional resins, Model 3 features a stable, matte finish that resists sticking to heated substrates and ensures consistent results. Its high pigment stability eliminates the need for frequent mixing, while its water-washable composition provides safe, eco-friendly handling—no alcohol or chemical cleaners required.

Whether you're fabricating clear aligners or custom appliances, Resinwork Model 3 is your go-to solution for dependable, lab-grade performance.



Almond



White



Beige



Grey



Features

- Economical
- Highly accurate printing and consistent models
- IPA and Water washable
- Superior surface quality, shows crisp details

Tensile Properties

Tensile Strength	45 MPa
Elongation at break	6%
E modulus	700 Mpa

Others

Hardness Shore D	72D
Water absorption, short term (24h)	1.59%

Packaging & Order Instructions

SKU	Colour	Pack Size / Case
2511-0415	Birch Beige	1 kg / 4
2511-0381	Aquaforge Grey	1 kg / 4
2511-0408	Aquaforge Almond	1 kg / 4
2511-0410	Snow Cream White	1 kg / 4

Physical & Chemical Properties

Appearance	Gray liquid
Colour	Aquaforge Grey
Odour	Almost odourless

Chemical Composition	Mixture of Monomers, Oligomers, Photo-initiator & Additives
Basic	Proprietary

Viscosity, 25°C	200 mPas
-----------------	----------

Density (Liquid Resin)	1.07 g/cm ³
Density (printed part)	1.2 g/cm ³

Flexural Properties

Flexural Modulus	1800 MPa
Flexural Strength	90 Mpa

Thermal Properties

HDT at 0.45 Mpa	1800 MPa
HDT at 1.82 MPa	55°C

Colours Available

	Birch Beige		Aquaforge Grey
	Snow Cream White		Aquaforge Almond



Manufactured & Marketed by:
Graichen Produktions- und Vertriebs GmbH
 Darmstädter Str. 127, 64625 Bensheim, Germany

Sales: Tel +49 6251 770 788-0
 info@graichen-bensheim.de

The above details have been compiled to the best of our knowledge on the basis of tests and research work and with regard to the current state of our practical experience. This technical product information is non-binding. No liabilities or guarantees deriving from or in connection with this leaflet can be imputed to us. Statements relating to possible uses of the product do not constitute a guarantee that such uses are appropriate in a particular user's case or that such uses do not infringe the patents or proprietary rights of any third party. The reproduction of any or all of the information contained in this leaflet is expressly forbidden without Graichen Produktions- und Vertriebs GmbH prior written consent.

© 2026 RESINWORK® is a registered trademark of Graichen Produktions- und Vertriebs GmbH, registered in Germany.