

INTRODUCING

MODEL 4

3D Photopolymer Dental resin
for vacuum/pressure thermoforming

IPA Washable


Compatible with most:

**LCD/DLP/SLA
365-405 nm**

**IPA
Washable**

**Anti-Stick
Formula**

**High Heat
Resistance**

**Fast
Curing**

**High Accuracy &
Consistent Models**

**Low
Shrinkage**

Advanced Thermoforming Resin

Resinwork® Model 4 is an advanced, IPA washable 3D printing resin engineered specifically for dental thermoforming applications. Designed to deliver high thermal resistance and dimensional accuracy, Model 4 ensures reliable performance under vacuum and pressure forming conditions.

Formulated with Resinwork's proprietary Anti-Stick Surface Chemistry, Model 4 enables effortless removal of thermoformed appliances—such as retainers, aligners, nightguards, and sportguards—without damage to the model or appliance. This unique surface release property significantly reduces the risk of breakage and enhances workflow efficiency in dental labs.

Unlike conventional resins, Model 4 features a stable, matte finish that resists sticking to heated substrates and ensures consistent results. Its high pigment stability eliminates the need for frequent mixing.

Whether you're fabricating clear aligners or custom appliances, Resinwork® Model 4 is your go-to solution for dependable, lab-grade performance.

In addition, Resinwork® Model 4 delivers outstanding print precision and dimensional fidelity while remaining cost-efficient for everyday lab production. Its optimized formulation supports consistent print quality across multiple builds, making it suitable not only for dental workflows but also for a wide range of high-precision 3D printing applications.

Aquaforge Almond



Birch Beige



Aquaforge Grey



Features

Strength

High structural strength ensures durable models without deformation.

Accuracy

Excellent dimensional accuracy for reliable dental models.

Precision

Sharp details and fine surface reproduction.

Cost Efficiency

Provides performance while remaining economical for everyday lab production.

Versatile Applications

Suitable for dental and other high-precision 3D printing applications.

Physical & Chemical Properties

Appearance	Liquid
Colour	Almond, Beige, Grey, White
Odour	Almost odourless

Chemical Composition	Mixture of oligomers and additives
Basic	Proprietary

Viscosity, 25°C	430 mPas
-----------------	----------

Density (Liquid Resin)	1.10 g/cm ³
Density (printed part)	1.25 g/cm ³

Tensile Properties

Tensile Strength	65 MPa
Elongation at break	5%
E modulus	1100 MPa

Flexural Properties

Flexural Modulus	3000 MPa
Flexural Strength	125 MPa

Others

Hardness Shore D	80D
Water absorption, short term (24h)	1.25%


Thermal Properties

HDT	66°C
-----	------

Packaging & Order Instructions

SKU	Colour	Pack Size / Case
2511-0446	Birch Beige	1 kg / 4
2511-0444	Aquaforge Grey	1 kg / 4
2511-0445	Aquaforge Almond	1 kg / 4

Colours Available



Manufactured & Marketed by:
Graichen Produktions- und Vertriebs GmbH
 Darmstädter Str. 127, 64625 Bensheim, Germany

Sales: Tel +49 6251 770 788-0
 info@graichen-bensheim.de

The above details have been compiled to the best of our knowledge on the basis of tests and research work and with regard to the current state of our practical experience. This technical product information is non-binding. No liabilities or guarantees deriving from or in connection with this leaflet can be imputed to us. Statements relating to possible uses of the product do not constitute a guarantee that such uses are appropriate in a particular user's case or that such uses do not infringe the patents or proprietary rights of any third party. The reproduction of any or all of the information contained in this leaflet is expressly forbidden without Graichen Produktions- und Vertriebs GmbH prior written consent.

© 2026 RESINWORK® is a registered trademark of Graichen Produktions- und Vertriebs GmbH, registered in Germany.