



KA997

Alumina (Al₂O₃) 99.7%

KEY PROPERTIES

- Excellent abrasion resistance
- Excellent dielectric properties
- High corrosion resistance
- Good thermal conductivity

APPLICATIONS

- Labware
- Furnace construction
- Abrasives industry
- Machinery parts
- Ballistic protection
- Chemical industry

MAIN PROPERTIES

Property	Value	Unit
Density	3.9	g/cm ³
Flexural Strength	350	MPa
Hardness	16	GPa
Fracture Toughness	3.5	MPa·Vm
Young Modulus	370	GPa
Thermal Conductivity (100°C)	30	W/m·K
CTE (20–1000°C)	8.6	x10 ⁻⁶ K ⁻¹

* All properties measured at 20°C unless otherwise stated.

** Measured in a wall thickness of 2 mm

OPERATING CONDITIONS

Max working temp (air)		1550	°C
Recomended temp		<1500	°C
Continuous temp		1400	°C

ELECTRICAL BEHAVIOR

Resistivity (25°C)		>1E14	Ω·cm
Dielectric strength		~15 kV/mm	

MATERIAL INFORMATION

Material type		Al ₂ O ₃
Machinability		Medium
Structure		Dense ceramic
Purity		99.7%
Color		Ivory

Local overheating may occur at electrical contact points due to current concentration and geometry effects.

The information provided is for guidance only and does not constitute a guarantee.

Nanoker Research S.L.

Polígono de Olloniego, Parcela 21A, Nave 4-8, 33660, Oviedo (Asturias), Spain

(+34) 985 20 76 13 | info@nanoker.com