

Tek-Clean RC

Rust remover and converter



Technical Data Sheet

Description

Tek-Clean RC is a single component acidic solution specially formulated to remove rust from metal surfaces without any mechanical methods. **Tek-Clean RC** removes rust and converts the residue to a phosphate protective coating appropriate for priming or painting.

Advantages

- Single component
- Easy to use
- Fast drying

Uses

- Rust removal
- Converts rust to a mild phosphate coating to allow priming or painting

Physical Properties

PROPERTY	TYPICAL RESULTS
Appearance	Clear liquid
Density	1.30
*The above properties are average laboratory values	

Packing

Tek-Clean RC is available in 1 and 5 lt. packs.

Shelf Life

24 months when stored in cool dry environment in factory packed unopened containers between 5oC – 25oC.

Installation Guidelines

Spraytek provides detailed method statements on all its products for use in various applications. These must be referred to prior to starting the work. The information below is a summary intended for guidance only.

Application

Apply to the rusted areas and leave the applied surfaces for 15 minutes. The **Tek-Clean RC** applied areas should

be converted to a phosphate protective coating. If rust is still visible, apply the second coat and leave it for another 15 minutes. Clean any loose particles with a light water wash.

Technical Support

Spraytek offers full technical support package to specifiers, contractors and end users, as well as technical assistance on site and after sales consultations.

Health & Safety

As with all chemical products, caution should always be exercised. Protective clothing, such as gloves and goggles, should be worn. See packaging/MSDS for specific instructions.

Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.

Reference #	TDS / STC /TCRC
Issue Date:	01/2012
Revision #	0

The information contained herein is to the best of our knowledge, belief, and accuracy. However, hence the conditions of handling and usage beyond our control. We make no warrantee of results, and assume no responsibility or liability for any damages or consequential damage incurred by the use of the product. Our products are sold on the condition that the user shall evaluate them, as well as our recommendations. To determine their suitability for a particular purpose. The user is solely responsible for the selection of Spraytek products.



Spraytek Coatings LLC

P.O. Box 27356, Dubai, U.A.E. , Tel.: +9714 2221432, Fax: +9714 2275750, Email: info@spraytek.ae

www.spraytek-me.com