





中国认可 国际互认 检测 TESTING CNAS L0599

Test Report SL52025257977001TX Date:May 22,2020 Page 1 of 4

NANNING TECBOD BIOLOGICAL TECHNOLOGY CO.,LTD.

ROOM 601 FLOOR 6, B2 BUILDING, NO 19 GUOKAI DADAO, NANNING, GUANGXI, P.R.CHINA

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Disposable Medical Isolation Gown:Nonwovens are used as the main raw

materials, which are made by cutting and sewing.non sterile, disposable. Used for

general isolation in out-patient, ward and laboratory of medical institution.

Style No. : XL

Composition : (A)non-woven fabric
Sample Color : (A)white non-woven fabric

Manufacturer : Nanning TECBOD Biological Technology Co.,Ltd.

Proposed Care Instruction: -

Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : Apr 13, 2020

Testing Period : Apr 15, 2020 - May 22, 2020

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Comment

	EN 13034:2005+ A1:2009 (Type 6)	EN 14126:2003/ AC:2004
Abrasion Resistance	Class 1	
Compression-Folding (Schildknecht) Flex Cracking	Class 6	
Resistance		
Compression-Folding	Class 6	Referring to
(Schildknecht) Flex Cracking		Type 6
Resistance at -30℃		comment
Trapezoidal Tear Resistance	Class 2	
Tensile Strength	Class 1	
Puncture Resistance	Class 1	
Seam Strength	Class 3	

Signed for and on behalf of

SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Sara Guo (Account Executive)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rdBuilding,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666 f (86-21) 64958763 f (86-21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com



Test Report

SL52025257977001TX

Date:May 22,2020

Page 2 of 4

Test Result

<u>Protective Clothing Against Chemicals — Test Methods and Performance Classification of Chemical Protective Clothing Materials, Seams, Joins and Assemblages</u>

(EN 14325:2018)

Clause 4.4 Abrasion Resistance

(EN ISO 12947-2:2016; Martindale Abrasion & Pilling Tester, Pressure: 9kPa, Grit 240 abrasion paper.)

(A)

<u>As Received</u>	No. 1	No. 2	No. 3	No. 4	Minimum
The quoted result(Rubs)	23	53	60	80	23

Recommended Class: 1

Remark:

- 1. Visual examination is used for damage assessment after abrasion. If the assessment is performed through visual inspection, the maximum classification that can be claimed is a Class 3.
- 3. Classification of abrasion resistance: Class 1 >10rubs; Class 2 >40rubs; Class 3 >100rubs; Class 4 >400rubs; Class 5 >1000rubs; Class 6 >2000rubs.

Clause 4.5 Compression-Folding (Schildknecht) Flex Cracking Resistance

(EN ISO 7854:1997, Method B;)

(A)

As Received	No. 1	No. 2	No. 3	Minimum
Warp/Lengthwise(Cycle s)	>50000	>50000	>50000	>50000
Weft/Widthwise(Cycles)	>50000	>50000	>50000	>50000

Recommended Class: 6

Remark:

- 1) Visual examination is used for damage assessment after flex cracking. Visual inspection shall not be used for the performance classification of Type 1 through Type 3(EN 943-1, EN 943-2, EN 14605)
- Classification of leak tightness after compression-folding(Schildknecht) flex cracking resistance: Class 1 >500cycles; Class 2 >1250cycles; Class 3 >3000cycles; Class 4 >8000cycles; Class 5 >20000cycles; Class 6 >50000cycles.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rd Building,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666 f (86–21) 64958763 f (86–21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com



Test Report SL52025257977001TX Date: May 22,2020 Page 3 of 4

Clause 4.6 Compression-Folding (Schildknecht) Flex Cracking Resistance at -30°C

(EN ISO 7854:1997, Method B;)

(A)

As Received	No. 1	No. 2	No. 3	Minimum
Warp/Lengthwise(Cycle s)	>4000	>4000	>4000	>4000
Weft/Widthwise(Cycles)	>4000	>4000	>4000	>4000

Recommended Class: 6

Remark:

- 1) Visual examination is used for damage assessment after flex cracking. Visual inspection shall not be used for the performance classification of Type 1 through Type 3(EN 943-1, EN 943-2, EN 14605)
- Classification of compression-folding(Schildknecht) flex cracking resistance at low temperatures: Class 1 >100cycles; Class 2 >200cycles; Class 3 >500cycles; Class 4 >1000cycles; Class 5 >2000cycles; Class 6 >4000cycles.

Clause 4.7 Trapezoidal Tear Resistance

(EN ISO 9073-4:1997;)

(A)

As Received	No. 1	No. 2	No. 3	No. 4	No. 5	Minimum
Warp/Length Yarns Torn(N)	57	53	56	56	64	53
Weft/Width Yarns Torn(N)	26	35	31	28	35	26

Recommended Class: 2

Classification of trapezoidal tear resistance: Class 1 >10N; Class 2 >20N; Class 3 >40N; Class 4 >60N; Class 5 >100N; Class 6 >150N.

Clause 4.9 Tensile Strength

(EN ISO 13934-1:2013; CRE - 2" Strip)

(A)

As Received	No. 1	No. 2	No. 3	No. 4	No. 5	Minimum
Warp/Length(N)	89	92	88	87	85	85
Weft/Width(N)	42	44	44	44	43	42

Recommended Class: 1

Remark:

Classification of tensile strength: Class 1 >30N; Class 2 >60N; Class 3 >100N; Class 4 >250N; Class 5 >500N; Class 6 > 1000N.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 中国·上海·徐汇区宜山路889号3号楼 邮编: 200233

t (86-21) 61402666 t (86-21) 61402666

f (86-21) 64958763 f (86-21) 64958763 e sgs.china@sgs.com



Test Report SL52025257977001TX Date:May 22,2020 Page 4 of 4

Clause 4.10 Puncture Resistance

(EN 863:1995;)

(A)

As Received No. 1 No. 2 No. 3 No. 4 No. 5 Minimum 9 8 8 Puncture Force(N) 8

Recommended Class: 1

Remark:

Classification of puncture resistance: Class 1 >5N; Class 2 >10N; Class 3 >50N; Class 4 >100N; Class 5 >150N; Class 6 >250N.

Clause 5.5 Seam Strength

(EN ISO 13935-2:2014)

	# 1	# 2	# 3	Average
Side seam(N)	78(F.R.)	86(F.R.)	72(F.R.)	79(F.R.)
Sleeve seam(N)	102(F.R.)	114(F.R.)	119(F.R.)	111(F.R.)
In-side seam(N)	91(F.R.)	91(F.R.)	80(F.R.)	88(F.R.)
Back rise seam(N)	69(F.R.)	83(F.R.)	83(F.R.)	78(F.R.)
Danaman dad Olasa	• • •	, ,	, ,	, ,

Recommended Class

F.R. = Fabric Rupture Notes

Remark:

Classification of seam strength: Class 1 >30N; Class 2 >50N; Class 3 >75N; Class 4 >125N; Class 5 >300N; Class 6 >500N.





The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration.

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rdBuilding,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666

f (86-21) 64958763 f (86-21) 64958763 e sgs.china@sgs.com