



UNIVERSITÀ DI PISA

Mott localisation, antiferromagnetism and nematic superconductivity in the extended Hubbard model with non-local pairing

Candidato:

Alessandro Gori

Relatore:

Prof. Giacomo Mazza

Outline

1. Cuprates and Hubbard physics
2. The Hartree-Fock method
3. The normal phase
4. The antiferromagnetic phase
5. The superconducting phase
6. Conclusions and outlook

Cuprates and Hubbard physics

The timeline of superconductivity




Figure 1: Timeline of the discoveries of superconductivity in various compounds. The cuprates branch is represented as cyan diamonds. Image source: P. Ray and O. Gingras, distributed according to [the license CC BY-SA 4.0](#).

The timeline of superconductivity




Figure 1: Timeline of the discoveries of superconductivity in various compounds. The cuprates branch is represented as cyan diamonds. Image source: P. Ray and O. Gingras, distributed according to [the license CC BY-SA 4.0](#).

The timeline of superconductivity




Figure 1: Timeline of the discoveries of superconductivity in various compounds. The cuprates branch is represented as cyan diamonds. Image source: P. Ray and O. Gingras, distributed according to [the license CC BY-SA 4.0](#).

The timeline of superconductivity




Figure 1: Timeline of the discoveries of superconductivity in various compounds. The cuprates branch is represented as cyan diamonds. Image source: P. Ray and O. Gingras, distributed according to [the license CC BY-SA 4.0](#).

The phase diagram of cuprates

Cuprates are the prototypical example of **strongly correlated materials**:

- ◇ **Antiferromagnetism** at null and low doping;
- ◇ ***d*-wave superconducting** domes.

Both arise from **strong electronic correlations**.



Failure of band theory in microscopic description.




Figure 2: Schematic phase diagram of cuprates.
Author: Holger Motzkau, [Wikimedia commons](#),
distributed according to [the license CC BY-SA 4.0](#)

These materials are stackings of:

- ◇ 2D copper oxide active layers;
- ◇ intermediate layers of inert material.




Figure 3: Sketch of a typical cuprate.

The single-band Hubbard model on the square lattice

$$\hat{H}_{\text{HM}} = \underbrace{-t \sum_{\langle ij \rangle} \sum_{\sigma} \hat{c}_{i\sigma}^{\dagger} \hat{c}_{j\sigma}}_{\text{Kinetic operator}} + \underbrace{U \sum_i \hat{n}_{i\uparrow} \hat{n}_{i\downarrow}}_{\text{On-site repulsion}} \quad \text{with } t, U > 0.$$

$$\hat{H}_{\text{HM}} = -t \sum_{\langle ij \rangle} \sum_{\sigma} \hat{c}_{i\sigma}^{\dagger} \hat{c}_{j\sigma} + U \sum_i \hat{n}_{i\uparrow} \hat{n}_{i\downarrow} \quad \text{with } t, U > 0.$$

Despite its simplicity, the Hubbard model describes:


- ◊ Insulation at half-filling (**Mott localisation**);
- ◊ **Antiferromagnetism** induced by Mott localisation;
- ◊ ***d*-wave superconductivity** emerging by doping the antiferromagnetic phase.

What is the origin of the insulating state at half-filling?

The Hubbard model at strong coupling,

$$t \ll U,$$

describes the **Mott insulator** state.




What is the origin of the insulating state at half-filling?

The Hubbard model at strong coupling,

$$t \ll U,$$

describes the **Mott insulator** state.



Mott localisation: a many-body insulator

What is the origin of the insulating state at half-filling?

The Hubbard model at strong coupling,


$$t \ll U,$$

describes the **Mott insulator** state.




Mott insulation mechanism

Electrons are **localised** as in a sort of “traffic jam”.




What is the origin of the antiferromagnetic ordering?




Antiferromagnetism in the undoped Hubbard model

What is the origin of the antiferromagnetic ordering?




Example: 2 sites, 2 electrons

At $U \gg t$, singlet pairing is energetically favoured:




What is the origin of the antiferromagnetic ordering?




Example: 2 sites, 2 electrons

At $U \gg t$, singlet pairing is energetically favoured:




Antiferromagnetism in the undoped Hubbard model

What is the origin of the antiferromagnetic ordering?




Example: 2 sites, 2 electrons

At $U \gg t$, singlet pairing is energetically favoured:




How does superconductivity emerge from doping the AF state in the Hubbard model?




Superconductivity emerges from attractive interaction between electrons.

How does superconductivity emerge from doping the AF state in the Hubbard model?




Superconductivity emerges from attractive interaction between electrons.

How does superconductivity emerge from doping the AF state in the Hubbard model?




Superconductivity emerges from attractive interaction between electrons.

How does superconductivity emerge from doping the AF state in the Hubbard model?



Superconductivity emerges from attractive interaction between electrons.

How does superconductivity emerge from doping the AF state in the Hubbard model?




Superconductivity emerges from attractive interaction between electrons.

Neighbouring electrons with opposite spin
“move together”:



Effective attractive interaction...

How does superconductivity emerge from doping the AF state in the Hubbard model?



Superconductivity emerges from attractive interaction between electrons.

Neighbouring electrons with opposite spin
“move together”:



Effective attractive interaction... favoured by doping.




Figure 5: Image source: Hari Padma et al., 2025. *Physical Review X* 15 (2): 021049.

Observed: incompatibilities of the Hubbard model with the spectrum of magnetic excitation in cuprate $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$.

Recent developments: the extended Hubbard model




Figure 5: Image source: Hari Padma et al., 2025. *Physical Review X* 15 (2): 021049.

Observed: incompatibilities of the Hubbard model with the spectrum of magnetic excitation in cuprate $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$.



Proposal: extension of the model with a **non-local attraction**,

$$\hat{H}_{\text{EHM}} = \hat{H}_{\text{HM}} - V \underbrace{\sum_{\langle ij \rangle} \hat{n}_i \hat{n}_j}_{\hat{H}_V}.$$

$\hat{H}_V$ can act as an independent source of *d*-wave superconductivity.

The model (EHM):

$$\hat{H}_{\text{EHM}} = \underbrace{-t \sum_{\langle ij \rangle} \sum_{\sigma} \hat{c}_{i\sigma}^{\dagger} \hat{c}_{j\sigma}}_{\text{Kinetic operator}} + \underbrace{U \sum_i \hat{n}_{i\uparrow} \hat{n}_{i\downarrow}}_{\text{Local repulsion}} - \underbrace{V \sum_{\langle ij \rangle} \hat{n}_i \hat{n}_j}_{\text{Non-local attraction}} \quad \text{with } t, U, V > 0.$$

The motivation: compatibility with some aspects of cuprates physics, including d -wave superconductivity.

The target: understand how the new interaction relates to Mott physics, antiferromagnetism and superconductivity.

The method: Hartree-Fock variational method, at low temperature.

The Hartree-Fock method

The constrained minimisation framework

We want to approximate the true ground state $|\Psi_0\rangle$ of the EHM, with energy E_0 .

Variational principle:

$$\forall |\Phi\rangle \in \mathcal{S} \subset \mathcal{H} : E[\Phi] \geq E_0.$$

$\Downarrow$

Constrained minimisation procedure

$$|\Psi\rangle : \left. \frac{\delta E[\Phi]}{\delta |\Phi\rangle} \right|_{|\Phi\rangle=|\Psi\rangle} = 0.$$

The state $|\Psi\rangle$ is the best approximation to $|\Psi_0\rangle$ inside of $\mathcal{S}$.




Figure 6: Sketch of the Hilbert space $\mathcal{H}$ and a subset $\mathcal{S}$.

The Hartree-Fock subspace of states

$\mathcal{S}$ is the set of all **gaussian states**,

$$|\Psi\rangle = \bigotimes_{\alpha} \hat{\gamma}_{\alpha}^{\dagger} |\Omega_{\gamma}\rangle, \quad \left\{ \hat{\gamma}_{\alpha}, \hat{\gamma}_{\beta}^{\dagger} \right\} = \delta_{\alpha\beta},$$

with $\hat{\gamma} \leftrightarrow \hat{c}$ through a unitary map.

The Hartree-Fock subspace of states

$\mathcal{S}$ is the set of all **gaussian states**,

$$|\Psi\rangle = \bigotimes_{\alpha} \hat{\gamma}_{\alpha}^{\dagger} |\Omega_{\gamma}\rangle, \quad \left\{ \hat{\gamma}_{\alpha}, \hat{\gamma}_{\beta}^{\dagger} \right\} = \delta_{\alpha\beta},$$

with $\hat{\gamma} \leftrightarrow \hat{c}$ through a unitary map.



Each gaussian state can be identified **uniquely** by fixing

$$\Delta_{\alpha\beta}^{+-} = \langle \hat{c}_{\alpha}^{\dagger} \hat{c}_{\beta} \rangle, \quad \Delta_{\alpha\beta}^{++} = \langle \hat{c}_{\alpha}^{\dagger} \hat{c}_{\beta}^{\dagger} \rangle.$$

These are the **variational parameters** collected in the vector $\mathbf{v}$. We aim to find the optimal $\mathbf{v}$, such that

$$|\Psi[\mathbf{v}]\rangle \simeq |\Psi_0\rangle.$$

Phase transition: spontaneous breaking of some symmetries of the model.

Phase X : shows symmetries $Y, Z \dots$



Restrict to $\mathcal{P} \subset \mathcal{S}$, gaussian states with symmetries $Y, Z \dots$



Symmetry selection rules on $\mathbf{v}$ entries.





Figure 7: Sketch of the Hilbert space $\mathcal{H}$, the subset $\mathcal{S}$ of gaussian states and the subset $\mathcal{P}$.

Identify symmetries $\rightarrow$ Derive $\mathbf{v}$ $\rightarrow$ Solve the variational problem.

The spatial symmetry channels

It is useful to introduce five spatial symmetry channels:



Function f on NNs: decomposition in harmonics $f^{(\gamma)}$.

The normal phase

The variational problem for the normal phase

Normal phase: no broken symmetries. Just one variational parameter,

$$\mathbf{v} = \left[u^{(s^*)} \right],$$

where $u^{(s^*)}$ is the s^* -wave component of $u_{\mathbf{k}\sigma} \equiv \langle \hat{c}_{\mathbf{k}\sigma}^\dagger \hat{c}_{\mathbf{k}\sigma} \rangle$.

$\Downarrow$

Renormalisation of kinetics

Hopping amplitude is **isotropically renormalised**,


$$t \rightarrow \tilde{t}^{(s^*)} \equiv t - \frac{u^{(s^*)}V}{2},$$

with the **theoretical constraint**:


$$0 < \tilde{t}^{(s^*)} < t \quad \implies \quad \text{Possible Mott localisation.}$$

Complete flattening of bare bands

In (δ, V) plane, we have determined theoretically the presence of a Mott critical boundary $V_c[\beta, \delta]$,



(a) Numerical results for $\tilde{t}^{(s^*)}$.



(b) Critical Mott boundary.

Within the Mott plateau, electrons are completely localised and **bands are flattened**.

The role of V/t :


- ◇ **Renormalise hopping;**
- ◇ **Induce complete Mott localisation:**

Effective kinetics energy scale $\ll$ Interaction energy scale .

The role of U/t :

- ◇ At HF level, U does not produce Mott localisation.

The antiferromagnetic phase



In cuprates, the AF phase is **commensurate**:

- ◇ 2-sites periodic in each direction;
- ◇ Sublattices oppositely magnetised;
- ◇ Zero net magnetisation.




Staggered magnetisation m :

$$2m = |\langle \hat{n}_{i\uparrow} \rangle - \langle \hat{n}_{i\downarrow} \rangle|,$$

with i a site.

Commensurate antiferromagnetism in cuprates



In cuprates, the AF phase is **commensurate**:

- ◇ 2-sites periodic in each direction;
- ◇ Sublattices oppositely magnetised;
- ◇ Zero net magnetisation.



Staggered magnetisation m :

$$2m = |\langle \hat{n}_{i\uparrow} \rangle - \langle \hat{n}_{i\downarrow} \rangle|,$$

with i a site.

Half-filling restriction

We limit to $\delta = 0$ (half-filling) due to **stability considerations**.

Variational parameters for the AF phase:

$$\mathbf{v} = \begin{bmatrix} m \\ u^{(s^*)} \end{bmatrix},$$

with $u^{(s^*)}$ defined as for the normal phase.

Renormalisation of kinetics

Mott localisation effect **formally** identical to the normal phase:

$$t \rightarrow \tilde{t}^{(s^*)} \equiv t - \frac{u^{(s^*)}V}{2},$$

with the **theoretical constraint**: $0 < \tilde{t}^{(s^*)} < t$.

The cooperation on magnetisation




Figure 9: Numerical results for m . The gray curves indicate isovalued lines.

The cooperation on magnetisation




Figure 9: Numerical results for m . The gray curves indicate isovalued lines.

$$U \gg V, t$$

“Conventional” Hubbard magnetisation, induced by the ratio U/t .

The cooperation on magnetisation





Figure 9: Numerical results for m . The gray curves indicate isovalues lines.

$$V \gg U, t$$

New “unconventional” source of magnetisation, induced by the ratio V/t .

The pairing enhancement of magnetisation




At low temperature:

$$m \simeq \frac{1}{2} + \mathcal{O}(r^2),$$

where $r = \tilde{t}^{(s^*)}/U$.

Figure 10: Numerical results for m (top) and $\tilde{t}^{(s^*)}$ (bottom). The gray curves indicate isovalues.

The pairing enhancement of magnetisation



At low temperature:

$$m \simeq \frac{1}{2} + \mathcal{O}(r^2),$$

where $r = \tilde{t}^{(s^*)}/U$.



To enhance m , either:

- ◇ Increase U ;
- ◇ **Decrease $\tilde{t}^{(s^*)}$** .

Figure 10: Numerical results for m (top) and $\tilde{t}^{(s^*)}$ (bottom). The gray curves indicate isovalued lines.

The role of V/t :

- ◇ **Renormalise hopping;**
- ◇ **Magnetise the lattice using Mott physics;**

The role of U/t :

- ◇ Magnetise the lattice, conventional Hubbard physics.



Cooperation among interactions to magnetise the lattice.

The superconducting phase

Cooper pairing:

- ◇ Described by a SC gap $\tilde{\Delta}_{ij}$, roughly the “binding energy” of the pairs;
- ◇ The pair spin obeys sum rules:

$$\frac{1}{2} \otimes \frac{1}{2} = 0 \oplus 1 = \text{singlet} \oplus \text{triplet}.$$

Cooper pairing:

- ◇ Described by a SC gap $\tilde{\Delta}_{ij}$, roughly the “binding energy” of the pairs;
- ◇ The pair spin obeys sum rules:

$$\frac{1}{2} \otimes \frac{1}{2} = \mathbf{0} \oplus 1 = \mathbf{singlet} \oplus \mathbf{triplet}.$$

$\Downarrow$

The singlet channel

The gap function is inversion symmetric, i.e. its harmonics are

$$\tilde{\Delta}^{(s)}, \quad \tilde{\Delta}^{(s^*)} \quad \text{and} \quad \tilde{\Delta}^{(d)}.$$

We limit to the **singlet channel**. Let the quantities:

$$u_{\mathbf{k}\sigma} \equiv \left\langle \hat{c}_{\mathbf{k}\sigma}^\dagger \hat{c}_{\mathbf{k}\sigma} \right\rangle, \quad w_{\mathbf{k}} \equiv \left\langle \hat{c}_{\mathbf{k}\uparrow}^\dagger \hat{c}_{-\mathbf{k}\downarrow}^\dagger \right\rangle.$$

Variational parameters: symmetric harmonics,

$$\mathbf{v} = \left(u^{(s^*)}, u^{(d)}, w^{(s)}, w^{(s^*)}, w^{(d)} \right)$$

The role of each parameter

- ◇ $u^{(s^*)}, u^{(d)}$: renormalisation of kinetics;
- ◇ $w^{(s)}, w^{(s^*)}$ and $w^{(d)}$: components of the SC gap.

Isotropic gap components:

$$\tilde{\Delta}^{(s^*)} = Vw^{(s^*)} \quad (\text{Mediated by the isotropic non-local attraction})$$

$$\tilde{\Delta}^{(s)} = -Uw^{(s)} \quad (\text{Mediated by the **local repulsion**})$$

Anisotropic gap component:

$$\tilde{\Delta}^{(d)} = Vw^{(d)} \quad (\text{Mediated by the isotropic non-local attraction})$$

The competition among gap components

Isotropic gap components:

$$\tilde{\Delta}^{(s^*)} = Vw^{(s^*)} \quad (\text{Mediated by the isotropic non-local attraction})$$

$$\tilde{\Delta}^{(s)} = -Uw^{(s)} \quad (\text{Mediated by the **local repulsion**})$$

Anisotropic gap component:

$$\tilde{\Delta}^{(d)} = Vw^{(d)} \quad (\text{Mediated by the isotropic non-local attraction})$$




Figure 11: Phase diagram for the SC phase.

In the SC phase, the renormalisation of t gives two components,

$$t \rightarrow \tilde{t}^{(s^*)} \equiv t - \frac{u^{(s^*)}V}{2} \quad \text{and} \quad \tilde{t}^{(d)} \equiv -\frac{u^{(d)}V}{2} .$$

The nematic order parameter

In the SC phase, the renormalisation of t gives two components,

$$t \rightarrow \tilde{t}^{(s^*)} \equiv t - \frac{u^{(s^*)}V}{2} \quad \text{and} \quad \tilde{t}^{(d)} \equiv -\frac{u^{(d)}V}{2}.$$




Figure 12: Sketch of nematic hopping.

Anisotropic hopping

Direction-resolved effective hopping:

$$\tilde{t}^{(x)} \equiv \frac{\tilde{t}^{(s^*)} + \tilde{t}^{(d)}}{2},$$

$$\tilde{t}^{(y)} \equiv \frac{\tilde{t}^{(s^*)} - \tilde{t}^{(d)}}{2}.$$

$\Downarrow$

$\tilde{t}^{(d)} \neq 0 \implies$ **nematic SSB.**

Symmetry mixing and insurgence of nematicity




Figure 13: Comparison of phase diagrams for the singlet SC phase and convergence values for the nematic order parameter.

Symmetry mixing and insurgence of nematicity




Figure 13: Comparison of phase diagrams for the singlet SC phase and convergence values for the nematic order parameter.

Symmetry mixing and insurgence of nematicity




Figure 13: Comparison of phase diagrams for the singlet SC phase and convergence values for the nematic order parameter.

The role of V/t :

- ◇ **Renormalise hopping anisotropically;**
- ◇ **Induce mixed-symmetry superconductivity;**
- ◇ **Induce nematic symmetry breaking.**

The role of U/t :

- ◇ **Participate in superconductivity even if locally repulsive.**

Conclusions and outlook

We wanted to understand how the new interaction relates to Mott physics, antiferromagnetism and superconductivity.

We conclude that at HF level, the non-local attraction:

- ◇ Acts as a source of Mott localisation;
- ◇ Enhances magnetisation at half filling;
- ◇ Can produce mixed-symmetry superconductivity;
- ◇ Can produce nematic superconductivity.

From here, we can follow various paths:

1. **Same model, other phases.**

Triplet superconductivity, breaking of translational invariance, nematic antiferromagnetism. . .

2. **Expand the model.**

Second nearest neighbours hopping, more refined potentials. . .

3. **More advanced numerical techniques.**

DMRG for chains and ladders; hybrid DMFT (local sector) and HF (non-local sector) to retrieve Mott physics induced by U . . .


That's all, thank you!

Backup 1: details on Mott localisation

Bands flattening: a signature of Mott localisation (1/2)

Renormalisation of electronic bands, $\epsilon_{\mathbf{k}\sigma} \rightarrow \tilde{\epsilon}_{\mathbf{k}\sigma}$:

$0 < \tilde{t}^{(s^*)} < t \implies$ **Flattening** of bands = Mott localisation.



Bands flattening: a signature of Mott localisation (2/2)




Figure 14: Image source: Gabriel Kotliar and Dieter Vollhardt, 2004. *Physics Today* 57 (March): 53–59.

As we increase the ratio U/t , the many-body DoS undergoes a transition:

- (a) Free model, conventional DoS;
- (b) Weak coupling, large coherent peak;
- (c) Intermediate coupling, **narrow coherent peak**;
- (d) Strong coupling, lower and upper Hubbard bands.



Localisation = flattening of bare bands.

Backup 2: details on the HF method

Hartree-Fock method: $\mathcal{S}$ is the set of all **gaussian states**, i.e. states that are non-interacting for some fermionic operators

$$|\Psi\rangle = \bigotimes_{\alpha} \hat{\gamma}_{\alpha}^{\dagger} |\Omega_{\gamma}\rangle, \quad \{\hat{\gamma}_{\alpha}, \hat{\gamma}_{\beta}^{\dagger}\} = \delta_{\alpha\beta},$$

with $\hat{\gamma} \leftrightarrow \hat{c}$ through a unitary map.



Wick's theorem: averages of quartic operators decompose nicely,

$$\langle \hat{c}_{\alpha}^{\dagger} \hat{c}_{\beta}^{\dagger} \hat{c}_{\gamma} \hat{c}_{\delta} \rangle = \underbrace{\langle \hat{c}_{\alpha}^{\dagger} \hat{c}_{\delta} \rangle \langle \hat{c}_{\beta}^{\dagger} \hat{c}_{\gamma} \rangle}_{\text{Hartree}} - \underbrace{\langle \hat{c}_{\alpha}^{\dagger} \hat{c}_{\gamma} \rangle \langle \hat{c}_{\beta}^{\dagger} \hat{c}_{\delta} \rangle}_{\text{Fock}} + \underbrace{\langle \hat{c}_{\alpha}^{\dagger} \hat{c}_{\beta}^{\dagger} \rangle \langle \hat{c}_{\gamma} \hat{c}_{\delta} \rangle}_{\text{Cooper}}.$$

The EHM hamiltonian is a quartic operator!

The self-consistency mapping

Each $|\Psi\rangle \in \mathcal{S}$ is uniquely defined by a particular choice of the **variational parameters** (HFPs)

$$\Delta_{\alpha\beta}^{+-} = \langle \hat{c}_{\alpha}^{\dagger} \hat{c}_{\beta} \rangle, \quad \Delta_{\alpha\beta}^{++} = \langle \hat{c}_{\alpha}^{\dagger} \hat{c}_{\beta}^{\dagger} \rangle.$$

Let $\mathbf{v}$ be the vector that collects all HFPs. We aim to find

$$|\Psi[\mathbf{v}]\rangle \simeq |\Psi_0\rangle,$$

with $\mathbf{v}$ such that:

Variational picture

Energy is minimised,

$$\left. \frac{\delta E[\Phi]}{\delta |\Phi\rangle} \right|_{|\Phi\rangle=|\Psi[\mathbf{v}]\rangle} = 0.$$

Self-consistency picture

A self-consistency problem is satisfied,

$$A(\mathbf{v}) = \mathbf{v},$$

being A a non-linear map **uniquely determined**.

The iterative algorithm (iHF)

The HF solution is the **fixed point** of a non-linear map A ,

$$A(\mathbf{v}) = \mathbf{v}.$$

$\Downarrow$

Strategy: “follow” the map up to the fixed point,

$$\mathbf{v}_{i+1} \equiv gA(\mathbf{v}_i) + (1 - g)\mathbf{v}_i.$$

with $i > 0$, $g \in [0, 1]$.

$\Downarrow$

Convergence criterion:

$$\forall j \quad : \quad [\mathbf{v}_{i+1} - \mathbf{v}_i]_j < \Delta v_j,$$

with $\Delta \mathbf{v}$ the vector of tolerances.

Example path (AF) ($t = 1.0$, $U = 3.0$, $V = 6.0$, $L = 128$, $\beta = 100.0$, $\delta = 0.0$)




Figure 15: Example path for the AF phase.

Backup 3: Mott localisation at higher temperature

Temperature dependence of Mott effects in the normal phase




Figure 16: Comparative plots of $\tilde{t}^{(s^*)}$ in the normal phase at various temperatures and dopings.

In the **normal phase**:

Increase in temperature $\implies$ Disruption of Mott effects

Backup 4: Mott localisation in AF and SC phases

Effective hopping is:

- ◇ reduced by V ;
- ◇ **increased** by U .



The two interactions
“oppose” each other.




Figure 17: Comparative plot of $\tilde{t}^{(s^*)}$ for normal and AF phase.




Figure 18: Comparative plot of $\tilde{t}^{(s^*)}$ for normal and AF phase.

Isotropic hopping
renormalisation:

$$\tilde{t}^{(s^*)} \equiv t - \frac{u^{(s^*)}V}{2}.$$

Formally identical to
normal and AF phases.

The effective hopping is mainly isotropic:

$$|\tilde{t}^{(s^*)}| \gg |\tilde{t}^{(d)}|.$$

Backup 5: energetic competition between AF and SC phases




Figure 19: Energy difference: SC versus AF phase.

By computing the free energy difference,

$$f^{(AF)} - f^{(SC)},$$

we identify a phase boundary. Possibly a critical ratio

$$\left(\frac{V}{U}\right)_c = k$$

exists?

The SC phase is dominant when $V \gg U, t$, the AF phase when $U \gg V, t$.

Backup 6: The origin of the $-V$ attraction

$$\hat{H}_V = -V \sum_{\langle ij \rangle} \hat{n}_i \hat{n}_j : \quad \text{Isotropic, spin independent attraction.}$$

Postulated: originated by e -ph Coulomb interaction. It is believed that this attraction is mediated by phonons (lattice vibrations).




Figure 20: Image source: Wang et al., *Phys. Rev. Lett.* 127: 197003