

Nii[®] FLOOR

4.5MM / 5.5MM

SPC FLOORING

Virgin Material



Type of Colour



Golden Oak

4.5MM F401

5.5MM F501



Beach Oak

4.5MM F402

5.5MM F502



Espresso Oak

4.5MM F403

5.5MM F503



Honey Pecan

4.5MM F404

5.5MM F504



Silver Oak

4.5MM F405

5.5MM F505



Chestnut Brown

4.5MM F406

5.5MM F506



Cherry Red

4.5MM F407

5.5MM F507



Golden Oak

4.5MM F401

5.5MM F501



Beach Oak

4.5MM F402

5.5MM F502





Silver Oak

4.5MM F405

5.5MM F505



Chestnut Brown

4.5MM F406

5.5MM F506



Cherry Red

4.5MM F407

5.5MM F507

	PRODUCT INFORMATION	
Construction	SPC Vinyl Flooring (Click)	
Material	100% Virgin PVC Power + Calcium carbonate	
Specifications	1220*184mm	
Thickness of SPC board	4.5mm	5.5mm
Wear Layer Thickness	0.2mm	0.3mm
Edge	Micro-bevel	
Emboss	Shallow emboss	
Locking System	Unilin	
Gloss Level	3°-5°; 5°-7°	
Installation	Click System	
Bevel	Four-sided micro bevel, Four-sided painted V-groove	


TEXTURE OPTIONS	Crystal
-----------------	----------------

PERFORMANCE	EN Norms	Result	ASTM Norms	Result
Dimension Squareness and Straightness	EN 427	Squareness:0.18mm Straightness:0.07mm		
Dimensional Stability and Curling	EN 434:1994	Stability:Pass 0.1% Curling:Pass 0.06mm	ASTM F1700:2004	PASS 0.013in/ft
Tolerance of Side Length	EN ISO 24342	≤0.15% , up to 0.5mm maximum		
Thickness	EN ISO 24346	3.99/4.00mm (+/- 0.01mm)		
Flexibility			ASTM F137:2008	Pass 100mm
Chemical Resistance	EN 423	Pass	ASTM F925	Pass
Resistant to Impact	EN 14617	Average 8.95J	ASTM F1265:2003A	Pass
Deflection	EN ISO 24344	MD: 9.05mm AMD:8.96mm		
Lock Strength	ISO 24334	Long side: f _{max} = 3.2kN/m Short side: f _{max} = 3.4kN/m		
Color Fastness to Artificial light	EN 20105:B02 method A	Pass, >=Grade6	ASTM F1515	Pass
Residual Indentation after static loading	EN 433	Pass, 0.06mm	ASTM F970	Pass
Slip Resistance	EN 13893	Class DS		
Behaviour to Fire	EN 13501-1	Bf1-S1	ASTM E648-10	Pass/Class 1
Smoke Density			ASTM E662	Pass, <=450
Wear Resistance	EN660-2:1999 /EN649-2011	Group T		
Sound insulation material performance test			ASTM E492-2009 ASTM E90-2009	IIC=68 STC=73
Heavy metal test	EN 12149	Not Detected		
Formaldehyde Test	GB 18580-2001	Not Detected		
Static Coefficient of Friction of Polish Coated Flooring Surfaces			ASTM D2047-11	Dry:0.38
				Wet:0.8
Thermal Resistance	EN12664	Pass 0.12K/W		

Floorscore Certificate



Dibt Certificate



CE Certificate



Quality Management System



SGS Certificates

