Novolen Polypropylene Plant - Monthly Batch QA Report

Report Period: August 2026 | Plant Capacity: 440 KTA (Novolen Gas-Phase, Ziegler-Natta)

1. Production Mix



2. Batch Quality Summary

Grade	Batches Produced	Avg MFI (g/10min)	Spec MFI Range	Density (g/cm3)	Off-Spec Batch
Homopolymer H030SG	22	3.4	3.0 - 3.8	0.905	0
Homopolymer H110F	16	11.2	10.0 - 12.0	0.905	1
Random Copolymer RP340	12	3.9	3.5 - 4.5	0.900	0
Impact Copolymer HP500	9	0.8	0.6 - 1.0	0.900	0

3. Off-Spec Batch Detail

Batch H110F-0847 (produced 2026-08-17) recorded MFI of 12.9 g/10min, above the upper spec limit of 12.0. Root cause: catalyst feed rate excursion during grade changeover from H030SG, duration

approximately 40 minutes before DCS alarm response. Batch downgraded to off-spec inventory; grade changeover checklist (see SOP reference) updated to add a hold point at the 20-minute mark for feed-rate confirmation.

This is a synthetic, illustrative document generated for RAG/retrieval testing purposes. It does not represent an actual MRPL internal document.