Blackwish 3D Printing Research Reference

Start here with the object you want, not the printer acronym.

This reference maps the major forms of additive manufacturing and the complete path from digital design to a finished object. It gives extra attention to miniatures, terrain, props and model generators, while also examining what 3D printing can and cannot contribute to electrical generators. It is a research guide, not a buying list or an operating manual.

Main conclusion: a convincing 3D model, a manufacturable print and a qualified functional object are three different claims. Good decisions keep those claims separate and include material handling, post-processing, inspection, rejected work and end of life.

Choose your route

I want figures or scenery. Read the selection matrix, miniature chapter, model-generator routes, and the display miniature example.

I want to understand all the technologies. Begin with the seven-family map, then follow the process chapters and the frontier survey. The map covers major families and important specialist domains, not every proprietary variant.

I mean an electrical generator. Read the generator evidence ladder before interpreting any claim that a machine is printed. Tooling, housings, tested active components and a qualified complete system are not interchangeable.

I want the safest useful next step. Define one object and its intended use; compare two suitable workflows; inspect a candidate design before committing to fabrication. Read safety, quality and full cost. No purchase is needed to use this reference.

How to read the evidence

Research was checked on **23 October 2026**. Linked source IDs link to a source and access ledger; ledger titles link to the original material. Government and research sources, vendor descriptions, limited extracts and original desk-study examples are labeled separately. No comparative physical print tests were conducted for this report.

The three Zen reviews and bounded Death Knell challenge are analytical structures, not quotations from recovered Blackwish canon. They do not ratify deployment. Originals remain preserved; any deployment requires the user's explicit manual ratification and appropriate technical safeguards.

Contents and reading map

Click a section title or use the PDF bookmarks. Page numbers refer to this PDF.

Pages	Section
3	Quick selection matrix
4	Seven process families
5 to 9	Extrusion, vat photopolymerization, powder bed fusion, jetting, DED and sheet lamination
10	Materials and design consequences
11	Miniatures terrain and props
12 to 13	Local and procedural generators, hosted character and AI services
14 to 15	Files and slicing, manufacturing and post-processing
16 to 19	Safety, quality, costs, lifecycle
20	Electrical generators and printed components
21 to 22	Industrial and medical specialisms, emerging forms
23 to 24	Miniature example, terrain generator example
25 to 28	Zen process review, Zen model review, Zen frontier review, Death Knell challenge
29	Glossary
30 to 35	Linked source and access ledger

Three questions that prevent most confusion

What is actually deposited: the finished material, a binder, a precursor or a sacrificial pattern? What still happens afterward: curing, sintering, casting, machining, assembly or qualification? What is the strongest claim the evidence supports: a picture, a model, a printed specimen, a tested component or a released system?

Navigation note: the footer on content pages returns to this contents page. Product names illustrate categories; they are not endorsements, checked purchase offers or universal performance rankings.

Quick selection matrix

Selection heuristics for narrowing a question, not universal rankings or guaranteed outcomes.

Intended object	Sensible starting routes	The issue to check first
Fine display miniature or sculpted bust	Vat photopolymerization; specialist fabrication service	Robust details, support contacts, complete cleaning and cure
Large terrain, buildings or storage	Material extrusion; mixed-process assembly	Feature size, visible stepping, fit and build time
Dimensioned insert or modular prop	Parametric CAD plus a suitable polymer process	Interfaces, clearance, orientation and repeatability
Functional nylon geometry	Polymer powder bed fusion	Powder evacuation, surface condition, finish and inspection
Complex metal component	Metal PBF; binder jetting plus sintering; casting or machining alternatives	Final material state, distortion, critical defects and qualification
Large metal repair or preform	DED or hybrid additive and machining	Interface integrity, thermal history and machining access
Colored or multi-material visual model	Material jetting or assembled models	Actual material behavior, support removal and aging
Casting mold, core or pattern	Sand binder jetting; wax/resin patterns	Foundry stages determine the final metal result
Electrical generator concept	Static cutaway, production aid or qualified component study	Which functions are printed and which evidence exists

These branches synthesize the process mechanisms and constraints described by NIST and manufacturer documentation. The right comparison includes conventional manufacture and external services, not just competing printers. PF02 PF03 PF25 PF28

Four inputs before choosing: intended use, critical dimensions and detail, likely consequences of failure, and the safe workflow actually available. A machine capable of the shape may still be the wrong route for the material, production volume or finishing burden.

No universal resolution shortcut: nominal layer height, nozzle size, screen pixels, repeatability and finished-part accuracy measure different things. A smooth surface can still be dimensionally wrong. PF09 PF12 W02

The seven process families

Organize the field by mechanism, then variant, material and complete production route.

Family	What creates the object	Familiar variants
Material extrusion	Material is dispensed through a nozzle or opening	FFF or FDM, pellet extrusion, direct ink writing
Vat photopolymerization	Light selectively solidifies liquid photopolymer	Laser SLA, DLP, LCD or MSLA
Powder bed fusion	Thermal energy fuses selected powder regions	Polymer SLS and MJF; metal LPBF and electron-beam PBF
Binder jetting	A liquid binder joins regions of a powder bed	Sand molds; metal or ceramic green parts
Material jetting	Droplets of build material are deposited	Photopolymer jetting; wax patterns; specialist inks
Directed energy deposition	Material is fused as it is deposited using focused thermal energy	Laser powder or wire DED; wire-arc AM
Sheet lamination	Sheets or foils are bonded into a stack	Laminated-object methods; ultrasonic metal-foil joining

The ISO catalog identifies ISO/ASTM 52900:2021 as reviewed and confirmed in 2025. Only its public catalog and abstract were available here, not the full paid standard. Public NIST material supplies the seven-family map. A NIST page describing six technologies in its facilities is not evidence that the standard has become a six-family system. PF01 PF02 PF03

Application domains overlap this map. Construction, clay, food and some bioprinting use extrusion; other biological and microfabrication routes use light or jetting. Multi-material and hybrid manufacture can cross boundaries. Volumetric methods also challenge a simple layer-by-layer mental model. PF34 F06 F09

Language discipline: say whether an object is directly printed, sintered from a printed intermediate, cast using printed tooling, or assembled using printed components. Each can be valuable; they are not equivalent manufacturing claims.

Material extrusion

A versatile family spanning familiar filament printers, large pellet systems and specialist pastes.

Material extrusion deposits material through a nozzle along a toolpath. Fused filament fabrication softens thermoplastic filament into roads or beads. FDM is a Stratasys trademark; FFF is a common generic label. Neither term identifies a machine's enclosure, temperature range or qualified material set. PF04 PF05

What it is good at

The family is a useful first branch for terrain, storage, larger models, fixtures, mockups and prototype enclosures. It also includes screw-driven pellet systems for larger forms and direct ink writing of shape-retaining pastes. Large-format extrusion is not simply a small detailed printer made bigger: feedstock, deposition rate, bead size and thermal behavior change. ORNL has investigated pellet-fed large-format composite manufacture. PF07

Materials and directional behavior

PLA, PETG, ABS or ASA, polyamides, flexible elastomers, polycarbonate and specialist high-temperature polymers are material classes, not interchangeable performance specifications. Grade, moisture, additives, orientation and processing matter. A filament described as carbon-fiber-filled usually remains a polymer composite. Chopped reinforcement and a separately laid continuous-fiber architecture are materially different; manufacturer claims must stay attached to the tested architecture. PF06 PF09

The finished geometry is not identical to an ideal toolpath. Flow and bead shape, bonding and thermal history affect features and directional properties. More infill does not automatically solve a poor load path or a weak interface. NIST's testing review is foundational rather than a current printer ranking. PF09 PF10

Hidden work and failure modes

Consider support access, overhangs, warping, thin walls, narrow gaps, surface texture and fit after finishing. Drying or other conditioning may be required for a particular feedstock. Material sold as metal-filled decorative plastic is not equivalent to a bound-metal system designed for later debinding and sintering; the latter produces an intermediate, not immediately a dense metal part. PF08

Decision rule: select extrusion because its whole route meets the object's requirements, not because it is perceived as universally safe or cheap. Emissions, hot surfaces, motion and finishing remain part of the safety assessment.

Vat photopolymerization

Often attractive for fine miniatures and smooth masters, with a substantial chemical and finishing workflow.

Light selectively solidifies liquid photopolymer. Laser SLA scans a spot; DLP projects an image; LCD or MSLA typically masks the exposure through an LCD. SLA is sometimes used loosely for the whole category, so specify the variant when comparing equipment. Continuous or reduced-separation implementations change mechanics and throughput without requiring a new top-level family. PF11

Detail is only one requirement

Faces, textures, jewelry masters and small display pieces make this a promising branch for miniature work. However, tiny visible detail can be fragile during washing, support removal, painting or handling. Tough, flexible, heat-resistant and castable formulations address different purposes. A descriptive material name is not a universal engineering guarantee.

Screen pixel count is not finished-part accuracy. The screen's area and pixel pitch matter, but reliable feature reproduction also depends on optics, exposure, resin behavior, geometry and processing. Formlabs' analysis is useful vendor evidence for the distinction, not an independent ranking of all printers. PF12

Plan the entire resin route

Orientation must balance visible surfaces, support contacts, unsupported islands, cross-sections and access for finishing. A pre-supported model is not certified for an arbitrary machine, resin, scaling factor or profile. There is no universal requirement to tilt every object by the same angle.

Hollowing a large model can save material, but every chamber must be accounted for. Drainage, washing and suitable final processing cannot be inferred from one external hole. Prusa's workflow recommends multiple drainage holes; that does not prove every compartment in an arbitrary model is reachable. Paint does not substitute for properly processed resin. MG16 W05

A different final material is possible

Ceramic-loaded photopolymer can hold ceramic particles in an organic network. Cleaning, debinding and sintering then create the ceramic object. Shrinkage and thermal processing are part of the manufacturing method, not optional finishing. Ceramic-filled polymer that retains its resin matrix is a different material. PF13 F08

Stop before fabrication if the exact resin's handling, wash, cure and disposal route cannot be supported by the workspace and applicable instructions.

Powder bed fusion

Polymer and metal variants share a family name but differ substantially in equipment, hazards and finishing.

A powder layer is spread and selected regions are thermally fused. Polymer selective laser sintering uses a laser. HP Multi Jet Fusion applies fusing and detailing agents and uses heat; despite the word jet, it belongs to powder bed fusion rather than material jetting or ordinary binder jetting. PF15 PF18

Polymer powder bed fusion

Nylon parts, selected elastomeric systems and filled polymers can benefit from complex geometry and nested builds. Surrounding powder supports much of the object, avoiding many attached sacrificial supports. That does not mean a sealed cavity can emerge clean and empty. Powder evacuation, accessible passages, cooling, surface texture, refresh rules and finishing must be planned. EOS describes production benefits for its own systems; those are not universal geometric allowances. PF16

This can be a useful service-bureau route for functional shapes that are awkward to support in extrusion or resin. Compare the delivered finish and dimensional acceptance, not only the raw print price. A rough surface or retained powder may make an otherwise clever design unsuitable.

Metal powder bed fusion

Laser powder bed fusion is a useful generic term. DMLS is EOS terminology within this family; the word sintering in a historical name does not establish that the metal never fully melts. Electron-beam PBF uses an electron beam rather than a laser. PF17 PF18

For metals, surrounding powder does not replace every thermal or mechanical support. Residual stress, distortion, porosity, microstructure and surface condition can determine performance. Stress relief, support removal, machining and specialist inspection may dominate the finished-part schedule. In a NIST titanium study, a common scan strategy did not reduce residual stress as expected: an important counterexample to universal best-setting claims. PF20

Boundary: this is an industrial manufacturing route, not a household powder-handling recipe. Combustible powders, energy sources and atmosphere control require suitable facilities. A printable internal channel must also be cleanable and inspectable for its intended service. W07

Binder jetting and material jetting

Ask what the printhead deposits: an agent into existing powder, or the object material itself.

Binder jetting

A printhead selectively deposits binder into a powder bed. Sand binder jetting produces molds and cores used in subsequent metal casting. Metal and ceramic systems often produce fragile green parts that require downstream densification. HP Metal Jet belongs here, unlike polymer Multi Jet Fusion. PF21 F07

Separating shaping from furnace processing can suit packed batches, but printing is not the final material transformation. Excavation, handling strength, binder removal, sintering, shrinkage and distortion all matter. Automated shrinkage compensation is a design tool, not proof that every new geometry will meet tolerance. Infiltration, where used, changes the resulting material system. PF22 PF23

Material jetting

Here the droplets are the build material itself. Photopolymer jetting deposits resin that is cured; wax jetting produces patterns. PolyJet and MultiJet Printing are commercial labels, not separate standard families. Multiple colors or material behaviors can help create visual demonstrators, transparent sections and tactile prototypes. PF25 PF27

Rubber-like photopolymer does not automatically replace an engineering elastomer. Support removal and aging remain important. Many digital blends do not equal the same number of independently qualified structural materials. PF26

Indirect manufacture is still important

Wax or castable-resin patterns can support investment casting of jewelry, detailed miniature metal objects and industrial parts. The final metal is cast; its condition depends on foundry stages as well as the pattern. Printed sand cores can create internal passages in large castings. These indirect routes may be more useful than direct metal AM for a particular generator housing or decorative object. PF28 F07

Comparison rule: compare finished objects of equivalent material, condition and accepted quality. Do not compare a green part, an uncleaned model and a machined final casting as though they were the same deliverable.

DED sheet lamination and hybrid manufacture

Additive manufacturing includes repair, near-net preforms and bonded foils, not only complete objects printed from an empty build plate.

Directed energy deposition

DED feeds material into a localized deposition zone where thermal energy fuses it. Variants include laser powder deposition, laser wire deposition, electron-beam wire methods and wire-arc additive manufacturing. Wire-fed describes the feedstock, not the energy source. NASA's electron-beam freeform fabrication is distinct from electron-beam powder-bed fusion. F17 PF29

DED can add features to an existing object, repair selected regions or make large near-net shapes. Its appeal may be efficient stock placement rather than a final polished surface. Thermal distortion, reachable geometry, interface condition, later machining and inspection determine whether the route is useful. Manufacturer descriptions of wire-arc AM establish a process offering, not independent proof of every economic claim. PF30

A repaired region and its interface with the original material both matter. The fact that a surface accepts deposition is not authorization to repair a critical part without its design authority and acceptance requirements.

Sheet lamination

Sheets or foils are bonded into a three-dimensional stack with shaping incorporated into the route. Historical approaches include paper and polymer sheets. Ultrasonic additive manufacturing joins metal foil using pressure and ultrasonic motion; it is explicitly described as sheet lamination by Fabrisonic. This is a reminder that not all metal AM relies on melting. PF31

Layered material combinations and embedded features can be useful, but bond integrity, layer interfaces, cutting or milling access and extraction of waste constrain the design. It should not be dismissed as merely paper modeling or promoted as an unrestricted way to combine any two metals.

Hybrid is a production strategy

A hybrid route may print a preform, machine precision interfaces and assemble conventional components. A printed casting pattern is another combined production chain. The honest question is not how much of an object can be labeled printed, but whether the manufacturing contribution improves the required result with acceptable cost and evidence.

For generator-related components, this page supplies a conceptual map only. Rotating, pressure-bearing, high-temperature or electrical service requires separate qualified review.

Materials and design consequences

The material name is only the beginning of the specification.

A useful identity is **composition and grade + manufacturing history + orientation + post-processing + service environment**. A catalog property from one specimen direction or conditioning state is not a guarantee for every printed geometry. NIST treats material, machine, process and part characterization as connected questions. PF09 W02

Material class	Opportunities	Questions to resolve
Thermoplastics	Prototypes, fixtures, terrain, selected functional parts	Heat, creep, moisture, bonding and directional behavior
Photopolymers	Fine detail, smooth masters, special optical or flexible behavior	Processing completeness, aging, brittleness and intended-use limits
Composites	Stiffness or other tailored properties	Filler architecture, fiber direction, interfaces and finishing
Metals	Complex engineering geometry and repair	Defects, residual stress, microstructure, surface and fatigue evidence
Ceramics	Complex hard or thermally capable shapes	Green handling, shrinkage, sintering and brittle features
Pastes and biological materials	Clay, food, cementitious and tissue-related forms	Rheology, subsequent transformation and domain-specific acceptance

The table is a screening synthesis, not a material-selection specification. Technical data sheets describe performance under stated conditions; safety data sheets describe hazards and handling information. Neither substitutes for the other. W06

Geometry changes the answer

Supports, cavities, channels, lattices, overhangs, thin walls and interfaces must suit the selected process. A closed mathematical surface can trap powder or liquid. A lattice can save mass yet be impossible to clean or inspect adequately. Orientation trades surface appearance against load paths, support burden, distortion and build height.

Shrinkage can come from cooling, polymerization or sintering, and each mechanism needs its own evidence. Do not apply one generic percentage to every process. Tolerance is a requirement to verify on the final object, not a synonym for layer height. PF13 PF22 W02

Miniatures terrain and props

Divide the job into organic detail, larger scenery and dimensionally controlled interfaces.

Miniatures include people, animals, original creatures, railway scenes, architecture, vehicles, educational exhibits, dollhouse furniture and game pieces. Props, scenic bases, signs, furniture and storage are part of the same ecosystem. A hybrid scene can use one process for detailed figures and another for large scenery.

Scale and robustness

A label such as 28 mm or 32 mm is not a universal measurement convention. Record whether height refers to eyes, head, overall figure or a base-inclusive dimension. For an explicit scale, a hypothetical 1.80 m person at 1:60 is 30 mm before the base. That arithmetic does not prove any commercial 30 mm figure uses 1:60.

Scaling changes walls, lettering, gaps and pins as well as overall height. For a geometrically similar solid object, doubling linear dimensions increases volume eightfold. Hollowing or holding wall thickness constant changes that relationship. Keep nominal size, intended clearance and finish thickness separate.

Match the geometry to the process

Vat photopolymerization is often a useful starting route for fine faces and texture; extrusion often suits larger walls, terrain and storage. Chunky stylized figures can also suit extrusion. Prusa's miniature demonstration is a process-specific example, not a guarantee that its nozzle or settings fit another machine. Reducing layer height alone does not make a narrow horizontal feature printable. MG17

Inspect support contacts on visible surfaces, delicate projections, isolated islands and accessible cleanup. Pre-supported or supportless labels are claims to review against the actual printer, material, scale and profile. Hollow resin models need all cavities to be drained, cleaned and adequately post-cured under the applicable material and process instructions. MG16

Assembly and intended use

Keyed joints, part labels, stable bases and accessible mating surfaces can simplify assembly. Paint and adhesive consume clearance. A decorative articulated model is not automatically a child-safe toy; small parts and breakable features require an intended-use assessment. W11

Practical starting point: choose one original display figure or terrain module, define the visual and handling goal, then compare two workflows. Keep the worked examples as desk studies until fabrication is separately authorized.

Procedural model generators

A model library, a character configurator, a procedural system and a CAD program solve different problems.

Route	Useful work	What to preserve or verify
OpenSCAD	Parameterized bases, tiles, boxes, signs and repeated props	Source code, parameters, units and dependency licenses
Blender	Organic sculpting, mesh editing and procedural scene assets	Applied or realized geometry, topology and export results
FreeCAD or CadQuery	Dimensioned assemblies, inserts and modular interfaces	Parametric source, design intent and exchange format
OpenForge ecosystem	Modular terrain and bases	Grid, connector version, component license and actual fit
Gridfinity implementations	Paint, tool or miniature storage	Exact repository, generated dimensions and its own license

OpenSCAD is a free solid-modeling route; its Customizer can expose parameters. Blender's official 3D Print Toolbox extension provides analysis, repair, thickness and export tools. FreeCAD and CadQuery suit repeatable dimensions; CadQuery documents formats including STEP, AMF, 3MF and STL. These are project capabilities, not tested compatibility guarantees for every plugin or printer. MG09 MG10 MG11 MG12

Reproducible does not automatically mean correct

A procedural generator can make the same faulty clearance perfectly reproducible. Require declared units, permitted parameter ranges and rejection of impossible combinations. Keep editable source rather than only a mesh if future dimensional revision matters. Automatic mesh repair may alter intended geometry; preserve the original and inspect the change.

A useful proposed record includes object ID, intended use, engine version, parameters or seed, source and asset licenses, model revision, dimensions, manufacturing assumptions, export files and validation status. Keep mesh review, slicer review and physical validation as separate fields.

OpenForge is an ecosystem with connector and license considerations, not merely a pile of interchangeable STLs. One Gridfinity repository's MIT license must not be generalized to every implementation or incorporated asset. MG13 MG14

Accessible design proposal: provide numeric entry alongside sliders, clear units, keyboard navigation, undo, readable warnings and a simple mode. These are proposed requirements, not an audit claiming the listed tools meet them.

Character configurators and AI model services

Current features and rights were checked on 23 October 2026 from the limited sources stated in the ledger.

Hosted character tools

Hero Forge distinguishes basic design access, paid features and digital-download offerings. An STL intended for printing is different from a virtual-tabletop asset bundle. Official indexed legal extracts distinguish a user's underlying character concept from service depictions; direct legal-page access was blocked in this research. Do not infer unrestricted ownership, resale or redistribution rights. MG03 MG04 MG05

TitanCraft describes a free browser app with paid asset unlocking and repeat downloads using purchased parts. Its merchant program separately addresses physical-print sales and excludes digital-file distribution. A free editor does not make every asset or export free. Inspect the current agreement before any commercial use. MG01 MG02

Eldritch Foundry is a candidate, not an equally verified recommendation here. An official-branded profile advertises an STL subscription, but current checkout, fulfillment and full output rights were not established. Its application EULA alone does not settle downloaded-model permissions. MG07 MG08

AI text and image to 3D

AI can help create an original decorative concept or variation. A textured render may imply detail that is absent from the mesh. A single photograph cannot uniquely determine the unseen back or internal geometry; inferred surfaces are not measurements. Dimensioned interfaces and small lettering need deliberate inspection and often remodeling.

Meshy's own printing workflow includes repair, wall-thickness correction, resizing and export checks. That is a better description of the work than an unqualified print-ready slogan. Vendor thresholds are not universal process limits, and some features may require paid access. No comparative print test or purchase was performed. MG15

Rights and privacy gates: separate software access, asset rights, modification, physical sales and digital redistribution. Preserve the raw result and repair history. Do not upload confidential designs or personal photographs without appropriate authorization and review of the service's terms. If rights or geometry remain unresolved, stop rather than promoting the output into a printable product.

From digital geometry to a sliced job

A successful export means a file was written, not that the design is correct or fit for use.

Preserve intent and dimensions

Keep the editable CAD or sculpt source, revision, declared units, intended scale and reference measurements. Traditional STL does not reliably convey standardized unit semantics; an importer assumption can change millimetres to inches by a factor of 25.4. 3MF explicitly represents units and can organize objects and resources, but extension and application support vary. A 3MF file is not universally interchangeable printer-ready instructions. MG19

A surface scan or reconstruction may help recover a shape, but it does not automatically recover design intent, hidden interiors or engineering tolerances. Preserve which geometry was measured and which was inferred. Choose tessellation sufficient for meaningful curvature, rather than assuming more triangles always improve the finished part.

Inspect actual geometry

Check open boundaries, nonmanifold edges, self-intersections, duplicate or zero-area faces, normals and disconnected shells. Multiple shells may be intentional; blindly joining everything can destroy articulation. TitanCraft notes that cavity warnings can misinterpret multishell models, so both accepting and dismissing a warning require inspection. MG01 MG10

Check minimum features against the selected process and material, not a generic internet threshold. Locate every cavity. Confirm that supports, retained material and finishing tools can reach the relevant surfaces. Record intended clearance separately from overall scale.

Treat slicing as a review stage

Slicing converts geometry into machine actions. Inspect the layer preview for disappearing walls, isolated islands, unintended fill, missing small features, inaccessible support contacts and closed cavities. Recheck after a scale, orientation, support or profile change. A repair tool's success message does not prove successful manufacturing.

Freeze a build record containing the exact exported file and slicer project, software version, machine, material identity, orientation, layout, support strategy and relevant settings. NIST's manufacturing-data work treats material, machine, process and part information as a connected record. W03

Acceptance gate: a design becomes a candidate for fabrication only when its units, geometry, intended use and process assumptions are explicit. It is still not physically validated.

Printing post processing and inspection

The printer often produces an intermediate object. The full production route determines the result.

Stage	Record or decision	Common mistaken shortcut
Requirements	Intended function, conditions, interfaces and acceptance criteria	Accepting a good-looking result as the specification
Design and preparation	Revision, orientation, support and cleanup access	Assuming every printable geometry is equally suitable
Build	Machine, material lot, profile and deviations	Treating a completed progress bar as quality evidence
Post-processing	Actual sequence and final material condition	Calling a green or uncured part finished
Inspection	Final dimensions, relevant flaws and function	Inspecting only before cure, heat treatment or assembly
Release or rejection	Evidence, limits and disposition	Treating one successful sample as a qualified process

This is a proposed generic record, not a universal certified workflow. Specific parameters, chemicals and equipment procedures must come from the applicable material-machine instructions and risk assessment. NIST's measurement program provides the broader rationale for treating each stage as part of manufacturing. W02

Secondary processes can dominate

Depending on the route, work may include cooling, support removal, washing, curing, depowdering, debinding, sintering, heat treatment, infiltration, machining, polishing, painting or assembly. These can change dimensions, surfaces and properties. Printing a metal or ceramic green body does not complete the final dense part. PF13 PF21 PF22

Miniature finishing and functional inspection serve different purposes. Primer can reduce visible stepping; it does not demonstrate strength or eliminate hidden defects. A hole judged before cure or thermal processing may no longer meet its requirement afterward.

Traceability without bureaucracy: retain the source file, exact manufacturing revision, material identity, process record, inspection result and reason for rejection or rework. Save what enables a meaningful repeat, rather than relying on memory of the same settings. W03

Safety across the complete workflow

Control hazards before printing, including cleaning, finishing, maintenance and waste.

NIOSH's small-user guide addresses particles, chemicals and physical hazards. PLA, low odor, plant-derived content and water-washable labels are not blanket safety classifications. The 2025 CDC-hosted school-study abstract reports VOCs and ultrafine particles in evaluations across 11 settings; it does not establish disease incidence or a universal exposure level. W01 W04

Use the control hierarchy

Eliminate an unnecessary hazardous task where feasible; substitute only with evidence of lower overall hazard; use engineering controls; add administrative controls and suitable PPE. A cabinet alone is not proof of capture. Particle and gas-control media do different jobs, and a filter label does not validate a complete system. NIOSH's review found local exhaust approaches generally performed better than isolation alone in the studied cases. W01 W15

Resin solvents dust and powders

Use the exact product SDS and equipment instructions. Liquid resin and contaminated objects can present skin and eye hazards; manufacturer guidance includes sensitization concerns and compatible protective equipment. Water-washable does not mean contaminated water belongs in a drain. A technical data sheet is not an SDS. W05 W06

Industrial powder handling is a separate category. OSHA explicitly includes 3D printing with combustible metals in its combustible-dust guidance. Do not improvise powder collection, fire response or inert-gas arrangements. Inert gases can displace oxygen. W17 Lasers and intense light, hot surfaces and furnaces, moving axes and finishing tools create additional hazards. Keep guards and interlocks intact; use appropriate facility-specific assessment. W07 W08

A practical planning gate

Obtain current manuals and SDSs; choose a dedicated controlled location; separate clean and contaminated handling; keep food out; prevent child and pet access; plan task-specific protection, labeled storage and legitimate waste disposal before use. Stop if the controls cannot be implemented. Outsourcing or retaining a digital model are valid alternatives.

US official sources are concrete examples, not a determination of the reader's local legal obligations. Finished-object use creates additional requirements: food contact, toys, medical devices and electrical protection cannot be inferred from a raw-material slogan. W10 W11 W12 W13

Quality metrology and qualification

Measure the requirements on the final object and keep uncertainty visible.

Accuracy concerns closeness to a reference value; precision concerns agreement among repeated measurements under stated conditions. Resolution concerns distinguishable detail; surface finish concerns texture. A repeatable dimensional error is precise but inaccurate. Calipers displaying hundredths of a millimetre do not automatically establish that accuracy on a flexible, rough or inaccessible surface.

NIST separates material, machine, process and part characterization and highlights internal flaws, complex surfaces and directional behavior as qualification challenges. In-process sensing and post-process inspection are complementary, not automatic substitutes for each other. W02 W16

A proposed inspection ladder

Visual screening: look for missing geometry, cracks, separation, warping, contamination, uncured material and severe support damage. Useful, but not enough for hidden defects.

Dimensional inspection: define datums and measurement locations; use suitable methods and record results and uncertainty against requirements.

Surface and internal assessment: choose methods that can detect relevant flaws in the actual geometry. A complicated internal channel may require specialist access or inspection.

Functional verification: evaluate the intended function under a justified safe test plan, not an improvised demonstration that creates new hazards.

Qualification and release: obtain the relevant professional, customer or regulatory evidence before critical service. The ladder is an analytical organization, not a certification protocol.

A successful sample is not a capable process

Part qualification concerns a design or produced item's requirements. Process qualification concerns a defined route's ability to produce acceptable outcomes under controlled conditions. Changing material formulation, orientation, machine, thermal treatment or software can change the evidence needed. A coupon also does not reproduce every feature, stress concentration or thermal history of a real part.

Track first-pass yield, rejected features, critical dimension variation, post-processing time and material use. These records support improvement without inventing reliability from one excellent specimen. W03

Electrical example: UL's Blue Card framework includes AM machine and build-condition information and warns against simply transferring conventional material ratings to printed parts. Even component recognition does not approve an unrestricted complete end product. W13

Calculate cost per accepted finished part

Fictional inputs for planning, not prices or measured printer results.

Use **cost per accepted part = total attributable batch cost / accepted parts**. Include design and setup allocation, material, machine ownership or rental, maintenance, energy, labor, consumables, space or controls, post-processing, inspection, rework and disposal. Define the boundary so the same expense is not counted twice.

Material consumption includes supports, rafts, purge and other attributable losses. Occupied material volume is not the bounding-box volume. Reusable powder inventory is not automatically consumed waste. Material yield and first-pass part yield answer different questions.

Hypothetical batch input	Calculation	Cost units
Ten attempted decorative parts plus supports	120 cm3 x 1.2 g/cm3 = 144 g	-
Fictional material rate	0.144 kg x 30/kg	4.32
Allocated machine and maintenance	5 hours x 2/hour	10.00
Assumed average power and tariff	0.12 kW x 5 h x 0.25/kWh	0.15
Direct labor	0.75 hours x 20/hour	15.00
Other consumables and waste	Assumed batch allowance	3.00
Recurring batch total	Sum of listed costs	32.47
Eight accepted parts	32.47 / 8	4.06 each
First batch including 20 setup units	52.47 / 8	6.56 each

Dividing by all ten attempts would misleadingly report 3.25 recurring units per part. If only six pass, the same recurring batch total becomes 5.41 per accepted part. If all ten pass, it is 3.25. Yield changes the denominator; better yield is not free if it requires extra inspection or processing.

Calibration for real use: replace every assumption with actual material consumption, power over the relevant workflow, labor records, machine allocation and accepted output. Add omitted tax, shipping, dedicated ventilation or room costs and unlisted finishing or testing. The fictional density and rates are not recommendations.

For outsourcing, compare equal finished conditions: raw, cleaned, cured, machined, painted, inspected or assembled delivery.

Lifecycle and waste

Additive manufacture is not automatically greener because it adds rather than cuts material.

Compare equivalent delivered function and service life. Include feedstock production, machine electricity, heating and cooling, supports, failed builds, cleaning media, consumables, post-processing, transport and end of life. A lightweight part may save use-phase energy in one context; a part that fails early can erase manufacturing savings in another. NIST frames sustainability as a lifecycle measurement problem. W14

Reduce avoidable work first

An unnecessary print avoided is different from a failed print recycled. Inspect geometry before long jobs, reduce preventable failure, design for adequate life and repair, and select only the finish needed. Reducing supports can save material but becomes counterproductive if it increases rejects or compromises function.

Recycling feasibility depends on formulation, contamination, collection and available processors. A polymer symbol, bio-derived feedstock or biodegradability claim does not establish that a local facility accepts a particular printed object. Keep reusable inventory, recyclable waste and hazardous or contaminated waste distinct in the cost model.

Plan the disposal route in advance

Do not assume that curing, filtering or dilution universally makes resin-related waste legally disposable. Consult the actual SDS and local waste authority for wash liquid, filters, gloves, residue and containers. EPA explains that US household hazardous waste management operates at state and local levels; household rules do not automatically apply to commercial waste generators. W06 W09

A bounded next step for Blackwish

Choose one low-consequence object family: a decorative miniature, a terrain module, a storage insert or a static machinery cutaway. Write its required size, visible detail, handling expectation and rights constraints. Compare a local design route and an external fabrication route before acquiring equipment or a subscription.

Preserve a one-page decision record: objective; process candidates; material assumptions; controls; estimated accepted-part cost; evidence still missing; and stop condition. This is a proposed desk-study method. It is not permission to buy, expose anyone, operate equipment or change a live system.

Decision quality improves when the alternatives remain real. An existing object, conventional manufacture, repair, a service provider or no physical object may satisfy the goal better than a new print.

Electrical generators and printed components

Printed geometry does not create energy or establish a safe operating machine.

An electromagnetic generator converts mechanical input into electrical output. The turbine or engine supplying rotation is a different subsystem. A magnet is not a power source, and a motor-generator loop does not evade losses. F01

Evidence level	What the claim can mean	What it does not prove
Display model	Labeled rotor, stator and housing geometry	Electrical operation
Production aid	Jig, fixture, mold or casting pattern	A printed final machine
Component	Housing, duct or cooling structure	Fitness for all temperatures or loads
Active component	Tested magnetic or rotating element	A fully printed qualified assembly
Complete system	Integrated machine with applicable evidence	Unrestricted use in other conditions

The ladder is an editorial claim-checking tool. Bearings, shaft, windings, insulation, magnetic circuit, cooling, protection and containment must work together; lower-level evidence must not silently be promoted to system qualification.

Real examples with narrow claims

An ORNL-listed 2025 peer-reviewed paper reports a multi-material LPBF rotor paired with an existing stator to make a functional synchronous-reluctance **motor**. The opened abstract reports a 4.15 Nm torque rating. This is not an entirely printed generator, and modeled opportunities must not be recast as tested product specifications. F02

DOE's 2021 account of NREL's 15-MW direct-drive generator work describes design optimization and AM opportunities, not proof that a fully printed 15-MW machine was built. ORNL's low-head hydropower case includes direct components and a runner-housing mold, not a wholly printed electrical plant. F03 F04

Bounded example: a nonfunctional cutaway can label the energy input, rotor, stator, output and which parts would remain conventional. That is a useful miniature and teaching object without energization. An operational proposal instead needs qualified review of actual loads, temperature, insulation, fatigue, fault behavior and inspection. No wiring, high-speed rotor or hazardous build recipe is supplied here.

Specialist industrial and medical domains

Maturity varies by application and product. These qualitative labels are not formal readiness scores.

Construction and cementitious printing: real deployments with evolving assurance. Extruded walls, formwork or infrastructure elements are not complete habitable buildings. Compare finished, permitted buildings at equal scope, including foundations, reinforcement, roof, services, finishes and inspection. NIST's work addresses long-term performance and methods; its July 2026 meeting illustrates continuing standardization activity, not a universal absence of codes. F06 PF38

Clay and technical ceramics: specialist commercial routes. Paste extrusion can shape clay, but drying and firing remain necessary ceramic processes. Technical ceramic methods can use loaded photopolymers followed by debinding and sintering. Offered equipment does not independently prove all proposed properties or total production economics. F05 F08

Sand molds and cores: established industrial niche. Binder-jetted sand enables foundry tooling and complex internal cores. The resulting metal is cast, cleaned, machined and inspected. Vendor time-saving examples remain case-specific rather than universal manufacturing forecasts. F07

Medical and dental: established for particular products, not unrestricted materials. FDA lists instrumentation, implants and external prostheses, while emphasizing finished devices and intended uses. An anatomy model, surgical guide and implanted component have different evidence requirements. Biocompatible feedstock does not approve an arbitrary device or workflow. F10 W12

Bioprinting: research and specialist development. Cell-containing constructs and tissue models differ from rigid anatomy replicas and from whole transplantable organs. NASA's station research illustrates investigation of tissue formation, not an ordinary consumer capability to print ready-to-transplant organs. F09

Repair and space: mixed maturity. Industrial repair and hybrid manufacture coexist with particular in-space demonstrations. NASA reported polymer printing on ISS beginning in 2014 and a metal-printing investigation update in 2025. These do not establish a self-sufficient factory: feedstock, power, maintenance and acceptance evidence remain necessary. F18

Common test: identify the deposited material, required subsequent transformation, actual demonstration and release conditions before accepting the broad label printed.

Emerging and unusual forms of printing

Distinguish an offered specialist capability, a tested experiment and a proposed future application.

Food: specialist equipment and research. Prepared edible materials can be arranged into designed portions and shapes. A 2023 Columbia-led open-access perspective reports multi-ingredient printed food and discusses controlled cooking. It does not establish universal nutritional, health or accessibility benefits. Printing does not create calories, remove allergens or replace hygiene requirements. F11

Electronics: specialty commercial platforms. Conductive and dielectric inks can form circuitry and selected functions. Nano Dimension describes a specialized materials system, not ordinary printing of arbitrary processors and every component. Conductive hobby filament, a cable guide and high-conductivity circuitry are different objects. F12

Batteries: demonstrated research architectures. Harvard and Illinois reported printed interdigitated microbattery electrodes in 2013, followed by packaging and electrolyte. A printed electrode architecture is not a complete consumer battery qualification; a printed battery case is a separate, simpler claim. F13

Textiles and fashion: a commercial hybrid niche. Depositing structures on fabric is not the same as printing an entire woven garment. Comfort, durability, washing, repair and recycling require their own assessment. F14

4D printing: material response over time. Harvard's 2016 hydrogel example used programmed swelling in water. The fourth dimension describes change, not an extra spatial printing axis. A transformation does not establish a durable actuator; reversibility, response and fatigue need evidence. F15

Volumetric printing: research and emerging specialist methods. Computed axial lithography distributes light exposure through resin rather than simply building conventional planar layers. Fast formation time is not a complete cleaned and inspected production cycle. Material compatibility and scale remain important. PF34

Two-photon microprinting: commercial precision niche and research. Focused ultrafast light supports very small photopolymer features for micro-optics and related structures. Submicron feature capability does not imply economical large objects at that resolution; size, surface quality and throughput are distinct measures. Nanoscribe's capability descriptions remain vendor evidence. F16

Worked example of a display miniature

Original hypothetical design exercise, not a validated print profile or product recommendation.

Define success before choosing a process

Suppose Blackwish needs a 40 mm tall original character for a painted display, not a toy, wearable or load-bearing object. Success means a readable silhouette, visible face and clothing at normal viewing distance and a stable base. A resin version also needs the specified wash, dry and post-cure workflow, with no trapped uncured resin or wash liquid. The tiny lantern handle is decorative, not load-bearing. A hollow interior is optional, not an automatic improvement.

Compare two honest candidates

A vat-photopolymer process is a plausible candidate when fine surface detail matters and an appropriate resin-handling workflow is available. Material extrusion is a plausible candidate when simpler handling, an existing controlled workspace or larger, deliberately stylized forms matter more. Neither choice guarantees the face will resolve or the handle will survive handling. Printer, material, orientation, support access and feature geometry must be considered together.

For a future separately authorized fabrication trial, first design a solid, simple test geometry that includes the smallest intended feature and a representative support contact. Compare outcomes against the stated goal, not against a photograph of a different machine's best print. Review supports on the face, cavities that can trap liquid, and whether removal could break thin projections. If the display goal can be met by thickening or integrating the handle into the silhouette, prefer that design change over claiming an unverified fine-feature limit.

Preserve the learning

Retain the source mesh, exported revision, unit convention, machine and material identifiers, slicer profile and observed result. If a real print is later authorized, record pass or fail against the original criteria and keep photographs of both successful and failed details. An attractive single print is evidence about that specimen, not a statistical reliability claim.

Stop condition: stop at the design comparison if the workspace cannot support the material's controls. Stop before making claims about skin contact, children's use or durability. The fallback is a larger simplified figure, an appropriate external fabrication service, or no physical print.

Worked example of a terrain generator

Original hypothetical parameter study for decorative tabletop terrain. The numbers describe design intent, not universal machine limits.

Make the generator explain its output

Imagine a procedural generator for modular ruins. Its inputs are tile width, wall height, doorway width, connection type and random seed. Set an illustrative tile width of 50 mm, a wall height of 30 mm and a doorway width of 18 mm. Use a fixed seed to reproduce the same arrangement. These values are bookkeeping examples; they do not assert a compatible miniature scale, structural capacity or print tolerance.

The generator should output closed solids, preserve a known unit system, and identify the revision and parameter values. It should reject negative dimensions, incompatible connection geometry, self-intersections and features that violate a deliberately chosen manufacturing envelope. A mesh viewer is not an adequate rejection test: attractive shading can conceal a missing face or coincident surface.

Test boundaries rather than one attractive sample

Check the smallest and largest allowed tiles, the thinnest wall option, maximum doorway width and a case where two features collide. Inspect a deliberately invalid input to ensure the generator refuses it rather than silently exporting broken geometry. A parameter sweep is software evidence about the generation rules; it is not physical evidence that each variant will print successfully.

For a future fabrication trial, separate a connection coupon from the full terrain set. Record the measured fit and update the generator's documented allowance only for the tested process and material. Do not silently scale every dimension to repair a connector, because that also changes door openings and the visual scale.

Decision: a reproducible procedural model is valuable when variation matters and geometry rules are inspectable. A manually modeled part is often simpler for one unique object. A licensed existing model may save time, but its manufacturing fitness and permitted uses still need separate checks.

Zen review of process selection

Review one tests whether the chosen manufacturing family follows from the actual objective.

POINT objective claim

The claim is not that one printing method is best. It is that a specific method can meet a defined object's geometry, material, finish, volume and use requirements within an acceptable workflow. For a detailed display miniature, visual fidelity may dominate. For a functional fixture, stiffness, repeatability, wear and inspection may dominate. The objective must name its audience and acceptance criteria before comparing options.

BRIDGE evidence and authority

The seven-family map organizes mechanisms; it is not a ranking. A supplier's attractive sample is evidence that the supplier produced that sample, not that every machine and material combination will reproduce it. Relevant evidence includes the intended material's documented behavior, comparable parts, machine-specific guidance and a measured representative trial. Safety and compliance claims require evidence from the relevant authority, not merely an online creator's confidence.

PATH consequences alternatives and stop

Choose the smallest reversible next step: clarify requirements, compare processes, inspect a model, or obtain a qualified service assessment. Compare machining, molding, casting, assembly, an off-the-shelf part and not making the object. Count support removal, cleaning, inspection and rejected work rather than judging only build time. Stop if essential acceptance criteria or required exposure controls cannot be specified.

SHADOW assumptions and counterexamples

Counterexample one: a higher-detail process produces a fragile feature that fails in use, so its prettier surface does not satisfy the objective. Counterexample two: a slower process is preferable because its material and repeatable inspection are better established. Counterexample three: a large, simple batch is cheaper by conventional manufacturing even though a printer can make the shape.

Review result: keep the process choice provisional until the objective, evidence and entire workflow agree. This is an analytical conclusion, not approval to purchase, fabricate or deploy anything.

Zen review of miniature and model generators

Review two tests the bridge from a generated representation to a usable physical object.

POINT objective claim

A generator is useful when it creates a relevant design efficiently while preserving enough control, provenance and reproducibility for the intended use. For miniatures, the objective may include pose, silhouette, scale, support access and the right to produce the object. For a parametric part, it may include explicit dimensions and controlled variants. A plausible render alone does not meet either objective.

BRIDGE evidence and authority

Inspect the actual exported geometry, not just a preview. Verify units, closed volume, disconnected islands, wall thickness, cavities and collision-prone details. Distinguish editable parametric rules from an inferred triangle mesh. Keep the input, seed or prompt when available, export version, license evidence and changes made during repair. A platform's export claim establishes a file feature, not structural certification, permission to copy someone else's character or proof that the mesh is printable.

PATH consequences alternatives and stop

Use a manual model, a deterministic generator, a licensed library asset or an AI-assisted starting point according to the job. Repair can consume more time than modeling a simpler object directly. Review repairs for changes to dimensions or intended meaning. Stop if the needed rights are unclear, provenance cannot support the intended use, trapped material cannot be removed, or unresolved geometry prevents reliable slicing.

SHADOW assumptions and counterexamples

A watertight model can still contain unsupported islands or features too fragile for its purpose. A mesh that slices without warning can still fail during printing or post-processing. A visually convincing miniature can contain hidden fused fingers or an impossible joint. A procedural tool can consistently reproduce the same incorrect clearance. A license may allow personal printing but not commercial distribution.

Review result: preserve generator output as a candidate design. Printability, acceptable use and rights are independent gates; passing one must not silently satisfy the others.

Zen review of functional and frontier claims

Review three tests when printed components justify claims about a working machine or emerging technology.

POINT objective claim

The relevant claim must be as narrow as the evidence: a printed housing, a tested coil specimen, a laboratory motor, a generator subsystem and a service-qualified machine are different achievements. A frontier process may demonstrate a mechanism without establishing economical manufacture, scale, reliability or suitability for unsupervised use.

BRIDGE evidence and authority

Separate peer-reviewed experimental results, institutional descriptions, technical standards and vendor capability claims. Ask what was actually fabricated, what remained conventional, how performance was measured, how long it ran, under what conditions, and what failure or uncertainty was reported. A simulation can guide design but does not establish the integrity of a manufactured specimen. A single successful specimen does not establish a qualified production process.

PATH consequences alternatives and stop

For electrical generators, restrict this reference to component roles and evidence needs. Operating rotating or energized machinery demands an appropriate engineering and safety review, including relevant electrical, thermal, mechanical and environmental conditions. Alternatives include a static educational model, qualified conventional equipment, a professionally reviewed component study or no build. Stop when the use case outruns the available material, process or test evidence.

SHADOW assumptions and counterexamples

A printed rotor can look correct while containing a defect that is critical at speed. An insulating shape can fit while failing the needed electrical or temperature conditions. A printed conductive path may work briefly but overheat in a different duty cycle. A small research demonstration may not scale because curing, heat flow, residual stress or material transport changes with size.

Review result: preserve the innovation claim where supported, but reject escalation from a successful shape or demonstration to unrestricted functional readiness. Independent review does not replace the user's manual ratification.

Bounded final challenge and preservation conditions

This Death Knell pass challenges overclaiming in the research. It does not reject 3D printing as a field or authorize any change to a live system.

The strongest challenge

A broad survey can create false confidence by placing hobby tools, industrial production, emerging laboratory techniques and speculative applications in one attractive document. It can also encourage a reader to treat generated geometry as an instruction to make a real object. The correct response is not to erase useful possibilities. It is to retain the distinctions that make those possibilities intelligible and bounded.

Conditions that preserve a defensible conclusion

Preserve the evidence boundary. Keep mechanism explanations separate from tested performance, supplier claims and hypotheses. Keep limited-access sources labeled. Preserve dates on current platform and frontier claims; an access date is not a guarantee that a product or paper is current forever.

Preserve the object boundary. A miniature, mold master, fixture, implant concept, architectural element and energized generator face different consequences. No process family grants universal strength, safety, biocompatibility, food suitability, fire resistance or legal compliance.

Preserve the manufacturing boundary. A simulation is not a manufactured proof. A manufacturable mesh is not a successful print. A successful print is not a qualified part. A qualified part is not automatic approval for every machine or operating context.

Preserve agency and originals. Keep source material, generator inputs and prior versions. The three Zen reviews and this challenge are research analyses, not ratification. No purchase, human experiment, hazardous machine construction or live deployment is authorized by the document. Any deployment remains subject to the user's explicit manual ratification and the relevant technical safeguards.

What survives the challenge

3D printing remains useful for rapid iteration, distinctive geometry, customization, selected production tasks and research. The defensible next step is a bounded question with an inspectable answer: which requirement, which process and material, which evidence, which acceptance test, and which stopping condition? Where that chain is incomplete, preserve the uncertainty rather than inventing completion.

Glossary

Working definitions for this reference. A glossary is not a substitute for the full terminology standard.

Term	Meaning here
Anisotropy	Properties that depend on direction; important in many printed material systems.
Binder jetting	A liquid binder joins selected regions of a powder bed.
CAD and mesh	CAD can preserve design intent and dimensions; a mesh approximates surfaces with facets.
DED and WAAM	Directed energy deposition; wire-arc additive manufacturing is an arc-and-wire variant.
DfAM	Design for additive manufacturing, including access, finishing and inspection constraints.
FFF and FDM	Fused filament fabrication and a commonly used Stratasys trademark for extrusion technology.
Green part	A shaped intermediate before full processing. Sintering thermally consolidates a powder body and may change size.
Infill	Deliberately generated interior structure; not a universal proxy for strength.
LPBF and SLS	Laser powder bed fusion, often used for metals; selective laser sintering, commonly polymers.
MJF and Metal Jet	HP polymer powder bed fusion and HP metal binder jetting respectively.
SLA DLP MSLA	Laser-scanned, projected-image and masked light approaches to vat photopolymerization.
Slicing	Converting geometry into process-specific layers and machine actions.
STL and 3MF	Mesh-oriented exchange formats; 3MF explicitly represents units and additional resources.
Support	Temporary geometry or surrounding material that enables manufacture; removal can matter.
Qualification	Evidence that a defined part or process satisfies its requirements and controlled conditions.

Definitions synthesize the cited process and workflow chapters. For formal terminology see the public ISO catalog and NIST taxonomy; file semantics are supported by the 3MF specification.

Source and access ledger 1

All sources checked on 23 October 2026. Click a title to open the original.

An extract may be indexed source text or a partial page view; it is not an exhaustive full-text reading. Opened pages and PDFs are stated explicitly. Vendor documentation verifies an offered claim, not independent performance. Publication dates are not search crawl dates.

PF01 ISO catalog. Catalog and abstract only; full standard paywalled. Confirmed in 2025.

PF02 NIST process taxonomy. Primary institutional reference; public extract, not exhaustive full-text review.

PF03 NIST technologies overview. Primary institutional reference; public extract, not exhaustive full-text review.

PF04 Stratasys legal information. Vendor documentation; public extract. Claims not independently tested.

PF05 NIST material extrusion. Primary institutional reference; public extract, not exhaustive full-text review.

PF06 Markforged composite architecture. Vendor documentation; public extract. Claims not independently tested.

PF07 ORNL large-format research. Primary institutional reference; public extract, not exhaustive full-text review.

PF08 Markforged workflow overview. Vendor documentation; public extract. Claims not independently tested.

PF09 NIST polymer testing review. Primary institutional reference; public extract, not exhaustive full-text review.

PF10 NIST die-swell research. Primary institutional reference; public extract, not exhaustive full-text review.

PF11 Formlabs technology comparison. Vendor documentation; public extract. Claims not independently tested.

PF12 Formlabs pixel-size analysis. Vendor documentation; public extract. Claims not independently tested.

PF13 Fraunhofer ceramic stereolithography. Primary institutional reference; public extract, not exhaustive full-text review.

PF15 HP process comparison. Vendor documentation; public extract. Claims not independently tested.

Source and access ledger 2

Access date 23 October 2026. Evidence limits remain attached to each source.

PF16 EOS SLS production overview. Vendor documentation; public extract. Claims not independently tested.

PF17 EOS DMLS explanation. Vendor documentation; public extract. Claims not independently tested.

PF18 NIST PBF. Primary institutional reference; public extract, not exhaustive full-text review.

PF20 NIST residual-stress study. Primary institutional reference; public extract, not exhaustive full-text review.

PF21 HP Metal Jet process. Vendor documentation; public extract. Claims not independently tested.

PF22 Desktop Metal design guidance. Vendor documentation; public extract. Claims not independently tested.

PF23 Desktop Metal ceramic overview. Vendor documentation; public extract. Claims not independently tested.

PF25 Stratasys PolyJet design guide. Vendor documentation; public extract. Claims not independently tested.

PF26 Stratasys material explanation. Vendor documentation; public extract. Claims not independently tested.

PF27 3D Systems wax MJP explanation. Vendor documentation; public extract. Claims not independently tested.

PF28 casting workflow overview. Vendor documentation; public extract. Claims not independently tested.

PF29 NASA EBF3 description. Primary institutional reference; public extract, not exhaustive full-text review.

PF30 WAAM3D FAQ. Vendor documentation; public extract. Claims not independently tested.

PF31 Fabrisonic design guide. Vendor documentation; public extract. Claims not independently tested.

Source and access ledger 3

Access date 23 October 2026. Evidence limits remain attached to each source.

PF34 LLNL CAL overview. Primary institutional reference; public extract, not exhaustive full-text review.

PF38 NIST 2026 construction standardization meeting. Primary institutional reference; public extract, not exhaustive full-text review.

MG01 TitanCraft FAQ. Indexed official FAQ: free app, asset reuse, merchant program, multishell warning.

MG02 TitanCraft merchant program. Indexed official product page: physical-print rights; excludes digital redistribution; detailed agreement still required.

MG03 Hero Forge subscriptions. Indexed official page: basic/Pro/Pro+ Download distinctions.

MG04 Hero Forge support archive. Indexed official archive: print STL versus VTT assets.

MG05 Hero Forge legal questions. Official indexed extract; direct fetch 403; abstract original character versus service depiction distinction.

MG07 Eldritch Foundry official profile. Official-branded profile indexed; subscription promotion only; does not verify current checkout.

MG08 Eldritch Foundry application EULA. Indexed official application EULA; not a verified downloaded-output license.

MG09 OpenSCAD project. Indexed official page: free solid-modeling software; no installation performed.

MG10 Blender 3D Print Toolbox extension. Indexed current official extension page; distinct from older bundled-add-on instructions.

MG11 CadQuery documentation. Indexed project documentation: parametric Python CAD and exchange formats.

MG12 FreeCAD manual. Indexed official manual; stable conceptual description, not a version-feature comparison.

MG13 OpenForge project organization. Indexed project organization: terrain/base repositories; individual licenses differ. Connector license notes.

Source and access ledger 4

Access date 23 October 2026. Evidence limits remain attached to each source.

MG14 Gridfinity OpenSCAD repository. Indexed repository and separate LICENSE result; MIT applies to this implementation.

MG15 Meshy printing workflow. Indexed vendor workflow; vendor claims not independent performance validation.

MG16 Prusa hollowing guide. Indexed official hollowing workflow; minimum thickness setting is tool-specific, not universal design advice.

MG17 Prusa miniature demonstration. Indexed official process demonstration; older hardware example, not a current product ranking.

MG19 3MF core specification. Indexed standards-maintainer repository; units and extension interoperability requirements.

W01 NIOSH small user guide. Opened official PDF. Publication 2024-103; published November 2023.

W02 NIST AM measurement science. Official page extract; characterization and qualification scope.

W03 NIST AM data management. Official publication extract; not a complete PDF review.

W04 CDC school evaluations study. Opened 2025 abstract; 11 settings. No disease-incidence inference.

W05 Formlabs resin care. Manufacturer safety guidance extract; exact product SDS still required.

W06 OSHA safety data sheet structure. Official regulatory extract; general US example, not local legal advice.

W07 OSHA combustible dust manual. Official manual extract includes combustible-metal AM; no operational recipe.

W08 OSHA laser technical manual. Official technical extract; classification and controls, not machine-specific assessment.

W09 EPA household hazardous waste. Official extract; state/local management and household boundary.

Source and access ledger 5

Access date 23 October 2026. Evidence limits remain attached to each source.

W10 FDA food contact information. Official extract; intended-use framework, not approval of a particular print.

W11 CPSC toy safety guidance. Official extract. Related small-parts guidance is linked below. Small parts guidance.

W12 FDA medical printing process. Official extract; finished-device versus unrestricted material distinction.

W13 UL AM Blue Card. Primary certification-service extract; AM build conditions and rating limitations.

W14 NIST sustainability characterization. Opened official landing page; lifecycle framework, not a universal savings estimate.

W15 NIOSH controls review. Research record extract; comparative control findings are setup-dependent.

W16 NIST part qualification. Official project extract; internal defects and measurement challenges.

W17 OSHA oxygen deficiency reference. Official safety reference extract; oxygen displacement hazard, not a facility-specific assessment.

F01 EIA electricity generation. Official explanatory extract; conversion versus primary energy source.

F02 Newman and colleagues rotor study. Opened ORNL abstract for 2025 IEEE paper, DOI 10.1109/TIA.2024.3522210. Full paper not separately reviewed.

F03 DOE NREL wind generator design study. Official summary extract dated 14 July 2021. Optimization study, not a completed printed 15-MW machine.

F04 ORNL low head hydropower case. Opened institutional case report; components and tooling, not entire plant certification.

F05 WASP clay extrusion system. Vendor product extract; existence of specialist equipment, no current purchase offer endorsed.

F06 NIST construction performance. Official research extract; assurance gaps, not exhaustive building-code inventory.

Source and access ledger 6

Access date 23 October 2026. Evidence limits remain attached to each source.

F07 ExOne sand casting workflow. Vendor process extract; savings anecdotes remain case-specific.

F08 Lithoz LCM process. Opened vendor page; ceramic route description, not independent property verification.

F09 NASA bioprinting research. Official research extract; tissue investigation, not routine organ replacement.

F10 FDA medical applications. Official extract; device categories, not authorization of a proposed design.

F11 Blutinger and colleagues food printing. Opened primary open-access perspective, 21 March 2023. Demonstration and research interpretation.

F12 Nano Dimension electronics materials. Vendor process extract; specialty materials and capability, not universal performance validation.

F13 Harvard microbattery report. Institutional report and original-paper excerpts; 2013 research architecture, not current cell qualification. Original microbattery paper.

F14 Stratasys direct to textile printing. Vendor capability extract; textile hybrid route, not verified garment durability.

F15 Harvard 4D hydrogel research. Primary research report extract; 2016 stimulus-responsive demonstration.

F16 Nanoscribe microfabrication technologies. Vendor technology extract; commercial precision niche, application-specific performance.

F17 NIST directed energy deposition. Official process extract; no authorization to repair a particular component.

F18 NASA metal printing on station. Official 3 March 2025 update extract. Earlier polymer demonstration linked below. NASA 2014 first object.