

Bostik

Issued December 1993

Information Sheet No.B842/4
(supersedes Sheet No. B842/3)

NEVER-SEEZ PURE NICKEL SPECIAL, NUCLEAR GRADE ANTI-SEIZE & LUBRICATING COMPOUND

DESCRIPTION

BOSTIK NEVER-SEEZ PURE NICKEL SPECIAL, NUCLEAR GRADE is a superior, extreme high temperature anti-seize and extreme pressure lubricant. It contains flake particles of pure nickel, graphite and other additives in a special grease carrier found to enhance anti-seize performance.

USES

BOSTIK NEVER-SEEZ PURE NICKEL SPECIAL, NUCLEAR GRADE is suitable for use where applications prohibit the presence of copper and especially where resistance to corrosive acidic and caustic solutions is required. It is specifically designed for use in nuclear power plants and other applications which require certification of purity. It provides the following advantages:

- * Certification of purity.
- * Minimises corrosion on fasteners in exhaust manifolds and boilers
- * Prevents seizure at high temperatures common to nuclear power generating plants.
- * Excellent heat dispersing qualities.
- * Resistance to strong alkaline solutions
- * Prevents galling on steel to stainless steel, titanium, magnesium and other hard metals.
- * Highly resistant to water wash out and salt spray exposure.

APPLICATION INSTRUCTIONS

Apply BOSTIK NEVER-SEEZ PURE NICKEL SPECIAL, NUCLEAR GRADE by brush to the mating surfaces of appropriate components. Then assemble these components as required. It is not necessary to degrease metal surfaces to which the compound is applied but all surfaces should be dry and free from foreign matter. Clean rusted metal surfaces by wire brushing and then removing the resulting surface powder.

/Continued....

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The Company cannot accept any responsibility for loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.

The word BOSTIK is a trade mark registered in the United Kingdom and many other countries.

Bostik Ltd., Leicester, LE4 6BW, England.
Telephone 0116 251 0015. Telex 34625. Fax 0116 253 1943.

(BOSTIK NEVER-SEEZ PURE NICKEL SPECIAL, NUCLEAR GRADE - continued 2)

CLEANER: Use BOSTIK CLEANER/THINNER M(M610) or BOSTIK CLEANER/THINNER 6020 for removing excess compound and for brush cleaning.

TYPICAL CHARACTERISTICS

Physical Form:	Viscous paste.	
Colour:	Silver.	
Odour:	Grease like.	
Chemical Type:	Hydrocarbon grease with metallic and graphitic particles.	
Viscosity:	Approximately 350 Pa s (3500 poise).	
Specific Gravity:	Approximately 1.4.	
Flash Point:	> 250°C (open cup).	
Trace Elements: (parts per million)	Average of Typical <u>Batches</u>	Maximum Manufacturing <u>Limits</u>
Cooper	15	50
Zinc	10	50
Iron	100	125
Magnesium	1	5
Inorganic Chlorides	5.5	10
Total Chlorides	70	500
Inorganic Fluorides	15	25
Total Fluorides	30	70
Lead	2.5	50
Antimony	None detected	5

/Continued....

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The Company cannot accept any responsibility for loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.

The word BOSTIK is a trade mark registered in the United Kingdom and many other countries.

Bostik Ltd., Leicester, LE4 6BW, England.
Telephone 0116 251 0015. Telex 34625. Fax 0116 253 1943.

(BOSTIK NEVER-SEEZ PURE NICKEL SPECIAL, NUCLEAR GRADE - continued 3)

Arsenic	None detected	5
Phosphorous	None detected	5
Sulphur	105	300
Calcium	20	50
Mercury	None detected	1*

* parts per billion

TYPICAL PERFORMANCE CHARACTERISTICS

Temperature -183 to 1300°C

Resistance: (Note: The grease carrier and other organic material will carbonise at approximately 300°C but the residual metallic particles provide lubrication at the higher temperatures because the platelets slip over each other).

Water, Salt

Water & Ionised

Water Resistance: Very good

Acid & Alkali

Resistance: Very good

Coefficient

of Friction: 0.062 (at 75°C)

PACKAGING

Please refer to Customer Service Department for details of current pack sizes.

STORAGE AND TRANSPORTATION

Store under dry conditions below 25°C. Keep containers away from sunlight and other heat sources.

Keep containers tightly closed.

SHELF LIFE

5 years from date of manufacture under the above conditions of storage.

/Continued

MATERIAL SAFETY DATA

	Long-term exposure limit (8-hour TWA reference period)			Short-term exposure limit (10-minute reference period)			
	<u>Wt%</u>	<u>ppm</u>	<u>mg m⁻³</u>	<u>ppm</u>	<u>mg m⁻³</u>		<u>Notes</u>
Hazardous							
Ingredients:							
*(Nickel powder	11-25	-	0.5	-	-	)	
*(Aluminium flake	1-10	-	10	-	20	)	

Ref: EH40/91 "Occupational Exposure Limits 1991"

*(): To be reviewed.

Solubility in water: Immiscible.

Material Stability: Stable in unopened containers under the recommended storage conditions.

Incompatible materials: Liquid or gaseous oxygen, reducing agents, perchlorates, strong mineral acids and phosphorous.

Disposal of waste: Utilise oil reclaimers as for grease disposal, otherwise treat as special, notifiable waste.

Spillages: Wipe up and thoroughly clean the area where the spillage occurred.

For detailed safety and handling advice, refer to BOSTIK Information Sheet SH17 "NEVER-SEEZ HIGH TEMPERATURE ANTI-SEIZE COMPOUNDS".