

NATIONAL UNIVERSITY OF HO CHI MINH CITY
UNIVERSITY OF SCIENCE

UNDERGRADUATE THESIS

Three-band tight binding model for TMD monolayers
in the presence of a magnetic field

Ho Chi Minh City, 2025

Student: Tran Khoi Nguyen

Supervisor: Dr. Huynh Thanh Duc

TABLE OF CONTENTS

TABLE OF CONTENTS	1
LIST OF FIGURES	2
1 INTRODUCTION	3
2 METHOD	4
2.1 Three-band tight binding method without magnetic field	4
2.2 Three-band tight binding method under a magnetic field	4
2.3 Spin-orbit coupling	11
2.4 Landau levels	12
3 DISCUSSION AND FUTURE WORK	15
REFERENCES	16
A Construct matrix	18
B Harper's equation	19

LIST OF FIGURES

2.1	Top view of monolayer MX_2 . The large sphere is M atom and the small sphere is X	5
2.2	Site index	7
2.3	Hofstadter's butterfly for one band $ dz\rangle \equiv \phi_1^1(x, y)\rangle$ (left) and all band(right) with $q = 797$ and vary p from 1 to q with field strength $B_0 = 4.6928 \times 10^4$ T.	10
2.4	An easy and intuitive visualization of matrix h_0 one band(left) and matrix H all band(right) through standard plotter with $q = 20$	11
2.5	(a) Same plot as Fig 2.3 but we consider a small area and (b) is the Landau fan diagram show for the first $n = 10$ levels near the bottom of the conduction band for a magnetic field up to $B = 100$ T.	14

CHƯƠNG 1

INTRODUCTION

CHƯƠNG 2

METHOD

2.1 Three-band tight binding method without magnetic field

The time-independent Schrödinger equation for an electron in the crystal has the form


$$\left[-\frac{\hbar^2 \nabla^2}{2m} + U_0(\mathbf{r}) \right] \quad (2.1)$$

2.2 Three-band tight binding method under a magnetic field

Under a uniform magnetic field given by a vector potential $\mathbf{A}(\mathbf{r})$ the single electron Hamiltonian changes into

$$H = \frac{(-i\hbar \nabla + e\mathbf{A}(\mathbf{r}))^2}{2m} + U_0(\mathbf{r}) + g^* \mu_B \mathbf{B} \cdot \mathbf{L}, \quad (2.2)$$

where $\mu_B = \frac{e\hbar}{2m}$ is Bohr magneton, g^* is an effective Landé g-factor, $\mathbf{B} = \nabla \times \mathbf{A}$ is the uniform magnetic field, and \mathbf{L} is the angular momentum. It is possible to add a phase



Hình 2.1: Top view of monolayer MX_2 . The large sphere is M atom and the small sphere is X .

factor to the tight binding wavefunction

$$\psi_{\lambda,\mathbf{k}}(\mathbf{r}) = \sum_{j=1}^3 C_j^\lambda \sum_{\mathbf{R}} e^{i\mathbf{k}\cdot\mathbf{R}} e^{i\theta_{\mathbf{R}}(\mathbf{r})} \phi_j(\mathbf{r} - \mathbf{R}). \quad (2.3)$$

We now have

$$H_{jj'}(\mathbf{k}) = H'_{jj'}(\mathbf{k}) + H^Z_{jj'}(\mathbf{k}), \quad (2.4)$$

where

$$\begin{aligned} H_{jj'}(\mathbf{k}) &= \sum_{\mathbf{R}} e^{i\mathbf{k}\cdot\mathbf{R}} \langle \phi_j(\mathbf{r}) | e^{-i\theta_0(\mathbf{r})} \left[\frac{(-i\hbar\nabla + e\mathbf{A}(\mathbf{r}))^2}{2m} + U_0(\mathbf{r}) \right] e^{i\theta_{\mathbf{R}}(\mathbf{r})} | \phi_{j'}(\mathbf{r} - \mathbf{R}) \rangle \\ &= \sum_{\mathbf{R}} e^{i\mathbf{k}\cdot\mathbf{R}} \langle \phi_j(\mathbf{r}) | e^{i(\theta_{\mathbf{R}} - \theta_0)} \left[\frac{(-i\hbar\nabla + e\mathbf{A} + \hbar\nabla\theta_{\mathbf{R}})^2}{2m} + U_0(\mathbf{r}) \right] | \phi_{j'}(\mathbf{r} - \mathbf{R}) \rangle, \end{aligned} \quad (2.5)$$

and

$$H_{jj'}^Z(\mathbf{k}) = g^* \mu_B \mathbf{B} \cdot \sum_{\mathbf{R}} \langle \phi_j(\mathbf{r}) | e^{i(\theta_{\mathbf{R}} - \theta_0)} \mathbf{L} | \phi_{j'}(\mathbf{r} - \mathbf{R}) \rangle. \quad (2.6)$$

By choosing $\theta_{\mathbf{R}} = -\frac{e}{\hbar} \int_{\mathbf{R}}^{\mathbf{r}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'$ as Peierls substitution, the Hamiltonian in Eq. (4) now reads

$$\begin{aligned} H_{jj'}(\mathbf{k}) &= \sum_{\mathbf{R}} e^{i\mathbf{k} \cdot \mathbf{R}} \langle \phi_j(\mathbf{r}) | e^{-\frac{ie}{\hbar} \int_{\mathbf{R}}^{\mathbf{r}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}' + \frac{ie}{\hbar} \int_0^{\mathbf{r}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} \left[-\frac{\hbar^2 \nabla^2}{2m} + U_0(\mathbf{r}) \right] | \phi_{j'}(\mathbf{r} - \mathbf{R}) \rangle \\ &= \sum_{\mathbf{R}} e^{i\mathbf{k} \cdot \mathbf{R}} e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} \langle \phi_j(\mathbf{r}) | e^{-\frac{ie}{\hbar} \Phi_{\mathbf{R},\mathbf{r},0}} \left[-\frac{\hbar^2 \nabla^2}{2m} + U_0(\mathbf{r}) \right] | \phi_{j'}(\mathbf{r} - \mathbf{R}) \rangle, \end{aligned} \quad (2.7)$$

where $\Phi_{\mathbf{R},\mathbf{r},0} = \oint_{\mathbf{R},\mathbf{r},0} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'$ is the closed loop line integral of \mathbf{A} along the triangle points $\mathbf{R}, \mathbf{r}, 0$, and $\int_0^{\mathbf{R}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'$ is the path integral along the two points $\mathbf{R}, 0$. Besides that, we have used the fact that

$$\int_{\mathbf{R}}^{\mathbf{r}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}' + \int_{\mathbf{r}}^0 \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}' = \Phi_{\mathbf{R},\mathbf{r},0} - \int_0^{\mathbf{R}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'. \quad (2.8)$$

We can show that the flux term $\Phi_{\mathbf{R},\mathbf{r},0}$ is negligibly small¹ by two observations. When \mathbf{r} is far away from the lattice points \mathbf{R} and 0 , the flux is large but since the atomic orbitals are highly localized at these two lattice points, the value of the hopping term is very small and the whole hopping term goes to zero. While \mathbf{r} is at or near any of these lattice points, the triangle formed is small, and assuming small magnetic field, the flux term $\Phi_{\mathbf{R},\mathbf{r},0}$ goes to zero, which giving us the Hamiltonian as

$$H_{jj'}(\mathbf{k}) = \sum_{\mathbf{R}} e^{i\mathbf{k} \cdot \mathbf{R}} e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} \langle \phi_j(\mathbf{r}) | \left[-\frac{\hbar^2 \nabla^2}{2m} + U_0(\mathbf{r}) \right] | \phi_{j'}(\mathbf{r} - \mathbf{R}) \rangle, \quad (2.9)$$


$$H_{jj'}^Z(\mathbf{k}) = g^* \mu_B \mathbf{B} \cdot \sum_{\mathbf{R}} e^{i\mathbf{k} \cdot \mathbf{R}} e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} \langle \phi_j(\mathbf{r}) | \mathbf{L} | \phi_{j'}(\mathbf{r} - \mathbf{R}) \rangle. \quad (2.10)$$

Considering only nearest neighbor(NN) hopping, Eq (2.9) becomes

$$\begin{aligned}
H_{\mu\mu'}^{jj'}(\mathbf{k}) &= \sum_{\mathbf{R}} e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} e^{i\mathbf{k} \cdot \mathbf{R}} E_{\mu\mu'}^{jj'}(\mathbf{R}) \\
&= E_{\mu\mu'}^{jj'}(\mathbf{0}) + e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}_1} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} e^{i\mathbf{k} \cdot \mathbf{R}_1} E_{\mu\mu'}^{jj'}(\mathbf{R}_1) \\
&+ e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}_2} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} e^{i\mathbf{k} \cdot \mathbf{R}_2} E_{\mu\mu'}^{jj'}(\mathbf{R}_2) + e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}_3} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} e^{i\mathbf{k} \cdot \mathbf{R}_3} E_{\mu\mu'}^{jj'}(\mathbf{R}_3) \\
&+ e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}_4} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} e^{i\mathbf{k} \cdot \mathbf{R}_4} E_{\mu\mu'}^{jj'}(\mathbf{R}_4) + e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}_5} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} e^{i\mathbf{k} \cdot \mathbf{R}_5} E_{\mu\mu'}^{jj'}(\mathbf{R}_5) \\
&+ e^{\frac{ie}{\hbar} \int_0^{\mathbf{R}_6} \mathbf{A}(\mathbf{r}') \cdot d\mathbf{r}'} e^{i\mathbf{k} \cdot \mathbf{R}_6} E_{\mu\mu'}^{jj'}(\mathbf{R}_6).
\end{aligned} \tag{2.11}$$

In the presence of a perpendicular magnetic field $\mathbf{B}\hat{z}$ with the vector potential $\vec{A} = (0, Bx, 0)$. For convenience, let us switch to a shorthand notation for these extra terms and define

$$\theta_{m,n}^{m',n'} \equiv -\frac{e}{\hbar} \int_{m,n}^{m',n'} \vec{A} \cdot d\mathbf{r}. \tag{2.12}$$



Hình 2.2: Site index

With the given Landau gauge, the line integral $\int \vec{A} \cdot d\mathbf{r}$ is evaluated to $\int Bx dy$. Let us now express the Hamiltonian from the zero-field are given by² with the transform

hopping parameters, noting that the NN coordinates are $x = \frac{ma}{2}(m = \pm 1, \pm 2)$ and $y = \frac{na\sqrt{3}}{2}(n = 0, \pm 1)$, a being the lattice constant, are shown in Fig (2.2). Since $dy = 0$ along the x direction, $\theta_{m,n}^{m\pm 2,n} = 0$, and using *ansatz* $x = \frac{ma}{2}$ for lattice site, the $\theta_{m,n}^{m',n'}$ can be written as

$$\theta_{m,n}^{m',n'} = \begin{cases} 0 & m' = m \pm 2, n' = n \\ \pm \frac{e}{\hbar} \frac{Ba^2\sqrt{3}}{4}(m + 1/2) & m' = m + 1, n' = n \pm 1 \\ \pm \frac{e}{\hbar} \frac{Ba^2\sqrt{3}}{4}(m - 1/2) & m' = m - 1, n' = n \pm 1 \end{cases} \quad (2.13)$$

Identifying $\frac{Ba^2\sqrt{3}}{4}$ as the magnetic flux Φ passing through per unit cell and \hbar/e as the flux quantum Φ_0 , then we have

$$\begin{aligned} H_{\mu\mu'}^{jj'}(\mathbf{k}) &= E_{\mu\mu'}^{jj'}(\mathbf{0}) + e^{i\theta_{m,n}^{m',n'}} e^{i\mathbf{k}\cdot\mathbf{R}_1} E_{\mu\mu'}^{jj'}(\mathbf{R}_1) + e^{i\theta_{m,n}^{m',n'}} e^{i\mathbf{k}\cdot\mathbf{R}_2} E_{\mu\mu'}^{jj'}(\mathbf{R}_2) \\ &+ e^{i\theta_{m,n}^{m',n'}} e^{i\mathbf{k}\cdot\mathbf{R}_3} E_{\mu\mu'}^{jj'}(\mathbf{R}_3) + e^{i\theta_{m,n}^{m',n'}} e^{i\mathbf{k}\cdot\mathbf{R}_4} E_{\mu\mu'}^{jj'}(\mathbf{R}_4) \\ &+ e^{i\theta_{m,n}^{m',n'}} e^{i\mathbf{k}\cdot\mathbf{R}_5} E_{\mu\mu'}^{jj'}(\mathbf{R}_5) + e^{i\theta_{m,n}^{m',n'}} e^{i\mathbf{k}\cdot\mathbf{R}_6} E_{\mu\mu'}^{jj'}(\mathbf{R}_6). \end{aligned} \quad (2.14)$$

The Hamiltonian depends on the site index m and does not invariant under the translation of a lattice vector along the x axis. In order to restore this invariance, we can look at the case where the ratio of magnetic flux and flux quanta is a rational number $\Phi/\Phi_0 = p/q$. This mean, we have expand the unit cell in the x direction, the Hamiltonian becomes invariant under translational, allowing us to define what we will call the magnetic unit cell, which is consisting of q M -atoms. We define a new basis set of $3q$ atomic orbitals $\phi_\mu^j(x, y) = \phi_\mu^j(ma/2, y)$ where $m = 1, 2, \dots, q$. Note that

$$\begin{cases} e^{ik_x a} \phi_\mu^j \left(m \frac{a}{2}, y \right) = \phi_\mu^j \left((m+2) \frac{a}{2}, y \right) \\ e^{-ik_x a} \phi_\mu^j \left(m \frac{a}{2}, y \right) = \phi_\mu^j \left((m-2) \frac{a}{2}, y \right) \\ e^{\pm ik_x \frac{a}{2}} e^{\pm ik_y \frac{a\sqrt{3}}{2}} \phi_\mu^j \left(m \frac{a}{2}, n \frac{a\sqrt{3}}{2} \right) = \phi_\mu^j \left((m \pm 1) \frac{a}{2}, (n \pm 1) \frac{a\sqrt{3}}{2} \right) \end{cases} \quad (2.15)$$

Consequently the Hamiltonian matrix in the new basis is written as

$$\begin{aligned}
H_{\mu\mu'}^{jj'}(\mathbf{k}) = & E_{\mu\mu'}^{jj'}(\mathbf{0})\delta_{m,m} + e^{i\theta_{m,n}^{m',n'}} E_{\mu\mu'}^{jj'}(\mathbf{R}_1)\delta_{m,m+2}\delta_{n,n} + e^{i\theta_{m,n}^{m',n'}} E_{\mu\mu'}^{jj'}(\mathbf{R}_2)\delta_{m,m+1}\delta_{n,n-1} \\
& + e^{i\theta_{m,n}^{m',n'}} E_{\mu\mu'}^{jj'}(\mathbf{R}_3)\delta_{m,m-1}\delta_{n,n-1} + e^{i\theta_{m,n}^{m',n'}} E_{\mu\mu'}^{jj'}(\mathbf{R}_4)\delta_{m,m+2}\delta_{n,n} \\
& + e^{i\theta_{m,n}^{m',n'}} E_{\mu\mu'}^{jj'}(\mathbf{R}_5)\delta_{m,m-1}\delta_{n,n+1} + e^{i\theta_{m,n}^{m',n'}} E_{\mu\mu'}^{jj'}(\mathbf{R}_6)\delta_{m,m+1}\delta_{n,n+1}.
\end{aligned} \tag{2.16}$$

By substituting Eq (2.15) and Eq (2.13) into Eq (2.16), we have


$$\begin{aligned}
H_{\mu\mu'}^{jj'}(\mathbf{k}) = & E_{\mu\mu'}^{jj'}(\mathbf{0}) + E_{\mu\mu'}^{jj'}(\mathbf{R}_1) + e^{-2i\pi(m+1/2)p/q} e^{-i\beta} E_{\mu\mu'}^{jj'}(\mathbf{R}_2) \\
& + e^{-2i\pi(m-1/2)p/q} e^{-i\beta} E_{\mu\mu'}^{jj'}(\mathbf{R}_3) + E_{\mu\mu'}^{jj'}(\mathbf{R}_4) \\
& + e^{-2i\pi(m-1/2)p/q} e^{i\beta} E_{\mu\mu'}^{jj'}(\mathbf{R}_5) + e^{2i\pi(m+1/2)p/q} e^{i\beta} E_{\mu\mu'}^{jj'}(\mathbf{R}_6).
\end{aligned} \tag{2.17}$$

Now, for given flux ratio p/q , only the q determines the periodicity of the magnetic cell assuming p and q are mutually prime numbers. When we plot the band energies while varying the p , we obtain the famous Hofstadter butterfly³, a complex fractal structure as seen in Fig. 2.3. This structure is generated at the $K = (\frac{4\pi}{3a}, 0)$ k-point. This fractal spectrum is a result of two competing effects, lattice periodicity and magnetic unit cell periodicity enforced by the presence of the magnetic field. Eq. 2.16 give the following matrix which must be diagonalized to obtain the energy eigenvalues.

The magnetic field enters the TB Hamiltonian only through the fraction p/q , which is the magnetic flux through the primitive unit cell of the lattice. In general, as the lattice geometry evolves, the area of the primitive unit cell changes $(m + 1/2)$ times.

Using Eq (2.16), we obtain the eigenvalue equation $H\phi_\mu^j = E\phi_\mu^j$ and

$$H = \begin{pmatrix} h_0 & h_1 & h_2 \\ h_1^* & h_{11} & h_{12} \\ h_2^* & h_{12}^* & h_{22} \end{pmatrix} \tag{2.18}$$




Hình 2.3: Hofstadter's butterfly for one band $|dz\rangle \equiv |\phi_1^1(x, y)\rangle$ (left) and all band (right) with $q = 797$ and vary p from 1 to q with field strength $B_0 = 4.6928 \times 10^4$ T.

where

$$h_0 = \begin{pmatrix} \epsilon_1 & 2t_0 \cos \zeta_1 & t_0 & 0 & \cdots & 0 & t_0 & 2t_0 \cos \gamma_1 \\ 2t_0 \cos \gamma_1 & \epsilon_1 & 2t_0 \cos \zeta_2 & t_0 & 0 & \cdots & 0 & t_0 \\ t_0 & 2t_0 \cos \gamma_2 & \epsilon_1 & 2t_0 \cos \zeta_3 & t_0 & 0 & 0 & 0 \\ \vdots & \vdots & \vdots & \vdots & \vdots & \vdots & \vdots & \vdots \\ t_0 & 0 & \cdots & 0 & t_0 & 2t_0 \cos \gamma_7 & \epsilon_1 & 2t_0 \cos \zeta_7 \\ 2t_0 \cos \zeta_8 & t_0 & \cdots & 0 & 0 & t_0 & 2t_0 \cos \gamma_8 & \epsilon_1 \end{pmatrix} \quad (2.19)$$

and $h_0, h_1, h_2, h_{11}, h_{12}, h_{22}$ are sub-matrices have size $q \times q$.

An alternative approach to the derivation of the Hamiltonian under an uniform magnetic field is given in Appendix B.



Hình 2.4: An easy and intuitive visualization of matrix h_0 one band(left) and matrix H all band(right) through standard plotter with $q = 20$.

2.3 Spin-orbit coupling

Due to the heavy mass of the transition-metal M atom, its spin orbit coupling(SOC) can be large. For the sake of simplicity, only the on-site contribution, namely, the $\mathbf{L} \cdot \mathbf{S}$ term from M atoms. Using the bases $\left\{ |d_{z^2}, \uparrow\rangle, |d_{xy}, \uparrow\rangle, |d_{x^2-y^2}, \uparrow\rangle, |d_{z^2}, \downarrow\rangle, |d_{xy}, \downarrow\rangle, |d_{x^2-y^2}, \downarrow\rangle \right\}$, we get the SOC contribution to the Hamiltonian as

$$H' = \lambda \mathbf{L} \cdot \mathbf{S} = \frac{\lambda}{2} \begin{pmatrix} L_z & 0 \\ 0 & -L_z \end{pmatrix}, \quad (2.20)$$

in which

$$L_z = \begin{pmatrix} 0 & 0 & 0 \\ 0 & 0 & 2i \\ 0 & -2i & 0 \end{pmatrix} \quad (2.21)$$

is the matrix of \hat{L}_z (z component of the orbital angular momentum) in bases of $d_{z^2}, d_{xy}, d_{x^2-y^2}$ and λ is characterized the strength of the SOC. Noting that, under the three bases, the matrix elements of \hat{L}_x and \hat{L}_y are all zeros. There for the Hamiltonian for the magnetic

unit cell with the SOC as follows

$$H_{\text{SOC}}(\mathbf{k}) = \mathbf{I}_2 \otimes H_0(\mathbf{k}) + H' \quad (2.22)$$

2.4 Landau levels

In solid-state physics, the behavior of electrons in magnetic fields is usually introduced by using the Hamiltonian

$$H = \frac{\mathbf{p} + e\mathbf{A}(\mathbf{r})^2}{2m}, \quad (2.23)$$

and the energy eigenfunctions are known as Landau levels

$$E = (n + 1/2) \hbar\omega_c. \quad (2.24)$$

This treatment is for free electrons,⁴ but near the bottom of the two-dimensional tight-binding band of TMD, the energy is approximately free-electron-like by Taylor expansion to second order of \mathbf{k}

$$\begin{aligned} H(\mathbf{k}) &\approx 2t_0 \left[1 - \frac{a^2 k_x^2}{2} + 2 \left(1 - \frac{a^2 k_x^2}{8} \right) \left(1 - \frac{3a^2 k_y^2}{8} \right) \right] \\ &= t_0 \frac{3}{16} (32 + a^4 k_x^2 k_y^2) - t_0 \frac{3}{2} a^2 (k_x^2 + k_y^2) + \epsilon_1, \end{aligned} \quad (2.25)$$

the first term a^2 is negligibly small and another can be treated like constant, then we have

$$H(\mathbf{k}) \approx 6t_0 - \frac{3}{2} t_0 a^2 (k_x^2 + k_y^2) + \epsilon_1. \quad (2.26)$$

One of the ways derivation of effective mass m^* is substitution $\mathbf{k} \rightarrow \mathbf{p} + e\mathbf{A}$

$$\begin{aligned} H(\mathbf{p}) &\approx 6t_0 - \frac{3}{2}t_0 \frac{a^2}{\hbar^2} \left[p_x^2 + (p_y + eBx)^2 \right] + \epsilon_1 \\ &\approx 6t_0 - \frac{3}{2}t_0 \frac{a^2}{\hbar^2} p_x^2 + \frac{3}{2}t_0 \frac{a^2}{\hbar^2} (eB)^2 \left[x - \left(-\frac{k_y}{eB} \right) \right]^2 + \epsilon_1. \end{aligned} \quad (2.27)$$

The Eq (2.24) can be rewrite in the form as

$$E(\mathbf{p}) = 6t_0 - \left[\frac{1}{2m^*} p_x^2 + \frac{1}{2} m^* \omega_c^2 (x - x_0)^2 \right] \quad (2.28)$$

where $m^* = \frac{\hbar^2}{(3t_0 a^2)}$ is the effective mass and $x_0 = \sqrt{-\frac{k_y}{eB}}$. Hence, the cyclotron frequency is


$$\omega_c = \frac{eB}{m^*} = \frac{8\pi\sqrt{3}t_0}{\hbar} \frac{p}{q}, \quad (2.29)$$

and therefore the Landau levels near the bottom of the band $|d_{z2}\rangle$ can be written as

$$\begin{aligned} E &= 6t_0 - \hbar\omega_c(n + 1/2) + \epsilon_1 \\ &= t_0 \left(6 - 8\pi\sqrt{3}\frac{p}{q}(n + 1/2) \right) + \epsilon_1, \end{aligned} \quad (2.30)$$

in linear order of an uniform-flux, where n is Landau index.

In Fig 2.4 we compare the spectrum of a small section of triangular lattice with $p/q = 1/797$. With the fan of Landau levels given by Eq.(2.26) plotted in Fig 2.4(b). The fan of Landau levels can be clearly seen emergin from the partern in Fig 2.4(a). It is this fan of Landau levels that responsible for the de Haas-van Alphen and Shubnikov-de Haas effects.^{5,6,7,8} The Landau levels are all close to being linear in B , resulting from the magnetic quantization of parabolic bands at $B = 0$. In our model study, Landau levels can be classified into specific groups. In each group, each levels can be further labeled by a Landau index n . Figure 2.4 displays a blowup of the low uniform magnetic region and the LLs as a function of Φ/Φ_0 ⁹



Hình 2.5: (a) Same plot as Fig 2.3 but we consider a small area and (b) is the Landau fan diagram show for the first $n = 10$ levels near the bottom of the conduction band for a magnetic field up to $B = 100$ T.

CHƯƠNG 3

DISCUSSION AND FUTURE WORK

REFERENCES

- [1] Fırat Yalçın. Tight binding investigation of graphene nanostructures under magnetic field. Master's thesis, Middle East Technical University, 2019.
- [2] Gui-Bin Liu, Wen-Yu Shan, Yugui Yao, Wang Yao, and Di Xiao. Three-band tight-binding model for monolayers of group-vib transition metal dichalcogenides. *Phys. Rev. B*, 88:085433, Aug 2013.
- [3] Douglas R. Hofstadter. Energy levels and wave functions of bloch electrons in rational and irrational magnetic fields. *Phys. Rev. B*, 14:2239–2249, Sep 1976.
- [4] James G. Analytis, Stephen J. Blundell, and Arzhang Ardavan. Landau levels, molecular orbitals, and the hofstadter butterfly in finite systems. *American Journal of Physics*, 72(5):613–618, 05 2004.
- [5] D. Shoenberg. *Magnetic Oscillations in Metals*. Cambridge Monographs on Physics. Cambridge University Press, 1984.
- [6] J. Singleton. *Band Theory and Electronic Properties of Solids*. Oxford Master Series in Condensed Matter Physics. OUP Oxford, 2001.
- [7] S. Blundell. *Magnetism in Condensed Matter*. Oxford Master Series in Condensed Matter Physics 4. OUP Oxford, 2001.
- [8] C. Kittel. *Quantum Theory of Solids*. Wiley, 1987.
- [9] Juan Li, Yi-Fei Wang, and Chang-De Gong. Tight-binding electrons on triangular and kagomé lattices under staggered modulated magnetic fields: quantum

- hall effects and hofstadter butterflies. *Journal of Physics: Condensed Matter*, 23(15):156002, apr 2011.
- [10] Andor Kormányos, Viktor Zólyomi, Neil D. Drummond, Péter Rakyta, Guido Burkard, and Vladimir I. Fal’ko. Monolayer mos_2 : Trigonal warping, the Γ valley, and spin-orbit coupling effects. *Phys. Rev. B*, 88:045416, Jul 2013.
 - [11] Fengyuan Xuan and Su Ying Quek. Valley zeeman effect and landau levels in two-dimensional transition metal dichalcogenides. *Phys. Rev. Res.*, 2:033256, Aug 2020.
 - [12] Jun John Sakurai and Jim Napolitano. *Modern quantum mechanics*. Cambridge University Press, 2020.
 - [13] Philip George Harper. The general motion of conduction electrons in a uniform magnetic field, with application to the diamagnetism of metals. *Proceedings of the Physical Society. Section A*, 68(10):879–892, 1955.
 - [14] Yakir Aharonov and David Bohm. Significance of electromagnetic potentials in the quantum theory. *Physical review*, 115(3):485–497, 1959.
 - [15] Rudolph Peierls. Zur theorie des diamagnetismus von leitungselektronen. *Zeitschrift für Physik*, 80(11):763–791, 1933.
 - [16] Gi-Yeong Oh. Energy spectrum of a triangular lattice in a uniform magnetic field: Effect of next-nearest-neighbor hopping. *Journal of the Korean Physical Society*, 37(5):534–539, 2000.

APPENDIX A

Construct matrix

In Ref.², G-B Liu *et al.* constructed

APPENDIX B

Harper's equation

Ta xét phương trình Harper cho trường hợp mạng tinh thể là mạng vuông được cho bởi Hamiltonian từ ví dụ trong bài¹

$$\begin{aligned} H(\mathbf{k}) &= 2t \left[\cos(k_x a) + \cos(k_y a) \right] \\ &= t \left[e^{ik_x a} + e^{-ik_x a} + e^{ik_y a} + e^{-ik_y a} \right] \end{aligned} \tag{B.1}$$

Bằng cách áp dụng Peierls's substitution $\mathbf{k} \rightarrow (\vec{p} - e\mathbf{A})/\hbar$, ta có

$$\begin{aligned} H &= t \left[e^{ik_x a} + e^{-ik_x a} + e^{i(p_y - eBx)a/\hbar} + e^{-i(p_y - eBx)a/\hbar} \right] \\ &= t \left[e^{ik_x a} + e^{-ik_x a} + e^{ip_y a/\hbar} e^{i2\pi Bx/\Phi_0} + e^{-ip_y a/\hbar} e^{-i2\pi Bx/\Phi_0} \right] \end{aligned} \tag{B.2}$$

Thay $x = ma$ và $y = na$ cho toạ độ của mạng tinh thể vuông, ta thu được phương trình Harper

Let us consider the case of hexagonal lattice with $|d_{z^2}\rangle$ band as a basis under an

uniform magnetic field given by the Landau gauge $\vec{A} = (0, Bx, 0)$. Given

$$\begin{aligned}
h_0 &= 2t_0 (\cos 2\alpha + 2 \cos \alpha \cos \beta) + \epsilon_1 \\
&= 2t_0 \left[\cos(k_x a) + 2 \cos\left(\frac{k_x a}{2}\right) \cos\left(\frac{\sqrt{3}k_y a}{2}\right) \right] + \epsilon_1 \\
&= 2t_0 \left\{ \cos(k_x a) + \cos\left[\left(k_x + \sqrt{3}k_y\right) \frac{a}{2}\right] + \cos\left[\left(k_x - \sqrt{3}k_y\right) \frac{a}{2}\right] \right\} + \epsilon_1 \\
&= 2t_0 \left\{ \cos\left(p_x \frac{a}{\hbar}\right) + \cos\left[\left(p_x + \sqrt{3}eBx + \sqrt{3}p_y\right) \frac{a}{2\hbar}\right] \right. \\
&\quad \left. + \cos\left[\left(p_x - \sqrt{3}eBx - \sqrt{3}p_y\right) \frac{a}{2\hbar}\right] \right\} + \epsilon_1 \\
&= t_0 \left[e^{ip_x \frac{a}{\hbar}} + e^{-ip_x \frac{a}{\hbar}} + e^{i(p_x + \sqrt{3}eBx + \sqrt{3}p_y)a/2\hbar} + e^{-i(p_x + \sqrt{3}eBx + \sqrt{3}p_y)a/2\hbar} \right. \\
&\quad \left. + e^{i(p_x - \sqrt{3}eBx - \sqrt{3}p_y)a/2\hbar} + e^{-i(p_x - \sqrt{3}eBx - \sqrt{3}p_y)a/2\hbar} \right] + \epsilon_1.
\end{aligned} \tag{B.3}$$

We replaced $\hbar k$ in the above function by the operators $\vec{p} - e\vec{A}/c$ in order to create an operator out of h_0 . When this substitution is made, the Hamiltonian element is seen to contain translation operators $\exp[ap_x/\hbar], \exp[a\sqrt{3}p_y/(2\hbar)]$. Depending on the gauge chosen, there are, in addition, certain phase factors dependent on the magnetic field strength, which multiply the translation operators. The Landau gauge was $\vec{A} = (0, Bx, 0)$ was chosen, then only the translation along y are multiplied by phases.³ Applying the BCH's formula and taking to account the commutation relation $[x, p_x] = i\hbar$

$$\begin{aligned}
e^{\pm i(p_x + \sqrt{3}eBx)a/2\hbar} &= e^{\pm ip_x a/2\hbar} e^{\pm i\sqrt{3}eBxa/2\hbar} e^{-\frac{1}{2}[\pm ip_x, \pm i\sqrt{3}eBx]a^2/2\hbar^2} \\
&= e^{\pm ip_x a/2\hbar} e^{\pm i\sqrt{3}eBxa/2\hbar} e^{\mp i\sqrt{3}eBa^2/8\hbar}
\end{aligned} \tag{B.4}$$

Substituting $x = \frac{ma}{2}$ into (B.2), this leads to

$$e^{\pm i(p_x + \sqrt{3}eBx)a/2\hbar} = e^{\pm ip_x a/2\hbar} e^{\pm i\sqrt{3}eB(m+1/2)a/4\hbar} \tag{B.5}$$

And

$$\begin{aligned} e^{\pm i(p_x - \sqrt{3}eBx)a/2\hbar} &= e^{\pm ip_x a/2\hbar} e^{\mp i\sqrt{3}eBxa/2\hbar} e^{-\frac{1}{2}[\pm ip_x, \mp i\sqrt{3}eBx]a^2/2\hbar^2} \\ &= e^{\pm ip_x a/2\hbar} e^{\mp i\sqrt{3}eBxa/2\hbar} e^{\mp i\sqrt{3}eBa^2/8\hbar} \end{aligned} \quad (\text{B.6})$$

Substituting $x = \frac{ma}{2}$ into (B.4), this leads to

$$e^{\pm i(p_x - \sqrt{3}eBx)a/2\hbar} = e^{\pm ip_x a/2\hbar} e^{\mp i\sqrt{3}eB(m-1/2)a^2/4\hbar} \quad (\text{B.7})$$

The operators $e^{\pm ip_x a/2\hbar}$, $e^{\pm ip_y \sqrt{3}a/2\hbar}$ can be regconized as translational operators, we can rewrite (B.1) as The time-indepentdent Schrödinger's equation now becomes

$$\begin{aligned} &t_0\varphi_1(x+a, y) + t_0\varphi_1(x-a, y) + t_0\varphi_1(x + \frac{a}{2}, y + \frac{a\sqrt{3}}{2})e^{\frac{ie}{\hbar}B(m+1/2)\frac{a^2\sqrt{3}}{4}} \\ &+ t_0\varphi_1(x + \frac{a}{2}, y - \frac{a\sqrt{3}}{2})e^{-\frac{ie}{\hbar}B(m+1/2)\frac{a^2\sqrt{3}}{4}} + t_0\varphi_1(x - \frac{a}{2}, y + \frac{a\sqrt{3}}{2})e^{\frac{ie}{\hbar}B(m+1/2)\frac{a^2\sqrt{3}}{4}} \\ &+ t_0\varphi_1(x - \frac{a}{2}, y - \frac{a\sqrt{3}}{2})e^{-\frac{ie}{\hbar}B(m-1/2)\frac{a^2\sqrt{3}}{4}} + \epsilon_1\varphi_1(x, y) = E_1\varphi_0(x, y), \end{aligned} \quad (\text{B.8})$$

for the sake of simplicity let us define $\varphi_0 \equiv |d_{z^2}\rangle$.

It is reasonable to assume planewave behavior in the y direction, since the coefficents in the above equation only involve x . Therefore, we can assume the partial solution for y to be in the form

$$\varphi(\frac{ma}{2}, \frac{na\sqrt{3}}{2}) = e^{ik_y n \frac{a\sqrt{3}}{2}} G(m), \quad (\text{B.9})$$

which reduces (B.6) to

$$\begin{aligned} &t_0\varphi_0(m+2) + t_0\varphi_0(m-2) + t_0\varphi_0(m+1)e^{2i\pi(m+1/2)p/q}e^{ik_y a\sqrt{3}/2} \\ &+ t_0\varphi_0(m+1)e^{-2i\pi(m+1/2)p/q}e^{-ik_y a\sqrt{3}/2} + t_0\varphi_0(m-1)e^{2i\pi(m-1/2)p/q}e^{ik_y a\sqrt{3}/2} \\ &+ t_0\varphi_0(m-1)e^{-2i\pi(m-1/2)p/q}e^{-ik_y a\sqrt{3}/2} + \epsilon_1\varphi_0(m) = E_1\varphi_0(m), \end{aligned} \quad (\text{B.10})$$

this is equivalent to Eq. 2.16 we have mentioned in Section 2.2. Equation B.7 is sometimes called ‘‘Harper’s equation’’.¹³ Since different m values give different equations, one

reaches a unique set of equations when Φ/Φ_0 is a rational number p/q and m goes through q different values, essentially resulting in the Hamiltonian matrix written for a magnetic unit cell enlarged in x direction q times.

Trong trường hợp của TMD của² đã đưa ra thì ta đã bỏ qua đi đóng góp của nguyên tử X , dẫn đến cấu trúc mạng tinh thể của TMD lục giác trở thành mạng tam giác bình thường và từ đó ta có thể mapping từ mạng tam giác thành trường hợp của mạng vuông. Ở mạng tam giác ta đã đưa ra được rằng các toán tử tịnh tiến phải tuân theo công thức Baker-Campbell-Hausdorff.