MIX PROPORTION DATA SHEET

(FORM : T2-MD2)

PROJECT : **Mess Taruna AAL**
LOCATION : **Tanjungsari**
CONTRACTOR : **PT Karen Nauli**

No **4071 /TC/QA/T2MD2/NA/IX/2024**

PROJECT REQUIREMENT

Grade of Concrete	:	=	**K-300 (Fc 25MPa)**	
Slump	:	=	100	± 20 mm
W/Ct Ratio	:	=	0.55	
CODE	:	=		
SAP CODE	:	=		

COMPOSITION FOR 1CuM (SSD Condition)

Water	: Deep Well	=	180	Lt
Cement	: OPC	=	325	kg
Fly Ash	: Paiton (Type C)	=	-	

Volume of Aggregates

AGGREGATES

Gravel-02	: Split 12 - 25 mm	=	677	kg
Gravel-01	: Split 5 - 12 mm	=	372	kg
Sand	: Natural Sand	=	850	kg

ADMIXTURE

Retarder	: GCP Daratard 38M	=	1.120	Ltr
Superplasticizer	: GCP Adva 512LN	=		
HRWR	:	=		

TOTAL	=	2,406	kg
Density	=	2.406	T/CuM
Volume	=	0.998	CuM

REMARK FA0%

* PT Solusi Bangun Beton will not responsible for all quality matters if any material other than specified herewith is applied as substitution or addition to mix design at above.

As part of PT. Solusi Bangun Beton commitment to continous improvement,
we reserve the right to change raw material sources or modify mix design
in accordance with technical standard without notice

PORTEX - LOCKED - 2026-04-30