Head Office : Talavera Suites 15 th Floor, Jl. Let Jend. TB Simatupang no 22-26 Jakarta Phone 021 29861000 fax 021 29863333
Central Laboratory: Jl. Rawa Sumur timur Ujung Komplek JIEP Pulo gadung

MIX PROPORTION DATA SHEET
(FORM : T2-MD2)

PROJECT : NPEA Seksi I
LOCATION : Onsite
CONTRACTOR : Hutama - Abipraya KSO

NO : 5096 /TC/QA/T2MD2/na/IV/2025

Material Price

PROJECT REQUIREMENT												
Grade of Concrete		=	**K-350 (Fc 30MPa)**		**K-350 (Fc 30MPa)**		**K-300 (Fc 25MPa)**		**K-250 (Fc 20MPa)**		**K-125 (Fc 10MPa)**	
Slump		=	120	± 20 mm	120	± 20 mm	120	± 20 mm	120	± 20 mm	120	± 20 mm
W/C Ratio		=	0.42		0.48		0.53		0.54		0.85	
CODE		=										
SAP CODE		=										
COMPOSITION FOR 1CuM (SSD Condition)												
Water	: Deep Well	=	180	Lt	180	Lt	180	Lt	185	Lt	185	Lt
Cement 1	: SprintPro	=	429	kg	375	kg	340	kg	343	kg	218	kg
Cement 2	: Power pro	=	-		-		-		-		-	
Slag	: KSI	=	-		-		-		-		-	
Fly Ash	: Suralaya		-		-		-		-		-	
MicroFiber	:	=										
Volume of Aggregates												
AGGREGATES												
Gravel-03	: Maloko 10/20	=	-		-		-					
Gravel-02	: Maloko 5/25	=	879	kg	880	kg	880	kg	879	kg	879	kg
Gravel-01	: Maloko 5/15	=	154	kg	154	kg	154	kg	155	kg	155	kg
Sand 1	: Tayan	=	431	kg	457	kg	475	kg	466	kg	529	kg
Sand 2	: Optima sand	=	284	kg	301	kg	313	kg	307	kg	348	kg
ADMIXTURE												
Admix1	: DARATARD 36 MR	=	0.943	Ltr	0.825	Ltr	0.747	Ltr	0.754	Ltr	0.479	Ltr
Admix2	: DARACEM 133 ADV	=	0.857	Ltr	0.750	Ltr	0.679	Ltr	-		-	
Admix3	: VISCOCRETE 1826	=	-		-		-		-		-	
TOTAL		=										
Density Fresh Concrete		=	2,359	T/CuM	2,349	T/CuM	2,343	T/CuM	2,335	T/CuM	2,313	T/CuM
Volume		=	1,002	Ml	1,002	Ltr	1,001	Ltr	1,001	Ltr	1,000	Ltr
REMARK												
			NFA		NFA		NFA		NFA		NFA	
			Cement Type V		Cement Type I		Cement Type I		Cement Type I		Cement Type I	
			Kelas B1		Kelas B1		-		Kelas C		Kelas E	

* PT Solusi Bangun Beton will not responsible for all quality matters if any material other than specified herewith is applied as substitution or addition to mix design at above.

As part of PT. Solusi Bangun Beton commitment to continous improvement, we reserve the right to change raw material sources or modify mix design in accordance with technical standard without notice

Form No : SF 4128	
16 June 2016	Ver 1.1