

TECHNICAL DATA SHEET Inslogic Galaxy PLA Filament



Inslogic Galaxy PLA Filament is infused with rich pigments and a unique color blend, delivering a dazzling, glossy finish that shifts between deep blue, purple, and green - mimicking the beauty of a nebula. It is easy to print, gentle on nozzles, and produces smooth prints with virtually invisible layer lines. Ideal for artistic projects, prototypes, and even jewelry, it combines elegance, fluidity, and cosmic flair in every print.

Key Features

- One-of-a-kind design inspired by outer space
- Glossy, shimmering finish with dynamic color shifts
- Smooth prints with minimal visible layers
- Effortless printing

Applications

- Art and design projects
- Decorative items
- Prototyping
- Concept models and prototypes



Specifications

Material Name	Inslogic Galaxy PLA
Diameter	1.75 ± 0.03 mm
Net Filament Weight	1 kg

Recommended Print Settings

Drying Settings	50 °C, 4h
Nozzle Size	0.4, 0.6 mm
Nozzle Temperature & Printing Speed	200-230 °C, ≤250 mm/s
Bed Temperature	50 - 60 °C
Cooling Fan Speed	100%
Bed Type	Textured PEI Sheet, Cool Plate

Physical Properties

Property	Method	Metric
Density	ISO1183	1.2225 g/cm ³
Melting Temperature, 10 °C/min	ISO11357-3	167 °C
Glass Transition Temperature, 10 °C/min	ISO11357-3	60.9 °C
Heat Deflection Temperature at 0.45 MPa	ISO75	54.6 °C



Mechanical Properties

Property	Method	Metric
Tensile Strength	ISO527/2	44 MPa
Elongation at Break	ISO527/2	17%
Flexural Strength	ISO178	82 MPa
Flexural Modulus	ISO178	3342 MPa
Izod Impact, Notched (X - Y, 23 °C)	ISO180	3.9 KJ/m ²



3, 13/F, Grand City Plaza
1-17 Sai Lau Kok Road
Tsuen Wan, New Territories
Hong Kong

Contact

WhatsApp: (852) 6268 5255
Sales: sales@inslogic3d.com
Support: support@inslogic3d.com

Disclaimer:

To the best of our knowledge, the information contained herein is accurate. However, Inslogic, Inc. makes no warranty, expressed or implied, regarding the accuracy of these results to be obtained from the use thereof. The results presented in this data sheet are just for your information and comparison. They should not be used for project specifications or its quality evaluation. In view of the many factors that may affect the processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose.

Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of Inslogic materials for the intended application. Inslogic makes no warranty of any kind unless announced separately, to the fitness for any particular use or application. Inslogic shall not be made liable for any damage, injury, or loss induced from the use of Inslogic materials in any particular application. Before using Inslogic material read properly all the details in the available safety data sheet (SDS).