

Main characteristics	Test method	Interval	Acceptance criteria
Electrical properties			
Conductor resistance	IEC 60851 - 5.3	1)	0,02817 $\Omega\text{mm}^2/\text{m}$
Conductivity	1/R	1)	> 35,5 $\text{m}/(\Omega\text{mm}^2)$
Breakdown voltage			
- Dafibre 180 1 AL	IEC 60851 - 5.4	All sizes	350 V
- Dafibre 180 2 AL			560 V
- Dafibre 180 3 AL			750 V
Mechanical properties			
Elongation	IEC 60851-3.3	$t \leq 3,15$	$\geq 15\%$
		$t > 3,15$	$\geq 20\%$
Flexibility - Bending flatwise	IEC 60851-3.5	All sizes	10 x thickness
Adherence -Stretch	IEC 60851-3.5	All sizes	10 % stretch, no loss of adhesion