

Properties for DAFIBRE 180 AL

Main characteristics	Test method	Interval	Acceptance criteria
<u>Electrical properties</u>			
Conductor resistance	IEC 60851 - 5.3	1)	0,02817 Ωmm²/m
Conductivity	1/R	1)	> 35,5 m/(Ωmm²)
Breakdown voltage	IEC 60851 - 5.4	All sizes	
- Dafibre 180 1 AL			350 V
- Dafibre 180 2 AL			560 V
- Dafibre 180 3 AL			750 V
<u>Mechanical properties</u>			
Elongation	IEC 60851-3.3	t ≤ 3,15	≥ 15%
		t > 3,15	≥ 20%
Flexibility	IEC 60851-3.5	All sizes	10 x thickness
- Bending flatwise			
Adherence	IEC 60851-3.5	All sizes	10 % stretch, no loss of adhesion
-Stretch			

1. Dependence of dimension is expressed by the unit