

Materiál	Tvrdost	Nástrojový materiál	Vc	Ø160			Ø200 — Ø250			
				ae	ap	fz	ae	ap	fz	
K	Šedé litiny	≤200MPa	MC5020	300 (250—350)	≤DC	≤10	0.4 (0.3—0.5)	≤DC	≤10	0.4 (0.3—0.5)
			VP15TF	250 (200—300)	≤DC	≤10	0.4 (0.3—0.5)	≤DC	≤10	0.4 (0.3—0.5)
		≤350MPa	MC5020	220 (150—300)	≤DC	≤10	0.3 (0.2—0.4)	≤DC	≤10	0.3 (0.2—0.4)
			VP15TF	200 (150—300)	≤DC	≤10	0.3 (0.2—0.4)	≤DC	≤10	0.3 (0.2—0.4)
	Tvárné litiny	≤450MPa	MC5020	200 (150—250)	≤0.3 DC	≤10	0.3 (0.2—0.4)	≤0.2 DC	≤10	0.3 (0.2—0.4)
			VP15TF	170 (150—200)	≤0.3 DC	≤10	0.3 (0.2—0.4)	≤0.2 DC	≤10	0.3 (0.2—0.4)
		≤800MPa	MC5020	170 (150—200)	≤0.3 DC	≤10	0.2 (0.1—0.3)	≤0.2 DC	≤10	0.2 (0.1—0.3)
			VP15TF	150 (100—200)	≤0.3 DC	≤10	0.2 (0.1—0.3)	≤0.2 DC	≤10	0.2 (0.1—0.3)