

Species of wood	Normal condition of glued joints	Comparative strength of joints			
		Tooth-planed		Smooth	
		Strength	Wood failure	Strength	Wood failure
		Lbs. per sq. in.	Percent	Lbs. per sq in.	Percent
Sugar maple	Good	3132	62	3148	69
	Starved	2261	4	1993	6
	Chilled	2718	36	3014	27
White oak	Good	2401	51	2317	66
	Starved	2019	28	1786	26
	Chilled	2501	64	2508	70
Sitka spruce	Good	1792	78	1853	88
	Starved	1932	94	1941	96
	Chilled	1649	33	1803	61