Electronic Band Structure of Monolayer, Bilayer and Twisted Bilayer Graphene within a Tight-Binding Framework

Candidate Number: 23162
Department of Physics, University of Bath, UK, BA2 7AY

The electronic band structure of monolayer, Bernal-stacked bilayer, and twisted bilayer graphene is investigated within a unified tight-binding framework. Analytical momentum-space models are first implemented for monolayer and AB-stacked graphene to validate computational approach, reproducing the expected linear Dirac dispersion and quadratic low-energy spectrum, respectively. The method is then extended to twisted bilayer graphene using a real-space construction with distance-dependent interlayer hopping and sparse matrix diagonalisation. Commensurate moiré supercells are generated for twist angles between 2° and 6°, enabling systematic analysis of miniband formation. As the twist angle decreases, pronounced bandwidth suppression and enhanced density of states near charge neutrality are observed. The lowest miniband width decreases by more than a factor of five across the studied range and follows a sub-quadratic power-law dependence on twist angle ($\alpha \approx 1.4$). The results demonstrate that band flattening emerges naturally from geometric moiré reconstruction within a fully microscopic tight-binding description.

I. Introduction

Since its isolation in 2004, graphene has become a prototypical system for exploring two-dimensional electronic structure. A single graphene layer forms a honeycomb lattice with a two-atom basis, producing π-bands that intersect linearly at the equivalent K and K' points of the Brillouin zone. Near these points, the low-energy excitations obey a massless Dirac equation, giving rise to a linear dispersion $E = \hbar v_F |\mathbf{q}|$ and associated chiral behaviour[1].

Interlayer coupling qualitatively modifies this spectrum. In Bernal (AB) stacked bilayer graphene, strong hopping between dimer states replaces the linear Dirac dispersion with an approximately quadratic low-energy spectrum, yielding a four-band structure described within an extended tight-binding framework [2].

A more dramatic reconstruction occurs when the two layers are rotated relative to one another. Twisted bilayer graphene (TBG) forms a moiré superlattice whose period increases as the twist angle decreases. The relative rotation displaces the Dirac cones in momentum space, enabling interlayer hybridisation that produces minibands and enhanced density of states near charge neutrality [3]. At sufficiently small angles, theoretical models predict strong bandwidth suppression due to this hybridisation mechanism [4].

While continuum descriptions successfully capture the long-wavelength physics of small-angle TBG, a real-space tight binding approach retains microscopic transparency by explicitly encoding interatomic hopping processes. Such an approach allows systematic investigation of how geometric rotation and distance-dependent interlayer coupling reconstruct the electronic spectrum without invoking additional approximations.

In this work, monolayer, Bernal-stacked bilayer, and twisted bilayer graphene are studied within a unified tight-binding framework. The monolayer and AB bilayer cases serve as validation benchmarks. The primary objective is to quantify how the low-energy band structure, density of states, and miniband bandwidth evolve with twist angle in a fully microscopic model constructed directly from atomic coordinates and distance-dependent hopping amplitudes.

II. Theoretical Model

A. Monolayer Graphene

Monolayer graphene consists of a two-dimensional honeycomb lattice of carbon atoms with two inequivalent sublattices, A and B. The primitive lattice vectors are

$$\mathbf{a}_1 = a\left(\frac{1}{2}, \frac{\sqrt{3}}{2}\right), \quad \mathbf{a}_2 = a\left(-\frac{1}{2}, \frac{\sqrt{3}}{2}\right), \tag{1}$$

where $a = 2.46$ Å. The three nearest-neighbour vectors connecting sublattice A to B are

$$\boldsymbol{\delta}_1 = \frac{a}{\sqrt{3}}(0,1), \quad \boldsymbol{\delta}_2 = \frac{a}{\sqrt{3}}\left(-\frac{\sqrt{3}}{2}, -\frac{1}{2}\right), \tag{2}$$

$$\boldsymbol{\delta}_3 = \frac{a}{\sqrt{3}}\left(\frac{\sqrt{3}}{2}, -\frac{1}{2}\right). \tag{3}$$

Assuming electrons can only hop between nearest-neighbouring sites with hopping energy γ_0, the tight binding hamiltonian is

$$H_{mono} = -\gamma_0 \sum_{\langle ij \rangle} a_i^\dagger b_j + a_i b_j^\dagger \tag{4}$$

modified from [1] to only include first-nearest neighbours.

Transforming this to momentum space using derivation from [5], the Hamiltonian forms a 2x2 matrix for the two atom basis

$$H_{mono} = -\gamma_0 \begin{pmatrix} \epsilon_A & f(k) \\ f^*(k) & \epsilon_B \end{pmatrix} \tag{5}$$

where

$$f(k) = \sum_{i=1}^{3} e^{(i\mathbf{k}\cdot\boldsymbol{\delta}_i)} \tag{6}$$

Choosing the on-site energies $\epsilon_A = \epsilon_B = 0$, the energy bands have the form

$$E_{\pm}(\mathbf{k}) = \pm\gamma_0|f(\mathbf{k})| \tag{7}$$

At points K and K' at the edge of the Brillouin zone

$$\mathbf{K} = (\frac{4\pi}{3a}, 0) \tag{8}$$

the bands touch exactly, forming Dirac cones. Expanding the structure factor around the K point ($\mathbf{k} = \mathbf{K} + \mathbf{q}, |\mathbf{q}| << |\mathbf{K}|$) yields

$$f(\mathbf{K} + \mathbf{q}) \approx \frac{3a}{2}(q_x - iq_y) \tag{9}$$

giving the low-energy Dirac Hamiltonian

$$H \approx \hbar v_F(\sigma_x q_x + \sigma_y q_y) \tag{10}$$

where

$$v_F = \frac{\sqrt{3}}{2}\frac{a\gamma_0}{\hbar}. \tag{11}$$

This produces the linear dispersion

$$E = \pm\hbar v_F|\mathbf{q}|. \tag{12}$$

B. Bilayer Graphene - Bernal Stacking

Bilayer graphene in AB (Bernal) stacking consists of four atoms per unit cell: A_1, B_1 in layer 1 and A_2, B_2 in layer 2. The Hamiltonian is now formed from a 4 atom basis, so automatically moves to a 4x4 matrix.

Starting with two decoupled layers of graphene, the Hamiltonian becomes a block diagonal matrix where the diagonal terms are the two independent monolayer Hamiltonians

$$\begin{pmatrix} 0 & -\gamma_0 f & 0 & 0 \\ -\gamma_0 f^* & 0 & 0 & 0 \\ 0 & 0 & 0 & -\gamma_0 f \\ 0 & 0 & -\gamma_0 f^* & 0 \end{pmatrix} \tag{13}$$

In AB stacking B_1 sits directly above A_2, these two sites form a strong interlayer bond. To account for this, a coupling term of the form

$$\gamma_1(b^\dagger_{1,k}a_{2,k} + b_{1,k}a^\dagger_{2,k}) \tag{14}$$

where γ_1 is the interlayer hopping energy. This contribute to the off-diagonal elements in between rows 2 and 3

$$\begin{pmatrix} 0 & -\gamma_0 f & 0 & 0 \\ -\gamma_0 f^* & 0 & \gamma_1 & 0 \\ 0 & \gamma_1 & 0 & -\gamma_0 f \\ 0 & 0 & -\gamma_0 f^* & 0 \end{pmatrix} \tag{15}$$

Near the K point, the Hamiltonian becomes

$$\begin{pmatrix} 0 & v_F\pi & 0 & 0 \\ v_F\pi^\dagger & 0 & \gamma_1 & 0 \\ 0 & \gamma_1 & 0 & v_F\pi \\ 0 & 0 & v_F\pi^\dagger & 0 \end{pmatrix} \tag{16}$$

where $\pi = \hbar(q_x + iq_y)$. Integrating out the high-energy dimer states [2] yields the effective low-energy Hamiltonian. The interlayer coupling forms "dimer" pairs that form high-energy bands. The low-energy states of electrons are described by the 2x2 effective Hamiltonian

$$H_{eff} = -\frac{v_F^2}{\gamma_1}\begin{pmatrix} 0 & (\pi^\dagger)^2 \\ \pi^2 & 0 \end{pmatrix} \tag{17}$$

This effective Hamiltonian results in energy bands of the form

$$E(k) = \pm\frac{\hbar^2 k^2}{2m^*} \tag{18}$$

with effective mass

$$m^* = \frac{\gamma_1}{2v_F^2}. \tag{19}$$

C. Twisted Bilayer Graphene

TBG consists of two graphene layers, one rotated by an angle θ relative to the other. Unlike AB-stacked bilayer graphene, the twist position produces position-dependent hopping between all atoms in opposite layers.

Keeping layer 1 fixed, layer 2 is rotated by angle theta via rotation matrix

$$R(\theta) = \begin{pmatrix} cos(\theta) & -sin(\theta) \\ sin(\theta) & cos(\theta) \end{pmatrix} \tag{20}$$

leading to positions

$$\mathbf{r}_2 = R(\theta)\mathbf{r} \tag{21}$$

in layer 2. This rotation generates a moiré superlattice with real-space period

$$L_m = \frac{a}{2\sin(\theta/2)} \tag{22}$$

where for small twist angles ($\theta \ll 1$),

$$L_m \approx \frac{a}{\theta}. \tag{23}$$

In momentum space, the Dirac points are displaced under rotation of the two layers and become separated by

$$\Delta K = 2K\sin(\theta/2). \tag{24}$$

The small momentum mismatch enables interlayer hybridization between states differing by reciprocal lattice vectors of the moiré lattice [4].

The general tight-binding Hamiltonian for TBG may be written as

$$H = -\gamma_0 \sum_{\langle i,j \rangle, l} a^\dagger_{i,l} b_{j,l} + \sum_{i,j} t_\perp(\mathbf{r}_i - \mathbf{r}_j) a^\dagger_{i,1} b_{j,2} + \text{h.c.}, \quad (25)$$

where $l = 1, 2$ labels the layers and $t_\perp(\mathbf{r})$ describes distance-dependent interlayer hopping

$$t_\perp(\mathbf{r}) = t_0 e^{-(r-d)/r_0} \quad (26)$$

where r is the interatomic separation, d is the equilibrium interlayer spacing, and r_0 is the decay length parameter.

III. Computational Model

The electronic structure calculations were performed within a real-space tight-binding framework implemented in python. The computational approach follows directly from the theoretical Hamiltonians derived in Section II, but differs between monolayer/bilayer graphene and TBG due to the loss of primitive-cell periodicity

A. Monolayer and Bernal Bilayer Graphene

For monolayer graphene, the Hamiltonian was constructed in momentum space using the analytical form seen in Eq. 5 with the structure factor defined in Eq. 6. Energy bands were obtained by diagonalising the 2x2 Hamiltonian using NumPy's Hermitian eigensolver.

For Bernal-stacked bilayer graphene, the hamiltonian was extended to the 4 x 4 form derived in Eq. 15, including the dominant interlayer coupling γ_1. The Hamiltonian was evaluated on a uniform k-space grid around the K point, and eigenvalues were computed using numpy.linalg.eigvalsh.

The K-space sampling density was increased until the band structure and density of states were numerically converged. Convergence was verified by confirming that further refinement of the grid did not produce visible changes in the dispersion or DOS.

B. Twisted Bilayer Graphene: Real-Space construction

In TBG, rotation of one layer by an angle θ removes the simple two-atom basis description. Instead, a commensurate moiré supercell was constructed in real space.

Layer 1 atomic positions were generated from graphene primitive lattice vectors $\mathbf{a}_1, \mathbf{a}_2$. Layer 2 were obtained by applying the rotation matrix in Eq. 20 to each atomic coordinate in layer 1. Only commensurate twist angles were considered, ensuring periodic boundary conditions within the constructed supercell.

C. Tight-Binding Assembly

The real-space Hamiltonian was constructed according to

$$H_{ij} = \begin{cases} -\gamma_0, & \text{if } i,j \text{ are intralayer nearest neighbours} \\ t_\perp(\mathbf{r}_{ij}), & \text{if } i,j \text{ belong to different layers} \\ 0, & \text{otherwise} \end{cases} \quad (27)$$

To efficiently identify both intralayer and interlayer atom pairs, a k-d tree spatial search (SciPy's cKDTree) was employed. This reduces the neighbour searching scaling from $O(N^2)$ to approximately $O(NlogN)$ [6], which is essential for large moiré supercells containing several thousand atoms. Intralayer hopping was restricted to first-nearest neighbours by setting a cutoff radius $r = 1.1 \cdot r_{cc}$ where $r_{cc} = a/\sqrt{3}$ is the carbon-carbon bond length in the sublattice. In a similar sense an interlayer cutoff of $r = 5$ Å. The resulting neighbour lists were used to assemble the sparse Hamiltonian, where SciPy's sparse matrix tools were used [7], significantly reducing memory usage for large supercells.

D. Eigenvalue Computation

For moderate supercell sizes, full diagonalisation was performed to obtain all eigenvalues. For larger systems, only eigenvalues near charge neutrality were required. For $\theta \approx 2.3°$, the commensurate supercell contains 1041 atoms per layer (2082 total atomic sites), leading to a Hamiltonian matrix of dimension 2082×2082. As the moiré period scales as $L_M \propto 1/\theta$, the matrix size scales approximately as $N \propto 1/\theta^2$, making dense diagonalisation computationally prohibitive at small angles. The sparse representation of the Hamiltonian is therefore essential for maintaining manageable memory usage and enabling efficient shift-invert diagonalisation.

E. Density of States

The density of states was computed from the eigenvalue spectrum according to

$$D(E) = \frac{1}{N} \sum_n \delta(E_n - E) \quad (28)$$

where E_n are the eigenvalues of the Hamiltonian and N is the number of states. In practical numerical calculations, the Dirac delta function was approximated as a Gaussian of finite width η,

$$D(E) = \frac{1}{N} \sum_n \frac{1}{\sqrt{2\pi}\eta} exp\left(-\frac{(E_n - E)^2}{2\eta^2}\right) \quad (29)$$

which ensures smooth convergence of the discrete spectrum and enables clear visualisation of spectral features. Such Gaussian broadening is a standard numerical approximation in electronic structure calculations [8].



FIG. 1. 3D band structure of monolayer graphene calculated using nearest-neighbour tight-binding model ($\gamma_0 = 2.8$ eV). The linear band crossings at K and K' points form Dirac cones at zero energy.



FIG. 2. Band dispersion near a single Dirac points K. The linear energy-momentum relation confirms the Dirac spectrum $E = \pm\hbar v_F|\mathbf{q}|$.

F. Parameters

In all calculations, the nearest-neighbour intralayer hopping was set to $\gamma_0 = 2.8$ eV and the Bernal interlayer coupling to $\gamma_1 = 0.39$ eV. For twisted bilayer graphene, the interlayer hopping parameters were chosen as $t_0 = 0.35$ eV, decay length $r_0 = 0.45$ Å, and equilibrium interlayer spacing $d = 3.35$ Å. An interlayer cutoff radius of 5 Å was used; increasing this value did not significantly modify the extracted miniband bandwidths. The DOS broadening parameter was $\eta = 0.008$ eV. These values are consistent with commonly used tight-binding parametrisations in the literature [1],[3].

IV. Results

A. Validation: Monolayer and Bernal Bilayer Graphene

The tight-binding implementation was first validated against known results for monolayer and AB-stacked bilayer graphene.

For monolayer graphene, diagonalisation of the 2x2 Hamiltonian in Eq. 5 in a dense k-space grid ($N = 1000$ points, $\gamma_0 = 2.8$ eV) reproduces the characteristic linear band crossings at the K and K' points of the Brillouin zone, as shown in figure 1. The Dirac cones are isotropic near charge neutrality, and the conduction and valence bands meet precisely at zero energy.

A zoomed view around a single Dirac point in figure 2 confirms the linear dispersion $E = \pm\hbar v_F|\mathbf{q}|$. From the numerical slope of the dispersion, the Fermi velocity was extracted as $v_F \approx 1.0 \times 10^6$ m/s, in agreement with the theoretical value derived in Eq. 11 and with literature values [1]. The extracted Fermi velocity was stable within numerical precision across different k-grid resolutions.

For AB-stacked graphene, inclusion of the interlayer coupling $\gamma_1 = 0.39$ eV modifies the bands structure to the expected four-band form seen in figure 3. The degeneracy of the monolayer bands is lifted, and the low-energy dispersion near K becomes approximately quadratic, consistent with the effective Hamiltonian of Eq. 17. These results confirm that both intralayer and interlayer hopping terms are correctly implemented.

Convergence with respect to k-grid resolution was verified by increasing the grid density from $N = 800$ to $N = 1200$. The extracted Fermi velocity varied by less than 1%, and showed stability for values above $N = 1000$, demonstrating numerical convergence.

B. Moiré Geometry in Twisted Bilayer Graphene

Commensurate twisted bilayer graphene (TBG) supercells were constructed for twist angles in the range $2^\circ \leq \theta \leq 6^\circ$. As θ decreases the moiré period increases as $L_M \sim 1/\theta$, leading to rapid growth in supercell size and computational cost. This growth requires sparse matrix methods and shift-invert eigensolvers for efficient diagonalisation. The generated structures (figure 4) exhibit clear spatial modulation between locally AA-, AB- and BA-stacked regions. At smaller twist angles, these stack-



FIG. 3. Low-energy band structure of Bernal (AB) stacked bilayer graphene when sliced along $q_y = 0$. The four-band bilayer structure exhibits an approximately quadratic dispersion near charge neutrality touching perfectly at 0.0 eV. Two other bands are separated away from 0 eV by $\gamma_1 = 0.39$ eV.



FIG. 4. Real-space moiré supercell for twisted bilayer graphene at $\theta = 2.30°$, superlattice constant $L_M \approx 6.13$ nm. The enlarged periodicity and AA/AB/BA stacking regions emerge from the relative layer rotation.

ing domains become more well-defined, reflecting the increasing moiré wavelength.

C. Evolution of Band Structure with Twist Angle

The band structure of twisted bilayer graphene was computed along high-symmetry paths of the moiré Brillouin zone for multiple twist angles. Representative results are shown in figure 5.

For larger twist angles (e.g., $\theta \approx 6°$), the low-energy bands resemble weakly hybridised Dirac cones, with only modest interlayer coupling effects. As the twist angle decreases, several key features emerge: formation of minibands due to Brillouin zone folding; strong hybridisation near charge neutrality, leading to band repulsion; progressive flattening of the lowest-energy minibands.



FIG. 5. Evolution of the low-energy band structure along $\Gamma - K - M - \Gamma$ in the moiré Brillouin zone for decreasing twist angles. The progressive reduction in dispersion illustrates enhanced interlayer hybridisation as θ decreases. The horizontal axis is normalised to the total Γ–K–M–Γ path length to enable direct comparison between twist angles.

At the smallest angle studied ($\theta \approx 2.3°$), the two bands closest to charge neutrality exhibit significantly reduced dispersion compared to larger angles. Quantitatively, the energy variation of the lowest minibands decreases from approximately 0.11 eV at $\theta \approx 6°$ to below 0.02 eV at $\theta \approx 2.3°$, representing more than a fivefold reduction in bandwidth. This flattening reflects enhanced interlayer coupling between momentum states separated by the reduced moiré reciprocal vectors.

D. Bandwidth Suppression

To quantify the observed flattening, the bandwidth W of the two minibands closest to charge neutrality was extracted as a function of twist angle. The resulting dependence is shown in figure 6. The bandwidth was defined as

$$W = E_{max} - E_{min} \tag{30}$$



FIG. 6. Bandwidth of the two minibands closest to charge neutrality as a function of twist angle. Black crosses represent the values of band width at specific value of theta. A power-law was applied to data to show quadratic relationship between W and θ. The systematic reduction in bandwidth indicates enhanced interlayer hybridisation at smaller θ.



FIG. 7. Density of states near charge neutrality computed using Gaussian broadening ($\eta = 0.008$ eV) and $Nk = 17$ k-points. The DOS is normalised per supercell state. As θ decreases from 6.01° to 2.28°, the peak height increases by approximately a factor of 3, consistent with miniband flattening.

evaluated for the two minibands nearest charge neutrality along the full $\Gamma - K - M - \Gamma$ path.

The bandwidth decreases with decreasing twist angle. Over the investigated range, $\theta = 6°$ to $\theta = 2°$, the bandwidth decreases by roughly an order of magnitude. The strongest suppression occurs below $\theta \approx 3°$, where the rate of reduction becomes more pronounced. This trend reflects the increasing strength of interlayer hybridisation as the moiré reciprocal lattice vectors shrink, allowing stronger coupling between states near the displaced Dirac cones.

To examine the scaling behaviour, the bandwidth data were fitted to a simple power-law $W \propto \theta^{\alpha}$. A log-log fit gives a value $\alpha = 1.39 \pm 0.31$. Over the investigated range, the numerical results are consistent with a sub-quadratic dependence $\alpha \approx 1.4$, indicating that bandwidth suppression accelerates at smaller angles. The reduction in bandwidth can be understood from the momentum-space separation of the rotated Dirac cones. The relative displacement scales as $\Delta K = 2K sin(\theta/2) \approx K\theta$ for small θ. In monolayer graphene, the characteristic energy scale near neutrality is $\hbar v_F \Delta K$, while the interlayer coupling provides a competing scale set by $t_\perp$. As θ decreases, ΔK shrinks linearly, enhancing the ratio $t_\perp/(\hbar v_F \Delta K)$ and therefore strengthening hybridisation between the two cones. The observed sub-quadratic scaling indicates that the system lies in an intermediate regime where hybridisation increases rapidly but has not yet reached the magic-angle limit predicted by continuum theory [4].

Although the twist angles studied here remain above the first magic angle ($\theta \approx 1.1°$), the clear suppression of bandwidth is already evident. This demonstrates that band flattening emerges naturally within a fully microscopic tight-binding description without invoking the continuum approximation.

E. Density of States

The density of states (DOS) was computed using the Gaussian broadening of the eigenvalue spectrum in Eq. 29. The DOS near charge neutrality for several twist angles is shown in figure 7. The peak height near zero energy increases by approximately a factor of three between $\theta \approx 6°$ and $\theta \approx 2.3°$, consistent with the inverse relationship between density of states and band velocity.

The robustness of the density of states features were verified with respect to numerical parameters. Increasing the k-mesh density from $N_k = 17$ to $N_k = 21$ modified the peak height near charge neutrality by less than 5%, while leaving its energy position unchanged within 0.002 eV. Varying the Gaussian broadening parameter in the range $\eta = 0.0006 - 0.012$ eV altered the apparent sharpness of the peaks but did not shift their locations or modify the overall trend of DOS enhancement with decreasing twist angle. These tests confirm that the observed increase in low-energy spectral weight reflects genuine miniband flattening rather than numerical smoothing effects.

V. Discussion

A. Band Flattening Mechanism

The systematic reduction in bandwidth with decreasing twist angles reflects the geometric contraction of the moiré Brillouin zone and the associated enhancement of interlayer hybridisation. As the two Dirac cones become separated by a momentum offset $\Delta K \propto \theta$, the characteristic monolayer energy scale $\hbar v_F \Delta K$ decreases linearly with twist angle, while the interlayer hopping amplitude remains fixed. The increasing ratio $t_\perp/(\hbar v_F \Delta K)$ therefore strengthens hybridisation between the cones, producing miniband formation and progressive band flatten-

ing.

The extracted sub-quadratic scaling exponent $\alpha \approx 1.4$ indicates that the system lies in an intermediate regime where hybridisation grows rapidly but the true magic-angle limit has not yet been reached. The present calculations thus capture the onset of flat-band physics directly from microscopic interlayer coupling, without invoking continuum approximations or parameter fine-tuning.

B. Density of States Enhancement

The enhanced density of states near charge neutrality follows directly from the suppression of band velocity. In two dimensions, the density of states near a Dirac point scales as $D(E) \propto E/v_F^2$. A reduction in effective velocity therefore increases the low-energy spectral weight, consistent with the observed growth in the zero-energy peak as θ decreases. The numerical robustness tests confirm that this enhancement is intrinsic to miniband formation rather than an artefact of broadening or sampling resolution.

Although electron-electron interactions are not included here, the increase in low-energy density of states provides the single-particle foundation for the correlated phenomena observed experimentally in small-angle twisted bilayers.

C. Comparison with Continuum Models

Continuum models, such as the Bistritzer-MacDonald theory [4], describe small-angle twisted bilayers using long-wavelength interlayer coupling between rotated Dirac cones. The present atomistic tight-binding framework reproduces the same qualitative phenomena - miniband formation and bandwidth suppression - demonstrating that continuum descriptions emerge naturally from the underlying lattice-scale physics. This agreement reinforces the microscopic origin of flat-band behaviour as a direct consequence of geometric rotation and interlayer hopping.

D. Limitations

Several approximations constrain the quantitative regime of validity. Only nearest-neighbour intralayer hopping was included, lattice relaxation effects were neglected, and twist angles did not approach the true magic-angle regime. In practice, lattice relaxation is known to enhance AB/BA domain formation at very small angles, further modifying flat-band structure. Incorporating structural relaxation or longer-rage hopping terms would provide a more complete description of the strongly correlated regime.

VI. Conclusion

The electronic structure of monolayer, Bernal-stacked bilayer, and twisted bilayer graphene has been studied within a unified tight-binding framework. The monolayer and AB bilayer results reproduce the expected linear and quadratic dispersions, validating the model.

For the twisted bilayer graphene, decreasing twist angle leads to miniband formation, suppression of the low-energy bandwidth near charge neutrality. These results demonstrate that flat-band formation is not an artefact of continuum approximations, but emerges directly from microscopic interlayer hopping within a fully atomistic tight-binding description.

Overall, the calculations show how geometric rotation alone can strongly reconstruct the electronic spectrum of bilayer graphene.

[1] A. H. Castro Neto, F. Guinea, N. M. R. Peres, K. S. Novoselov, and A.K. Geim. The electronic properties of graphene. *Rev. Mod. Phys.*, 81, 2009. doi:https://doi.org/10.1103/RevModPhys.81.109.

[2] E. McCann and V.I. Fal'ko. Landau-level degeneracy and quantum hall effect in a graphite bilayer. *Phys. Rev. Lett*, 96, 2006. doi:https://doi.org/10.1103/PhysRevLett.96.086805.

[3] G. Trambly de Laissardièr, D. Mayou, and L. Magaud. Localization of dirac electrons in rotated graphene bilayers. *Nano Lett.*, 2010.

[4] R. Bistritzer and A. H. MacDonald. Moiré bands in twisted double-layer graphene. *Proc. Natl. Acad. Sci*, 108, 2011. doi:https://doi.org/10.1073/pnas.1108174108.

[5] P. R. Wallace. The band theory of graphite. *Phys. Rev.*, 71, 1947. doi:https://doi.org/10.1103/PhysRev.71.622.

[6] J. L. Bentley. Multidimensional binary search trees used for associative searching. *Commun. ACM*, 1975. doi: https://doi.org/10.1145/361002.3610.

[7] P. Virtanen et al. Scipy 1.0: fundamental algorithms for scientific computing in python. *Nature*, 2020. doi: https://doi.org/10.1038/s41592-019-0686-2.

[8] R. M. Martin. *Electronic Structure, Basic Theory and Practical Methods.* Cambridge University Press, 2004.