Ercole® Ecoactive

PHOTOCATALYTIC CEMENTITIOUS OVERLAY

FOR PROFESSIONAL USE ONLY - REVISION DATE 18th OCTOBER 18

Ercole® Ecoactive is a photocatalytic cementitious coating, that can be applied even at very low thickness and activates a chemical reaction which causes the decomposition of pollutants, making them harmless.
Ercole® Ecoactive ensures over 60% of pollution reduction and it is certified by Italcementi.
Ercole® Ecoactive is ready for use, you need just to add water it is designed for low thinkness coacting on concrete, plaster, wood, asphalt and other surfaces.
Ercole® Ecoactive contains the Tx principle of Italcementi, that accelerates the decomposition of pollutants, and a selection of special additives, ensuring an excellent adhesion on the surface on which it is applied.

Features

- Ready to use, mix with water
- For indoor and outdoor applications
- High versatility
- Easy application
- Application from 1 to 3 mm thickness
- Excellent adhesion on the surface
- Wear resistance
- Weatherproof
- High freeze-thaw cycles resistance
- De-icing salt resistance
- Waterproof
- No toxic, eco-friendly and safe
- It reduces NO_x, fine particulate matter and smog emissions
- It reduces the pollution of over 60%
- it is a photocatalysis activator
- It makes clean and healthy air

Uses

Ercole® Ecoactive can be used in:

- Schools, nursery schools, universities, youth centres
- Town halls, public buildings
- Medical structures, hospitals, nursing homes
- Cycle tracks
- Pedestrian crossings, footpaths
- Commercial buildings
- Residential buildings
- Roads, squares, parking spaces
- Pedestrian and vehicular areas
- Industrial zones, storages, industrial waehouses

Properties

Properties	Results
Tensile strenght	5,4 MPa after 7 days 11 MPa after 28 days
Adhesion on concrete after freeze and thaw cycles	4,3 MPa class R3 > 2 MPa
Compressive strenght	31,1 MPa after 7 days class R3 > 25 MPa 46,4 MPa after 28 days class R3 > 25 MPa

Application

Ercole® Ecoactive can be applied with a squeegee, spray machine, float, trowel or similar systems.

The low thickness cementitous overlays need mild temperature and, if possible, unifrom sunlight in order to complete the curing. The product must be applied only where surface temperature is above 5 °C and air temperature above 10 °C. Do not apply if temperature is above 40 °C. Do not apply if precipitations are foreseen in the following 24 hours.

Product mixing:

Ercole® Ecoactive is ready to use, just by adding water (3-4 litres for a dry mixture, 4-6 litres of the self-leveling mixture) and mixing with a mixing drill in the bucket until you get the desidered consistency, trying to avoid air bubbles during mixing. Self leveling mixture is the most common application for 1 to 3 mm thickness overlays.

Application:

The surface must be dampened before the application. For low thickness coatings use the self levelling mixture with a squeegee. It can be sandpapered both between coats and after the final application (on dry surface), using a single-brush machine with sandpaper or a polishing machine. The final surface should appear uniform in texture and appearance.

ecoBETON

Coverage rate

Coverage rate may vary. These are approximations, the actual coverage depend on the substrate conditions and surface porosity.

Coverage rate	1,5 kg/m^2 on smooth/not damaged surfaces, considering two coats application.
Curing	Light foot traffic is allowed after 72 hours in normal conditions of temperature and humidity. Complete curing will be achieved in 28 days.
Expiry date	6 months if stored in a dry place
Packages	25 kg pails - 33 pails per pallet

Warnings

Ecobeton products can be applied when surface temperature is above 5 °C and air temperature between 10 and 40 °C. Do not expose the material to frost.

Do not apply **Ercole® Ecoactive** with temperature lower than 10 °C. Do not apply if rainfall is forecasyed in the following 24 hours.

Note:
These informations are true to the best of our knowledge. The products are of highest quality and uniform within manufacturing tolerances. Since no control is exercised over products use, no earranty, expressed or implied is made as to the effect of such use and no liability is assumed directly or indirectly from their use. Buyers and users are encouraged to conduct their own test prior to application.

Visit our webiste:
www.ecobeton.com
or write us:
europe@ecobeton.it

Ecobeton Italy s.r.l. unipersonal is a company certified with ISO 14001 environmental management system.

ecobeton

Ecobeton Europe
via G.Galilei, 47
36030 Costabissara (VI) Italy

T (+39) 0444 971893
E europe@ecobeton.lit
I www.ecobeton.com