TEST REPORT - BOX COMPRESSION & BURST

Supplier: Hosur Corrutech Pvt Ltd
Report date: 22 September 2026
3-ply 18BF: Burst 7.4 kg/cm2, BCT 290 kgf (400x280x220)
5-ply 18BF: Burst 12.8 kg/cm2, BCT 610 kgf (400x300x300)
7-ply 18BF: Burst 17.1 kg/cm2, BCT 980 kgf (600x400x400)
Result: PASS against customer spec