

Fit Quality Screening of Biochar for Phosphorus Capture

Bee Rosa Davis

Research note for scientific discussion
5 October 2026

A reproducible secondary analysis using GIGI

Abstract

Selecting biochars for phosphorus capture requires distinguishing a large fitted capacity from a well-supported estimate and from measured performance in runoff. This note reanalyzes 36 published formulation-level Langmuir summaries from a poultry-litter biochar experiment. Capacity estimates, reported standard errors, fit quality and net-release labels were retained in a queryable GIGI dataset. Applying the descriptive screen $R^2 > 0.80$ retained 16 formulations, excluded eight numeric fits and preserved 12 net-release entries without assigning them zero capacity. All nine formulations prepared using 1 M magnesium activation passed this screen; none of the nine untreated formulations did. The largest retained point estimate was 10.35 ± 1.45 mg P/g biochar, whereas the largest unscreened estimate was 134.41 ± 133.98 mg P/g with $R^2 = 0.00$. Here, $\pm$ denotes the source-reported standard error. Tightening the screen to $R^2 > 0.90$ changed the highest-ranked formulation. The resulting shortlist is therefore conditional on model screening and does not identify a statistically established optimum. The contribution is a transparent and verified data workflow, not new sorption experiments or proof of reduced field runoff. A proposed follow-up protocol links material screening to P mass balances, breakthrough and release testing. The archived workbook additionally contributes 540 measured isotherm pairs, including 171 negative sorption values; all were preserved and independently checked after import. These observations support descriptive release screening but do not constitute independent field trials.

1 Research question and scope

The practical question is which biochar formulations warrant additional testing for phosphorus capture. An appropriate workflow must retain evidence of weak fits and phosphorus release, rather than report only a ranked list of capacities. It must also preserve the distinction between a model parameter and a directly measured environmental outcome.

The sources are Table 1 of Padilla et al. [1] and the accompanying Dryad isotherm worksheet [2], covering three poultry-litter feedstock age categories, four magnesium activation concentrations and three pyrolysis temperatures. Each of the 36 rows in the expanded table represents a formulation-level summary, not an independent experimental replicate. A separate dataset preserves 540 measured concentration–sorption pairs. The present note analyzes both layers descriptively. It does not reproduce the authors’ inferential analysis or claim new evidence for a sorption mechanism.

Three questions are addressed: which reported capacity estimates survive a declared fit-quality screen; how sensitive the shortlist is to that screen; and how GIGI can preserve and query the evidence needed

for a subsequent laboratory program. Crop-uptake outcomes from the earlier exploratory work are outside this note because they do not measure P removal from water.

2 What a fiber bundle database means

2.1 A sample tray with a measurement card at every position

Imagine a laboratory sample tray. Each occupied position has a permanent label, such as formulation 24. Above that position is a measurement card with spaces for the recipe, capacity estimate, standard error, fit quality and source reference. The tray’s labeled positions answer *which formulation?*; the card answers *what is recorded about it?*

In the fiber-bundle analogy, the labeled positions form the **base space**. The collection of possible measurements and attributes attached to one position is its **fiber**. The collection of positions together with their attached fibers is the **bundle**. A stored record supplies the actual values on a card. Using the same card layout across the tray makes it possible to retrieve, filter and compare records consistently.

The distinction between possible and observed values matters. A blank capacity box still exists on an NR record’s card; it has not become a measurement of zero. Similarly, a formulation’s unique label identifies its record but does not tell us how chemically similar it is to another formulation. Formulation 24 is not physically “closer” to formulation 25 merely because their identifiers are consecutive.

Analogy	This dataset
Labeled tray position	Base key: formulation ID 24
Measurement card	Fiber fields: PL3, 1 M Mg, 900 °C, capacity, SE, R^2 , provenance
Completed card	Observed values: 10.35, 1.45 and 0.90, with units and field meanings
Whole tray	The named bundle containing all 36 formulation records

2.2 Where geometry enters and what the analogy leaves out

A fiber bundle is a mathematical way to organize local spaces over a base. In geometry, a section selects a value in the fiber over each base point. For this finite database, the stored records can be understood as a discrete assignment of values to indexed positions. This explanation provides intuition; the sample tray is not a claim that the experimental design has been shown to form a smooth physical manifold.

GIGI uses this organization as a basis for database operations and geometric analyses [3]. For example, a collection of numeric measurement cards can be studied for neighborhood structure or unusual records when the selected representation and distance rule are appropriate. Those comparisons require scientific choices: units, scaling, categorical encoding, missingness and which fields should enter a distance. A difference of one in temperature, capacity and R^2 does not carry the same meaning. The database cannot make that experimental judgment merely from a field name.

In this note, the base key is the unique formulation identifier; recipe, measurement and provenance fields live with that key. We use GIGI to preserve complete cards and to ask an explicit question: retain records whose reported R^2 exceeds the chosen threshold, then rank their capacities. Conventional databases or analysis scripts can perform the same screening. No advantage of geometric learning is inferred here, and GIGI’s geometric metadata are not substitutes for the experiment’s SE, model diagnostic or runoff validation.




Figure 1: Conceptual drawing of the fiber-bundle organization used here. Three records illustrate the base-fiber distinction; the full bundle contains 36. The connecting lines show attachment, not causal relationships or a measured geometric distance.

3 Data and analytical methods

3.1 Source and measurement context

Published capacity estimates, standard errors (SE), R^2 values and NR labels were extracted with source-cell identifiers. The table defines NR as net P release. These entries were stored as null capacity, SE and R^2 , not as zero. Feedstock codes PL1, PL3 and PL7 identify litter aged 1, 3–5 and 7–9 years, respectively. Magnesium activation concentration refers to the preparation solution, not the final Mg content of the biochar.

The source batch tests used 0.1 g biochar in 20 mL solution, initial P of 25–150 mg/L, 10 mM KCl, initial pH around 5 and 24 h equilibration at 21 °C; experiments were conducted in triplicate [1]. These conditions constrain transfer to runoff water. After an initial direct-download failure, the public Dryad workbook [2] was supplied as the 10 October 2023 archive. Its unchanged bytes and README are preserved with SHA-256 digests. The worksheet **Figure 5 and Sup. Fig. S5** supplies 540 paired solution-concentration and sorbed-P values: 15 points for each of the 36 formulations. These measured pairs are analyzed descriptively in addition to the published fit summaries; they are not used here to refit the Langmuir parameters.

Each pair retains its sheet name and Excel cell coordinates. Point indices preserve sheet order; no experimental-unit identity, initial concentration, or replicate assignment is inferred solely from position. Negative sorbed-P values are retained as net release. The 540 rows pool multiple concentration conditions and within-condition measurements and must not be treated as 540 independent manufacturing batches. The workbook’s notes refer to a nonexistent **Figure 4 and Sup. Fig. S5** tab; the actual isotherm tab was identified by its headers. Two other sheets use PL9 labels where the paper’s age category is PL7. Those sheets are archived but not merged into the isotherm analysis or silently relabeled.

3.2 Descriptive screening and ranking

For a formulation i , inclusion in the primary numerical shortlist was defined as

$$I_i = \mathbf{1}\{P_{\max,i} \text{ is reported and } R_i^2 > 0.80\}. \quad (1)$$

This follows the threshold in the source figure description. The article also describes excluding $R^2 < 0.80$ elsewhere. No displayed value equals 0.80, so that wording difference does not change the primary result. All thresholds in this analysis are explicitly strict and operate on the published values rounded to two decimal places.

Retained records were ordered by decreasing $P_{\max}$. Group counts use all nine formulations at each Mg concentration as their denominator. Capacity ranges describe only the retained subset. No imputation, inverse-variance pooling, new hypothesis test, confidence interval, or causal comparison between Mg levels was performed. The source-reported SE was carried with each estimate rather than converted into a nominal 95% interval without the necessary fit details.

Sensitivity analyses repeated the rule with $R^2 > 0.70$, > 0.85 , > 0.90 and > 0.95 . These are alternative descriptive screens, not independently calibrated standards for sorbent suitability. A good R^2 does not establish correct model specification, an unbiased parameter estimate, independent predictive accuracy, or field performance.

3.3 Implementation and verification

Python’s standard library extracted the attributed HTML table excerpt into JSON and CSV and computed an independent reference result. GIGI stored the formulation records and executed filtering, ranking and grouped aggregation. A complete roundtrip checked identifiers, text and nulls exactly and numeric fields within 10^{-12} relative or absolute tolerance. Returned rankings at all five thresholds and the grouped counts and means were compared with the independent reference.

A synthetic check planted a capacity of 9999 with $R^2 = 0.01$ and a capacity of 5 with $R^2 = 0.95$. The screened query had to select the latter. Removing the fit condition had to select the former, demonstrating that the verification distinguishes the screening mechanism from capacity-only ranking. Synthetic records occupy a separate bundle. The repository includes deterministic offline tests and exact live HTTP receipts.

GIGI’s geometric confidence metadata were not used as statistical uncertainty. No spectral clustering, manifold prediction or performance comparison against conventional statistical software was undertaken. The demonstrated contribution is reproducible evidence handling with the measurements and their qualifications co-located.

4 Results

4.1 Primary screen

Of the 36 formulations, 24 had numeric capacity estimates and 12 carried NR labels. Sixteen numeric estimates satisfied Equation 1; eight did not. Table 1 shows that the 1 M group contains nine retained estimates, while the untreated group contains seven NR entries and two excluded numeric fits. This does not mean that all untreated materials have exactly zero uptake under every condition. The table does not quantify their release, and an excluded model may summarize a condition-dependent response poorly.

Table 1: Primary screening outcomes by activation concentration. Ranges summarize retained estimates only and are not uncertainty intervals. Each formulation is counted once.

Mg (M)	Total	Retained	Excluded	NR	Range (mg P/g)
0	9	0	2	7	–
0.25	9	3	3	3	0.62–4.10
0.5	9	4	3	2	1.67–5.33
1	9	9	0	0	2.60–10.35

The highest retained point estimate was PL3 at 1 M Mg and 900 °C: 10.35 ± 1.45 mg P/g, with $R^2 = 0.90$. In comparison, PL1 at 1 M and 500 °C was 8.55 ± 0.97 mg P/g, with $R^2 = 0.94$. Figure 2 displays all retained estimates with their reported SE. Neither the ordering of point estimates nor visual overlap of SE bars is a formal pairwise test. Unknown dependence between fitted estimates prevents treating these bars as independent experimental-batch uncertainty.

The unscreened maximum, PL7 at 0.5 M and 500 °C, was 134.41 ± 133.98 mg P/g with $R^2 = 0.00$. Its SE is approximately as large as the estimate itself. The screening workflow excludes this value from the numerical shortlist but keeps it in the source inventory. This illustrates a failure of capacity-only ranking without implying that a fit threshold alone validates the remaining models.

4.2 Threshold sensitivity

Tightening the strict threshold changes both the set of retained formulations and the largest retained point estimate (Table 2). At $R^2 > 0.90$, the PL3/1 M/900 °C formulation is excluded because its displayed R^2 equals 0.90. PL1/1 M/500 °C becomes the highest-ranked retained formulation. At $R^2 > 0.95$, PL1/1 M/700 °C leads. These changes show that a unique recipe recommendation would depend on an analyst-selected cutoff and on the precision of the published fit diagnostic.

The concentration-level result is more stable across the first three thresholds: all nine 1 M formulations remain eligible at 0.70, 0.80 and 0.85. Seven remain at 0.90 and four at 0.95. This supports prioritizing multiple 1 M formulations for further comparison within this dataset, while retaining lower-activation candidates when testing chemical-use and performance tradeoffs. Costs and manufacturing energy were not measured here.

Table 2: Sensitivity to a strict R^2 cutoff. Every leading recipe uses 1 M Mg. Capacities are point estimates $\pm$ published SE. Equality with the cutoff is excluded.

Cutoff	Retained	At 1 M	Leading feedstock, °C	Capacity (mg P/g)
0.70	17	9	PL3, 900	10.35 ± 1.45
0.80	16	9	PL3, 900	10.35 ± 1.45
0.85	14	9	PL3, 900	10.35 ± 1.45
0.90	12	7	PL1, 500	8.55 ± 0.97
0.95	5	4	PL1, 700	7.41 ± 0.23

4.3 Descriptive analysis of the underlying isotherm measurements

The supplied workbook contains 540 paired observations across the same 36 formulations. Of these, 171 have negative sorbed-P values. Grouped descriptively by activation concentration, the counts are 93/135




Figure 2: All 16 estimates retained at $R^2 > 0.80$, ranked by point estimate. Horizontal bars are the *published standard errors*, not 95% confidence intervals and not field-performance ranges. Values are replotted from Table 1 of Padilla et al. [1]. The leading estimate is not a statistically established winner.

at 0 M, 52/135 at 0.25 M, 26/135 at 0.5 M and 0/135 at 1 M. Every recorded 1 M point in this sheet is positive, ranging from 1.47 to 13.47 mg P/g. These denominators count observations over different concentrations and materials, not independent studies. They do not estimate the probability of success in runoff or establish a causal dose response.

Figure 3 preserves the signed measurements and their solution-concentration coordinates. A formulation can show uptake at some conditions and release at others, so the sign of an individual observation and a formulation-level NR label answer different questions. The numerical values were loaded into a separate GIGI bundle, fully checked against the source-derived reference, and queried for negative sorption; all 171 returned records matched. No summary fit was replaced by an ad hoc fit to these points.

5 Interpretation and limitations

5.1 Saturation capacity is not removal at a target concentration

A fitted maximum does not determine uptake at a specific water concentration. In the Langmuir form,

$$q(C_e) = \frac{P_{\max} K C_e}{1 + K C_e}, \quad (2)$$

the affinity parameter K is required along with $P_{\max}$. The analyzed table does not supply K . Consequently, it cannot support predicting effluent quality or sizing a treatment unit for a specified dilute influent. Extrapolation from 24-hour batch tests to short-contact runoff treatment also requires kinetic and transport evidence. Fitting a linearized isotherm changes the error structure relative to fitting the original concentration-response relationship; residual diagnostics and alternative fits cannot be checked from these summaries.

5.2 Sampling and uncertainty

These 36 formulations belong to one experiment and do not represent 36 independent studies or manufacturing batches. Feedstock age labels are also material identities; they do not isolate an age effect from all other feedstock differences. Source-reported parameter SE does not quantify scale-up variation, seasonal water chemistry, aging, or field-to-field variation. No claim of a general optimum, a causal Mg dose response, or a reduction in agricultural P export follows from this analysis.

Conditioning on a fit screen changes the composition of each activation subset. Comparing retained means without accounting for that selection could overstate a material advantage. NR and excluded fits therefore remain visible in the denominators and full inventory. Low R^2 can identify an unreliable capacity estimate without identifying the physical reason for the poor fit.

5.3 Source fidelity

The table reports PL7/0.25 M/900 °C as 0.62 ± 0.06 mg P/g with $R^2 = 0.96$, whereas the article narrative reports a minimum of 0.66 mg P/g. The tabulated value was retained without correction and is flagged for author or model-reconstruction verification. All 36 formulation summaries are provided in Appendix A. Access to the workbook resolves the earlier download limitation, but descriptive extraction alone does not resolve this table/text discrepancy or reproduce the original model fitting. Formal comparisons require a reviewed error model and experimental-unit mapping.




Figure 3: All 540 archived isotherm observations, separated by Mg activation concentration, with common axes. Points pool three feedstocks and three temperatures within each panel (135 points). Negative values indicate net release; the dashed line denotes zero. No curve fitting, smoothing, inferred replicate identities, or independence assumption is used. Coincident points may overlap. Source: Dryad isotherm worksheet [2].

6 A proposed validation study for runoff applications

The next experiment should ask whether candidate materials remove P from the target water at realistic contact times and retain it through subsequent exposure. This is a proposed protocol, not an experiment performed in the present work.




Figure 4: Proposed upflow-column experiment linking material screening to P-load measurements. Schematic only, not to scale and not a description of apparatus used in the source study. Column dimensions, bed length L , flow, material mass and sampling schedule must be selected and recorded for the target application. The drawing specifies measurement locations, not an engineered treatment-unit design.

Candidate and control selection. Include several retained 1 M formulations spanning production temperatures, a lower-activation candidate, unmodified biochar and a no-biochar control. Use independently prepared biochar batches as experimental units where manufacturing reproducibility is the question. Randomize units and choose replication from a pilot estimate of variance and a stated minimum useful effect; the current fit SE should not be substituted for that variance.

Mass balance and release. Measure dissolved reactive P and total P, water volume or flow, initial and final pH, background ions, dissolved organic carbon and relevant material-derived constituents. Include no-added-P leaching controls. For a closed batch with consistent volumes, apparent net removal per unit biochar is

$$q_{\text{net}} = \frac{(C_0 - C_t)V}{m}. \quad (3)$$

Here, C is in mg P/L, V in L and m in g. This is an apparent aqueous mass difference; a no-biochar blank and volume accounting are needed to distinguish material-associated removal from other losses. Subsequent clean-water exposures should test desorption or release rather than assuming that initial removal is permanent.

Flow and repeated events. A column or rainfall experiment should retain separate inlet and outlet flow measurements and calculate

$$M_{\text{retained}} = \int Q_{\text{in}}(t)C_{\text{in}}(t) dt - \int Q_{\text{out}}(t)C_{\text{out}}(t) dt. \quad (4)$$

Sampling removals, storage changes and solid-phase P need accounting when interpreting this balance. Concentration reduction alone is not equivalent to reduced P export when flow differs. Follow repeated

events to identify breakthrough, clogging, aging and remobilization. For particulate P, distinguish physical particle retention from dissolved-phosphate sorption.

GIGI data structure. A follow-up dataset should identify site, event, experimental unit, batch, material, control, sample time, assay method, detection limit, concentration, flow and units. Store below-detection results with qualifiers rather than silently replacing them with zero. Keep calibration and blank records traceable. These records would support event-level mass balances, batch comparisons and future models validated on entirely held-out batches or sites.

7 Conclusion

Keeping fit diagnostics and missing-result labels alongside capacity estimates materially changes a biochar shortlist. In this published dataset, the primary screen retains 16 of 36 formulations and all nine 1 M formulations, while sensitivity analysis changes the highest-ranked recipe. GIGI reproduced the filtering, ranking and aggregation against independent checks. The result is a transparent starting point for targeted experiments. Demonstrating reduced runoff requires measurements of P loads, contact-time performance and subsequent release under the intended application conditions.

Data and code availability

The accompanying repository, <https://github.com/nurdymuny/gigi-biochar>, contains an attributed source-table excerpt, unchanged source workbooks, SHA-256 provenance records, normalized data in JSON and CSV, deterministic analysis, automated tests, exact live GIGI receipts and this standalone LaTeX manuscript. The separate Wang dataset and contact-time analysis are documented in Appendix B. Technical drawings and plotted data are embedded as vector LaTeX graphics. The engine is obtained separately from its upstream repository [3]; this analysis does not redistribute or relicense it. Published source data retain their original attribution and reuse terms.

Preparation and authorship

Original text and figures: copyright © 2026 Bee Rosa Davis, licensed under CC BY-NC 4.0. Analysis code is licensed separately under PolyForm Noncommercial 1.0.0. Third-party source data retain their original terms.

This research note was prepared by Bee Rosa Davis with AI assistance for scientific discussion. No new laboratory work was conducted. Affiliation, funding and competing-interest declarations remain to be supplied and verified before journal submission. The computational checks do not replace scientific review of the source data and interpretation.

References

- [1] Padilla JT, Watts DW, Novak JM, Cerven V, Ippolito JA, Szogi AA, Johnson MG. Magnesium activation affects the properties and phosphate sorption capacity of poultry litter biochar. *Biochar*. 2023;5:64. doi:10.1007/s42773-023-00263-5. Table 1 and experimental methods.
- [2] Padilla J, Watts DW, Novak JM, et al. Digital research data from: Magnesium activation affects the properties and phosphate sorption capacity of poultry litter biochar. Dryad; version 10 October

2023. doi:10.5061/dryad.pc866t1w7. Isotherm worksheet analyzed descriptively; source files preserved unchanged.

- [3] GIGI source repository. <https://github.com/nurdymuny/gigi>. Accessed 5 October 2026. Engine distributed separately under its stated license; live execution evidence is supplied with the analysis repository.
- [4] Wang P. Dataset of a comparative study on phosphate removal from water using *Phragmites australis* biochars loaded with different metal oxides. Dryad; version 22 April 2021. doi:10.5061/dryad.3xsj3txf4. Kinetic means and SD analyzed separately in Appendix B.

A Complete formulation inventory

Values below reproduce the source table after expansion to one formulation per row. Mg is activation solution concentration (M); temperature is in °C; capacity is mg P/g biochar $\pm$ reported SE. “Retained” means $R^2 > 0.80$. NR preserves the source label and does not quantify a release rate. PL1, PL3 and PL7 denote litter age categories of 1, 3–5 and 7–9 years.

Table 3: All published formulation summaries and the derived primary screening status.

ID	Feedstock	Mg	Temp.	Capacity $\pm$ SE	R^2	Status
1	PL1	0	500	NR	–	NR
2	PL1	0	700	NR	–	NR
3	PL1	0	900	NR	–	NR
4	PL1	0.25	500	14.52 ± 6.58	0.27	Excluded
5	PL1	0.25	700	4.10 ± 0.17	0.92	Retained
6	PL1	0.25	900	0.66 ± 0.12	0.83	Retained
7	PL1	0.5	500	NR	–	NR
8	PL1	0.5	700	2.39 ± 0.29	0.93	Retained
9	PL1	0.5	900	1.67 ± 0.22	0.91	Retained
10	PL1	1	500	8.55 ± 0.97	0.94	Retained
11	PL1	1	700	7.41 ± 0.23	1.00	Retained
12	PL1	1	900	2.60 ± 0.25	0.96	Retained
13	PL3	0	500	NR	–	NR
14	PL3	0	700	0.56 ± 0.25	0.59	Excluded
15	PL3	0	900	3.36 ± 2.12	0.25	Excluded
16	PL3	0.25	500	NR	–	NR
17	PL3	0.25	700	NR	–	NR
18	PL3	0.25	900	1.19 ± 0.31	0.67	Excluded
19	PL3	0.5	500	NR	–	NR
20	PL3	0.5	700	0.38 ± 0.11	0.60	Excluded
21	PL3	0.5	900	5.33 ± 0.60	0.94	Retained
22	PL3	1	500	6.32 ± 0.32	0.99	Retained
23	PL3	1	700	7.43 ± 0.83	0.94	Retained
24	PL3	1	900	10.35 ± 1.45	0.90	Retained
25	PL7	0	500	NR	–	NR
26	PL7	0	700	NR	–	NR
27	PL7	0	900	NR	–	NR
28	PL7	0.25	500	NR	–	NR
29	PL7	0.25	700	1.17 ± 1.03	0.01	Excluded
30	PL7	0.25	900	0.62 ± 0.06	0.96	Retained
31	PL7	0.5	500	134.41 ± 133.98	0.00	Excluded
32	PL7	0.5	700	0.95 ± 0.19	0.79	Excluded
33	PL7	0.5	900	4.25 ± 0.21	0.85	Retained
34	PL7	1	500	4.90 ± 0.61	0.92	Retained
35	PL7	1	700	2.84 ± 0.40	0.90	Retained
36	PL7	1	900	5.41 ± 1.85	0.96	Retained

B Follow-up computational experiment: contact time

This separate exploratory analysis uses Wang’s archived reed-biochar kinetic data [4]: six materials at 12 times from 0.5 to 72 h. It does not add observations to the poultry-litter study or describe a new laboratory experiment. The unchanged workbook supplies 72 means with standard deviations (SD), not individual replicates. Replicate count and covariance across time are not specified in the workbook. Original cell locations and signed values are preserved. The kinetic header reports mg/g under PO4-P; no phosphate-to-P mass conversion is applied. The accompanying isotherm sheet labels Q_e as mg/L rather than mg/g and is excluded pending unit review.

B.1 Question and method

We asked how the ordering of reported mean uptake changes with contact time. We ranked materials independently at all 12 measured times and examined illustrative uptake targets of 5, 8 and 9 mg/g. These targets were chosen after inspecting the data; they are not preregistered hypotheses, regulatory limits or field-performance criteria. For each target we found the first sampled time whose mean, and every later sampled mean, met the target. We repeated this calculation for mean minus one and two SD, giving 54 material/target/scenario combinations. We also counted strictly separated mean $\pm k$ SD bands for all 15 material pairs at each time, for $k = 1, 2$. These perturbations are descriptive sensitivity checks, not confidence bounds or hypothesis tests.

GIGI retrieved and ranked the records; independent Python calculations verified all 12 ranked selections and three inclusive target selections. A synthetic control planted early low and high values and a much larger late value: the filtered ranking had to select the early high value, while removing the time filter had to select the late value. Python computed the sampled attainment and SD sensitivity. Exact requests and responses accompany the results. No new kinetic model was fitted, no interpolation was used, and 72 h was not assumed to represent equilibrium.

Table 4: Selected kinetic means $\pm$ source SD (mg/g). SD is not SE or a confidence interval. A source SD displayed as zero is retained as reported and does not establish absence of measurement uncertainty.

Material	0.5 h	2 h	6 h	24 h	72 h
Al-BC	1.81 $\pm$ 0.30	2.86 $\pm$ 0.22	3.78 $\pm$ 0.20	6.55 $\pm$ 0.37	9.25 $\pm$ 0.01
Ca-BC	6.83 $\pm$ 0.29	7.75 $\pm$ 0.12	9.56 $\pm$ 0.04	9.79 $\pm$ 0.06	9.83 $\pm$ 0.01
Fe-BC	5.87 $\pm$ 0.45	6.49 $\pm$ 0.22	7.57 $\pm$ 0.31	8.82 $\pm$ 0.16	8.75 $\pm$ 0.02
La-BC	9.82 $\pm$ 0.04	9.87 $\pm$ 0.02	9.91 $\pm$ 0.01	9.91 $\pm$ 0.01	9.91 $\pm$ 0.02
Mg-BC	1.51 $\pm$ 0.02	7.38 $\pm$ 0.01	9.28 $\pm$ 0.00	9.86 $\pm$ 0.02	9.82 $\pm$ 0.01
BC	-0.33 $\pm$ 0.06	-0.22 $\pm$ 0.18	-0.37 $\pm$ 0.33	-0.43 $\pm$ 0.09	-0.77 $\pm$ 0.02

Table 5: Sampled attainment based on means (hours). An arrow joins the preceding sample and the first sample meeting the target with all later sampled means also meeting it. It does not bound a continuous-time crossing or establish retention between samples. Attainment at 72 h has no later observation to check persistence.

Material	5 mg/g	8 mg/g	9 mg/g
Al-BC	8 $\rightarrow$ 12	24 $\rightarrow$ 48	48 $\rightarrow$ 72
Ca-BC	First sample (0.5)	2 $\rightarrow$ 3	3 $\rightarrow$ 4
Fe-BC	First sample (0.5)	6 $\rightarrow$ 8	Not by 72
La-BC	First sample (0.5)	First sample (0.5)	First sample (0.5)
Mg-BC	1.5 $\rightarrow$ 2	2 $\rightarrow$ 3	4 $\rightarrow$ 6
BC	Not by 72	Not by 72	Not by 72

B.2 Interpretation

La-BC has the largest reported mean at every sampled time. Mg-BC moves from fifth at 30 min to second at 24 h, but Ca-BC is again higher at 48 and 72 h. Their close late means do not establish a reliable material winner: Ca-BC and Mg-BC bands overlap even at one SD at 24 and 72 h. The unmodified BC has negative means at 11 of 12 times. Negative uptake is preserved rather than set to zero. Thirty minutes is the earliest measured time, and there is no desorption phase. These data therefore motivate, but cannot replace, a controlled flow-and-flush experiment with realistic water chemistry, independent columns and full phosphorus-load accounting.




Figure 5: All 72 kinetic means and reported $\pm$ SD, with common axes and an explicit zero reference. Error bars smaller than the marker may be difficult to see. No connecting curve is fitted or interpolated. Data are from the separate Wang study [4]; the chart does not measure field performance or subsequent phosphorus release.